

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250287651

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

SHIH; Yang-Hsin et al.

SEMICONDUCTOR DEVICE AND METHOD OF MANUFACTURING THE SAME

Abstract

A semiconductor device and a method of manufacturing the same are provided. The semiconductor device includes a first type active region structure and a second type active region structure extending along a first direction. The semiconductor device also includes a first S/D contact over the first type active region structure and extending along a second direction different from the first direction. The semiconductor device further includes a backside conductive layer under the first type active region structure. In addition, the semiconductor device includes a backside interconnection structure between the backside conductive layer and the first type active region structure. The backside interconnection structure includes a first portion between the backside conductive layer and the first type active region structure, a second portion between the backside conductive layer and the second type active region structure, and a third portion connecting the first portion and the second portion.

Inventors: SHIH; Yang-Hsin (Hsinchu, TW), XIAO; You-Cheng (Hsinchu, TW), SUE; Pin-Dai (Hsinchu, TW)

Applicant: TAIWAN SEMICONDUCTOR MANUFACTURING COMPANY, LTD.
(Hsinchu, TW)

Family ID: 96166020

Appl. No.: 18/756057

Filed: June 27, 2024

Related U.S. Application Data

us-provisional-application US 63562458 20240307

Publication Classification

Int. Cl.: H01L29/06 (20060101); H01L29/423 (20060101); H01L29/66 (20060101);
H01L29/775 (20060101); H01L29/786 (20060101)

U.S. Cl.:

CPC H10D62/10 (20250101); H10D30/014 (20250101); H10D30/43 (20250101);
H10D30/6735 (20250101); H10D30/6757 (20250101); H10D62/121 (20250101)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S) [0001] This application claims the benefit of U.S. Provisional Application No. 63/562,458, filed Mar. 7, 2024, the entire disclosure of which is incorporated by reference herein.

BACKGROUND

[0002] Currently, semiconductor devices are widely used in various fields, such as cloud storage, medicine, transportation, mobile devices, etc. The current trend in some aspects of semiconductor device manufacturing focuses on providing semiconductor devices with smaller dimensions and better power efficiency. It is therefore desirable to continuously improve the structure and manufacturing of the semiconductor devices.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0003] Aspects of the embodiments of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It should be noted that, in accordance with the standard practice in the industry, various structures are not drawn to scale. In fact, the dimensions of the various structures may be arbitrarily increased or reduced for clarity of discussion.

[0004] FIG. 1A and FIG. 1B are layout diagrams of a semiconductor device, in accordance with some embodiments.

[0005] FIG. 2A, FIG. 2B, and FIG. 2C are cross-sectional views of the semiconductor device as specified by the layout diagrams in FIGS. 1A-1B, in accordance with some embodiments.

[0006] FIG. 3 is a cross-sectional view of a semiconductor device in accordance with some embodiments.

[0007] FIG. 4 is a cross-sectional view of a semiconductor device in accordance with some embodiments.

[0008] FIG. 5 is a layout diagram of a semiconductor device, in accordance with some embodiments.

[0009] FIG. 6 is a layout diagram of a semiconductor device, in accordance with some embodiments.

[0010] FIG. 7 is a layout diagram of a semiconductor device, in accordance with some embodiments.

[0011] FIG. 8 is a perspective view of a semiconductor device in accordance with some embodiments.

[0012] FIG. 9A, FIG. 9B, and FIG. 9C are cross-sectional views of the semiconductor device as shown in FIG. 8, in accordance with some embodiments.

[0013] FIG. 10 and FIG. 11 are flowcharts of a method for manufacturing a layout of a semiconductor device according to various aspects of the present disclosure.

[0014] FIG. 12 is a block diagram of a system of designing a semiconductor device, in accordance with some embodiments.

[0015] FIG. 13 is a block diagram of a semiconductor device manufacturing system, and a semiconductor device flow associated therewith, in accordance with some embodiments.

[0016] FIG. 14 is a flowchart of a method for manufacturing a semiconductor device, in accordance with some embodiments.

DETAILED DESCRIPTION

[0017] The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of elements and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

[0018] Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “over,” “upper,” “on” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

[0019] As used herein, although terms such as “first,” “second” and “third” describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms may only be used to distinguish one element, component, region, layer or section from another. Terms such as “first,” “second” and “third” when used herein do not imply a sequence or order unless clearly indicated by the context.

[0020] Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the disclosure are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in the respective testing measurements. Also, as used herein, the terms “substantially,” “approximately” and “about” generally mean within a value or range that can be contemplated by people having ordinary skill in the art. Alternatively, the terms “substantially,” “approximately” and “about” mean within an acceptable standard error of the mean when considered by one of ordinary skill in the art. People having ordinary skill in the art can understand that the acceptable standard error may vary according to different technologies. Other than in the operating/working examples, or unless otherwise expressly specified, all of the numerical ranges, amounts, values and percentages such as those for quantities of materials, durations of times, temperatures, operating conditions, ratios of amounts, and the likes thereof disclosed herein should be understood as modified in all instances by the terms “substantially,” “approximately” or “about.” Accordingly, unless indicated to the contrary, the numerical parameters set forth in the present disclosure and attached claims are approximations that can vary as desired. At the very least, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques. Ranges can be expressed herein as from one endpoint to another endpoint or between two endpoints. All ranges disclosed herein are inclusive of the endpoints, unless specified otherwise.

[0021] This present disclosure generally relates to semiconductor devices, and more particularly to

semiconductor devices with a backside interconnection structure (or a backside via). The backside interconnection structure includes fingers and a main portion connecting the fingers, enhancing the overlap area between the backside interconnection structure and a backside conductive layer (or backside power rail). This results in a decrease in resistance for transmitting power.

[0022] FIG. 1A and FIG. 1B are layout diagrams of a semiconductor device **10a** in accordance with some embodiments. FIG. 1A includes the layout patterns for specifying the backside conductive features, and FIG. 1B includes the layout patterns for specifying the front-side conductive features.

[0023] Referring to FIG. 1A, the semiconductor device **10a** includes active-region structures **102** and **104**. Each of the active-region structures **102** and **104** extends along the X direction. In some embodiments, the active-region structure **102** includes a p-type active-region structure, and the active-region structure **104** includes an n-type active-region structure. Non-limiting examples of the active-region structures **102** and **104** include fin field-effect transistor (FinFETs), nano-sheet transistors, and nano-wire transistors. In some embodiments, the active-region structure **102** is spaced apart from the active-region structure **104** by an isolation structure (not shown), such as a shallow trench isolation (STI). In some embodiments, the active-region structures **102** and **104** can be referred to as an oxide definition region (also referred to as “OD”).

[0024] The semiconductor device **10a** includes gate structures **111**, **112**, **113**, and **114**. Each of the gate structures **111** to **114** extends along the Y direction. The gate structures **111** to **114** intersect the active-region structure **102** at the channel region of a p-type transistor, and intersect the active-region structure **104** at the channel region of an n-type transistor. The gate structures **111** to **114** are disposed on a front-side of a substrate. In some embodiments, the gate structures **111** to **114** can be referred to as poly (PO) of a semiconductor device.

[0025] The semiconductor device **10a** includes contacts **121**, **122a**, **122b**, **123a**, **123b**, **124a**, **124b**, **125a**, and **125b**. Each of the contacts **121**, **122a** to **125a** and **122b** to **125b** extends along the Y direction. The contacts **121** and **122a** to **125a** intersect the active-region structure **102** at a source/drain (S/D) region of a p-type transistor. The contacts **121** and **122b** to **125b** intersect the active-region structure **104** at a source/drain region of an n-type transistor. Each of the contacts **121**, **122a** to **125a** and **122b** to **125b** are disposed on a front-side of a substrate. In some embodiments, the contacts **121**, **122a** to **125a** and **122b** to **125b** can be referred to as metal diffusion (MD) conductive features of a semiconductor device. In some embodiments, each of the contacts **121**, **122a** to **125a** and **122b** to **125b** corresponds to a source/drain contact of a semiconductor device.

[0026] The semiconductor device **10a** includes a backside interconnection structure **130**. In some embodiments, the backside interconnection structure **130** is interposed between the active regions (e.g., the active-region structures **102** and **104**) and a backside power rail (e.g., backside conductive layer **140**). In some embodiments, the backside interconnection structure **130** is electrically connected to some of the contacts **121**, **122a** to **125a** and **122b** to **125b** for transmitting a power signal. In some embodiments, the backside interconnection structure **130** can be referred to as a backside via (VB).

[0027] In some embodiments, the backside interconnection structure **130** includes a main portion **132** extending along the X direction. In some embodiments, the main portion **132** is disposed between the active-region structures **102** and **104** in a top view. In some embodiments, the main portion **132** is free from overlapping the active-region structures **102** and **104** along the Z direction. In some embodiments, the main portion **132** is disposed between two source/drain contacts (e.g., contacts **122a** and **122b**) in a top view. In some embodiments, the main portion **132** overlaps the contact **121** along the Z direction and is connected to the contact **121**.

[0028] In some embodiments, the backside interconnection structure **130** includes fingers **134a**, **134b**, **134c**, **134d**, and **134e** protruding from the main portion **132**. The fingers **134a** to **134e** are configured to be connected to a source/drain contact for transmitting a power signal. In some embodiments, each of the fingers **134a** to **134e** extends along the Y direction. The fingers **134a**,

134c, and **134d** overlap the active-region structure **102** along the Z direction. The fingers **134b** and **134e** overlap the active-region structure **104** along the Z direction. In some embodiments, the fingers **134a** and **134b** overlap the contact **121** along the Z direction and are connected to the contact **121**. The finger **134c** overlaps the contact **123a** along the Z direction and is connected to the contact **123a**. The finger **134d** overlaps the contact **125a** along the Z direction and is connected to the contact **125a**. The finger **134e** overlaps the contact **124b** along the Z direction and is connected to the contact **124b**. In some embodiments, the finger **134a** is connected to the finger **134b** through the main portion **132**. Although FIG. 1A illustrates that the backside interconnection structure **130** includes five fingers, it should be noted that the backside interconnection structure **130** can include more or fewer fingers based on the design requirements.

[0029] In some embodiments, each of the main portion **132** (or a part of the main portion **132**) and fingers **134a** to **134e** can be regarded as a sub-region of the backside interconnection structure **130**.

[0030] In some embodiments, the semiconductor device **10a** includes a backside conductive layer **140**. The backside conductive layer **140** may be disposed on a backside of a substrate. The backside conductive layer **140** may be connected to the backside interconnection structure **130**. In some embodiments, the backside conductive layer **140** can be referred to as a first backside metal (BMO). The backside conductive layer **140** may be a power rail for providing electric power to the corresponding source/drain feature that is connected to the backside interconnection structure **130**. In some embodiments, the backside conductive layer **140** at least partially overlaps the active-region structures **102** and **104** along the Z direction. In some embodiments, the backside conductive layer **140** overlaps the main portion **132** at a region between the active-region structures **102** and **104** in a top view.

[0031] Referring to FIG. 1B, the semiconductor device **10a** includes vias **152a**, **152b**, **152c**, **152d**, and **152e**. The vias **152a** and **152d** overlap the contact **121** along the Z direction and are connected to the contact **121**. The via **152b** overlaps the contact **123a** along the Z direction and is connected to the contact **123a**. The via **152c** overlaps the contact **125a** along the Z direction and is connected to the contact **125a**. The via **152e** overlaps the contact **124b** along the Z direction and is connected to the contact **124b**. In some embodiments, each of the vias **152a** to **152e** can be referred to as “VD.”

[0032] The semiconductor device **10a** includes vias **154a**, **154b**, **154c**, **154d**, **154e**, **154f**, **154g**, and **154h**. The vias **154a** and **154e** overlap the gate structure **111** along the Z direction and are connected to the gate structure **111**. The vias **154b** and **154f** overlap the gate structure **112** along the Z direction and are connected to the gate structure **112**. The vias **154c** and **154g** overlap the gate structure **113** along the Z direction and are connected to the gate structure **113**. The vias **154d** and **154h** overlap the gate structure **114** along the Z direction and are connected to the gate structure **114**. In some embodiments, the vias **154a** to **154h** can be referred to as “VG.”

[0033] The semiconductor device **10a** includes front-side conductive layers **161**, **162**, **163**, **164**, **165**, **166**, and **167**. Each of the front-side conductive layers **161** to **167** extends along the X direction. In some embodiments, the front-side conductive layers **161** to **167** may be configured for being electrically connected to the contacts **121** to **125b** and/or gate structures **111** to **114**. In some embodiments, the front-side conductive layers **161** and **167** are configured for providing a supply voltage. For example, the front-side conductive layer **161** may be connected to the contact **121** by the via **152a**, and the front-side conductive layer **167** may be connected to the contact **121** by the via **152d**. The front-side conductive layers **162** to **166** are configured for transmitting, for example, signals (e.g., input and/or out signals). In some embodiments, some of the front-side conductive layers **162** to **166** may function as dummy tracks which are not connected to the contacts **121** to **125b** and gate structures **111** to **114**. The profiles of the front-side conductive layers **162** to **166** can be modified based on the design requirements. In some embodiments, the front-side conductive layers **161** to **167** can be referred to as “M0.”

[0034] In some embodiments of the disclosure, the backside interconnection structure **130** includes

the main portion **132** connected to the fingers **134a** to **134e**. The main portion **132** is configured to enhance the overlapping area between the backside interconnection structure **130** and the backside conductive layer **140**, which results in a reduction in the resistance for transmitting power. [0035] FIG. 2A, FIG. 2B, and FIG. 2C are cross-sectional views along lines A-A', B-B', and C-C' of FIGS. 1A-1B, respectively. It should be noted that FIGS. 2A-2C merely illustrate the features shown in FIGS. 1A-1B, and some features, such as a substrate, dielectric layers, isolation structures and/or other elements, are omitted for brevity.

[0036] Referring to FIG. 2A, the contact **121** is disposed over the active-region structures **102** and **104**. The front-side conductive layer **161** is disposed over and electrically connected to the contact **121** by the via **152a**. The front-side conductive layer **167** is disposed over and electrically connected to the contact **121** by the via **152d**. The backside interconnection structure **130** is disposed between the active-region structure **102** and the backside conductive layer **140** as well as between the active-region structure **104** and the backside conductive layer **140**. The backside conductive layer **140** is disposed under the backside interconnection structure **130**. The backside conductive layer **140** is connected to the active-region structures **102** and **104** by the backside interconnection structure **130**. In some embodiments, the contact **121** includes a protruding portion **121t**. The protruding portion **121t** is disposed between the active-region structures **102** and **104**. The protruding portion **121t** protrudes toward the backside interconnection structure **130**. In some embodiments, the protruding portion **121t** includes a curved lower surface or boundary. In some embodiments, the backside interconnection structure **130** includes a protruding portion **130t**. The protruding portion **130t** is disposed between the active-region structures **102** and **104**. The protruding portion **130t** protrudes toward the contact **121**. In some embodiments, the protruding portion **130t** includes a curved upper surface or boundary. In some embodiments, the protruding portion **121t** is in contact with the protruding portion **130t** and builds an interface between the contact **121** and the backside interconnection structure **130**. The backside interconnection structure **130** has a first portion, under the active-region structure **102** (or active-region structure **104**) with a thickness $T_{sub.1}$. The backside interconnection structure **130** has a second portion, in contact with the contact **121**, with a thickness $T_{sub.2}$. In some embodiments, the thickness $T_{sub.2}$ is greater than the thickness $T_{sub.1}$. The contact **121** has a first portion, over the active-region structure **102** (or active-region structure **104**) with a thickness $T_{sub.3}$. The contact **121** has a second portion, in contact with the backside interconnection structure **130**, with a thickness $T_{sub.4}$. In some embodiments, the thickness $T_{sub.4}$ is greater than the thickness $T_{sub.3}$. In some embodiments, the protruding portion **121t** and the protruding portion **130t** are configured to add a linkage between the backside interconnection structure **130** and the contact **121**, which results in a decrease in electrical resistance.

[0037] Referring to FIG. 2B, the fingers **134a**, **134c**, and **134d** are disposed under the active-region structure **102**. The fingers **134a**, **134c**, and **134d** are connected to the backside conductive layer **140**. The fingers **134a**, **134c**, and **134d** are disposed between the active-region structure **102** and the backside conductive layer **140**. The gate structures **111** to **114** are disposed over the active-region structure **102**. The vias **154a**, **154b**, **154c**, and **154d** are disposed on and electrically connected to the gate structures **111**, **112**, **113**, and **114**, respectively. The front-side conductive layer **162** covers the gate structures **111** to **114** as well as the contacts **121** to **125a**.

[0038] Referring to FIG. 2C, the gate structure **111** is spaced apart from the backside interconnection structure **130**. The front-side conductive layers **161** to **167** are disposed over the gate structure **111**. The front-side conductive layer **162** is electrically connected to the gate structure **111** by the via **154a**. The front-side conductive layer **166** is electrically connected to the gate structure **111** by the via **154e**.

[0039] FIG. 3 is a cross-sectional view of a semiconductor device **10b** in accordance with some embodiments. The semiconductor device **10b** has a structure similar to that of the semiconductor device **10a**. One of the differences between the semiconductor devices **10b** and **10a** is that the

contact **121** includes a protruding portion **121p** protruding toward the backside interconnection structure **130**. In some embodiments, the protruding portion **121p** is disposed between the active-region structures **102** and **104**. In some embodiments, the protruding portion **121p** is in direct contact with the backside interconnection structure **130** and builds an interface therebetween. In some embodiments, the protruding portion **121p** overlaps the backside conductive layer **140** along the Z direction. In some embodiments, the protruding portion **121p** is configured to add a linkage between the backside interconnection structure **130** and the contact **121**, which results in a decrease in electrical resistance.

[0040] FIG. 4 is a cross-sectional view of a semiconductor device **10c** in accordance with some embodiments. The semiconductor device **10c** has a structure similar to that of the semiconductor device **10a**. One of the differences between the semiconductor devices **10c** and **10a** is that the backside interconnection structure **130** includes a protruding portion **130p** protruding toward the contact **121**. In some embodiments, the protruding portion **130p** is disposed between the active-region structures **102** and **104**. In some embodiments, the protruding portion **130p** is in direct contact with the contact **121** and builds an interface therebetween. In some embodiments, the protruding portion **130p** overlaps the backside conductive layer **140** along the Z direction. In some embodiments, the protruding portion **130p** is configured to add a linkage between the backside interconnection structure **130** and the contact **121**, which results in a decrease in electrical resistance. Although FIGS. 3 to FIG. 4 illustrate that the backside interconnection structure **130** and/or the contact **121** may have a protruding portion(s), it should be noted that the protruding portion(s) can be formed by an additional step which is different from a step for producing the backside interconnection structure **130** and/or the contact **121**.

[0041] FIG. 5 is a layout diagram of a semiconductor device **10d** in accordance with some embodiments. The semiconductor device **10d** has a structure similar to that of the semiconductor device **10a**. One of the differences between the semiconductor devices **10d** and **10a** is that the semiconductor devices **10d** includes a cut-poly pattern **110** and a cut-MD pattern **120**.

[0042] In some embodiments, the cut-poly pattern **110** is configured to disconnect the gate structures **111** to **114** to avoid leakage. The cut-poly pattern **110** may define a gap of the gate structure **111** (or **112** to **114**). Dielectric material(s) may fill the cut-poly pattern **110**. In some embodiments, the cut-poly pattern **110** is disposed between the active-region structures **102** and **104** in a top view. In some embodiments, the cut-poly pattern **110** overlaps the main portion **132** of the backside interconnection structure **130** along the Z direction. In some embodiments, the cut-poly pattern **110** can be referred to as a poly cut layer “CPO.”

[0043] In FIG. 5, the cut-MD pattern **120** includes portions **120_1**, **120_2** and **120_3**. The portion **120_1** overlaps the contact **122a**, **122b**, and **123b** along the Z direction. The portion **120_2** overlaps the contact **124a** along the Z direction. The portion **120_3** overlaps the contact **125b** along the Z direction. In some embodiments, the cut-MD pattern **120** is configured to disconnect the contacts **121**, **122a** to **125a**, and/or **122b** to **125b** to avoid leakage between the MDs. For example, the portion **120_1** of the cut-MD pattern **120** can avoid leakage between the contacts **122a** and **123a**. Dielectric material(s) may fill the cut-MD pattern **120**. In some embodiments, the cut-MD pattern **120** is disposed between the active-region structures **102** and **104**. In some embodiments, the cut-MD pattern **120**, including portions **120_1**, **120_2** and **120_3**, overlaps a portion of the main portion **132** of the backside interconnection structure **130** along the Z direction. In some embodiments, a portion of the main portion **132** is free from overlapping the cut-MD pattern **120** along the Z direction. In some embodiments, the profile of the cut-MD pattern **120** depends on the location of the fingers (e.g., the fingers **134c**, **134d**, and **134e**) of the backside interconnection structure **130**. For example, the backside interconnection structure **130** includes segments **132d** connected to the fingers (e.g., the fingers **134c**, **134d**, and **134e**). The segment **132d** is free from overlapping the cut-MD pattern **120** along the Z direction, and the segment **132d** overlaps the cut-poly pattern **110** along the Z direction. In some embodiments, the cut-MD pattern **120** can be

referred to as an MD cut layer “CMD” or a source/drain contact cut layer.

[0044] FIG. 6 is a layout diagram of a semiconductor device **10e** in accordance with some embodiments. The semiconductor device **10e** has a structure similar to that of the semiconductor device **10d**. One of the differences between the semiconductor devices **10e** and **10d** is that the backside interconnection structure **130** of the semiconductor devices **10e** includes an extension **136**. In FIG. 6, the cut-MD pattern **120** includes portions **120_2**, **120_3**, **120_4** and **120_5**. The portion **120_4** overlaps the contact **122a** along the Z direction. The portion **120_5** overlaps the contact **123b** along the Z direction.

[0045] In some embodiments, the extension **136** is connected to the main portion **132**. The extension **136** is connected to the finger **134d**. In some embodiments, the extension **136** is free from overlapping the cut-poly pattern **110**. In some embodiments, the extension **136** is free from overlapping the cut-MD pattern **120**. In some embodiments, the extension **136** extends from the contact **121** to the contact **122b** through the gate structure **111** in a top view. In some embodiments, the extension **136** overlaps the gate structure **111** and the active-region structure **104** along the Z direction. In some embodiments, the extension **136** overlaps a region between the contacts **121** and **122b** along the Z direction. In some embodiments, the extension **136** is disposed on a dummy region where no signal passes through, which thereby enhances the overlapping area between the backside interconnection structure **130** and the backside conductive layer **140**.

[0046] FIG. 7 is a layout diagram of a semiconductor device **10f** in accordance with some embodiments. In some embodiments, the semiconductor device **10f** includes a cell **12** and a cell **14** abutting the cell **12**. Each of the cells **12** and **14** has features (e.g., the gate structure, source/drain contact, backside interconnection structure, backside conductive layer, and/or other features) that are the same as or similar to those of the semiconductor device **10a** as shown in FIG. 1A.

[0047] The cell **12** includes a backside interconnection structure **130a** and a backside conductive layer **140a** configured to transmit a power signal. The backside interconnection structure **130a** is electrically connected to the backside conductive layer **140a**. The cell **12** includes a cut-MD pattern **120a** configured to disconnect the source/drain contacts within the cell **12**. The cell **14** has a backside interconnection structure **130b** and a backside conductive layer **140b** configured to transmit a power signal. The backside interconnection structure **130b** is electrically connected to the backside conductive layer **140b**. The cell **14** includes a cut-MD pattern **120b** configured to disconnect the source/drain contacts within the cell **14**. In some embodiments, each of the backside interconnection structures **130a** and **130b** has a main portion extending along the X direction and multiple fingers connected to the main portion and extending along the Y direction. In some cases, when the backside conductive layers **140a** and **140b** are configured to transmit the same power signal, the backside interconnection structure **130a** can be connected to the backside interconnection structure **130b**, which results in a reduction in the resistance for transmitting power. In this embodiment, the backside interconnection structures **130a** and **130b** define an O-shaped profile. In other embodiments, the backside interconnection structures **130a** and **130b** can define other profiles depending on the location of fingers.

[0048] In some embodiments, the layout diagram of the semiconductor devices **10a** to **10f** can be applied to a semiconductor device including nano-sheet transistors. FIG. 8 and FIGS. 9A to FIG. 9C illustrate a semiconductor device **20** which has a layout diagram the same as or similar to that as shown in FIG. 1A. It should be noted that some features are omitted from FIG. 8 for brevity, and the detailed structure is shown in FIGS. 9A to FIG. 9C.

[0049] Referring to FIG. 8, in some embodiments, the semiconductor device **20** includes a substrate **202** which includes a plurality of fins **204** protruding upwardly. In some embodiments, the semiconductor device **20** further includes a plurality of isolation regions **206** surrounding the fins **204**. In some embodiments, the backside of the substrate **202** is ground or polished until the isolation regions **206** are exposed, and a backside conductive layer **266** is formed on a backside of the substrate **202** to cover the isolation regions **206** and the substrate **202**.

[0050] A plurality of nanostructures **212** are disposed over the substrate **202** and the fins **204**. A plurality of gate dielectric layers **208** are disposed over the substrate **202** and the fins **204** and surround the nanostructures **212**. A plurality of gate electrodes **210** are disposed over the gate dielectric layers **208**. A plurality of epitaxial structures **214** (shown by dotted lines) are disposed over the substrate **202** and connected to the nanostructures **212**.

[0051] FIG. **9A**, FIG. **9B**, and FIG. **9C** are cross-sectional views taken along lines D-D', E-E' and F-F' of the semiconductor device **20**, respectively. As shown in FIGS. **9A-9C**, the semiconductor device **20** further includes a dielectric layer **216** that is disposed over the isolation regions **206** and a dielectric layer **218** that is disposed over the dielectric layer **216**. The epitaxial structures **214** and the gate electrodes **210** are disposed in the dielectric layer **216**. In some embodiments, the semiconductor device **20** further includes a plurality of spacers **234** (see FIG. **9B**) that are connected to side walls of the gate dielectric layers **208** around the gate electrodes **210**. In some embodiments, the semiconductor device **20** further includes a plurality of spacers **222** that are disposed in the dielectric layer **216** and that surround lower portions of the epitaxial structures **214**. In some embodiments, the semiconductor device **20** further includes a contact etch stop layer **226** that is disposed in the dielectric layer **216** and around the epitaxial structures **214**. In some embodiments, the semiconductor device **20** further includes a plurality of gate masks **238** that are disposed in the dielectric layer **216**, and over the gate electrodes **210**. In some embodiments, the semiconductor device **20** further includes a plurality of gate contacts **228** that are disposed in the dielectric layer **218**, and that are connected to the gate electrodes **210**. In some embodiments, the semiconductor device **20** further includes a plurality of source/drain contacts **230** that are disposed in the dielectric layers **216** and **218**. The source/drain contacts **230** are connected to the epitaxial structures **214**. In some embodiments, the semiconductor device **20** further includes a plurality of silicide structures **236** that are connected between the epitaxial structures **214** and the source/drain contacts **230**.

[0052] In some embodiments, the substrate **202** may be a suitable substrate, such as an elemental semiconductor or a compound semiconductor. The elemental semiconductor may contain a single species of atom, such as Si, Ge or other suitable materials. The compound semiconductor may be composed of at least two elements, such as GaAs, SiC, SiGe, GaP, InSb, InAs, InP, GaAsP, GaInAs, AlGaAs, AlInAs, GaInAsP, or the like. In some embodiments, the composition of the compound semiconductor including the aforesaid elements may vary by having one ratio at one location and another ratio at a different location (i.e., the compound semiconductor may have a gradient composition). In some embodiments, the substrate **202** may be a semiconductor-on-insulator (SOI) substrate, such as silicon germanium-on-insulator (SGOI) substrate, or the like. In some embodiments, an SOI substrate may include an epitaxially grown semiconductor layer, such as Si, Ge, SiGe, any combination thereof, or the like, which is formed over an oxide layer.

[0053] In some embodiments, the isolation regions **206** may include or be made of an insulating material, such as silicon oxide, or other suitable materials, and may be made by chemical vapor deposition (CVD), or other suitable techniques. The isolation region **206** includes STI or other suitable structures.

[0054] In some embodiments, the gate dielectric layers **208** may include or be made of a high-k dielectric material, such as a metal oxide or silicate of hafnium, aluminum, zirconium, lanthanum, manganese, barium, titanium, lead, other suitable materials, or any combination thereof, and may be made by CVD, atomic layer deposition (ALD), other suitable techniques, or any combination thereof.

[0055] In some embodiments, the gate electrodes **210** may include or be made of titanium nitride, titanium oxide, tantalum nitride, tantalum carbide, cobalt, ruthenium, aluminum, tungsten, other suitable materials, or any combination thereof, and may be made by physical vapor deposition (PVD), other suitable techniques, or any combination thereof.

[0056] In some embodiments, each of the nanostructures **212** may include or be made of silicon,

silicon germanium, silicon carbide, other suitable materials, or any combination thereof, and may be made by CVD, ALD, other suitable techniques, or any combination thereof.

[0057] In some embodiments, each of the epitaxial structures **214** may include or be made of silicon, silicon carbide, silicon phosphide, other suitable materials, or any, combination thereof, and may be made by CVD, ALD, vapor phase epitaxy (VPE), molecular beam epitaxy (MBE), other suitable techniques, or any combination thereof.

[0058] In some embodiments, each of the dielectric layers **216** and **218** may include or be made of SiO_x, SiO_xC_y, SiO_xC_yH_z, SiC_x, SiN_x, other suitable materials, or any combination thereof, and may be made by CVD, other suitable techniques, or any combination thereof.

[0059] In some embodiments, the spacers **222** and **234** may include or be made of silicon oxide, silicon nitride, silicon oxynitride, other suitable materials, or any combination thereof, and may be made by CVD, ALD, other suitable techniques, or any combination thereof.

[0060] In some embodiments, the contact etch stop layer **226** may include or be made of silicon nitride, silicon oxide, silicon oxynitride, other suitable materials, or any combination thereof, and may be made by CVD, ALD, other suitable techniques, or any combination thereof.

[0061] In some embodiments, each of the gate contacts **228** and the source/drain contacts **230** may include or be made of Cu, Ni, Ti, Co, Ru, Ir, Al, Pt, Pd, Au, Ag, Os, Mo, W, other suitable materials, or any combination thereof, and may be made by CVD, ALD, PVD, plating (including electroplating, electroless plating, etc.), other suitable techniques, or any combination thereof.

[0062] In some embodiments, the silicide structures **236** may include or be made of NiSi, TiSi, TiNiSi, TiSiGe, NiSiGe, TiNiSiGe, RuSi, CoSi, MoSi, PtSi, TaSi, WSi, CrSi, ZrSi, other suitable materials, or any combination thereof.

[0063] In some embodiments, the gate masks **238** may include or be made of silicon oxide, silicon nitride, silicon oxynitride, other suitable materials, or any combination thereof, and may be made by CVD, PVD, other suitable techniques, or any combination thereof.

[0064] In some embodiments, the semiconductor device **20** further includes a backside interconnection structure **260**. In some embodiments, a portion of the isolation regions **206** and a portion of the fins **204** are removed to form a trench. The backside interconnection structure **260** is formed within the trench.

[0065] In some embodiments, the backside interconnection structure **260** is disposed under the epitaxial structures **214**. A plurality of silicide structures **254** are connected between the epitaxial structures **214** and the backside interconnection structure **260**. In some embodiments, the backside interconnection structure **260** continuously extends from one epitaxial structure **214** to another epitaxial structure **214** as shown in FIG. **9A**. The backside interconnection structure **260** may include or be made of Cu, Ni, Co, Ru, Ir, Al, Pt, Pd, Au, Ag, Os, Mo, W, other suitable materials, or any combination thereof, and may be made by CVD, ALD, PVD, plating (including electroplating, electroless plating, etc.), other suitable techniques, or any combination thereof. The backside interconnection structure **260** may be referred to as a backside via (VB). In some embodiments, the backside interconnection structure **260** includes a main portion **260m** and fingers **260f**. The finger **260f** is connected to the bottom of the epitaxial structure **214**. The main portion **260m** is connected to multiple fingers **260f**. In some embodiments, the main portion **260m** is disposed between two abutting fins **204**.

[0066] In some embodiments, the semiconductor device **20** further includes a backside conductive layer **266**. The backside conductive layer **266** is disposed under the backside interconnection structure **260**. The backside conductive layer **266** may function as a power rail for providing electric power to the epitaxial structures **214**. The backside conductive layer **266** may include or be made of Cu, Ni, Ti, Co, Ru, Ir, Al, Pt, Pd, Au, Ag, Os, Mo, W, other suitable materials, or any combination thereof, and may be made by CVD, ALD, PVD, plating (including electroplating, electroless plating, etc.), other suitable techniques, or any combination thereof. The backside conductive layer **266** may be referred to as a first backside metal (BM0). The backside

interconnection structure **260** has a surface **260s1** facing the backside conductive layer **266** and a surface **260s2** opposite to the surface **260s1** (see FIG. 9A). The surface **260s1** has parts **260s1_P1** and **260s1_P2**. The part **260s1_P1** is exposed by the backside conductive layer **266** along a direction from the surface **260s1** toward the surface **260s2**. The part **260s1_P2** is covered by the backside conductive layer **266** along a direction from the surface **260s1** toward the surface **260s2**. [0067] In some embodiments, the semiconductor device **20** further includes a conductive structure **256** (see FIG. 9A). The conductive structure **256** is formed within the dielectric layer **216**. The conductive structure **256** is disposed between two abutting epitaxial structures **214**. In some embodiments, the conductive structure **256** electrically connects the backside interconnection structure **260** and the source/drain contact **230**, which thereby results in a reduction in the resistance for transmitting power. In some embodiments, the conductive structure **256** may include or be made of Cu, Ni, Ti, Co, Ru, Ir, Al, Pt, Pd, Au, Ag, Os, Mo, W, other suitable materials, or any combination thereof, and may be made by CVD, ALD, PVD, plating (including electroplating, electroless plating, etc.), other suitable techniques, or any combination thereof. In some embodiments, the conductive structure **256** can be a protruding portion of the backside interconnection structure **260**. In some embodiments, the conductive structure **256** can be a protruding portion of the source/drain contact **230**. In some embodiments, the conductive structure **256** can include two parts which are the protruding portion of the backside interconnection structure **260** and the protruding portion of the source/drain contact **230**.

[0068] In some embodiments, the semiconductor device **20** further includes a cutting feature **280** (see FIG. 9C) within the gate electrode **210**. In some embodiments, the cutting feature **280** is disposed over the main portion **260m** of the backside interconnection structure **260**. In some embodiments, the cutting feature **280** is configured to disconnect the gate electrode **210** to avoid leakage between the gate electrode **210** and the backside interconnection structure **260** in a condition in which the formation of the opening for accommodating the backside interconnection structure **260** is overetched. In some embodiments, the cutting feature **280** may include or be made of silicon oxide, silicon nitride, silicon oxynitride, other suitable materials, or any combination thereof, and may be made by CVD, PVD, other suitable techniques, or any combination thereof. The cutting feature **280** can also be referred to as “CPO.”

[0069] In this embodiment, the semiconductor device **20** includes the backside interconnection structure **260** with the main portion **260m**. The main portion **260m** is configured to enhance the overlapping area between the backside interconnection structure **260** and the backside conductive layer **266**, which results in a decrease in electrical resistance.

[0070] FIG. 10 and FIG. 11 are flowcharts of a method for manufacturing a layout of a semiconductor device according to various aspects of the present disclosure. FIG. 10 illustrates a method **30** of manufacturing a semiconductor device in accordance with some embodiments. The generation of the layout diagram is discussed in more detail as follows with respect to FIG. 11.

[0071] In some embodiments, the method **30** includes operations **32** and **34**. The method begins with the operation **32**, in which a layout diagram is generated.

[0072] The method **30** continues with the operation **34**: based on the layout diagram, in which at least one of (A) one or more photolithographic exposures are made or (B) one or more semiconductor masks are fabricated or (C) one or more components in a layer of a semiconductor device are fabricated.

[0073] As shown in FIG. 11, the operation **32** includes operations **321**, **322**, **323**, and **324**. In some embodiments, the operation **321** includes generating active patterns, gate patterns, and conductive patterns. In some embodiments, the active patterns correspond to the active-region structures **102** and **104** as shown in FIG. 1A. In some embodiments, the gate patterns correspond to the gate structures **111** to **114** as shown in FIG. 1A. In some embodiments, the conductive patterns correspond to the contacts **121**, **122a** to **125a**, and **122b** to **125b** as shown in FIG. 1A.

[0074] In some embodiments, the operation **322** includes generating a backside interconnection

pattern which includes finger patterns and a main pattern connected to the finger patterns. In some embodiments, the backside interconnection pattern corresponds to the backside interconnection structure **130** as shown in FIG. **1A**. In some embodiments, the finger patterns correspond to the fingers **134a** to **134e** as shown in FIG. **1A**. In some embodiments, the main pattern corresponds to the main portion **132** as shown in FIG. **1A**.

[0075] In some embodiments, the operation **323** includes generating a backside conductive pattern. In some embodiments, the backside conductive pattern corresponds to the backside conductive layer **140** as shown in FIG. **1A**.

[0076] In some embodiments, the operation **324** includes, based on the locations of finger patterns, generating a cut-poly pattern and/or a cut-MD pattern. In some embodiments, the cut-poly pattern corresponds to the cut-poly pattern **110** as shown in FIG. **5**. In some embodiments, the cut-MD pattern corresponds to the cut-MD pattern **120** as shown in FIG. **5**.

[0077] FIG. **12** is a block diagram of a system **400** of designing a semiconductor device, in accordance with some embodiments. The system **400** can include, for example, an electronic design automation (EDA) system.

[0078] In some embodiments, system **400** includes an automatic placement and routing (APR) system. Methods described herein of generating PG layout diagrams, in accordance with one or more embodiments, are implementable, for example, using the system **400**, in accordance with some embodiments.

[0079] In some embodiments, system **400** is a general purpose computing device including a hardware processor **402** and a non-transitory, computer-readable storage medium **404**. Storage medium **404**, amongst other things, is encoded with, i.e., stores, computer program code **406**, i.e., a set of executable instructions. Execution of instructions **406** by hardware processor **402** represents (at least in part) an EDA tool which implements a portion or all of a method according to an embodiment, e.g., the methods described herein in accordance with one or more embodiments. (hereinafter, the noted processes and/or methods).

[0080] Processor **402** is electrically coupled to computer-readable storage medium **404** via a bus **408**. Processor **402** is also electrically coupled to an I/O interface **410** by bus **408**. A network interface **412** is also electrically connected to processor **402** via bus **408**. Network interface **412** is connected to a network **414**, so that processor **402** and computer-readable storage medium **404** are capable of connecting to external elements via network **414**. Processor **402** is configured to execute computer program code **406** encoded in computer-readable storage medium **404** in order to cause system **400** to be usable for performing a portion or all of the noted processes and/or methods. In one or more embodiments, processor **402** is a central processing unit (CPU), a multi-processor, a distributed processing system, an application specific integrated circuit (ASIC), and/or a suitable processing unit.

[0081] In one or more embodiments, computer-readable storage medium **404** is an electronic, magnetic, optical, electromagnetic, infrared, and/or semiconductor system (or apparatus or device). For example, computer-readable storage medium **404** includes a semiconductor or solid-state memory, a magnetic tape, a removable computer diskette, a random access memory (RAM), a read-only memory (ROM), a rigid magnetic disk, and/or an optical disk. In one or more embodiments using optical disks, computer-readable storage medium **404** includes a compact disk-read only memory (CD-ROM), a compact disk-read/write (CD-R/W), and/or a digital video disc (DVD).

[0082] In one or more embodiments, storage medium **404** stores computer program code (instructions) **406** configured to cause system **400** (where such execution represents (at least in part) the EDA tool) to be usable for performing a portion or all of the noted processes and/or methods. In one or more embodiments, storage medium **404** also stores information which facilitates performing a portion or all of the noted processes and/or methods. In one or more embodiments, storage medium **404** stores library **407** of standard cells including such standard cells as disclosed herein and one or more layout diagrams **405** such as are disclosed herein.

[0083] System **400** includes I/O interface **410**. I/O interface **410** is coupled to external circuitry. In one or more embodiments, I/O interface **410** includes a keyboard, keypad, mouse, trackball, trackpad, touchscreen, and/or cursor direction keys for communicating information and commands to processor **402**.

[0084] System **400** also includes network interface **412** coupled to processor **402**. Network interface **412** allows system **400** to communicate with network **414**, to which one or more other computer systems are connected. Network interface **412** includes wireless network interfaces such as BLUETOOTH, WIFI, WIMAX, GPRS, or WCDMA; or wired network interfaces such as ETHERNET, USB, or IEEE-1364. In one or more embodiments, a portion or all of noted processes and/or methods, is implemented in two or more systems **400**.

[0085] System **400** is configured to receive information through I/O interface **410**. The information received through I/O interface **410** includes one or more of instructions, data, design rules, libraries of standard cells, and/or other parameters for processing by processor **402**. The information is transferred to processor **402** via bus **408**. System **400** is configured to receive information related to a UI through I/O interface **410**. The information is stored in computer-readable medium **404** as user interface (UI) **442**.

[0086] In some embodiments, a portion or all of the noted processes and/or methods is implemented as a standalone software application for execution by a processor. In some embodiments, a portion or all of the noted processes and/or methods is implemented as a software application that is a part of an additional software application. In some embodiments, a portion or all of the noted processes and/or methods is implemented as a plug-in to a software application. In some embodiments, at least one of the noted processes and/or methods is implemented as a software application that is a portion of an EDA tool. In some embodiments, a portion or all of the noted processes and/or methods are implemented as a software application running on System **400**. In some embodiments, a layout diagram which includes standard cells is generated using a tool such as VIRTUOSO® available from CADENCE DESIGN SYSTEMS, Inc., or another suitable layout generating tool.

[0087] In some embodiments, the processes are realized as functions of a program stored in a non-transitory computer readable recording medium. Examples of a non-transitory computer readable recording medium include, but are not limited to, external/removable and/or internal/built-in storage or memory unit, e.g., one or more of an optical disk, such as a DVD, a magnetic disk, such as a hard disk, a semiconductor memory, such as a ROM, a RAM, a memory card, and the like.

[0088] FIG. **13** is a block diagram of a semiconductor device manufacturing system **500**, and a semiconductor device flow associated therewith, in accordance with some embodiments. In some embodiments, based on a layout diagram, at least one of (A) one or more semiconductor masks or (B) at least one component in a layer of a semiconductor integrated circuit is fabricated using manufacturing system **500**.

[0089] In FIG. **13**, IC manufacturing system **500** includes entities, such as a design house **520**, a mask house **530**, and an IC manufacturer/fabricator (“fab”) **550**, that interact with one another in the design, development, and manufacturing cycles and/or services related to manufacturing an IC device **560**. The entities in system **500** are connected by a communications network. In some embodiments, the communications network is a single network. In some embodiments, the communications network is a variety of different networks, such as an intranet and the Internet. The communications network includes wired and/or wireless communication channels. Each entity interacts with one or more of the other entities and provides services to and/or receives services from one or more of the other entities. In some embodiments, two or more of design house **520**, mask house **530**, and IC fab **550** is owned by a single larger company. In some embodiments, two or more of design house **520**, mask house **530**, and IC fab **550** coexist in a common facility and use common resources.

[0090] Design house (or design team) **520** generates an IC design layout diagram **522**. IC design

layout diagram 522 includes various geometrical patterns designed for an IC device 560. The geometrical patterns correspond to patterns of metal, oxide, or semiconductor layers that make up the various components of IC device 560 to be fabricated. The various layers combine to form various IC features. For example, a portion of IC design layout diagram 522 includes various IC features, such as an active region, gate electrode, source and drain, metal lines or vias of an interlayer interconnection, and openings for bonding pads, to be formed in a semiconductor substrate (such as a silicon wafer) and various material layers disposed on the semiconductor substrate. Design house 520 implements a proper design procedure to form IC design layout diagram 522. The design procedure includes one or more of logic design, physical design or place and route. IC design layout diagram 522 is presented in one or more data files having information of the geometrical patterns. For example, IC design layout diagram 522 can be expressed in a GDSII file format or DFII file format.

[0091] Mask house 530 includes data preparation 532 and mask fabrication 544. Mask house 530 uses IC design layout diagram 522 to manufacture one or more masks 545 to be used for fabricating the various layers of IC device 560 according to IC design layout diagram 522. Mask house 530 performs mask data preparation 532, where IC design layout diagram 522 is translated into a representative data file (“RDF”). Mask data preparation 532 provides the RDF to mask fabrication 544. Mask fabrication 544 includes a mask writer. A mask writer converts the RDF to an image on a substrate, such as a mask (reticle) 545 or a semiconductor wafer 553. The design layout diagram 522 is manipulated by mask data preparation 532 to comply with particular characteristics of the mask writer and/or requirements of IC fab 550. In FIG. 13, mask data preparation 532 and mask fabrication 544 are illustrated as separate elements. In some embodiments, mask data preparation 532 and mask fabrication 544 can be collectively referred to as mask data preparation.

[0092] In some embodiments, mask data preparation 532 includes optical proximity correction (OPC) which uses lithography enhancement techniques to compensate for image errors, such as those that can arise from diffraction, interference, other process effects and the like. OPC adjusts IC design layout diagram 522. In some embodiments, mask data preparation 532 includes further resolution enhancement techniques (RET), such as off-axis illumination, sub-resolution assist features, phase-shifting masks, other suitable techniques, and the like or combinations thereof. In some embodiments, inverse lithography technology (ILT) is also used, which treats OPC as an inverse imaging problem.

[0093] In some embodiments, mask data preparation 532 includes a mask rule checker (MRC) that checks the IC design layout diagram 522 that has undergone processes in OPC with a set of mask creation rules which contain certain geometric and/or connectivity restrictions to ensure sufficient margins, to account for variability in semiconductor manufacturing processes, and the like. In some embodiments, the MRC modifies the IC design layout diagram 522 to compensate for limitations during mask fabrication 544, which may undo part of the modifications performed by OPC in order to meet mask creation rules.

[0094] In some embodiments, mask data preparation 532 includes lithography process checking (LPC) that simulates processing that will be implemented by IC fab 550 to fabricate IC device 560. LPC simulates this processing based on IC design layout diagram 522 to create a simulated manufactured device, such as IC device 560. The processing parameters in LPC simulation can include parameters associated with various processes of the IC manufacturing cycle, parameters associated with tools used for manufacturing the IC, and/or other aspects of the manufacturing process. LPC takes into account various factors, such as aerial image contrast, depth of focus (“DOF”), mask error enhancement factor (“MEEF”), other suitable factors, and the like or combinations thereof. In some embodiments, after a simulated manufactured device has been created by LPC, if the simulated device is not close enough in shape to satisfy design rules, OPC and/or MRC are repeated to further refine IC design layout diagram 522.

[0095] It should be understood that the foregoing description of mask data preparation **532** has been simplified for the purposes of clarity. In some embodiments, data preparation **532** includes additional features such as a logic operation (LOP) to modify the IC design layout diagram **522** according to manufacturing rules. Additionally, the processes applied to IC design layout diagram **522** during data preparation **532** may be executed in a variety of different orders.

[0096] After mask data preparation **532** and during mask fabrication **544**, a mask **545** or a group of masks **545** are fabricated based on the modified IC design layout diagram **522**. In some embodiments, mask fabrication **544** includes performing one or more lithographic exposures based on IC design layout diagram **522**. In some embodiments, an electron-beam (e-beam) or a mechanism of multiple e-beams is used to form a pattern on a mask (photomask or reticle) **545** based on the modified IC design layout diagram **522**. Mask **545** can be formed in various technologies. In some embodiments, mask **545** is formed using binary technology. In some embodiments, a mask pattern includes opaque regions and transparent regions. A radiation beam, such as an ultraviolet (UV) beam, used to expose the image sensitive material layer (e.g., photoresist) which has been coated on a wafer, is blocked by the opaque region and transmits through the transparent regions. In one example, a binary mask version of mask **545** includes a transparent substrate (e.g., fused quartz) and an opaque material (e.g., chromium) coated in the opaque regions of the binary mask. In another example, mask **545** is formed using a phase shift technology. In a phase shift mask (PSM) version of mask **545**, various features in the pattern formed on the phase shift mask are configured to have proper phase difference to enhance the resolution and imaging quality. In various examples, the phase shift mask can be attenuated PSM or alternating PSM. The masks generated by mask fabrication **544** are used in a variety of processes. For example, such a mask(s) can be used in an ion implantation process to form various doped regions in semiconductor wafer **553**, in an etching process to form various etching regions in semiconductor wafer **553**, and/or in other suitable processes.

[0097] IC fab **550** includes wafer fabrication **552**. IC fab **550** is an IC fabricator that includes one or more manufacturing facilities for the fabrication of a variety of different IC products. In some embodiments, IC Fab **550** can be a semiconductor foundry. For example, there may be a manufacturing facility for the front end fabrication of a plurality of IC products (front-end-of-line (FEOL) fabrication), while a second manufacturing facility may provide the back end fabrication for the interconnection and packaging of the IC products (back-end-of-line (BEOL) fabrication), and a third manufacturing facility may provide other services for the foundry business.

[0098] IC fab **550** uses mask(s) **545** fabricated by mask house **530** to fabricate IC device **560**. Thus, IC fab **550** at least indirectly uses IC design layout diagram **522** to fabricate IC device **560**. In some embodiments, semiconductor wafer **553** is fabricated by IC fab **550** using mask(s) **545** to form IC device **560**. In some embodiments, the IC fabrication includes performing one or more lithographic exposures based at least indirectly on IC design layout diagram **522**. Semiconductor wafer **553** includes a silicon substrate or other proper substrate having material layers formed thereon. Semiconductor wafer **553** further includes one or more of various doped regions, dielectric features, multilevel interconnects, and the like (formed at subsequent manufacturing steps).

[0099] Details regarding an integrated circuit (IC) manufacturing system (e.g., system **500** of FIG. **13**), and an IC manufacturing flow associated therewith are found, e.g., in U.S. Pat. No. 9,256,709, granted Feb. 9, 2016, U.S. Pre-Grant Publication No. 20150278429, published Oct. 1, 2015, U.S. Pre-Grant Publication No. 20140040838, published Feb. 6, 2014, and U.S. Pat. No. 7,260,442, granted Aug. 21, 2007, the entireties of each of which are hereby incorporated by reference.

[0100] FIG. **14** is a flowchart of a method **600** for manufacturing a semiconductor device (e.g., the semiconductor devices **10a-10f** and **20**), in accordance with some embodiments.

[0101] The method **600** begins with operation **602** in which a semiconductor structure is formed. In some embodiments, the semiconductor structure includes a substrate (e.g., the substrate **202**) and fins (e.g., the fins **204**) over the substrate. The fins define a plurality of trenches over the substrate.

In some embodiments, the semiconductor structure includes isolation regions (e.g., the isolation regions **206**) filling the trenches and surrounded by the fins. In some embodiments, the semiconductor structure includes gate structures extending along a first direction. Each of the gate structures includes nanostructures (e.g., the nanostructures **212**), a gate dielectric layer (e.g., the gate dielectric layer **208**), and a gate electrode (e.g., the gate electrode **210**). In some embodiments, the semiconductor structure includes epitaxial structures (e.g., epitaxial structures **214**) over the fins. In some embodiments, the semiconductor structure includes an interlayer dielectric (ILD, e.g., the dielectric layer **216**) covering the epitaxial structures.

[0102] The method **600** continues with operation **604** in which the semiconductor structure is patterned. In some embodiments, portions of the fins under the epitaxial structures are removed to form first openings (the opening for accommodating the fingers **260f** of a backside via) exposing the epitaxial structure. In some embodiments, portions of the isolation regions are removed to form a second opening (the opening for accommodating the main portion **260m** of a backside via). In some embodiments, the second openings correspondingly are in communication with the first openings.

[0103] The method **600** continues with operation **606** in which a backside interconnection structure (e.g., the backside interconnection structure **260**) is formed to fill the first openings and the second openings. The backside interconnection structure includes a main portion (e.g., the main portion **260m**) and fingers (e.g., the finger **260f**) connected by the main portion.

[0104] The method **600** continues with operation **608** in which a backside conductive layer (e.g., the backside conductive layer **266**) is formed under the backside interconnection structure.

[0105] The method **600** continues with operation **610** in which a conductive structure (e.g., the conductive structure **256**) is formed over the main portion of the backside interconnection structure. In some embodiments, a portion of the ILD is removed to form a third opening (e.g., the opening for accommodating the conductive structure **256**) exposing the backside interconnection structure. In some embodiments, the conductive structure is formed within the third opening.

[0106] The method **600** continues with operation **612** in which source/drain contacts (e.g., the source/drain contacts **230**) are formed over the epitaxial structures of the semiconductor structure. Each of the source/drain contacts extends along the first direction. In some embodiments, the source/drain contact is electrically connected to the backside interconnection structure through the conductive structure.

[0107] The method **600** continues with operation **614** in which cutting structures are formed. In some embodiments, the cutting structures include CPO (e.g., the cutting feature **280**) configured to cut a portion of the gate structures. In some embodiments, the cutting structures include CMD (e.g., the cut-MD pattern **120**) configured to cut a portion of the source/drain contacts.

[0108] The method **600** is merely an example, and is not intended to limit the present disclosure beyond what is explicitly recited in the claims. Additional operations can be provided before, during, and after the method **600**, and some operations described can be replaced, eliminated, or reordered for additional embodiments of the method.

[0109] Some embodiments of the present disclosure provide a semiconductor device. The semiconductor device includes a first type active region structure and a second type active region structure extending along a first direction. The semiconductor device also includes a first S/D contact over the first type active region structure and extending along a second direction different from the first direction. The semiconductor device further includes a backside conductive layer under the first type active region structure. In addition, the semiconductor device includes a backside interconnection structure between the backside conductive layer and the first type active region structure. The backside interconnection structure includes a first portion between the backside conductive layer and the first type active region structure, a second portion between the backside conductive layer and the second type active region structure, and a third portion connecting the first portion and the second portion.

[0110] Some embodiments of the present disclosure provide a semiconductor device. The semiconductor device includes a substrate. The semiconductor device also includes a first epitaxial structure and a second epitaxial structure on the substrate. The semiconductor device further includes a backside conductive layer under the substrate. In addition, the semiconductor device includes a backside interconnection structure between the backside conductive layer and the first epitaxial structure and between the backside conductive layer and the second epitaxial structure.

[0111] Some embodiments of the present disclosure provide a method of manufacturing a semiconductor device. The method includes providing a substrate and forming a first epitaxial structure and a second epitaxial structure on the substrate. The method also includes forming a backside interconnection structure under the first epitaxial structure and under the second epitaxial structure. The backside interconnection structure includes a first finger connected to the first epitaxial structure, a second finger connected to the second epitaxial structure, and a main portion connecting the first finger to the second finger. The method further includes forming a backside conductive layer under the backside interconnection structure.

[0112] The foregoing outlines structures of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A semiconductor device, comprising: a first type active region structure and a second type active region structure extending along a first direction; a first source/drain (S/D) contact over the first type active region structure and extending along a second direction different from the first direction; a backside conductive layer under the first type active region structure; and; a backside interconnection structure between the backside conductive layer and the first type active region structure, the backside interconnection structure including a first portion coupled between the backside conductive layer and the first type active region structure, a second portion coupled between the backside conductive layer and the second type active region structure, and a third portion coupling the first portion and the second portion.
2. The semiconductor device of claim 1, wherein the first S/D contact is coupled to the third portion of the backside interconnection structure.
3. The semiconductor device of claim 1, wherein the backside interconnection structure further includes a fourth portion protruding toward the first S/D contact along a third direction different from the first direction and the second direction.
4. The semiconductor device of claim 1, wherein the first S/D contact includes a first portion protruding toward the backside interconnection structure along a third direction different from the first direction and the second direction.
5. The semiconductor device of claim 1, further comprising: a second S/D contact over the first type active region structure and extending along the second direction; and wherein the backside interconnection structure comprises a fourth portion coupled between the second S/D contact and the backside conductive layer and coupled to the third portion.
6. The semiconductor device of claim 5, further comprising: a gate structure extending along the second direction and across a gap between the first type active region structure and the second type active region structure; and; wherein the third portion overlaps the gap along a third direction different from the first direction and the second direction.

7. The semiconductor device of claim 1, further comprising: a gate structure extending along the second direction and over the first type active region structure and the second type active region structure; a gate structure cut layer disposed between the first type active region structure and the second type active region structure; and; wherein the gate structure cut layer overlaps the third portion of the backside interconnection structure along a third direction different from the first direction and the second direction.

8. The semiconductor device of claim 1, further comprising: a second S/D contact over the first type active region structure and extending along the second direction; a third S/D contact over the second type active region structure and extending along the second direction; and; an S/D contact cut layer between second S/D contact and the third S/D contact, wherein the S/D contact cut layer overlaps the backside interconnection structure along a third direction different from the first direction and the second direction.

9. The semiconductor device of claim 8, wherein the third portion of the backside interconnection structure extends along the first direction.

10. A semiconductor device, comprising: a substrate; a first epitaxial structure and a second epitaxial structure on the substrate; a backside conductive layer under the substrate; and; a backside interconnection structure between the backside conductive layer and the first epitaxial structure and between the backside conductive layer and the second epitaxial structure.

11. The semiconductor device of claim 10, further comprising: a source/drain (S/D) contact over the first epitaxial structure and electrically connected to the backside interconnection structure.

12. The semiconductor device of claim 11, further comprising: a conductive structure electrically connecting the S/D contact to the backside interconnection structure, wherein the conductive structure is between the first epitaxial structure and the second epitaxial structure.

13. The semiconductor device of claim 10, wherein the backside interconnection structure has a first surface facing the backside conductive layer, and a portion of the first surface is exposed by the backside conductive layer along a direction substantially orthogonal to the first surface.

14. The semiconductor device of claim 10, further comprising: a gate electrode over the substrate; and; a cutting feature within the gate electrode, wherein the cutting feature vertically overlaps the backside interconnection structure.

15. The semiconductor device of claim 10, wherein the backside interconnection structure has a first portion under the first epitaxial structure, a second portion under the second epitaxial structure, and a third portion coupled to the first portion to the second portion.

16. A method of manufacturing a semiconductor device, comprising: forming a first epitaxial structure and a second epitaxial structure on a substrate; forming a backside interconnection structure under the first epitaxial structure and under the second epitaxial structure, wherein the backside interconnection structure includes a first finger connected to the first epitaxial structure, a second finger connected to the second epitaxial structure, and a main portion connecting the first finger to the second finger; and; forming a backside conductive layer under the backside interconnection structure.

17. The method of claim 16, further comprising: forming a conductive structure over the backside interconnection structure; and; forming a source/drain contact over the first epitaxial structure, the second epitaxial structure, and the conductive structure.

18. The method of claim 16, further comprising: forming a gate electrode over the substrate, wherein the main portion of the backside interconnection structure is formed under the gate electrode; removing a portion of the gate electrode over the main portion of the backside interconnection structure; and; forming a cut feature over the main portion of the backside interconnection structure.

19. The method of claim 16, further comprising: forming a plurality of fins over the substrate to define trenches; forming isolation regions within the trenches; and; removing a portion of the isolation regions to form a first opening, wherein the main portion of the backside interconnection

structure is formed within the first opening.

20. The method of claim 19, further comprising: removing a portion of the plurality of fins to form a second opening under the first epitaxial structure and a third opening under the second epitaxial structure, wherein the first finger is formed within the second opening, and the second finger is formed within the third opening.
