

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12389799
Kind Code	B2
Date of Patent	August 12, 2025
Inventor(s)	Chen; Chih-Ming

Piezoelectric device and method of forming the same

Abstract

A piezoelectric device including a substrate, a metal-insulator-metal element, a hydrogen blocking layer, a passivation layer, a first contact terminal and a second contact terminal is provided. The metal-insulator-metal element is disposed on the substrate. The hydrogen blocking layer is disposed on the metal-insulator-metal element. The passivation layer covers the hydrogen blocking layer and the metal-insulator-metal element. The first contact terminal is electrically connected to the metal-insulator-metal element. The second contact terminal is electrically connected to the metal-insulator-metal element.

Inventors:	Chen; Chih-Ming (Hsinchu, TW)
Applicant:	Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)
Family ID:	75586179
Assignee:	Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)
Appl. No.:	18/513640
Filed:	November 20, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240090334 A1	Mar. 14, 2024

Related U.S. Application Data

continuation parent-doc US 17988723 20221116 US 11856859 child-doc US 18513640
continuation parent-doc US 16666395 20191028 US 11527701 20221213 child-doc US 17988723

Publication Classification

Int. Cl.: H10N30/50 (20230101); H10N30/00 (20230101); H10N30/076 (20230101); H10N30/853 (20230101); H10N30/87 (20230101); G02B3/14 (20060101); G02B26/00 (20060101); H10N30/01 (20230101); H10N30/20 (20230101)

U.S. Cl.:

CPC H10N30/708 (20240501); H10N30/076 (20230201); H10N30/501 (20230201); H10N30/853 (20230201); H10N30/871 (20230201); H10N30/872 (20230201); G02B3/14 (20130101); G02B26/004 (20130101); H10N30/01 (20230201); H10N30/204 (20230201)

Field of Classification Search

CPC: H10N (30/07); H10N (30/082); H10N (30/20); H10N (30/30); H10N (30/50); H10N (30/883); H10N (30/708); H10N (30/076); H10N (30/501); H10N (30/853); H10N (30/871); H10N (30/872); H10N (30/01); H10N (30/204); H10N (30/704); H10N (30/02); H10N (30/80); H10N (30/05); G02B (3/14); G02B (26/004)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
10032977	12/2017	Fujimori	N/A	B41J 2/161
11527701	12/2021	Chen	N/A	G02B 26/004
11856859	12/2022	Chen	N/A	H10N 30/872
2012/0236083	12/2011	Mizukami	347/70	B41J 2/1612
2015/0077475	12/2014	Mizukami	29/25.35	H10N 30/101

Primary Examiner: Rodela; Eduardo A

Attorney, Agent or Firm: JCIPRNET

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION (1) This application is a continuation application of and claims the priority benefit of a prior application Ser. No. 17/988,723, filed on Nov. 16, 2022. The prior application Ser. No. 17/988,723 is a continuation application of and claims the priority benefit of a prior application Ser. No. 16/666,395, filed on Oct. 28, 2019. The entirety of each of the above-mentioned patent applications is hereby incorporated by reference herein and made a part of this specification.

BACKGROUND

(1) Piezoelectric devices are used in many fields and the global demand for piezoelectric devices becomes strong nowadays.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the critical dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1 is a schematic cross-sectional view illustrating a piezoelectric device in accordance with some embodiments.

(3) FIG. 2 is a schematic top view illustrating a piezoelectric device in accordance with some embodiments.

(4) FIGS. 3A-3I are schematic cross-sectional views illustrating various stages of a method of forming the piezoelectric device in FIG. 1 and FIG. 2 in accordance with some embodiments.

(5) FIG. 4 is a schematic cross-sectional view illustrating a piezoelectric device in accordance with alternative embodiments.

(6) FIG. 5 is a schematic cross-sectional view illustrating a piezoelectric device in accordance with alternative embodiments.

(7) FIG. 6A and FIG. 6B are schematic views illustrating one exemplary application of the piezoelectric device in accordance with some embodiments.

DETAILED DESCRIPTION

(8) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(9) Further, spatially relative terms, such as “beneath”, “below”, “lower”, “on”, “over”, “overlying”, “above”, “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(10) Piezoelectric devices are devices utilizing piezoelectric effects, including piezoelectric sensors, actuators, transducers, transformers and motors. A piezoelectric device (such as an actuator) may include a piezoelectric layer stacked between a first electrode and a second electrode. When a voltage is applied, the electrical field generated by the applied voltage will cause the piezoelectric layer to stretch or compress in a direction normal to the piezoelectric layer (i.e. deform). The deformation of the piezoelectric layer is translated into a physical displacement. Such physical displacement may be used to move or position objects in various kinds of mechanical systems and optical systems. The amount of the physical displacement or movement generally depends upon the voltage applied as well as the piezoelectric coefficient of the piezoelectric layer (i.e. the efficiency of the piezoelectric material in transferring the electrical energy to mechanical energy). The performance of the piezoelectric devices may be determined by the characteristics of the piezoelectric layer in the piezoelectric devices. For improving the reliability of the piezoelectric devices, the amount of the hydrogen-ions present in the piezoelectric layer of the piezoelectric

device is better to be reduced or minimized.

(11) During the manufacturing processes, hydrogen-ion containing processing may be performed after the formation of the piezoelectric layer, which may cause the inclusion of the hydrogen-ions into the piezoelectric layer and degrade the reliability of the piezoelectric devices. According to some embodiments, it is desirable to form a blocking material or a shielding layer deterring and hindering the hydrogen-ions from entering into the piezoelectric layer before performing hydrogen-ion containing processing.

(12) FIG. 1 is a schematic cross-sectional view illustrating a piezoelectric device in accordance with some embodiments. FIG. 2 is a schematic top view illustrating a piezoelectric device in accordance with some embodiments. FIG. 2 is a cross-sectional view taken along line A-A' and line B-B' of FIG. 1. It should be noted that for simplicity, certain elements of the piezoelectric device 10 in FIG. 2 are omitted.

(13) Referring to FIG. 1 and FIG. 2, the piezoelectric device 10 includes a substrate 100, a first electrode 101, a piezoelectric layer 102, a second electrode 103, a hydrogen blocking layer 104, a passivation layer 105, a first contact terminal 106 and a second contact terminal 107. In some embodiments, the first electrode 101 is disposed on the substrate 100, the piezoelectric layer 102 is disposed on the first electrode 101, the second electrode 103 is disposed on the piezoelectric layer 102, the hydrogen blocking layer 104 is disposed on the second electrode 103, the passivation layer 105 covers the hydrogen blocking layer 104, the second electrode 103, the piezoelectric layer 102 and the first electrode 101, the first contact terminal 106 is electrically connected to the first electrode 101, and the second contact terminal 107 is electrically connected to the second electrode 103.

(14) In FIG. 1 and FIG. 2, the first electrode 101, the piezoelectric layer 102 and the second electrode 103 are sequentially stacked on the substrate 100. In other words, the piezoelectric layer 102 is located between the first electrode 101 and the second electrode 103. In some embodiments, the first electrode 101 includes a first metal pattern 101A, and the second electrode 103 includes a second metal pattern 103A. In some embodiments, the material of the piezoelectric layer 102 includes a piezoelectric ceramic material such as lead zirconate titanate (PZT). Specifically, the stacked structure of the first electrode 101, the piezoelectric layer 102 and the second electrode 103 constitutes a metal-insulator-metal element MIM. That is to say, in some embodiments, the metal-insulator-metal element MIM is disposed on the substrate 100, the hydrogen blocking layer 104 is disposed on the metal-insulator-metal element MIM, the passivation layer 105 covers the hydrogen blocking layer 104 and the metal-insulator-metal element MIM, and the first contact terminal 106 and the second contact terminal 107 are electrically connected to the metal-insulator-metal element MIM.

(15) Still referring to FIG. 1, from the top view, the first electrode 101 is designed to be a substantially circular electrode with a contact portion P1 protruding from the contour of the circular electrode, and the second electrode 103 is designed to be a substantially circular electrode with a contact portion P2 protruding from the contour of the circular electrode. However, the disclosure is not limited thereto. In some alternative embodiments, the shapes of the patterns of the first electrode 101 and the second electrode 103 may be oval shapes, tetragonal, hexagonal or polygonal shapes or any suitable shapes from the top view. In addition, the shape of the pattern of the piezoelectric layer 102 is designed, corresponding to the shapes of the top and bottom electrodes 101, 103, to be a circular shape. From the top view as shown in FIG. 1, the shapes of the first electrode 101, the piezoelectric layer 102 and the second electrode 103 are arranged as concentric circles. However, the disclosure is not limited thereto. In some alternative embodiments, the shape of the pattern of the piezoelectric layer 102 may be designed to be a polygonal shape or any suitable shape from the top view. In yet alternative embodiments, the shapes of the first electrode 101, the piezoelectric layer 102 and the second electrode 103 may be arranged as non-concentric circles.

(16) Continue referring to FIG. 1, from the top view, the span of the first electrode 101 is greater

than the span of the piezoelectric layer **102**, and the span of the piezoelectric layer **102** is greater than the span of the second electrode **103**. From another point of view, the first electrode **101**, the piezoelectric layer **102** and the second electrode **103** constitute a staircase shaped stacked-structure, as shown in the cross-section of FIG. 2.

(17) In some embodiments, the first contact terminal **106** is electrically connected to the first electrode **101** through a first contact hole H1 in the passivation layer **105** and the hydrogen blocking layer **104**, and the second contact terminal **107** is electrically connected to the second electrode **103** through a second contact hole H2 in the passivation layer **105** and the hydrogen blocking layer **104**. In detail, the first contact terminal **106** is electrically connected to the contact portion P1 of the first electrode **101**, and the second contact terminal **107** is electrically connected to the contact portion P2 of the second electrode **103**. In some embodiments, the first contact terminal **106** and the second contact terminal **107** both may serve as external input/output terminals of the piezoelectric device **10**. When a voltage is applied between the first contact terminal **106** and the second contact terminal **107**, the same voltage is applied between the first electrode **101** and the second electrode **103**. The electrical field caused by the applied voltage can cause the piezoelectric layer **102** to stretch or compress in a direction normal to the surface of the substrate **100**. The stretch and compression of the piezoelectric layer **102** is translated into a physical displacement for controlling a mechanical system or optical system.

(18) In some embodiments, the hydrogen blocking layer **104** includes a first hydrogen blocking layer **104a**, a second hydrogen blocking layer **104b** and a third hydrogen blocking layer **104c**. That is to say, in some embodiments, the hydrogen blocking layer **104** is a multilayer structure.

Specifically, as shown in FIG. 2, the first hydrogen blocking layer **104a** covers and contacts the top surface of the second electrode **103**, the second hydrogen blocking **104b** layer covers the first hydrogen blocking layer **104a** and contacts the top surface of the piezoelectric layer **102**, and the third hydrogen blocking layer **104c** covers the second hydrogen blocking layer **104b** and contacts the top surface of the first electrode **101**. In other words, during the fabrication process of the piezoelectric device **10**, the hydrogen blocking layer **104** covers and protects the outermost top surface of the metal-insulator-metal element MIM. Because the hydrogen blocking layer **104** covers and protects the outermost top surface of the metal-insulator-metal element MIM, the hydrogen-ions of the photoresist layer are barred from penetrating into the metal-insulator-metal element MIM by the hydrogen blocking layer **104**. As such, no hydrogen-ions or minimal hydrogen-ions are included in the piezoelectric layer **102** of the piezoelectric device **10** and the piezoelectric characteristics of the piezoelectric layer **102** are maintained. This is to say, better reliability of the piezoelectric device **10** can be achieved due to the hydrogen blocking layer **104**.

(19) The method of forming the piezoelectric device **10** will be described in details below with reference to FIG. 3A to FIG. 3I. FIGS. 3A-3I are schematic cross-sectional views illustrating various stages of a method of forming the piezoelectric device in FIG. 1 and FIG. 2 in accordance with some embodiments.

(20) Referring to FIG. 3A, a substrate **100** is provided. In some embodiments, the material of the substrate **100** may include, for example, silicon, glass, silicon dioxide, aluminum oxide, or the like. Referring to FIG. 3A, a first conductive layer **108**, a piezoelectric material layer **109**, a second conductive layer **110** and a first hydrogen blocking material layer **111** are sequentially formed on the substrate **100**. In other words, the piezoelectric material layer **109** is located between the first conductive layer **108** and the second conductive layer **110**, and the first hydrogen blocking material layer **111** is located on the second conductive layer **110**. In some embodiments, the materials of the first conductive layer **108** and the second conductive layer **110** may respectively include, but not limited to, molybdenum (Mo), titanium nitride (TiN), aluminum (Al), platinum (Pt), gold (Au), tungsten (W), a combination thereof, or the like. In some embodiments, the material of the first conductive layer **108** is the same as the material of the second conductive layer **110**. In some alternative embodiments, the material of the first conductive layer **108** is different from the

material of the second conductive layer **110**. In some embodiments, the first conductive layer **108** and the second conductive layer **110** each may have a thickness that is in a range from about 200 Å to about 2000 Å. In some embodiments, the first conductive layer **108** and the second conductive layer **110** each may be formed with a deposition process, such as chemical vapor deposition (CVD), physical vapor deposition (PVD), or atomic layer deposition (ALD).

(21) In some embodiments, the material of the piezoelectric material layer **109** may include, but not limited to, aluminum nitride (AlN), lead zirconate titanate (PZT), gallium orthophosphate (GaPO.sub.4), langasite (La.sub.3Ga.sub.0.5SiO.sub.14), barium titanate (BaTiO.sub.3), potassium niobate (KNbO.sub.3), lithium niobate (LiNbO.sub.3), lithium tantalate (LiTaO.sub.3), sodium tungstate (Na.sub.2WO.sub.3), zinc oxide (ZnO), a combination thereof, or the like. In some embodiments, the piezoelectric material layer **109** may have a thickness that is in a range from about 2000 Å to about 20000 Å. In some embodiments, the piezoelectric material layer **109** may be formed with PVD or a sol-gel process.

(22) In some embodiments, the material of the first hydrogen blocking material layer **111** may include a metal oxide. Examples of the metal oxide may include Al.sub.2O.sub.3, TiO.sub.2, Fe.sub.2O.sub.3, ZrO.sub.2, ZnO, CuO or Ta.sub.2O.sub.5. In some embodiments, the first hydrogen blocking material layer **111** may have a thickness that is greater than 200 Å. In detail, owing to having the thickness greater than 200 Å, the first hydrogen blocking layer **104a** formed from the first hydrogen blocking material layer **111** has good blocking ability for hydrogen-ions. In some embodiments, the first hydrogen blocking material layer **111** may be formed with a deposition process, such as ALD or PVD. In detail, the first hydrogen blocking material layer **111** is formed with ALD, thereby the first hydrogen blocking material layer **111** is dense enough for the first hydrogen blocking layer **104a** formed from the first hydrogen blocking material layer **111** to have good blocking ability for hydrogen-ions. Moreover, the first hydrogen blocking material layer **111** is formed with PVD, thereby there is no additional hydrogen-ions from the first hydrogen blocking material layer **111**.

(23) Referring to FIG. 3B, a first photolithography step is performed to form a first photoresist layer PR1 on the first hydrogen blocking material layer **111**. In other words, the first hydrogen blocking material layer **111** is located between the first photoresist layer PR1 and the second conductive layer **110**. In some embodiments, the first photolithography step for forming the first photoresist layer PR1 may include the following steps of coating a photoresist material on the first hydrogen blocking material layer **111**, exposing the photoresist material with a photolithography mask (or called photomask), and developing the exposed photoresist material. In some embodiments, the first photoresist layer PR1 includes a positive photoresist material which is photo-solubilized when exposed to light. In some alternative embodiments, the first photoresist layer PR1 includes a negative photoresist material.

(24) Referring to FIG. 3B and FIG. 3C, a first etching step is performed to the first hydrogen blocking material layer **111** and the second conductive layer **110** by using the first photoresist layer PR1 as an etch mask, such that the first hydrogen blocking material layer **111** and the second conductive layer **110** are etched to form the first hydrogen blocking layer **104a** and the second electrode **103**, and the portions of the piezoelectric material layer **109** that are not covered by the first hydrogen blocking layer **104a** and the second electrode **103** are exposed. In other words, the first hydrogen blocking material layer **111** and the second conductive layer **110** are simultaneously patterned by using the same mask to form the first hydrogen blocking layer **104a** and the second electrode **103**. That is to say, the first hydrogen blocking layer **104a** and the second electrode **103** have substantially identical layout. In some embodiments, the first etching step is an ion-beam etching step used to pattern the first hydrogen blocking material layer **111** and the second conductive layer **110** in a single patterning process. In some embodiments, during the ion-beam etching step, there is substantially no etching selectivity between the first hydrogen blocking material layer **111** and the second conductive layer **110**, which means that the etching rate ratio of

the material of the first hydrogen blocking material layer **111** to the material of the second conductive layer **110** is substantially 1. It is noted that, as the first hydrogen blocking material layer **111** is formed between the first photoresist layer PR1 and the second conductive layer **110**, during the first etching step, the first hydrogen blocking layer **104a** helps prevent the hydrogen-ions in the first photoresist layer PR1 from penetrating into the second electrode **103**.

(25) As shown in FIG. 3C, the first hydrogen blocking layer **104a** is located between the first photoresist layer PR1 and the second electrode **103**. From another point of view, the first hydrogen blocking layer **104a** is formed to physically contact the second electrode **103** at the top surface of the second electrode **103**. Details of the first hydrogen blocking layer **104a** and the second electrode **103** have been described above, and will not be iterated herein.

(26) Referring to FIG. 3C and FIG. 3D, after the first hydrogen blocking layer **104a** and the second electrode **103** are formed, the first photoresist layer PR1 is removed. In some embodiments, the first photoresist layer PR1 may be removed by a stripping process, such as a dry stripping process, a wet stripping process or a combination thereof. As mentioned above, since the first hydrogen blocking layer **104a** is located between the first photoresist layer PR1 and the second electrode **103**, during the stripping process of the first photoresist layer PR1, the first hydrogen blocking layer **104a** helps prevent the hydrogen-ions in the first photoresist layer PR1 from penetrating into the second electrode **103**.

(27) Still referring to FIG. 3D, a second hydrogen blocking material layer **112** is formed on the first hydrogen blocking layer **104a** and the second electrode **103**. In addition, the second hydrogen blocking material layer **112** is formed on the portions of the piezoelectric material layer **109** that are not covered by the first hydrogen blocking layer **104a** and the second electrode **103**. In some embodiments, the second hydrogen blocking material layer **112** is a conformal layer. In detail, the second hydrogen blocking material layer **112** conformally and completely covers the top surface and the sidewall of the first hydrogen blocking layer **104a**, the sidewall of the second electrode **103**, and the portions of the piezoelectric material layer **109** that are not covered by the first hydrogen blocking layer **104a** and the second electrode **103**. However, the disclosure is not limited thereto. In some alternative embodiments, the second hydrogen blocking material layer **112** is not a conformal layer.

(28) In some embodiments, the material of the second hydrogen blocking material layer **112** may include a metal oxide. Examples of the metal oxide may include Al.sub.2O.sub.3, TiO.sub.2, Fe.sub.2O.sub.3, ZrO.sub.2, ZnO, CuO or Ta.sub.2O.sub.5. In some embodiments, the material of the second hydrogen blocking material layer **112** is the same as the material of the first hydrogen blocking material layer **111**. In some alternative embodiments, the material of the second hydrogen blocking material layer **112** is different from the material of the first hydrogen blocking material layer **111**.

(29) In some embodiments, the second hydrogen blocking material layer **112** may have a thickness that is greater than 200 Å. In detail, owing to having the thickness greater than 200 Å, the second hydrogen blocking layer **104b** formed from the second hydrogen blocking material layer **112** has good blocking ability for hydrogen-ions. In some embodiments, the thickness of the second hydrogen blocking material layer **112** is the same as the thickness of the first hydrogen blocking material layer **111**. In some alternative embodiments, the thickness of the second hydrogen blocking material layer **112** is different from the thickness of the first hydrogen blocking material layer **111**.

(30) In some embodiments, the second hydrogen blocking material layer **112** may be formed with a deposition process, such as ALD or PVD. In detail, the second hydrogen blocking material layer **112** is formed with ALD, thereby the second hydrogen blocking material layer **112** is dense enough for the second hydrogen blocking layer **104b** formed from the second hydrogen blocking material layer **112** to have good blocking ability for hydrogen-ions. Moreover, the second hydrogen blocking material layer **112** is formed with PVD, thereby there is no additional hydrogen-ions from

the second hydrogen blocking material layer **112**.

(31) Continue referring to FIG. 3D, a second photolithography step is performed to form a second photoresist layer PR2 on the second hydrogen blocking material layer **112**. In other words, the second hydrogen blocking material layer **112** is located between the second photoresist layer PR2 and the second electrode **103**, and between the second photoresist layer PR2 and the piezoelectric material layer **109**. In some embodiments, the second photolithography step for forming the second photoresist layer PR2 may include the following steps of coating a photoresist material on the second hydrogen blocking material layer **112**, exposing the photoresist material with a photolithography mask (or called photomask), and developing the exposed photoresist material. In some embodiments, the second photoresist layer PR2 includes a positive photoresist material which is photo-solubilized when exposed to light. In some alternative embodiments, the second photoresist layer PR2 includes a negative photoresist material.

(32) Referring to FIG. 3D and FIG. 3E, a second etching step is performed to the second hydrogen blocking material layer **112** and the piezoelectric material layer **109** by using the second photoresist layer PR2 as an etch mask, such that the second hydrogen blocking material layer **112** and the piezoelectric material layer **109** are etched to form the second hydrogen blocking layer **104b** and the piezoelectric layer **102**, and the portions of the first conductive layer **108** that are not covered by the second hydrogen blocking layer **104b** and the piezoelectric layer **102** are exposed. In other words, the second hydrogen blocking material layer **112** and the piezoelectric material layer **109** are simultaneously patterned by using the same mask to form the second hydrogen blocking layer **104b** and the piezoelectric layer **102**. That is to say, the second hydrogen blocking layer **104b** and the piezoelectric layer **102** have substantially identical layout. In some embodiments, the second etching step is an ion-beam etching step used to pattern the second hydrogen blocking material layer **112** and the piezoelectric material layer **109** in a single patterning process. In detail, in some embodiments, during the ion-beam etching step, there is substantially no etching selectivity between the second hydrogen blocking material layer **112** and the piezoelectric material layer **109**, which means that the etching rate ratio of the material of the second hydrogen blocking material layer **112** to the material of the piezoelectric material layer **109** is substantially 1. It is noted that, as the second hydrogen blocking material layer **112** is formed between the second photoresist layer PR2 and the second electrode **103**, and between the second photoresist layer PR2 and the piezoelectric material layer **109**, during the second etching step, the hydrogen-ions in the second photoresist layer PR2 are barred from penetrating into the second electrode **103** and the piezoelectric layer **102** by the second hydrogen blocking layer **104b**.

(33) As shown in FIG. 3E, the second hydrogen blocking layer **104b** is located between the second photoresist layer PR2 and the first hydrogen blocking layer **104a**, between the second photoresist layer PR2 and the second electrode **103**, and between the second photoresist layer PR2 and the piezoelectric layer **102**. In detail, the second hydrogen blocking layer **104b** is formed to physically contact the first hydrogen blocking layer **104a** at the top surface and the sidewall of the first hydrogen blocking layer **104a**, physically contact the second electrode **103** at the sidewall of the second electrode **103**, and physically contact the piezoelectric layer **102** at the top surface of the piezoelectric layer **102**. In addition, as shown in the cross-section of FIG. 3E, the sidewall of the piezoelectric layer **102** is laterally shifted from the sidewall of the second electrode **103**. In detail, the sidewall of the piezoelectric layer **102** is laterally shifted outward from the sidewall of the second electrode **103**. In other words, in the cross-section of FIG. 3E, the width of the piezoelectric layer **102** is greater than the width of the second electrode **103**. Specifically, as shown in the cross-section of FIG. 3E, the second electrode **103** and the piezoelectric layer **102** constitute a stacked structure having stepped sidewalls at both sides. Moreover, as shown in FIG. 3E, the second electrode **103** covers a part of the piezoelectric layer **102**, thereby the top surface of the piezoelectric layer **102** which is contacted with the second hydrogen blocking layer **104b** is uncovered by the second electrode **103**. From another point of view, as from the top view of FIG. 1,

the boundary of the second electrode **103** is within the boundary of the piezoelectric layer **102**. The other details of the second hydrogen blocking layer **104b** and the piezoelectric layer **102** have been described above, and will not be iterated herein.

(34) Referring to FIG. 3E and FIG. 3F, after the second hydrogen blocking layer **104b** and the piezoelectric layer **102** are formed, the second photoresist layer PR2 is removed. In some embodiments, the second photoresist layer PR2 may be removed by a stripping process, such as a dry stripping process, a wet stripping process or a combination thereof. As mentioned above, since the second hydrogen blocking layer **104b** is located between the second photoresist layer PR2 and the second electrode **103**, and between the second photoresist layer PR2 and the piezoelectric layer **102**, during the stripping process of the second photoresist layer PR2, the second hydrogen blocking layer **104b** helps prevent the hydrogen-ions in the second photoresist layer PR2 from penetrating into the second electrode **103** and the piezoelectric layer **102**.

(35) Still referring to FIG. 3F, a third hydrogen blocking material layer **113** is formed on the second hydrogen blocking layer **104b** and the piezoelectric layer **102**. In addition, the third hydrogen blocking material layer **113** is formed on the portions of the first conductive layer **108** that are not covered by the second hydrogen blocking layer **104b** and the piezoelectric layer **102**. In some embodiments, the third hydrogen blocking material layer **113** is a conformal layer. In detail, the third hydrogen blocking material layer **113** conformally and completely covers the top surface and the sidewall of the second hydrogen blocking layer **104b**, the sidewall of the piezoelectric layer **102**, and the portions of the first conductive layer **108** that are not covered by the second hydrogen blocking layer **104b** and the piezoelectric layer **102**. However, the disclosure is not limited thereto. In some alternative embodiments, the third hydrogen blocking material layer **113** is not a conformal layer.

(36) In some embodiments, the material of the third hydrogen blocking material layer **113** may include a metal oxide. Examples of the metal oxide may include Al_2O_3 , TiO_2 , Fe_2O_3 , ZrO_2 , ZnO , CuO or Ta_2O_5 . In some embodiments, the material of the third hydrogen blocking material layer **113** is the same as the material of the second hydrogen blocking material layer **112** and the material of the first hydrogen blocking material layer **111**. In some alternative embodiments, the material of the third hydrogen blocking material layer **113** is different from at least one of the material of the second hydrogen blocking material layer **112** and the material of the first hydrogen blocking material layer **111**. That is to say, the material of the third hydrogen blocking material layer **113** and the material of the second hydrogen blocking material layer **112** are the same or not the same, and the material of the third hydrogen blocking material layer **113** and the material of the first hydrogen blocking material layer **111** are the same or not the same.

(37) In some embodiments, the third hydrogen blocking material layer **113** may have a thickness that is greater than 200 Å. In detail, owing to having the thickness greater than 200 Å, the third hydrogen blocking layer **104c** formed from the third hydrogen blocking material layer **113** has good blocking ability for hydrogen-ions. In some embodiments, the thickness of the third hydrogen blocking material layer **113** is the same as the thickness of the second hydrogen blocking material layer **112** and the thickness of the first hydrogen blocking material layer **111**. In some alternative embodiments, the thickness of the third hydrogen blocking material layer **113** is different from at least one of the thickness of the second hydrogen blocking material layer **112** and the thickness of the first hydrogen blocking material layer **111**. That is to say, the thickness of the third hydrogen blocking material layer **113** and the thickness of the second hydrogen blocking material layer **112** are the same or not the same, and the thickness of the third hydrogen blocking material layer **113** and the thickness of the first hydrogen blocking material layer **111** are the same or not the same.

(38) In some embodiments, the third hydrogen blocking material layer **113** may be formed with a deposition process, such as ALD or PVD. In detail, the third hydrogen blocking material layer **113** is formed with ALD, thereby the third hydrogen blocking material layer **113** is dense enough for

the third hydrogen blocking layer **104c** formed from the third hydrogen blocking material layer **113** to have good blocking ability for hydrogen-ions. Moreover, the third hydrogen blocking material layer **113** is formed with PVD, thereby there is no additional hydrogen-ions from the third hydrogen blocking material layer **113**.

(39) Continue referring to FIG. 3F, a third photolithography step is performed to form a third photoresist layer PR3 on the third hydrogen blocking material layer **113**. In other words, the third hydrogen blocking material layer **113** is located between the third photoresist layer PR3 and the piezoelectric layer **102**, and between the third photoresist layer PR3 and the first conductive layer **108**. In some embodiments, the third photolithography step for forming the third photoresist layer PR3 may include the following steps of coating a photoresist material on the third hydrogen blocking material layer **113**, exposing the photoresist material with a photolithography mask (or called photomask), and developing the exposed photoresist material. In some embodiments, the third photoresist layer PR3 includes a positive photoresist material which is photo-solubilized when exposed to light. In some alternative embodiments, the third photoresist layer PR3 includes a negative photoresist material.

(40) Referring to FIG. 3F and FIG. 3G, a third etching step is performed to the third hydrogen blocking material layer **113** and the first conductive layer **108** by using the third photoresist layer PR3 as an etch mask, such that the third hydrogen blocking material layer **113** and the first conductive layer **108** are etched to form the third hydrogen blocking layer **104c** and the first electrode **101**, and the portions of the substrate **100** that are not covered by the third hydrogen blocking layer **104c** and the first electrode **101** are exposed. In other words, the third hydrogen blocking material layer **113** and the first conductive layer **108** are simultaneously patterned by using the same mask to form the third hydrogen blocking layer **104c** and the first electrode **101**. That is to say, the third hydrogen blocking layer **104c** and the first electrode **101** have substantially identical layout. In some embodiments, the third etching step is an ion-beam etching step used to pattern the third hydrogen blocking material layer **113** and the first conductive layer **108** in a single patterning process. In detail, in some embodiments, during the ion-beam etching step, there is substantially no etching selectivity between the third hydrogen blocking material layer **113** and the first conductive layer **108**, which means that the etching rate ratio of the material of the third hydrogen blocking material layer **113** to the material of the first conductive layer **108** is substantially 1. It is noted that, as the third hydrogen blocking material layer **113** is formed between the third photoresist layer PR3 and the piezoelectric layer **102**, and between the third photoresist layer PR3 and the first conductive layer **108**, during the third etching step, the third hydrogen blocking layer **104c** helps prevent the hydrogen-ions in the third photoresist layer PR3 from penetrating into the piezoelectric layer **102** and the first electrode **101**.

(41) As shown in FIG. 3G, the third hydrogen blocking layer **104c** is located between the third photoresist layer PR3 and the second hydrogen blocking layer **104b**, between the third photoresist layer PR3 and the piezoelectric layer **102**, and between the third photoresist layer PR3 and the first electrode **101**. In detail, the third hydrogen blocking layer **104c** is formed to physically contact the second hydrogen blocking layer **104b** at the top surface and the sidewall of the second hydrogen blocking layer **104b**, physically contact the piezoelectric layer **102** at the sidewall of the piezoelectric layer **102**, and physically contact the first electrode **101** at the top surface of the first electrode **101**. In addition, as shown in the cross-section of FIG. 3G, the sidewall of the first electrode **101** is laterally shifted from the sidewall of the piezoelectric layer **102**. In detail, the sidewall of the first electrode **101** is laterally shifted outward from the sidewall of the piezoelectric layer **102**. In other words, in the cross-section of FIG. 3G, the width of the first electrode **101** is greater than the width of the piezoelectric layer **102**. Specifically, as shown in the cross-section of FIG. 3G, the piezoelectric layer **102** and the first electrode **101** constitute a stacked structure having stepped sidewalls at both sides. Moreover, as shown in FIG. 3G, the piezoelectric layer **102** covers a part of the first electrode **101**, thereby the top surface of the first electrode **101** which is contacted

with the third hydrogen blocking layer **104c** is uncovered by the piezoelectric layer **102**. From another point of view, as from the top view of FIG. **1**, the boundary of the piezoelectric layer **102** is within the boundary of the first electrode **101**. The other details of the third hydrogen blocking layer **104c** and the first electrode **101** have been described above, and will not iterated herein.

(42) After the first electrode **101** is formed, the formation of the metal-insulator-metal element MIM comprising the first electrode **101**, the piezoelectric layer **102** and the second electrode **103** is thus completed. In detail, as mentioned above, since the second electrode **103** and the piezoelectric layer **102** are formed to constitute a stacked structure having stepped sidewalls at both sides, and the piezoelectric layer **102** and the first electrode **101** are also formed to constitute a stacked structure having stepped sidewalls at both sides, the metal-insulator-metal element MIM comprising the first electrode **101**, the piezoelectric layer **102** and the second electrode **103** has a staircase shaped stacked-structure, as shown in the cross-section of FIG. **3G**.

(43) Furthermore, after the third hydrogen blocking layer **104c** is formed, the formation of the hydrogen blocking layer **104** comprising the first hydrogen blocking layer **104a**, the second hydrogen blocking layer **104b** and the third hydrogen blocking layer **104c** is thus completed. As shown in FIG. **3G**, the hydrogen blocking layer **104** covers and contacts the top surface of the second electrode **103**, and contacts a part of the top surface of the first electrode **101** and a part of the top surface of the piezoelectric layer **102**. In detail, the hydrogen blocking layer **104** physically contacts the metal-insulator-metal element MIM at the top surface and the sidewall of the second electrode **103**, the sidewall and a part of the top surface of the piezoelectric layer **102**, and a part of the top surface of the first electrode **101**. Moreover, as shown in FIG. **3G**, the thickness of the hydrogen blocking layer **104** that is located on and contacts the top surface of the second electrode **103** is greater than the thickness of the hydrogen blocking layer **104** that is located on and contacts the top surface of the piezoelectric layer **102**, and the thickness of the hydrogen blocking layer **104** that is located on and contacts the top surface of the piezoelectric layer **102** is greater than the thickness of the hydrogen blocking layer **104** that is located on and contacts the top surface of the first electrode **101**.

(44) Referring to FIG. **3G** and FIG. **3H**, after the third hydrogen blocking layer **104c** and the first electrode **101** are formed, the third photoresist layer PR3 is removed. In some embodiments, the third photoresist layer PR3 may be removed by a stripping process, such as a dry stripping process, a wet stripping process or a combination thereof. As mentioned above, since the third hydrogen blocking layer **104c** is located between the third photoresist layer PR3 and the piezoelectric layer **102**, and between the third photoresist layer PR3 and the first electrode **101**, during the stripping process of the third photoresist layer PR3, the third hydrogen blocking layer **104c** helps prevent the hydrogen-ions in the third photoresist layer PR3 from penetrating into the piezoelectric layer **102** and the first electrode **101**.

(45) Still referring to FIG. **3H**, a passivation layer **105** is formed to cover the hydrogen blocking layer **104** and the metal-insulator-metal element MIM. In some embodiments, the passivation layer **105** may be formed with CVD, PVD, or any other suitable techniques. In some embodiments, the material of the passivation layer **105** may be a dielectric material, such as silicon oxide, silicon nitride, silicon oxynitride or a combination thereof. In some embodiments, the passivation layer **105** may has a thickness that is in a range from about 200 Å to about 2000 Å. Details of the passivation layer **105** have been described above, and will not iterated herein.

(46) Referring to FIG. **3H** and FIG. **3I**, the passivation layer **105** and the hydrogen blocking layer **104** are patterned to form a first contact hole H1 and a second contact hole H2 for exposing a contact portion P1 of the first electrode **101** and a contact portion P2 of the second electrode **103**. In detail, as shown in FIG. **3I**, the first contact hole H1 is formed in the passivation layer **105** and the third hydrogen blocking layer **104c**, and the second contact hole H2 is formed in the passivation layer **105**, the first hydrogen blocking layer **104a**, the second hydrogen blocking layer **104b** and the third hydrogen blocking layer **104c**. In some embodiments, the first contact hole H1 and the second

contact hole H2 may be formed by performing photolithography and etching processes.

(47) Then, referring back to FIG. 2, a first contact terminal **106** is formed on the passivation layer **105** to be electrically connected to the first electrode **101** through the first contact hole H1, and a second contact terminal **107** is formed on the passivation layer **105** to be electrically connected to the second electrode **103** through the second contact hole H2. In detail, the first contact terminal **106** is formed to be electrically connected to the contact portion P1 of the first electrode **101**, and the second contact terminal **107** is formed to be electrically connected to the contact portion P2 of the second electrode **103**. In some embodiments, the materials of the first contact terminal **106** and the second contact terminal **107** may respectively include, but not limited to, silver (Ag), titanium (Ti), tantalum (Ta), ruthenium (Ru), aluminum (Al), copper (Cu), gold (Au), or a combination thereof, or the like. So far, the manufacture of the piezoelectric device **10** according to some embodiments is completed. The first contact terminal **106** and the second contact terminal **107** provide the input/output terminals for receiving the electrical voltage for controlling the physical displacement of the piezoelectric device **10**. Details of the first contact terminal **106** and the second contact terminal **107** have been described above, and will not iterated herein.

(48) In the above-mentioned embodiments shown in FIG. 3A to FIG. 3I, since before each photoresist layer utilized as an etch mask for forming the metal-insulator-metal element MIM (i.e., the first photoresist layer PR1, the second photoresist layer PR2, the third photoresist layer PR3) is formed, the corresponding hydrogen blocking material layer (i.e., the first hydrogen blocking material layer **111**, the second hydrogen blocking material layer **112**, the third hydrogen blocking material layer **113**) is already formed, the hydrogen-ions in the photoresist layer are barred from penetrating into the metal-insulator-metal element MIM during the etching process and the striping process by the corresponding hydrogen blocking material layer. From another point of view, since the hydrogen blocking layer **104** includes the first hydrogen blocking layer **104a**, the second hydrogen blocking layer **104b** and the third hydrogen blocking layer **104c**, the first hydrogen blocking layer **104a** is formed to covers and contacts the top surface of the second electrode **103**, the second hydrogen blocking layer **104b** is formed to covers the second electrode **103** and contacts the top surface of the piezoelectric layer **102**, and the third hydrogen blocking layer **104c** is formed to covers the second electrode **103** and the piezoelectric layer **102** and contacts the top surface of the first electrode **101**, during the manufacture of the piezoelectric device **10**, each of the first hydrogen blocking layer **104a**, the second hydrogen blocking layer **104b** and the third hydrogen blocking layer **104c** helps prevent the hydrogen-ions of the photoresist layer from penetrating into the metal-insulator-metal element MIM. Based on the above discussion, it is noted that owing to arranging the hydrogen blocking layer **104**, the amount of the hydrogen-ions existing in the metal-insulator-metal element MIM of the piezoelectric device **10** can be reduced, and the reliability of the piezoelectric device **10** can be improved.

(49) When compared with the piezoelectric device without the hydrogen blocking layer, due to the arrangement of the additional hydrogen blocking layer, the amount of the hydrogen-ions included in the metal-insulator-metal element MIM of the piezoelectric device is reduced by about 50%.

(50) Moreover, during the reliability test under the same conditions, when compared with the failure rate of more than 50% for the piezoelectric device without the hydrogen blocking layer, the piezoelectric device designed with at least one additional hydrogen blocking layer based on certain previous embodiments has a failure rate approaching zero. Furthermore, the piezoelectric device designed with at least one additional hydrogen blocking layer based on certain previous embodiments offers a higher breakdown voltage. When compared with the piezoelectric device without the hydrogen blocking layer, a breakdown voltage difference equal to or greater than 20V can be observed. Based on the above results, through the arrangement of the hydrogen blocking layer in the piezoelectric device, the performance and reliability of the piezoelectric device can be significantly improved.

(51) In the embodiments of FIG. 1 and FIG. 2, the metal-insulator-metal element MIM has a

staircase shaped stacked-structure. However, the disclosure is not limited thereto. Possible modifications and alterations may be made to the configuration of the metal-insulator-metal element MIM. Such modifications and alterations will be described below with reference to FIG. 4 and FIG. 5, which are provided for illustration purposes, and are not construed as limiting the present disclosure.

(52) FIG. 4 is a schematic cross-sectional view illustrating a piezoelectric device in accordance with alternative embodiments. Referring to FIG. 4 and FIG. 2, the piezoelectric device **20a** of FIG. 4 is similar to the piezoelectric device **10** of FIG. 2 that taken along line A-A', hence the same reference numerals are used to refer to the same or liked parts, and its detailed description will be omitted herein. The differences between the piezoelectric device **20a** and the piezoelectric device **10** will be described below.

(53) Referring to FIG. 4, in the piezoelectric device **20a**, the sidewalls of the first electrode **101**, the piezoelectric layer **102** and the second electrode **103** are vertically aligned. Further, as shown in FIG. 4, the sidewall of the hydrogen blocking layer **104** is vertically aligned with the sidewalls of the first electrode **101**, the piezoelectric layer **102** and the second electrode **103**. From another point of view, in the piezoelectric device **20a**, the hydrogen blocking layer **104** is disposed right above the second electrode **103** and physically contacts the metal-insulator-metal element MIM at the top surface of the second electrode **103**. In detail, as shown in FIG. 4, the hydrogen blocking layer **104** physically contacts the second electrode **103** at the top surface of the second electrode **103**, and does not physically contact the piezoelectric layer **102** and the first electrode **101**. In some embodiments, as shown in FIG. 4, the hydrogen blocking layer **104** is a single layer. However, the disclosure is not limited thereto. In some alternative embodiments, the hydrogen blocking layer **104** of the piezoelectric device **20a** is a multilayer structure.

(54) FIG. 5 is a schematic cross-sectional view illustrating a piezoelectric device in accordance with alternative embodiments. Referring to FIG. 5 and FIG. 4, the piezoelectric device **20b** of FIG. 5 is similar to the piezoelectric device **20a** of FIG. 4, and the main difference between them lies in that, in the piezoelectric device **20b**, the sidewalls of the first electrode **101**, the piezoelectric layer **102** and the second electrode **103** are tilted sidewalls; while in the piezoelectric device **20a**, the sidewalls of the first electrode **101**, the piezoelectric layer **102** and the second electrode **103** are vertically aligned. That is to say, in the piezoelectric device **20b**, the metal-insulator-metal element MIM has a taper profile. Further, as shown in FIG. 5, the sidewall of the hydrogen blocking layer **104** is also a tilted sidewall. In some embodiments, an angle θ between the tilted sidewall of each of the first electrode **101**, the piezoelectric layer **102**, the second electrode **103** and the hydrogen blocking layer **104** and the normal direction (illustrated by a dash line shown in FIG. 5) of the substrate **100** may range from greater than 0° to about 40° . In some embodiments, the method of forming the metal-insulator-metal element MIM having a taper profile of the piezoelectric device **20b** may include the step of adjusting the incidence angle of the ion beam during the ion-beam etching step with respect to the normal direction of the substrate **100**.

(55) FIG. 6A and FIG. 6B are schematic views illustrating one exemplary application of the piezoelectric device in accordance with some embodiments. Referring to FIG. 6A and FIG. 6B, two piezoelectric devices **1000** are used for controlling a variable focus optical system. It is noted that the piezoelectric device **1000** may be implemented by using the piezoelectric device **10**, piezoelectric device **20a** or piezoelectric device **20b** in the above-mentioned embodiments. Moreover, the number and the type(s) of the piezoelectric devices **1000** illustrated in FIG. 6A and FIG. 6B are merely for illustrative purposes, and the disclosure is not limited thereto. In some alternative embodiments, one piezoelectric device **1000** or more than two piezoelectric devices **1000** may be used for controlling a variable focus optical system.

(56) As shown in FIG. 6A and FIG. 6B, the variable focus optical system includes a glass carrier **2000**, a glass thin membrane **2004** and a transparent polymer **2002**. The piezoelectric devices **1000** are disposed on the glass thin membrane **2004**. The transparent polymer **2002** with well-defined

optical index may be used to fill up the space between the glass carrier **2000** and the glass thin membrane **2004**. As mentioned above, when a voltage is applied to the piezoelectric devices **1000**, the piezoelectric layer of each piezoelectric device **1000** can stretch or compress to provide a physical displacement in a direction normal to the surface of the glass thin membrane **2004**. As a result, each piezoelectric device **1000** forces the glass thin membrane **2004** so as to change the position of the glass thin membrane **2004** and/or the shape of the glass thin membrane **2004**. That is, the piezoelectric device **1000** may function as an actuator. As shown in FIG. **6B**, the piezoelectric devices **1000** force the glass thin membrane **2004** to bend accordingly. At this time, a beam of light L, after passing through the glass carrier **2000**, the transparent polymer **2002** and the glass thin membrane **2004**, gets focused at a focus point F, as shown in FIG. **6B**. It is noted that since the amount of the physical displacement generally depends upon the voltage applied to the piezoelectric device, by adjusting the magnitude of the applied voltage, the position of the focus point F will change. Furthermore, when the piezoelectric devices **1000** are in standby mode, no force is applied to the glass thin membrane **2004**, thereby a beam of light L passes through the glass carrier **2000**, the transparent polymer **2002** and the glass thin membrane **2004** without deviation, as shown in FIG. **6A**.

(57) In some embodiments, the variable focus optical system may be comprised within a package of a semiconductor chip having one or more image sensors. For example, in some embodiments, the variable focus optical system may be configured to focus light onto an integrated chip having one or more image sensing devices (e.g., CMOS image sensors, CCD image sensors). It will be appreciated that the variable focus optical system shown in FIG. **6A** and FIG. **6B** is merely one example showing possible applications of the piezoelectric device **1000**. People skilled in the art can understand other possible applications of the piezoelectric device **1000**.

(58) In accordance with some embodiments of the present disclosure, a piezoelectric device including a substrate, a metal-insulator-metal element, a hydrogen blocking layer, a passivation layer, a first contact terminal and a second contact terminal is provided. The metal-insulator-metal element is disposed on the substrate. The hydrogen blocking layer is disposed on the metal-insulator-metal element. The passivation layer covers the hydrogen blocking layer and the metal-insulator-metal element. The first contact terminal is electrically connected to the metal-insulator-metal element. The second contact terminal is electrically connected to the metal-insulator-metal element.

(59) In accordance with alternative embodiments of the present disclosure, a piezoelectric device including a substrate, a first electrode, a piezoelectric layer, a second electrode, a hydrogen blocking layer, a passivation layer, a first contact terminal and a second contact terminal is provided. The first electrode is disposed on the substrate. The piezoelectric layer is disposed on the first electrode. The second electrode is disposed on the piezoelectric layer. The hydrogen blocking layer is disposed on the second electrode and over the substrate. The passivation layer covers the hydrogen blocking layer, the second electrode, the piezoelectric layer and the first electrode. The first contact terminal is electrically connected to the first electrode. The second contact terminal is electrically connected to the second electrode.

(60) In accordance with yet alternative embodiments of the present disclosure, a method of forming a piezoelectric device including at least the following steps is provided. A first conductive layer, a piezoelectric material layer and a second conductive layer are sequentially formed on a substrate. A first hydrogen blocking material layer is formed on the second conductive layer. The first hydrogen blocking material layer is patterned to form a first hydrogen blocking layer. A passivation layer is formed to cover the first hydrogen blocking layer.

(61) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages

of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A piezoelectric device, comprising: a substrate; a metal-insulator-metal element disposed on the substrate, wherein the metal-insulator-metal element comprises a bottom electrode, a top electrode and a piezoelectric layer between the top electrode and the bottom electrode; a hydrogen blocking layer covering the metal-insulator-metal element, wherein the hydrogen blocking layer includes a first hydrogen blocking layer, a second hydrogen blocking layer and a third hydrogen blocking layer sequentially stacked on the substrate, the first hydrogen blocking layer contacts a top surface of the top electrode, the second hydrogen blocking layer contacts a top surface of the piezoelectric layer and a sidewall of the top electrode, and the third hydrogen blocking layer contacts a top surface of the bottom electrode and a sidewall of the piezoelectric layer; a passivation layer covering the hydrogen blocking layer and the metal-insulator-metal element; a first contact terminal electrically connected to the metal-insulator-metal element; and a second contact terminal electrically connected to the metal-insulator-metal element.
2. The piezoelectric device of claim 1, wherein a material of the piezoelectric layer comprises lead zirconate titanate.
3. The piezoelectric device of claim 1, wherein the second hydrogen blocking layer contacts a sidewall of the first hydrogen blocking layer.
4. The piezoelectric device of claim 1, wherein in a top view, a span of the bottom electrode is greater than a span of the piezoelectric layer, and a span of the piezoelectric layer is greater than a span of the top electrode.
5. The piezoelectric device of claim 1, wherein a material of the hydrogen blocking layer comprises Al.sub.2O.sub.3 , TiO.sub.2 , Fe.sub.2O.sub.3 , ZrO.sub.2 , ZnO , CuO or Ta.sub.2O.sub.5 .
6. A piezoelectric device, comprising: a substrate; a bottom electrode disposed on the substrate; a piezoelectric layer disposed on the bottom electrode and exposing a portion of a top surface of the bottom electrode; a top electrode disposed on the piezoelectric layer and exposing a portion of a top surface of the piezoelectric layer; a hydrogen blocking layer disposed on the top electrode and over the substrate, wherein the hydrogen blocking layer comprises a first hydrogen blocking layer, a second hydrogen blocking layer and a third hydrogen blocking layer, the second hydrogen blocking layer is between the first hydrogen blocking layer and the third hydrogen blocking layer, a sidewall of the first hydrogen blocking layer is aligned with a sidewall of the top electrode, a sidewall of the second hydrogen blocking layer is aligned with a sidewall of the piezoelectric layer, and a sidewall of the third hydrogen blocking layer is aligned with a sidewall of the bottom electrode; a passivation layer covering the hydrogen blocking layer, the top electrode, the piezoelectric layer and the bottom electrode; a first contact terminal contacting the bottom electrode; and a second contact terminal contacting the top electrode.
7. The piezoelectric device of claim 6, wherein the first hydrogen blocking layer is disposed right above the top electrode and physically contacts the top electrode at a top surface of the top electrode.
8. The piezoelectric device of claim 7, the sidewalls of the top electrode, the piezoelectric layer and the bottom electrode are tilted sidewalls.
9. The piezoelectric device of claim 7, wherein the sidewalls of the top electrode, the piezoelectric layer and the bottom electrode are vertically aligned.
10. The piezoelectric device of claim 6, wherein in a top view, shapes of the top electrode, the piezoelectric layer and the bottom electrode are arranged as concentric circles.

11. The piezoelectric device of claim 6, wherein materials of the first hydrogen blocking layer, the second hydrogen blocking layer and the third hydrogen blocking layer are the same.
 12. The piezoelectric device of claim 6, wherein in a cross-section, the bottom electrode, the piezoelectric layer and the top electrode constitute a staircase shaped stacked-structure.
 13. The piezoelectric device of claim 6, wherein the passivation layer and the hydrogen blocking layer have a first contact hole and a second contact hole, the first contact terminal is electrically connected to the bottom electrode through the first contact hole, and the second contact terminal is electrically connected to the top electrode through the second contact hole.
 14. The piezoelectric device of claim 6, wherein a material of the hydrogen blocking layer comprises Al.sub.2O.sub.3 , TiO.sub.2 , Fe.sub.2O.sub.3 , ZrO.sub.2 , ZnO , CuO or Ta.sub.2O.sub.5 .
 15. The piezoelectric device of claim 6, wherein at least one of the first hydrogen blocking material layer, the second hydrogen blocking material layer and the third hydrogen blocking material layer has a thickness that is greater than 200 Å.
 16. A method of forming a piezoelectric device, comprising: sequentially forming a first conductive layer, a piezoelectric material layer and a second conductive layer on a substrate; forming a first hydrogen blocking material layer on the second conductive layer; removing portions of the first hydrogen blocking material layer and the second conductive layer in a first patterning process to form a first hydrogen blocking layer and a top electrode; forming a second hydrogen blocking material layer on the first hydrogen blocking layer; removing portions of the second hydrogen blocking material layer and the piezoelectric material layer in a second patterning process to form a second hydrogen blocking layer and a piezoelectric layer; forming a third hydrogen blocking material layer on the piezoelectric layer and on the second hydrogen blocking layer; and removing portions of the third hydrogen blocking material layer and the first conductive layer in a third patterning process to form a third hydrogen blocking layer and a bottom electrode.
 17. The method of claim 16, wherein: the first hydrogen blocking layer contacts a top surface of the top electrode, the second hydrogen blocking layer covers the first hydrogen blocking layer and contacts a top surface of the piezoelectric layer, and the third hydrogen blocking layer covers the second hydrogen blocking layer and contacts a top surface of the bottom electrode.
 18. The method of claim 16, wherein the piezoelectric material layer is formed by PVD or a sol-gel process.
 19. The method of claim 16, wherein at least one of the first hydrogen blocking material layer, the second hydrogen blocking material layer and the third hydrogen blocking material layer is formed by atomic layer deposition (ALD) or physical vapor deposition (PVD).
 20. The method of claim 16, wherein at least one of removing the portions of the first hydrogen blocking material layer and the second conductive layer, removing the portions of the second hydrogen blocking material layer and the piezoelectric material layer, and removing the portions of the third hydrogen blocking material layer and the first conductive layer includes using an ion-beam etching step.
-