

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250281872

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Adhikari; Birendra et al.

CARBON DIOXIDE SELECTIVE MEMBRANES, GAS SEPARATION SYSTEMS INCLUDING THE CARBON DIOXIDE SELECTIVE MEMBRANES, AND RELATED METHODS

Abstract

A carbon dioxide (CO.sub.2) selective membrane is disclosed and comprises a support and a selective structure comprising poly [bis(methoxy ethoxy) ethoxy]phosphazene] (MEEP) on the support. The CO.sub.2 selective membrane exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1. A gas separation system comprising one or more CO.sub.2 selective membranes and related methods are also disclosed.

Inventors: Adhikari; Birendra (Ammon, ID), Orme; Christopher J. (Firth, ID), Klaehn; John R. (Idaho Falls, ID), McNally; Joshua S. (Idaho Falls, ID), Stewart; Frederick F. (Idaho Falls, ID), Lee; Hyeonseok (Ammon, ID)

Applicant: Battelle Energy Alliance, LLC (Idaho Falls, ID)

Family ID: 88731150

Appl. No.: 18/863585

Filed (or PCT Filed): May 12, 2023

PCT No.: PCT/US2023/066970

Related U.S. Application Data

us-provisional-application US 63341837 20220513

Publication Classification

Int. Cl.: B01D53/22 (20060101); B01D69/02 (20060101); B01D69/08 (20060101); B01D69/10 (20060101); B01D71/58 (20060101); C01B32/50 (20170101)

U.S. Cl.:

CPC B01D53/228 (20130101); B01D53/226 (20130101); B01D53/227 (20130101); B01D69/02 (20130101); B01D69/08 (20130101); B01D69/107 (20220801); B01D71/58 (20130101); C01B32/50 (20170801); B01D2256/22 (20130101); B01D2257/102 (20130101); B01D2325/02832 (20220801); B01D2325/02833 (20220801)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS [0001] This application is a national phase entry under 35 U.S.C. § 371 of International Patent Application PCT/US2023/066970, filed May 12, 2023, designating the United States of America and published as International Patent Publication WO 2023/220743 A1 on Nov. 16, 2023, which claims the benefit under Article 8 of the Patent Cooperation Treaty of U.S. Patent Application Ser. No. 63/341,837, filed May 13, 2022.

TECHNICAL FIELD

[0003] Embodiments of the disclosure relate to gas separation membranes, gas separation systems, and methods for capturing carbon dioxide (CO.sub.2). More specifically, embodiments of the disclosure relate to CO.sub.2 selective membranes for capturing carbon dioxide and related gas separation systems and methods.

BACKGROUND

[0004] Increases in global energy demand have led to increases in the combustion of coal, natural gas, and fossil fuels, leading to a concomitant increase in carbon dioxide (CO.sub.2) emissions. Existing industrial manufacturing infrastructure is designed to use coal, natural gas, and fossil fuels (electricity from non-renewable sources) as the primary energy source. However, concerns over adverse effects on the environment due to the presence of CO.sub.2 in the atmosphere have driven efforts to capture and/or sequester CO.sub.2 from the atmosphere. Carbon capture is the enrichment of CO.sub.2 from various sources, storing the CO.sub.2 permanently or using it for enhanced oil recovery or making fuels and chemicals such as syn gas, butanol, methanol, ethanol, and dimethyl ether. By doing this, the CO.sub.2 is restricted from going back into the atmosphere.

[0005] Membranes have been investigated to capture CO.sub.2 from CO.sub.2-containing streams. Conventional membranes for CO.sub.2 capture operate effectively at higher CO.sub.2 concentrations, but are not effective for CO.sub.2-containing streams containing lower concentrations of CO.sub.2. The effectiveness of the conventional membranes drops with decreasing CO.sub.2 concentration. In addition, manufacturing defects in the conventional membranes significantly affect the selectivity for CO.sub.2 at lower CO.sub.2 concentrations. Membrane-based separation processes are also expensive, due to the high costs of the membranes and of installation of systems including the membranes. In addition, electricity is used to run the membrane-based systems, adding to the overall cost. Therefore, capturing CO.sub.2 from streams containing lower concentrations of CO.sub.2 is expensive.

BRIEF SUMMARY

[0006] A carbon dioxide (CO.sub.2) selective membrane is disclosed and comprises a support and a selective structure comprising poly[bis((methoxyethoxy)ethoxy)phosphazene] (MEEP) on the support. The CO.sub.2 selective membrane exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1.

[0007] A gas separation system is also disclosed and comprises a housing and one or more

CO.sub.2 selective membranes contained within the housing. The one or more CO.sub.2 selective membranes comprises a support and a selective structure comprising MEEP on the support, wherein the CO.sub.2 selective membrane exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1.

[0008] A method of capturing CO.sub.2 comprises introducing a source stream containing CO.sub.2 at a concentration of less than about 10% by weight to a first chamber of a gas separation system, transporting the CO.sub.2 through the CO.sub.2 selective membrane and to a second chamber of the gas separation system, and recovering the CO.sub.2 from the second chamber of the gas separation system. The second chamber is in fluid communication with the first chamber. The gas separation system comprises one or more CO.sub.2 selective membranes and the one or more CO.sub.2 selective membranes comprise a support and a selective structure comprising MEEP on the support. The one or more CO.sub.2 selective membranes exhibit a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] FIG. 1 is a simplified cross-sectional view of a carbon dioxide selective membrane in accordance with embodiments of the disclosure;

[0010] FIG. 2 is a simplified schematic view of a gas separation system in accordance with embodiments of the disclosure;

[0011] FIG. 3 is a scanning electron microscopy (SEM) image of a carbon dioxide selective membrane in accordance with embodiments of the disclosure;

[0012] FIG. 4 is a graph showing CO.sub.2 permeability as a function of temperature for carbon dioxide selective membranes in accordance with embodiments of the disclosure using pure gases;

[0013] FIG. 5 is a graph showing CO.sub.2 selectivity as a function of temperature for carbon dioxide selective membranes in accordance with embodiments of the disclosure using pure gases;

[0014] FIG. 6 is a graph showing CO.sub.2 permeability as a function of temperature for carbon dioxide selective membrane in accordance with embodiments of the disclosure using 1% CO.sub.2 in N.sub.2;

[0015] FIG. 7 is a graph showing CO.sub.2 selectivity as a function of temperature for carbon dioxide selective membranes in accordance with embodiments of the disclosure using 1% CO.sub.2 in N.sub.2; and

[0016] FIG. 8 is a graph showing CO.sub.2/N.sub.2 selectivity as a function of CO.sub.2 permeability for carbon dioxide selective membranes in accordance with embodiments of the disclosure.

DETAILED DESCRIPTION

[0017] Carbon dioxide selective membranes (CO.sub.2 selective membranes), gas separation systems, and methods for capturing and concentrating CO.sub.2 from a source stream are disclosed. The CO.sub.2 selective membranes, gas separation systems, and methods are used to effectively and inexpensively capture (e.g., remove) and concentrate the CO.sub.2 from the source stream, which contains a relatively low concentration of CO.sub.2. The CO.sub.2 selective membrane according to embodiments of the disclosure is a multiple layer structure that exhibits CO.sub.2 selectivity and permeability while also being durable and easy to manufacture. The CO.sub.2 selective membrane includes a support, and a selectivity structure on the support that is formed from and includes a material highly selective to CO.sub.2. The CO.sub.2 selective membrane is substantially free of defects and is also self-guttering, providing the ability to repair defects. Therefore, the CO.sub.2 selective membrane according to embodiments of the disclosure may be used to capture and enrich CO.sub.2 from a low concentration source stream that contains

[0018] The following description provides specific details, such as material compositions and processing conditions (e.g., temperatures, pressures, flow rates, etc.) in order to provide a thorough description of embodiments of the disclosure. However, a person of ordinary skill in the art will understand that the embodiments of the disclosure may be practiced without necessarily employing these specific details. Indeed, the embodiments of the disclosure may be practiced in conjunction with conventional systems and methods employed in the industry. In addition, only those system components and acts necessary to understand the embodiments of the disclosure are described in detail below. A person of ordinary skill in the art will understand that some system components (e.g., pipelines, line filters, valves, pumps, motors, temperature detectors, flow detectors, pressure detectors, and the like) are inherently disclosed herein and that adding various conventional system components and acts would be in accord with the disclosure. In addition, the drawings accompanying the disclosure are for illustrative purposes only, and are not meant to be actual views of any particular material, device, or system.

[0019] As used herein, spatially relative terms, such as “beneath,” “below,” “lower,” “bottom,” “above,” “upper,” “top,” “front,” “rear,” “left,” “right,” and the like, may be used for ease of description to describe one element's or feature's relationship to another element(s) or feature(s) as illustrated in the figures. Unless otherwise specified, the spatially relative terms are intended to encompass different orientations of the materials in addition to the orientation depicted in the figures. For example, if materials in the figures are inverted, elements described as “below” or “beneath” or “under” or “on bottom of” other elements or features would then be oriented “above” or “on top of” the other elements or features. Thus, the term “below” can encompass both an orientation of above and below, depending on the context in which the term is used, which will be evident to one of ordinary skill in the art. The materials may be otherwise oriented (e.g., rotated 90 degrees, inverted, flipped) and the spatially relative descriptors used herein interpreted accordingly.

[0020] As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0021] As used herein, “and/or” includes any and all combinations of one or more of the associated listed items.

[0022] As used herein, “about” or “approximately” in reference to a numerical value for a particular parameter is inclusive of the numerical value and a degree of variance from the numerical value that one of ordinary skill in the art would understand is within acceptable tolerances for the particular parameter. For example, “about” or “approximately” in reference to a numerical value may include additional numerical values within a range of from 90.0 percent to 110.0 percent of the numerical value, such as within a range of from 95.0 percent to 105.0 percent of the numerical value, within a range of from 97.5 percent to 102.5 percent of the numerical value, within a range of from 99.0 percent to 101.0 percent of the numerical value, within a range of from 99.5 percent to 100.5 percent of the numerical value, or within a range of from 99.9 percent to 100.1 percent of the numerical value.

[0023] As used herein, the term “compatible” means that a material does not undesirably react, decompose, or absorb another material, and also that the material does not undesirably impair the chemical and/or mechanical properties of the another material.

[0024] As used herein, the term “configured” refers to a size, shape, material composition, material distribution, and arrangement of one or more of at least one structure and at least one system facilitating operation of one or more of the structure and the system in a pre-determined way.

[0025] As used herein, the term “substantially” in reference to a given parameter, property, or condition means and includes to a degree that one of ordinary skill in the art would understand that the given parameter, property, or condition is met with a degree of variance, such as within acceptable manufacturing tolerances. By way of example, depending on the particular parameter, property, or condition that is substantially met, the parameter, property, or condition may be at least

90.0% met, at least 95.0% met, at least 99.0% met, or even at least 99.9% met.

[0026] A CO.sub.2 selective membrane **100** includes a support **104** and a selectivity structure **106**, as shown in FIG. **1**, with the selectivity structure **106** on one or more surfaces of the selectivity structure **106**. The CO.sub.2 selective membrane **100** is configured as a gas separation membrane and is formulated to selectively remove CO.sub.2 from a source stream that contains a low concentration of CO.sub.2. The support **104** is configured and formulated to exhibit a high porosity and a high gas throughput (e.g., gas permeability), as well as providing mechanical strength to the CO.sub.2 selective membrane **100**. The selectivity structure **106** may be configured and formulated to be highly selective to CO.sub.2 relative to other gaseous components of the source stream, such as nitrogen (N.sub.2), oxygen (O.sub.2), or a combination thereof. The CO.sub.2 selective membrane **100** may, for example, exhibit a CO.sub.2/N.sub.2 selectivity greater than about 40/1 and a CO.sub.2 permeability greater than about 450 Barrer. The CO.sub.2 selective membrane **100** may, optionally, include one or more additives, such as a filler. If present, the additive does not substantially degrade performance (e.g., CO.sub.2 selectivity and permeability) of the CO.sub.2 selective membrane **100**. Therefore, the CO.sub.2 selective membrane **100** may be configured as a multiple layer structure.

[0027] The support **104** is configured and formulated to exhibit a high porosity and a high gas permeability, as well as providing mechanical strength to the CO.sub.2 selective membrane **100**. The support **104** may be a substantially rigid material that provides support and stability to the selectivity structure **106**, which overlies the support **104**. The support **104** is of sufficient thickness to provide the support and stability to the selectivity structure **106**. By way of example only, the support **104** may be from about 0.7 mm to about 1.0 mm in thickness. The support **104** may also be substantially free of defects (e.g., pinholes) or may have a low level of defects.

[0028] Pores (not shown) may be homogeneously distributed throughout the support **104**, with a size of the pores sufficient for migration (e.g., selective transport) of CO.sub.2 therethrough while excluding other gaseous component(s) of the source stream from migrating therethrough. The pores (e.g., voids, apertures, openings, etc.) in the support **104** may be micropores that are appropriately sized to permit CO.sub.2 to traverse through the support **104**. By way of example only, the pores may be from about 0.005 μm to about 0.050 μm in diameter, such as from about 0.007 μm to about 0.040 μm , from about 0.008 μm to about 0.030 μm , from about 0.009 μm to about 0.020 μm , or from about 0.009 μm to about 0.015 μm , or from about 0.009 μm to about 0.012 μm . In some embodiments, the pores are about 0.01 μm in diameter. The pores may extend in tortuous (e.g., twisting, winding, etc.) paths throughout a thickness of the support **104** and/or may extend in substantially linear paths throughout a thickness of the support **104**.

[0029] The permeance of the support **104** may be greater than or equal to about 20,000 GPU, such as from about 30,000 GPU to about 50,000 GPU or from about 35,000 GPU to about 45,000 GPU. "Permeance" is measured in GPU, where membrane thickness is unknown or inconsistent, in contrast to "permeability," expressed in Barrers, where membrane thickness is substantially constant and known.

[0030] The support **104** may be configured as a substantially flat sheet, as shown in FIG. **1**, that exhibits the desired porosity and gas permeability. Alternatively, the support **104** may be configured as hollow fibers that exhibit the desired porosity and gas permeability. With the hollow fibers, both inner surfaces and outer surfaces of the support **104** are available for the selectivity structure **106** to be formed upon. Therefore, the support **104** containing the hollow fibers may provide an increased surface area for the selectivity structure **106** to be formed upon when compared to a surface area of the substantially flat sheet. The hollow fibers may include an inner diameter and an outer diameter, where the inner diameter is less than or equal to about one-half of the outer diameter. The outer diameter of the hollow fibers may be from about 200 μm to about 400 μm , such as from about 200 μm to about 400 μm or from about 180 μm to about 200 μm .

[0031] The support **104** may be formed of and include one or more of a polymer material, a metal

material, or a ceramic material that exhibits the desired porosity and gas permeability. By way of example only, the polymer material may be a polyolefin, such as a polyethylene (PE), a polypropylene, etc.; a polyamide; a polyphosphazene; a polysulfone; a fluorinated polymer, such as poly(terafluoroethylene) (PTFE), poly(vinylidene fluoride) (PVDF), etc.; a poly(ether ketone); a poly(ether ketone); a poly(ether sulfone) (PES); a polysiloxane (e.g., a polydimethylsiloxane (PDMS)); a silicone polymer; a cellulose acetate; etc., a polymeric composite material, or a combination thereof.

[0032] The support **104** may be formed of and include a metal material or a metal alloy material (e.g., cobalt, iron, nickel, aluminum, copper, magnesium, titanium, zirconium, a cobalt-based alloy, an iron-based alloy, a nickel-based alloy, an iron- and nickel-based alloy, a cobalt- and nickel-based alloy, an iron- and cobalt-based alloy, an aluminum-based alloy, a copper-based alloy, a magnesium-based alloy, a titanium-based alloy, a steel, a low-carbon steel, a stainless steel, etc.), or a combination thereof. The support **104** may, for example, be a fritted metal. In some embodiments, the support **104** is fritted stainless steel having a pore size of about 0.01 μm .

[0033] The support **104** may be formed of and include a ceramic material, such as a metal carbide material, a metal nitride material, a metal oxide material, a metal boride material, or a combination thereof. By way of example only, the support **104** may be formed of and include aluminum oxide, titanium oxide, zirconium oxide, or a mixed metal oxide. The support **104** may also be formed of and include silica, a siloxane, carbon nitride, boron nitride, a ceramic-metal composite material, a two-dimensional material (e.g., a transition metal dichalcogenide (TMDC) having a chemical formula of $\text{MX}_{2.0}$, where M is a transition metal and X is a chalcogen such as sulfur(S), selenium (Se), or tellurium (Te); graphene; graphene oxide; stanene; phosphorene; hexagonal boron nitride (h-BN); borophene; silicene; graphyne; germanene; germanane; a 2D supracrystal; etc.), or combinations thereof.

[0034] The substantially flat sheet of the support **104** or the hollow fibers of the support **104** may be formed by conventional techniques or may be commercially available from numerous sources. By way of example only, the hollow fibers may be formed by a phase inversion process using a specialized nozzle (e.g., a spinneret). A polymer dope is forced through the spinneret while simultaneously a flow of miscible non-solvent is pumped down the center bore of the spinneret forming the hollow fibers.

[0035] The support **104** may, optionally, include one or more additives, such as one or more fillers, to provide additional mechanical properties to the CO₂ selective membrane **100**. The filler may be a nanofiller that includes, but is not limited to, nanodiamond particles, such as functionalized nanodiamond particles. By way of example only, the nanodiamond particles may be functionalized with carboxylic acid groups (COOH), carboxylates with alkyl groups including from one carbon atom to twenty carbon atoms (e.g., three carbon atoms (C₃), six carbon atoms (C₆), twelve carbon atoms (C₁₂), eighteen carbon atoms (C₁₈)), and perfluoro groups (e.g., $-\text{CF}_2\text{H}$ groups, $-\text{OCH}_2\text{CF}_2\text{CF}_2\text{H}$ groups). In some embodiments, the filler includes octadecane (C₁₈) functionalized nanodiamonds (CND). The selectivity structure **106** may include from about 1% by weight (wt %) nanodiamond particles to about 10 wt % nanodiamond particles.

[0036] The nanodiamond particles may individually exhibit a desired particle size, such as a particle size within a range of from about 2 nanometers (nm) to about 8 nm, such as within a range of from about 4 nm to about 6 nm, or from about 4 nm to about 5 nm. In addition, each of the nanodiamond particles may individually exhibit a desired shape, such as at least one of a spherical shape, a hexahedral shape, an ellipsoidal shape, a cylindrical shape, a tubular shape, a conical shape, or an irregular shape. In some embodiments, each of the nanodiamond particles individually exhibits a generally spherical shape.

[0037] In some embodiments, the support **104** is formed of and includes PDMS. In other embodiments, the support **104** is formed of and includes polysulfone. In other embodiments, the

support **104** is formed of and includes PVDF. In yet other embodiments, the support **104** is formed of and includes PDMS and nanodiamond particles. In yet other embodiments, the support **104** is formed of and includes polysulfone and nanodiamond particles. In still other embodiments, the support **104** is formed of and includes PVDF and nanodiamond particles.

[0038] The selectivity structure **106** of the CO.sub.2 selective membrane **100** directly contacts the support **104**. The selectivity structure **106** of the CO.sub.2 selective membrane **100** may be configured and formulated to be highly selective to CO.sub.2 relative to other gaseous components of the source stream, such as N.sub.2. The selectivity structure **106** may also be highly selective for CO.sub.2 relative to oxygen (O.sub.2). The selectivity structure **106** may, for example, exhibit a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1 at about 30° C. At a lower temperature, such as about 0° C., the CO.sub.2/N.sub.2 selectivity may be from about 40/1 to about 60/1 or from about 40/1 to about 70/1. The selectivity structure **106** may also be configured and formulated to repair defects in the support **104**, exhibiting so-called “self-guttering” properties by filling defects, such as pinholes, in the support **104**. To achieve the CO.sub.2 selectivity and the self-guttering properties, the selectivity structure **106** may be a relatively flexible (e.g., soft, rubbery) film that is formed over the support **104**.

[0039] In addition to being highly selective to CO.sub.2, the selectivity structure **106** may be a material that is flowable at a temperature (e.g., a process temperature) at which the CO.sub.2 selective membrane **100** is formed. The selectivity structure **106** may be formed of and include a polyphosphazene compound, which is a hybrid organic-inorganic polymer having a repeating phosphorus-nitrogen backbone and functional groups, such as organic functional groups, attached to phosphorus atoms of the polyphosphazene compound. The functional groups of the polyphosphazene compound provide mechanical properties and performance properties to the selectivity structure **106**, as well as properties including thermal stability and solubility in various solvents. In some embodiments, the polyphosphazene compound is poly [bis((methoxyethoxy)ethoxy)phosphazene] (MEEP), which has a chemical structure of:

##STR00001##

MEEP is an amorphous material having a low glass transition at -80° C. and is a soft, gel-like material at the process temperature. The polyphosphazene compound may, however, be a heteropolymer, with different functional groups on adjacent phosphorus atoms of the polyphosphazene compound.

[0040] The polyphosphazene compound functions as a selectivity material of the selectivity structure **106**. Depending on the functional groups present, the polyphosphazene compound may range from being a hard, solid material to a soft gel, with the gas permeability of the polyphosphazene compound being higher with a softer material. To achieve the self-guttering properties, the functional groups of the selectivity structure **106** may be selected to formulate the selectivity structure **106** as a soft, gel-like material. The functional groups may also be selected such that the polyphosphazene compound is soluble in a coating solution and the coating solution is flowable at the process temperature.

[0041] While embodiments herein describe the polyphosphazene compound as being MEEP, other polyphosphazene compounds having different functional groups on the phosphorus atoms or a combination of polyphosphazene compounds having different functional groups on the phosphorus atoms may be used. For instance, to achieve the high CO.sub.2 selectivity, gas permeability, and material strength (e.g., durability) properties, the polyphosphazene compound may be a heteropolymer. The polyphosphazene compound may include a crosslinking functional group, a material property functional group, and a functional group providing the polyphosphazene compound with a high affinity for CO.sub.2 on the phosphorus atoms of the phosphorus-nitrogen backbone. The crosslinking functional group may, for example, be an allylphenol functional group, such as 2-allylphenol. The material property functional group may be a 4-methoxyphenol functional group. The functional group having affinity for CO.sub.2 may, for example, be a

(methoxyethoxy) ethoxy (MEE) functional group. However, other functional groups may be present on adjacent phosphorus atoms of the polyphosphazene compound. In the heteropolymeric polyphosphazene compound, the functional groups may be present in different ratios, depending on the desired properties of the selectivity structure **106**. By way of example only, the polyphosphazene compound may include between about 70 mol % and about 100 mol % of the MEE functional group on the phosphorus-nitrogen backbone to provide the desired CO.sub.2 selectivity. In some embodiments, about 80 mol % of the MEE functional group is present in the heteropolymeric polyphosphazene compound.

[0042] The selectivity structure **106** including the polyphosphazene compound may be configured as a layer on the substantially flat surface of the support **104** or on the sidewalls of the hollow fibers of the support **104**. The selectivity structure **106** may be formed at a minimum thickness sufficient to form a substantially continuous film on the support **104**. The thickness of the selectivity structure **106** may range from about 100 nm to less than or equal to about 2 μm , such as less than or equal to about 1.5 μm , less than or equal to about 1 μm , or less than or equal to about 0.5 μm . In some embodiments, the selectivity structure **106** has a thickness of about 0.5 μm .

[0043] The selectivity structure **106** may, optionally, include one or more additives, such as one or more fillers, which provide improved mechanical properties to the CO.sub.2 selective membrane **100**. The filler, when present, may increase the durability and strength of the selectivity structure **106** without decreasing its gas permeability and CO.sub.2 selectivity. The filler, when present, may also affect rheological properties of the coating solution, such as increasing the viscosity of the coating solution. The filler may be one of the nanofillers as described above. The nanofiller may include, but is not limited to, nanodiamond particles, such as functionalized nanodiamond particles, which provide desirable dispersion characteristics in a solvent. The selectivity structure **106** may include from about 1 wt % nanodiamond particles to about 10 wt % nanodiamond particles.

[0044] In some embodiments, the filler includes octadecane (C.sub.18) functionalized nanodiamonds. Unexpectedly, when the filler is present in the selectivity structure **106**, the CO.sub.2 selectivity of the CO.sub.2 selective membrane **100** remains substantially the same (e.g., constant). In contrast, when a filler is included in a conventional gas separation membrane, the performance (e.g., CO.sub.2 selectivity) of the conventional membrane is decreased.

[0045] The nanodiamond particles may individually exhibit a desired particle size, such as a particle size within a range of from about 2 nanometers (nm) to about 8 nm, such as within a range of from about 4 nm to about 6 nm, or from about 4 nm about 5 nm. In addition, each of the nanodiamond particles may individually exhibit a desired shape, such as at least one of a spherical shape, a hexahedral shape, an ellipsoidal shape, a cylindrical shape, a tubular shape, a conical shape, or an irregular shape. In some embodiments, each of the nanodiamond particles individually exhibits a generally spherical shape.

[0046] To form the CO.sub.2 selective membrane **100**, the coating solution of the selectivity material (e.g., MEEP) of the selectivity structure **106** may be applied to the support **104**. The selectivity material may be dissolved into a solvent, such as ethanol, to form the coating solution. As used herein, the term “solution” means and includes a solution, a suspension, an emulsion, or a combination thereof. The coating solution may exhibit a viscosity that is formulated to be coatable, with the optional filler included in the coating solution to increase the viscosity as needed. The additives, if present, may be substantially soluble in the solvent of the coating solution. The coating solution may be spin coated, dip coated, sprayed, or otherwise coated onto the support **104**. If the support **104** is substantially planar, the coating solution may be applied to one or more surfaces of the support **104** to form a substantially planar and substantially continuous layer of the selectivity structure **106** on the support **104**. If the support **104** includes the hollow fibers, the coating solution may be applied to form the substantially continuous layer of the selectivity structure **106** on inner surfaces and outer surfaces of the hollow fibers. The coating solution may be applied to one or more of inner surfaces and outer surfaces of the hollow fibers. Since the coating solution include

the selectivity material is flowable, the coating solution may flow into defects (e.g., pinholes) in the support **104** after being applied. After removing the solvent, the selectivity structure **106** is formed as a thin layer on the support **104**. The solvent may be removed (e.g., volatilized) from the applied coating solution by heating to a temperature at or below the boiling point of the solvent used to form the selectivity structure **106**. For instance, if ethanol is used as the solvent, the ethanol may be removed by heating to a temperature of about 70° C. The temperature used to remove the solvent may not degrade or otherwise damage the selectivity structure **106**.

[0047] In some embodiments, the CO.sub.2 selective membrane **100** includes a support **104** formed of and including PDMS and a selectivity structure **106** including MEEP. In other embodiments, the CO.sub.2 selective membrane **100** includes a support **104** formed of and including PDMS and a selectivity structure **106** including MEEP and nanodiamond particles (e.g., CNDs).

[0048] In some embodiments, the CO.sub.2 selective membrane **100** includes a support **104** formed of and including polysulfone and a selectivity structure **106** including MEEP. In other embodiments, the CO.sub.2 selective membrane **100** includes a support **104** formed of and including polysulfone and a selectivity structure **106** including MEEP and nanodiamond particles (e.g., CNDs).

[0049] In some embodiments, the CO.sub.2 selective membrane **100** includes a support **104** formed of and including PVDF and a selectivity structure **106** including MEEP. In other embodiments, the CO.sub.2 selective membrane **100** includes a support **104** formed of and including PVDF and a selectivity structure **106** including MEEP and nanodiamond particles (e.g., CNDs).

[0050] One or more of the CO.sub.2 selective membranes **100** may be incorporated into a gas separation system **200** that is configured to capture CO.sub.2 from the source stream, as shown in FIG. 2. The gas separation system **200** includes a housing **202** that contains the CO.sub.2 selective membrane **204**, and chambers **206** on opposing sides of the CO.sub.2 selective membrane **204**. The CO.sub.2 selective membrane **204** is substantially similar to one or more embodiments of the CO.sub.2 selective membrane **100** described above. Dimensions and a shape of the CO.sub.2 selective membrane **204** may be selected depending on dimensions and a shape of the housing **202** and on the gaseous components of the source stream. The CO.sub.2 selective membrane **204** is coupled to or integral with the housing **202**. The chambers **206** may include a first chamber **208** on one side of the CO.sub.2 selective membrane **204** and a second chamber **210** on another, opposing, side of the CO.sub.2 selective membrane **204**, with the CO.sub.2 selective membrane **204**, the first chamber **208**, and the second chamber **210** in fluid communication with the source stream. For simplicity, some components (e.g., pipelines, line filters, valves, pumps, motors, temperature detectors, flow detectors, pressure detectors, etc.) of the gas separation system **200** are not included in FIG. 2.

[0051] The housing **202** of the gas separation system **200** may exhibit any shape (e.g., a tubular shape, a quadrilateral shape, a spherical shape, a semi-spherical shape, a cylindrical shape, a semi-cylindrical shape, truncated versions thereof, or an irregular shape) and size able to contain (e.g., hold) the CO.sub.2 selective membrane **204** therein, and to direct the source stream to a first side of the CO.sub.2 selective membrane **204** and to direct a product stream (e.g., a concentrated CO.sub.2 stream) to a second side of the CO.sub.2 selective membranes **204**. The housing **202** may be formed of and include any material (e.g., glass, metal, alloy, polymer, ceramic, composite, combinations thereof, etc.) compatible with the source stream and with the operating conditions (e.g., temperatures, pressures, material interactions) of the gas separation system **200**.

[0052] The housing **202** may at least partially define the chambers **206** of the gas separation system **200**, with the CO.sub.2 selective membrane **204** between the first chamber **208** and the second chamber **210**. The CO.sub.2 selective membrane **204** may serve as a boundary between the chambers **206**, with the first chamber **208** configured and positioned to receive the source stream and to direct the source stream to the CO.sub.2 selective membrane **204**, and the second chamber **210** configured and positioned to receive the product stream and to direct the product stream from

the gas separation system **200**. The source stream is introduced to the first chamber **208** through an inlet (not shown), passes through the CO.sub.2 selective membrane **204**, and the product stream (e.g., the concentrated carbon dioxide stream) exits the second chamber **210** through an outlet (not shown).

[0053] While FIG. 2 illustrates one (e.g., a single) CO.sub.2 selective membrane **204**, the gas separation system **200** may include multiple CO.sub.2 selective membranes **204**. The multiple CO.sub.2 selective membranes **204** may be provided in parallel with one another or in series with one another within the housing **202**.

[0054] During use and operation of the gas separation system **200**, CO.sub.2 is removed (e.g., captured) and concentrated from the source stream. The source stream may be contained in a storage vessel (not shown) and subsequently introduced to the first chamber **208** of the gas separation system **200** through the inlet. The source stream is a gaseous source stream that contains less than about 10% wt % of CO.sub.2, such as between about 0.1 wt % and about 10% wt of CO.sub.2. The source stream may be ambient air or atmospheric air, which includes about 80% by volume of N.sub.2, about 21% by volume of O₂, and about 0.4% by volume of CO.sub.2.

Alternatively, the source stream may be an industrial offgas (e.g., an industrial exhaust gas, an industrial flue gas), such as an offgas or a flue gas from the steel, cement, or oil and gas industry. The source stream may be introduced to the first chamber at a flow rate of from about 20 ml min⁻¹ to about 150 ml min⁻¹. However, other flow rates may be used depending on the gas permeability of the CO.sub.2 selective membrane **204** and the surface area of the CO.sub.2 selective membrane **204**. Higher flow rates may be used if, for example, the gas separation system **200** is used to remove and concentrate CO.sub.2 from industrial quantities of the source stream.

[0055] The CO.sub.2 in the source stream is transported through the CO.sub.2 selective membrane **204** by a transmembrane pressure gradient and into the second chamber **210**, while other gaseous components of the source stream remain in the first chamber **208**. When the CO.sub.2 selective membrane **100** is configured as hollow fibers having the layer of the selectivity structure **106** thereon, as shown in FIG. 3, an increased surface area of the selectivity structure **106** is exposed to the source stream, increasing the CO.sub.2/N.sub.2 selectivity. Therefore, the CO.sub.2 is selectively separated from the other gaseous components of the source stream. The CO.sub.2 is selectively separated from the other gaseous components of the source stream without using a solvent during use and operation of the gas separation system **200**.

[0056] The gas separation system **200** may be operated at a temperature of less than about 70° C., such as less than about 60° C., less than about 50° C., less than about 40° C., or less than about 30° C. In some embodiments, the gas separation system **200** is operated at about 30° C.

[0057] The product stream in the second chamber **210** includes CO.sub.2 at a higher concentration than was present in the source stream. The product stream is recovered from the second chamber **210** through the outlet. The product stream may contain between about 15 wt % and about 50 wt % of CO.sub.2, such as between about 20 wt % and about 50 wt % of CO.sub.2, between about 25 wt % and about 50 wt % of CO.sub.2, between about 30 wt % and about 50 wt % of CO.sub.2, between about 35 wt % and about 50 wt % of CO.sub.2, between about 40 wt % and about 50 wt % of CO.sub.2, between about 45 wt % and about 50 wt % of CO.sub.2, between about 20 wt % and about 40 wt % of CO.sub.2, between about 20 wt % and about 35 wt % of CO.sub.2, between about 25 wt % and about 30 wt % of CO.sub.2, or between about 20 wt % and about 25 wt % of CO.sub.2. In some embodiments, the product stream includes greater than about 20 wt % of CO.sub.2. The gas separation system **200** may be used to recover the CO.sub.2 in a product stream containing greater than about 20 wt % CO.sub.2 after conducting a single pass of the source stream through the CO.sub.2 selective membrane **204** of the gas separation system **200**. The product stream may also be of a high purity, such as having a CO.sub.2 purity of greater than about 90 wt %, such as greater than about 95 wt % or greater than about 99 wt %.

[0058] The product stream including the concentrated CO.sub.2 may be collected for use as a

starting material or as a commodity chemical. The product stream may, for example, be used in various industries, such as in oil recovery, chemical production/manufacturing, or coal-fired power plants. Alternatively, the product stream including the concentrated CO.sub.2 may be sequestered. Since the product stream may be produced at a low cost, the recovered CO.sub.2 may be used in various industrial processes that are currently too expensive to conduct using CO.sub.2 recovered using conventional gas separation membranes.

[0059] The gaseous components of the source stream that remain in the first chamber **208** may be recovered and disposed of or utilized. The gaseous components may form a CO.sub.2 depleted stream that is used as a starting material or as a commodity chemical in other industrial processes.

[0060] The self-guttering properties of the selectivity structure **106** substantially reduce or eliminate the defects present in the support **104** and enable the CO.sub.2 selective membrane **100**, according to embodiments of the disclosure, to be used to capture and recover CO.sub.2 from the air or other low concentration CO.sub.2-containing source streams. Therefore, the CO.sub.2 may be captured and recovered from the low concentration CO.sub.2-containing source stream by a cost-effective process. Although the process of forming the CO.sub.2 selective membrane **100** according to embodiments of the disclosure includes forming an additional layer, which adds to production time, the high CO.sub.2 selectivity of the CO.sub.2 selective membrane **100** outweighs the increased production time.

[0061] The following examples serve to explain embodiments of the disclosure in more detail. These examples are not to be construed as being exhaustive, exclusive, or otherwise limiting as to the scope of the disclosure.

EXAMPLES

Example 1

[0062] MEEP was prepared by reacting a sodium salt of 2-(2-methoxyethoxy) ethanol with poly[bis-(chloro)phosphazene]. The MEEP was sprayed on a PDMS support to observe the CO.sub.2 selectivity of the resulting CO.sub.2 selective membrane. The PDMS support was commercially available. The source stream included 1 wt % of CO.sub.2 and 99 wt % of N.sub.2 and was passed through the PDMS/MEEP CO.sub.2 selective membrane. Passing the source stream through the PDMS/MEEP CO.sub.2 selective membrane increased the concentration of CO.sub.2 from 390 ppm to 2000 ppm. In comparison, passing the source stream through a PDMS only membrane increased the CO.sub.2 concentration from 390 ppm to 800 ppm.

Example 2

[0063] A solution including MEEP was sprayed on a polysulfone support. Solutions including MEEP and octadecane (C.sub.18) functionalized nanodiamonds (CND) were also sprayed on a polysulfone support. The solutions included 2% C.sub.18 functionalized CNDs and 4% C.sub.18 functionalized CNDs. The CO.sub.2 permeability of the resulting CO.sub.2 selective membranes was measured, as shown in FIG. 4. The CO.sub.2/N.sub.2 selectivity of the resulting CO.sub.2 selective membranes was measured, as shown in FIG. 5. A PEBAX® membrane, PEBAX® 1657, was used as a control. Pure gas permeation (CO.sub.2, N.sub.2, O.sub.2) was measured through the CO.sub.2 selective membranes.

[0064] The MEEP-based CO.sub.2 selective membranes showed a significantly higher CO.sub.2 permeability than the PEBAX® 1657 at a given temperature. The MEEP-based CO.sub.2 selective membranes showed a generally higher CO.sub.2/N.sub.2 selectivity than the PEBAX® 1657 at a given temperature.

Example 3

[0065] The CO.sub.2 permeability of the CO.sub.2 selective membranes described in Example 2 was measured, as shown in FIG. 6. The CO.sub.2/N.sub.2 selectivity of the CO.sub.2 selective membranes described in Example 2 was measured, as shown in FIG. 7. A PEBAX® membrane, PEBAX® 1657, was used as a control. Permeation of a gas containing 1% CO.sub.2 in N.sub.2 was measured through the CO.sub.2 selective membranes.

[0066] The MEEP-based CO.sub.2 selective membranes showed a significantly higher CO.sub.2 permeability than the PEBAX® 1657 at a given temperature. The MEEP-based CO.sub.2 selective membrane showed a higher CO.sub.2/N.sub.2 selectivity than the PEBAX® 1657 at a given temperature. The MEEP-based CO.sub.2 selective membranes including the C.sub.18 functionalized CNDs showed a lower CO.sub.2/N.sub.2 selectivity than the PEBAX® 1657 at a given temperature.

Example 4

[0067] A comparison of the CO.sub.2 permeability and the CO.sub.2/N.sub.2 selectivity of the MEEP-based CO.sub.2 selective membranes with and without C.sub.18 functionalized CNDs was determined. A PEBAX® membrane, PEBAX® 1657, and PDMS were used as a control. As shown in FIG. 8, the MEEP-based CO.sub.2 selective membranes without C.sub.18 functionalized CNDs exhibited high selectivities and exceptional permeabilities. The MEEP-based CO.sub.2 selective membranes with C.sub.18 functionalized CNDs exhibited reasonable selectivities and exceptionally high permeabilities. The MEEP-based CO.sub.2 selective membranes with the C.sub.18 functionalized CNDs also exhibited increased mechanical properties (data not shown).

Example 5

[0068] MEEP- and PEBAX®-based membranes were evaluated using the United States Department of Energy (US DOE) developed Greenhouse gases, Regulated Emissions and Energy in Transportation (GREET) fuel-cycle model and database. The model calculates fuel cycle emissions of 6 pollutants: carbon monoxide, nitrogen oxides, sulfur oxides, volatile organic compounds, and particulate matter with a diameter of 10 microns or less, and three greenhouse gases: CO.sub.2, methane, and nitrous oxide. The basis of CO.sub.2 separation was 1% CO.sub.2 in nitrogen for the MEEP membranes, while the basis of separation parameters for other membranes, such as the PEBAX® derived membranes, is as reported in the literature. The PEBAX® membranes were formed from block copolymers including polyamide block and polyether blocks. Most membranes have used pure gas measurements, and some have used a 50/50 CO.sub.2/N.sub.2 mixture. Some of the PEBAX®-based membranes included nanofilled-filled membranes, such as PEBAX® ZIF-8. A comparison of the permeability and CO.sub.2/N.sub.2 selectivity for the MEEP- and PEBAX®-based membranes is shown in Table 1.

TABLE-US-00001 TABLE 1 Comparison of Physical Properties of MEEP- and PEBAX®-based Membranes Separation Feed gas condition Membrane (CO.sub.2 (Temperature thickness vol %/N.sub.2 ° C./Pressure Permeability CO.sub.2/N.sub.2 Membrane (μm) vol %) bar) (Barrer) selectivity MEEP 0.1 99/1 15/1 100.0 40.0 MEEP/CND 0.1 99/1 15/1 100.0 35.0 Pristine PEBAX® (lower end) 1 pure gas 25/1 55.0 40.0 Pristine PEBAX® (higher end) 1 pure gas 25/1 100.0 70.0 PEBAX®/ZIF-8 105 pure gas 23/1 105.0 34.8 PEBAX®/ZIF-8(90 nm) 55 pure gas 25/1 154.0 40.5 PEBAX®/ZIF-8-90(50) 75 pure gas 35/— 217.5 54.1 PEBAX®/NH2-ZIF-8 — pure gas 25/1 163.8 62.0 PEBAX®/UiO-66 18 50/50 25/3 97.2 56.6 PEBAX®/NH2-MIL-53 75 pure gas 35/10 120.0 55.5 PEBAX®/MoS2 nanosheet 28 pure gas 30/1 52.3 90.6 PEBAX®/NaY 23 pure gas 30/2 82.8 35.0 PEBAX®/NOTT300 38 pure gas 25/10 395.2 61.2 PEBAX®/MCM-41 88 pure gas 25/2 122.5 53.0 PEBAX®/GO 83 20/80 35/2 105.0 41.2 PEBAX®/aminosilane-GO 83 20/80 35/2 166.3 45.2 PEBAX®/PEI-ZIF-8 1 50/50 25/1 13.0 49.0

[0069] Properties of the PEBAX®-based membranes were as reported from the literature.

[0070] Embodiment 1: A carbon dioxide (CO.sub.2) selective membrane, comprising: a support and a selective structure comprising poly [bis((methoxyethoxy) ethoxy)phosphazene] (MEEP) on the support. The CO.sub.2 selective membrane exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1.

[0071] Embodiment 2: The CO.sub.2 selective membrane of Embodiment 1, wherein the support comprises a polymer, a metal, or a ceramic.

[0072] Embodiment 3: The CO.sub.2 selective membrane of Embodiment 1 or Embodiment 2, wherein the support comprises a substantially flat sheet of a polymer, a metal, or a ceramic.

[0073] Embodiment 4: The CO.sub.2 selective membrane of Embodiment 1 or Embodiment 2, wherein the support comprises hollow fibers of a polymer.

[0074] Embodiment 5: The CO.sub.2 selective membrane of any of Embodiments 1-4, wherein the support exhibits a thickness of from about 0.7 mm to about 1.0 mm.

[0075] Embodiment 6: The CO.sub.2 selective membrane of any of Embodiments 1-5, wherein pores are homogeneously distributed throughout the support.

[0076] Embodiment 7: The CO.sub.2 selective membrane of Embodiment 6, wherein the pores exhibit a diameter of from about 0.008 μm to about 0.030 μm .

[0077] Embodiment 8: The CO.sub.2 selective membrane of any of Embodiments 1-7, wherein the selective structure directly contacts one or more surfaces of the support.

[0078] Embodiment 9: The CO.sub.2 selective membrane of any of Embodiments 1-8, further comprising one or more nanofillers.

[0079] Embodiment 10: The CO.sub.2 selective membrane of Embodiment 9, wherein the one or more nanofillers comprise nanodiamond particles.

[0080] Embodiment 11: The CO.sub.2 selective membrane of Embodiment 9 or Embodiment 10, wherein the one or more nanofillers comprise octadecane functionalized nanodiamonds.

[0081] Embodiment 12: The CO.sub.2 selective membrane of any of Embodiments 1-11, wherein the MEEP further comprises between about 70 mol % and about 100 mol % of a (methoxyethoxy) ethoxy functional group on a phosphorus-nitrogen backbone of the MEEP.

[0082] Embodiment 13: A gas separation system, the gas separation system comprising: a housing and one or more carbon dioxide (CO.sub.2) selective membranes contained within the housing. The one or more CO.sub.2 selective membranes comprise a support and a selective structure comprising poly [bis((methoxyethoxy) ethoxy)phosphazene] (MEEP) on the support, wherein the one or more CO.sub.2 selective membranes exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1.

[0083] Embodiment 14: The gas separation system of Embodiment 13, wherein the gas separation system comprises two or more CO.sub.2 selective membranes and the two or more CO.sub.2 selective membranes are configured in series.

[0084] Embodiment 15: The gas separation system of Embodiment 13, wherein the gas separation system comprises two or more CO.sub.2 selective membranes and the two or more CO.sub.2 selective membranes are configured in parallel.

[0085] Embodiment 16: A method of capturing carbon dioxide (CO.sub.2) comprising introducing a source stream containing CO.sub.2 at a concentration of less than about 10% by weight to a first chamber of a gas separation system, transporting the CO.sub.2 through the one or more CO.sub.2 selective membranes and to a second chamber of the gas separation system, the second chamber in fluid communication with the first chamber, and recovering the CO.sub.2 from the second chamber of the gas separation system. The gas separation system comprises one or more CO.sub.2 selective membranes and the one or more CO.sub.2 selective membranes comprise a support and a selective structure comprising poly [bis((methoxyethoxy) ethoxy)phosphazene] (MEEP) on the support, wherein the selective structure exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1.

[0086] Embodiment 17: The method of Embodiment 16, wherein introducing a source stream containing CO.sub.2 at a concentration of less than about 10% by weight to a first chamber of a gas separation system comprises introducing the source stream containing CO.sub.2 at a concentration of between about 1% by weight and about 10% by weight to the first chamber.

[0087] Embodiment 18: The method of Embodiment 16 or Embodiment 17, wherein introducing a source stream containing CO.sub.2 at a concentration of less than about 10% by weight to a first chamber of a gas separation system comprises introducing air or an industrial offgas to the first chamber of the gas separation system.

[0088] Embodiment 19: The method of any of Embodiments 16-18, wherein recovering the

CO.sub.2 comprises recovering a product stream comprising the CO.sub.2 at greater than or equal to about 15% by weight.

[0089] Embodiment 20: The method of any of Embodiments 16-19, wherein transporting the CO.sub.2 through the one or more CO.sub.2 selective membranes comprises transporting the CO.sub.2 without transporting nitrogen gas (N.sub.2) through the one or more CO.sub.2 selective membranes.

[0090] While the disclosure is susceptible to various modifications and alternative forms, specific embodiments have been shown by way of example in the drawings and have been described in detail herein. However, the disclosure is not limited to the particular forms disclosed. Rather, the disclosure is to cover all modifications, equivalents, and alternatives falling within the scope of the following appended claims and their legal equivalent. For example, elements and features disclosed in relation to one embodiment may be combined with elements and features disclosed in relation to other embodiments of the disclosure.

Claims

1. A carbon dioxide (CO.sub.2) selective membrane, comprising: a support; and a selective structure comprising poly [bis((methoxyethoxy) ethoxy)phosphazene] (MEEP) on the support, wherein the CO.sub.2 selective membrane exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1.
2. The CO.sub.2 selective membrane of claim 1, wherein the support comprises a polymer, a metal, or a ceramic.
3. The CO.sub.2 selective membrane of claim 1, wherein the support comprises a substantially flat sheet of a polymer, a metal, or a ceramic.
4. The CO.sub.2 selective membrane of claim 1, wherein the support comprises hollow fibers of a polymer.
5. The CO.sub.2 selective membrane of claim 1, wherein the support exhibits a thickness of from about 0.7 mm to about 1.0 mm.
6. The CO.sub.2 selective membrane of claim 1, wherein pores are homogeneously distributed throughout the support.
7. The CO.sub.2 selective membrane of claim 6, wherein the pores exhibit a diameter of from about 0.008 μm to about 0.030 μm .
8. The CO.sub.2 selective membrane of claim 1, wherein the selective structure directly contacts one or more surfaces of the support.
9. The CO.sub.2 selective membrane of claim 1, further comprising one or more nanofillers.
10. The CO.sub.2 selective membrane of claim 9, wherein the one or more nanofillers comprise nanodiamond particles.
11. The CO.sub.2 selective membrane of claim 9, wherein the one or more nanofillers comprise octadecane functionalized nanodiamonds.
12. The CO.sub.2 selective membrane of claim 1, wherein the MEEP further comprises between about 70 mol % and about 100 mol % of a (methoxyethoxy) ethoxy functional group on a phosphorus-nitrogen backbone of the MEEP.
13. A gas separation system, the gas separation system comprising: a housing; and one or more carbon dioxide (CO.sub.2) selective membranes contained within the housing, the one or more CO.sub.2 selective membranes comprising: a support; and a selective structure comprising poly [bis((methoxyethoxy) ethoxy)phosphazene] (MEEP) on the support, wherein the one or more CO.sub.2 selective membranes exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1.
14. The gas separation system of claim 13, wherein the gas separation system comprises two or more CO.sub.2 selective membranes and the two or more CO.sub.2 selective membranes are

configured in series.

15. The gas separation system of claim 13, wherein the gas separation system comprises two or more CO.sub.2 selective membranes and the two or more CO.sub.2 selective membranes are configured in parallel.

16. A method of capturing carbon dioxide (CO.sub.2) comprising: introducing a source stream containing CO.sub.2 at a concentration of less than about 10% by weight to a first chamber of a gas separation system, the gas separation system comprising one or more CO.sub.2 selective membranes and the one or more CO.sub.2 selective membranes comprising: a support; and a selective structure comprising poly [bis((methoxyethoxy) ethoxy)phosphazene] (MEEP) on the support, wherein the selective structure exhibits a CO.sub.2/N.sub.2 selectivity greater than or equal to about 40/1; transporting the CO.sub.2 through the one or more CO.sub.2 selective membranes and to a second chamber of the gas separation system, the second chamber in fluid communication with the first chamber; and recovering the CO.sub.2 from the second chamber of the gas separation system.

17. The method of claim 16, wherein introducing a source stream containing CO.sub.2 at a concentration of less than about 10% by weight to a first chamber of a gas separation system comprises introducing the source stream containing CO.sub.2 at a concentration of between about 1% by weight and about 10% by weight to the first chamber.

18. The method of claim 16, wherein introducing a source stream containing CO.sub.2 at a concentration of less than about 10% by weight to a first chamber of a gas separation system comprises introducing air or an industrial offgas to the first chamber of the gas separation system.

19. The method of claim 16, wherein recovering the CO.sub.2 comprises recovering a product stream comprising the CO.sub.2 at greater than or equal to about 15% by weight.

20. The method of claim 16, wherein transporting the CO.sub.2 through the one or more CO.sub.2 selective membranes comprises transporting the CO.sub.2 without transporting nitrogen gas (N.sub.2) through the one or more CO.sub.2 selective membranes.
