

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250285876

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

JULIEN; Franck

PROCESS FOR FABRICATING AN ELECTRONIC DEVICE

Abstract

A method of manufacturing an electronic device includes the doping by ion implantation of a first portion of the silicon nitride layer overlying a dielectric layer, where a second portion of the silicon nitride layer is protected from the ion implantation. A partial etching of the silicon nitride layer is then performed to etch the first portion down to a first depth smaller than or equal to a thickness of the silicon nitride layer and etch the second portion down to a second depth smaller than the first depth. The partial etching forms an etched silicon nitride layer having a cavity in all or part of the first portion. The cavity is filled with a polysilicon material to form a transistor gate.

Inventors: JULIEN; Franck (La Penne sur Huveaune, FR)
Applicant: STMicroelectronics International N.V. (Geneva, CH)
Family ID: 92925830
Assignee: STMicroelectronics International N.V. (Geneva, CH)
Appl. No.: 19/069708
Filed: March 04, 2025

Foreign Application Priority Data

FR FR2402184 Mar. 05, 2024

Publication Classification

Int. Cl.: H01L21/3115 (20060101); H01L21/311 (20060101)

U.S. Cl.:

CPC H01L21/31155 (20130101); H01L21/31111 (20130101);

Background/Summary

PRIORITY CLAIM

[0001] This application claims the priority benefit of French Application for Patent No. 2402184, filed on Mar. 5, 2024, the content of which is hereby incorporated by reference in its entirety to the maximum extent allowable by law.

TECHNICAL FIELD

[0002] The present disclosure generally concerns electronic devices, and in particular the manufacturing of electronic devices.

[0003] The present disclosure concerns, in particular, the manufacturing of an electronic device comprising an electronic component in a trench in a semiconductor substrate and another electronic component on the same semiconductor substrate.

BACKGROUND

[0004] During the manufacturing of an electronic device comprising different electronic components inside and on top of a same semiconductor substrate, a manufacturer may seek to use a same manufacturing method for all or part of the electronic components, in particular for reasons of manufacturing cost. For example, the electronic components of the electronic device may be manufactured on a same production line. However, if the manufacturing method is entirely implemented on the entire semiconductor substrate, without any separate treatment such as the fact of providing protections, such as masks, any implemented treatment applies to all electronic components. Now, a treatment used to form an electronic component may be unsuitable for another electronic component, and it is generally necessary to provide protections, such as masks, so that certain treatments do not apply to all electronic components.

[0005] According to the electronic device to be manufactured, and in particular to the different electronic components to be formed inside and on top of the same semiconductor substrate, it may be complicated, or even impossible, to manufacture the different electronic components on the same production line. For example, it may be necessary to implement specific technological steps to form an electronic component in a trench, or vertical electronic component, in the semiconductor substrate and other specific technological steps to form another electronic component on the semiconductor substrate (so-called “planar” electronic component) which may be difficult to reconcile with the specific technological steps for forming the trench electronic component.

[0006] It should be specified that, when it is indicated that the electronic component is “on the semiconductor substrate”, this does not necessarily mean that all the elements of this electronic component are on the semiconductor substrate, and other elements may be formed in the semiconductor substrate but not in a trench formed in the semiconductor substrate.

[0007] The electronic component in a trench may be, for example, a capacitor, a selection transistor, a vertical transistor or a transistor in a trench. The electronic component on the semiconductor substrate may be, for example, a MOS transistor or a gate.

[0008] Further, it is generally desired to use a number of protection masks which is the lowest possible.

[0009] There exists a need for a manufacturing method enabling to manufacture an electronic device comprising different electronic components inside and on top of a same semiconductor substrate, in particular an electronic component in a trench in the semiconductor substrate and another electronic component on the semiconductor substrate, and which does not require using specific technological steps to form all or part of the electronic components. It would be advantageous for this manufacturing method to use a decreased number of manufacturing steps, for example as many common manufacturing steps as possible, and/or as few protection masks as possible.

[0010] There is a need in the art to overcome all or part of the disadvantages of known electronic device manufacturing methods.

SUMMARY

[0011] An embodiment provides a method of manufacturing an electronic device comprising: providing a semiconductor substrate covered with a dielectric layer; forming a silicon nitride layer of a first thickness on the dielectric layer; doping by ion implantation of a first portion of the silicon nitride layer located above a first semiconductor region of the semiconductor substrate, a second portion of said silicon nitride layer located above a second semiconductor region of the semiconductor substrate being protected from said ion implantation; and partially etching the silicon nitride layer, wherein the rate of etching of the first portion is greater than the rate of etching of the second portion so that the first portion is etched down to a first depth smaller than or equal to the first thickness and the second portion is etched down to a second depth smaller than the first depth, said partial etching forming an etched silicon nitride layer comprising a cavity in all or part of the first portion.

[0012] According to an embodiment, the rate of etching of the first portion is greater than four times the rate of etching of the second portion, for example greater than or equal to five times, or even ten times, the rate of etching of the second portion.

[0013] According to an embodiment, the etching of the first portion stops before, or at, the dielectric layer, the dielectric layer forming, for example, an etch stop layer for the silicon nitride, the dielectric layer being, for example, made of silicon oxide.

[0014] According to an embodiment, the method comprises forming an insulating trench in the semiconductor substrate between the first semiconductor region and the second semiconductor region, wherein forming said insulating trench is performed prior to forming the silicon nitride layer.

[0015] According to an embodiment, the method comprises forming a trench in the second semiconductor region through the silicon nitride layer and the dielectric layer, preferably prior to the partial etching of the silicon nitride layer, wherein forming said trench comprises, for example, a dry etching.

[0016] According to an embodiment, the method comprises forming a polysilicon filling layer so as to at least fill the cavity and the trench, and forming a first polysilicon region in said cavity and a second polysilicon region in said trench.

[0017] According to an embodiment, the method comprises forming a first layer of oxide, for example of silicon oxide, on the sides and the bottoms of the cavity and of the trench, prior to forming the filling layer.

[0018] According to an embodiment, the method comprises removing the etched silicon nitride layer, after forming the filling layer, said removing, for example, comprising a wet etching with a solution comprising phosphoric acid.

[0019] According to an embodiment, the method comprises forming a second oxide layer on the first and second polysilicon regions, and for example also on portions of the semiconductor substrate from which the dielectric layer has been removed, wherein forming the second oxide layer is carried out after removing the etched silicon nitride layer.

[0020] According to an embodiment, the method comprises removing a second thickness of polysilicon in the second polysilicon region from a first surface of the etched silicon nitride layer, the first polysilicon region being protected by a mask during this removal.

[0021] According to an embodiment, the first polysilicon region forms all or part of a first gate region of a first electronic component, said first gate region being on the first semiconductor region, and the second polysilicon region forms all or part of a second gate region of a second electronic component, said second gate region being in a trench in the second semiconductor region.

[0022] According to an embodiment, the first component is a MOS transistor, the method

comprising: forming a doped well in the first semiconductor region, prior to forming the silicon nitride layer; forming insulating spacers on the sides of the first gate region; and forming drain and source regions in the first semiconductor region.

[0023] According to an embodiment, the second component is a transistor in a trench, for example a selection transistor in a trench.

[0024] According to an embodiment, the partial etching of the silicon nitride layer is a wet etching, for example with a solution comprising phosphoric acid or a solution based on hydrofluoric acid.

[0025] According to an embodiment: the first depth is greater than or equal to 80% of the first thickness, for example substantially equal to the first thickness; and/or the second depth is smaller than or equal to 50% of the first thickness, for example smaller than or equal to 20% of the first thickness, or even smaller than or equal to 10% of the first thickness.

[0026] According to an embodiment, the doping of the first portion of the silicon nitride layer is configured to less heavily dope a first sublayer in contact with the dielectric layer than a second sublayer above the first sublayer, so that, during the partial etching of the silicon nitride layer, the cavity formed in the silicon nitride layer comprises a first portion corresponding to the less heavily doped first sublayer and a second portion corresponding to the more heavily doped second sublayer, the second portion being wider than the first portion, for example the second portion having a domed shape wider than the first portion having a cylindrical shape.

[0027] Another embodiment provides an electronic device comprising: a first electronic component comprising a first gate region on a first semiconductor region of a semiconductor substrate; and a second electronic component comprising a second gate region in a trench in a second semiconductor region of the semiconductor substrate, the first gate region having a thickness greater than 50 nm, for example greater than or equal to 100 nm.

[0028] According to an embodiment, the first gate region comprises a first portion on the semiconductor substrate and a second portion on the first portion, the second portion being wider than the first portion, for example the first portion having a cylindrical shape and the second portion having a domed shape wider than the first portion.

[0029] An embodiment provides an electronic device likely to be obtained during one of the manufacturing methods described hereabove.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0030] The foregoing features and advantages, as well as others, will be described in detail in the rest of the disclosure of specific embodiments given as an illustration and not limitation with reference to the accompanying drawings, in which:

[0031] FIGS. 1A to 1Q are cross-section views showing steps of a method of manufacturing an electronic device;

[0032] FIG. 2 is a cross-section view showing an electronic device; and

[0033] FIGS. 3A and 3B are cross-section views showing a variant of the manufacturing method of FIGS. 1A to 1Q.

DETAILED DESCRIPTION

[0034] Like features have been designated by like references in the various figures. In particular, the structural and/or functional features that are common among the various embodiments may have the same references and may dispose identical structural, dimensional and material properties.

[0035] For clarity, only those steps and elements which are useful to the understanding of the described embodiments have been shown and are described in detail. In particular, not all the steps of the method of manufacturing the electronic components have been described, as they can be carried out with usual processes of microelectronics. Similarly, not all the details of the electronic

components have been described. Further, not all the applications that the described electronic devices may have been detailed.

[0036] Unless indicated otherwise, when reference is made to two elements connected together, this signifies a direct connection without any intermediate elements other than conductors, and when reference is made to two elements coupled together, this signifies that these two elements can be connected or they can be coupled via one or more other elements.

[0037] In the following description, where reference is made to absolute position qualifiers, such as “front”, “back”, “top”, “bottom”, “left”, “right”, etc., or relative position qualifiers, such as “top”, “bottom”, “upper”, “lower”, etc., or orientation qualifiers, such as “horizontal”, “vertical”, etc., reference is made unless otherwise specified to the orientation of the drawings.

[0038] Unless specified otherwise, the expressions “about”, “approximately”, “substantially”, and “in the order of” signify plus or minus 10%, preferably of plus or minus 5%.

[0039] When reference is made to a trench running through the semiconductor substrate, this does not mean that the trench necessarily extends across the entire thickness of the semiconductor substrate. The trench may be formed from an upper surface of the semiconductor substrate, which is the surface covered by the dielectric layer and the silicon nitride layer described later on.

[0040] When reference is made to an electronic component in a trench, reference is made to an electronic component mainly positioned in a trench running through the semiconductor substrate, for example comprising a gate which is included in the trench. When reference is made to a planar electronic component, or to an electronic component on the semiconductor substrate, reference is made to an electronic component which is not positioned in a trench running through the semiconductor substrate, and which comprises an element, for example a gate, positioned on the semiconductor substrate.

[0041] In the following description, the qualifiers “insulating” and “conductive” respectively signify, unless otherwise specified, electrically insulating and electrically conductive.

[0042] FIGS. **1A** to **1Q** are cross-section views showing a method of manufacturing an electronic device.

[0043] FIG. **1A** shows an initial structure comprising a semiconductor substrate **101** covered with a layer **102** made of a dielectric material, or dielectric layer.

[0044] Semiconductor substrate **101** may be a solid-state semiconductor substrate, for example made of silicon, without this example being considered limiting. Semiconductor substrate **101** may be a semiconductor layer, for example a silicon layer, on a buried insulating layer of a Silicon On Insulator (SOI) structure. More generally, semiconductor substrate **101** may be any semiconductor substrate in which a trench may be formed.

[0045] Dielectric layer **102** is preferably an oxide layer, for example made of a silicon oxide, for example of silicon dioxide (SiO₂). According to variants, dielectric layer **102** may be made of other insulating materials, such as in particular SiON, HfSiON, ZrO₂, TiO₂, TaO₂ (non-limiting list).

[0046] Advantageously, the material of dielectric layer **102** may be selected to be less rapidly etchable, or even non-etchable, than silicon nitride (SiN). For example, the material of dielectric layer **102** may be selected to form an etch stop layer when the silicon nitride is etched. Dielectric layer **102** may form an interface layer between semiconductor layer **101**, for example made of silicon, and a silicon nitride layer **105** described later on.

[0047] For example, dielectric layer **102** has a thickness in the range from 1 to 50 nm.

[0048] A first semiconductor region **11** is defined in semiconductor substrate **101** by first and second insulating trenches **103A**, **103B**. A second semiconductor region **12** is defined in semiconductor substrate **101**, insulated from first semiconductor region **11** by the first insulating trench **103A**. Although this is not shown, other semiconductor regions may be defined in semiconductor substrate **101**.

[0049] A doping by ion implantation, schematized by the six vertical arrows, is carried out in first

semiconductor region **11**, from the upper surface of semiconductor substrate **101** covered by dielectric layer **102**, in such a way as to form a doped well **104**. For example, if first semiconductor region **11** is intended to form the drain, source, and channel regions of an NMOS transistor, the well is P doped. As a variant, if first semiconductor region **11** is intended to form the drain, source, and channel regions of a PMOS transistor, the well is N doped.

[0050] Although this is not shown, in order to clearly define the ion implantation area for forming doped well **104**, a mask comprising, in particular, an opening located above first semiconductor region **11**, for example between insulating trenches **103A**, **103B**, but covering other semiconductor regions, and in particular second semiconductor region **12**, may be used. This mask may be a mask already used to implant other semiconductor regions (not shown), that is, open on these other semiconductor regions, and it may be provided to form in this existing mask this opening located above the first semiconductor region to implant this first semiconductor region.

[0051] FIG. **1B** shows a structure obtained at the end of the deposition of a layer of silicon nitride **105** on dielectric layer **102**.

[0052] The thickness e_1 (first thickness) of silicon nitride layer **105** may be, for example, in the range from 50 to 200 nm, for example equal to approximately 80 nm. These values of thickness e_1 are non-limiting, and thickness e_1 may, for example, depend on the destructuring effect of silicon nitride desired in the step described hereafter.

[0053] FIG. **1C** shows a structure obtained at the end of the forming of a first mask **106** on the upper surface of silicon nitride layer **105**, then of the doping by ion implantation, schematized by the two vertical arrows, of silicon nitride layer **105** through the first mask **106**.

[0054] The first mask **106** comprises a first opening **106A** exposing a first portion **105A** of silicon nitride layer **105** positioned above first semiconductor region **11**, so that only first portion **105A** is doped by ion implantation.

[0055] Other portions **105B**, **105C** of silicon nitride layer **105** are covered by this first mask **106**. These other portions comprise, in particular, a second portion **105B** located above second semiconductor region **12**, and third portions **105C** located on either side of first portion **105A** above first semiconductor region **11**.

[0056] The first mask **106** may be formed by deposition of a resist which is removed opposite the first portion **105A** of silicon nitride layer **105**.

[0057] Other portions of the silicon nitride layer above other semiconductor regions defined in the semiconductor substrate may be covered with the first mask. Further, the first mask may comprise a plurality of first openings exposing a plurality of first portions of the silicon nitride layer, so that the silicon nitride layer may comprise a plurality of first doped portions, for example above other semiconductor regions defined in the semiconductor substrate.

[0058] The ion implantation parameters are preferably determined so that the rate of etching of the first doped portion **105A** is greater than the rate of etching of the undoped portions **105B**, **105C** of silicon nitride layer **105**. The first portion **105A** of silicon nitride layer **105** can be said to be “destructured” as a result of the ion implantation.

[0059] For example, the rate of etching of the doped silicon nitride may be up to 4 times, or 5 times, or even up to 10 times, higher than the rate of etching of the undoped silicon nitride.

[0060] The rate of etching of the doped silicon nitride may vary according to the type and/or to the number of implanted atoms. Those skilled in the art will know how to act on the type and/or the number of implanted atoms to increase the rate of etching of the doped silicon nitride. The rate of etching of the doped silicon nitride may be a function of the modification of the silicon nitride crystal lattice induced by the ion implantation.

[0061] The implantation energy may be selected to be able to reach the entire thickness of nitride layer **105** in the first portion **105A**, but this is not limiting and it may not reach the entire thickness of nitride layer **105**.

[0062] As an example, for a thickness e_1 of silicon nitride layer **105** in the range from 60 to 200

nm, the implantation energy is in the range from 10 to 150 keV.

[0063] The implanted atoms may be selected from among argon, nitrogen, and phosphorus, but other atoms may be used. Those skilled in the art will be capable of selecting the right atoms according to the implemented manufacturing process.

[0064] FIG. 1D shows a structure obtained at the end of the removal of the first mask **106**, and of the forming of a second mask **107** on the upper surface of silicon nitride layer **105**, and then of the etching of a trench **109** through silicon nitride layer **105** and dielectric layer **102** and into the semiconductor substrate **101** across all or part of its thickness.

[0065] The second mask **107** comprises a second opening **107A** exposing a fourth portion **105D** of silicon nitride layer **105** positioned above second semiconductor region **12**, the second mask covering the rest of the silicon nitride layer, so that the etching is localized inside of and under this fourth portion, and in second semiconductor region **12**.

[0066] The second mask **107** may be formed by deposition of a resist which is removed opposite the fourth portion **105D** of silicon nitride layer **105**.

[0067] The second mask **107** may comprise a plurality of second openings exposing a plurality of fourth portions of the silicon nitride layer, so that a plurality of trenches may be formed, for example in other semiconductor regions defined in the semiconductor substrate.

[0068] The etching of trench **109** is preferably a dry etching, of plasma etching type.

[0069] In the shown example, trench **109** does not run through semiconductor substrate **101** across its entire thickness.

[0070] FIG. 1E shows a structure obtained at the end of the removal of second mask **107**, and of the etching of silicon nitride layer **105**. This etching is a partial etching since the silicon nitride layer is not entirely removed. This etching can be designated as a Nitride Pull Back (NPB) process.

[0071] During the NPB, the first doped portion **105A** of silicon nitride layer **105** is etched faster than the undoped portions **105B**, **105C** of silicon nitride layer **105**, typically at least 4 times or 5 times faster, and up to 10 times. It can be spoken of an over-etch factor. Thus, the etched silicon nitride layer **105'** has a cavity **111** located on the first etched portion **105A**, without it being necessary to provide a specific mask to form this cavity, and with no dry etching which might generate parasitic charges and/or defectivity problems.

[0072] Thus, the first doped portion **105A** is etched down to a first depth $p1$ equal to the first thickness $e1$, and the undoped portions **105B**, **105C** are etched down to a second depth $p2$ smaller than the first depth $p1$, for example much smaller than the first depth $p1$. The first depth $p1$ being equal to the first thickness $e1$, the first portion **105A** is etched across its entire thickness $e1$, down to dielectric layer **102**.

[0073] The etching of the silicon nitride is preferably a wet etching, based on a solution. The solution is, for example, a solution comprising phosphoric acid ($H_{sub.3}PO_{sub.4}$), or a solution based on diluted hydrofluoric acid (HF). Such a solution has an advantage of making the etching of silicon nitride highly selective over the silicon oxide that may form dielectric layer **102**. Thus, the silicon nitride can be etched while keeping dielectric layer **102** virtually intact. The solution may advantageously be hot, for example at a temperature higher than or equal to 160° C.

[0074] The parameters of the etching of the silicon nitride, in particular the composition and the concentration of the solution, the duration and the temperature of the etching, may be selected so that the first depth $p1$ is equal to the first thickness $e1$. The second thickness $p2$ may, in particular, depend on the overetching factor and on the first thickness $e1$ to be etched in first portion **105A**. As an example, the second depth $p2$ may be in the range from 10 to 50% of the first thickness $e1$.

[0075] The second depth $p2$ is, for example, equal to from approximately 10 to 20 nm for a thickness $e1$ in the range from 60 to 200 nm.

[0076] During this etch step, semiconductor substrate **101** is not etched. Dielectric layer **102** is also preferably not etched, and may form an etch stop layer.

[0077] In the shown example, it can be observed that this etching etches the silicon nitride more

than the material, for example, the SiO.sub.2, of dielectric layer **102**, so as to form a lateral recess **R** of the silicon nitride above and on either side of trench **109**. This lateral recess technique can also be designated by the term “Nitride Pull Back” (NPB), and enables to create a flared opening that may facilitate the subsequent filling of this trench. This lateral recess **R** may be in the range from 4 to 40 nm, for example from 10 to 20 nm.

[0078] FIG. **1F** shows a structure obtained at the end of the deposition of a first layer of oxide **112**, for example of silicon oxide, on the structure of FIG. **1E**. The first oxide layer **112** comes on the bottom and on the sides of trench **109**, on the bottom and on the sides of cavity **111**, and on the etched silicon nitride layer **105'**.

[0079] This step of deposition of first oxide layer **112** may be preceded by a step of removal of the exposed portions of dielectric layer **102**, for example at least the portion **102A** of the dielectric layer located at the bottom of cavity **111**. This removal may be carried out by implementing a wet etching, for example with a solution of hydrofluoric acid (HF).

[0080] This first oxide layer **112** may form a gate insulator layer for future gate regions, for example to form future transistors in trench **109** and/or in cavity **111**. This oxide may be deposited or formed by growth, for example of SiO.sub.2 or SiON type, with a thickness of, for example, from 2 to 25 nm.

[0081] FIG. **1G** shows a structure obtained at the end of the deposition of a first polysilicon layer **113** (filling layer) on first oxide layer **112**. The first polysilicon layer **113** fills at least trench **109** and cavity **111**, and may comprise a portion which extends above first oxide layer **112**.

[0082] FIG. **1H** shows a structure obtained at the end of the planarization of first polysilicon layer **113**, to remove the portion which extends above first oxide layer **112**, so that the polysilicon is flush with the upper surface of the etched silicon nitride layer **105'**. This planarization is, for example, achieved by chemical mechanical polishing (CMP). During this polishing, exposed portions of first oxide layer **112** may also be removed, as shown.

[0083] There are thus formed a first polysilicon region **114** on first oxide layer **112** in cavity **111** above the first semiconductor region **11** of semiconductor substrate **101**, and a second polysilicon region **115** on first oxide layer **112** in trench **109** in the second semiconductor region **12** of semiconductor substrate **101**.

[0084] The first polysilicon region **114** may form a first gate region **130** in cavity **111**, for example the gate region of a first transistor (first electronic component), for example a MOS transistor **13**, as described hereafter in relation with FIG. **1Q**. The thickness of the first polysilicon region **114**, and thus of the first gate region **130**, may be substantially equal to, or greater than or equal to, the depth **p1** of the cavity, that is, the thickness **e1** of silicon nitride layer **105**. The thickness of the first polysilicon region **114** may be greater than 50 nm, or even greater than 100 nm, for example in the range from 50 to 200 nm.

[0085] The second polysilicon region **115** may form a second gate region **140** in trench **109**, for example the gate region of a second transistor in a trench (second electronic component), for example a selection transistor **14**, as described hereafter in relation with FIG. **1Q**.

[0086] More generally, the embodiments enable to form a first polysilicon region on an oxide layer on a first semiconductor region of a semiconductor substrate, and a second polysilicon region on an oxide layer in a trench in a second semiconductor region of the same semiconductor substrate.

[0087] The following description shows that, according to the embodiment, a method of manufacturing a transistor in a trench in a semiconductor substrate can be carried out with no impact on the manufacturing of a planar transistor on the semiconductor substrate, and conversely. For example, the transistor in a trench and the planar transistor can be manufactured at the same time. The following description also shows that, after the forming of the cavity in the silicon nitride layer and the filling with polysilicon of this cavity, common manufacturing steps, for example, according to a same manufacturing process, can be implemented to form both types of transistors, and this, without having to multiply the number of masks. Further, the fact of doping a portion of

the silicon nitride layer to then etch the silicon nitride selectively in this doped portion enables to avoid carrying out a dry etching, other than the dry etching for forming the trench. This thus enables to form a polysilicon region with no other dry etching (since a dry etching may have too strong an impact on nearby electronic components).

[0088] The following steps of the manufacturing method are specific to the forming of a transistor in a trench in the semiconductor substrate, such as a memory cell selection transistor, next to a MOS transistor on the semiconductor substrate. The manufacturing method may be adapted by those skilled in the art to manufacture other electronic components, including at least one electronic component in a trench in the semiconductor substrate and another electronic component on the semiconductor substrate.

[0089] FIG. 1I shows a structure obtained after an optional step of removal by etching of a thickness of polysilicon in trench **109**, that is, the removal of a thickness e_2 (second thickness) of polysilicon in the second polysilicon region **115**, from the upper surface (first surface) of the etched silicon nitride layer **105'**. As a non-limiting example, the removal may be performed so that the upper surface of the second etched polysilicon region **115'** arrives below the level of dielectric layer **102**. This etching of the polysilicon is, for example, a dry etching. During this removal by etching of the polysilicon, first polysilicon region **114** is preferably protected by a mask **116**, which is then removed from silicon nitride layer **105'**. The portions **105C** (third portions) of silicon nitride located above first semiconductor region **11** may also be protected by mask **116**.

[0090] FIG. 1J shows a structure obtained at the end of the removal of the etched silicon nitride layer **105'**. The removal of the silicon nitride may be performed by wet etching by means of a solution of phosphoric acid (H.sub.3PO.sub.4).

[0091] FIG. 1K shows a structure obtained at the end of the deposition of a second oxide layer **117** on the structure of FIG. 1J.

[0092] This step of deposition of second oxide layer **117** may be preceded by a step of removal of the exposed portions of dielectric layer **102**. This removal may be performed by implementing a wet etching, for example with a solution of hydrofluoric acid (HF).

[0093] At the end of this step, there has been formed all or part of a planar gate with the first polysilicon region **114** above semiconductor substrate **101** co-integrated next to a vertical gate with the second polysilicon region **115** in trench **109**. Starting from this structure, different electronic components may be formed, including at least one planar electronic component and one electronic component in a trench. FIGS. 1L to 1Q described hereafter show an example of electronic components that can be manufactured, that is, an example of co-integration, starting from the structure of FIG. 1J. This example comprises forming gate stacks on either side of the vertical gate to form memory cells, and a MOS transistor from the planar gate. This is a non-limiting example, and other examples of co-integration of a planar electronic component with a vertical, or trenched, electronic component may be envisaged by those skilled in the art.

[0094] FIG. 1L shows a structure obtained at the end of the deposition of a second layer of polysilicon **118** on the structure of FIG. 1K.

[0095] FIG. 1M shows a structure obtained at the end of the removal of a portion **118A** of the second polysilicon layer **118** located above the first semiconductor region **11**, for example by dry etching. Thus, the second polysilicon layer **118** is located above the second semiconductor region **12**.

[0096] FIG. 1N shows a structure obtained at the end of the deposition of an oxide-nitride-oxide (ONO) layer **119** on the structure of FIG. 1M, and then of a third polysilicon layer **120** on ONO layer **119**.

[0097] FIG. 1O shows a structure obtained at the end of the removal of a portion **120A** of the third polysilicon layer **120** located above the first semiconductor region **11**, for example by dry etching. Thus, the third polysilicon layer **120** is located above the second semiconductor region **12**.

[0098] ONO layer **119** may be kept on the second oxide layer **117**. The first polysilicon region **114**

thus covered with the second oxide layer **117** and ONO layer **119** may form a first gate region **130** above the first semiconductor region **11**.

[0099] FIG. **1P** shows a structure obtained at the end of the forming of lightly-doped drain (LDD) regions **131** in the first semiconductor region **11** and of insulating spacers **132** on the sides of the first gate region **130**. The drain and source regions may then be formed in the first semiconductor region **11**, with a channel-forming region between these drain and source regions. Contact regions, for example via silicided regions, may be formed on the drain, source, and gate regions.

[0100] A MOS transistor **13** (first electronic component) is thus obtained.

[0101] FIG. **1Q** shows a structure obtained at the end of the etching of the second polysilicon layer **118**, of ONO layer **119**, and of the third polysilicon layer **120** above the second semiconductor region **12**, so as to form state transistors **15** of memory cells separated by a selection transistor **14** (second electronic component) having its gate region **140** in trench **109**.

[0102] Each state transistor **15** comprises a gate region **150** comprising, for example, a floating gate **151** formed by a portion of the second polysilicon layer **118** topped with a control gate **153** formed by a portion of the third polysilicon layer **120**, the control gate being insulated from the floating gate by a portion **152** of ONO layer **119**. The gate region **150** of each state transistor **15** may be insulated by insulating spacers **154**.

[0103] The electronic device **100** shown in FIG. **1Q** thus comprises a MOS transistor **13** having its gate region **130** on semiconductor substrate **101** (on the first semiconductor region **11**) next to state transistors **15** of memory cells separated by a selection transistor **14** having its gate region **140** in trench **109** in semiconductor substrate **101** (in the second semiconductor region **12**). As previously indicated, this is a non-limiting example of co-integration of a planar electronic component with a vertical electronic component, but other examples of co-integration may be envisaged by those skilled in the art. In particular, starting from a technology for manufacturing an electronic component in a trench, the embodiments enable to form at least one planar electronic component.

[0104] FIG. **2** is a cross-section view showing an electronic device according to an embodiment. FIG. **2** more generally illustrates an electronic device **200** that can be obtained by a manufacturing method according to an embodiment.

[0105] Electronic device **200** comprises: a first electronic component **23** comprising a first gate region **230** on a first semiconductor region **11** of a semiconductor substrate **101**; and a second electronic component **24** comprising a second gate region **240** in a trench **109** in a second semiconductor region **12** of the semiconductor substrate.

[0106] A gate insulator layer **112** is preferably comprised between the first gate region **230** and semiconductor substrate **101**, and between the second gate region **240** and semiconductor substrate **101**.

[0107] The first and second electronic components may be separated by a first insulating trench **103A**.

[0108] For example, the thickness of the first gate region **230** is greater than 50 nm, or even greater than or equal to 100 nm, for example in the range from 50 to 200 nm.

[0109] FIG. **3A** and FIG. **3B** are cross-section views showing a variant of the manufacturing method of FIGS. **1A** to **1Q**, in particular of the steps shown in FIGS. **1C** to **1H**. In FIGS. **3A** and **3B**, only the first semiconductor region **11** has been shown so as not to overload the drawing, but the second semiconductor region **12** may be present, as well as other semiconductor regions in the same semiconductor substrate **101**.

[0110] According to this variant, as shown in FIG. **3A**, the doping by ion implantation of silicon nitride layer **305** is carried out in such a way as to dope an upper portion **305S** (second sub-layer) of the silicon nitride layer more than a lower portion **305I** (first sub-layer) of this silicon nitride layer in contact with dielectric layer **102**. Thus, during the partial etching of silicon nitride layer **305**, the cavity **311** formed in the silicon nitride may take a specific shape. In the shown example, cavity **311** comprises a lower portion **311A** on dielectric layer **102**, the lower portion being

substantially cylindrical, and an upper portion **311B** on the lower portion **311A**, the upper portion **311B** having a domed shape wider than the lower portion.

[0111] As shown in FIG. **3B**, when cavity **311** is filled with the first polysilicon layer, such as the first polysilicon layer **113** of FIG. **1G**, a first polysilicon gate region **330** may be obtained, which comprises a first portion **330A** in contact with gate insulator layer **112** and a second portion **330B** on the first portion **330A**, the second portion **330B** being wider than the first portion **330A**, for example the first portion having a cylindrical shape and the second portion having a domed shape wider than the first portion. Other shapes of the first gate region are also possible.

[0112] This for example enables to decrease parasitic overlap capacitances between the gate region **330** formed in cavity **311**, the gate insulator **112** under gate region **330**, and the semiconductor substrate **101** under gate insulator **112**.

[0113] More generally, the doping by ion implantation of the silicon nitride layer may be adapted to obtaining specific cavity shapes during the partial etching of the silicon nitride layer, so as to obtain a polysilicon region having a specific shape.

[0114] The electronic devices obtained by the described manufacturing methods, more generally by a manufacturing method according to an embodiment, may find applications in the fields of microcontrollers, of the Internet of Things (IoT), of analog circuits, of memories, for example non-volatile memories (NVM) or memories of Electrically Programmable Read-Only Memory (EEPROM) type.

[0115] Those skilled in the art will understand that certain features of these various embodiments and variants may be combined, and other variants will occur to those skilled in the art. In particular, a first planar electronic component adjacent to a second electronic component in a trench has been shown, but other configurations are possible. For example, one or a plurality of other electronic components may be provided between the electronic component in a trench and the planar electronic component. The first planar electronic component may be an electronic component different from a MOS transistor, for example, a capacitor, a resistor, etc. The second planar electronic component may be an electronic component different from a selection transistor, for example another transistor, a capacitor, etc. Further, a polysilicon layer for filling the trench and cavity has been described, but other conductive or semiconductor materials can be envisaged by those skilled in the art, for example materials for forming a High-K metal gate, or HKMG.

[0116] Finally, the practical implementation of the described embodiments and variants is within the abilities of those skilled in the art based on the functional indications given hereabove.

Claims

1. A method of manufacturing an electronic device, comprising: providing a semiconductor substrate covered with a dielectric layer; forming a silicon nitride layer having a first thickness on the dielectric layer; doping by ion implantation a first portion of the silicon nitride layer located above a first semiconductor region of the semiconductor substrate, wherein a second portion of said silicon nitride layer located above a second semiconductor region of the semiconductor substrate is protected from said ion implantation; and partially etching the silicon nitride layer, wherein a rate of etching of the first portion is greater than a rate of etching of the second portion so that the first portion is etched down by a first depth smaller than or equal to the first thickness and the second portion is etched down by a second depth smaller than the first depth, said partial etching forming an etched silicon nitride layer comprising a cavity in all or part of the first portion.
2. The method according to claim 1, wherein the rate of etching of the first portion is greater than four times the rate of etching of the second portion.
3. The method according to claim 1, wherein etching the first portion stops before, or at, the dielectric layer, the dielectric layer forming an etch stop layer for the silicon nitride, the dielectric layer being made of silicon oxide.

4. The method according to claim 1, comprising forming an insulating trench in the semiconductor substrate between the first semiconductor region and the second semiconductor layer, wherein forming said insulating trench is performed prior to forming the silicon nitride layer.
5. The method according to claim 1, comprising forming a trench in the second semiconductor region through the silicon nitride layer and the dielectric layer, wherein forming the trench is performed prior to partially etching the silicon nitride layer.
6. The method according to claim 5, wherein forming the trench comprises performing a dry etching.
7. The method according to claim 5, comprising forming a polysilicon filling layer which fills the cavity and the trench, said polysilicon filling layer forming a first polysilicon region in said cavity and a second polysilicon region in said trench.
8. The method according to claim 7, comprising forming, prior to forming the filling layer, a first layer of oxide on sides and bottoms of the cavity and the trench.
9. The method according to claim 7, comprising removing the etched silicon nitride layer, after the forming the filling layer, wherein removing comprises performing a wet etching with a solution comprising phosphoric acid.
10. The method according to claim 9, comprising forming a second oxide layer on the first and second polysilicon regions, wherein forming the second oxide layer is carried out after removing the etched silicon nitride layer.
11. The method according to claim 10, wherein the second oxide layer is further formed on portions of the semiconductor substrate from which the dielectric layer has been removed.
12. The method according to claim 7, wherein the first polysilicon region forms all or part of a first gate region of a first electronic component, said first gate region being on the first semiconductor region, and the second polysilicon region forms all or part of a second gate region of a second electronic component, said second gate region being in a trench in the second semiconductor region.
13. The method according to claim 12, wherein the first component is a MOS transistor, and wherein the second component is a transistor in a trench.
14. The method according to claim 7, comprising removing a second thickness of polysilicon in the second polysilicon region from a first surface of the etched silicon nitride layer, wherein the first polysilicon region is protected by a mask during removal of the second thickness.
15. The method according to claim 1, wherein partially etching the silicon nitride layer comprises performing a wet etching using one of: a solution comprising phosphoric acid, or a solution based on hydrofluoric acid.
16. The method according to claim 1, wherein the first depth is greater than or equal to 80% of the first thickness.
17. The method according to claim 1, wherein the first depth is substantially equal to the first thickness.
18. The method according to claim 1, wherein the second depth is smaller than or equal to 50% of the first thickness.
19. The method according to claim 1, wherein doping the first portion of the silicon nitride layer is configured to less heavily dope a first sublayer in contact with the dielectric layer than a second sublayer above the first sublayer, and wherein partially etching the silicon nitride layer forms the cavity in the silicon nitride layer which comprises a first portion corresponding to the less heavily doped first sublayer and a second portion corresponding to the more heavily doped second sublayer, the second portion being wider than the first portion.
20. The method according to claim 19, wherein the first portion has a cylindrical shape and the second portion has a domed shape wider than the first portion.
21. An electronic device, comprising: a first electronic component comprising a first gate region on a first semiconductor region of a semiconductor substrate; and a second electronic component

comprising a second gate region in a trench in a second semiconductor region of the semiconductor substrate, wherein the first gate region has a thickness greater than 50 nm.

22. The electronic device according to claim 21, where the thickness of the first gate region is greater than or equal to 100 nm.

23. The electronic device according to claim 21, wherein the first gate region comprises a first portion on the semiconductor substrate and a second portion on the first portion, the second portion being wider than the first portion.

24. The electronic device according to claim 23, wherein the first portion has a cylindrical shape and the second portion has a domed shape wider than the first portion.
