

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12402391
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Zhou; Huimei et al.

Stressed material within gate cut region

Abstract

A semiconductor device includes a substrate with a planar top surface. At least a first gate cut stressor within a first gate cut region separates a first transistor region from a second transistor region. The first gate cut stressor is directly upon the planar top surface and applies a first tensile force perpendicular to a channel of the first transistor region and perpendicular to a channel of the second transistor region. The tensile force may improve hole and/or electron mobility within a transistor in the first transistor region and within a transistor in the second transistor region. The gate cut stressor may include a lower material within the gate cut region and an upper material upon the lower material. Alternatively, the gate cut stressor may include a liner material that lines the gate cut region and an inner material upon the liner material.

Inventors: Zhou; Huimei (Albany, NY), Greene; Andrew M. (Slingerlands, NY), Belyansky; Michael P. (Halfmoon, NY), Gluschenkov; Oleg (Tannersville, NY), Robison; Robert (Rexford, NY), Li; Juntao (Cohoes, NY), Conti; Richard A. (Altamont, NY), Lie; Fee Li (Albany, NY)

Applicant: International Business Machines Corporation (Armonk, NY)

Family ID: 1000008781744

Assignee: International Business Machines Corporation (Armonk, NY)

Appl. No.: 17/516505

Filed: November 01, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20230139399 A1	May. 04, 2023

Publication Classification

Int. Cl.: H10D84/03 (20250101); H01L21/762 (20060101); H10D30/01 (20250101); H10D30/62 (20250101); H10D30/67 (20250101); H10D62/10 (20250101); H10D64/01 (20250101); H10D84/01 (20250101); H10D84/85 (20250101)

U.S. Cl.:

CPC H10D84/038 (20250101); H01L21/76224 (20130101); H10D30/024 (20250101); H10D30/031 (20250101); H10D30/6211 (20250101); H10D30/67 (20250101); H10D30/6735 (20250101); H10D62/118 (20250101); H10D64/017 (20250101); H10D84/0188 (20250101); H10D84/853 (20250101);

Field of Classification Search

CPC: H10D (30/024); H10D (30/031); H10D (30/6211); H10D (30/67); H10D (62/118); H10D (84/853)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8766364	12/2013	Doornbos	N/A	N/A
9136330	12/2014	Liu	N/A	N/A
9373641	12/2015	Anderson	N/A	N/A
9537007	12/2016	Yang	N/A	N/A
9761495	12/2016	Ruilong	N/A	N/A
9991361	12/2017	Dai	N/A	N/A
10014298	12/2017	Zang et al.	N/A	N/A
10056382	12/2017	Guo	N/A	N/A
10176995	12/2018	Wu	N/A	H01L 21/76829
10522679	12/2018	Jha	N/A	N/A
2011/0169085	12/2010	Xu et al.	N/A	N/A
2016/0300948	12/2015	Yang et al.	N/A	N/A
2017/0243790	12/2016	Xie et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
101677085	12/2009	CN	N/A
107438902	12/2016	CN	N/A
109087888	12/2017	CN	N/A

OTHER PUBLICATIONS

International Search Report, International Application No. PCT/CN2022/125927, Dec. 27, 2022, 9 pgs. cited by applicant

Pei Zhao et al., "Influence of stress induced CT local layout effect (LLE) on 14nm FinFET," Symposium on VLSI Technology, 2017, pp. T228-T229. cited by applicant

Primary Examiner: Toledo; Fernando L

Assistant Examiner: Bowen; Adam S

Background/Summary

BACKGROUND

(1) Various embodiments of the present application generally relate semiconductor device fabrication methods and resulting structures. More specifically the various embodiments relate to a semiconductor device, such as a fin field effect transistor (FET) or nanosheet transistor, that includes a stressed material within its gate cut region.

SUMMARY

(2) In an embodiment of the present invention, a semiconductor device is presented. The device includes one or more first fins that extend from a planar top surface of a substrate within a first device region and one or more second fins that extend from the planar top surface of the substrate within a second device region. The device further includes first shallow trench isolation (STI) within the first device region. The first STI is upon the planar top surface of the substrate and upon and between respective lower portion(s) of the one or one or more first fins. The first STI includes a first STI sidewall that faces the second device region. The device further includes a second STI within the second device region. The second STI is upon the planar top surface of the substrate and is upon and between respective lower portion(s) of the one or one or more second fins. The second STI includes a second STI sidewall that faces the first device region. The device includes a first gate within the first device region. The first gate is upon the first STI and is upon and between respective upper portion(s) of the one or more first fins. The first gate includes a first gate sidewall that faces the second device region. The device further includes a second gate within the second device region. The second gate is upon the second STI and is upon and between respective upper portion(s) of the one or more second fins. The second gate includes a second gate sidewall that faces the first device region. The device further includes a gate cut stressor upon the planar top surface of the substrate, upon the first STI sidewall, upon the second STI sidewall, upon the first gate sidewall, and upon the second gate sidewall. The gate cut stressor includes an intrinsic stress that applies a tensile force to the first gate perpendicular to the first fins and to the second gate perpendicular to the second fins.

(3) In an embodiment of the present invention, another semiconductor device is presented. The device includes a substrate comprising a planar top surface. The device includes a first gate cut stressor within a first gate cut region that separates a first transistor region from a second transistor region. The first gate cut stressor is directly upon the planar top surface and applies a first tensile force to a first gate perpendicular to a first channel in the first transistor region and to a second gate perpendicular to a second channel in the second transistor region. The device further includes a second gate cut stressor within a second gate cut region that separates a third transistor region from a fourth transistor region. The second gate cut stressor is directly upon the planar top surface and applies a second tensile force to a third gate perpendicular to a third channel in the third transistor region and to a fourth gate perpendicular to a fourth channel in the fourth transistor region. The second gate cut stressor is formed of a different material relative to the first gate cut stressor.

(4) In another embodiment of the present invention, a semiconductor device fabrication method is presented. The method includes forming a gate cut region that separates a sacrificial gate layer into a first sacrificial gate and a second sacrificial gate and that separates a shallow trench isolation (STI) layer into a first STI and a second STI. The method further includes forming a sacrificial gate cut plug within the gate cut region, removing the first sacrificial gate, and removing the second sacrificial gate. The method includes forming a first replacement gate in place of the removed first sacrificial gate and forming a second replacement gate in place of the removed second sacrificial gate. The method includes removing the sacrificial gate cut plug thereby exposing a first STI sidewall of the first STI, exposing a first gate sidewall of the first replacement gate, exposing a

second STI sidewall of the second STI, exposing a second gate sidewall of the second replacement gate, and exposing a portion of an upper surface of a planar substrate. The method further includes forming a gate cut stressor upon the upper surface of the planar substrate, upon the first STI sidewall, upon the second STI sidewall, upon the first gate sidewall, and upon the second gate sidewall. The gate cut stressor includes an intrinsic stress that applies a tensile force along the first gate and along the second gate.

(5) These and other embodiments, features, aspects, and advantages will become better understood with reference to the following description, appended claims, and accompanying drawings.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 through FIG. 10 depicts cross-sectional views of a semiconductor structure shown after fabrication operations, in accordance with one or more embodiments.

(2) FIG. 11 through FIG. 14 depicts cross-sectional views of a semiconductor structure shown after fabrication operations, in accordance with one or more embodiments.

(3) FIG. 15 is a flow diagram of a semiconductor device fabrication method, in accordance with one or more embodiments.

(4) FIG. 16 is a flow diagram of a semiconductor device fabrication method, in accordance with one or more embodiments.

DETAILED DESCRIPTION

(5) It is understood in advance that although a detailed description is provided herein of an exemplary fin FET and/or nanosheet architecture that has a stress material within its gate cut region, implementation of the teachings recited herein are not limited to the particular device architecture described herein. Rather, embodiments of the present invention are capable of being implemented in conjunction with any other appropriate type of transistor device now known or later developed.

(6) Various embodiments of the present invention are described herein with reference to the related drawings. Alternative embodiments can be devised without departing from the scope of this invention. It is noted that various connections and positional relationships (e.g., over, below, adjacent, etc.) are set forth between elements in the following description and in the drawings. These connections and/or positional relationships, unless specified otherwise, can be direct or indirect, and the present invention is not intended to be limiting in this respect. Accordingly, a coupling of entities can refer to either a direct or an indirect coupling, and a positional relationship between entities can be a direct or indirect positional relationship. As an example of an indirect positional relationship, references in the present description to forming layer “A” upon layer “B” include situations in which one or more intermediate layers (e.g., layer “C”) is between layer “A” and layer “B” as long as the relevant characteristics and functionalities of layer “A” and layer “B” are not substantially changed by the intermediate layer(s).

(7) For purposes of the description hereinafter, the terms “upper,” “lower,” “right,” “left,” “vertical,” “horizontal,” “top,” “bottom,” and derivatives thereof relate to the described structures and methods, as oriented in the drawing figures. The terms “overlying,” “atop,” “on top,” “positioned on” or “positioned atop” mean that a first element, such as a first structure, is present on a second element, such as a second structure, wherein intervening elements such as an interface structure can be present between the first element and the second element. The term “direct contact,” or the like, means that a first element, such as a first structure, and a second element, such as a second structure, are connected without any intermediary conducting, insulating or semiconductor layers at the interface of the two elements. It should be noted that the term “selective to,” such as, for example, “a first element selective to a second element,” means that the

first element can be etched and the second element can act as an etch stop.

(8) The terms “about,” “substantially,” “approximately,” and variations thereof, are intended to include the degree of error associated with measurement of the particular quantity based upon the equipment available at the time of filing the application. For example, substantial coplanarity between various materials can include an appropriate manufacturing tolerance of $\pm 8\%$, $\pm 5\%$, or $\pm 2\%$ difference between the coplanar materials.

(9) For the sake of brevity, conventional techniques related to semiconductor device and integrated circuit (IC) fabrication may or may not be described in detail herein. Moreover, the various tasks and process steps described herein can be incorporated into a more comprehensive procedure or process having additional steps or functionality not described in detail herein. In particular, various steps in the manufacture of semiconductor devices and semiconductor-based ICs are well known and so, in the interest of brevity, many conventional steps will only be mentioned briefly herein or will be omitted entirely without providing the well-known process details.

(10) In general, the various processes used to form a micro-chip that will be packaged into an IC fall into four general categories, namely, film deposition, removal/etching, semiconductor doping and patterning/lithography. Deposition is any process that grows, coats, or otherwise transfers a material onto the wafer. Available technologies include physical vapor deposition (PVD), chemical vapor deposition (CVD), electrochemical deposition (ECD), molecular beam epitaxy (MBE) and more recently, atomic layer deposition (ALD) among others. Removal/etching is any process that removes material from the wafer. Examples include etch processes (either wet or dry), and chemical-mechanical planarization (CMP), and the like. Semiconductor doping is the modification of electrical properties by doping, for example, transistor sources and drains, generally by diffusion and/or by ion implantation. These doping processes are followed by furnace annealing or by rapid thermal annealing (RTA). Annealing serves to activate the implanted dopants. Films of both conductors (e.g., poly-silicon, aluminum, copper, etc.) and insulators (e.g., various forms of silicon dioxide, silicon nitride, etc.) are used to connect and isolate transistors and their components. Selective doping of various regions of the semiconductor substrate allows the conductivity of the substrate to be changed with the application of voltage. By creating structures of these various components, millions of transistors can be built and wired together to form the complex circuitry of a modern microelectronic device. Semiconductor lithography is the formation of three-dimensional relief images or patterns on the semiconductor substrate for subsequent transfer of the pattern to the substrate. In semiconductor lithography, the patterns are formed by a light sensitive polymer called a photo-resist. To build the complex structures that make up a transistor and the many wires that connect the millions of transistors of a circuit, lithography and etch pattern transfer steps are repeated multiple times. Each pattern being printed on the wafer is aligned to the previously formed patterns and slowly the conductors, insulators and selectively doped regions are built up to form the final device.

(11) Turning now to a more detailed description of technologies that are more specifically relevant to aspects of the present invention, transistors are semiconductor devices commonly found in a wide variety of ICs. A transistor is essentially a switch. When a voltage is applied to a gate of the transistor that is greater than a threshold voltage, the switch is turned on, and current flows through the transistor. When the voltage at the gate is less than the threshold voltage, the switch is off, and current does not flow through the transistor.

(12) Semiconductor devices can be formed in the active regions of a wafer. The active regions are defined by isolation regions used to separate and electrically isolate adjacent semiconductor devices. For example, in an integrated circuit having a plurality of metal oxide semiconductor field effect transistors (MOSFETs), each MOSFET has a source and a drain that are formed in an active region of a semiconductor layer by implanting n-type or p-type impurities in the layer of semiconductor material. Disposed between the source and the drain is a channel (or body) region. Disposed above the body region is a gate. The gate and the body are spaced apart by a gate

dielectric layer. The channel connects the source and the drain, and electrical current flows through the channel from the source to the drain. The electrical current flow is induced in the channel region by a voltage applied at the gate.

(13) FIG. 1 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include a first device region **103**, a second device region **105**, a substrate **102**, one or more fins **110** within the first device region **103**, one or more fins **114** within second device region **105**, a shallow trench isolation (STI) layer **112** upon the substrate **102** and between the one or more fins **110** and between the one or more fins **114**, and one or more sacrificial gates **120** with a gate mask **122** thereupon.

(14) First device region **103** may include a nFET and second device region **105** may include a pFET, or vice versa. As such, the transistor within first device region **103** may be of a first dopant type and the transistor within the second device region may be of a second dopant type.

Alternatively, first device region **103** may include a first nFET and second device region **105** may include a second nFET. Similarly, first device region **103** may include a first pFET and second device region **105** may include a second pFET. As such, the transistors within first device region **103** and within the second device region **105** may be of the same dopant type.

(15) Generally, first device region **103** and second device region **105** may be associated with transistor(s) that are associated with physically and/or electrically distinct or separated gates. For example, as shown in FIG. 5 and FIG. 6, a transistor within first device region **103** has a replacement gate **150** and a transistor within second device region **105** has a replacement gate **154** that is physically and electrically distinct, isolated, and/or separated from replacement gate **150** by a gate cut region **132**.

(16) Non-limiting examples of suitable materials for the substrate **102** include Si (silicon), strained Si, SiC (silicon carbide), Ge (germanium), SiGe (silicon germanium), SiGe:C (silicon-germanium-carbon), Si alloys, Ge alloys, III-V materials (e.g., GaAs (gallium arsenide), InAs (indium arsenide), InP (indium phosphide), or aluminum arsenide (AlAs)), II-VI materials (e.g., CdSe (cadmium selenide), CdS (cadmium sulfide), CdTe (cadmium telluride), ZnO (zinc oxide), ZnSe (zinc selenide), ZnS (zinc sulfide), or ZnTe (zinc telluride)), or any combination thereof. Other non-limiting examples of semiconductor materials include III-V materials, for example, indium phosphide (InP), gallium arsenide (GaAs), aluminum arsenide (AlAs), or any combination thereof. The III-V materials can include at least one “III element,” such as aluminum (Al), boron (B), gallium (Ga), indium (In), and at least one “V element,” such as nitrogen (N), phosphorous (P), arsenic (As), antimony (Sb). The substrate **102** can be a bulk substrate. Alternatively, the substrate **102** may be one layer or a top layer of a multi-layered substrate. For example, substrate **102** may be a top layer of a substrate on insulator (e.g., silicon on insulator (SOI), or the like) that may include a lower substrate **106**, such as a Si substrate **104**, an insulator **104**, such as a SiO insulator, upon the lower substrate **104**, and the top substrate **102** upon the insulator **106**. The substrate **102** may be doped, as is known in the art, so as to form the appropriate dopant type of the transistor in the first device region **103** and the appropriate dopant type of the transistor in the second device region **105**.

(17) When Si-containing substrate **102** is employed, it may have different surface crystallographic orientations. Common substrate **102** surface orientations are {100}, {110}, and {111}, while {100} crystallographic orientation is more typical due to its inherent crystallographic symmetry with respect to its response to asymmetric surface stressors imparted by useful surface structures. Furthermore, useful structures that are built on the substrate surface maybe aligned to a particular crystallographic direction that is chosen based on substrate crystallography. Such reference crystallographic direction for a substrate **102** is often made visible to the substrate alignment equipment by placing a physical notch, flat, or other marker at the substrate perimeter. Typical crystallographic direction between such marker and the substrate center is <110> for Si-containing substrate **102** with {100} surface orientation. If the reference crystallographic direction to the

substrate notch or other marker is different from $\langle 110 \rangle$ the substrate can be referred to as rotated. (18) In one embodiment, utilizing known patterning, lithography, etching, etc. techniques, undesired portions of the substrate **102** may be removed while desired portions thereof may be retained and may form fins **110** and fins **114**. Fins **110** and fins **114** can be patterned by conventional patterning techniques, such as Self-Aligned Double Patterning (SADP), Self-Aligned Quadruple Patterning (SAQP), etc. As fins **110** and fins **114** may be formed from subtracting material(s) from substrate **102**, fins **110** and fins **114** may retain the material properties (e.g., dopants, or the like) therefrom.

(19) In another embodiment, utilizing known deposition techniques, fins **110** and fins **114** may be formed upon substrate **102**. Fins **110** and fins **114** could be positively formed upon substrate **102** by known deposition techniques such PVD, CVD, ALD, Epitaxial growth, or the like. In this embodiment, fins **110** and fins **114** may be doped, as is known in the art, so as to form the appropriate dopant type of the transistor in the first device region **103** and the appropriate dopant type of the transistor in the second device region **105**.

(20) In one embodiment, the fins **110** and fins **114** have crystalline sidewalls that are $\{110\}$ crystallographic planes. These planes may provide increased hole mobility and are therefore preferred. This can be accomplished by selecting a $\{100\}$ surface substrate and aligning fins perpendicular to $\langle 110 \rangle$ direction. For a normal, nonrotated $\{100\}$ substrate **102**, aligning fins perpendicular to notch-center line produces $\{110\}$ fin sidewalls and sets $\langle 110 \rangle$ crystallographic direction along the fins **110**, **114**.

(21) STI region(s), an STI layer, or the like, which may be collectively referred herein as STI **112**, may be formed by depositing STI material(s), such as silicon nitride (SiN), Silicon Dioxide (SiO₂), a combination of SiN and Silicon Dioxide (SiO₂) by different deposition method, upon the substrate **102**, upon and between fins **110**, and upon and between fins **114**. STI **112** may be formed by depositing the STI material(s) by for example, PVD, CVD, ALD, or the like. As is known in the art, STI **112** may, at least partially, electrically isolate neighboring transistor components or features. For example, STI **112** may at least partially physically and electrically isolate one fin **110** from a neighboring fin **110**, may physically and electrically isolate fins **110** from fins **114**, or the like.

(22) In some embodiments, a sacrificial gate **120** material layer may be formed upon STI **112**, upon and between fins **110**, and upon and between fins **114**. The sacrificial gate **120** material layer may be formed by known deposition techniques such PVD, CVD, ALD, or the like. The sacrificial gate **120** material layer may be formed to a thickness greater than the height of fins **110** and/or fins **114**. For example, the top surface of the sacrificial gate **120** material layer may be above the top surface of fins **110** and/or fins **114**. The sacrificial gate **120** material layer can have a thickness of from about 30 nm to about 200 nm, although other thicknesses are within the contemplated scope.

(23) Subsequently a gate mask **122** layer may be formed upon the sacrificial gate **120** material layer. The gate mask **122** layer may be a hard mask layer. Exemplary gate mask **122** layer materials may be SiN, SiO₂, a combination of SiN and SiO₂, SiON, SiCN, SiOCN, or the like. The gate mask **122** material layer may be formed by known deposition techniques such PVD, CVD, ALD, or the like. The gate mask **122** material layer can have a thickness of from about 1 nm to about 200 nm, although other thicknesses are within the contemplated scope.

(24) Utilizing known patterning, lithography, etching, etc. techniques, undesired portions of the gate mask **122** material layer may be removed, followed by further removal of the sacrificial gate **110** material layer that is not covered by an associated gate mask **122**, while desired portions of the sacrificial gate **120** material layer thereupon may be retained. These retained features may respectively form one or more sacrificial gates **120** with a gate mask **122** thereupon. The combined structure of the sacrificial gate **120** and the associated gate mask **122** thereupon may be referred herein as a sacrificial gate structure. Multiple sacrificial gate structures may be arranged in an in-out of the page perspective, with respect to the exemplary cross section of FIG. 1. In some

embodiments, a gate spacer may be formed upon each of the opposing sidewalls of the sacrificial gate structure(s), as is known in the art.

(25) FIG. 2 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include a partial gate cut region **130** physically separates sacrificial gate **121** within first device region **103** from sacrificial gate **123** within second device region **105**.

(26) In a particular implementation, an undesired portion of gate mask **124** may be removed to expose a portion of the sacrificial gate **120** there below. The undesired portion of gate mask **124** may be removed known removal techniques such as e.g., patterning, lithography, etching, or the like. The removal of the portion of gate mask **124** splits the gate mask **122** into at least gate mask **124** located within first device region **103** and gate mask **126** located within second device region **105**.

(27) Subsequently, the unprotected portion of the sacrificial gate **120** may be removed to form partial gate cut region **130**. The unprotected portion of the sacrificial gate **120** may be removed known removal techniques such as e.g., patterning, lithography, etching, or the like. The removal of the unprotected portion of sacrificial gate **120** splits the sacrificial gate **120** into at least sacrificial gate **121** located within first device region **103** and sacrificial gate **123** located within second device region **105**.

(28) Partial gate cut region **130** may be an opening, trench, or the like, and may include an inner facing sidewall(s) of gate mask **124**, an inner facing sidewall(s) of sacrificial gate **121**, an inner facing sidewall(s) of gate mask **126**, and an inner facing sidewall(s) of sacrificial gate **123**. A bottom or well surface of the partial gate cut region **130** may be at least an exposed portion of the upper surface of STI **112**.

(29) FIG. 3 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include a gate cut region **132** that physically separates sacrificial gate **121** within first device region **103** from sacrificial gate **123** within second device region **105** and that physically separates STI **113** within first device region **103** from STI **115** within second device region **105**.

(30) In a particular implementation, the portion of the upper surface of STI **112** exposed by partial gate cut region **130** may be removed to expose a portion of the substrate **102** there below. This portion of the upper surface of STI **112** may be removed known removal techniques such as e.g., patterning, lithography, etching, punch-through processing, or the like. The removal of this portion of the upper surface of STI **112** splits STI **112** into at STI **113** located within first device region **103** and STI **115** located within second device region **105**.

(31) Gate cut region **132** may be an opening, trench, or the like, and may include an inner facing sidewall(s) of gate mask **124**, an inner facing sidewall(s) of sacrificial gate **121**, an inner facing sidewall(s) of gate mask **126**, an inner facing sidewall(s) of sacrificial gate **123**, an inner facing sidewall(s) of STI **113**, and an inner facing sidewall(s) of STI **115**.

(32) In embodiments, as depicted, a bottom or well surface of the gate cut region **132** may be at least an exposed portion of the upper surface substrate **102**. In some embodiments, the bottom or well surface of the gate cut region **132** may be at least an exposed portion of substrate **102** that is below the upper surface substrate **102**. In other words, gate cut region **132** may extend below the top surface of substrate **102** by way of further removal of a portion of the substrate **102**. An example of this type of gate cut region extending below the top surface of the substrate **102** is exemplary shown in FIG. 11.

(33) FIG. 4 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include a sacrificial gate cut plug **140** within gate cut region **132**. The sacrificial gate cut plug **140** physically separates sacrificial gate **121** from sacrificial gate **123**

and physically separates STI **113** from STI **115**.

(34) Sacrificial gate cut plug **140** may be formed by depositing a dielectric material upon substrate **102** and upon the inner facing sidewalls of gate cut region **132**. For example, the sacrificial gate cut plug **140** can be formed by any suitable techniques such as deposition (ALD, CVD, etc.).

(35) Sacrificial gate cut plug **140** can have a width of from about 30 nm to about 200 nm. In some embodiments, the sacrificial gate cut plug **140** can have a width of from about 5 nm to about 50 nm, although other widths are within the contemplated scope of the invention. Exemplary sacrificial gate cut plug **140** material may be but are not limited to: silicon nitride (SiN), silicon carbide (SiC), silicon oxynitride (SiON), carbon-doped silicon oxide (SiOC), silicon-carbon-nitride (SiCN), boron nitride (BN), silicon boron nitride (SiBN), silicoboron carbonitride (SiBCN), silicon oxycarbonitride (SiOCN), silicon oxide, a sacrificial metal upon a liner as an insulator, combinations thereof, etc. The sacrificial gate cut plug **140** can be a low-k material having a dielectric constant less than about 7, less than about 5.

(36) After formation of sacrificial gate cut plug **140**, excessive sacrificial gate cut plug **140** material can be removed by an etching or polish process, such as a chemical mechanical polish (CMP). Removal of the excess sacrificial gate cut plug **140** material can be accomplished using, for example, a selective wet etch process, or a selective dry etch process, or other subtractive removal technique, as is known in the art. As such, the top surface of gate mask **124**, gate mask **126**, and sacrificial gate cut plug **140** may be coplanar.

(37) Though not shown or described semiconductor structure **100** may undergo interim fabrication operations, such as source and drain formation, or the like, prior to the fabrication of replacement gate structures, as described below. Such fabrication techniques and structures are known and are omitted here.

(38) FIG. 5 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include a replacement gate structure formed in place of each sacrificial gate structure. For example, a replacement gate structure within the first device region **103** may be formed by initially removing the sacrificial gate **121** and gate mask **124** associated therewith, forming a gate dielectric **152** upon STI **113** and upon fins **110**, forming a gate conductor, hereinafter referred to as replacement gate **150**, upon the gate dielectric **152**, and with forming a gate cap **151** upon the replacement gate **150**.

(39) Likewise, a replacement gate structure within the second device region **105** may be formed by initially removing the sacrificial gate **123** and gate mask **126** associated therewith, forming a gate dielectric **156** upon STI **115** and upon fins **114**, forming a gate conductor, hereinafter referred to as replacement gate **154**, upon the gate dielectric **156**, and with forming a gate cap **155** upon the replacement gate **154**.

(40) Gate dielectric **152**, **156** can comprise any suitable dielectric material, including but not limited to silicon oxide, silicon nitride, silicon oxynitride, high-k materials, or any combination of these materials. Examples of high-k materials include but are not limited to metal oxides such as hafnium oxide, hafnium silicon oxide, hafnium silicon oxynitride, lanthanum oxide, lanthanum aluminum oxide, zirconium oxide, zirconium silicon oxide, zirconium silicon oxynitride, tantalum oxide, titanium oxide, barium strontium titanium oxide, barium titanium oxide, strontium titanium oxide, yttrium oxide, aluminum oxide, lead scandium tantalum oxide, and lead zinc niobate. The high-k may further include dopants such as lanthanum, aluminum, magnesium. The gate dielectric **152**, **156** material can be formed by any suitable deposition process or the like. In some embodiments, the gate dielectric **152**, **156** material has a thickness ranging from 1 nm to 5 nm, although less thickness and greater thickness are also conceived.

(41) Replacement gate **150**, **154** may be formed of any suitable conductive material, including but not limited to, doped polycrystalline or amorphous silicon, germanium, silicon germanium, a metal (e.g., tungsten (W), titanium (Ti), tantalum (Ta), ruthenium (Ru), hafnium (Hf), zirconium (Zr),

cobalt (Co), nickel (Ni), copper (Cu), aluminum (Al), platinum (Pt), tin (Sn), silver (Ag), gold (Au), a conducting metallic compound material (e.g., tantalum nitride (TaN), titanium nitride (TiN), tantalum carbide (TaC), titanium carbide (TiC), titanium aluminum carbide (TiAlC), tungsten silicide (WSi), tungsten nitride (WN), ruthenium oxide (RuO₂), cobalt silicide (CoSi), nickel silicide (NiSi)), transition metal aluminides (e.g. Ti₃Al, ZrAl), TaC, TaMgC, carbon nanotube, conductive carbon, graphene, or any suitable combination of these materials. The conductive material may further comprise dopants that are incorporated during or after deposition.

(42) In some embodiments, the replacement gate structure may further include a work function setting layer between the gate dielectric **152**, **156** and replacement gate **150**, **154**, respectively. The work function setting layer can be a work function metal (WFM). WFM can be any suitable material, including but not limited a nitride, including but not limited to titanium nitride (TiN), titanium aluminum nitride (TiAlN), hafnium nitride (HfN), hafnium silicon nitride (HfSiN), tantalum nitride (Ta₂N₅), tantalum silicon nitride (TaSiN), tungsten nitride (WN), molybdenum nitride (MoN), niobium nitride (NbN); a carbide, including but not limited to titanium carbide (TiC) titanium aluminum carbide (TiAlC), tantalum carbide (TaC), hafnium carbide (HfC), and combinations thereof. In some embodiments, a conductive material or a combination of multiple conductive materials can serve as both replacement gate **150**, **154**, respectively, and the WFM.

(43) Replacement gate **150**, **154** and the WFM (if present) can be formed by any suitable process or any suitable combination of multiple processes, including but not limited to, ALD, CVD, PVD, sputtering, plating, evaporation, ion beam deposition, electron beam deposition, laser assisted deposition, chemical solution deposition, etc.

(44) Subsequently, a gate cap **151** may be formed upon the replacement gate **150** and a gate cap **155** may be formed upon the replacement gate **154**. The gate cap **151**, **155** may be a hard mask, or the like. Exemplary gate cap **151**, **155** materials may be SiN, SiO₂, a combination of SiN and SiO₂, SiON, SiCN, SiOCN, or the like. The gate cap **151**, **155** may be formed by known deposition techniques such PVD, CVD, ALD, or the like. The gate cap **151**, **155** material can have a thickness of from about 1 nm to about 200 nm, although other thicknesses are within the contemplated scope.

(45) After formation of replacement gate structures, excessive gate cap **151**, **155** materials can be removed by an etching or polish process. Removal of the excess gate cap **151**, **155** materials can be accomplished using, for example, a selective wet etch process, or a selective dry etch process, or other subtractive removal technique, as is known in the art. As such, the top surface of gate cap **151**, **155** and sacrificial gate cut plug **140** may be coplanar.

(46) FIG. 6 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include an re-formed or otherwise re-exposed gate cut region **132**. The gate cut region **132** may be re-exposed by removing sacrificial gate cut plug **140** therewithin.

(47) After such exposure, gate cut region **132** may include inner facing sidewall(s) of gate mask **151**, inner facing sidewall(s) of replacement gate **150**, inner facing sidewall(s) of gate dielectric **152**, and inner facing sidewall(s) of STI **113**. Similarly, gate cut region **132** may include inner facing sidewall(s) of gate mask **155**, inner facing sidewall(s) of replacement gate **154**, inner facing sidewall(s) of gate dielectric **156**, and inner facing sidewall(s) of STI **115**. Further, after such exposure gate cut region **132** may also include a bottom or well surface as an exposed portion of the substrate **102**.

(48) FIG. 7 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include a gate cut stressor **170** within gate cut region **132**. The gate cut stressor **170** physically separates gate cap **151**, replacement gate **150**, gate dielectric **152**, and STI **113** from the second device region **105**. Similarly, the gate cut stressor **170** physically separates gate cap **155**, replacement gate **154**, gate dielectric **156**, and STI **115** from the first device region

103.

(49) Gate cut stressor **170** may be formed by depositing a dielectric material upon substrate **102** and upon the inner facing sidewalls of gate cut region **132**.

(50) Gate cut stressor **170** can have a width of from about 30 nm to about 200 nm. In some embodiments, the sacrificial gate cut stressor **170** can have a width of from about 5 nm to about 50 nm, although other widths are within the contemplated scope of the invention. Exemplary sacrificial gate cut stressor **170** material may be but are not limited to: SiN, SiC, SiON, SiOC, SiCN, BN, SiBN, SiBCN, SiOCN, SiO.sub.x, a replacement metal upon a liner as an insulator, combinations thereof, etc. Further, the gate cut stressor **170** can be a low-k material having a dielectric constant less than about 7, less than about 5.

(51) After formation of gate cut stressor **170**, excessive gate cut stressor **170** material can be removed by an etching or polish process, such as a chemical mechanical polish (CMP). Removal of the excess gate cut stressor **170** material can be accomplished using, for example, a selective wet etch process, or a selective dry etch process, or other subtractive removal technique, as is known in the art. As such, the top surface of gate cap **151**, gate cap **155**, and gate cut stressor **170** may be coplanar.

(52) Gate cut stressor **170** has an internal or intrinsic tension or stress, such that there is an internally generated effective force $T_{sub.170}$ that attempts to compress or shrink the gate cut stressor **170** internally pulling the adjacent the first device region **103** and toward the second device region **105** laterally or horizontally, as depicted. This internal tension applied to the gate material **150**, **154** creates tensile stress within the gate material **150**, **154** along the gate direction and within the fins **110**, **114** perpendicular to the fin **110**, **114** direction. In turn, this tensile stress may resultingly create a smaller compressive stress $TFI_{sub.170}$ along the fins **110**, **114** (into and/or out of the page, as depicted) through the stress mixing Poisson effect. These forces and stresses within fins **110**, **114** may improve hole mobility and/or electron mobility therewithin. In one embodiment, the fin **110**, **114** are aligned along $\langle 110 \rangle$ crystallographic direction and have $\{110\}$ oriented crystallographic sidewalls. In this arrangement, both hole mobility and electron mobility improve. Hole mobility is improved through the secondary compressive $TFI_{sub.170}$ force, while electron mobility is improved through the primary tensile $T_{sub.170}$ force. Here, electron mobility may improve by a larger factor. However, because both electron mobility and hole mobility may improve, the inclusion of gate cut stressor **170** may be particularly useful for CMOS switching devices.

(53) Gate cut stressor **170** may be formed by plasma enhanced chemical vapor deposition (PECVD), or the like, such that respective process parameters, such as composition of carrier gases and reactive gases, substrate temperature, deposition pressure and, in particular, ion bombardment during the deposition, may significantly influence the finally obtained intrinsic stress of gate cut stressor **170** as deposited with respect to the underlying or otherwise surrounding material(s). High level of intrinsic tensile stress in the gate cut stressor **170** can be also produced by an annealing or curing step that induces shrinkage of gate cut stressor **170** material. This additional step can be conducted immediately after gate cut stressor **170** material deposition or later in the process flow. In one example, such additional annealing or curing step detaches hydrogen from within the gate cut stressor **170** material, producing stretched chemical bonds within, that yield a high level of tensile intrinsic stress. For example, when gate cut stressor **170** is deposited and annealed within gate cut region **132** a high intrinsic tensile stress of up to 2 GPa or even significantly higher may be achieved by e.g., detaching hydrogen during or after deposition or, alternatively, reducing ion bombardment by establishing the deposition atmosphere with a low level of radio frequency (RF) power so as to obtain the desired internally generated effective force $T_{sub.170}$ that attempts to compress or shrink the gate cut stressor **170** internally away from both first device region **103** and second device region **105** laterally.

(54) FIG. 8 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication

operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include a gate cut stressor **180** within gate cut region **132**. The gate cut stressor **180** physically separates gate cap **151**, replacement gate **150**, gate dielectric **152**, and STI **113** from the second device region **105**. Similarly, the gate cut stressor **180** physically separates gate cap **155**, replacement gate **154**, gate dielectric **156**, and STI **115** from the first device region **103**.

(55) Gate cut stressor **180** may be formed by depositing dielectric material(s), different than the dielectric material(s) of gate cut stressor **170**, upon substrate **102** and upon the inner facing sidewalls of gate cut region **132**.

(56) Gate cut stressor **180** can have a width of from about 30 nm to about 200 nm. In some embodiments, the sacrificial gate cut stressor **170** can have a width of from about 5 nm to about 50 nm, although other widths are within the contemplated scope of the invention. Exemplary sacrificial gate cut stressor **180** material may be but are not limited to: SiN, SiC, SiON, SiOC, SiCN, BN, SiBN, SiBCN, SiOCN, SiO.sub.x, a replacement metal upon a liner as an insulator, combinations thereof, etc. The gate cut stressor **180** can be a

(57) After formation of gate cut stressor **180**, excessive gate cut stressor **180** material can be removed by an etching or polish process, such as a chemical mechanical polish (CMP). Removal of the excess gate cut stressor **180** material can be accomplished using, for example, a selective wet etch process, or a selective dry etch process, or other subtractive removal technique, as is known in the art. As such, the top surface of gate cap **151**, gate cap **155**, and gate cut stressor **180** may be coplanar.

(58) Gate cut stressor **180** has an internal or intrinsic tension or stress, such that there is an internally generated effective force $T_{sub.180}$ that attempts to compress or shrink the gate cut stressor **180** internally pulling adjacent the first device region **103** and toward the second device region **105** laterally or horizontally, as depicted. This internal tension applied to the gate material **150**, **154** creates tensile stress within the gate material **150**, **154** along the gate direction and within the fins **110**, **114** perpendicular to the fin **110**, **114** direction. In turn, this tensile stress may resultingly create a smaller compressive stress $TFI_{sub.180}$ along the fins **110**, **114** (into and/or out of the page, as depicted) through the stress mixing Poisson effect. These forces and stresses within fins **110**, **114** may improve hole mobility and/or electron mobility therewithin. In one embodiment, the fins **110**, **114** are aligned along $\langle 110 \rangle$ crystallographic direction and have $\{110\}$ oriented crystallographic sidewalls. In this arrangement, both hole mobility and electron mobility improve. Hole mobility is improved through the secondary compressive $TFI_{sub.180}$ force, while electron mobility is improved through the primary tensile $T_{sub.180}$ force. Here, electron mobility may improve by a larger factor. However, because both electron mobility and hole mobility may improve, the inclusion of gate cut stressor **180** may be particularly useful for CMOS switching devices.

(59) Gate cut stressor **180** may be formed by PECVD, or the like, such that respective process parameters, such as composition of carrier gases and reactive gases, substrate temperature, deposition pressure and, in particular, ion bombardment during the deposition, may significantly influence the finally obtained intrinsic stress of gate cut stressor **180** as deposited with respect to the underlying or otherwise surrounding material(s). High level of intrinsic tensile stress in the gate cut stressor **180** can be also produced by an annealing or curing step that induces shrinkage of gate cut stressor **180** material. This additional step can be conducted immediately after gate cut stressor **180** deposition or later in the process flow. In one example, such additional annealing or curing step detaches hydrogen from within the gate cut stressor **180** material producing stretched chemical bonds within that yield a high level of tensile intrinsic stress. For example, when gate cut stressor **180** is deposited and annealed within gate cut region **132** a high intrinsic tensile stress of up to 2 GPa or even significantly higher may be achieved by e.g., detaching hydrogen during or after deposition or, alternatively, reducing ion bombardment by establishing the deposition atmosphere

with a low level of radio frequency (RF) power so as to obtain the desired internally generated effective force $T_{sub.180}$ that attempts to compress or shrink the gate cut stressor **180** internally away from both first device region **103** and second device region **105** laterally.

(60) For clarity, it is to be understood that semiconductor structure **100** may include a first gate cut region **132** that contains gate cut stressor **170** therewithin, as is depicted in FIG. 7 and may further include a different second gate cut region **132** that contains gate cut stressor **180**, therewithin, as is depicted in FIG. 8.

(61) FIG. 9 depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include gate cut stressor **180** and gate cut stressor **170** within gate cut region **132**. Gate cut stressor **170** may be located in a lower portion of gate cut region **132** and gate cut stressor **180** may be located in an upper portion of gate cut region **132**, or vice versa.

(62) The gate cut stressors **170**, **180** physically separate gate cap **151**, replacement gate **150**, gate dielectric **152**, and/or STI **113** from the second device region **105**, respectively. Similarly, the gate cut stressors **170**, **180** physically separates gate cap **155**, replacement gate **154**, gate dielectric **156**, and/or STI **115** from the first device region **103**, respectively.

(63) As depicted, gate cut stressor **170** may be initially formed by depositing the gate cut stressor **170** dielectric material upon substrate **102** and upon a lower portion of the inner facing sidewalls of gate cut region **132**. Subsequently, gate cut stressor **180** may be formed by depositing the gate cut stressor **180** dielectric material upon gate cut stressor **170** and upon an upper portion of the inner facing sidewalls of gate cut region **132**. Alternatively, subsequently to forming the gate cut stressor **170**, the gate cut stressor **180** can be formed by curing a top portion of the gate cut stressor **170**, thereby effectively forming gate cut stressor **180** that has a relatively higher tensile stress within as compared to the non-cured bottom portion of gate cut stressor **170**. In some implementations, curing the entire gate cut stressor **170** to cause a uniform intrinsic tensile stress may not be feasible due to a high aspect ratio of gate cut region **132**.

(64) Alternatively, gate cut stressor **180** may be initially formed by depositing the gate cut stressor **180** dielectric material upon substrate **102** and upon a lower portion of the inner facing sidewalls of gate cut region **132**. Subsequently, gate cut stressor **170** may be formed by depositing the gate cut stressor **170** dielectric material upon gate cut stressor **180** and upon an upper portion of the inner facing sidewalls of gate cut region **132**.

(65) After formation of gate cut stressor **170**, **180**, excessive gate cut stressor **170**, **180** material can be removed by an etching or polish process. As such, the top surface of gate cap **151**, gate cap **155**, and gate cut stressor **170** or gate cut stressor **180** may be coplanar.

(66) The internally generated tensile force $T_{sub.180}$ is generally larger than internally generated tensile force $T_{sub.170}$. Because the Fin FETs are typically formed in the upper portion of the fins **110**, **114**, the positive effect of $T_{sub.180}$ may be dominant. This internal tension applied to the gate material **150**, **154** creates tensile stress within the gate material along the gate direction and within the fins **110**, **114** perpendicular to the fin **110**, **114** direction. In turn, this tensile stress may resultingly create a smaller compressive stress $TFI_{sub. eff}$ along the fins **110**, **114** (into and/or out of the page, as depicted) through the stress mixing Poisson effect. These forces and stresses within fins **110**, **114** may improve hole mobility and/or electron mobility therewithin. In one embodiment, the fin **110**, **114** are aligned along $\langle 110 \rangle$ crystallographic direction and have $\{110\}$ oriented crystallographic sidewalls. For this arrangement, both hole mobility and electron mobility improve. While electron mobility may improve by a larger factor, the fact that both electron mobility and hole mobility may improve with gate cut stressor **170**, **180** may be particularly useful for CMOS switching devices.

(67) In implementations where relatively improved hole mobility or electron mobility would be beneficial in an upper region of fins **110**, **114**, it may be beneficial to initially form gate cut stressor **170** within the lower portion of gate cut region **132** and then to subsequently form gate cut stressor

180 upon the gate cut stressor **170** within an upper portion of gate cut region **132**.

(68) Alternatively, in implementations where relatively improved hole mobility or electron mobility would be beneficial in an lower region of fins **110**, **114**, it may be beneficial to initially form gate cut stressor **180** within the lower portion of gate cut region **132** and then to subsequently form gate cut stressor **170** upon the gate cut stressor **180** within the upper portion of gate cut region **132**.

(69) FIG. **10** depicts a cross-sectional view of semiconductor structure **100** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **100** may include gate cut stressor **180** and gate cut stressor **170** within gate cut region **132**. Gate cut stressor **170** may be a liner upon the internal sidewalls of gate cut region **132** and gate cut stressor **180** may be located upon gate cut stressor **170** and filling the remaining gate cut region **132**, or vice versa.

(70) The gate cut stressors **170**, **180** physically separate gate cap **151**, replacement gate **150**, gate dielectric **152**, and/or STI **113** from the second device region **105**, respectively. Similarly, the gate cut stressors **170**, **180** physically separates gate cap **155**, replacement gate **154**, gate dielectric **156**, and/or STI **115** from the first device region **103**, respectively.

(71) As depicted, gate cut stressor **170** may be initially formed by depositing the gate cut stressor **170** dielectric material upon substrate **102** and upon the inner facing sidewalls of gate cut region **132**. This gate cut stressor **170** liner layer can have a thickness of from about 1 nm to about 20 nm, although other thicknesses are within the contemplated scope. Subsequently, gate cut stressor **180** may be formed by depositing the gate cut stressor **180** dielectric material upon gate cut stressor **170** and may generally fill the remaining gate cut region **132**.

(72) Alternatively, gate cut stressor **180** may be initially formed by depositing the gate cut stressor **180** dielectric material upon substrate **102** and upon the inner facing sidewalls of gate cut region **132**. This gate cut stressor **180** liner layer can have a thickness of from about 1 nm to about 20 nm, although other thicknesses are within the contemplated scope. Subsequently, gate cut stressor **170** may be formed by depositing the gate cut stressor **170** dielectric material upon gate cut stressor **180** and may generally fill the remaining gate cut region **132**.

(73) After formation of gate cut stressor **170**, **180**, excessive gate cut stressor **170**, **180** material can be removed by an etching or polish process. As such, the top surface of gate cap **151**, gate cap **155**, gate cut stressor **170**, and gate cut stressor **180** may be coplanar.

(74) The internally generated tensile force $T_{sub,eff}$ applies stress to the gate material **150/154** creating tensile stress within the gate material along the gate direction and within the fins **110**, **114** perpendicular to the fin direction. In turn, this tensile stress may resultingly create a smaller compressive stress $TFI_{sub,eff}$ along the fins **110**, **114** (into and/or out of the page, as depicted) through the stress mixing Poisson effect. These forces and stresses within fins **110**, **114** may improve hole mobility and/or electron mobility therewithin, as described herein.

(75) FIG. **11** depicts a cross-sectional view of semiconductor structure **200** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **200** may include a first device region **203**, a second device region **205**, a substrate **102**, one or more channel nanosheets **210** within the first device region **203**, one or more channel nanosheets **214** within second device region **205**, replacement gate **150** upon the substrate **102** and around the one or more channel nanosheets **210**, gate cap **151** upon the replacement gate **150**, replacement gate **154** upon the substrate **102** and around the one or more channel nanosheets **214**, gate cap **155** upon the replacement gate **150**, and gate cut stressor **170**. Nanosheets **210** and **214** have surfaces **210a** and **210b** and **214a** and **214b**, respectively, as depicted. In one embodiment, **210a** and **214a** surfaces have {100} crystallographic orientation and **210b** and **214b** surface have {110} crystallographic orientation and nanosheets **210**, **214** channel and current flow therewithin is oriented along <110> crystallographic direction.

(76) First device region **203** may include a N-type nanosheet transistor and second device region **205** may include a P-type nanosheet transistor, or vice versa. As such, the transistor within first

device region **203** may be of a first dopant type and the transistor within the second device region **205** may be of a second dopant type. Alternatively, first device region **203** may include a first N-type nanosheet transistor and second device region **205** may include a second N-type nanosheet transistor. Similarly, first device region **203** may include a first P-type nanosheet transistor and second device region **205** may include a second P-type nanosheet transistor. As such, the transistor(s) within first device region **203** and within the second device region **205** may be of the same dopant type.

(77) Generally, first device region **203** and second device region **205** may be associated with transistor(s) that are associated with physically and/or electrically distinct or separated replacement gates **150**, **154**. For example, the nanosheet transistor within first device region **203** has replacement gate **150** and the nanosheet transistor within second device region **205** has replacement gate **154** that is physically and electrically distinct, isolated, and/or separated from replacement gate **150** by gate cut region **132**.

(78) Initial fabrication operations of semiconductor device **200** may include forming the substrate **102**, forming alternating layers of sacrificial nanosheets and channel nanosheets, and forming a mask layer upon a top sacrificial nanosheet layer. The channel nanosheet layers may be formed from silicon (Si), and the sacrificial nanosheet layers may be formed from silicon germanium (SiGe). The channel nanosheet layers can include, for example, monocrystalline Si. The channel nanosheet layers can have a thickness of, for example, from about 4 to about 10 nm, from about 4 to about 7 nm, or of about 7 nm. In embodiments where the sacrificial nanosheet layers include SiGe, for example, SiGe having a Ge concentration of about 25 atomic percent. The sacrificial nanosheet layers can have a thickness of, for example, about 12 nm. The mask layer may be formed by depositing known hard mask material(s) upon the top sacrificial nanosheet layer.

(79) In some embodiments, the alternating series of sacrificial nanosheet layers and channel nanosheet layers are formed by epitaxially growing one layer and then the next until the desired number and desired thicknesses of such layers are achieved. Epitaxial materials can be grown from gaseous or liquid precursors. Epitaxial materials can be grown using vapor-phase epitaxy (VPE), molecular-beam epitaxy (MBE), liquid-phase epitaxy (LPE), or other suitable process. Epitaxial silicon, silicon germanium, and/or carbon doped silicon (Si:C) silicon can be doped during deposition (in-situ doped) by adding dopants, n-type dopants (e.g., phosphorus or arsenic) or p-type dopants (e.g., boron or gallium), depending on the type of transistor.

(80) The terms “epitaxial growth and/or deposition” and “epitaxially formed and/or grown” mean the growth of a semiconductor material (crystalline material) on a deposition surface of another semiconductor material (crystalline material), in which the semiconductor material being grown (crystalline overlayer) has substantially the same crystalline characteristics as the semiconductor material of the deposition surface (seed material). In an epitaxial deposition process, the chemical reactants provided by the source gases are controlled and the system parameters are set so that the depositing atoms arrive at the deposition surface of the semiconductor substrate with sufficient energy to move about on the surface such that the depositing atoms orient themselves to the crystal arrangement of the atoms of the deposition surface. Therefore, an epitaxially grown semiconductor material has substantially the same crystalline characteristics as the deposition surface on which the epitaxially grown material is formed. For example, an epitaxially grown semiconductor material deposited on a {100} orientated crystalline surface will take on a {100} orientation. In some embodiments of the invention, epitaxial growth and/or deposition processes are selective to forming on semiconductor surfaces, and generally do not deposit material on exposed surfaces, such as silicon dioxide or silicon nitride surfaces.

(81) In some embodiments of the invention, the gas source for the deposition of epitaxial semiconductor material include a silicon containing gas source, a germanium containing gas source, or a combination thereof. For example, an epitaxial silicon layer can be deposited from a silicon gas source that is selected from the group consisting of silane, di silane, trisilane, tetrasilane,

hexachlorodisilane, tetrachlorosilane, dichlorosilane, trichlorosilane, methyl silane, dimethylsilane, ethyl silane, methylsilane, dimethylsilane, hexamethylsilane and combinations thereof. An epitaxial germanium layer can be deposited from a germanium gas source that is selected from the group consisting of germane, digermane, halogermane, dichlorogermane, trichlorogermane, tetrachlorogermane and combinations thereof. While an epitaxial silicon germanium alloy layer can be formed utilizing a combination of such gas sources. Carrier gases like hydrogen, nitrogen, helium, and argon can be used.

(82) Next, the sacrificial nanosheet layers and channel nanosheet layers may be patterned by removing respective undesired portions while retaining respective desired portions. Similarly, the mask layer may be patterned by removing respective undesired portions while retaining respective desired portions, as depicted.

(83) The removal of undesired portions of sacrificial nanosheets, removal of undesired portions of the channel nanosheets, and removal of undesired portions of the mask layer can be accomplished using, for example, a sidewall image transfer (SIT) operation, a wet etch process, or a dry etch process. The removal of such undesired portions may further remove undesired portions of substrate **102** there below. Such removal may form a gate cut trench between the first device region **203** and the second device region **205**.

(84) Desired portions of sacrificial nanosheet layers, desired portions of the channel nanosheet layers, and desired portions of the mask may be retained and generally form respective nanosheet stacks within first device region **203** and within second device region **205**.

(85) A sacrificial gate cut plug may be formed within the gate cut trench by depositing a first dielectric material upon the substrate **102** and between the respective nanosheet stacks within the first device region **203** and within the second device region **205**. For example, the sacrificial gate cut plug can be formed by any suitable techniques such as deposition (ALD, CVD, etc.) followed by directional etch. As such, the sacrificial gate cut plug physically and, at least partially, electrically separates the respective nanosheet stacks within first device region **203** and within the second device region **205**. The sacrificial gate cut plug can have a width of from about 5 nm to about 40 nm. In some embodiments, the sacrificial gate cut plug can have a width of from about 10 nm to about 20 nm, although other widths are within the contemplated scope of the invention. Exemplary sacrificial gate cut plug materials may be, but are not limited to: SiN, SiC, SiON, SiOC, SiCN, BN, SiBN, SiBCN, SiOCN, SiO.sub.x, combinations thereof, etc. The sacrificial gate cut plug can be a low-k material having a dielectric constant less than about 7, less than about 5.

(86) After deposition, excessive sacrificial gate cut plug material can be removed by etching back or polish process. Removal of the mask **118** can be accomplished using, for example, a selective wet etch process, or a selective dry etch process, or other subtractive operation, as is known in the art.

(87) Next a sacrificial gate within the first device region **203** and a sacrificial gate within the second device region **205** may be formed by initially depositing a sacrificial gate liner (e.g. a dielectric, oxide, or the like) upon substrate **102** and upon the nanosheet stacks within the first device region **203** and within the second device region **205**. The gate dielectric may also be formed around exposed portions of the sacrificial gate cut plug. The sacrificial gates may further be formed by subsequently depositing a sacrificial gate material (e.g. a dielectric, amorphous silicon, or the like) upon the sacrificial gate liner. A CMP may planarize the upper surface of the sacrificial gates and the sacrificial gate cut plug. A gate mask may be formed upon the top surface of the sacrificial gates, respectively, and gate spacers may be formed upon opposing sidewalls of the sacrificial gates.

(88) Gate spacers may laterally abut each sacrificial gate and associated gate mask. Gate spacers may be formed, e.g., by a combination of deposition and etching, over the initial structure of nanosheet stack and laterally adjacent to sacrificial gate and gate mask. Gate spacers may be comprised of a variety of different materials, such as silicon nitride, SiBCN, SiNC, SiN, SiCO, and

SiNOC, etc., and they may each be made of the same or different materials.

(89) The channel nanosheets **210, 214** may be exposed by laterally recessing alternating nanosheets to yield a plurality of recesses in each nanosheet stack. The lateral recessing of alternating nanosheets can be provided, e.g., by application of a wet etchant selective to the composition of the sacrificial nanosheets (e.g., SiGe or similar crystalline semiconductors), and which leaves other structures (e.g., substrate **102**, channel nanosheets **210, 214**, etc.) substantially intact.

(90) Channel nanosheet spacers may be formed by depositing an insulative material, such as a dielectric, can be deposited to pinch off these previously formed recesses to yield a channel nanosheet spacer positioned therewithin, (e.g., between alternating channel nanosheets **210, 214** within the nanosheet stack).

(91) Source or Drain (S/D) regions may be formed by epitaxially growing a source/drain epitaxial region between respective pairs of nanosheet stacks, e.g., from exposed sidewalls of channel nanosheets **210, 214** and upper surface of substrate **102**. In some embodiments, the S/D region(s) is formed by in-situ doped epitaxial growth. In some embodiments, epitaxial growth and/or deposition processes may be selective to forming on semiconductor surfaces, and may not deposit material on dielectric surfaces, such as silicon dioxide or silicon nitride surfaces.

(92) Suitable n-type dopants include but are not limited to phosphorous (P), and suitable p-type dopants include but are not limited to boron (B). The use of an in-situ doping process is merely an example. For instance, one may instead employ an ex-situ process to introduce dopants into the source and drains. Other doping techniques can be used to incorporate dopants in the bottom source/drain region. Dopant techniques include but are not limited to, ion implantation, gas phase doping, plasma doping, plasma immersion ion implantation, cluster doping, infusion doping, liquid phase doping, solid phase doping, in-situ epitaxy growth, or any suitable combination of those techniques. In preferred embodiments the source drain epitaxial growth conditions that promote in-situ boron doped SiGe for P-type and phosphorus or arsenic doped silicon or Si:C for N-Type. The doping concentration in S/D can be in the range of $1 \times 10^{19} \text{ cm}^{-3}$ to $2 \times 10^{21} \text{ cm}^{-3}$, or preferably between $2 \times 10^{20} \text{ cm}^{-3}$ to $7 \times 10^{20} \text{ cm}^{-3}$.

(93) Next, replacement gates may be formed. The replacement gates may be formed by exposing and removing the sacrificial gates, removing the remaining sacrificial nanosheets in the gate region, and forming replacement gates around the exposed portions of the channel nanosheets **210, 214**.

(94) Each replacement gate can comprise the gate dielectric **152**, gate conductor(s) **150, 154**, hereinafter referred to as replacement gates, and gate cap **151, 155**, respectively. The replacement gates **150, 154** may include two inline gate structures with a first gate structure located in the first device region **203** and a second gate structure located in the second device region **205**. These formed gates structures may be physically and, at least partially electrically, separated by the sacrificial gate cut plug material within the gate cut region **132**.

(95) Subsequently, the gate cut region **132** may be re-formed or otherwise re-exposed by removing the sacrificial gate cut plug therewithin. After such exposure, gate cut region **132** may include inner facing sidewall(s) of gate mask **151**, inner facing sidewall(s) of replacement gate **150**, and inner facing sidewall portion(s) of substrate **102**. Similarly, gate cut region **132** may include inner facing sidewall(s) of gate mask **155**, inner facing sidewall(s) of replacement gate **154**, and inner facing sidewall portion(s) of substrate **102**. Further, after such exposure gate cut region **132** may also include a bottom or well surface as an exposed recessed portion of the substrate **102** that is below the top surface of substrate **102**.

(96) FIG. **11** depicts a cross-sectional view of semiconductor structure **200** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **200** may include gate cut stressor **170** within gate cut region **132**. The gate cut stressor **170** physically separates gate cap **151**, replacement gate **150**, and a portion of substrate **102** from the second device region **205**. Similarly, the gate cut stressor **170** physically separates gate cap **155**, replacement gate **154**, and a portion of substrate **102** from the first device region **203**.

(97) Gate cut stressor **170** may be formed by depositing a dielectric material upon substrate **102** and upon the inner facing sidewalls of gate cut region **132**. After formation of gate cut stressor **170**, excessive gate cut stressor **170** material can be removed by an etching or polish process. Removal of the excess gate cut stressor **170** material can be accomplished using, for example, a selective wet etch process, or a selective dry etch process, or other subtractive removal technique, as is known in the art. As such, the top surface of gate cap **151**, gate cap **155**, and gate cut stressor **170** may be coplanar.

(98) Gate cut stressor **170** has an internal or intrinsic tension or stress, such that there is an internally generated effective force $T_{sub.170}$ that attempts to compress or shrink the gate cut stressor **170** internally pulling first device region **203** and toward the second device region **205** laterally or horizontally, as depicted. This internal tension applied to the gate material **150**, **154** creates tensile stress within the gate material along the gate direction and within the nanosheets **210**, **214** perpendicular to the nanosheet **210**, **214** channel and current flow direction. In turn, this tensile stress may resultingly create a smaller compressive stress $TFI_{sub.170}$ along nanosheets **210**, **214** channel and current direction (into and/or out of the page, as depicted) through the stress mixing Poisson effect. These forces and stresses within nanosheets **210**, **214** may improve hole mobility and/or electron mobility therewithin.

(99) In one embodiment, the channels of nanosheets **210**, **214** are aligned along $\langle 110 \rangle$ crystallographic direction, nanosheet surfaces **210a** and **214a** are $\{100\}$ oriented, and nanosheet surfaces **210b** and **214b** are $\{110\}$ oriented. In this arrangement, both hole mobility and electron mobility may improve on all surfaces **210a**, **210b**, **214a**, and **214b**. On surfaces **210a** and **214a**, hole mobility is improved through the primary tensile force $T_{sub.170}$ and through the secondary compressive force $TFI_{sub.170}$ while the electron mobility is improved through the primary tensile force $T_{sub.170}$. On these surfaces **210a** and **214a**, hole mobility may improve by a larger factor. On surfaces **210b** and **214b**, the hole mobility is improved through the secondary compressive $TFI_{sub.170}$ force while the electron mobility is improved through the primary tensile $T_{sub.170}$ force. On these surfaces **210b** and **214b**, the electron mobility improves by a larger factor. The relative ratio of electron mobility and hole mobility improvement depends on nanosheet **210**, **214** width (nanosheet lateral dimension in FIG. **11**) that sets the ratio between surfaces **210a/214a** and **210b/214b**. Because the nanosheet **210**, **214** width can be varied by design, the relative ratio of mobility improvement can be tuned in accordance with the specific circuit function. For CMOS logic switching circuits, wider nanosheets **210**, **214** may provide a larger hole mobility improvement and faster switching speed per given footprint. For CMOS SRAM cells, narrow nanosheets **210**, **214** may provide a larger electron mobility improvement and faster and more stable operation per given footprint.

(100) Gate cut stressor **170** may be formed PECVD, or the like, such that respective process parameters, such as composition of carrier gases and reactive gases, substrate temperature, deposition pressure and, in particular, ion bombardment during the deposition, may significantly influence the finally obtained intrinsic stress of gate cut stressor **170** as deposited with respect to the underlying or otherwise surrounding material(s). High level of intrinsic tensile stress in the gate cut stressor **170** can be also produced by an annealing or curing step that induces shrinkage of gate cut material. This additional step can be conducted immediately after gate cut stressor deposition or later in the process flow. In one example, such additional annealing or curing step detaches hydrogen from within the gate cut stressor material producing stretched chemical bonds within that yield a high level of tensile intrinsic stress. For example, when gate cut stressor **170** is deposited and annealed within gate cut region **132** a high intrinsic tensile stress of up to 2 GPa or even significantly higher may be achieved by e.g., detaching hydrogen during or after deposition or, alternatively, reducing ion bombardment by establishing the deposition atmosphere with a low level of radio frequency (RF) power so as to obtain the desired internally generated effective force $T_{sub.170}$ that attempts to compress or shrink the gate cut stressor **170** internally away from both

first device region **203** and second device region **205** laterally.

(101) FIG. **12** depicts a cross-sectional view of semiconductor structure **200** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **200** may include gate cut stressor **180** within gate cut region **132**. The gate cut stressor **180** physically separates gate cap **151**, replacement gate **150**, and a portion of substrate **102** from the second device region **205**. Similarly, the gate cut stressor **180** physically separates gate cap **155**, replacement gate **154**, and a portion of substrate **102** from the first device region **203**.

(102) Gate cut stressor **180** may be formed by depositing a dielectric material, different than the dielectric material of gate cut stressor **170**, upon substrate **102** and upon the inner facing sidewalls of gate cut region **132**. After formation of gate cut stressor **180**, excessive gate cut stressor **180** material can be removed by an etching or polish process. As such, the top surface of gate cap **151**, gate cap **155**, and gate cut stressor **180** may be coplanar.

(103) Gate cut stressor **180** has an internal or intrinsic tension or stress, such that there is an internally generated effective force $T_{sub.180}$ that attempts to compress or shrink the gate cut stressor **180** internally pulling first device region **203** and toward the second device region **205** laterally or horizontally, as depicted. This internal tension applied to the gate material **150**, **154** creates tensile stress within the gate material along the gate direction and within the nanosheets **210** and **214** perpendicular to the nanosheet **210** and **214** channel and current flow direction. In turn, this tensile stress may resultingly create a smaller compressive stress $TFI_{sub.180}$ along nanosheets **210** and **214** channel and current direction (into and/or out of the page, as depicted) through the stress mixing Poisson effect. These forces and stresses within nanosheets **210** and **214** may improve hole mobility and/or electron mobility therewithin.

(104) In one embodiment, the channels of nanosheets **210**, **214** are aligned along $\langle 110 \rangle$ crystallographic direction, nanosheet surfaces **210a** and **214a** are $\{100\}$ oriented, and nanosheet surfaces **210b** and **214b** are $\{110\}$ oriented. In this arrangement, both hole mobility and electron mobility improve on all surfaces **210a**, **210b**, **214a**, and **214b**. On surfaces **210a** and **214a**, hole mobility is improved through the primary tensile force $T_{sub.180}$ force and through the secondary compressive $TFI_{sub.180}$ force while electron mobility is improved through the primary tensile $T_{sub.180}$ force. On these surfaces **210a** and **214a**, hole mobility improves by a larger factor. On surfaces **210b** and **214b**, hole mobility is improved through the secondary compressive $TFI_{sub.180}$ force while electron mobility is improved through the primary tensile $T_{sub.180}$ force. On these surfaces **210b** and **214b**, electron mobility improves by a larger factor. The relative ratio of electron mobility and hole mobility improvement depends on nanosheet **210**, **214** width (nanosheet lateral dimension in FIG. **12**) that sets the ratio between surfaces **210a/214a** and **210b/214b**. Because the nanosheet **210**, **214** width can be varied by design, the relative ratio of mobility improvement can be tuned in accordance with the specific circuit function. For CMOS logic switching circuits, wider nanosheets **210**, **214** provide a larger hole mobility improvement and faster switching speed per given footprint. For CMOS SRAM cells, narrow nanosheets **210**, **214** provide a larger electron mobility improvement and faster and more stable operation per given footprint.

(105) Gate cut stressor **180** may be formed by PECVD, or the like, such that respective process parameters, such as composition of carrier gases and reactive gases, substrate temperature, deposition pressure and, in particular, ion bombardment during the deposition, may significantly influence the finally obtained intrinsic stress of gate cut stressor **180** as deposited with respect to the underlying or otherwise surrounding material(s). High level of intrinsic tensile stress in the gate cut stressor **180** can be also produced by an annealing or curing step that induces shrinkage of gate cut material. This additional step can be conducted immediately after gate cut stressor deposition or later in the process flow. In one example, such additional annealing or curing step detaches hydrogen from within the gate cut stressor material producing stretched chemical bonds within that yield a high level of tensile intrinsic stress. For example, when gate cut stressor **180** is deposited and annealed within gate cut region **132** a high intrinsic tensile stress of up to 2 GPa or even

significantly higher may be achieved by e.g., detaching hydrogen during or after deposition or, alternatively, reducing ion bombardment by establishing the deposition atmosphere with a low level of radio frequency (RF) power so as to obtain the desired internally generated effective force $T_{sub.180}$ that attempts to compress or shrink the gate cut stressor **180** internally away from both first device region **203** and second device region **205** laterally.

(106) FIG. **13** depicts a cross-sectional view of semiconductor structure **200** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **200** may include gate cut stressor **180** and gate cut stressor **170** within gate cut region **132**. Gate cut stressor **170** may be located in a lower portion of gate cut region **132** and gate cut stressor **180** may be located in an upper portion of gate cut region **132**, or vice versa.

(107) The gate cut stressors **170**, **180** physically separate gate cap **151**, replacement gate **150**, and/or a portion of substrate **102** from the second device region **205**, respectively. Similarly, the gate cut stressors **170**, **180** physically separates gate cap **155**, replacement gate **154**, and/or a portion of substrate **102** from the first device region **203**, respectively.

(108) As depicted, gate cut stressor **170** may be initially formed by depositing the gate cut stressor **170** dielectric material upon substrate **102**, upon sidewall portions of substrate **102**, and upon a lower portion of the inner facing sidewalls of gate cut region **132**. Subsequently, gate cut stressor **180** may be formed by depositing the gate cut stressor **180** dielectric material upon gate cut stressor **170** and upon an upper portion of the inner facing sidewalls of gate cut region **132**. Alternatively, subsequently to forming the gate cut stressor **170**, the gate cut stressor **180** can be formed by curing a top portion of the gate cut stressor **170**, thereby effectively forming gate cut stressor **108** that has a higher tensile stress within. In some implementations, curing the entire gate cut stressor **170** to cause a uniform intrinsic tensile stress may not be feasible due to a high aspect ratio of gate cut region **132**.

(109) Alternatively, gate cut stressor **180** may be initially formed by depositing the gate cut stressor **180** dielectric material upon substrate **102**, upon sidewall portions of substrate **102**, and upon a lower portion of the inner facing sidewalls of gate cut region **132**. Subsequently, gate cut stressor **170** may be formed by depositing the gate cut stressor **170** dielectric material upon gate cut stressor **180** and upon an upper portion of the inner facing sidewalls of gate cut region **132**.

(110) After formation of gate cut stressor **170**, **180**, excessive gate cut stressor **170**, **180** material can be removed by an etching or polish process. As such, the top surface of gate cap **151**, gate cap **155**, and gate cut stressor **170** or gate cut stressor **180** may be coplanar.

(111) The internally generated tensile force $T_{sub.180}$ is generally larger than internally generated tensile force $T_{sub.170}$. This internal tension applied to the gate material **150**, **154** creates tensile stress within the gate material along the gate direction and within the nanosheets **210** and **214** perpendicular to the nanosheet **210** and **214** channel and current flow direction. In turn, this tensile stress may resultingly create a smaller compressive stress $TFI_{sub.eff}$ along nanosheets **210** and **214** channel and current direction (into and/or out of the page, as depicted) through the stress mixing Poisson effect.

(112) In one embodiment, the channels of nanosheets **210**, **214** are aligned along $\langle 110 \rangle$ crystallographic direction, nanosheet **210** and **214** surfaces **210a** and **214a** are $\{100\}$ oriented, and nanosheet **210** and **214** surfaces **210b** and **214b** are $\{110\}$ oriented. In this arrangement, both hole mobility and electron mobility improve on all surfaces **210a**, **210b**, **214a**, and **214b**. On surfaces **210a** and **214a**, the hole mobility is improved through the primary tensile $T_{sub.180}$ and $T_{sub.170}$ forces and through the secondary compressive $TFI_{sub.eff}$ force while the electron mobility is improved through the primary tensile $T_{sub.180}$ and $T_{sub.170}$ forces. On these surfaces **210a** and **214a**, hole mobility improves by a larger factor. On surfaces **210b** and **214b**, hole mobility is improved through the secondary compressive $TFI_{sub.eff}$ force while electron mobility is improved through the primary tensile $T_{sub.180}$ and $T_{sub.170}$ forces. On these surfaces **210b** and **214b**, electron mobility improves by a larger factor. The amount mobility improvement will be different

for top and bottom nanosheets and this can be used to tune desired mobility improvement according to a specific circuit function. The relative ratio of electron mobility and hole mobility improvement also depends on nanosheet **210** and **214** width (nanosheet lateral dimension in FIG. **13**) that sets the ratio between surfaces **210a/214a** and **210b/214b**. Because the nanosheet **210** and **214** width can be varied by design, the relative ratio of mobility improvement can be further tuned in accordance with the specific circuit function. For CMOS logic switching circuits, wider nanosheets **210** and **214** provide a larger hole mobility improvement and faster switching speed per given footprint. Additionally, placing pFET channel nanosheets **210** and **214** in a proximity of the stronger stressor **180** further improves hole mobility and switching speed per given footprint. For CMOS SRAM cells, narrow nanosheets **210** and **214** provide a larger electron mobility improvement and a faster and more stable operation per given footprint. Additionally, placing nFET channel nanosheets **210** and **214** in a proximity of the stronger stressor **180** and placing pFET channel nanosheets **210** and **214** in a proximity of the weaker stressor **170** provide even faster and more stable SRAM cell operation per given footprint.

(113) In implementations where relatively improved hole mobility or electron mobility would be beneficial in an upper nanosheets **210**, **214**, it may be beneficial to initially form gate cut stressor **170** within the lower portion of gate cut region **132** and then to subsequently form gate cut stressor **180** upon the gate cut stressor **170** within an upper portion of gate cut region **132**.

(114) Alternatively, in implementations where relatively improved hole mobility or electron mobility would be beneficial in a lower nanosheets **210**, **214**, it may be beneficial to initially form gate cut stressor **180** within the lower portion of gate cut region **132** and then to subsequently form gate cut stressor **170** upon the gate cut stressor **180** within the upper portion of gate cut region **132**.

(115) FIG. **14** depicts a cross-sectional view of semiconductor structure **200** shown after fabrication operations, in accordance with one or more embodiments. After such fabrication operations, semiconductor device **200** may include gate cut stressor **180** and gate cut stressor **170** within gate cut region **132**. Gate cut stressor **170** may be a liner upon the internal sidewalls of gate cut region **132** and gate cut stressor **180** may be located upon gate cut stressor **170** and filling the remaining gate cut region **132**, or vice versa.

(116) The gate cut stressors **170**, **180** physically separate gate cap **151**, replacement gate **150**, gate dielectric **152**, and portions of substrate **102** from the second device region **205**, respectively. Similarly, the gate cut stressors **170**, **180** physically separates gate cap **155**, replacement gate **154**, and/or portions of substrate **102** from the first device region **203**, respectively.

(117) As depicted, gate cut stressor **170** may be initially formed by depositing the gate cut stressor **170** dielectric material upon substrate **102**, upon sidewall portions of substrate **102**, and upon the inner facing sidewalls of gate cut region **132**. This gate cut stressor **170** liner layer can have a thickness of from about 1 nm to about 20 nm, although other thicknesses are within the contemplated scope. Subsequently, gate cut stressor **180** may be formed by depositing the gate cut stressor **180** dielectric material upon gate cut stressor **170** and may generally fill the remaining gate cut region **132**.

(118) Alternatively, gate cut stressor **180** may be initially formed by depositing the gate cut stressor **180** dielectric material upon substrate **102**, upon sidewall portions of substrate **102**, and upon the inner facing sidewalls of gate cut region **132**. This gate cut stressor **180** liner layer can have a thickness of from about 1 nm to about 20 nm, although other thicknesses are within the contemplated scope. Subsequently, gate cut stressor **170** may be formed by depositing the gate cut stressor **170** dielectric material upon gate cut stressor **180** and may generally fill the remaining gate cut region **132**.

(119) After formation of gate cut stressor **170**, **180**, excessive gate cut stressor **170**, **180** material can be removed by an etching or polish process. As such, the top surface of gate cap **151**, gate cap **155**, gate cut stressor **170**, and gate cut stressor **180** may be coplanar.

(120) The internally generated tensile force $T_{sub,eff}$ applies stress to the gate material **150**, **154**

creating tensile stress within the gate material along the gate direction and within the nanosheets **210** and **214** perpendicular to the nanosheet **210** and **214** channel and current flow direction. In turn, this tensile stress may resultingly create a smaller compressive stress TFI.sub.eff along nanosheets **210** and **214** channel and current direction (into and/or out of the page, as depicted) through the stress mixing Poisson effect. These forces and stresses within nanosheets **210**, **214** may improve hole mobility and/or electron mobility therewithin, as described herein.

(121) FIG. **15** is a flow diagram of semiconductor device **100** fabrication method **300**, in accordance with one or more embodiments. Method **300** begins at block **302** and may continue with forming gate cut region **130** that exposes a portion of STI **112** (block **304**). The gate cut region **130** may effectively split sacrificial gate **120** into sacrificial gate **121** within the first device region **103** and sacrificial gate **123** within the second device region (block **306**).

(122) Method **300** may continue with forming gate cut region **132** by expanding gate cut region **130** by removing the exposed portion of STI **112** and exposing a portion of the underlying substrate **102** (block **308**). Gate cut region **130** may alternatively be formed by further partially recessing a portion of the underlying substrate **102**.

(123) Method **300** may continue with forming sacrificial gate cut plug **140** within the gate cut region **132** (block **310**). Method **300** may continue with removing sacrificial gate **121** and sacrificial gate **123** (block **312**) and forming replacement gates in place thereof (block **314**). For example, in place of the removed sacrificial gate **121**, a gate dielectric **152** may be formed upon STI region **113** and upon fins **110**, a replacement gate **150** may be formed upon the gate dielectric **152**, and a gate cap **151** may be formed upon the replacement gate **150**. Similarly, in place of the removed sacrificial gate **123**, a gate dielectric **156** may be formed upon STI region **113** and upon fins **114**, a replacement gate **154** may be formed upon the gate dielectric **156**, and a gate cap **155** may be formed upon the replacement gate **154**.

(124) Method **300** may continue with re-exposing or otherwise re-forming gate cut region **132** by removing sacrificial gate cut plug **140** (block **316**) and forming a gate cut stressor within the re-exposed gate cut region **132** (block **318**). For example, gate cut stressor **170** may be formed within the gate cut region **132** (block **320**) or gate cut stressor **180** may be formed within the gate cut region (block **322**). Alternatively, gate cut stressor **170** may be formed within a first gate cut region **132** and gate cut stressor **180** may be formed within a second or different gate cut region **132**. Alternatively, method **300** may continue with forming gate cut stressor **170** and with forming gate cut stressor **180** in the same gate cut region **132** (block **324**). For example, gate cut stressor **170** may be formed in a lower portion of gate cut region **132** and gate cut stressor **180** may be formed upon the gate cut stressor **170** in an upper portion of gate cut region **132**, or vice versa (block **326**). Alternatively, gate cut stressor **170** may be formed as a liner within gate cut region **132** and gate cut stressor **180** may be formed upon the gate cut stressor **170** filling the remaining portions of gate cut region **132**, or vice versa (block **328**). Method **300** may end at block **330**.

(125) FIG. **16** is a flow diagram of semiconductor device **200** fabrication method **400**, in accordance with one or more embodiments. Method **400** begins at block **402**.

(126) In some embodiments, method **400** may include forming, choosing, providing, or the like, substrate **102** with a preferred or predetermined crystallographic orientation(s) and structures, forming alternating layers of sacrificial nanosheets and channel nanosheets, and forming a mask layer upon a top sacrificial nanosheet layer. Next, the sacrificial nanosheet layers, channel nanosheet layers, and mask layer may be patterned. The removal of such undesired portions may further remove undesired portions of substrate **102** there below. Such removal may form a gate cut region between the first device region **203** and the second device region **205** (block **404**).

(127) Desired portions of sacrificial nanosheet layers, desired portions of the channel nanosheet layers, and desired portions of the mask may be retained and generally form a nanosheet stack within first device region **203** and a nanosheet stack within second device region **205**. The gate cut region may physically separate the nanosheet stack within first device region **203** and the nanosheet

stack within second device region **205**.

(128) Method **400** may continue with forming a sacrificial gate cut plug within the gate cut region between the first device region **203** and the second device region **205** by depositing a dielectric material upon the substrate **102** and between the nanosheet stacks (block **406**). As such, the sacrificial gate cut plug physically and, at least partially, electrically separates the nanosheet stack within first device region **203** and the nanosheet stack within second device region **205**.

(129) Method **400** may continue with forming a sacrificial gate within the first device region **203** and a sacrificial gate within the second device region **205** (block **408**). For example, the sacrificial gates may be formed by initially removing the mask upon the nano sheet stacks, thereby exposing an upper portion of the sacrificial gate cut plug, and further depositing a sacrificial gate liner upon substrate **102** and upon the nanosheet stacks within the first device region **203** and within the second device region **205**, respectively. The sacrificial gate liner may also be formed around exposed portions of the sacrificial gate cut plug. The sacrificial gates may further be formed by subsequently depositing a sacrificial gate material upon the sacrificial gate liner.

(130) The channel nanosheets **210**, **214** may be exposed by laterally recessing alternating nanosheets to yield a plurality of recesses in each nanosheet stack (block **410**). The lateral recessing of alternating nanosheets can be provided, e.g., by application of a wet etchant selective to the composition of the sacrificial nanosheets (e.g., SiGe or similar crystalline semiconductors), and which leaves other structures (e.g., substrate **102**, channel nanosheets **210**, **214**, etc.) substantially intact.

(131) Source or Drain (S/D) regions may be formed (block **412**) by epitaxially growing a source/drain epitaxial region between front and rear surfaces of respective nanosheet stacks, e.g., from exposed sidewalls of channel nanosheets **210**, **214** and/or upper surface of substrate **102**.

(132) Method **400** may continue by forming replacement gates in place of the sacrificial gate (block **414**). The replacement gates may be formed by exposing and removing the sacrificial gates, thereby exposing an upper portion of the sacrificial gate cut plug, removing the remaining sacrificial nanosheets in the gate region, and forming replacement gates around the exposed portions of the channel nanosheets **210**, **214** and upon a respective sidewall of the exposed upper portion of the sacrificial gate cut plug.

(133) Method **400** may continue with exposing gate cut region **132** by removing the sacrificial gate cut plug. After such exposure, gate cut region **132** may include inner facing sidewall(s) of gate mask **151**, inner facing sidewall(s) of replacement gate **150**, and inner facing sidewall portion(s) of substrate **102**. Similarly, gate cut region **132** may include inner facing sidewall(s) of gate mask **155**, inner facing sidewall(s) of replacement gate **154**, and inner facing sidewall portion(s) of substrate **102**. Further, after such exposure gate cut region **132** may also include a bottom or well surface as an exposed recessed portion of the substrate **102** that is below the top surface of substrate **102**.

(134) Method **400** may continue with forming a gate cut stressor within the re-exposed gate cut region **132** (block **418**). For example, gate cut stressor **170** may be formed within the gate cut region **132** (block **420**) or gate cut stressor **180** may be formed within the gate cut region **132** (block **422**). Alternatively, gate cut stressor **170** may be formed within a first gate cut region **132** and gate cut stressor **180** may be formed within a second or different gate cut region **132** formed within semiconductor device **200**. Alternatively, method **400** may continue with forming gate cut stressor **170** and with forming gate cut stressor **180** in the same gate cut region **132** (block **424**). For example, gate cut stressor **170** may be formed in a lower portion of gate cut region **132** and gate cut stressor **180** may be formed upon the gate cut stressor **170** in an upper portion of gate cut region **132**, or vice versa (block **426**). Alternatively, gate cut stressor **170** may be formed as a liner within gate cut region **132** and gate cut stressor **180** may be formed upon the gate cut stressor **170** filling the remaining portions of gate cut region **132**, or vice versa (block **428**). Method **400** may end at block **430**.

(135) The method flow diagrams depicted herein are exemplary. There can be many variations to

the diagram or operations described therein without departing from the spirit of the embodiments. For instance, the operations can be performed in a differing order, or operations can be added, deleted or modified. All of these variations are considered a part of the claimed embodiments. (136) The descriptions of the various embodiments of the present invention have been presented for purposes of illustration but are not intended to be exhaustive or limited to the embodiments described. Many modifications and variations will be apparent to those of ordinary skill in the art without departing from the scope and spirit of the invention. The terminology used herein was chosen to best explain the principles of the embodiment, the practical application or technical improvement over technologies found in the marketplace, or to enable others of ordinary skill in the art to understand the embodiments described herein.

Claims

1. A semiconductor device comprising: one or more first fins that extend from a planar top surface of a substrate within a first device region; one or more second fins that extend from the planar top surface of the substrate within a second device region; first shallow trench isolation (STI) within the first device region, the first STI upon the planar top surface of the substrate and upon and between respective lower portion(s) of the one or one or more first fins, the first STI comprising a first STI sidewall that faces the second device region; second STI within the second device region, the second STI upon the planar top surface of the substrate and upon and between respective lower portion(s) of the one or one or more second fins, the second STI comprising a second STI sidewall that faces the first device region; a first gate within the first device region, the first gate upon the first STI and upon and between respective upper portion(s) of the one or more first fins, the first gate comprising a first gate sidewall that faces the second device region; a second gate within the second device region, the second gate upon the second STI and upon and between respective upper portion(s) of the one or more second fins, the second gate comprising a second gate sidewall that faces the first device region; and a gate cut stressor upon the planar top surface of the substrate, upon the first STI sidewall, upon the second STI sidewall, upon the first gate sidewall, and upon the second gate sidewall, the gate cut stressor comprising a first gate cut stressor material and a second gate cut stressor material directly upon the first gate cut stressor material, wherein the second gate cut stressor material different from the first gate cut stressor material and wherein the gate cut stressor comprises an intrinsic stress that applies a tensile force to the first gate and to the second gate perpendicular to the first fins and to the second fins.
2. The semiconductor device of claim 1, wherein the first STI sidewall is coplanar with the first gate sidewall and wherein the second STI sidewall is coplanar with the second gate sidewall.
3. The semiconductor device of claim 1, wherein the gate cut stressor is formed of a different material relative to the first STI and relative to the second STI.
4. The semiconductor device of claim 1, wherein the second gate cut stressor material is directly upon a top surface of the first gate cut stressor material.
5. The semiconductor device of claim 1, wherein the first gate cut stressor material is a liner and the second gate cut stressor material is directly upon the liner.
6. The semiconductor device of claim 1, further comprising: a first gate cap within the first device region, the first gate cap upon the first gate, the first gate cap comprising a first gate cap sidewall that faces the second device region; a second gate cap within the second device region, the second gate cap upon the second gate, the second gate cap comprising a second gate cap sidewall that faces the first device region; and wherein the gate cut stressor is further upon the first gate cap sidewall and upon the second gate cap sidewall.
7. A semiconductor device comprising: a substrate comprising a planar top surface; a first gate cut stressor within a first gate cut region that separates a first transistor region from a second transistor region, wherein the first gate cut stressor is directly upon the planar top surface and applies a first

tensile force to a first gate perpendicular to a first channel in the first transistor region and to a second gate perpendicular to a second channel in the second transistor region; and a second gate cut stressor within a second gate cut region that separates a third transistor region from a fourth transistor region, wherein the second gate cut stressor is directly upon the planar top surface and applies a second tensile force to a third gate perpendicular to a third channel in the third transistor region and to a fourth gate perpendicular to a fourth channel in the fourth transistor region, wherein the second gate cut stressor is formed of a different material relative to the first gate cut stressor.

8. The semiconductor device of claim 7, wherein each of the first transistor region, the second transistor region, the third transistor region, and the fourth transistor region comprise: a shallow trench isolation (STI) directly upon the planar top surface; a gate directly upon the STI; and a gate cap directly upon the gate.

9. The semiconductor device of claim 8, wherein the first gate cut stressor physically connects the first transistor region STI with the second transistor region STI and wherein the first gate cut stressor further physically connects the first transistor region gate with the second transistor region gate.

10. The semiconductor device of claim 9, wherein the second gate cut stressor physically connects the third transistor region STI with the fourth transistor region STI and wherein the second gate cut stressor further physically connects the third transistor region gate with the fourth transistor region gate.

11. The semiconductor device of claim 10, wherein the first transistor region further comprises an N-type transistor, wherein the second transistor region further comprises a P-type transistor, wherein the third transistor region further comprises an N-type transistor, and wherein the fourth transistor region further comprises a P-type transistor.

12. The semiconductor device of claim 10, wherein the first transistor region further comprises an first N-type transistor, wherein the second transistor region further comprises a second N-type transistor, wherein the third transistor region further comprises a first P-type transistor, and wherein the fourth transistor region further comprises a second P-type transistor.

13. The semiconductor device of claim 10, wherein the first transistor region further comprises an first P-type transistor, wherein the second transistor region further comprises a second P-type transistor, wherein the third transistor region further comprises a first N-type transistor, and wherein the fourth transistor region further comprises a second N-type transistor.

14. The semiconductor device of claim 10, wherein the first gate cut stressor physically connects the first transistor region gate cap with the second transistor region gate cap.

15. The semiconductor device of claim 14, wherein the second gate cut stressor physically connects the third transistor region gate cap with the fourth transistor region gate cap.

16. A semiconductor device comprising: a first gate associated with a first transistor; a second gate associated with a second transistor; a gate cut region adequately electrically separating a first sidewall of the first gate from a second sidewall of the second gate; and a first gate cut stressor comprising a first gate cut stressor material and a second gate cut stressor material directly upon the first gate cut stressor material, the second gate cut stressor material different from the first gate cut stressor material, the first gate cut stressor directly connected to the first sidewall of the first gate and directly connected to the sidewall of the second gate, wherein the first gate cut stressor applies a first tensile force against the first gate substantially perpendicular to the first sidewall and applies the first tensile force against the second gate substantially perpendicular to the second sidewall.

17. The semiconductor device of claim 16, further comprising: a second gate cut stressor directly connected to the first sidewall of the first gate, directly connected to the sidewall of the second gate, and directly connected to the first gate cut stressor, wherein the second gate cut stressor applies a second tensile force against the first gate substantially perpendicular to the first sidewall and applies a second tensile force against the second gate substantially perpendicular to the second sidewall.

18. The semiconductor device of claim 16, further comprising: a second gate cut stressor directly connected to the first gate cut stressor, wherein the second gate cut stressor applies a second tensile force against the first gate substantially perpendicular to the first sidewall and applies a second tensile force against the second gate substantially perpendicular to the second sidewall.
19. The semiconductor device of claim 16, wherein the first sidewall of the first gate and the second sidewall of the second gate are substantially vertical and wherein the first tensile force and the second tensile force are substantially horizontal.
20. The semiconductor device of claim 16, wherein the first tensile force applies a compressive stress to one or more channels associated with the first transistor and wherein the second tensile force applies a compressive stress to one or more channels associated with the second transistor.
-