

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12417807
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Conti; Anna Maria et al.

Microelectronic devices including staircase structures, and related memory devices, electronic systems, and methods

Abstract

A microelectronic device comprises a stack structure overlying a source tier. The stack structure comprises a vertically alternating sequence of conductive structures and insulative structures arranged in tiers. The microelectronic device comprises a staircase structure within the stack structure and having steps comprising lateral edges of the tiers, conductive contacts within a horizontal area of the staircase structure and vertically extending through the stack structure to the source tier, and strapping structures laterally adjacent to the conductive contacts and having upper surfaces substantially coplanar with upper surfaces of the conductive contacts. Each of the strapping structures are in contact with one of the conductive contacts and with one of the conductive structures of the stack structure at one of the steps of the staircase structure. Related memory devices, electronic systems, and methods of forming the microelectronic devices are also described.

Inventors: Conti; Anna Maria (Milan, IT), Tessariol; Paolo (Arcore, IT), Meotto; Umberto Maria (Dietlikon, CH)

Applicant: Micron Technology, Inc. (Boise, ID)

Family ID: 1000008821600

Assignee: Micron Technology, Inc. (Boise, ID)

Appl. No.: 17/930279

Filed: September 07, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20240079057 A1	Mar. 07, 2024

Publication Classification

Int. Cl.: G11C16/04 (20060101); H10B41/10 (20230101); H10B41/20 (20230101); H10B41/35 (20230101); H10B43/10 (20230101); H10B43/20 (20230101); H10B43/35 (20230101)

U.S. Cl.:

CPC G11C16/0483 (20130101); H10B41/10 (20230201); H10B41/20 (20230201); H10B41/35 (20230201); H10B43/10 (20230201); H10B43/20 (20230201); H10B43/35 (20230201);

Field of Classification Search

CPC: G11C (16/0483); H10B (41/10); H10B (41/20); H10B (41/35); H10B (43/10); H10B (43/20); H10B (43/35); H10B (41/50); H10B (43/50)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9941209	12/2017	Tessariol et al.	N/A	N/A
10580795	12/2019	Luo et al.	N/A	N/A
10622369	12/2019	Zhou	N/A	H10B 43/50
10727248	12/2019	Kaminaga	N/A	H10B 43/40
2025/0024685	12/2024	Zhou	N/A	H10D 30/6755

Primary Examiner: Bernstein; Allison

Attorney, Agent or Firm: TraskBritt

Background/Summary

TECHNICAL FIELD

(1) The disclosure, in various embodiments, relates generally to the field of microelectronic device design and fabrication. More specifically, the disclosure relates to microelectronic devices, and related memory devices, electronic systems, and methods of forming the microelectronic devices.

BACKGROUND

(2) A continuing goal of the microelectronics industry has been to increase the memory density (e.g., the number of memory cells per memory die) of memory devices, such as non-volatile memory devices (e.g., NAND Flash memory devices). One way of increasing memory density in non-volatile memory devices is to utilize vertical memory array (also referred to as a “three-dimensional (3D) memory array”) architectures. A conventional vertical memory array includes vertical memory strings extending through openings in one or more conductive stack structures including tiers of conductive structures and insulative structures. Each vertical memory string may include at least one select device coupled in series to a serial combination of vertically stacked memory cells. Such a configuration permits a greater number of switching devices (e.g., transistors) to be located in a unit of die area (i.e., length and width of active surface consumed) by

building the array upwards (e.g., vertically) on a die, as compared to structures with conventional planar (e.g., two-dimensional) arrangements of transistors.

(3) Vertical memory array architectures generally include electrical connections between the conductive structures of the tiers of the conductive stack structure(s) of the memory device and access lines (e.g., word lines) so that the memory cells of the vertical memory array can be uniquely selected for writing, reading, or erasing operations. One method of forming such an electrical connection includes forming so-called “staircase” (or “stair step”) structures at edges (e.g., horizontal ends) of the tiers of the conductive stack structure(s) of the memory device. The staircase structure includes individual “steps” defining contact regions of the conductive structures, upon which conductive contact structures can be positioned to provide electrical access to the conductive structures.

(4) As vertical memory array technology has advanced, additional memory density has been provided by forming vertical memory arrays to include stacks comprising additional tiers of conductive structures and, hence, additional staircase structures and/or additional steps in individual staircase structures associated therewith. As the height of the stacks increases to facilitate additional memory cells in the vertical memory arrays, the stacks may be prone to toppling or collapse during various processing acts. For example, during replacement gate processing acts, the stacks may be subject to tier collapse during or after removal of portions of the tiers to be replaced with the conductive structures. Collapse of the portions of the stacks may reduce reliability of the vertical memory strings.

(5) In addition, as the dimensions and spacing of the conductive features decrease, multilevel wiring structures have been used in memory devices to electrically connect the conductive features to one another. The memory device includes the wiring structures at different levels, with the wiring structures formed of electrically conductive materials to provide conductive pathways through the memory device. As the dimensions and spacing of the conductive features continue to decrease, parasitic (e.g., stray) capacitance between adjacent conductive features within the memory device increases. The increased parasitic capacitance causes higher power demands and delay of the memory device.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIGS. 1A through 1N are simplified, partial top-down views (FIGS. 1A, 1F, and 1K) and simplified, partial cross-sectional views (FIGS. 1B through 1E, 1G through 1J, and 1L through 1N) illustrating different processing stages of a method of forming a microelectronic device, in accordance with embodiments of the disclosure;

(2) FIGS. 2A through 2F are simplified, partial top-down views (FIG. 2A) and simplified, partial cross-sectional views (FIGS. 2B through 2F) illustrating a method of forming a microelectronic device, in accordance with additional embodiments of the disclosure;

(3) FIG. 3 is a simplified, partial cutaway perspective view of a microelectronic device, in accordance with embodiments of the disclosure;

(4) FIG. 4 is a schematic block diagram of an electronic system, in accordance with embodiments of the disclosure; and

(5) FIG. 5 is a schematic block diagram of a processor-based system, in accordance with embodiments of the disclosure.

DETAILED DESCRIPTION

(6) The following description provides specific details, such as material compositions, shapes, and sizes, in order to provide a thorough description of embodiments of the disclosure. However, a person of ordinary skill in the art would understand that the embodiments of the disclosure may be

practiced without employing these specific details. Indeed, the embodiments of the disclosure may be practiced in conjunction with conventional microelectronic device fabrication techniques employed in the industry. In addition, the description provided below does not form a complete process flow for manufacturing a microelectronic device (e.g., a memory device, such as NAND Flash memory device). The structures described below do not form a complete microelectronic device. Only those process acts and structures necessary to understand the embodiments of the disclosure are described in detail below. Additional acts to form a complete microelectronic device from the structures may be performed by conventional fabrication techniques.

(7) Drawings presented herein are for illustrative purposes only and are not meant to be actual views of any particular material, component, structure, device, or system. Variations from the shapes depicted in the drawings as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein are not to be construed as being limited to the particular shapes or regions as illustrated, but include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as box-shaped may have rough and/or nonlinear features, and a region illustrated or described as round may include some rough and/or linear features. Moreover, sharp angles that are illustrated may be rounded, and vice versa. Thus, the regions illustrated in the figures are schematic in nature, and their shapes are not intended to illustrate the precise shape of a region and do not limit the scope of the claims. The drawings are not necessarily to scale. Additionally, elements common between figures may retain the same numerical designation.

(8) As used herein, a “memory device” means and includes a microelectronic device exhibiting memory functionality, but not necessarily limited to memory functionality. Stated another way, and by way of non-limiting example only, the term “memory device” includes not only conventional memory (e.g., conventional non-volatile memory, such as conventional NAND memory; conventional volatile memory, such as conventional dynamic random-access memory (DRAM)), but also includes an application specific integrated circuit (ASIC) (e.g., a system on a chip (SoC)), a microelectronic device combining logic and memory, and a graphics processing unit (GPU) incorporating memory.

(9) As used herein, the terms “vertical,” “longitudinal,” “horizontal,” and “lateral” are in reference to a major plane of a structure and are not necessarily defined by earth's gravitational field. A “horizontal” or “lateral” direction is a direction that is substantially parallel to the major plane of the structure, while a “vertical” or “longitudinal” direction is a direction that is substantially perpendicular to the major plane of the structure. The major plane of the structure is defined by a surface of the structure having a relatively large area compared to other surfaces of the structure. With reference to the figures, a “horizontal” or “lateral” direction may be perpendicular to an indicated “Z” axis, and may be parallel to an indicated “X” axis and/or parallel to an indicated “Y” axis; and a “vertical” or “longitudinal” direction may be parallel to an indicated “Z” axis, may be perpendicular to an indicated “X” axis, and may be perpendicular to an indicated “Y” axis.

(10) As used herein, features (e.g., regions, materials, structures, devices) described as “neighboring” one another means and includes features of the disclosed identity (or identities) that are located most proximate (e.g., closest to) one another. Additional features (e.g., additional regions, additional materials, additional structures, additional devices) not matching the disclosed identity (or identities) of the “neighboring” features may be disposed between the “neighboring” features. Stated another way, the “neighboring” features may be positioned directly adjacent one another, such that no other feature intervenes between the “neighboring” features; or the “neighboring” features may be positioned indirectly adjacent one another, such that at least one feature having an identity other than that associated with at least one of the “neighboring” features is positioned between the “neighboring” features. Accordingly, features described as “vertically neighboring” one another means and includes features of the disclosed identity (or identities) that are located most vertically proximate (e.g., vertically closest to) one another. Moreover, features

described as “horizontally neighboring” one another means and includes features of the disclosed identity (or identities) that are located most horizontally proximate (e.g., horizontally closest to) one another.

(11) As used herein, reference to an element as being “on” or “over” another element means and includes the element being directly on top of, directly adjacent to (e.g., directly laterally adjacent to, directly vertically adjacent to), directly underneath, or in direct contact with the other element. It also includes the element being indirectly on top of, indirectly adjacent to (e.g., indirectly laterally adjacent to, indirectly vertically adjacent to), indirectly underneath, or near the other element, with other elements present therebetween. In contrast, when an element is referred to as being “directly on” or “directly adjacent to” another element, there are no intervening elements present.

(12) As used herein, spatially relative terms, such as “beneath,” “below,” “lower,” “bottom,” “above,” “upper,” “top,” “front,” “rear,” “left,” “right,” and the like, may be used for ease of description to describe one element's or feature's relationship to another element(s) or feature(s) as illustrated in the figures. Unless otherwise specified, the spatially relative terms are intended to encompass different orientations of the materials in addition to the orientation depicted in the figures. For example, if materials in the figures are inverted, elements described as “below” or “beneath” or “under” or “on bottom of” other elements or features would then be oriented “above” or “on top of” the other elements or features. Thus, the term “below” can encompass both an orientation of above and below, depending on the context in which the term is used, which will be evident to one of ordinary skill in the art. The materials may be otherwise oriented (e.g., rotated 90 degrees, inverted, flipped) and the spatially relative descriptors used herein interpreted accordingly.

(13) As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

(14) As used herein, “and/or” includes any and all combinations of one or more of the associated listed items.

(15) As used herein, the term “configured” refers to a size, shape, material composition, orientation, and arrangement of one or more of at least one structure and at least one apparatus facilitating operation of one or more of the structure and the apparatus in a pre-determined way.

(16) As used herein, the phrase “coupled to” refers to structures operatively connected with each other, such as electrically connected through a direct Ohmic connection or through an indirect connection (e.g., by way of another structure).

(17) As used herein, the term “substantially” in reference to a given parameter, property, or condition means and includes to a degree that one of ordinary skill in the art would understand that the given parameter, property, or condition is met with a degree of variance, such as within acceptable tolerances. By way of example, depending on the particular parameter, property, or condition that is substantially met, the parameter, property, or condition may be at least 90.0 percent met, at least 95.0 percent met, at least 99.0 percent met, at least 99.9 percent met, or even 100.0 percent met.

(18) As used herein, “about” or “approximately” in reference to a numerical value for a particular parameter is inclusive of the numerical value and a degree of variance from the numerical value that one of ordinary skill in the art would understand is within acceptable tolerances for the particular parameter. For example, “about” or “approximately” in reference to a numerical value may include additional numerical values within a range of from 90.0 percent to 108.0 percent of the numerical value, such as within a range of from 95.0 percent to 105.0 percent of the numerical value, within a range of from 97.5 percent to 102.5 percent of the numerical value, within a range of from 99.0 percent to 101.0 percent of the numerical value, within a range of from 99.5 percent to 100.5 percent of the numerical value, or within a range of from 99.9 percent to 100.1 percent of the numerical value.

(19) As used herein, “conductive material” means and includes electrically conductive material, such as one or more of a metal (e.g., tungsten (W), titanium (Ti), molybdenum (Mo), niobium (Nb),

vanadium (V), hafnium (Hf), tantalum (Ta), chromium (Cr), zirconium (Zr), iron (Fe), ruthenium (Ru), osmium (Os), cobalt (Co), rhodium (Rh), iridium (Ir), nickel (Ni), palladium (Pd), platinum (Pt), copper (Cu), silver (Ag), gold (Au), aluminum (Al)), an alloy (e.g., a Co-based alloy, an Fe-based alloy, an Ni-based alloy, an Fe- and Ni-based alloy, a Co- and Ni-based alloy, an Fe- and Co-based alloy, a Co- and Ni- and Fe-based alloy, an Al-based alloy, a Cu-based alloy, a magnesium (Mg)-based alloy, a Ti-based alloy, a steel, a low-carbon steel, a stainless steel), a conductive metal-containing material (e.g., a conductive metal nitride, a conductive metal silicide, a conductive metal carbide, a conductive metal oxide), and a conductively doped semiconductor material (e.g., conductively doped polysilicon, conductively doped germanium (Ge), conductively doped silicon germanium (SiGe)). In addition, a “conductive structure” means and includes a structure formed of and including a conductive material.

(20) As used herein, “insulative material” means and includes electrically insulative material, such one or more of at least one dielectric oxide material (e.g., one or more of a silicon oxide (SiO.sub.x), phosphosilicate glass, borosilicate glass, borophosphosilicate glass, fluorosilicate glass, an aluminum oxide (AlO.sub.x), a hafnium oxide (HfO.sub.x), a niobium oxide (NbO.sub.x), a titanium oxide (TiO.sub.x), a zirconium oxide (ZrO.sub.x), a tantalum oxide (TaO.sub.x), and a magnesium oxide (MgO.sub.x)), at least one dielectric nitride material (e.g., a silicon nitride (SiN.sub.y)), at least one dielectric oxynitride material (e.g., a silicon oxynitride (SiO.sub.xN.sub.y)), and at least one dielectric carboxynitride material (e.g., a silicon carboxynitride (SiO.sub.xC.sub.zN.sub.y)). Formulae including one or more of “x,” “y,” and “z” herein (e.g., SiO.sub.x, AlO.sub.x, HfO.sub.x, NbO.sub.x, TiO.sub.x, SiN.sub.y, SiO.sub.xN.sub.y, SiO.sub.xC.sub.zN.sub.y) represent a material that contains an average ratio of “x” atoms of one element, “y” atoms of another element, and “z” atoms of an additional element (if any) for every one atom of another element (e.g., Si, Al, Hf, Nb, Ti). As the formulae are representative of relative atomic ratios and not strict chemical structure, an insulative material may comprise one or more stoichiometric compounds and/or one or more non-stoichiometric compounds, and values of “x,” “y,” and “z” (if any) may be integers or may be non-integers. As used herein, the term “non-stoichiometric compound” means and includes a chemical compound with an elemental composition that cannot be represented by a ratio of well-defined natural numbers and is in violation of the law of definite proportions. In addition, an “insulative structure” means and includes a structure formed of and including an insulative material.

(21) As used herein, the term “homogeneous” means relative amounts of elements included in a feature (e.g., a material, a structure) do not vary throughout different portions (e.g., different horizontal portions, different vertical portions) of the feature. Conversely, as used herein, the term “heterogeneous” means relative amounts of elements included in a feature (e.g., a material, a structure) vary throughout different portions of the feature. If a feature is heterogeneous, amounts of one or more elements included in the feature may vary stepwise (e.g., change abruptly), or may vary continuously (e.g., change progressively, such as linearly, parabolically) throughout different portions of the feature. The feature may, for example, be formed of and include a stack of at least two different materials.

(22) As used herein, the term “amorphous,” when referring to a material, means and refers to a material having a substantially noncrystalline structure.

(23) As used herein, the term “sacrificial,” when used in reference to a material or structure, means and includes a material, structure, or a portion of a material or structure that is formed during a fabrication process but which is at least partially removed (e.g., substantially removed) prior to completion of the fabrication process.

(24) As used herein, the term “sacrificial,” when used in reference to a material or structure, means and includes a material or structure that is formed during a fabrication process but which is removed (e.g., substantially removed) prior to completion of the fabrication process.

(25) As used herein, the term “selectively etchable” means and includes a material that exhibits a

greater etch rate responsive to exposure to a given etch chemistry relative to another material exposed to the same etch chemistry. For example, the material may exhibit an etch rate that is at least about three times (3×) greater than the etch rate of another material, such as about five times (5×) greater than the etch rate of another material, such as an etch rate of about ten times (10×) greater, about twenty times (20×) greater, or about forty times (40×) greater than the etch rate of the another material. Etch chemistries and etch conditions for selectively etching a desired material may be selected by a person of ordinary skill in the art.

(26) Unless otherwise specified, materials described herein may be formed by conventional techniques including, but not limited to, spin coating, blanket coating, chemical vapor deposition (CVD), atomic layer deposition (ALD), plasma-enhanced ALD, physical vapor deposition (PVD), plasma-enhanced chemical vapor deposition (PECVD), or low-pressure chemical vapor deposition (LPCVD). Alternatively, the materials may be grown in situ. Depending on the specific material to be formed, the technique for depositing or growing the material may be selected by a person of ordinary skill in the art. The removal of materials may be accomplished by any suitable technique including, but not limited to, etching, abrasive planarization (e.g., chemical-mechanical planarization), or other known methods unless the context indicates otherwise.

(27) FIGS. 1A through 1N are simplified, partial top-down views (FIGS. 1A, 1F, and 1K) and simplified, partial cross-sectional views (FIGS. 1B through 1E, 1G through 1J, and 1L through 1N) illustrating different processing stages of a method of forming a microelectronic device (e.g., a memory device, such as a three-dimensional (3D) NAND Flash memory device), in accordance with embodiments of the disclosure. FIG. 1M illustrates an enlarged portion of the top-down view of box M of FIG. 1K, and FIG. 1N illustrates an enlarged portion of the cross-sectional view of box N of FIG. 1L. With the description provided below, it will be readily apparent to one of ordinary skill in the art that the methods and structures described herein with reference to FIGS. 1A through 1N may be used in the formation and configuration of various devices and electronic systems. In other words, the methods of the disclosure may be used whenever it is desired to form a microelectronic device. For convenience in describing FIGS. 1A through 1N, a first horizontal direction may be defined as the X-direction shown in some of FIGS. 1A through 1N; a second horizontal direction transverse (e.g., orthogonal, perpendicular) to the first horizontal direction may be defined as the Y-direction shown in some of FIGS. 1A through 1N; and a third direction (e.g., a vertical direction) transverse (e.g., orthogonal, perpendicular) to each of the first horizontal direction and the second horizontal direction may be defined the Z-direction shown in some of FIGS. 1A through 1N. Similar directions are shown in FIGS. 2A through 2F and FIG. 3, which are discussed in further detail below.

(28) With reference to FIG. 1A, a microelectronic device structure **100** may be formed to include a preliminary stack structure **102** (FIG. 1B). A dielectric material **116** may, optionally, be formed to vertically overlie (e.g., in the Z-direction) the preliminary stack structure **102**. The microelectronic device structure **100** may include a staircase region **105** including at least one staircase structure **120** (FIG. 1B). The microelectronic device structure **100** may also include an array region horizontally (e.g., in the X-direction) neighboring the staircase region **105**. For example, the array region may include memory pillar structures (e.g., cell pillar structures) employed as memory cells (e.g., strings of NAND memory cells), as described in further detail with reference to FIG. 3. While not illustrated in FIGS. 1A through 1N, features of the array region of the microelectronic device structure **100** may be formed during (e.g., substantially simultaneous with) formation of corresponding features of the staircase region **105**. Openings **130** may be formed to vertically extend (e.g., in the Z-direction) through one or more materials overlying the staircase structure **120** within the staircase region **105**. The preliminary stack structure **102** of the staircase region **105** is described in further detail below, along with additional components (e.g., structures, features) of the microelectronic device structure **100** at the processing stage depicted in FIG. 1A. FIG. 1B is a simplified, partial cross-sectional view of the microelectronic device structure **100** about the line B-

B shown in FIG. 1A. For clarity and ease of understanding of the drawings and related description, not all features depicted in one of FIGS. 1A and 1B are depicted the other of FIGS. 1A and 1B.

(29) Referring to FIG. 1B, the preliminary stack structure **102** may be formed to include a vertically alternating (e.g., in the Z-direction) sequence of insulative structures **104** and additional insulative structures **106** arranged in tiers **108**. Each of the tiers **108** of the preliminary stack structure **102** may include at least one (1) of the insulative structures **104** vertically neighboring at least one (1) of the additional insulative structures **106**. The insulative structures **104** may be interleaved with the additional insulative structures **106**.

(30) The insulative structures **104** of the preliminary stack structure **102** may be formed of and include at least one insulative material. In some embodiments, the insulative structures **104** are formed of and include silicon dioxide (SiO_2). Each of the insulative structures **104** may individually include a substantially homogeneous distribution or a substantially heterogeneous distribution of the at least one insulative material. The insulative structures **104** may each be substantially planar, and may each independently exhibit any desired thickness. In addition, each of the insulative structures **104** may be substantially the same (e.g., exhibit substantially the same material composition, material distribution, size, and shape) as one another, or at least one of the insulative structures **104** may be different (e.g., exhibit one or more of a different material composition, a different material distribution, a different size, and a different shape) than at least one other of the insulative structures **104**. In some embodiments, each of the insulative structures **104** is substantially the same as each other of the insulative structures **104**.

(31) The additional insulative structures **106** may be formed of and include at least one additional insulative material that is different than, and that exhibits etch selectivity with respect to, the insulative material of the insulative structures **104**. For example, the additional insulative structures **106** may individually be formed of and include at least one dielectric nitride material (e.g., Si_3N_4) and/or at least one oxynitride material (e.g., $\text{Si}_x\text{O}_y\text{N}_z$). In some embodiments, the additional insulative structures **106** are formed of and include Si_3N_4 . Each of the additional insulative structures **106** may individually include a substantially homogeneous distribution or a substantially heterogeneous distribution of the at least one additional insulative material. The additional insulative structures **106** may serve as sacrificial structures for the subsequent formation of conductive structures, as described in further detail below.

(32) Although FIG. 1B illustrates a particular quantity of tiers **108** of the insulative structures **104** and the additional insulative structures **106**, the disclosure is not so limited. In some embodiments, the preliminary stack structure **102** includes a desired quantity of the tiers **108**, such as within a range from thirty-two (32) of the tiers **108** to two hundred fifty-six (256) of the tiers **108**. In some embodiments, the preliminary stack structure **102** includes sixty-four (64) of the tiers **108**. In other embodiments, the preliminary stack structure **102** includes a different quantity of the tiers **108**, such as less than sixty-four (64) of the tiers **108** (e.g., less than or equal to sixty (60) of the tiers **108**, less than or equal to fifty (50) of the tiers **108**, less than about forty (40) of the tiers **108**, less than or equal to thirty (30) of the tiers **108**, less than or equal to twenty (20) of the tiers **108**, less than or equal to ten (10) of the tiers **108**); or greater than sixty-four (64) of the tiers **108** (e.g., greater than or equal to seventy (70) of the tiers **108**, greater than or equal to one hundred (100) of the tiers **108**, greater than or equal to about one hundred twenty-eight (128) of the tiers **108**, greater than two hundred fifty-six (256) of the tiers **108**) of the insulative structures **104** and the additional insulative structures **106**. In addition, in some embodiments, the preliminary stack structure **102** overlies a deck structure comprising additional tiers **108** of insulative structures **104** and the additional insulative structures, separated from the preliminary stack structure **102** by at least one dielectric material, such as an interdeck insulative material.

(33) With continued reference to FIG. 1B, the microelectronic device structure **100** further includes a source tier **110** vertically underlying (e.g., in the Z-direction) the preliminary stack structure **102**. The source tier **110** may comprise, for example, a first conductive material **112** and a second

conductive material **114**. In some embodiments, the first conductive material **112** comprises conductively doped silicon. In some such embodiments, the second conductive material **114** is formed of and includes one or more of a metal silicide material (e.g., tungsten silicide (WSi.sub.x)), a metal nitride material (e.g., tungsten nitride), and a metal silicon nitride material (e.g., tungsten silicon nitride (WSi.sub.xN.sub.y)). In some embodiments, the second conductive material **114** comprises tungsten silicide.

(34) The dielectric material **116**, which may serve as a mask material, may vertically overlie (e.g., in the Z-direction) a vertically uppermost tier **108** of the insulative structures **104** and the additional insulative structures **106** of the preliminary stack structure **102**. The dielectric material **116** may comprise one or more of the materials described above with reference to the insulative structures **104**. In some embodiments, the dielectric material **116** comprises silicon dioxide.

(35) In some embodiments, the source tier **110** is formed to include one or more source structures **118** (e.g., a source plate, source lines) horizontally extending into a horizontal area of the staircase region **105**. The source structure(s) **118** may be operatively associated with vertically extending strings of memory cells within a memory array region of the microelectronic device structure **100**, as described in further detail below. The source structure(s) **118** may be formed of and include the first conductive material **112** and the second conductive material **114**, and may be electrically isolated from other portions of the first conductive material **112** and the second conductive material **114** (e.g., other portions employed as conductive routing structures **117** and/or as conductive pad structures) by insulative material **119**.

(36) As shown in FIG. 1B, the staircase structure **120** may be formed within the staircase region **105** of the preliminary stack structure **102**. A dielectric fill material **126** may be formed to fill at least one valley **124** (e.g., space, gap, trench, opening) vertically overlying the staircase structure **120**. In some embodiments, one or more insulative liner materials are formed to vertically overlie (e.g., in the Z-direction) the staircase structure **120** prior to forming the dielectric fill material **126**, as described in greater detail below.

(37) The dielectric fill material **126** may be formed of and include at least one material exhibiting etch selectivity with respect to one or more of the dielectric material **116**, the insulative structures **104**, the additional insulative structures **106**, as well as additional materials (e.g., additional insulative materials, additional conductive materials) formed during subsequent processing of the microelectronic device structure **100**. In some embodiments, the dielectric fill material **126** comprises at least one insulative material, such as one or more of the materials described above with reference to the insulative structures **104** (e.g., SiO.sub.2). The dielectric fill material **126** may, alternatively, be formed of and include one or more of silicon oxycarbide (SiO.sub.xC.sub.y), silicon oxynitride (SiO.sub.xN.sub.y), hydrogenated silicon oxycarbide (SiC.sub.xO.sub.yH.sub.z), or silicon oxycarbonitride (SiO.sub.xC.sub.yN.sub.z), for example.

(38) The staircase structure **120** may be formed to include steps **122** comprising edges (e.g., horizontal ends) of the tiers **108** of the insulative structures **104** and additional insulative structures **106**. For example, individual steps **122** may include an uppermost insulative structure **104a** and an uppermost additional insulative structure **106a** overlying the uppermost insulative structure **104a** such that the uppermost additional insulative structure **106a** is proximate (e.g., directly adjacent) to the dielectric fill material **126**. Although FIG. 1B illustrates two (2) of the tiers **108** of the insulative structures **104** and the additional insulative structures **106** corresponding to one (1) step **122** of the staircase structure **120**, the quantity of steps **122** of the staircase structure **120** may correspond to the quantity of tiers **108**, such that a single (e.g., only one) step **122** corresponds to one of the tiers **108**. The staircase structure **120** (and the valley **124** at least partially defined by the staircase structure **120**) include a stepped cross-sectional profile in the ZY-plane, as shown in FIG. 1B. The stepped cross-sectional profile of the staircase structure **120** (and of the valley **124**) may be defined by the geometric configurations of the steps **122** of the staircase structure **120**.

(39) For clarity and ease of understanding the description, FIG. 1B illustrates only a particular

quantity of steps **122** in the staircase structure **120**. However, it will be understood that the staircase structure **120** may include a greater quantity of steps **122** than those illustrated. For example, the staircase structure **120** may include greater or equal to eight (8) of the steps **122**, greater than or equal to sixteen (16) of the steps **122**, greater or equal to than thirty-two (32) of the steps **122**, greater than or equal to sixty-four (64) of the steps **122**, greater than or equal to one hundred twenty-eight (128) of the steps **122**, or greater than or equal to two hundred fifty-six (256) of the steps **122**.

(40) In some embodiments, the staircase structure **120** forms a portion of a stadium structure including opposing staircase structures **120** each having steps **122** defined by horizontal ends of the tiers **108** of the preliminary stack structure **102**. In some such embodiments, multiple (e.g., more than one) stadium structures individually including one or more initial staircase structures may be formed to be positioned at substantially the same elevations (e.g., vertical locations) as one another within the preliminary stack structure **102**. During formation of the steps **122** of the staircase structure **120**, an initial staircase structure (e.g., configured substantially similar to the staircase structure **120**) may be formed at an upper vertical position within the preliminary stack structure **102** within horizontal boundaries of the staircase region **105** of the microelectronic device structure **100** using conventional processes (e.g., conventional photolithographic patterning processes, conventional material removal processes), and conventional processing equipment, which are not described in detail herein. The microelectronic device structure **100** may then be subjected to one or more additional material removal processes (e.g., one or more chopping processes) to increase the depth(s) (e.g., in the Z-direction) of the initial staircase structure relative to an upper surface of the preliminary stack structure **102** and form the staircase structure **120**. The staircase structure **120** may be substantially similar to the initial staircase structure used to form the staircase structure **120**, except located at a relatively lower vertical position within the microelectronic device structure **100** (e.g., within the preliminary stack structure **102**). The additional material removal processes may permit a lower boundary of the staircase structure **120** to be positioned at or below a lower boundary of the preliminary stack structure **102**.

(41) Still referring to FIG. **1B**, following formation of the staircase structure **120**, the openings **130** (e.g., initial contact openings) may be formed to vertically extend (e.g., in the Z-direction) through the dielectric material **116**, if present, and through the dielectric fill material **126** overlying the staircase structure **120** within the staircase region **105**. The openings **130** may be formed to extend to upper boundaries of the staircase structure **120** on at least some (e.g., each) of the steps **122**, without extending through the preliminary stack structure **102**. At least portions of the dielectric material **116** and the dielectric fill material **126** may be removed by exposing the respective materials to wet etch chemistries and/or dry etch chemistries, for example, in one or more material removal processes. The uppermost additional insulative structure **106a** may act as an etch stop material during removal of the dielectric fill material **126** and formation of the openings **130**.

(42) In some such embodiments, the openings **130** terminate at the steps **122** of the staircase structure **120** at the processing stage depicted in FIG. **1B**. In other embodiments, the openings **130** terminate at or within one or more insulative liner materials overlying the staircase structure **120**, as described in greater detail with reference to FIG. **1D**. Accordingly, the openings **130** may be formed to extend to varying (e.g., differing) depths corresponding to various locations of the individual steps **122** of the staircase structure **120**. A horizontal dimension (e.g., width) of each of the openings **130** may be relatively less than that of upper surfaces (e.g., treads) of the steps **122** of the staircase structure **120**. For example, a width of the openings **130** may be within a range of from about 150 nanometers (nm) to about 500 nm, such as from about 150 nm to about 250 nm, from about 250 nm to about 350 nm, or from about 350 nm to about 500 nm. However, the disclosure is not so limited and the width of the openings **130** may be different than those described above. In some embodiments, the width of the openings **130** may be selected and tailored to effect a size and shape of one or more features to be formed in the microelectronic device structure **100**,

as will be described herein. Additional portions of the dielectric fill material **126** may remain on the upper surfaces of the steps **122** of the staircase structure **120** following formation of the openings **130**.

(43) Referring next to FIG. **1C**, sacrificial material **132** may be formed within the openings **130**. The sacrificial material **132** may be formed using one or more conformal deposition processes, such as one or more of a conventional conformal CVD process or a conventional ALD process. Since the sacrificial material **132** is conformally formed, a portion of the openings **130** within the dielectric fill material **126** may remain substantially free of the sacrificial material **132**.

Accordingly, the sacrificial material **132** is formed in the openings **130** without fully filling the openings **130**. The sacrificial material **132** may have a thickness within a range of from about 50 nm to about 150 nm, such as from about 50 nm to about 75 nm, from about 75 nm to about 125 nm, or from about 125 nm to about 150 nm. However, the disclosure is not so limited and the thickness of the sacrificial material **132** may be different than those described above. In some embodiments, the thickness of the sacrificial material **132** represents less than about one-half (e.g., less than about one-third) of the width of the openings **130**. The thickness of the sacrificial material **132** may be tailored to facilitate dimensions (e.g., widths) of additional materials to be formed within central portions of the openings **130** and within regions vacated by the sacrificial material **132**.

(44) The sacrificial material **132** may be formed adjacent to (e.g., directly adjacent to) exposed surfaces (e.g., side surfaces) of the dielectric material **116**, if present, and the dielectric fill material **126** and adjacent to (e.g., directly adjacent to) exposed surfaces (e.g., upper surfaces) of the steps **122** of the staircase structure **120**. For example, the sacrificial material **132** may terminate at the uppermost additional insulative structure **106a** (FIG. **1B**) of the individual steps **122**. In some embodiments, a so-called “punch through” etch is then performed to remove portions of the sacrificial material **132** and expose the underlying portions of the uppermost additional insulative structure **106a** of the individual steps **122**. Accordingly, the sacrificial material **132** may be formed to extend from an upper surface of the dielectric material **116** to the steps **122** of the staircase structure **120**. After forming the sacrificial material **132**, the microelectronic device structure **100** may be exposed to a chemical mechanical planarization (CMP) process to remove sacrificial material outside of the boundaries of the openings **130**.

(45) The sacrificial material **132** may be formed of and include at least one material exhibiting etch selectivity with respect to each of the dielectric material **116**, the dielectric fill material **126**, the additional insulative structures **106**, and the insulative structures **104**, as well as additional materials (e.g., additional insulative materials, additional conductive materials) formed during subsequent processing of the microelectronic device structure **100**. In some embodiments, the sacrificial material **132** comprises conductive material. By way of non-limiting example, the sacrificial material **132** may be formed of and include one or more of polysilicon, tungsten, titanium, titanium nitride, aluminum oxide, and another material. In some embodiments, the sacrificial material **132** comprises amorphous silicon or polycrystalline silicon. In some such embodiments, the sacrificial material **132** may be doped with one or more dopants, such as with at least one N-type dopant (e.g., one or more of arsenic, phosphorous, antimony, and bismuth) or at least one P-type dopant (e.g., one or more of boron, aluminum, and gallium). In other embodiments, the sacrificial material **132** comprises tungsten. The sacrificial material **132** may, alternatively, be formed of and include one or more of silicon oxycarbide ($\text{SiO}_{\text{sub.x}}\text{C}_{\text{sub.y}}$), silicon oxynitride ($\text{SiO}_{\text{sub.x}}\text{N}_{\text{sub.y}}$), hydrogenated silicon oxycarbide ($\text{SiC}_{\text{sub.x}}\text{O}_{\text{sub.y}}\text{H}_{\text{sub.z}}$), or silicon oxycarbonitride ($\text{SiO}_{\text{sub.x}}\text{C}_{\text{sub.y}}\text{N}_{\text{sub.z}}$), for example. In some embodiments, the sacrificial material **132** is formed of and includes a carbon-containing material.

(46) For clarity and ease of understanding the disclosure, the dielectric material **116** is not shown throughout the remaining description and the accompanying figures, but it is understood that the microelectronic device structure **100** may, optionally, include the dielectric material **116**.

(47) Referring to FIG. **1D**, prior to formation of the dielectric fill material **126**, an insulative liner

material **128** may, optionally, be formed to vertically overlie (e.g., in the Z-direction) the staircase structure **120**, the vertically uppermost tier **108** of the insulative structures **104**, and the additional insulative structures **106**. For convenience, the insulative liner material **128** is absent in previous views of the drawings, although it is understood that the insulative liner material **128** may be present in embodiments of the disclosure at the processing stages of FIGS. **1A** through **1C**. If present, the insulative liner material **128** may be formed to vertically overlie (e.g., in the Z-direction) the staircase structure **120**.

(48) As shown in FIG. **1D**, the insulative liner material **128** may include upper portions **128a** and side portions **128b** proximate to and intervening between neighboring portions of the upper portions **128a**. For example, the upper portions **128a** may horizontally extend across (e.g., in the Y-direction) and substantially cover upper surfaces of the steps **122**, and the side portions **128b** may vertically extend across (e.g., in the Z-direction) and substantially cover side surfaces of the steps **122**. The insulative liner material **128** may be formed to include a substantially continuous material (e.g., a substantially continuous liner material) on or over the steps **122** of the staircase structure **120**. The upper portion **128a** of the insulative liner material **128** may be formed to include a sacrificial portion (e.g., a central portion) formulated to be removed during formation of openings (e.g., the openings **130** (FIG. **1C**)) and a remaining portion designated to remain on or over the steps **122** of the staircase structure **120**. The remaining portion of the upper portions **128a** of the insulative liner material **128** may be located horizontally proximate to and at least partially surrounding the sacrificial portion thereof. In some embodiments, the sacrificial material **132** extends to an upper surface of the insulative liner material **128**, as shown in FIG. **1D**. The insulative liner material **128** may act as an etch stop material during removal of the dielectric fill material **126** and formation of the openings **130**. In other embodiments, the openings **130** and, thus, the sacrificial material **132** are formed to extend through the insulative liner material **128** such that portions of the sacrificial material **132** are laterally adjacent to the insulative liner material **128**.

(49) The insulative liner material **128** may exhibit etch selectivity relative to the dielectric material **116**, the dielectric fill material **126**, and the sacrificial material **132**. In some embodiments, the insulative liner material **128** is formed of and includes at least one insulative material, such as one or more of the materials described above with reference to the insulative structures **104** (e.g., SiO.sub.2). In other embodiments, the insulative liner material **128** may be formed of and include one or more of the materials described above with reference to the additional insulative structures **106** (e.g., Si.sub.3N.sub.4). The insulative liner material **128** may, alternatively, be formed of and include one or more of silicon oxycarbide (SiO.sub.xC.sub.y), silicon oxynitride (SiO.sub.xN.sub.y), hydrogenated silicon oxycarbide (SiC.sub.xO.sub.yH.sub.z), or silicon oxycarbonitride (SiO.sub.xC.sub.yN.sub.z), for example.

(50) With continued reference to FIG. **1D**, following formation of the sacrificial material **132**, extended openings **131** (e.g., extended contact openings) may be formed to vertically extend (e.g., in the Z-direction) through the dielectric fill material **126**, the insulative liner material **128**, if present, and the preliminary stack structure **102**, such as through tiers **108** of the insulative structures **104** and the additional insulative structures **106** within the staircase region **105**. For example, the extended openings **131** may vertically extend from a vertically uppermost boundary of the dielectric fill material **126** to or beyond a vertically uppermost boundary of the first conductive material **112** of the source tier **110**, without terminating on the steps **122** of the staircase structure **120**. The extended openings **131** may be formed to be self-aligned with the openings **130**. Accordingly, the extended openings **131** may be formed within horizontal areas of the openings **130** (FIG. **1C**) and extend below a lower boundary of the sacrificial material **132**.

(51) At least portions of each of the insulative liner material **128**, the insulative structures **104**, and the additional insulative structures **106** are removed by exposing the respective materials to wet etch chemistries and/or dry etch chemistries, for example, in one or more material removal processes. Portions of the initial material of the insulative liner material **128** (e.g., the central

portions) may be removed (e.g., etched) in one or more material removal processes resulting in a horizontal dimension (e.g., width) of each of the extended openings **131** being relatively less than that of the upper portions **128a** of the insulative liner material **128** (e.g., corresponding to upper surfaces of the steps **122** of the staircase structure **120**). Additional portions of the upper portions **128a** of the insulative liner material **128** may remain on the upper surfaces of the steps **122** of the staircase structure **120** following formation of the extended openings **131**.

(52) As shown in FIG. 1D, the extended openings **131** extend beyond the upper surfaces of the steps **122** of the staircase structure **120** and through the materials of the preliminary stack structure **102**. Accordingly, the extended openings **131** may be formed to extend from an upper surface of the dielectric fill material **126** to the source tier **110** underlying the preliminary stack structure **102**. In other words, the extended openings **131** extend entirely through a vertical extent (e.g., a height) of the preliminary stack structure **102**. Thus, a height of each of the extended openings **131** in the vertical direction (e.g., the Z-direction) may be substantially similar to (e.g., substantially the same as) one another irrespective of horizontal orientation relative to the steps **122** of the staircase structure **120**.

(53) The first conductive material **112** of the source tier **110** may act as an etch stop material during removal of each of the dielectric fill material **126**, the insulative liner material **128**, the insulative structures **104**, and the additional insulative structures **106**, and formation of the extended openings **131**. In some such embodiments, the extended openings **131** terminate within the source tier **110**, such as at or within the first conductive material **112** at the processing stage depicted in FIG. 1D. In other embodiments, the extended openings **131** terminate at or within an insulative material overlying the first conductive material **112**. In additional embodiments, the extended openings **131** extend through the first conductive material **112** and terminate at or within the second conductive material **114**. As will be described herein, the extended openings **131** may be used to form conductive contacts (e.g., conductive contacts **140** (FIGS. 1F and 1G)) in contact with conductive contact structures (e.g., strapping structures **160** (FIG. 1J)) of the staircase structure **120**.

(54) Referring to FIG. 1E, prior to forming materials of the conductive contacts **140** (FIG. 1G) within the extended openings **131**, lateral (e.g., in the X-direction, in the Y-direction) portions of the additional insulative structures **106** may be converted to another insulative material to isolate the additional insulative structures **106** from the materials of the conductive contacts **140**. For example, an initial material (e.g., a silicon nitride material of the additional insulative structures **106**) may be oxidized to form a liner material **136** (e.g., an inner liner material, an inner insulative material). Accordingly, the liner material **136** may be directly laterally adjacent to (e.g., continuous with) remaining portions of the additional insulative structures **106**. In some such embodiments, the liner material **136** is formed of and includes an oxide material having a material composition that differs from that of the remaining portions of the additional insulative structures **106**, although other materials of the liner material **136** may be contemplated, so long as the liner material **136** exhibits etch selectivity relative to surrounding materials.

(55) Formation of the liner material **136** within the recessed regions may result in formation of isolation regions **134** between the extended openings **131** and the remaining portions of the additional insulative structures **106**, such that portions of the additional insulative structures **106** having a first material composition are remote (e.g., isolated) from the extended openings **131** by the liner material **136** of the isolation regions **134** having a second, different material composition. Stated another way, process acts may be selected to provide (e.g., facilitate, promote) formation of the liner material **136** proximate the extended openings **131** for formation of the isolation regions **134** between the remaining portions of the horizontally neighboring additional insulative structures **106** and subsequently formed materials of the conductive contacts **140** (FIG. 1G) within the extended openings **131**.

(56) Alternatively, the lateral portions of the additional insulative structures **106** may be selectively removed through the extended openings **131** to form recessed regions for formation of the isolation

regions **134**. By way of non-limiting example, exposed portions of the additional insulative structures **106** may be exposed to an etchant (e.g., a wet etchant) through the extended openings **131** to selectively remove portions of the additional insulative structures **106** with respect to the insulative structures **104**. In some embodiments, the additional insulative structures **106** are exposed to phosphoric acid (H_3PO_4) to selectively remove portions of the additional insulative structures **106** proximate the extended openings **131**.

(57) After selectively removing portions of the additional insulative structures **106**, the liner material **136** may be formed within the recessed regions proximate remaining portions of the additional insulative structures **106** without fully filling the extended openings **131**. For example, the liner material **136** may be formed within the recessed regions to effectively “pinch off” and close (e.g., seal) the recessed regions immediately adjacent to the extended openings **131**. The liner material **136** may be formed to extend between vertically neighboring insulative structures **104** proximate the recessed regions vacated by portions of the additional insulative structures **106** such that the liner material **136** substantially vertically fills portions of the recessed regions proximate the extended openings **131** without entirely filling the extended openings **131**. The liner material **136** is formed by conventional techniques, such as one or more of in situ growth, CVD, ALD, and PVD using conventional processing equipment. In some embodiments, the liner material **136** may be formed (e.g., deposited) using a single, continuous ALD process or a single, continuous CVD process.

(58) The liner material **136** may be formed of and include one or more of the materials described above with reference to the insulative structures **104** (SiO_2). For example, the liner material **136** may be formed of and include at least one insulative material that is different than, and that exhibits etch selectivity with respect to, one or more of the additional insulative structures **106** and the insulative liner material **128**. In some embodiments, the liner material **136** is formed of and includes a single high-quality silicon oxide material, such as an ALD SiO_x . For example, the liner material **136** may be a highly uniform and highly conformal silicon oxide material (e.g., a highly uniform and highly conformal silicon dioxide material) so that substantially no voids are present in the liner material **136**. The liner material **136** may, alternatively, be formed of and include one or more of silicon oxycarbide (SiO_xC_y), silicon oxynitride (SiO_xN_y), hydrogenated silicon oxycarbide ($\text{SiC}_x\text{O}_y\text{H}_z$), or silicon oxycarbonitride ($\text{SiO}_x\text{C}_y\text{N}_z$), for example.

(59) As shown in FIG. 1E, one or more side surfaces (e.g., lateral side surfaces, horizontal side surfaces) of the isolation regions **134** may directly contact side surfaces of the remaining portions of the additional insulative structures **106** of the preliminary stack structure **102** along interfaces **138** (e.g., vertical interfaces). The sacrificial material **132** may exhibit a greater lateral extent (e.g., a width in the Y-direction) than a lateral extent of the isolation regions **134**, as shown in FIG. 1E. In other words, the remaining portions of the additional insulative structures **106** may be adjacent to (e.g., underlying) the sacrificial material **132**. In additional embodiments, side surfaces of the sacrificial material **132** are substantially aligned with side surfaces of the isolation regions **134** or, alternatively, the isolation regions **134** may exhibit a slightly greater lateral extent than a lateral extent of the sacrificial material **132**, so long as remaining portions of the uppermost additional insulative structure **106a** are accessible through subsequently formed openings proximate to the isolation regions **134**.

(60) Referring next to FIG. 1F, following formation of the isolation regions **134** (FIG. 1E), a liner material **142** (e.g., insulative material) and a fill material **144** (e.g., conductive material) may be formed within the extended openings **131** (FIG. 1E) to form the conductive contacts **140**. Formation of the liner material **142** and the fill material **144** of the conductive contacts **140** is described in further detail below, along with additional components (e.g., structures, features) of the microelectronic device structure **100** at the processing stage depicted in FIG. 1F. FIG. 1G is a simplified, partial cross-sectional view of the microelectronic device structure **100** about the line G-

G shown in FIG. 1F. For clarity and ease of understanding of the drawings and related description, not all features depicted in one of FIGS. 1F and 1G are depicted the other of FIGS. 1F and 1G. (61) As shown in FIG. 1F, in combination with FIG. 1G, the liner material **142** of the conductive contacts **140** may be formed (e.g., conformally formed) in the extended openings **131** (FIG. 1E). Accordingly, the liner material **142** is formed in the extended openings **131** without fully filling the extended openings **131**. The liner material **142** may be continuous along a vertical dimension (e.g., a vertical height) of the dielectric fill material **126** and the preliminary stack structure **102**. The liner material **142** may be formed of and include insulative material, such as a dielectric oxide material. For example, the material of the liner material **142** may include a silicon oxide material (e.g., relatively high-quality silicon oxide material, such as an ALD SiO₂). A material composition of the liner material **142** may be substantially the same as a material composition of the dielectric fill material **126**, or the material composition of the liner material **142** may be different than the material composition of the dielectric fill material **126**. Accordingly, the material of the liner material **142** may or may not exhibit etch selectivity with respect to the dielectric fill material **126**. The liner material **142** may be formed by conventional techniques, such as by CVD or ALD. In some embodiments, the liner material **142** is formed by plasma-enhanced ALD (PEALD).

(62) Portions (e.g., upper portions) of the liner material **142** of the conductive contacts **140** may be in contact with and substantially surrounded by the sacrificial material **132** above an elevational level of the staircase structure **120** at the processing stage of FIGS. 1F and 1G. Additional portions (e.g., lower portions) of the liner material **142** may be in contact with and substantially surrounded by the insulative liner material **128**, the insulative structures **104**, and the liner material **136** of the isolation regions **134** of the preliminary stack structure **102**. The liner material **142** may also be in contact with the first conductive material **112** of the source tier **110**. Accordingly, the liner material **142** may be formed to extend from the upper surface of the dielectric fill material **126** to the source tier **110** underlying the preliminary stack structure **102**. The liner material **142** may terminate at or within the second conductive material **114** of the source tier **110**. Alternatively, the liner material **142** may terminate at or within the first conductive material **112**.

(63) The liner material **142** of the conductive contacts **140** may have a thickness within a range of from about 10 nm to about 60 nm, such as from about 10 nm to about 20 nm, from about 20 nm to about 30 nm, from about 30 nm to about 40 nm, from about 40 nm to about 50 nm, or from about 50 nm to about 60 nm. In some embodiments, the thickness of the liner material **142** is about 40 nm. However, the disclosure is not so limited and the thickness of the liner material **142** may be different than those described above. The thickness of the liner material **142** may be tailored to facilitate isolation of the fill material **144** from additional materials (e.g., conductive materials) to be formed adjacent to the conductive contacts **140**. For example, the thickness of the liner material **142** may be responsive to a magnitude of a bias voltage applied during use and operation of the microelectronic device structure **100**.

(64) The fill material **144** (e.g., conductive material) of the conductive contacts **140** may be formed adjacent to the liner material **142** within the extended openings **131** (FIG. 1E). For example, the fill material **144** may substantially fill a remainder of the extended openings **131** and be at least partially (e.g., substantially) laterally surrounded by the liner material **142**. Accordingly, the conductive contacts **140** may be formed to extend from the upper surface of the dielectric fill material **126** to the source tier **110** underlying the preliminary stack structure **102**. The conductive contacts **140** may terminate at or within the second conductive material **114** of the source tier **110**. Alternatively, the conductive contacts **140** may terminate at or within the first conductive material **112**. In such embodiments, the conductive contacts **140** are formed to be self-aligned with the underlying conductive materials (e.g., the first conductive material **112**) using a so-called “assisted self-alignment” process.

(65) The fill material **144** of the conductive contacts **140** may be formed of and include at least one

conductive material. By way of non-limiting example, the fill material **144** may be formed of and include one or more of polysilicon, tungsten, titanium, titanium nitride, and another material. In some embodiments, the conductive material comprises polysilicon. In some such embodiments, the fill material **144** is doped with one or more dopants, such as with at least one N-type dopant (e.g., one or more of arsenic, phosphorous, antimony, and bismuth) or at least one P-type dopant (e.g., one or more of boron, aluminum, and gallium). In other embodiments, the fill material **144** comprises tungsten. After forming the conductive contacts **140**, the microelectronic device structure **100** may be exposed to a chemical mechanical planarization (CMP) process to remove sacrificial material outside of the boundaries of the extended openings **131**. Upper surfaces of each of the sacrificial material **132**, the liner material **142**, and the fill material **144** may be substantially coplanar with one another at the processing stage of FIGS. **1F** and **1G**.

(66) Once formed, each of the conductive contacts **140** may vertically extend completely through the preliminary stack structure **102** without terminating on the steps **122** of the staircase structure **120**, as shown in FIG. **1G**. For example, the conductive contacts **140** may vertically extend (e.g., in the Z-direction) from a vertically uppermost boundary of the dielectric fill material **126** (e.g., at or above an elevational level of a vertically uppermost tier **108** of the preliminary stack structure **102**) to or beyond a vertically uppermost boundary of the second conductive material **114** of the source tier **110**. In some embodiments, the staircase structure **120** is substantially free of conductive contacts formed to terminate on the steps **122** thereof.

(67) The conductive contacts **140** may individually exhibit a substantially circular horizontal cross-sectional shape, as shown in the top-down view of FIG. **1F**. However, the disclosure is not so limited. As a non-limiting example, in additional embodiments, the conductive contacts **140** individually exhibit a substantially rectangular cross-sectional shape (e.g., a substantially square cross-sectional shape), or a different elongate cross-sectional shape (e.g., an oblong cross-sectional shape). At least some of the conductive contacts **140** may exhibit a different geometric configuration (e.g., one or more different dimensions, a different shape) and/or different horizontal spacing than at least some other of the conductive contacts **140**, or each of the conductive contacts **140** may exhibit substantially the same geometric configuration (e.g., the same dimensions and the same shape) and horizontal spacing (e.g., in the X-direction) as each of the other conductive contacts **140**. For example, individual conductive contacts **140** of the microelectronic device structure **100** may exhibit a height (e.g., in the Z-direction) that is substantially similar to a height of each other of the conductive contacts **140**.

(68) Accordingly, manufacturing processes may be simplified by forming the conductive contacts **140** to extend entirely through the vertical extent of the preliminary stack structure **102** and to terminate at a single location (e.g., at or within the source tier **110**), without forming the conductive contacts **140** to extend to varying (e.g., differing) depths of individual steps **122** of the staircase structure **120**. In contrast, conventional microelectronic device structures include conductive contacts that terminate (e.g., land on) upper surfaces of individual steps of staircase structures, resulting in varying heights of conductive contacts throughout the staircase structures. In some instances, damage may occur within the staircase structures during fabrication of conventional microelectronic device structures. Particularly, damage to the tier materials of the tiers, also called “clipping,” may be a source of defect, which can adversely affect memory device performance.

(69) In addition, misaligned conductive contacts that terminate on upper surfaces of the individual steps of staircase structures, may be susceptible to bridging (e.g., shorting, electrical connection) between neighboring portions of conductive structures (e.g., access lines). Further, terminating the conductive contacts at varying (e.g., differing) depths of the steps of the staircase structure of conventional microelectronic device structures may result in so-called “overetch” or “underetch” during processing. Accordingly, each of the conductive contacts **140** of the microelectronic device structure **100** may be formed to extend entirely through the vertical extent of the preliminary stack structure **102** and to terminate at the single location in order to substantially reduce (e.g.,

substantially prevent) damage within the staircase structure **120** during fabrication.

(70) Referring to FIG. **1H**, the sacrificial material **132** (FIG. **1G**) may be removed (e.g., exhumed) to form second openings **146** vertically extending (e.g., in the Z-direction) through the dielectric fill material **126**. The second openings **146** (e.g., initial second openings) may horizontally (e.g., in the X-direction, in the Y-direction) neighbor the liner material **142** of the conductive contacts **140** and the dielectric fill material **126** overlying the steps **122** of the staircase structure **120**. To remove the sacrificial material **132**, the microelectronic device structure **100** may be exposed to one or more etchants formulated and configured to selectively remove the sacrificial material **132** without substantially removing the dielectric fill material **126** and the liner material **142**. By way of non-limiting example, the second openings **146** may be formed by exposing the sacrificial material **132** to a wet etchant, such as one or more of potassium hydroxide (KOH), sodium hydroxide (NaOH), tetramethylammonium hydroxide (TMAH), and another material. Prior to formation of the second openings **146**, portions of the dielectric fill material **126** and the conductive contacts **140** may be covered with an additional dielectric material (e.g., an additional portion of the dielectric material **116** (FIG. **1C**)) and/or an additional mask material configured and positioned to protect the dielectric fill material **126** and the materials of the conductive contacts **140** from being removed (e.g., exhumed) during the material removal processes of the sacrificial material **132**.

(71) The insulative liner material **128** or, alternatively, the uppermost additional insulative structure **106a** may act as an etch stop material during removal of the sacrificial material **132** and formation of the second openings **146**. For example, the second openings **146** may be formed to extend through the dielectric fill material **126** to expose upper surfaces of the insulative liner material **128**, as shown in FIG. **1H**. Alternatively, the second openings **146** may be formed to extend through each of the dielectric fill material **126** and the insulative liner material **128**, such as when the sacrificial material **132** (FIG. **1G**) is formed to extend laterally adjacent to the insulative liner material **128**. Accordingly, the second openings **146** may terminate at or within the insulative liner material **128** or, alternatively, at or within the uppermost additional insulative structure **106a** (FIG. **1B**) including the liner material **136** of the isolation regions **134**.

(72) Referring to FIG. **1I**, following formation of the second openings **146** (FIG. **1H**), expanded openings **147** may be formed to vertically extend (e.g., in the Z-direction) through the dielectric fill material **126**. By way of non-limiting example, following the formation of the second openings **146**, the dielectric fill material **126** may be subjected to an etching process to expand (e.g., increase) horizontal dimensions of the second openings **146** vertically extending within the dielectric fill material **126**. As will be described herein, the expanded openings **147** may be used to form structures (e.g., structures **152** (FIG. **1J**)) including the conductive contact structures (e.g., the strapping structures **160** (FIG. **1J**)) of the staircase structure **120**.

(73) The insulative liner material **128** or, alternatively, the uppermost additional insulative structure **106a** may act as an etch stop material during removal of the dielectric fill material **126** and formation of the expanded openings **147**. The expanded openings **147** may vertically extend from a vertically uppermost boundary of the dielectric fill material **126** to or beyond a vertically uppermost boundary of the insulative liner material **128** or, alternatively, to a vertically uppermost boundary of the uppermost additional insulative structure **106a**. Accordingly, at least portions of the expanded openings **147** may extend through the insulative liner material **128**.

(74) In some embodiments, portions (e.g., lateral portions) of the liner material **142** of the conductive contacts **140** are selectively removed through the expanded openings **147**. For example, upper portions of the liner material **142** may be selectively removed relative to lower portions thereof within the expanded openings **147**, to recess the upper portions of the liner material **142** a lateral distance. Accordingly, a width of the upper portions of the liner material **142** above the staircase structure **120** (e.g., above upper surfaces of the uppermost additional insulative structure **106a** of the individual steps **122** thereof) may be relatively less than a width of the lower portions of the liner material **142** within the staircase structure **120**, as best shown in the enlarged view of

FIG. 1N.

(75) Portions of one or more of the dielectric fill material **126** and the liner material **142** are removed by exposing the respective materials to wet etch chemistries and/or dry etch chemistries, for example, in one or more material removal processes. By way of non-limiting example, portions of the dielectric fill material **126** and/or the liner material **142** may be exposed to hydrogen fluoride (HF), or to other halogen-based etch chemistries. However, the disclosure is not so limited and the dielectric fill material **126** and the liner material **142** may be removed by additional or alternative methods (e.g., by a buffered oxide etching (BOE) process). Thus, portions of one or more of the dielectric fill material **126** and the liner material **142** may be recessed to form the expanded openings **147**. Recessing the dielectric fill material **126** and/or the liner material **142** increases the horizontal width of the second openings **146** (FIG. 1H), forming the expanded openings **147** adjacent to the dielectric fill material **126** and the liner material **142**.

(76) Additional portions (e.g., uppermost portions) of the liner material **142** may also be removed (e.g., exhumed) to form lateral openings **148** in communication with (e.g., continuous with) the expanded openings **147** and to expose side surfaces of the fill material **144**. Further, portions of the liner material **136** of the isolation regions **134** of the uppermost additional insulative structure **106a** may be removed (e.g., exhumed) to form vertical openings **150** in communication with the expanded openings **147** and to expose upper surfaces of the uppermost insulative structure **104a**. The isolation regions **134** of the uppermost additional insulative structure **106a** may be locations designated for the vertical openings **150**. Accordingly, the vertical openings **150** are defined in at least one horizontal direction (e.g., the X-direction, the Y-direction) by the liner material **142** (e.g., the lower portions thereof) and the remaining portions of the uppermost additional insulative structure **106a** at the processing stage of FIG. 1I.

(77) The lateral openings **148** and the vertical openings **150** may be formed by, for example, forming and patterning one or more mask materials over the microelectronic device structure **100** and exposing the microelectronic device structure **100** to suitable etchants. For example, the lateral openings **148** may be formed in regions vacated by the uppermost portions of the liner material **142**, and the vertical openings **150** may be formed in regions vacated by the liner material **136** of the isolation regions **134** of the uppermost additional insulative structure **106a** following formation or, alternatively, during formation of the expanded openings **147**.

(78) The expanded openings **147** may exhibit a greater lateral extent (e.g., a width in the Y-direction) than a lateral extent of additional isolation regions **134** underlying the uppermost insulative structure **104a**, as shown in FIG. 1I. In other words, the remaining portions of the additional insulative structures **106** may be adjacent to (e.g., underlying) the expanded openings **147**. Since the vertical openings **150** are formed in regions vacated by the liner material **136** of the isolation regions **134**, the expanded openings **147** may also exhibit a greater lateral extent than a lateral extent of the vertical openings **150**. While FIG. 1I illustrates the expanded openings **147**, as well as the lateral openings **148** and the vertical openings **150**, being formed following formation of the second openings **146** (FIG. 1H) for clarity, the disclosure is not so limited, and one or more of the expanded openings **147**, the lateral openings **148**, and the vertical openings **150** may be formed during (e.g., substantially simultaneous with) formation of the second openings **146** to reduce cost and the number of process acts conducted.

(79) Referring next to FIG. 1J, following formation of the expanded openings **147** (FIG. 1I), the lateral openings **148** (FIG. 1I), and the vertical openings **150** (FIG. 1I), conductive material **154** may be formed within each of the expanded openings **147**, the lateral openings **148**, and the vertical openings **150** to form the structures **152** (e.g., conductive contact structures, combined contact and support structures) adjacent to (e.g., directly laterally adjacent to) the liner material **142** of the conductive contacts **140**. The structures **152** are defined by the conductive material **154** (also described herein as the strapping structures **160**) and the materials (e.g., the liner material **142**, the fill material **144**) of the conductive contacts **140**. The structures **152** may be configured as so-called

“through array contacts.”

(80) Since the conductive contacts **140** are aligned within and substantially surrounded by the strapping structures **160**, the structures may be characterized as “coaxial structures.” As used herein, the term “coaxial” means and includes structures and features that share a common axis. For example, the conductive contacts **140** of the structures **152** share a common axis (e.g., a longitudinal axis) with the strapping structures **160** thereof. Accordingly, the structures **152** may be three-dimensional linear structures individually including an inner conductive core (e.g., the fill material **144** of the conductive contacts **140**) vertically extending from an uppermost boundary of the preliminary stack structure **102** to conductive material (e.g., the second conductive material **114**) of the source tier **110** underlying a lowermost boundary of the preliminary stack structure **102**, an outer conductive shell (e.g., the conductive material **154** of the strapping structures **160**) laterally surrounding portions of the inner conductive core, and the liner material **142** of the conductive contacts **140** separating the inner conductive core from the outer conductive shell.

(81) The conductive material **154** of the structures **152** may be formed over exposed portions of the uppermost additional insulative structure **106a** and may fill (e.g., substantially fill) the expanded openings **147** (FIG. 1I). Since the upper portions of the liner material **142** may be laterally recessed relative to the lower portions thereof, lower surfaces of the conductive material **154** may directly contact upper surfaces of the lower portions of the liner material **142** along interfaces **156** (e.g., horizontal interfaces). In addition, the conductive material **154** may be formed over uppermost surfaces of remaining portions of the liner material **142** and may fill (e.g., substantially fill) the lateral openings **148** (FIG. 1I).

(82) Side surfaces (e.g., lateral side surfaces) of the conductive material **154** may be in direct physical contact with side surfaces of the fill material **144** along interfaces **158** (e.g., vertical interfaces). The conductive material **154** may be directly adjacent to and operably coupled (e.g., electrically connected) with the fill material **144**. In some embodiments, the conductive material **154** of the structures **152** is integral and continuous with the fill material **144** of the conductive contacts **140** at an elevational level above the liner material **142**. Thus, the strapping structures **160** are electrically coupled to upper portions of the fill material **144** of the conductive contacts **140** and isolated from lower portions of the fill material **144** thereof by the liner material **142**. Further, the conductive material **154** may be formed over exposed portions of the uppermost insulative structure **104a** and may fill (e.g., substantially fill) the vertical openings **150** (FIG. 1I).

Accordingly, the conductive material **154** of individual structures **152** includes a first portion **154a** within the lateral openings **148**, a second portion **154b** within the expanded openings **147**, and a third portion **154c** within the vertical openings **150**. Upper surfaces of the strapping structures **160** (e.g., the conductive material **154** thereof) and the conductive contacts **140** (e.g., the fill material **144** thereof) may be substantially coplanar with one another.

(83) As shown in FIG. 1J, the conductive material **154** may be continuous along a vertical dimension (e.g., a vertical height) of the expanded openings **147** (FIG. 1I), including the lateral openings **148** (FIG. 1I) and the vertical openings **150** (FIG. 1I). Accordingly, the conductive material **154** may be formed to extend from the upper surface of the dielectric fill material **126** to the uppermost insulative structure **104a** of the preliminary stack structure **102**, with portions of the conductive material **154** terminating at or within the uppermost insulative structure **104a** and additional portions thereof terminating at or within the uppermost additional insulative structure **106a**.

(84) Portions (e.g., upper portions) of the fill material **144** of the conductive contacts **140** may be in contact (e.g., physical contact, electrical contact) with and substantially surrounded by the conductive material **154** (e.g., the first portion **154a**), without the liner material **142** thereof intervening therebetween. In addition, portions of the liner material **142** may be in contact with and substantially surrounded by the conductive material **154** (e.g., the second portion **154b**) above an elevational level of the uppermost additional insulative structure **106a** of the preliminary stack

structure **102**, and additional portions of the liner material **142** may be in contact with and substantially surrounded by the conductive material **154** (e.g., the third portion **154c**) laterally adjacent to the uppermost additional insulative structure **106a** at the processing stage of FIG. **1J**. The conductive material **154** (e.g., the first portion **154a** thereof) directly intervenes between the fill material **144** and the dielectric fill material **126** overlying the staircase structure **120**, the second portion **154b** thereof directly intervenes between the upper portion of the liner material **142** and the dielectric fill material **126**, and the third portion **154c** thereof directly intervenes between the lower portion of the liner material **142** and the uppermost additional insulative structure **106a**. Thus, the structures **152** include the liner material **142** of the conductive contacts **140** laterally intervening between a lower portion of the fill material **144** thereof and the conductive material **154**, with an upper portion of the conductive material **154** overlying the liner material **142** and physically contacting the fill material **144**. Stated another way, the strapping structures **160** substantially laterally surround upper portions of the conductive contacts **140** above an elevational level of the individual steps **122** of the staircase structure **120**, without being laterally adjacent to the conductive contacts **140** within the preliminary stack structure **102**.

(85) The first portion **154a** of the conductive material **154** may have a thickness (e.g., a height in the Z-direction) within a range of from about 10 nm to about 40 nm, such as from about 10 nm to about 20 nm, from about 20 nm to about 30 nm, or from about 30 nm to about 40 nm. However, the disclosure is not so limited and the thickness of the first portion **154a** of the conductive material **154** may be different than those described above. In some embodiments, the thickness of the first portion **154a** of the conductive material **154** substantially equal to a thickness (e.g., a height) of the additional insulative structures **106** of the preliminary stack structure **102**, which reflects a thickness of subsequently formed conductive structures (e.g., access lines) within regions vacated by the additional insulative structures **106**.

(86) The conductive material **154** of the structures **152** may be formed of and include at least one conductive material. By way of non-limiting example, the conductive material **154** may be formed of and include one or more of polysilicon, tungsten, titanium, titanium nitride, and another material. In some embodiments, the conductive material comprises polysilicon. In some such embodiments, the conductive material **154** is doped with one or more dopants, such as with at least one N-type dopant (e.g., one or more of arsenic, phosphorous, antimony, and bismuth) or at least one P-type dopant (e.g., one or more of boron, aluminum, and gallium). In other embodiments, the conductive material **154** comprises tungsten. The conductive material **154** of the structures **152** and the fill material **144** of the conductive contacts **140** may or may not include substantially the same material composition as one another.

(87) With continued reference to FIG. **1J**, formation of the conductive material **154** results in formation of the strapping structures **160** (e.g., vertically projecting structures, horizontally projecting structures) of the staircase structure **120**. The size and location of the strapping structures **160** may correspond to the size and location of the expanded openings **147** (FIG. **1I**), the lateral openings **148**, (FIG. **1I**), and the vertical openings **150** (FIG. **1I**). The strapping structures **160** may be considered portions of the structures **152** including the respective portions (e.g., the first portion **154a**, the second portion **154b**, the third portion **154c**) of the conductive material **154** that, in turn, are operably coupled (e.g., electrically connected) to the fill material **144** of the conductive contacts **140**. In other words, the strapping structures **160** provide electrical connection between the conductive contacts **140** and conductive structures (e.g., access lines, conductive structures **174** (FIG. **1L**)), as will be described herein.

(88) For example, as shown in FIG. **1J**, the conductive contacts **140** of the structures **152** may individually include the fill material **144** in electrical communication with the source tier **110**, such as with the second conductive material **114** thereof. In addition, the structures **152** may also individually include the conductive material **154**, corresponding to one of the strapping structures **160**, in electrical communication with the fill material **144** and adjacent to (e.g., laterally adjacent

to, vertically adjacent to) the uppermost additional insulative structure **106a** of the individual steps **122** of the staircase structure **120** at the processing stage of FIG. **1J**. The additional insulative structures **106** defining each step **122** (e.g., the uppermost additional insulative structure **106a**) may be directly adjacent to the strapping structures **160** on at least two sides (e.g., a lateral side and a vertical side).

(89) Referring next to FIG. **1K**, slots **162** (also referred to herein as “replacement gate slots”) may be formed through the preliminary stack structure **102** (FIG. **1J**) to facilitate the replacement of the additional insulative structures **106** (FIG. **1J**) with conductive structures. The additional insulative structures **106** may be at least partially (e.g., substantially) replaced with the conductive structures **174** comprising at least one conductive material **180** to form a stack structure **175** comprising tiers **176** of the conductive structures **174** vertically interleaved with the insulative structures **104** through so-called “replacement gate” or “gate last” processing acts. The slots **162** may then be filled with dielectric material **166**. Formation of the slots **162** and the conductive structures **174** is described in further detail below, along with additional components (e.g., structures, features) of the microelectronic device structure **100** at the processing stage depicted in FIG. **1K**. FIG. **1L** is a simplified, partial cross-sectional view of the microelectronic device structure **100** about the line L-L shown in FIG. **1K**. For clarity and ease of understanding of the drawings and related description, not all features depicted in one of FIGS. **1K** and **1L** are depicted the other of FIGS. **1K** and **1L**.

(90) As shown in FIG. **1K**, the slots **162** may be formed to vertically extend (e.g., in the Z-direction) through the preliminary stack structure **102** (FIG. **1J**), such as through the dielectric fill material **126**, the insulative liner material **128**, and the tiers **108** (FIG. **1J**) of the insulative structures **104** and the additional insulative structures **106** (FIG. **1J**). At least portions of each of the dielectric fill material **126**, the insulative liner material **128**, the insulative structures **104**, and the additional insulative structures **106** are removed by exposing the respective materials to wet etch chemistries and/or dry etch chemistries, for example, in one or more material removal processes. Prior to formation of the slots **162**, portions of the dielectric fill material **126** and the preliminary stack structure **102** including the structures **152** may be covered with an additional dielectric material (e.g., an additional portion of the dielectric material **116** (FIG. **1C**)) and/or an additional mask material configured and positioned to protect the dielectric fill material **126** and the structures **152** from being removed (e.g., etched) during the material removal processes of the dielectric fill material **126** and the materials of the preliminary stack structure **102**. While the slots **162** are illustrated as being formed after formation of the structures **152** for clarity and ease of understanding of the drawings and related description, the slots **162** may, alternatively, be formed before formation of the structures **152**. For example, the slots **162** may be formed during (e.g., substantially simultaneous with) formation of the extended openings **131** (FIG. **1E**) to reduce cost and the number of process acts conducted.

(91) The slots **162** may extend to the source tier **110**, such as to the first conductive material **112**. Alternatively, the slots **162** may terminate at or within an insulative material overlying the first conductive material **112**. The slots **162** may separate (e.g., divide) the microelectronic device structure **100** into block structures **164**. Although FIG. **1K** illustrates only three slots **162** and only two block structures **164**, the disclosure is not so limited. The microelectronic device structure **100** may include a plurality of (e.g., four, five, six, eight) block structures **164**, each separated from laterally neighboring (e.g., in the X-direction) block structures **164** by one of the slots **162**. In other words, the slots **162** may divide the microelectronic device structure **100** into any desired quantity of block structures **164**.

(92) In addition, support structures **168** (e.g., additional support structures, mechanical support structures) may, optionally, be formed between at least some of the slots **162** within the staircase region **105**, as shown in FIG. **1K**. The support structures **168** may be formed to horizontally neighbor one or more areas of the structures **152**, although other configurations may be contemplated.

(93) The support structures **168**, if present, may provide additional mechanical integrity and support to portions of the tiers **108** (FIG. 1J) of the insulative structures **104** (FIG. 1J) and the additional insulative structures **106** (FIG. 1J) within the staircase region **105**, in addition to the mechanical support provided by the structures **152**. The support structures **168** may be positioned within or proximate to regions of the preliminary stack structure **102** (FIG. 1J) prone to tier collapse during the replacement gate processing acts. In some embodiments, the support structures **168** are positioned horizontally proximate to the structures **152**, such as between neighboring columns of the structures **152** and/or between a column of the structures **152** and one of the slots **162**. In some such embodiments, the microelectronic device structure **100** may include the support structures **168** between horizontally neighboring portions of the slots **162** that are substantially absent (e.g., substantially devoid) of the structures **152**.

(94) The support structures **168** may be formed in openings vertically extending through the tiers **108** (FIG. 1J) of the preliminary stack structure **102** (FIG. 1J). The support structures **168** may individually include a liner material **170**, and a fill material **172** surrounded by the liner material **170**. For each of the support structures **168**, the liner material **170** may be formed (e.g., conformally formed) within an opening formed in the preliminary stack structure **102**. The liner material **170** may be continuous along a vertical distance of the preliminary stack structure **102**. The liner material **170** may be formed of and include insulative material, such as a dielectric oxide material. For example, the material of the liner material **170** may include a silicon oxide material (e.g., relatively high-quality silicon oxide material, such as an ALD SiO₂). A material composition of the liner material **170** may be substantially the same as a material composition of the liner material **142** of the conductive contacts **140**, or the material composition of the liner material **170** may be different than the material composition of the liner material **142** of the conductive contacts **140**. The material of the liner material **170** may exhibit etch selectivity with respect to the additional insulative structures **106** (FIG. 1J). The liner material **170** may be formed by conventional techniques, such as by CVD or ALD. In some embodiments, the liner material **170** is formed by plasma-enhanced ALD (PEALD).

(95) The fill material **172** of the support structures **168** may be formed adjacent (e.g., over) the liner material **170**. In some embodiments, the fill material **172** is formed of and includes an insulative material, such as a silicon oxide material. In other embodiments, the fill material **172** is formed of and includes a conductive material including, but not limited to, N-doped polysilicon, P-doped polysilicon, undoped polysilicon, or a metal, such as tungsten. A material composition of the fill material **172** may be substantially the same as a material composition of the fill material **144** of the conductive contacts **140**, or the material composition of the fill material **172** may be different than the material composition of the fill material **144** of the conductive contacts **140**. In some such embodiments, one or more of the liner material **170** and the fill material **172** of the support structures **168** may be formed during (e.g., substantially simultaneous with) formation of the liner material **142** and the fill material **144**, respectively, of the conductive contacts **140** in order to simplify manufacturing processes. The liner material **170** may substantially surround sidewalls of the fill material **172**. In some embodiments, such as where the fill material **172** comprises an insulative material, the support structures **168** may not include the liner material **170** on sidewalls of the fill material **172**, and the support structures **168** may only include the fill material **172** (e.g., the insulative material).

(96) The fill material **172** of the support structures **168** may be formed to substantially fill remaining portions of the openings extending vertically through the dielectric fill material **126** and the preliminary stack structure **102** (FIG. 1J) and to the source tier **110**. The support structures **168** may be proximate to the slots **162** and may be confined within the staircase region **105** of the microelectronic device structure **100**. At least some of the support structures **168** may be formed to extend vertically from an upper surface of the dielectric fill material **126** to or within the first conductive material **112** of the source tier **110**. Alternatively or additionally, at least some of the

support structures **168** (e.g., including the conductive material as the fill material **172**) may be formed to extend below the upper surface of first conductive material **112** into the second conductive material **114**. In some embodiments, the support structures **168** are configured to provide one or more functions (e.g., electrical connections) in addition to support functions. In additional embodiments, the support structures **168** are configured to substantially only serve support functions, and the structures **152** (e.g., alone) are configured to provide electrical connections to the source tier **110**. Upper surfaces of each of the dielectric fill material **126**, the structures **152**, and the support structures **168** may be substantially coplanar with one another. The conductive contacts **140** (and, hence, the structures **152**) may have about a same height as the support structures **168**, such as when each of the conductive contacts **140** and the support structures **168** vertically extend from a vertically uppermost boundary of the dielectric fill material **126** to or beyond a vertically uppermost boundary of the second conductive material **114** of the source tier **110** underlying the stack structure **175**.

(97) The support structures **168** may individually exhibit a substantially circular cross-sectional shape, as shown in the top-down view of FIG. **1K**. However, the disclosure is not so limited. As a non-limiting example, in additional embodiments, the support structures **168** individually exhibit a substantially rectangular cross-sectional shape (e.g., a substantially square cross-sectional shape), or a different elongate cross-sectional shape (e.g., an oblong cross-sectional shape). A lateral dimension (e.g., a width, a diameter in a horizontal direction) of one or more of the support structures **168** may be relatively less than a lateral dimension of the structures **152**. While only three support structures **168** are illustrated in FIG. **1K**, the disclosure is not so limited, and additional support structures **168** may be located adjacent to the structures **152** within the block structures **164** between horizontally (e.g., in the X-direction) neighboring portions of the dielectric material **166** within the slots **162** within the staircase region **105**.

(98) Further, in some embodiments, at least some of the structures **152** may be configured as mechanical support structures, without being configured to provide electrical connection between the conductive structures **174** (FIG. **1L**) and the source tier **110** (e.g., without forming the strapping structures **160**). For example, the sacrificial material **132** (FIG. **1G**) may be maintained (e.g., remain) laterally adjacent to the conductive contacts **140** in at least some of the structures **152**, without forming the second openings **146** (FIG. **1H**). Alternatively, the sacrificial material **132** may be replaced with insulative material (e.g., SiO₂, a carbon-containing material). In other embodiments, the sacrificial material **132** is initially be formed to include insulative material, which is maintained laterally adjacent to the conductive contacts **140**. In other words, at least some of the support structures **168** may be formed (e.g., derived) from initial structures of the structures **152**, but excluding the strapping structures **160**. In additional embodiments, the staircase structure **120** is substantially free of additional support structures (e.g., the support structures **168**) formed within the staircase region **105** and only the structures **152** including the strapping structures **160** serve as support structures within the staircase region **105**.

(99) Referring to FIG. **1L**, the additional insulative structures **106** (FIG. **1J**) may be selectively removed (e.g., exhumed) through the slots **162** (FIG. **1K**). Spaces between vertically neighboring (e.g., in the Z-direction) insulative structures **104** may be filled with the conductive material **180** to form the conductive structures **174** and the stack structure **175** including the tiers **176** of the insulative structures **104** and the conductive structures **174**.

(100) In some embodiments, the conductive material **180** of the conductive structures **174** comprises tungsten (W). In other embodiments, the conductive material **180** of the conductive structures **174** comprises conductively doped polysilicon. For each of the conductive structures **174**, the conductive material **180** thereof may be substantially homogeneous or may be substantially heterogeneous. In some embodiments, each of the conductive structures **174** is substantially homogeneous. In additional embodiments, at least one of the conductive structures **174** is substantially heterogeneous.

(101) At least one vertically (e.g., in the Z-direction) lower conductive structure **174** of the stack structure **175** may be employed as at least one lower select gate (e.g., at least one source side select gate (SGS)) of the microelectronic device structure **100**. In some embodiments, a single (e.g., only one) conductive structure **174** of a vertically lowermost tier **176** of the stack structure **175** is employed as a lower select gate (e.g., a SGS) of the microelectronic device structure **100**. In addition, vertically (e.g., in the Z-direction) upper conductive structure(s) **174** of the stack structure **175** may be employed as upper select gate(s) (e.g., drain side select gate(s) (SGDs)) of the microelectronic device structure **100**. In some embodiments, horizontally neighboring conductive structures **174** of a vertically uppermost tier **176** of the stack structure **175** (e.g., separated from each other by slots) are employed as upper select gates (e.g., SGDs) of the microelectronic device structure **100**. In some embodiments, more than one (e.g., two, four, five, six) conductive structures **174** are employed as upper select gates (e.g., SGDs) of the microelectronic device structure **100**.

(102) In addition to serving as conductive contacts (e.g., the conductive contacts **140**), the structures **152** may also serve as support structures during and/or after the formation of one or more components of the microelectronic device structure **100**. For example, the structures **152** may serve as support structures for the formation of the conductive structures **174** during replacement of the additional insulative structures **106** (FIG. 1J) to form the conductive structures **174**. The structures **152** may impede (e.g., prevent) tier collapse during the selective removal of the additional insulative structures **106**. By forming the conductive contacts **140** of the structures **152** to extend entirely through the vertical extent of the preliminary stack structure **102** (FIG. 1J) (e.g., below the steps **122** of the staircase structure **120**), lower portions of the conductive contacts **140** may provide additional support to lowermost portions of the preliminary stack structure **102**, compared to conventional device structures having conductive contacts that terminate at steps of staircase structures. Further, formation of the structures **152**, including the conductive contacts **140** and the strapping structures **160**, prior to performing replacement gate processing acts may provide increased structural support within the staircase structure **120** of the staircase region **105**, without undesirably increasing the overall width (e.g., horizontal footprint) of the staircase region **105**.

(103) As shown in FIG. 1L, one or more side surfaces (e.g., lateral side surfaces, horizontal side surfaces) of the isolation regions **134** may directly contact side surfaces of the conductive structures **174** of the stack structure **175** along interfaces **178** (e.g., vertical interfaces). The presence of the liner material **136** provides the isolation regions **134** between the conductive contacts **140** and the conductive structures **174**, such that the conductive structures **174** are remote (e.g., isolated) from the conductive contacts **140** by the isolation regions **134**. After forming the conductive material **180** of the conductive structures **174** of the stack structure **175**, the slots **162** (FIG. 1K) may be filled with the dielectric material **166** (FIG. 1K).

(104) The dielectric material **166** may be formed of and include at least one insulative material, such as one or more of at least one dielectric oxide material (e.g., one or more of SiO.sub.x, phosphosilicate glass, borosilicate glass, borophosphosilicate glass, fluorosilicate glass, AlO.sub.x, HfO.sub.x, NbO.sub.x, TiO.sub.x, ZrO.sub.x, TaO.sub.x, and MgO.sub.x), at least one dielectric nitride material (e.g., SiN.sub.y), at least one dielectric oxynitride material (e.g., SiO.sub.xN.sub.y), and at least one dielectric carboxynitride material (e.g., SiO.sub.xC.sub.zN.sub.y). A material composition of the dielectric material **166** may substantially the same as a material composition of one or more of the dielectric fill material **126** and the insulative structures **104** of the stack structure **175**, or the material composition of the dielectric material **166** may be different than the material composition of the dielectric fill material **126** and the insulative structures **104**. In some embodiments, the dielectric material **166** is formed of and includes SiO.sub.2.

(105) The strapping structures **160** may be considered portions (e.g., vertically projecting structures, horizontally projecting structures) of the structures **152**. For example, as shown in FIG. 1L, the conductive contacts **140** of the structures **152** may individually include the fill material **144**

in electrical communication with the source tier **110**, such as with the second conductive material **114** thereof, without being in electrical communication with all of the conductive structures **174** of the stack structure **175** vertically underlying (e.g., in the Z-direction) individual steps **122** of the staircase structure **120**. In addition, the structures **152** may also individually include the conductive material **154** external to the conductive contacts **140**, corresponding to one of the strapping structures **160**, in electrical communication with the fill material **144** of the conductive contacts **140** and with the conductive material **180** of one of the conductive structures **174**. For example, an uppermost one of the conductive structures **174** defining each step **122** (e.g., an uppermost conductive structure **174a**) may be configured as a contact region for the strapping structures **160** of each of the structures **152**. At least some (e.g., each) of the conductive contacts **140** are operably coupled to one of the conductive structures **174** of the stack structure **175** at one of the steps **122** of the staircase structure **120** through the strapping structures **160**.

(106) Accordingly, an individual strapping structure **160**, in combination with the conductive contacts **140**, of the structures **152** may be configured to facilitate electrical communication between the source tier **110** and an uppermost conductive structure **174a** defining an individual step **122** of the staircase structure **120**. Stated another way, the uppermost conductive structure **174a** may be provided in electrical communication with the conductive contacts **140** (and, hence, the source tier **110**) by way of the strapping structures **160** formed to extend therebetween. Further, the strapping structure **160** of at least one of the structures **152** is vertically offset from the strapping structure **160** of at least one other of the structures **152**. Accordingly, the structures **152** may serve as conductive contacts to the conductive structures **174** of the stack structure **175**, as well as conductive contacts to the source tier **110**, while providing increased structural support within the staircase structure **120**.

(107) Forming the structures **152**, including the conductive contacts **140** and the strapping structures **160**, to facilitate electrical communication between the source tier **110** and the conductive structures **174** may reduce a quantity of the support structures **168** (FIG. **1K**) within the staircase region **105**. By forming the strapping structures **160** to extend laterally adjacent to and over the conductive contacts **140**, portions (e.g., the first portion **154a**) of the conductive material **154** of the strapping structures **160** may be electrically coupled to the fill material **144** of the conductive contacts **140** along the interfaces **158** to provide enhanced electrical connection thereto, without undesirably increasing the overall width (e.g., horizontal footprint) of the staircase region **105**.

(108) For example, facilitating electrical communication between the source tier **110** and the conductive structures **174** through the conductive contacts **140** and the strapping structures **160** may facilitate forming the structures **152** within the staircase structure **120** without the need to form complex conductive pathways above the stack structure **175**. Accordingly, a greater quantity of the steps **122** of the staircase structure **120** may be provided within a given area of the microelectronic device structure **100** as compared to conventional microelectronic device structure configurations. By providing the structures **152** (including the conductive contacts **140** and the strapping structures **160** thereof) within the staircase structure **120**, such configurations may also allow for reduced congestion in conductive pathways above the stack structure **175**, with or without formation of the support structures **168**. By reducing congestion in conductive pathways above the stack structure **175**, spacing of the conductive features may be increased, resulting in a decrease in parasitic (e.g., stray) capacitance between adjacent conductive features during use and operation of the microelectronic device structure **100**.

(109) FIG. **1M** illustrates an enlarged portion of box M of FIG. **1K**, in accordance with the embodiment of the microelectronic device structure **100** of FIG. **1K**. For clarity and ease of understanding the drawings and associated description, surrounding materials including the dielectric fill material **126** are absent from FIG. **1M**. Portions of the liner material **142** and the fill material **144** of the conductive contacts **140** and portions of the conductive material **154** of the

structures **152** are illustrated at an elevational level of the insulative liner material **128** over each step **122** of the staircase structure **120** (FIG. **1N**). Additional portions of the conductive material **154** may laterally (e.g., in the X-direction, in the Y-direction) surround the liner material **142** at an elevational level of the uppermost conductive structure **174a** (FIG. **1N**). Accordingly, the conductive material **154** (also described herein as the strapping structures **160**) of an individual structure **152** may be located horizontally proximate to and may at least partially (e.g., substantially) surround the materials (e.g., the liner material **142**, the fill material **144**) of the conductive contact **140** thereof. The insulative liner material **128** may be located horizontally proximate to and may at least partially (e.g., substantially) surround the materials of the structures **152**.

(110) As shown in FIG. **1M**, each of the conductive contacts **140** and the strapping structures **160** of the structures **152** may be horizontally centered within individual steps **122** of the staircase structure **120** (FIG. **1N**), although other configurations may be contemplated. A lateral dimension (e.g., a second width $W_{sub.2}$ in the X-direction) of one or more of the steps **122** may be relatively larger than a lateral dimension (e.g., a first width $W_{sub.1}$, a diameter in the X-direction) of an individual structure **152** (including the conductive contacts **140** and the strapping structures **160** thereof). By way of non-limiting example, the first width $W_{sub.1}$ may be within a range of from about 300 nm to about 1000 nm (e.g., 1 μm), such as from about 300 nm to about 400 nm, from about 400 nm to about 500 nm, from about 500 nm to about 600 nm, from about 600 nm to about 700 nm, from about 700 nm to about 800 nm, from about 800 nm to about 900 nm, or from about 900 nm to about 1000 nm. However, the disclosure is not so limited and the first width $W_{sub.1}$ may be different than those described above. In some embodiments, the second width $W_{sub.2}$ is within a range from about 1.5 times greater than the first width $W_{sub.1}$ of the structure **152** to about 2.5 times the first width $W_{sub.1}$ of the structure **152** at a lateral boundary of the structure **152** at an elevational level of the insulative liner material **128**. In some embodiments, the second width $W_{sub.2}$ is at least about 2.0 times the first width $W_{sub.1}$. In some embodiments, the second width $W_{sub.2}$ is about the same size as the first width $W_{sub.1}$. In other embodiments, the second width $W_{sub.2}$ is such that the lateral boundary of the structures **152** at an elevational level of the insulative liner material **128** overlying the staircase structure **120** does not laterally extend beyond the steps **122** to reduce or prevent electrical shorting of the structures **152** to additional conductive structures **174** of the stack structure **175**. Stated another way, the second width $W_{sub.2}$ may be sized such that the structures **152** do not laterally extend beyond the lateral boundary of the steps **122**.

(111) FIG. **1N** illustrates an enlarged portion of box N of FIG. **1L**, in accordance with the embodiment of the microelectronic device structure **100** of FIG. **1L**. In some embodiments, remaining portions of the upper portions **128a** of the insulative liner material **128** are maintained (e.g., remain) vertically over each step **122** of the staircase structure **120**. In other embodiments, the staircase structure **120** lacks the insulative liner material **128** thereover, and the dielectric fill material **126** is directly vertically adjacent to the uppermost conductive structure **174a**. The remaining portions of the upper portions **128a** of the insulative liner material **128**, if present, may laterally (e.g., in the X-direction, in the Y-direction) surround a first portion **160a** (e.g., an upper portion) of the strapping structures **160**, and the uppermost conductive structure **174a** of the individual steps **122** may laterally surround a second portion **160b** (e.g., a lower portion) of the strapping structures **160**.

(112) The first portion **160a** of the strapping structures **160** may laterally surround a first portion **142a** (e.g., an upper portion) of the liner material **142** of the conductive contacts **140** at an elevational level of the dielectric fill material **126** and the insulative liner material **128** over each step **122** of the staircase structure **120**. The second portion **160b** of the strapping structures **160** may laterally surround a second portion **142b** (e.g., a lower portion) of the liner material **142** at an elevational level of the uppermost conductive structure **174a** of the individual steps **122**.

Accordingly, the second portion **160b** of the strapping structures **160** (also described herein as the third portion **154c** of the conductive material **154**) of an individual structure **152** may be located below a lowermost boundary of the first portion **160a** of the strapping structures **160** (also described herein as the second portion **154b** of the conductive material **154**) thereof. The third portion **154c** of the conductive material **154** laterally intervenes between the uppermost conductive structure **174a** and the liner material **142** of the conductive contacts **140**. The first portion **160a** and the second portion **160b** of the strapping structures **160** may include substantially the same material composition with no easily discernable physical interface therebetween.

(113) In some embodiments, only a lower surface of each of the strapping structures **160** is in physical contact with any of the conductive structures **174** of the stack structure **175**. In other embodiments, the lower surfaces of at least some (e.g., each) of the strapping structures **160** are in physical contact with the uppermost conductive structure **174a** along horizontal interfaces **184**, and side surfaces of the strapping structures **160** are in physical contact with the uppermost conductive structure **174a** along vertical interfaces **186**, as shown in FIG. 1N. Accordingly, portions of the strapping structures **160** (e.g., the second portion **160b** thereof) may be laterally adjacent to the uppermost conductive structure **174a** located vertically adjacent (e.g., between) the insulative liner material **128** overlying the steps **122** of the staircase structure **120** and the uppermost insulative structure **104a** (FIG. 1L) of the stack structure **175** (FIG. 1L) in the vertical direction (e.g., the Z-direction). Additional portions of the strapping structures **160** (e.g., the first portion **160a** thereof) may also be vertically adjacent to the uppermost conductive structure **174a**. Stated another way, the first portion **160a** and the second portion **160b** of the strapping structures **160** may form an “L-shaped” structure of the strapping structures **160** proximate the upper surfaces and the side surfaces of the uppermost conductive structure **174a** of the individual steps **122**. Therefore, the strapping structures **160** physically contact the uppermost conductive structure **174a** on at least two consecutive sides (e.g., a lateral side and a vertical side). Thus, multidimensional (e.g., two-dimensional) contact regions of the uppermost conductive structure **174a** may be formed adjacent to two corresponding consecutive sides of the strapping structures **160**. Forming the multidimensional contact regions of the uppermost conductive structure **174a** further enhances (e.g., further increases) an available area having more than one side (e.g., two sides) in which to form the strapping structures **160**.

(114) Accordingly, the shape of the structures **152** including the conductive contacts **140** substantially surrounded by the strapping structures **160** may facilitate a greater margin for electrical connection to the uppermost conductive structure **174a** of the individual steps **122** of the staircase structure **120** compared to conventional microelectronic device structures. Further, the shape of the structures **152**, including the strapping structures **160** laterally adjacent and external to the conductive contacts **140**, may simplify manufacturing processes by avoiding material removal processes within the conductive contacts **140** and may provide increased process margins, which, in turn, may facilitate a reduction in capacitive coupling of the conductive contacts **140** compared to conventional microelectronic device structures.

(115) As shown in FIG. 1N, a conductive liner material **182** may be formed within the spaces between the vertically neighboring insulative structures **104**. In some such embodiments, the conductive structures **174** individually comprise the conductive liner material **182** in contact with the insulative structures **104** and the conductive material **180** in contact with the conductive liner material **182**. The conductive liner material **182** may be vertically interposed between the conductive material **180** and an insulative structure **104**. For ease of illustration and understanding, the conductive liner material **182** is illustrated within a single space between the vertically neighboring insulative structures **104** in FIG. 1N, but it will be understood that the microelectronic device structure **100** may include the conductive liner material **182** within additional (e.g., each of the) spaces between the vertically neighboring insulative structures **104**. The conductive structures **174** may be located at locations corresponding to the locations of the additional insulative

structures **106** (FIG. 1J) removed through the slots **162** (FIG. 1K).

(116) The conductive liner material **182** (if formed) surrounding the conductive structures **174** may be formed of and include, for example, at least one seed material from which the conductive material **180** may be formed. The conductive liner material **182** may be formed of and include, for example, one or more of at least one (e.g., titanium, tantalum), at least one metal nitride (e.g., tungsten nitride, titanium nitride, tantalum nitride), or at least one additional material. In some embodiments, the conductive liner material **182** comprises titanium nitride (TiN.sub.x).

(117) In some such embodiments, at least portions of the conductive liner material **182** proximate one or more of the conductive structures **174** (e.g., the uppermost conductive structure **174a**) adjacent to the strapping structures **160** of the structures **152** may be absent (e.g., removed). Accordingly, the conductive material **180** of the uppermost conductive structure **174a** may be formed directly neighboring (e.g., in the Y-direction, in the Z-direction) the strapping structures **160**. Alternatively, at least one material (e.g., the conductive liner material **182**) may vertically intervene between the conductive material **180** of the uppermost conductive structure **174a** and the strapping structures **160**. In either instance, the strapping structures **160** may be formed directly neighboring the uppermost conductive structure **174a**.

(118) Since each of the conductive contacts **140** vertically extend completely through the stack structure **175** (FIG. 1L), the conductive contacts **140** vertically extends through the steps **122** of the staircase structure **120** without terminating at upper surfaces thereof. As shown in FIG. 1N, the liner material **136** within the isolation regions **134** horizontally intervenes between the conductive contacts **140** and the additional conductive structures **174** aligned below the uppermost conductive structure **174a**, such that the additional conductive structures **174** are remote (e.g., isolated) from the conductive contacts **140** by the isolation regions **134**. For example, the conductive contacts **140** may extend through each of the dielectric fill material **126** and the steps **122** of the staircase structure **120**, without contacting the additional conductive structures **174** thereunder. Each step **122** may individually be in contact with one of the conductive contacts **140** through the conductive material **154** (also described as one of the strapping structures **160**) of the structures **152**. As described above, the first portion **160a** and the second portion **160b** of the strapping structures **160** may be configured (e.g., sized and shaped) to maximize (e.g., increase) overlap with a contact region of the uppermost conductive structure **174a** of the individual steps **122**.

(119) A lateral dimension (e.g., a third width $W_{sub.3}$, a diameter in the Y-direction) of the first portion **142a** (e.g., the upper portion) of the liner material **142** may be relatively less than a lateral dimension (e.g., a fourth width $W_{sub.4}$, a diameter in the Y-direction) of the second portion **142b** (e.g., the lower portion) of the liner material **142**. In some embodiments, the third width $W_{sub.3}$ of the first portion **142a** of the liner material **142** may be within a range of from about 100 nm to about 300 nm, such as from about 100 nm to about 150 nm, from about 150 nm to about 200 nm, from about 200 nm to about 250 nm, or from about 250 nm to about 300 nm, and the fourth width $W_{sub.4}$ of the second portion **142b** of the liner material **142** may be within a range of from about 150 nm to about 500 nm, such as from about 150 nm to about 200 nm, from about 200 nm to about 300 nm, from about 300 nm to about 400 nm, or from about 400 nm to about 500 nm. In additional embodiments, the third width $W_{sub.3}$ of the first portion **142a** of the liner material **142** is substantially the same as (e.g., substantially equal to) the fourth width $W_{sub.4}$ of the second portion **142b** thereof, such as when the first portion **142a** of the liner material **142** is not recessed.

(120) As shown in FIG. 1N, the uppermost conductive structure **174a** may be separated from the liner material **142** of the conductive contacts **140**, by the strapping structures **160** (e.g., the second portion **160b** thereof), by a distance $D_{sub.1}$ in the Y-direction. The additional conductive structures **174** underlying the uppermost conductive structure **174a** may be separated from the liner material **142** of the conductive contacts **140**, by the isolation regions **134**, by the distance $D_{sub.1}$. By way of non-limiting example, the distance $D_{sub.1}$ may be within a range of from about 20 nm to about 100 nm, such as from about 20 nm to about 40 nm, from about 40 nm to about 60 nm, from about

60 nm to about 80 nm, or from about 80 nm to about 100 nm. In some embodiments, the distance D.sub.1 is about 80 nm, which corresponds to a horizontal width of the third portion **154c** in the vertical openings **150** (FIG. **1I**) in the Y-direction and to a horizontal width of the liner material **136** within the isolation regions **134** in the Y-direction. However, the disclosure is not so limited and the distance D.sub.1 may be different than those described above. Further, the horizontal width of the liner material **136** may vary along a vertical height of each of the conductive structures **174**.

(121) Further, a lateral dimension (e.g., a fifth width W.sub.5, a diameter in the Y-direction) of the second portion **160b** of the strapping structures **160** may be relatively less than a lateral dimension (e.g., the first width W.sub.1 (FIG. **1M**) of the structures **152**, corresponding to the first portion **160a** of the strapping structures **160**). Thus, the first width W.sub.1 of the structures **152** is relatively greater than the fifth width W.sub.5 of the second portion **160b** of the strapping structures **160**, which corresponds to a lateral dimension of the isolation regions **134**. In some embodiments, the fifth width W.sub.5 of the second portion **160b** of the strapping structures **160** may be within a range of from about 150 nm to about 500 nm, such as from about 150 nm to about 200 nm, from about 200 nm to about 300 nm, from about 300 nm to about 400 nm, or from about 400 nm to about 500 nm. However, the disclosure is not so limited and the fifth width W.sub.5 may be different than those described above.

(122) In some embodiments, the first width W.sub.1 is within a range from about 1.5 times greater than the fifth width W.sub.5 of the second portion **160b** of the strapping structures **160** to about 2.5 times the fifth width W.sub.5 at a lateral boundary of the strapping structures **160** at an elevational level of the uppermost conductive structure **174a**. In some embodiments, the first width W.sub.1 is at least about 2.0 times the fifth width W.sub.5. The relative widths of the first portion **160a** and the second portion **160b** of the strapping structures **160** may be tailored to have a desired value that may be selected at least partially based on design requirements of the microelectronic device structure **100**. Specifically, the shape of the structures **152** may facilitate an increased contact region with the uppermost conductive structure **174a** of the individual steps **122** compared to conventional microelectronic device structures. For example, the size, shape, and orientation of the strapping structures **160** may facilitate an increased surface area available for contact with the uppermost conductive structure **174a**. As a result, the RC (product of resistance and capacitance) of the structures **152** including the conductive contacts **140** and the strapping structures **160** may be optimized, which may correlate to an increase in the performance of a device containing the microelectronic device structure **100** by allowing for a reduction in operational speed (e.g., programming time).

(123) One of ordinary skill in the art will appreciate that, in accordance with additional embodiments of the disclosure, the features and feature configurations described above in relation to FIGS. **1A** through **1N** may be adapted to design needs of different microelectronic devices (e.g., different memory devices) depending on desired electrical performance properties of the microelectronic devices. By way of non-limiting example, in accordance with additional embodiments of the disclosure, FIGS. **2A** through **2F** are simplified, partial top-down views (FIG. **2A**) and simplified, partial cross-sectional views (FIGS. **2B** through **2F**) of a method of forming a microelectronic device structure having a different configuration than the microelectronic device structure **100**. Throughout the remaining description and the accompanying figures, functionally similar features (e.g., structures, devices) are referred to with similar reference numerals. To avoid repetition, not all features shown in the remaining figures (including FIGS. **2A** through **2F**) are described in detail herein. Rather, unless described otherwise below, a feature designated by a reference numeral of a previously described feature (whether the previously described feature is first described before the present paragraph, or is first described after the present paragraph) will be understood to be substantially similar to the previously described feature.

(124) FIG. **2A** is a simplified, partial top-down view of a microelectronic device structure **100'** (e.g., a memory device, such as a 3D NAND Flash memory device). At the processing stage

depicted in FIG. 2A, the microelectronic device structure **100'** may be substantially similar to the microelectronic device structure **100** at the processing stage depicted in FIG. 1F. FIG. 2B is simplified cross-sectional views of the microelectronic device structure **100'** about the line B-B of FIG. 2A. For clarity and ease of understanding of the drawings and related description, not all features depicted in one of FIGS. 2A and 2B are depicted in the other of FIGS. 2A and 2B.

(125) The microelectronic device structure **100'** illustrated in FIGS. 2A and 2B includes the preliminary stack structure **102**, and the conductive contacts **140** including the liner material **142** and the fill material **144** vertically extending through the dielectric fill material **126** and the preliminary stack structure **102**. The preliminary stack structure **102** of the microelectronic device structure **100'** may also be formed to include the vertically alternating (e.g., in the Z-direction) sequence of the insulative structures **104** and the additional insulative structures **106** arranged in the tiers **108**. The preliminary stack structure **102** may be formed to vertically overlie the source tier **110** including the first conductive material **112** and the second conductive material **114**. The microelectronic device structure **100'** may include the staircase structure **120** including the steps **122**, the dielectric fill material **126** overlying the staircase structure **120** and, optionally, the insulative liner material **128** vertically overlying (e.g., in the Z-direction) the staircase structure **120**. The dielectric material **116** (FIGS. 1A and 1B) may, optionally, be formed to vertically overlie the preliminary stack structure **102**.

(126) Referring to collectively to FIGS. 2A and 2B, the microelectronic device structure **100'** may be formed to include the isolation regions **134** including the liner material **136** laterally adjacent to the liner material **142** of the conductive contacts **140** and directly contacting the side surfaces of the remaining portions of the additional insulative structures **106** along the interfaces **138**.

(127) The additional insulative structures **106** may be separated from the liner material **142** of the conductive contacts **140**, by the isolation regions **134**, as in processing stage of the embodiment of the disclosure previously described with reference to FIG. 1E. However, as shown in FIG. 2B, configurations of the isolation regions **134** may be modified relative to the configurations thereof previously described with reference to FIG. 1E to spatially accommodate subsequently formed features (e.g., the strapping structures **160**), as described in further detail below. By way of non-limiting example, a lateral dimension (e.g., horizontal width in the Y-direction) of the isolation regions **134** may be within a range of from about 40 nm to about 200 nm, such as from about 40 nm to about 80 nm, from about 80 nm to about 120 nm, from about 120 nm to about 160 nm, or from about 160 nm to about 200 nm. In some embodiments, the lateral dimension of the isolation regions **134** is about 160 nm, which lateral dimension is relatively larger than that of the previous embodiment.

(128) The microelectronic device structure **100'** may also be formed to include the sacrificial material **132** adjacent to (e.g., laterally adjacent to) the dielectric fill material **126** and adjacent to (e.g., vertically adjacent to) the steps **122** of the staircase structure **120**. At the processing stage of FIGS. 2A and 2B, the microelectronic device structure **100'** may be formed to include the liner material **142** of the conductive contacts **140** laterally adjacent to and substantially surrounded by the sacrificial material **132** and the fill material **144** thereof laterally adjacent to and substantially surrounded by the liner material **142**, as in processing stage of the embodiment of the disclosure previously described with reference to FIG. 1C. However, as collectively shown in FIGS. 2A and 2B, configurations of the sacrificial material **132** may be modified relative to the configurations thereof previously described with reference to FIG. 1C to spatially accommodate the subsequently formed features. By way of non-limiting example, the sacrificial material **132** may have a thickness within a range of from about 50 nm to about 200 nm, such as from about 50 nm to about 75 nm, from about 75 nm to about 125 nm, or from about 125 nm to about 150 nm, or from about 150 nm to about 200 nm. However, the disclosure is not so limited and the thickness of the sacrificial material **132** may be different than those described above. Accordingly, the thickness of the sacrificial material **132** of the embodiment of FIGS. 2A and 2B may be relatively larger than that of

the previous embodiment. In addition, the width of the openings **130** (FIG. 1B) of the embodiment of FIGS. 2A and 2B may be relatively larger than that of the previous embodiment.

(129) Further, the sacrificial material **132** of the microelectronic device structure **100'** may exhibit a greater lateral extent (e.g., a width in the Y-direction) than a lateral extent of the isolation regions **134**, as shown in FIG. 2B. In other words, the remaining portions of the additional insulative structures **106** may be adjacent to (e.g., underlying) the sacrificial material **132**. In additional embodiments, side surfaces of the sacrificial material **132** are substantially aligned with side surfaces of the isolation regions **134** or, alternatively, the isolation regions **134** may exhibit a slightly greater lateral extent than a lateral extent of the sacrificial material **132**.

(130) In addition, configurations of the liner material **142** of the conductive contacts **140** may be modified relative to the configurations thereof previously described with reference to FIGS. 1F and 1G to further spatially accommodate the subsequently formed features. By way of non-limiting example, the liner material **142** may have a thickness within a range of from about 5 nm to about 30 nm, such as from about 5 nm to about 10 nm, from about 10 nm to about 20 nm, from about 20 nm to about 25 nm, or from about 25 nm to about 30 nm. In some embodiments, the thickness of the liner material **142** is about 20 nm. However, the disclosure is not so limited and the thickness of the liner material **142** may be different than those described above. Accordingly, the thickness of the liner material **142** of the conductive contacts **140** of the embodiment of FIGS. 2A and 2B may be relatively less than the thickness of the liner material **142** of the embodiment of FIGS. 1F and 1G. Further, the liner material **142** of the embodiment of FIGS. 2A and 2B may exhibit a thickness that is substantially uniform (e.g., substantially constant, non-variable) along a vertical extent thereof.

(131) Referring to FIG. 2C, following formation of the conductive contacts **140**, the sacrificial material **132** (FIG. 2B) may be removed (e.g., exhumed) to form the second openings **146** (see FIG. 1H) vertically extending (e.g., in the Z-direction) through the dielectric fill material **126**, as in the previous embodiment of FIG. 1H. However, since the thickness of the sacrificial material **132** of the embodiment of FIGS. 2A and 2B is relatively larger than the thickness of the sacrificial material **132** of the previous embodiment, a lateral dimension (e.g., a horizontal width in the Y-direction) of the second openings **146** of the microelectronic device structure **100'** will be relatively larger than that of the second openings **146** of FIG. 1H.

(132) As shown in FIG. 2C, the expanded openings **147** may be formed to vertically extend (e.g., in the Z-direction) through the dielectric fill material **126** to expand (e.g., increase) the horizontal dimensions of the second openings **146** (FIG. 1H). In addition, portions of the liner material **136** of the isolation regions **134** of the uppermost additional insulative structure **106a** may be removed (e.g., exhumed) to form the vertical openings **150** in communication with the expanded openings **147** and to expose upper surfaces of the uppermost insulative structure **104a**.

(133) In addition, portions of the liner material **142** of the conductive contacts **140** may be selectively removed. For example, the upper portions of the liner material **142** of the conductive contacts **140** of the microelectronic device structure **100'** may be substantially removed (e.g., substantially exhumed) above an elevational level of the uppermost additional insulative structure **106a** of the individual steps **122** of the staircase structure **120**. Thus, side surfaces (e.g., lateral side surfaces) of the fill material **144** of the conductive contacts **140** may be exposed in regions laterally adjacent to the dielectric fill material **126** and the insulative liner material **128** at the processing stage of FIG. 2C. In other words, microelectronic device structure **100'** is substantially devoid (e.g., substantially free) of the liner material **142** of the conductive contacts **140** laterally adjacent to the dielectric fill material **126** and the insulative liner material **128**, which configuration differs from that of the previous embodiment, as shown in FIG. 1I. Accordingly, a lateral dimension (e.g., a width) of the expanded openings **147** of the microelectronic device structure **100'** may be relatively larger than that of the expanded openings **147** of the embodiment of FIG. 1I.

(134) Referring to FIG. 2D, following formation of the expanded openings **147** (FIG. 2C) and the

vertical openings **150** (FIG. 2C), the conductive material **154** may be formed within each of the expanded openings **147** and the vertical openings **150** to form the structures **152** adjacent to (e.g., directly laterally adjacent to) the liner material **142** and the fill material **144** of the conductive contacts **140**. The structures **152** are defined by the conductive material **154** (also described herein as the strapping structures **160**) and the materials (e.g., the liner material **142**, the fill material **144**) of the conductive contacts **140**. Lower surfaces of the conductive material **154** may directly contact upper surfaces of the lower portions of the liner material **142** along the interfaces **156** (e.g., horizontal interfaces), and side surfaces (e.g., lateral side surfaces) of an upper portion of the conductive material **154** of the structures **152** may be in direct physical contact with side surfaces of the fill material **144** along the interfaces **158** (e.g., vertical interfaces).

(135) The conductive material **154** may be directly adjacent to and operably coupled (e.g., electrically connected) with the fill material **144**. In some embodiments, the conductive material **154** of the structures **152** is integral and continuous with the fill material **144** of the conductive contacts **140** with no easily discernable physical interface therebetween at an elevational level above the liner material **142**. The fill material **144** may physically contact the strapping structures **160** along a vertical extent of upper portions of the conductive contacts **140** laterally adjacent to the dielectric fill material **126**. Further, the conductive material **154** may be formed over exposed portions of the uppermost insulative structure **104a** and may fill (e.g., substantially fill) the vertical openings **150** (FIG. 2C). Accordingly, the conductive material **154** of individual structures **152** includes the second portion **154b** within the expanded openings **147** and the third portion **154c** within the vertical openings **150**. Therefore, the conductive material **154** is laterally adjacent to the liner material **142** of the conductive contacts **140** only within the vertical openings **150**, which configuration differs from the conductive material **154** laterally intervening between the dielectric fill material **126** and the upper portions of the liner material **142** of the microelectronic device structure **100**, as shown in FIG. 1J.

(136) Referring next to FIG. 2E, the additional insulative structures **106** (FIG. 2D) may be selectively removed (e.g., exhumed) through the slots **162** (see FIG. 1K). Spaces between vertically neighboring (e.g., in the Z-direction) insulative structures **104** may be filled with the conductive material **180** (FIG. 2F) to form the conductive structures **174** and the stack structure **175** including the tiers **176** of the insulative structures **104** and the conductive structures **174**. In addition to serving as conductive contacts (e.g., the conductive contacts **140**), the structures **152** may also serve as support structures during and/or after the formation of one or more components of the microelectronic device structure **100'**.

(137) As shown in FIG. 2E, one or more side surfaces (e.g., lateral side surfaces) of the isolation regions **134** may directly contact side surfaces of the conductive structures **174** of the stack structure **175** along the interfaces **178** (e.g., vertical interfaces), such that the conductive structures **174** are remote (e.g., isolated) from the conductive contacts **140** by the isolation regions **134**. The relatively larger lateral dimension of the isolation regions **134** of the microelectronic device structure **100'** may facilitate a corresponding increase in a lateral dimension of the third portion **154c** laterally adjacent to the uppermost conductive structure **174a** of the individual steps **122**. The relatively larger lateral dimension of the third portion **154c** of the conductive material **154**, as a result of the relatively larger lateral dimension of the isolation regions **134**, may facilitate an increased contact region between the strapping structures **160** and the uppermost conductive structure **174a** of the individual steps **122**, without undesirably increasing the overall width (e.g., horizontal footprint) of the staircase region **105** of the microelectronic device structure **100'**. After forming the conductive material **180** of the conductive structures **174** of the stack structure **175**, the slots **162** (FIG. 1K) may be filled with the dielectric material **166** (FIG. 1K).

(138) FIG. 2F illustrates an enlarged portion of box F of FIG. 2E, in accordance with the embodiment of the microelectronic device structure **100'** of FIG. 2E. The remaining portions of the upper portions **128a** of the insulative liner material **128**, if present, may laterally (e.g., in the X-

direction, in the Y-direction) surround the first portion **160a** (e.g., the upper portion) of the strapping structures **160**, and the uppermost conductive structure **174a** may laterally surround the second portion **160b** (e.g., the lower portion) of the strapping structures **160**.

(139) The configuration of the strapping structures **160** of the structures **152** of the microelectronic device structure **100'** of FIG. 2F differs from the configuration of FIG. 1N. For example, the first portion **160a** of the strapping structures **160** may laterally surround the fill material **144** of the conductive contacts **140**, without laterally surrounding an upper portion of the liner material **142** thereof at an elevational level of the dielectric fill material **126** and the insulative liner material **128** over each step **122** of the staircase structure **120**. As shown in FIG. 2F, the second portion **160b** of the strapping structures **160** may laterally surround a remaining portion of the liner material **142** at an elevational level of the uppermost conductive structure **174a** of the individual steps **122**.

Accordingly, the second portion **160b** of the strapping structures **160** (also described herein as the third portion **154c** of the conductive material **154**) of an individual structure **152** may be located below a lowermost boundary of the first portion **160a** of the strapping structures **160** (also described herein as the second portion **154b** of the conductive material **154**) thereof.

(140) The conductive liner material **182** may or may not be present adjacent to the uppermost conductive structure **174a**. Accordingly, the conductive material **180** of the uppermost conductive structure **174a** of individual steps **122** may be formed directly neighboring (e.g., in the Y-direction, in the Z-direction) the strapping structures **160**. Alternatively, at least one material (e.g., the conductive liner material **182**) may vertically intervene between the conductive material **180** of the uppermost conductive structure **174a** and the strapping structures **160**.

(141) As shown in FIG. 2F, lower surfaces of at least some (e.g., each) of the strapping structures **160** may be in physical contact with the uppermost conductive structure **174a** along the horizontal interfaces **184**, and side surfaces of the strapping structures **160** may be in physical contact with the uppermost conductive structure **174a** along the vertical interfaces **186**. Accordingly, portions of the strapping structures **160** (e.g., the second portion **160b** thereof) may be laterally adjacent to the uppermost conductive structure **174a**, and additional portions of the strapping structures **160** (e.g., the first portion **160a** thereof) may be vertically adjacent to the uppermost conductive structure **174a**. The first portion **160a** and the second portion **160b** of the strapping structures **160** may form the “L-shaped” structure of the strapping structures **160** proximate the upper surfaces and the side surfaces of the uppermost conductive structure **174a** of the individual steps **122**, such that the strapping structures **160** of the microelectronic device structure **100'** physically contact the uppermost conductive structure **174a** on at least two consecutive sides.

(142) The first portion **160a** and the second portion **160b** of the strapping structures **160** of the microelectronic device structure **100'** may be configured (e.g., sized and shaped) to maximize (e.g., increase) overlap with the contact region of the uppermost conductive structure **174a** of the individual steps **122**. For example, a lateral dimension (e.g., the fourth width $W_{sub.4}$, a diameter in the Y-direction) of the second portion **142b** (e.g., the lower portion) of the liner material **142** of the microelectronic device structure **100'** of the embodiment of FIG. 2F may be relatively less than that of the embodiment of FIG. 1N, as a result of the thickness of the liner material **142** of the conductive contacts **140** being relatively less than that of the previous embodiment. In some embodiments, the fourth width $W_{sub.4}$ of the second portion **142b** of the liner material **142** may be within a range of from about 100 nm to about 400 nm, such as from about 100 nm to about 200 nm, from about 200 nm to about 300 nm, or from about 300 nm to about 400 nm. However, the disclosure is not so limited and the fourth width $W_{sub.4}$ may be different than those described above. A decrease in the fourth width $W_{sub.4}$ may facilitate an increased lateral dimension of the third portion **154c** of the conductive material **154** laterally adjacent to the liner material **142**.

(143) As shown in FIG. 2F, the uppermost conductive structure **174a** may be separated from the liner material **142** of the conductive contacts **140**, by the strapping structures **160** (e.g., the second portion **160b** thereof), by the distance $D_{sub.1}$ in the Y-direction. Since the lateral dimension of the

liner material **136** within the isolation regions **134** of the embodiment of FIG. 2B of the microelectronic device structure **100'** is relatively larger than that of the previous embodiment, the distance D.sub.1 of the embodiment of FIG. 2F is relatively larger than that of the embodiment of FIG. 1N. By way of non-limiting example, the distance D.sub.1 may be within a range of from about 40 nm to about 200 nm, such as from about 40 nm to about 80 nm, from about 80 nm to about 120 nm, from about 120 nm to about 160 nm, or from about 160 nm to about 200 nm. In some embodiments, the distance D.sub.1 is about 160 nm. However, the disclosure is not so limited and the distance D.sub.1 may be different than those described above.

(144) In some embodiments, a lateral dimension (e.g., the fifth width W.sub.5) of the second portion **160b** of the strapping structures **160** of the microelectronic device structure **100'** of the embodiment of FIG. 2F may be relatively larger than that of the embodiment of FIG. 1N, as a result of the distance D.sub.1 being relatively larger than that of the previous embodiment. In some embodiments, the fifth width W.sub.5 of the second portion **160b** of the strapping structures **160** may be within a range of from about 200 nm to about 550 nm, such as from about 200 nm to about 250 nm, from about 250 nm to about 350 nm, from about 350 nm to about 450 nm, or from about 450 nm to about 550 nm. However, the disclosure is not so limited and the fifth width W.sub.5 may be different than those described above. In other embodiments, the fifth width W.sub.5 may be relatively less than or, alternatively, substantially the same as (e.g., substantially equal to) that of the embodiment of FIG. 1N.

(145) The shape of the structures **152** of the microelectronic device structure **100'** may further enhance (e.g., further increase) the contact region with the uppermost conductive structure **174a** of the individual steps **122** by varying the size, shape, and orientation of the strapping structures **160** to further increase the surface area available for contact with the uppermost conductive structure **174a**. As a result, the RC (product of resistance and capacitance) of the structures **152** including the conductive contacts **140** and the strapping structures **160** may be optimized, which may correlate to a further increase in the performance of a device containing the microelectronic device structure **100'**.

(146) FIG. 3 illustrates a simplified, partial cutaway perspective view of a portion of a microelectronic device **201** (e.g., a memory device, such as a dual deck 3D NAND Flash memory device) including a microelectronic device structure **200**. The microelectronic device structure **200** may be substantially similar to the microelectronic device structures **100**, **100'** following the processing stage previously described with reference to FIGS. 1K and 1L, and FIG. 2E. As shown in FIG. 3, the microelectronic device structure **200** may include a staircase structure **220** (e.g., including the staircase structure **120** (FIGS. 1L and 2E)) defining contact regions for connecting conductive contacts **206** (e.g., corresponding to the conductive contacts **140** (FIGS. 1L and 2E)) directly to conductive tiers **205** (e.g., conductive layers, conductive plates, such as the conductive structures **174** (FIGS. 1L and 2E)). The microelectronic device structure **200** may include vertically extending strings **207** of memory cells **203** that are coupled to each other in series. The vertically extending strings **207** may extend vertically (e.g., in the Z-direction) and orthogonally to data lines **202**, a source tier **204** (e.g., corresponding to the source tier **110** (FIGS. 1L and 2E)), the conductive tiers **205**, first select gates **208** (e.g., upper select gates, drain select gates (SGDs)), select lines **209**, and a second select gate **210** (e.g., a lower select gate, a source select gate (SGS)). The microelectronic device **201** may include multiple blocks **232** (e.g., corresponding to the block structures **164** (FIG. 1K)) horizontally separated (e.g., in the X-direction) from one another by filled slot structures **230** (e.g., corresponding to the slots **162** (FIG. 1K)) filled with the dielectric material **166** (FIG. 1K)).

(147) Conductive contacts **213** and additional conductive contacts **211** may, optionally, electrically couple components to each other as shown. For example, the select lines **209** may be electrically coupled to the first select gates **208**. The microelectronic device **201** may also include a control unit **212** positioned under and within a horizontal area of the memory array including the vertically

extending strings **207** of memory cells **203**. The control unit **212** may include control logic devices configured to control various operations of other features (e.g., the vertically extending strings **207** of memory cells **203**) of the microelectronic device **201**. By way of non-limiting example, the control unit **212** may include one or more (e.g., each) of charge pumps (e.g., V.sub.CCP charge pumps, V.sub.NEGWL charge pumps, DVC2 charge pumps), delay-locked loop (DLL) circuitry (e.g., ring oscillators), V.sub.dd regulators, drivers (e.g., string drivers), decoders (e.g., local deck decoders, column decoders, row decoders), sense amplifiers (e.g., equalization (EQ) amplifiers, isolation (ISO) amplifiers, NMOS sense amplifiers (NSAs), PMOS sense amplifiers (PSAs)), repair circuitry (e.g., column repair circuitry, row repair circuitry), I/O devices (e.g., local I/O devices), memory test devices, MUX, error checking and correction (ECC) devices, self-refresh/wear leveling devices, and other chip/deck control circuitry. The control unit **212** may be electrically coupled to the data lines **202**, the source tier **204**, the conductive contacts **206**, the first select gates **208**, and the second select gates **210**, for example. In some embodiments, the control unit **212** includes CMOS (complementary metal-oxide-semiconductor) circuitry. In such embodiments, the control unit **212** may be characterized as having a “CMOS under Array” (“CuA”) configuration, wherein the CMOS circuitry of a logic region is at least partially (e.g., substantially) positioned within horizontal areas of memory array regions of a microelectronic device including the microelectronic device structures **100**, **100'**. The conductive material **154** (FIG. 1L) of the strapping structures **160** (FIG. 1L) and the fill material **144** (FIG. 1L) of the conductive contacts **140** (FIG. 1L) may be operably coupled to logic circuitry of the control unit **212** underlying the source tier **204**, without additional conductive tiers **205** below steps of the staircase structure **220** being operably coupled to the logic circuitry of the control unit **212**.

(148) Source structures **218** (e.g., corresponding to the source structure(s) **118** (FIG. 1B)) of the source tier **204** may be electrically isolated from other portions thereof (e.g., other portions employed as conductive routing structures **217** (e.g., corresponding to the conductive routing structures **117** (FIG. 1B))). The conductive routing structures **217** may electrically couple components (e.g., the conductive contacts **206**, the source structures **218**) to circuitry of the control unit **212**.

(149) The first select gates **208** may extend horizontally in a first direction (e.g., the Y-direction) and may be coupled to respective first groups of vertically extending strings **207** of memory cells **203** at a first end (e.g., an upper end) of the vertically extending strings **207**. The second select gate **210** may be formed in a substantially planar configuration and may be coupled to the vertically extending strings **207** at a second, opposite end (e.g., a lower end) of the vertically extending strings **207** of memory cells **203**.

(150) The data lines **202** (e.g., bit lines) may extend horizontally in a second direction (e.g., in the X-direction) that is at an angle (e.g., perpendicular) to the first direction in which the first select gates **208** extend. The data lines **202** may be coupled to respective second groups of the vertically extending strings **207** at the first end (e.g., the upper end) of the vertically extending strings **207**. A first group of vertically extending strings **207** coupled to a respective first select gate **208** may share a particular vertically extending string **207** with a second group of vertically extending strings **207** coupled to a respective data line **202**. Thus, a particular vertically extending string **207** may be selected at an intersection of a particular first select gate **208** and a particular data line **202**. Accordingly, the first select gates **208** may be used for selecting memory cells **203** of the vertically extending strings **207** of memory cells **203**.

(151) The conductive tiers **205** (e.g., word line plates, such as the conductive structures **174** (FIGS. 1L and 2E)) may extend in respective horizontal planes. The conductive tiers **205** may be stacked vertically, such that each conductive tier **205** is coupled to all of the vertically extending strings **207** of memory cells **203**, and the vertically extending strings **207** of the memory cells **203** extend vertically through the stack of conductive tiers **205**. The conductive tiers **205** may be coupled to or may form control gates of the memory cells **203** to which the conductive tiers **205** are coupled.

Each conductive tier **205** may be coupled to one memory cell **203** of a particular vertically extending string **207** of memory cells **203**.

(152) The first select gates **208** and the second select gates **210** may operate to select a particular vertically extending string **207** of the memory cells **203** between a particular data line **202** and the source tier **204**. Thus, a particular memory cell **203** may be selected and electrically coupled to a data line **202** by operation of (e.g., by selecting) the appropriate first select gate **208**, second select gate **210**, and conductive tier **205** that are coupled to the particular memory cell **203**.

(153) The staircase structure **220** may be configured to provide electrical connection directly between the conductive contacts **206** and the conductive tiers **205**. In other words, a particular conductive tier **205** may be selected via a conductive contact **206** in electrical communication therewith. The data lines **202** may be electrically coupled to the vertically extending strings **207** through conductive contact structures **234**.

(154) Thus, in accordance with embodiments of the disclosure a microelectronic device comprises a stack structure overlying a source tier. The stack structure comprises a vertically alternating sequence of conductive structures and insulative structures arranged in tiers. The microelectronic device comprises a staircase structure within the stack structure and having steps comprising lateral edges of the tiers, conductive contacts within a horizontal area of the staircase structure and vertically extending through the stack structure to the source tier, and strapping structures laterally adjacent to the conductive contacts and having upper surfaces substantially coplanar with upper surfaces of the conductive contacts. Each of the strapping structures are in contact with one of the conductive contacts and with one of the conductive structures of the stack structure at one of the steps of the staircase structure.

(155) Thus, in accordance with additional embodiments of the disclosure, a memory device comprises a stack structure comprising conductive structures vertically interleaved with insulative structures, strings of memory cells vertically extending through the stack structure, a staircase structure within the stack structure and having steps defined by lateral ends of the conductive structures and the insulative structures, and conductive contact structures vertically extending through the stack structure. Each of the conductive contact structures individually comprise an inner conductive core vertically extending from an uppermost boundary of the stack structure to conductive material underlying a lowermost boundary of the stack structure, and an outer conductive shell laterally surrounding portions of the inner conductive core and in physical contact with one of the conductive structures of the stack structure at an elevational level of one of the steps of the staircase structure.

(156) Furthermore, in accordance with further embodiments of the disclosure, a method of forming a microelectronic device comprises forming a stack structure over a source tier including one or more conductive structures. The stack structure comprises tiers each including an insulative material and additional insulative material vertically neighboring the insulative material. The method comprises forming dielectric material over a staircase structure within the stack structure. The staircase structure has steps comprising lateral edges of the tiers of the stack structure. The method comprises forming openings extending through the stack structure and within a horizontal area of the staircase structure. The openings expose portions of the one or more conductive structures of the source tier. The method comprises forming conductive contacts individually comprising liner material and conductive fill material within the openings, forming conductive material laterally adjacent and in contact with portions of the conductive contacts vertically overlying the staircase structure to form strapping structures in contact with the steps of the staircase structure, and at least partially replacing the additional insulative material with additional conductive material to form additional conductive structures. The conductive contacts are coupled to the additional conductive structures by way of the strapping structures.

(157) Microelectronic devices (e.g., the microelectronic device **201**) including microelectronic device structures (e.g., the microelectronic device structures **100**, **100'**, **200**) of the disclosure may

be included in embodiments of electronic systems of the disclosure. For example, FIG. 4 is a schematic block diagram of an electronic system **303**, in accordance with embodiments of the disclosure. The electronic system **303** may comprise, for example, a computer or computer hardware component, a server or other networking hardware component, a cellular telephone, a digital camera, a personal digital assistant (PDA), portable media (e.g., music) player, a Wi-Fi or cellular-enabled tablet such as, for example, an iPad® or SURFACE® tablet, an electronic book, a navigation device, etc. The electronic system **303** includes at least one memory device **305**. The memory device **305** may include, for example, an embodiment of a microelectronic device structure previously described herein (e.g., the microelectronic device structures **100**, **100'**, **200** previously described with reference to FIGS. 1A through 2F and FIG. 3) or a microelectronic device (e.g., the microelectronic device **201**) previously described with reference to FIG. 3.

(158) The electronic system **303** may further include at least one electronic signal processor device **307** (often referred to as a “microprocessor”). The electronic signal processor device **307** may, optionally, include an embodiment of one or more of a microelectronic device and a microelectronic device structure previously described herein. The electronic system **303** may further include one or more input devices **309** for inputting information into the electronic system **303** by a user, such as, for example, a mouse or other pointing device, a keyboard, a touchpad, a button, or a control panel. The electronic system **303** may further include one or more output devices **311** for outputting information (e.g., visual or audio output) to a user such as, for example, a monitor, a display, a printer, an audio output jack, a speaker, etc. In some embodiments, the input device **309** and the output device **311** may comprise a single touchscreen device that can be used both to input information to the electronic system **303** and to output visual information to a user. The input device **309** and the output device **311** may communicate electrically with one or more of the memory device **305** and the electronic signal processor device **307**.

(159) With reference to FIG. 5, depicted is a processor-based system **400**. The processor-based system **400** may include one or more of a microelectronic device and a microelectronic device structure previously described herein and manufactured in accordance with embodiments of the disclosure. The processor-based system **400** may be any of a variety of types such as a computer, pager, cellular phone, personal organizer, control circuit, or other electronic device. The processor-based system **400** may include one or more processors **402**, such as a microprocessor, to control the processing of system functions and requests in the processor-based system **400**. The processor **402** and other subcomponents of the processor-based system **400** may include one or more of a microelectronic device and a microelectronic device structure previously described herein and manufactured in accordance with embodiments of the present disclosure.

(160) The processor-based system **400** may include a power supply **404** in operable communication with the processor **402**. For example, if the processor-based system **400** is a portable system, the power supply **404** may include one or more of a fuel cell, a power scavenging device, permanent batteries, replaceable batteries, and rechargeable batteries. The power supply **404** may also include an AC adapter; therefore, the processor-based system **400** may be plugged into a wall outlet, for example. The power supply **404** may also include a DC adapter such that the processor-based system **400** may be plugged into a vehicle cigarette lighter or a vehicle power port, for example.

(161) Various other devices may be coupled to the processor **402** depending on the functions that the processor-based system **400** performs. For example, a user interface **406** may be coupled to the processor **402**. The user interface **406** may include input devices such as buttons, switches, a keyboard, a light pen, a mouse, a digitizer and stylus, a touch screen, a voice recognition system, a microphone, or a combination thereof. A display **408** may also be coupled to the processor **402**. The display **408** may include an LCD display, an SED display, a CRT display, a DLP display, a plasma display, an OLED display, an LED display, a three-dimensional projection, an audio display, or a combination thereof. Furthermore, an RF sub-system/baseband processor **410** may also be coupled to the processor **402**. The RF sub-system/baseband processor **410** may include an

antenna that is coupled to an RF receiver and to an RF transmitter (not shown). A communication port **412**, or more than one communication port **412**, may also be coupled to the processor **402**. The communication port **412** may be adapted to be coupled to one or more peripheral devices **414**, such as a modem, a printer, a computer, a scanner, or a camera, or to a network, such as a local area network, remote area network, intranet, or the Internet, for example.

(162) The processor **402** may control the processor-based system **400** by implementing software programs stored in the memory. The software programs may include an operating system, database software, drafting software, word processing software, media editing software, or media playing software, for example. The memory is operably coupled to the processor **402** to store and facilitate execution of various programs. For example, the processor **402** may be coupled to system memory **416**, which may include one or more of spin torque transfer magnetic random-access memory (STT-MRAM), magnetic random-access memory (MRAM), dynamic random-access memory (DRAM), static random-access memory (SRAM), racetrack memory, and other known memory types. The system memory **416** may include volatile memory, non-volatile memory, or a combination thereof. The system memory **416** is typically large so that it can store dynamically loaded applications and data. In some embodiments, the system memory **416** may include semiconductor devices, such as one or more of a microelectronic devices and a microelectronic device structure previously described herein.

(163) The processor **402** may also be coupled to non-volatile memory **418**, which is not to suggest that system memory **416** is necessarily volatile. The non-volatile memory **418** may include one or more of STT-MRAM, MRAM, read-only memory (ROM) such as an EPROM, resistive read-only memory (RRAM), and flash memory to be used in conjunction with the system memory **416**. The size of the non-volatile memory **418** is typically selected to be just large enough to store any necessary operating system, application programs, and fixed data. Additionally, the non-volatile memory **418** may include a high-capacity memory such as disk drive memory, such as a hybrid-drive including resistive memory or other types of non-volatile solid-state memory, for example. The non-volatile memory **418** may include microelectronic devices, such as one or more of a microelectronic device and a microelectronic device structure previously described herein.

(164) Thus, in accordance with embodiments of the disclosure an electronic system comprises a processor operably coupled to an input device and an output device, and a memory device operably coupled to the processor. The memory device comprises a stack structure comprising dielectric materials and conductive materials vertically alternating with the dielectric materials, conductive contacts vertically extending through the stack structure from an uppermost boundary of the stack structure to conductive routing structures underlying a lowermost boundary of the stack structure, and conductive structures substantially surrounding upper portions of the conductive contacts. At least some of the conductive materials of the stack structure are in electrical communication with at least some of the conductive routing structures through the conductive contacts and the conductive structures.

(165) While certain illustrative embodiments have been described in connection with the figures, those of ordinary skill in the art will recognize and appreciate that embodiments encompassed by the disclosure are not limited to those embodiments explicitly shown and described herein. Rather, many additions, deletions, and modifications to the embodiments described herein may be made without departing from the scope of embodiments encompassed by the disclosure, such as those hereinafter claimed, including legal equivalents. In addition, features from one disclosed embodiment may be combined with features of another disclosed embodiment while still being encompassed within the scope of the disclosure.

Claims

1. A microelectronic device, comprising: a stack structure overlying a source tier, the stack structure comprising a vertically alternating sequence of conductive structures and insulative structures arranged in tiers; a staircase structure within the stack structure and having steps comprising lateral edges of the tiers; conductive contacts within a horizontal area of the staircase structure and vertically extending through the stack structure to the source tier; and strapping structures laterally adjacent to the conductive contacts and having upper surfaces substantially coplanar with upper surfaces of the conductive contacts, each of the strapping structures in contact with one of the conductive contacts and with one of the conductive structures of the stack structure at one of the steps of the staircase structure.
2. The microelectronic device of claim 1, wherein each of the strapping structures physically contact the one of the conductive structures of the stack structure on a lateral side and on a vertical side.
3. The microelectronic device of claim 1, wherein: the conductive contacts comprise conductive material at least partially laterally surrounded by a liner material; and the strapping structures are coupled to upper portions of the conductive material of the conductive contacts and are physically separated from lower portions of the conductive material of the conductive contacts by the liner material.
4. The microelectronic device of claim 1, wherein the conductive contacts vertically extend through the stack structure from an upper surface of the stack structure to conductive features within the source tier.
5. The microelectronic device of claim 1, wherein: each of the conductive contacts exhibits substantially the same vertical height; and the steps of the staircase structure are free of additional conductive contacts terminating thereon.
6. The microelectronic device of claim 1, wherein the strapping structures substantially laterally surround and physically contact upper portions of the conductive contacts above an elevational level of individual steps of the staircase structure, without being laterally adjacent and in physical contact with lower portions of the conductive contacts within the stack structure.
7. The microelectronic device of claim 1, further comprising at least one dielectric material overlying the stack structure, wherein conductive portions of the conductive contacts physically contact the strapping structures along a vertical extent of upper portions of the conductive contacts laterally adjacent to the at least one dielectric material.
8. A memory device, comprising: a stack structure comprising conductive structures vertically interleaved with insulative structures; strings of memory cells vertically extending through the stack structure; a staircase structure within the stack structure and having steps defined by lateral ends of the conductive structures and the insulative structures; and conductive contact structures vertically extending through the stack structure, each of the conductive contact structures individually comprising: an inner conductive core vertically extending from an uppermost boundary of the stack structure to conductive material underlying a lowermost boundary of the stack structure; and an outer conductive shell laterally surrounding portions of the inner conductive core and in physical contact with one of the conductive structures of the stack structure at an elevational level of one of the steps of the staircase structure.
9. The memory device of claim 8, further comprising insulative material laterally intervening between lower portions of the inner conductive core and the outer conductive shell of each of the conductive contact structures, an upper portion of the outer conductive shell overlying the insulative material and physically contacting the inner conductive core.
10. The memory device of claim 8, wherein the outer conductive shell of each of the conductive contact structures is in physical contact with the one of the conductive structures of the stack structure on at least two consecutive sides thereof.
11. The memory device of claim 8, further comprising isolation regions individually laterally

separating the inner conductive core of one of the conductive contact structures from additional conductive structures below individual steps of the stack structure, wherein a lateral dimension of the outer conductive shell of the one of the conductive contact structures is relatively greater than a lateral dimension of one of the isolation regions most proximate thereto.

12. The memory device of claim 8, further comprising an insulative liner material overlying the steps of the staircase structure, a width of the outer conductive shell of each of the conductive contact structures laterally adjacent to the insulative liner material relatively larger than an additional width of the outer conductive shell laterally adjacent to the one of the conductive structures of the stack structure.

13. An electronic system, comprising: a processor operably coupled to an input device and an output device; and a memory device operably coupled to the processor, the memory device comprising: a stack structure comprising dielectric materials and conductive materials vertically alternating with the dielectric materials; conductive contacts vertically extending through the stack structure from an uppermost boundary of the stack structure to conductive routing structures underlying a lowermost boundary of the stack structure; and conductive structures substantially surrounding upper portions of the conductive contacts, at least some of the conductive materials of the stack structure in electrical communication with at least some of the conductive routing structures through the conductive contacts and the conductive structures.
