

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent

12418050

Kind Code

B2

Date of Patent

September 16, 2025

Inventor(s)

Busacca; Robert S. et al.

Three-dimensional batteries with compressible cathodes

Abstract

A secondary battery for cycling between a charged and a discharged state is provided. The secondary battery has an electrode assembly having a population of anode structures, a population of cathode structures, and an electrically insulating microporous separator material. The electrode assembly also has a set of electrode constraints that at least partially restrains growth of the electrode assembly. Members of the anode structure population have a first cross-sectional area, A.sub.1 when the secondary battery is in the charged state and a second cross-sectional area, A.sub.2, when the secondary battery is in the discharged state, and members of the cathode structure population have a first cross-sectional area, C.sub.1 when the secondary battery is in the charged state and a second cross-sectional area, C.sub.2, when the secondary battery is in the discharged state, where A.sub.1 is greater than A.sub.2, and C.sub.1 is less than C.sub.2.

Inventors: Busacca; Robert S. (Oakland, CA), Ramasubramanian; Murali S. (Fremont, CA), Valdes; Bruno A. (Sunnyvale, CA), Wilcox; James D. (Pleasanton, CA), Spindt; Christopher J. (Menlo Park, CA), Ho; Geoffrey Matthew (San Ramon, CA), Varni; John F. (Campbell, CA), Lee; Kim Han (Pleasanton, CA), Contreras; Richard J. (Campbell, CA), Schuerlein; Thomas John (Pleasanton, CA), Lahiri; Ashok (Cupertino, CA)

Applicant: Enovix Corporation (Fremont, CA)

Family ID: 1000008821542

Assignee: Enovix Corporation (Fremont, CA)

Appl. No.: 18/399062

Filed: December 28, 2023

Prior Publication Data

Document Identifier

US 20240213541 A1

Publication Date

Jun. 27, 2024

Related U.S. Application Data

continuation parent-doc US 17363148 20210630 US 11901514 child-doc US 18399062
division parent-doc US 16349785 US 11063299 20210713 WO PCT/US2017/061892 20171116
child-doc US 17363148
us-provisional-application US 62422983 20161116

Publication Classification

Int. Cl.: **H01M10/058** (20100101); **H01M10/04** (20060101); **H01M10/0525** (20100101);
H01M10/054 (20100101); **H01M10/42** (20060101); **H01M50/489** (20210101);
H01M50/491 (20210101)

U.S. Cl.:

CPC **H01M10/058** (20130101); **H01M10/049** (20130101); **H01M10/0525** (20130101);
H01M10/054 (20130101); **H01M50/489** (20210101); **H01M50/491** (20210101);
H01M2010/4292 (20130101)

Field of Classification Search

CPC: H01M (10/058); H01M (10/049); H01M (10/0525); H01M (10/054); H01M (50/489);
H01M (50/491); H01M (2010/4292); H01M (10/052); H01M (10/0468); H01M (4/13);
Y02E (60/10); Y02P (70/50)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3563805	12/1970	Deierhoi, Jr.	N/A	N/A
4396689	12/1982	Grimes et al.	N/A	N/A
4587182	12/1985	Stiles et al.	N/A	N/A
4889777	12/1988	Akuto	N/A	N/A
5238759	12/1992	Plichta et al.	N/A	N/A
5294504	12/1993	Otagawa et al.	N/A	N/A
5350645	12/1993	Lake et al.	N/A	N/A
5709962	12/1997	Bailey	N/A	N/A
6083640	12/1999	Lee et al.	N/A	N/A
6090505	12/1999	Shimamura et al.	N/A	N/A
6235427	12/2000	Idota et al.	N/A	N/A
6287371	12/2000	Ota et al.	N/A	N/A
6355369	12/2001	Iarochencko et al.	N/A	N/A
6383234	12/2001	Noh	N/A	N/A
6432579	12/2001	Tsuji et al.	N/A	N/A
6432585	12/2001	Kawakami et al.	N/A	N/A
6525391	12/2002	Bertrand et al.	N/A	N/A
6548208	12/2002	Kasamatsu et al.	N/A	N/A
6679925	12/2003	Tanizaki et al.	N/A	N/A

6726733	12/2003	Lee et al.	N/A	N/A
6791737	12/2003	Giron	N/A	N/A
6835496	12/2003	Kaminaka et al.	N/A	N/A
6855378	12/2004	Narang	N/A	N/A
7066971	12/2005	Carlson	N/A	N/A
7309548	12/2006	Ota et al.	N/A	N/A
7402829	12/2007	Green	N/A	N/A
7722984	12/2009	Kim et al.	N/A	N/A
7794881	12/2009	Fujimoto et al.	N/A	N/A
7824806	12/2009	Visco et al.	N/A	N/A
8101298	12/2011	Green et al.	N/A	N/A
8129048	12/2011	Hirakawa et al.	N/A	N/A
8133613	12/2011	Ramasubramanian et al.	N/A	N/A
8192788	12/2011	Shah et al.	N/A	N/A
8367244	12/2012	Ramasubramanian et al.	N/A	N/A
8475957	12/2012	Ramasubramanian et al.	N/A	N/A
8527395	12/2012	Pylant	N/A	N/A
8580439	12/2012	Kaiser et al.	N/A	N/A
8722226	12/2013	Chiang et al.	N/A	N/A
8841030	12/2013	Lahiri et al.	N/A	N/A
8865345	12/2013	Ramasubramanian et al.	N/A	N/A
8993159	12/2014	Chiang et al.	N/A	N/A
9105905	12/2014	Ramasubramanian et al.	N/A	N/A
9153833	12/2014	Chiang et al.	N/A	N/A
9343772	12/2015	Byun	N/A	N/A
9356271	12/2015	Ramasubramanian et al.	N/A	N/A
9362553	12/2015	Lahiri et al.	N/A	N/A
9660292	12/2016	Rust et al.	N/A	N/A
9692044	12/2016	Delpuech et al.	N/A	N/A
9806331	12/2016	Lahiri et al.	N/A	N/A
9991490	12/2017	Ramasubramanian et al.	N/A	N/A
10020514	12/2017	Ramasubramanian et al.	N/A	N/A
10038214	12/2017	Rust et al.	N/A	N/A
10177400	12/2018	Busacca et al.	N/A	N/A
10256507	12/2018	Busacca et al.	N/A	N/A
10283807	12/2018	Busacca et al.	N/A	N/A
10784477	12/2019	Fischer et al.	N/A	N/A
11063299	12/2020	Busacca et al.	N/A	N/A
11081718	12/2020	Busacca et al.	N/A	N/A
11128020	12/2020	Busacca et al.	N/A	N/A
11264680	12/2021	Busacca et al.	N/A	N/A
11411253	12/2021	Busacca et al.	N/A	N/A
11444310	12/2021	Busacca et al.	N/A	N/A
11901514	12/2023	Busacca et al.	N/A	N/A
2002/0013986	12/2001	Ahn et al.	N/A	N/A
2003/0082446	12/2002	Chiang et al.	N/A	N/A
2003/0175589	12/2002	Kaminaka et al.	N/A	N/A
2004/0048151	12/2003	Hayashi et al.	N/A	N/A
2004/0185336	12/2003	Ito et al.	N/A	N/A
2004/0214085	12/2003	Sheem et al.	N/A	N/A

2004/0234861	12/2003	Kawase et al.	N/A	N/A
2004/0241540	12/2003	Tsutsumi et al.	N/A	N/A
2004/0253512	12/2003	Watanabe et al.	N/A	N/A
2005/0008939	12/2004	Ota et al.	N/A	N/A
2005/0095503	12/2004	Adachi et al.	N/A	N/A
2005/0130383	12/2004	Divakaruni et al.	N/A	N/A
2005/0208379	12/2004	Musha et al.	N/A	N/A
2006/0051663	12/2005	Fujita et al.	N/A	N/A
2006/0093871	12/2005	Howard et al.	N/A	N/A
2006/0188648	12/2005	Yudasaka	N/A	N/A
2007/0002523	12/2006	Ando et al.	N/A	N/A
2007/0031733	12/2006	Kogetsu et al.	N/A	N/A
2007/0097481	12/2006	Burdis et al.	N/A	N/A
2007/0172732	12/2006	Jung et al.	N/A	N/A
2007/0285051	12/2006	Jeon et al.	N/A	N/A
2008/0003490	12/2007	Christensen et al.	N/A	N/A
2008/0081256	12/2007	Madou et al.	N/A	N/A
2008/0081257	12/2007	Yoshida et al.	N/A	N/A
2008/0118826	12/2007	Shimamura et al.	N/A	N/A
2008/0233455	12/2007	Deimede et al.	N/A	N/A
2009/0023073	12/2008	Okada et al.	N/A	N/A
2009/0035664	12/2008	Chiang et al.	N/A	N/A
2009/0068567	12/2008	Konishiike et al.	N/A	N/A
2009/0123847	12/2008	Okada et al.	N/A	N/A
2009/0136844	12/2008	Watanabe et al.	N/A	N/A
2009/0142656	12/2008	Nathan et al.	N/A	N/A
2009/0155678	12/2008	Less et al.	N/A	N/A
2009/0159311	12/2008	Zheng et al.	N/A	N/A
2009/0166187	12/2008	Nagase et al.	N/A	N/A
2009/0263716	12/2008	Ramasubramanian et al.	N/A	N/A
2009/0303660	12/2008	Nair et al.	N/A	N/A
2010/0040951	12/2009	Yamamoto et al.	N/A	N/A
2010/0051856	12/2009	Kim et al.	N/A	N/A
2010/0209775	12/2009	Kim et al.	N/A	N/A
2010/0266907	12/2009	Yazami	N/A	N/A
2010/0285368	12/2009	Yamamoto et al.	N/A	N/A
2011/0008656	12/2010	Tanahashi et al.	N/A	N/A
2011/0014522	12/2010	Visco et al.	N/A	N/A
2011/0020701	12/2010	Park et al.	N/A	N/A
2011/0020713	12/2010	Cui et al.	N/A	N/A
2011/0020719	12/2010	Manabe et al.	N/A	N/A
2011/0067228	12/2010	Green	N/A	N/A
2011/0070489	12/2010	Chiang et al.	N/A	N/A
2011/0111283	12/2010	Rust et al.	N/A	N/A
2011/0129732	12/2010	Bachrach et al.	N/A	N/A
2011/0159328	12/2010	Yeo	N/A	N/A
2011/0171518	12/2010	Dunn et al.	N/A	N/A
2011/0200862	12/2010	Kurosawa	N/A	N/A
2011/0294015	12/2010	Pirk et al.	N/A	N/A
2012/0052341	12/2011	Kim et al.	N/A	N/A

2012/0100438	12/2011	Fasching et al.	N/A	N/A
2012/0176093	12/2011	Ramasubramanian et al.	N/A	N/A
2012/0202113	12/2011	Hodge et al.	N/A	N/A
2012/0288742	12/2011	Tanaka et al.	N/A	N/A
2013/0078493	12/2012	Chen	N/A	N/A
2013/0136963	12/2012	Chiba	N/A	N/A
2013/0143120	12/2012	Ramasubramanian et al.	N/A	N/A
2013/0189602	12/2012	Lahiri et al.	N/A	N/A
2013/0202942	12/2012	Sakai et al.	N/A	N/A
2013/0230751	12/2012	Shaw	N/A	N/A
2014/0050959	12/2013	Ryu et al.	N/A	N/A
2014/0050969	12/2013	Rust et al.	N/A	N/A
2014/0072850	12/2013	Kwon et al.	N/A	N/A
2014/0154531	12/2013	Furuya et al.	N/A	N/A
2014/0272547	12/2013	Ramasubramanian et al.	N/A	N/A
2014/0335395	12/2013	Ramasubramanian et al.	N/A	N/A
2015/0007952	12/2014	Mderl et al.	N/A	N/A
2015/0024253	12/2014	Noh	N/A	N/A
2015/0033547	12/2014	Yang et al.	N/A	N/A
2015/0079452	12/2014	Park et al.	N/A	N/A
2015/0104686	12/2014	Brommer et al.	N/A	N/A
2015/0135522	12/2014	Seto et al.	N/A	N/A
2015/0162575	12/2014	Son et al.	N/A	N/A
2016/0197332	12/2015	Lee et al.	N/A	N/A
2016/0218339	12/2015	Nishimori et al.	N/A	N/A
2017/0352850	12/2016	Nagane et al.	N/A	N/A
2018/0040876	12/2017	Lahiri et al.	N/A	N/A
2018/0079035	12/2017	Watanabe	N/A	N/A
2018/0145367	12/2017	Busacca et al.	N/A	N/A
2018/0166735	12/2017	Busacca et al.	N/A	N/A
2018/0309110	12/2017	Iwasaki et al.	N/A	N/A
2019/0207264	12/2018	Busacca et al.	N/A	N/A
2019/0221878	12/2018	Busacca et al.	N/A	N/A
2019/0319294	12/2018	Busacca et al.	N/A	N/A
2019/0350633	12/2018	Ramadhyan et al.	N/A	N/A
2019/0372150	12/2018	Busacca et al.	N/A	N/A
2020/0212493	12/2019	Busacca et al.	N/A	N/A
2020/0313146	12/2019	Busacca et al.	N/A	N/A
2020/0335754	12/2019	Ramasubramanian et al.	N/A	N/A
2020/0350633	12/2019	Busacca et al.	N/A	N/A
2020/0381771	12/2019	Rust et al.	N/A	N/A
2021/0265617	12/2020	Okano et al.	N/A	N/A
2022/0115711	12/2021	Busacca et al.	N/A	N/A
2022/0115753	12/2021	Busacca et al.	N/A	N/A
2022/0123370	12/2021	Busacca et al.	N/A	N/A
2022/0149423	12/2021	Busacca et al.	N/A	N/A
2022/0158220	12/2021	Busacca et al.	N/A	N/A
2022/0166051	12/2021	Busacca et al.	N/A	N/A
2022/0173485	12/2021	Busacca et al.	N/A	N/A
2022/0181702	12/2021	Busacca et al.	N/A	N/A

2022/0399612	12/2021	Busacca et al.	N/A	N/A
2023/0178787	12/2022	Busacca et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2388711	12/2000	CA	N/A
85106872	12/1985	CN	N/A
1286811	12/2000	CN	N/A
1555588	12/2003	CN	N/A
101960643	12/2010	CN	N/A
102007625	12/2010	CN	N/A
102569758	12/2011	CN	N/A
104347856	12/2014	CN	N/A
104662714	12/2014	CN	N/A
105518904	12/2015	CN	N/A
207199697	12/2017	CN	N/A
207967108	12/2017	CN	N/A
209447946	12/2018	CN	N/A
210576107	12/2019	CN	N/A
212625870	12/2020	CN	N/A
109994663	12/2020	CN	N/A
109994671	12/2020	CN	N/A
216085187	12/2021	CN	N/A
216872119	12/2021	CN	N/A
218274993	12/2022	CN	N/A
218385615	12/2022	CN	N/A
218677233	12/2022	CN	N/A
218677326	12/2022	CN	N/A
219658948	12/2022	CN	N/A
220341311	12/2023	CN	N/A
220492106	12/2023	CN	N/A
220510172	12/2023	CN	N/A
220692103	12/2023	CN	N/A
109428021	12/2023	CN	N/A
109428107	12/2023	CN	N/A
114256497	12/2023	CN	N/A
220895659	12/2023	CN	N/A
220963563	12/2023	CN	N/A
221226383	12/2023	CN	N/A
221353058	12/2023	CN	N/A
221632726	12/2023	CN	N/A
221766962	12/2023	CN	N/A
221766963	12/2023	CN	N/A
221805673	12/2023	CN	N/A
221861763	12/2023	CN	N/A
222282154	12/2023	CN	N/A
222463111	12/2024	CN	N/A
222826444	12/2024	CN	N/A
102018203033	12/2018	DE	N/A
0883199	12/1997	EP	N/A

1028476	12/1999	EP	N/A
1100134	12/2000	EP	N/A
1102340	12/2000	EP	N/A
1270765	12/2002	EP	N/A
1465268	12/2003	EP	N/A
2048262	12/2008	EP	N/A
2277214	12/2010	EP	N/A
2858162	12/2014	EP	N/A
2223367	12/2014	EP	N/A
3051606	12/2015	EP	N/A
3295507	12/2017	EP	N/A
3367468	12/2017	EP	N/A
3455898	12/2018	EP	N/A
01-132064	12/1988	JP	N/A
06-236768	12/1993	JP	N/A
2001-185224	12/2000	JP	N/A
2003-323882	12/2002	JP	N/A
2004-351500	12/2003	JP	N/A
2005-149891	12/2004	JP	N/A
2005-285378	12/2004	JP	N/A
2006-100280	12/2005	JP	N/A
2006-173001	12/2005	JP	N/A
2006-236768	12/2005	JP	N/A
2006-286427	12/2005	JP	N/A
2007-258160	12/2006	JP	N/A
2008-140633	12/2007	JP	N/A
2008-171732	12/2007	JP	N/A
2009-170258	12/2008	JP	N/A
2010-146732	12/2009	JP	N/A
2010-225552	12/2009	JP	N/A
2010-262752	12/2009	JP	N/A
2010-278125	12/2009	JP	N/A
2011-171029	12/2010	JP	N/A
2012-516941	12/2011	JP	N/A
2012-160352	12/2011	JP	N/A
2015-505120	12/2014	JP	N/A
2015-064959	12/2014	JP	N/A
2015-524994	12/2014	JP	N/A
2015-172997	12/2014	JP	N/A
2015-220218	12/2014	JP	N/A
2019-169476	12/2018	JP	N/A
10-2003-0044508	12/2002	KR	N/A
10-2006-0050988	12/2005	KR	N/A
10-2007-0021192	12/2006	KR	N/A
10-2013-0105001	12/2012	KR	N/A
10-2015-0010226	12/2014	KR	N/A
10-2015-0045456	12/2014	KR	N/A
1015956	12/2001	NL	N/A
201225385	12/2011	TW	N/A
201414048	12/2013	TW	N/A

99/00588	12/1998	WO	N/A
02/43168	12/2001	WO	N/A
2003/105258	12/2002	WO	N/A
2005/101973	12/2004	WO	N/A
2006/064344	12/2005	WO	N/A
2008/030215	12/2007	WO	N/A
2008/089110	12/2007	WO	N/A
2009/109834	12/2008	WO	N/A
2009/129490	12/2008	WO	N/A
2009/140300	12/2008	WO	N/A
2010/090956	12/2009	WO	N/A
2010/092059	12/2009	WO	N/A
2010/138176	12/2009	WO	N/A
2011/154862	12/2010	WO	N/A
2012/054767	12/2011	WO	N/A
2013/112135	12/2012	WO	N/A
2013/112670	12/2012	WO	N/A
2014/024424	12/2013	WO	N/A
2014/028230	12/2013	WO	N/A
2014/151202	12/2013	WO	N/A
2016/183410	12/2015	WO	N/A
2018/020906	12/2017	WO	N/A
2018/115016	12/2017	WO	N/A
2019/099642	12/2018	WO	N/A
2019/099650	12/2018	WO	N/A
2021/020480	12/2020	WO	N/A
2022/021056	12/2021	WO	N/A
2022/060703	12/2021	WO	N/A
2022/108954	12/2021	WO	N/A
2022/125529	12/2021	WO	N/A

OTHER PUBLICATIONS

Zhang et al., High aspect ration nickel structions fabricated by electrochemical replication of hydrofluoric acid etched silicon, Electrochemical and Solid-State Letters, 2006, 9(9): C150-C152. cited by applicant

Alliance Rubber Company, Rubber Band Size Chari, retrieved from www.rubberband.com/public/userfiles/sales-collateral/RubberBandChart.pdf, 2 pgs 2021. cited by applicant

Arora, P. et al., "Battery Separators", Chem. Reviews, 2004, 104, 4419-4462 Mar. 30, 2004. cited by applicant

Bourderau et al., "Amorphous Silicon as a Possible Anode Material for Li-Ion Batteries," Journal of Power Sources, 1999, 81-82, 233-236 Sep. 30, 1999. cited by applicant

Broussely et al., Li-ion batteries and portable power source prospects for the next 5-10 years, Journal of Power Sources, 136, 2004, 386-394. cited by applicant

Dierks, S., GuideChem, NickelSilicide {Ni₂Si} {cas 12059-14-2) MSDS, Material safety data sheet, retrieved from www.guidechem.com/cas-120/12059-14-2.html, 2 pgs Sep. 30, 1993. cited by applicant

European Patent Office, Extended European Search Report for 12866772.2, EP 2807698, dated Oct. 8, 2015, 3 pages. cited by applicant

European Patent Office, Extended European Search Report for 13829954.0, EP 2885830, dated

Feb. 19, 2016, 7 pages. cited by applicant

European Patent Office, Extended European Search Report for 14768734.7, EP 2973785, 10 pages dated Jul. 15, 2016. cited by applicant

European Patent Office, Extended European Search Report for 20191612.9, 7 pages Mar. 5, 2021. cited by applicant

European Patent Office, Extended European Search Report for Application No. 16793590.7, publication EP 3295507, 7 pages dated Aug. 28, 2018. cited by applicant

European Patent Office, Extended European Search Report for EP 17872332.6, 7 pages dated Sep. 1, 2020. cited by applicant

European Patent Office, Extended Search Report for EP 13 74 0825, App. No. 13740825.8, dated Aug. 8, 2015, 9 pages. cited by applicant

European Patent Office, Extended Search Report for EP App. 17796914.4, 10 pages dated Nov. 19, 2019. cited by applicant

European Patent Office, Extended Search Report for EP App. 19197127.4, 3 pages dated Jan. 17, 2020. cited by applicant

Golodnitsky et al., Advanced materials for the 3D microbattery, *Journal of Power Sources*, 2006, 153, 281-287. cited by applicant

Google Query Result Page for “Pressure a Rubber Band Can Apply” and “How much pressure does a rubber band have?”, 1 page 2021. cited by applicant

Green et al., Structured silicon anodes for lithium battery applications, *Electrochemical and Solid State Letters*, 6, 2003, A75-A79 Mar. 5, 2003. cited by applicant

Harraz et al., Different behavior in immersion plating of nickel on porous silicon from acidic and alkaline fluoride media, *J. Elect. Soc.*, 2003, 150(5): C277-284. cited by applicant

Harraz et al., Immersion plating of nickel onto a porous silicon layer from fluoride solutions, *Phys. Stat. Sol.*, 2003, 197(1): 51-56. cited by applicant

Iaboni et al., Li₁₅Si₄ Formation in silicon thin film negative electrodes, *Journal of the Electrochemical Society*, 2016, 163(2), A255-A261. cited by applicant

Kasavajula et al., Nano- and Bulk-Silicon-Based Insertion Anodes for Lithium-Ion Secondary Cells, *Journal of Power Sources*, 2007, 1003-1039, 163 Nov. 9, 2006. cited by applicant

Keener Rubber Bands Federal Specifications, retrieved from keenerrubber.com/Federal%20Specifications.htm, 1 page 2021. cited by applicant

Li et al., “The Crystal Structural Evolution of Nano-Si Anode Caused by Lithium Insertion and Extraction at Room Temperature,” *Solid State Ionics*, 2000, 135, 181-191 Nov. 30, 2000. cited by applicant

Liu, C., *Bulk Micromachining and Silicon Anisotropic Etching, Foundations of MEMS*, Prentice Hall Inc. Chapter 10, pp. 326-370; Prentice Hall Dec. 31, 2006. cited by applicant

Long et al., Three-Dimensional battery Architectures, *Chemical Reviews*, 2004, 104, 4463-4492. cited by applicant

Maranchi et al., High capacity, reversible silicon thin-film anodes for lithium-ion batteries, *Electrochemical and Solid-State Letters*, 2001, 6(9), A198-A201. cited by applicant

Mu et al., Silicon nanotube array/gold electrode for direct electrochemistry of cytochrome C, *J. Phys. Chem. B*, 2007, 111(6), 1491-1495. cited by applicant

Obrovac et al., Reversible cycling of crystalline silicon powder, *J. Elect. Soc.*, 2007, 154(2): A103-A108. cited by applicant

Patent Cooperation Treaty, International Search Report for PCT/US2009/041012, dated Sep. 8, 2009, 4 pages Sep. 8, 2009. cited by applicant

Patent Cooperation Treaty, International Search Report for PCT/US2013/053235, dated Jan. 28, 2014, 5 pages Jan. 28, 2014. cited by applicant

Patent Cooperation Treaty, International Search Report for PCT/US2016/032284, dated Aug. 26, 2016, 4 pages 2016. cited by applicant

Patent Cooperation Treaty, International Search Report for PCT/US2017/032355, 4 pages dated Aug. 25, 2017. cited by applicant

Patent Cooperation Treaty, International Search Report for PCT/US2017/032355, dated Aug. 25, 2017, 4 pages 2017. cited by applicant

Patent Cooperation Treaty, International Search Report for PCT/US2017/061892, 6 pages dated Mar. 27, 2018. cited by applicant

Patent Cooperation Treaty, International Search Report for PCT/US2018/061245, 10 pgs, dated May 7, 2019. cited by applicant

Patent Cooperation Treaty, International Search Report for PCT/US2018/061254, 5pgs, dated Mar. 7, 2019. cited by applicant

Patent Cooperation Treaty, International Search report issued for PCT/US2013/022868, dated May 15, 2013, 3 pages dated May 15, 2013. cited by applicant

Patent Cooperation Treaty, International Search Report issued for PCT/US2014/025200, dated Jul. 29, 2014, 4 pages dated Jul. 29, 2014. cited by applicant

Patent Cooperation Treaty, International Search Report issued on PCT/US2012/022393, dated Oct. 10, 2012, 4 pages. cited by applicant

Patent Cooperation Treaty, Written Opinion for PCT/US2017/061892, 6 pages dated Mar. 27, 2018. cited by applicant

Roberts et al., 3D lithium ion batteries—from fundamentals to fabrication, Journal of Materials Chemistry, Royal Society of Chemistry, 2011, 21: 9876-9890 2011. cited by applicant

Shin et al. Porous Silicon Negative Electrodes for Rechargeable Lithium Batteries, Journal of Power Sources, 139 (2005) 314-320 Sep. 13, 2004. cited by applicant

Su et al., Silicon-Based Nanomaterials for Lithium-Ion Batteries: A Review, Advanced Energy Materials, 2013, 1-23. cited by applicant

Taiwan Search Report for App. No. 102129550, dated Sep. 9, 2016, 1 page dated Sep. 9, 2016. cited by applicant

United Kingdom Search Report dated Dec. 18, 2012, 4 pages dated Dec. 18, 2012. cited by applicant

Vyatkin et al., Random and Ordered Macropore in p-type silicon J. Electrochem. Soc. 149, 1, G70-G76 (2002) Dec. 6, 2001. cited by applicant

Waidmann et al., Tuning nickel silicide properties using a lamp based RTA, a heat conduction based RTA or a furnace anneal, Microelectronic Engineering, 2006, 83, 2282-2286. cited by applicant

Whitehead et al., Current Collectors for positive electrodes of lithium-based batteries, Journal of the Electrochemical Society, 2005, A5105-A2113, 152(11) Sep. 8, 2005. cited by applicant

Xu et al., Nickel displacement deposition of porous silicon with ultrahigh aspect ratio, J. Elect. Soc., 2007, 154(3): 170-174. cited by applicant

Xu, Chengkun et al., Theoretical studies of displacement disposition of nickel into porous silicon with ultrahigh aspect ratio, Electrochimica Acta, Dec. 4, 2006, 3901-3909, 52 Dec. 4, 2006. cited by applicant

Research Institute Overview, R&D and Smart Manufacturing,
<https://www.atlbattery.com/en/research.html> (Jan. 24, 2025), 7 pages. cited by applicant

Primary Examiner: Gatewood; Daniel S

Attorney, Agent or Firm: Haley Guiliano LLP

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS (1) This is a continuation of U.S. application Ser. No. 17/363,148, filed on Jun. 30, 2021, which is a divisional application of U.S. application Ser. No. 16/349,785, filed May 14, 2019, now U.S. Pat. No. 11,063,299, which is a U.S. National Phase Application of International Application PCT Application Number PCT/US17/61892, filed Nov. 16, 2017, which claims priority to U.S. Application Ser. No. 62/422,983 filed Nov. 16, 2016. The contents of each of these applications are hereby incorporated by reference in their entireties.

FIELD OF THE INVENTION

(1) This disclosure generally relates to structures for use in energy storage devices, to energy storage devices employing such structures, and to methods for producing such structures and energy devices.

BACKGROUND

(2) Rocking chair or insertion secondary batteries are a type of energy storage device in which carrier ions, such as lithium, sodium, potassium, calcium or magnesium ions, move between a positive electrode and a negative electrode through an electrolyte. The secondary battery may comprise a single battery cell, or two or more battery cells that have been electrically coupled to form the battery, with each battery cell comprising a positive electrode, a negative electrode, a microporous separator, and an electrolyte.

(3) In rocking chair battery cells, both the positive and negative electrodes comprise materials into which a carrier ion inserts and extracts. As a cell is discharged, carrier ions are extracted from the negative electrode and inserted into the positive electrode. As a cell is charged, the reverse process occurs: the carrier ion is extracted from the positive and inserted into the negative electrode.

(4) When the carrier ions move between electrodes, one of the persistent challenges resides in the fact that the electrodes tend to expand and contract as the battery is repeatedly charged and discharged. The expansion and contraction during cycling tends to be problematic for reliability and cycle life of the battery because when the electrodes expand, electrical shorts and battery failures occur.

(5) Therefore, there remains a need for improving the reliability and cycle life of secondary batteries having electrodes that tend to expand and contract.

SUMMARY

(6) Briefly, therefore, one aspect of this disclosure relates to the implementation of constraint structures to improve the energy density, reliability, and cycle life of batteries.

(7) According to one aspect, a secondary battery for cycling between a charged and a discharged state is provided, the secondary battery having a battery enclosure, an electrode assembly, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure. The electrode assembly has a population of anode structures, a population of cathode structures, and an electrically insulating microporous separator material electrically separating members of the anode and cathode structure populations, wherein the anode and cathode structure populations are arranged in an alternating sequence in a longitudinal direction, each member of the anode structure population has a first cross-sectional area, $A_{sub.1}$ when the secondary battery is in the charged state and a second cross-sectional area, $A_{sub.2}$, when the secondary battery is in the discharged state, each member of the cathode structure population has a first cross-sectional area, $C_{sub.1}$ when the secondary battery is in the charged state and a second cross-sectional area, $C_{sub.2}$, when the secondary battery is in the discharged state, and the cross-sectional areas of the members of the anode and cathode structure populations are measured in a first longitudinal plane that is parallel to the longitudinal direction. The electrode assembly also has a set of electrode constraints that at least partially restrains growth of the electrode assembly in the longitudinal direction upon cycling of the secondary battery between the charged and discharged states. Each member of the population of cathode structures has a layer of a cathode active material and each member of the population of anode structures has

a layer of an anode active material having a capacity to accept more than one mole of carrier ion per mole of anode active material when the secondary battery is charged from a discharged state to a charged state, and $A_{sub.1}$ is greater than $A_{sub.2}$ for each of the members of a subset of the anode structure population and $C_{sub.1}$ is less than $C_{sub.2}$ for each of the members of a subset of the cathode structure population. The charged state is at least 75% of the rated capacity of the secondary battery, and the discharged state is less than 25% of the rated capacity of the secondary battery.

(8) According to yet another aspect, a method of formation is provided for a secondary battery, the secondary battery being capable of cycling between a charged and a discharged state. The secondary battery has a battery enclosure, an electrode assembly, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure. The electrode assembly has a population of anode structures, a population of cathode structures, and an electrically insulating microporous separator material electrically separating members of the anode and cathode structure populations. Members of the anode and cathode structure populations are arranged in an alternating sequence in a longitudinal direction, and members of the population of anode structures have anode active material layers that expand in cross-sectional area A upon charging of the secondary battery. Members of the population of cathode structures have compressible cathode active material layers having a cross-sectional area C , the cross-sectional areas being measured in a first longitudinal plane that is parallel to the longitudinal direction. The method includes, in an initial formation stage, charging the secondary battery such that an expansion in cross-sectional area of the anode active material layers in the members of the population of anode structures compresses the compressible cathode active material layers of the population of cathode structure, such that a cross-sectional area of members of a subset of the cathode structure population decreases from an initial cross-sectional area $C_{sub.i}$ prior to the initial formation stage to a post-formation cross-sectional area $C_{sub.f}$ after the initial formation stage that is less than 95% of the initial cross-sectional area $C_{sub.i}$ prior to the initial formation stage.

(9) According to yet another aspect, a method of formation is provided for a secondary battery, the secondary battery being capable of cycling between a charged and a discharged state. The secondary battery has a battery enclosure, an electrode assembly, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure. The electrode assembly has a population of anode structures, a population of cathode structures, and electrically insulating microporous separators electrically separating members of the anode and compressible cathode structure populations. Members of the anode and cathode structure populations are arranged in an alternating sequence in a longitudinal direction, and members of the population of anode structures have anode active material layers that expand in cross-sectional area A upon charging of the secondary battery. Members of the population of cathode structures have compressible cathode active material layers having a cross-sectional area C , the cross-sectional areas being measured in a first longitudinal plane that is parallel to the longitudinal direction. The method includes, in an initial formation stage, charging the secondary battery such that expansion of the anode active material layers in the members of the population of anode structures compresses the microporous separators against the compressible cathode active material layers of the cathode structures at a pressure that contracts the cross-sectional area C of the compressible cathode active material layers, while also at least partially adhering the microporous separators to the compressible cathode active material layers of the cathode structures and the anode active material layers of the anode structures, wherein, upon discharge of the secondary battery and contraction in the cross-sectional area A of the anode active material layers, the at least partial adhesion of the microporous separators to the compressible cathode active material layers and the anode active material layers causes expansion in the cross-sectional area C of the compressible cathode active material layers.

(10) According to yet another aspect, a secondary battery for cycling between a charged and a discharged state is provided, the secondary battery having a battery enclosure, an electrode

assembly, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure. The electrode assembly has a population of anode structures, a population of cathode structures, and an electrically insulating microporous separator material electrically separating members of the anode and cathode structure populations. The electrode assembly also has a set of electrode constraints that at least partially restrains growth of the electrode assembly in the longitudinal direction upon cycling of the secondary battery. Members of the population of anode structures have an anode active material, and wherein the anode active material has the capacity to accept more than one mole of carrier ion per mole of anode active material when the secondary battery is charged from a discharged state to a charged state. Members of the population of cathode structures have a porous cathode active material, wherein a volume $V_{sub.2}$ of the porous cathode active material occupied by the non-aqueous liquid electrolyte in the discharged state is greater than a volume $V_{sub.1}$ of the porous cathode active material occupied by the non-aqueous electrolyte in the charged state. The charged state is at least 75% of the rated capacity of the secondary battery, and the discharged state is less than 25% of the rated capacity of the secondary battery.

(11) According to yet another aspect, a secondary battery for cycling between a charged and a discharged state is provided, the secondary battery having a battery enclosure, an electrode assembly, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure. The electrode assembly has a population of anode structures, a population of cathode structures, and an electrically insulating microporous separator material electrically separating members of the anode and cathode structure populations. Members of the population of anode structures have an anode active material, and members of the population of cathode structures have a cathode active material. Members of the population of cathode structures have an areal capacity of at least 5 mA.Math.h/cm.sup.2 at 0.1 C, and a rate capability of 1 C:C/10 of at least 80% for discharge from a charged state to a discharged state. The charged state is at least 75% of the rated capacity of the secondary battery, and the discharged state is less than 25% of the rated capacity of the secondary battery.

(12) According to yet another aspect, a secondary battery for cycling between a charged and a discharged state is provided, the secondary battery having a battery enclosure, an electrode assembly, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure. The electrode assembly has a population of anode structures, a population of cathode structures, and an electrically insulating microporous separator material electrically separating members of the anode and cathode structure populations, wherein members of the anode and cathode structure populations are arranged in an alternating sequence in a longitudinal direction. Each member of the population of anode structures has a layer of an anode active material and each member of the population of cathode structures has a layer of a cathode active material. Each member of the population of cathode structures has a first cross-sectional area $C_{sub.1}$ when the secondary battery is in the charged state, and has a second cross-sectional area $C_{sub.2}$ when the secondary battery is in the discharged state, wherein the second cross-sectional area $C_{sub.2}$ of the cathode structures in the discharged state is greater than the first cross-sectional area $C_{sub.1}$ of the cathode structures in the charged state, and wherein a ratio of second cross-sectional area $C_{sub.2}$ of a subset of the members of the population of cathode structures to the first cross-sectional area $C_{sub.1}$ of the subset of the members of the population of cathode structures is at least 1.05:1 upon discharging of the secondary battery from the charged state to the discharged state. The charged state is at least 75% of the rated capacity of the secondary battery, and the discharged state is less than 25% of the rated capacity of the secondary battery.

(13) Other aspects, features and embodiments of the present disclosure will be, in part, discussed and, in part, apparent in the following description and drawing.

Description

BRIEF DESCRIPTION OF THE DRAWING

- (1) FIG. 1A is a schematic view of one embodiment of an electrode assembly having a population of cathode structures and a population of anode structures.
- (2) FIG. 1B is a perspective view of one embodiment of an electrode assembly having a population of cathode structures and a population of anode structures.
- (3) FIG. 1C is a perspective view of one embodiment of an electrode assembly having a population of cathode structures and a population of anode structures, and a first longitudinal plane;
- (4) FIG. 1D is a cross-sectional view of an embodiment of an electrode assembly illustrating cross-sectional areas of a population of cathode structures and a population of anode structures.
- (5) FIG. 1E is a cross-sectional view of an embodiment of an electrode assembly illustrating an opposing surface area of an anode structure;
- (6) FIGS. 2A-2C are cross-sectional views of an embodiment of an electrode assembly with a population of cathode structures
- (7) FIG. 3 is a schematic view of an embodiment of a layer of cathode active material.
- (8) FIGS. 4A-4B are cross-sectional views of an embodiment of an electrode assembly with cathode structures having layers of cathode active material that are porous.
- (9) FIGS. 5A-5H show exemplary embodiments of different shapes and sizes for an electrode assembly.
- (10) FIG. 6A illustrates a cross-section of an embodiment of the electrode assembly taken along the line A-A' as shown in FIG. 1B, and further illustrates elements of primary and secondary growth constraint systems.
- (11) FIG. 6B illustrates a cross-section of an embodiment of the electrode assembly taken along the line B-B' as shown in FIG. 1B, and further illustrates elements of primary and secondary growth constraint systems.
- (12) FIG. 6C illustrates a cross-section of an embodiment of the electrode assembly taken along the line B-B' as shown in FIG. 1B, and further illustrates elements of primary and secondary growth constraint systems.
- (13) FIG. 6D illustrates a cross section of an embodiment of the electrode assembly taken along the line A-A1' as shown in FIG. 1B.
- (14) FIG. 7 illustrates a cross-section of an embodiment of the electrode assembly taken along the line A-A' as shown in FIG. 1B, further including a set of electrode constraints, including one embodiment of a primary constraint system and one embodiment of a secondary constraint system.
- (15) FIG. 8 illustrates one embodiment of a top view of a porous growth constraint over an electrode assembly.
- (16) FIG. 9 illustrates an exploded view of an embodiment of an energy storage device or a secondary battery having compressible cathode structures.

DEFINITIONS

- (17) “A,” “an,” and “the” (i.e., singular forms) as used herein refer to plural referents unless the context clearly dictates otherwise. For example, in one instance, reference to “an electrode” includes both a single electrode and a plurality of similar electrodes.
- (18) “About” and “approximately” as used herein refers to plus or minus 10%, 5%, or 1% of the value stated. For example, in one instance, about 250 μm would include 225 μm to 275 μm . By way of further example, in one instance, about 1,000 μm would include 900 μm to 1,100 μm . Unless otherwise indicated, all numbers expressing quantities (e.g., measurements, and the like) and so forth used in the specification and claims are to be understood as being modified in all instances by the term “about.” Accordingly, unless indicated to the contrary, the numerical parameters set forth in the following specification and attached claims are approximations. Each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques.

(19) “Areal capacity” as used herein in the context of a secondary battery refers to the capacity of the battery per unit area, where the area is the geometrical area of a portion of an anode structure (ignoring porosity) facing the cathode structure, summed over all anode structures in the secondary battery. The areal capacity will also typically be specified at a certain C-rate, such as 0.1 C. For example, if the rated capacity of a battery is 1000 mA.Math.h at a C-rate of 0.1 C, and the geometrical area of the portion of each anode structure facing each cathode structure is 250 cm.sup.2, and there are 5 anode structures (each having two facing sides), then the areal capacity is $1000/(250 \times 5 \times 2) = 0.4$ mA.Math.h/cm.sup.2.

(20) “C-rate” as used herein refers to a measure of the rate at which a secondary battery is discharged, and is defined as the discharge current divided by the theoretical current draw under which the battery would deliver its nominal rated capacity in one hour. For example, a C-rate of 1 C indicates the discharge current that discharges the battery in one hour, a rate of 2 C indicates the discharge current that discharges the battery in ½ hours, a rate of C/2 indicates the discharge current that discharges the battery in 2 hours, etc.

(21) “Charged state” as used herein in the context of the state of a secondary battery refers to a state where the secondary battery is charged to at least 75% of its rated capacity. For example, the battery may be charged to at least 80% of its rated capacity, at least 90% of its rated capacity, and even at least 95% of its rated capacity, such as 100% of its rated capacity.

(22) “Discharged state” as used herein in the context of the state of a secondary battery refers to a state where the secondary battery is discharged to less than 25% of its rated capacity. For example, the battery may be discharged to less than 20% of its rated capacity, such as less than 10% of its rated capacity, and even less than 5% of its rated capacity, such as 0% of its rated capacity.

(23) A “cycle” as used herein in the context of cycling of a secondary battery between charged and discharged states refers to charging and/or discharging a battery to move the battery in a cycle from a first state that is either a charged or discharged state, to a second state that is the opposite of the first state (i.e., a charged state if the first state was discharged, or a discharged state if the first state was charged), and then moving the battery back to the first state to complete the cycle. For example, a single cycle of the secondary battery between charged and discharged states can include, as in a charge cycle, charging the battery from a discharged state to a charged state, and then discharging back to the discharged state, to complete the cycle. The single cycle can also include, as in a discharge cycle, discharging the battery from the charged state to the discharged state, and then charging back to a charged state, to complete the cycle.

(24) “Ferret diameter” as referred to herein with respect to the electrode assembly is defined as the distance between two parallel planes restricting the electrode assembly measured in a direction perpendicular to the two planes. For example, a Feret diameter of the electrode assembly in the longitudinal direction is the distance as measured in the longitudinal direction between two parallel planes restricting the electrode assembly that are perpendicular to the longitudinal direction. As another example, a Feret diameter of the electrode assembly in the transverse direction is the distance as measured in the transverse direction between two parallel planes restricting the electrode assembly that are perpendicular to the transverse direction. As yet another example, a Feret diameter of the electrode assembly in the vertical direction is the distance as measured in the vertical direction between two parallel planes restricting the electrode assembly that are perpendicular to the vertical direction.

(25) “Inversely related” as used herein with respect to a change in at least one dimension (e.g., the width), cross-sectional area, and/or volume of an electrode structure (i.e., anode structure and/or cathode structure), refers to a sign of the change being the opposite of that of a sign of the change in the same dimension, cross-section and/or volume in a counter-electrode structure. For example, for an increase in width of an anode structure, a change in the width dimension of the cathode structure that is inversely related thereto would be a decrease in width of the cathode structure. As another example, for an increase in a cross-sectional area of an anode structure, a change in the

cross-sectional area of the cathode structure that is inversely related thereto would be a decrease in cross-sectional area of the cathode structure. Similarly, for a decrease in width of an anode structure, a change in the width dimension of the cathode structure that is inversely related thereto would be an increase in width of the cathode structure. As another example, for a decrease in a cross-sectional area of an anode structure, a change in the cross-sectional area of the cathode structure that is inversely related thereto would be an increase in cross-sectional area of the cathode structure. By way of further example, for an increase in width of a cathode structure, a change in the width dimension of the anode structure that is inversely related thereto would be a decrease in width of the anode structure. As another example, for an increase in a cross-sectional area of a cathode structure, a change in the cross-sectional area of the anode structure that is inversely related thereto would be a decrease in cross-sectional area of the anode structure. Similarly, for a decrease in width of a cathode structure, a change in the width dimension of the anode structure that is inversely related thereto would be an increase in width of the anode structure. As another example, for a decrease in a cross-sectional area of a cathode structure, a change in the cross-sectional area of the anode structure that is inversely related thereto would be an increase in cross-sectional area of the anode structure.

(26) “Longitudinal axis,” “transverse axis,” and “vertical axis,” as used herein refer to mutually perpendicular axes (i.e., each are orthogonal to one another). For example, the “longitudinal axis,” “transverse axis,” and the “vertical axis” as used herein are akin to a Cartesian coordinate system used to define three-dimensional aspects or orientations. As such, the descriptions of elements of the inventive subject matter herein are not limited to the particular axis or axes used to describe three-dimensional orientations of the elements. Alternatively stated, the axes may be interchangeable when referring to three-dimensional aspects of the inventive subject matter.

(27) “Longitudinal direction,” “transverse direction,” and “vertical direction,” as used herein, refer to mutually perpendicular directions (i.e., each are orthogonal to one another). For example, the “longitudinal direction,” “transverse direction,” and the “vertical direction” as used herein may be generally parallel to the longitudinal axis, transverse axis and vertical axis, respectively, of a Cartesian coordinate system used to define three-dimensional aspects or orientations.

(28) “Repeated cycling” as used herein in the context of cycling between charged and discharged states of the secondary battery refers to cycling more than once from a discharged state to a charged state, or from a charged state to a discharged state. For example, repeated cycling between charged and discharged states can include cycling at least 2 times from a discharged to a charged state, such as in charging from a discharged state to a charged state, discharging back to a discharged state, charging again to a charged state and finally discharging back to the discharged state. As yet another example, repeated cycling between charged and discharged states at least 2 times can include discharging from a charged state to a discharged state, charging back up to a charged state, discharging again to a discharged state and finally charging back up to the charged state. By way of further example, repeated cycling between charged and discharged states can include cycling at least 5 times, and even cycling at least 10 times from a discharged to a charged state. By way of further example, the repeated cycling between charged and discharged states can include cycling at least 25, 50, 100, 300, 500 and even 1000 times from a discharged to a charged state.

(29) “Rate capability” as used herein in the context of a secondary battery refers to the ratio of the capacity of the secondary battery at a first C-rate to the capacity of the secondary battery at a second C-rate, expressed as a percentage. For example, the rate capability may be calculated according to $\text{Capacity.sub.1} / \text{Capacity.sub.2} \times 100$, where Capacity.sub.1 is the capacity for discharge at the first C-rate, such as a C-rate of 1 C, and Capacity.sub.2 is the capacity for discharge at a second C-rate, such as a C-rate of C/10, and may be expressed as the calculated percentage for a specified ratio C.sub.x:C.sub.y, where C.sub.x is the first C-rate, and C.sub.y is the second C-rate.

(30) “Rated capacity” as used herein in the context of a secondary battery refers to the capacity of the secondary battery to deliver a specified current over a period of time, as measured under

standard temperature conditions (25° C.). For example, the rated capacity may be measured in units of Amp-hour, either by determining a current output for a specified time, or by determining for a specified current, the time the current can be output, and taking the product of the current and time. For example, for a battery rated 20 Amp.Math.hr, if the current is specified at 2 amperes for the rating, then the battery can be understood to be one that will provide that current output for 10 hours, and conversely if the time is specified at 10 hours for the rating, then the battery can be understood to be one that will output 2 amperes during the 10 hours. In particular, the rated capacity for a secondary battery may be given as the rated capacity at a specified discharge current, such as the C-rate, where the C-rate is a measure of the rate at which the battery is discharged relative to its capacity. For example, a C-rate of 1 C indicates the discharge current that discharges the battery in one hour, 2C indicates the discharge current that discharges the battery in ½ hours, C/2 indicates the discharge current that discharges the battery in 2 hours, etc. Thus, for example, a battery rated at 20 Amp.Math.hr at a C-rate of 1 C would give a discharge current of 20 Amp for 1 hour, whereas a battery rated at 20 Amp.Math.hr at a C-rate of 2 C would give a discharge current of 40 Amps for ½ hour, and a battery rated at 20 Amp.Math.hr at a C-rate of C/2 would give a discharge current of 10 Amps over 2 hours.

(31) “Maximum width” (W.sub.EA) as used herein in the context of a dimension of an electrode assembly corresponds to the greatest width of the electrode assembly as measured from opposing points of longitudinal end surfaces of the electrode assembly in the longitudinal direction.

(32) “Maximum length” (L.sub.EA) as used herein in the context of a dimension of an electrode assembly corresponds to the greatest length of the electrode assembly as measured from opposing points of a lateral surface of the electrode assembly in the transverse direction.

(33) “Maximum height” (H.sub.EA) as used herein in the context of a dimension of an electrode assembly corresponds to the greatest height of the electrode assembly as measured from opposing points of the lateral surface of the electrode assembly in the transverse direction.

(34) “Porosity” or “void fraction” as used herein refers to the fraction of voids in a volume over the total volume, and may be expressed as a percentage. For example, the porosity of a cathode active material layer is the fraction of volume made up by voids in the layer per total layer volume. In the context of a secondary battery, the voids in a cathode active material layer may be at least partially filled with electrolyte, such as liquid electrolyte, during charging and/or discharging of the secondary battery, and as such the porosity or void fraction may be a measure of the volume fraction of the layer that can potentially be occupied by the electrolyte.

DETAILED DESCRIPTION

(35) In general, aspects of the present disclosure are directed to an energy storage device **100** (see, e.g., FIG. **9**), such as a secondary battery **102**, as shown for example in FIGS. **1A-1B** and/or FIG. **9**, that cycles between a charged and a discharged state. The secondary battery **102** includes a battery enclosure **104**, an electrode assembly **106**, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure. In the embodiment as shown in FIG. **1A**, the electrode assembly **106** comprises a population of anode structures **110** (i.e., negative electrode structures), a population of cathode structures **112** (i.e., positive electrode structures), and electrically insulating microporous separators **130** arranged to electrically separate the members of the populations of anode structures **110** and **112**.

(36) According to one embodiment, aspects of the disclosure are directed to addressing issues that can arise in energy storage devices **100**, such as secondary batteries **102**, in a case where members of the population of anode structures **110** expand and/or contract upon cycling of the secondary battery **102** between charged and discharged states. For example, the anode structures **110** may comprise a layer of anode active material **132** (see, e.g., FIG. **7**) that accepts carrier ions during charging of the secondary battery **102**, such as by intercalating with or alloying with the carrier ions, in an amount that is sufficient to generate an increase in the volume of the anode structure. Referring to FIG. **1A**, an embodiment of a three-dimensional electrode assembly **106** is shown with

an alternating set of the anode structures **110** and cathode structures **112** that are interdigitated with one another, and which has a longitudinal axis A.sub.EA that is generally parallel to a stacking direction D (which is depicted as being parallel to the Y axis, in FIG. 1A) a transverse axis (not shown) generally parallel to the X axis, and a vertical axis (not shown) generally parallel to the Z axis. The X, Y and Z axes shown herein are arbitrary axes intended only to show a basis set where the axes are mutually perpendicular to one another in a reference space, and are not intended in any way to limit the structures herein to a specific orientation. Generally, upon charge and discharge cycling of a secondary battery **102** having the electrode assembly **106**, the carrier ions travel between the anode and cathode structures **110** and **112**, respectively, such as generally in a direction that is parallel to the Y axis as shown in the embodiment depicted in FIG. 1A, and can intercalate and/or move into anode/cathode active material of one or more of the anode structures **110** and cathode structures **112** that are located within the direction of travel. In particular, in moving from a discharged state to a charged state, carrier ions such as, for example, one or more of lithium, sodium, potassium, calcium and magnesium, can move between the positive and negative electrodes in the battery. Upon reaching the anode structure, the carrier ions may then intercalate or alloy into the electrode material, thus increasing the size and volume of that electrode. Conversely, reversing from the charged state to the discharged state can cause the ions to de-intercalate or de-alloy, thus contracting the anode structure. This alloying and/or intercalation and de-alloying and/or de-intercalation can cause significant volume change in the anode structure, which can cause strain in the electrode assembly **106**, due to an overall macroscopic expansion of the electrode assembly **106** that can occur as a result of expansion of members of the population of anode structures **110** during cycling of the secondary battery **102**. Thus, the repeated expansion and contraction of the anode structures **110** upon charging and discharging can create strain in the electrode assembly **106**. (37) According to one embodiment, the anode structures **110** that expand and/or contract with cycling of the secondary battery comprise an anode active material that has the capacity to accept more than one mole of carrier ion per mole of anode active material, when the secondary battery **102** is charged from a discharged to a charged state. By way of further example, the anode active material may comprise a material that has the capacity to accept 1.5 or more moles of carrier ion per mole of anode active material, such as 2.0 or more moles of carrier ion per mole of anode active material, and even 2.5 or more moles of carrier ion per mole of anode active material, such as 3.5 moles or more of carrier ion per mole of anode active material. The carrier ion accepted by the anode active material may be at least one of lithium, potassium, sodium, calcium, and magnesium. Examples of anode active materials that expand to provide such a volume change include one or more of silicon, aluminum, tin, zinc, silver, antimony, bismuth, gold, platinum, germanium, palladium, and alloys thereof.

(38) According to one embodiment, the secondary battery **102** includes a set of electrode constraints **108** that restrain growth of the electrode assembly **106**. The growth of the electrode assembly **106** that is being constrained may be a macroscopic increase in one or more dimensions of the electrode assembly **106**, and which may be due to an increase in the volume of members of the population of anode structures **110**. In one embodiment, the set of electrode constraints **108** comprise a primary growth constraint system **151** to mitigate and/or reduce at least one of growth, expansion, and/or swelling of the electrode assembly **106** in the longitudinal direction (i.e., in a direction that parallels the Y axis), as shown for example in FIG. 1B. For example, the primary growth constraint system **151** can include structures configured to constrain growth by opposing expansion, such as at longitudinal end surfaces **116**, **118** of the electrode assembly **106**. In one embodiment, the primary growth constraint system **151** comprises first and second primary growth constraints **154**, **156**, that are separated from each other in the longitudinal direction, and that operate in conjunction with at least one primary connecting member **162** that connects the first and second primary growth constraints **154**, **156** together to restrain growth in the longitudinal direction of the electrode assembly **106**. For example, the first and second primary growth constraints **154**,

156 may at least partially cover first and second longitudinal end surfaces **116**, **118** of the electrode assembly **106**, and may operate in conjunction with one or more connecting members **162**, **164** connecting the primary growth constraints **154**, **156** to one another to oppose and restrain any growth in the electrode assembly **106** that occurs during repeated cycles of charging and/or discharging. In another embodiment, one or more of the first and second primary growth constraints **154**, **156** may be internal to the electrode assembly **106**, and may operate in conjunction with at least one connecting member **162** to constrain growth in the longitudinal direction. Further discussion of embodiments and operation of the primary growth constraint system **151** is provided in more detail below.

(39) In addition, repeated cycling through charge and discharge processes in a secondary battery **102** can induce growth and strain not only in a longitudinal direction of the electrode assembly **106** (e.g., Y-axis in FIGS. **1A-1B**), but can also induce growth and strain in directions orthogonal to the longitudinal direction, such as the transverse and vertical directions (e.g., X and Z axes, respectively, in FIGS. **1A-1B**). Furthermore, in certain embodiments, the incorporation of a primary growth constraint system **151** to inhibit growth in one direction can even exacerbate growth and/or swelling in one or more other directions. For example, in a case where the primary growth constraint system **151** is provided to restrain growth of the electrode assembly **106** in the longitudinal direction, the intercalation of carrier ions during cycles of charging and discharging and the resulting swelling of electrode structures can induce strain in one or more other directions. In particular, in one embodiment, the strain generated by the combination of electrode growth/swelling and longitudinal growth constraints can result in buckling or other failure(s) of the electrode assembly **106** in the vertical direction (e.g., the Z axis as shown in FIGS. **1A-1B**), or even in the transverse direction (e.g., the X axis as shown in FIGS. **1A-1B**).

(40) Accordingly, in one embodiment of the present disclosure, the secondary battery **102** includes not only a primary growth constraint system **151**, but also at least one secondary growth constraint system **152** that may operate in conjunction with the primary growth constraint system **151** to restrain growth of the electrode assembly **106** along one or more axes of the electrode assembly **106**. For example, in one embodiment, the secondary growth constraint system **152** may be configured to interlock with, or otherwise synergistically operate with, the primary growth constraint system **151**, such that overall growth of the electrode assembly **106** can be restrained to impart improved performance and reduced incidence of failure of the secondary battery having the electrode assembly **106** and primary and secondary growth constraint systems **151** and **152**, respectively. In one embodiment, the secondary growth constraint system **152** comprises first and second secondary growth constraints **158**, **160** separated in a second direction and connected by at least one secondary connecting member **166**, wherein the secondary constraint system at least partially restrains growth of the electrode assembly in the direction orthogonal to the longitudinal direction (e.g., the Z direction), upon cycling of the secondary battery. Further discussion of embodiments of the interrelationship between the primary and secondary growth constraint systems **151** and **152**, respectively, and their operation to restrain growth of the electrode assembly **106**, is provided in more detail below.

(41) In one embodiment of the disclosure, the set of electrode constraints **108** may constrain the growth of the electrode assembly **106**, such that the growth of members of the population of anode structures **110**, i.e. during charging of the secondary battery **102** having the electrode assembly **106**, results in compression of other structures of the electrode assembly **106**. For example, the set of electrode constraints **108** may provide a longitudinal constraint, i.e. via the primary growth constraint system **151**, that constrains growth of the electrode assembly **106** in the longitudinal direction, such that expansion of members of the population of anode structures **110** in the longitudinal direction during charging of the secondary battery **102** exerts a compressive pressure on members of the population of cathode structures **112** in the electrode assembly **106**. That is the members of the population of cathode structures **112** may be at least partially prevented from

longitudinally translating away from the expanding anode structures members by the presence of the longitudinal constraints, with the result that longitudinal expansion of members of the population of anode structures **110** compresses the members of the population of cathode structures **112**. According to yet another embodiment, the set of electrode constraints **108** may constrain growth of the electrode assembly **106** in other direction(s) orthogonal to the longitudinal direction, such as in the vertical direction (Z direction), and/or in the transverse direction (X direction), such that growth of members of the population of anode structures **110** during charging generates a compressive force. The growth of the members of the population of anode structures **110** in an electrode assembly **106** having the set of electrode constraints may thus generate compressive forces and/or pressures on other components of the electrode assembly, which can lead to failure of such components if a force and/or pressure failure limit is exceeded.

(42) In one embodiment, the expansion and/or contraction of the members of the population of anode structures **110** in the constrained electrode assembly **106** can be at least partially accommodated by providing members of the population of cathode structures **112** that are capable of expanding and/or contracting, such as at least partly in relation to the expansion and/or contraction of the members of the population of anode structures **110**, thereby reducing strain in the electrode assembly **106**. For example, in one embodiment, the members of the population of cathode structures **112** are capable of changing (e.g., expanding and/or contracting) in at least one dimension in a manner that is inversely related to a change in at least one dimension of the members of the population of anode structures. For example, in a case where members of the population of anode structures **110** increase in a width dimension and/or cross-sectional area during charging of the secondary battery **102**, the members of the population of cathode structures **112** may be capable of contracting in the width dimension and/or cross-sectional area, to at least partially accommodate the change in dimension(s) of members of the population of anode structures **110**.

(43) In one embodiment, each member of a population of anode structures **110** has a cross-section **114** with cross-sectional area A, and each member of the population of cathode structures **112** has a cross-section **114** with cross-sectional area C, wherein the cross-sectional areas are measured in a first longitudinal plane **113** that is parallel to the longitudinal direction (i.e., parallel to the longitudinal axis A.sub.EA), as shown for example in FIGS. 1 C and 1D. As seen in the embodiment as shown in FIG. 1D, which depicts generally rectangular cross-sections as taken along the longitudinal plane **113**, the cross-sectional area A of the anode structure for such a rectangular cross-section may be equal to the height H.sub.A of the anode structure **110** times the width W.sub.A of the anode structure, and the cross-sectional area C of the cathode structure **112** may be equal to the height H.sub.C of the cathode structure **110** times the width W.sub.C of the cathode structure **112**. Alternatively and/or additionally, the cross-sectional area **114** may be calculated for electrodes having different shapes and/or cross-sections other than that shown in FIGS. 1C-1D, for example by a suitable cross-sectional area determination method understood by those of ordinary skill in the art. Without being limited thereto, in one embodiment, the cross-sectional area may be calculated by using a Scanning Electron Microscopy (SEM) technique to identify a cross-section of a member of the cathode and/or anode structure populations that is of interest, in the first longitudinal plane **113**. The cross-sectional area for the cross-section obtained by SEM may then be obtained using methods known to those of ordinary skill in the art, such as for example by using available software programs capable of determining the areas of various shapes and objects, such as for example the ImageJ software (Image Processing and Analysis in Java) available from the National Institutes of Health. In one embodiment, the area of a cross-section in an image identified by SEM may be generally determined using a software program by computationally or manually identifying the boundaries of the cross-section in the SEM image, counting a number of pixels that fall within the identified boundaries of the portion of the SEM image corresponding to the cross-section, and inputting a scale of the image (e.g., dimension size

per pixel in the image), to calculate the area of the identified cross-section. Other methods known to those of ordinary skill in the art for the determination of cross-sectional areas may also be used in determining the area of a cross-section of one or more members of the anode and cathode structure populations.

(44) Accordingly, in one embodiment, a change in size of either a member of the population of anode structures **110** and/or a member of the population of cathode structure **112** may be determined according to a change in the cross-sectional area of the structure as measured in the first longitudinal plane. For example, in one embodiment, each member of the anode structure population has a first cross-sectional area, A.sub.1, when the secondary battery is in the charged state, and a second cross-sectional area A.sub.2 when the secondary battery is in the discharged state, and each member of the cathode structure population has a first cross-sectional area C.sub.1 when the secondary battery is in the charged state, and a second cross-sectional area C.sub.2, when the secondary battery is in the discharged state. The change in dimension and/or volume of the members of the population of anode and/or cathode structures upon charging and discharging may thus result in an assembly where A.sub.1 is greater than A.sub.2 for each of the members of a subset of the anode structure population, and C.sub.1 is less than C.sub.2 for each of the members of a subset of the cathode structure population. That is, upon charging of the secondary battery, the cross-sectional areas of members of the anode structure population increase from A.sub.1 to A.sub.2, whereas the cross-sectional areas of members of the cathode structure population contract from C.sub.2 to C.sub.1, and upon discharging of the secondary battery, the cross-sectional areas of members of the anode structure population decrease from A.sub.2 to A.sub.1, whereas the cross-sectional areas of members of the cathode structure population increase from C.sub.2 to C.sub.1. Thus, in one embodiment, the changing dimension(s) of members of the cathode structure population can at least partially accommodate an increase and/or decrease in the dimensions and/or size of members of the anode structure population.

(45) Furthermore, by “subset” of the anode structure population, it is meant at least one member of the anode structure population, and the subset can also be co-extensive with the number of members in the anode structure population in the electrode assembly **106**. That is, the subset of the population of anode structures can include only one or all members of the population of anode structures in the electrode assembly **106**, or any number in between. Similarly, by “subset” of the cathode structure population, it is meant at least one member of the cathode structure population, and the subset can also be co-extensive with the number of members in the cathode structure population in the electrode assembly **106**. That is, the subset of the population of cathode structures can include only one or all members of the population of cathode structures in the electrode assembly, or any number in between. For example, the subset of either anode or cathode structure populations can comprise one member or two members, or more. In one embodiment, the subset comprises at least five members. In another embodiment, the subset comprises at least 10 members. In yet another embodiment, the subset comprises at least 20 members. In yet another embodiment, the subset comprises at least 50 members. For example, in one embodiment, the subset of the population can comprise from 1 to 7 members, such as from 2 to 6 members, and even from 3 to 5 members. In yet another embodiment, the subset (of either the anode and/or cathode structure populations) can comprise a percentage of the total number of members in the electrode assembly **106**. For example, the subset can comprise at least 10% of the members (anode and/or cathode members) in the electrode assembly, such as at least 25% of the members, and even at least 50%, such as at least 75%, and even at least 90% of the members in the electrode assembly.

(46) By way of further explanation, in one embodiment, the members of the population of cathode structures **112** can be understood to exhibit a change in size, such as a change in dimension, cross-section and/or volume. For example, members of the population of cathode structure **112** may exhibit a change in the cross-sectional areas C, or width W.sub.C of each cathode structure **112** as measured in the longitudinal direction (i.e., parallel to the longitudinal axis A.sub.EA), to at least

partially accommodate an expansion/contraction of the anode structures **110**. For example, in one embodiment, the change in width $W_{sub.C}$ and/or cross-sectional area C of members of the population of cathode structures **112** may at least partially accommodate a change in width $W_{sub.A}$ and/or cross-sectional areas A of members of the population of anode structures **110**, such as a width as measured in the longitudinal direction and/or a cross-section having at least a portion of the width as a dimension thereof, which may occur due to intercalation and/or alloying or de-intercalation and de-alloying of carrier ions in the direction of travel of the carrier ions between the anode and cathode structures, which direction of travel may generally be in the longitudinal direction. That is, in a case where members of the population of anode structures **110** increase in width and/or cross-sectional area upon charging, the members of the population of cathode structures **112** may decrease in width and/or cross-sectional area upon charging, and in a case where members of the population of anode structures **110** decrease in width and/or cross-sectional area upon discharging, members of the population of the cathode structures **112** may increase in width and/or cross-sectional area upon discharging. In yet another embodiment, the change in the at least one dimension of the member of the population of cathode structures **112** upon expansion/contraction of the members of the population of anode structures **110** can be understood to generate an overall change in the cross-sectional area of the members of the population of cathode structures **112** that is inversely related to a change in the cross-sectional areas of the members of the population of anode structures. That is, in a case where members of the population of the anode structures **110** increase in cross-sectional area upon charging, members of the population of cathode structures **112** may decrease in cross-sectional area upon charging, and in a case where members of the population of anode structures **110** decrease in cross-sectional area upon discharging, members of the population of cathode structures **112** may increase in cross-sectional area upon discharging. In yet another embodiment, the change in the at least one dimension of members of the population of cathode structures **112** upon expansion/contraction of members of the population of anode structures **110** can be understood to generate an overall change in volume of the cathode structures **112** that is inversely related to a change in volume of members of the population of anode structures. That is, in a case where members of the population of anode structures **110** increase in volume upon charging, members of the population of cathode structures **112** may decrease in volume upon charging, and in a case where members of the population of anode structures **110** decrease in volume upon discharging, members of the population of cathode structures **112** may increase in volume upon discharging.

(47) Furthermore, in one embodiment, a sign of the change in the at least one dimension (e.g., the width), cross-section and/or volume of members of the population of cathode structures **112** is the opposite of that of a sign of the change in the at least one dimension, cross-section and/or volume of members of the population of anode structures **110**, such that the change in sizes are inversely related to each other. For example, for a member of the population of anode structures **110** that increases in width upon charging of the secondary battery **102**, a sign for the change in width would be the sign of the number resulting from subtraction of the initial width $W_{sub.I}$ from the final width $W_{sub.F}$, ($W_{sub.F} - W_{sub.I} = +\Delta W$), which is a positive number with a positive sign (+) since $W_{sub.F}$ of the anode structure is greater than $W_{sub.I}$. Conversely, for a member of the population of cathode structures **112** that decreases in width upon charging of the secondary battery **102**, a sign for the width change would be $W_{sub.F} - W_{sub.I} = -\Delta W$, which is a negative number with a negative sign (-) since $W_{sub.F}$ for the cathode structure is smaller than $W_{sub.I}$. However, it should be noted that the absolute value of the magnitude of ΔW of the anode structure is not necessarily the same as the absolute value of the magnitude of ΔW for the cathode structure, during charge and/or discharge. In other words, the extent of expansion of the anode structure during charging does not have to equal the extent of contraction of the cathode structure. For example, other structures in the secondary battery may at least partially accommodate the expansion of the anode structure, such that the compression of the cathode structure is less than what might

otherwise be expected if the cathode structure were to compress to an extent to completely accommodate the full extent of the anode structure expansion. The same may be true of discharging, where an extent of expansion of the cathode structure may be of a different magnitude than the extent of contraction of the anode structure during the discharge process. Thus, in a case where a member of the population of anode structures **110** exhibits a change in width, cross-section and/or volume that has a positive sign (e.g., the width increases), the change in width, cross-section and/or volume of a member of the population of cathode structures **112** may be inversely related thereto (although possibly of a different magnitude), and thus has a negative sign. Conversely, in a case where a member of the population of anode structures exhibits a change in width, cross-section and/or volume that has a negative sign (e.g., the width decreases), the change in width, cross-section and/or volume of a member of the population of cathode structures **112** may be inversely related thereto (although possibly of a different magnitude), and thus has a positive sign. By providing members of the population of cathode structures that are capable of changing in at least one dimension, such as the width, cross-section and/or volume in relation to an expansion and/or contraction of members of the population of anode structures, the strain on the electrode assembly **106** that can otherwise be caused by repeated expansion and contraction over multiple cycles of the secondary battery can be reduced, thereby improving the lifetime and performance of the secondary battery **102**.

(48) By way of further explanation, referring to FIGS. 2A-2C, an embodiment is shown of an electrode assembly **106** having members of the population of cathode structures **110** that change size (e.g., width, cross-sectional area and/or volume) in relation to expansion/contraction of members of the population of anode structures **112**, in both a charged state (FIGS. 2A and 2C) and in a discharged state (FIG. 2B). In FIG. 2A showing a charged state for the secondary battery **102**, the members of the population of anode structure **110** have a cross-sectional area $A_{sub.1}$ with width $W_{sub.A1}$, and members of the population of cathode structure **112** have a cross-sectional area $C_{sub.1}$ with width $W_{sub.C1}$. However, when the secondary battery **102** is discharged to the discharged state shown in FIG. 2B, the width of members of the population of anode structures **110** decreases to provide cross-sectional area $A_{sub.2}$ and width $W_{sub.A2}$, while the width of members of the population of cathode structure **112** increases to provide cross-sectional area $C_{sub.2}$ and width $W_{sub.C2}$, where $A_{sub.2} < A_{sub.1}$ and $C_{sub.2} > C_{sub.1}$, and $W_{sub.A2} < W_{sub.A1}$ and $W_{sub.C2} > W_{sub.C1}$. That is, the change in size of members of the population of cathode structures **112** may be inversely related to that of members of the population of anode structures **110**, because the cathode structure population members increase in cross-sectional area and/or width, while the anode structure population members decrease in cross-sectional area and/or width, when the secondary battery is discharged (the direction of the change in width is depicted schematically by the arrows in FIG. 2B). When the secondary battery **102** is charged up from the discharged state shown in FIG. 2B to a subsequent charged state shown in FIG. 2C, members of the population of anode and cathode structures **110**, **112** exhibit a further change in cross-sectional area and/or width, with cross-sectional area of the members of the population of anode structures increasing to $A_{sub.3}$, where $A_{sub.3} < A_{sub.2}$, and the width of the members of the population of anode structures increasing to $W_{sub.A3}$, where $W_{sub.A3} > W_{sub.A2}$, and the cross-sectional area of members of the population of cathode structures decreasing to $C_{sub.3}$, where $C_{sub.3} < C_{sub.2}$, and the width of members of the population of cathode structures decreasing to $W_{sub.C3}$, where $W_{sub.C3} < W_{sub.C2}$. While in some embodiments the cross-sectional area $A_{sub.3}$ and/or width $W_{sub.A3}$ of the members of the population of anode structures **110** in the subsequent charged state depicted in FIG. 2C may be the same as the corresponding cross-sectional area $A_{sub.1}$ and/or width $W_{sub.A1}$ of the members of the population of anode structures **110** in the initial charged state shown in FIG. 2A, it is also possible that the cross-sectional area $A_{sub.3}$ and/or width $W_{sub.A3}$ of members of the population of anode structures **110** in a subsequent charged state may be increased over the cross-sectional area $A_{sub.1}$ and/or width $W_{sub.A1}$ of members of the

population of anode structure **110** in the initial charged state. That is, in certain embodiments, the width, cross-sectional area and/or volume of members of the population of anode structures **110** in the charged state may increase over repeated cycling of the secondary battery **102** between charged and discharged states. Similarly, while the cross-sectional area $C_{sub.3}$ and/or width $W_{sub.C3}$ of members of the population of cathode structure **112** in the subsequent charged state depicted in FIG. 2C may be the same as the cross-sectional area $C_{sub.3}$ and/or width $W_{sub.C1}$ of the members of the population of cathode structures **112** in the initial charged state depicted in 3A, it is also possible that the cross-sectional area $C_{sub.3}$ and/or width $W_{sub.C3}$ of members of the population of cathode structures **112** in a subsequent charged state may be decreased over the corresponding cross-sectional area $C_{sub.3}$ and/or width $W_{sub.C1}$ of members of the population of cathode structures **112** in the initial charged state. That is, in certain embodiments, the width, cross-sectional area and/or volume of the members of the population of cathode structures **112** in the charged state may decrease over repeated cycling of the secondary battery **102** between charged and discharged states, such as to accommodate an increase in growth of members of the population of anode structures **110** that may occur over repeated cycling of the secondary battery **102**.

(49) Accordingly, in one embodiment, members of the population of cathode structures **112** have a first size, such as a first dimension and/or cross-sectional area when the secondary battery **102** is in the charged state, and have a second size, such as a second dimension and/or cross-sectional area when the secondary battery **102** is in the discharged state, with the first dimension and/or cross-sectional area being less than the second dimension and/or cross-sectional area. In yet another embodiment, the change in size, such as change in dimension and/or cross-sectional area of the cathode structures **112** may be inversely related to a change in the dimension and/or cross-sectional area of members of the population of anode structures **110**. For example, in one embodiment, at least one member of the population of cathode structures **112** may have a first cross-sectional area $C_{sub.1}$ in the charged state that is no more than $3 \times 10^{sup.7} \mu m^{sup.2}$. By way of further example, in one embodiment at least one member of the population of cathode structures may have a first cross-sectional area $C_{sub.1}$ in the charged state that is no more than $1 \times 10^{sup.7} \mu m^{sup.2}$. By way of further example, in one embodiment at least one member of the population of cathode structures may have a first cross-sectional area $C_{sub.1}$ in the charged state that is no more than $9.5 \times 10^{sup.6} \mu m^{sup.2}$. By way of yet further example, in one embodiment at least one member of the population of cathode structure may have a first cross-sectional area $C_{sub.1}$ in the charged state that is no more than $8 \times 10^{sup.6} \mu m^{sup.2}$. By way of yet further example, at least one member of population of cathode structures may have a first cross-sectional area $C_{sub.1}$ in the charged state that is no more than $5 \times 10^{sup.6} \mu m^{sup.2}$. In general, the first cross-sectional area $C_{sub.1}$ of at least one member of the population of cathode structures in the charged state may be at least $2 \times 10^{sup.2} \mu m^{sup.2}$, for example the first cross-sectional area $C_{sub.1}$ in the charged state may be at least $2.5 \times 10^{sup.2} \mu m^{sup.2}$, and even at least $3 \times 10^{sup.2} \mu m^{sup.2}$. For example, the first cross-sectional area $C_{sub.1}$ may be in the range of from $2 \times 10^{sup.2} \mu m^{sup.2}$ to $3 \times 10^{sup.7} \mu m^{sup.2}$, such as from $2.5 \times 10^{sup.2} \mu m^{sup.2}$ to $9.5 \times 10^{sup.6} \mu m^{sup.2}$, and even in the range of from $3 \times 10^{sup.2} \mu m^{sup.2}$ to $8 \times 10^{sup.6} \mu m^{sup.2}$.

(50) Furthermore, in one embodiment, at least one member of the population of cathode structures have a second cross-sectional area $C_{sub.2}$ in the discharged state that is at least $1.01 \times 10^{sup.2} \mu m^{sup.2}$. By way of further example, in one embodiment at least one member of the population of cathode structures may have a second cross-sectional area $C_{sub.2}$ in the discharged state that is at least $1.05 \times 10^{sup.2} \mu m^{sup.2}$. By way of further example, in one embodiment at least one member of the population of cathode structures may have a second cross-sectional area $C_{sub.2}$ in the discharged state that is at least $1.0 \times 10^{sup.3} \mu m^{sup.2}$. By way of further example, in one embodiment at least one member of the population of cathode structures may have a second cross-sectional area $C_{sub.2}$ in the discharged state that is at least $1.05 \times 10^{sup.3} \mu m^{sup.2}$. By way of further example, in one embodiment at least one member of the population of cathode structures

may have a second cross-sectional area C.sub.2 in the discharged state that is at least $1.1 \times 10^{10.3} \mu\text{m}^2$. In general, the second cross-sectional area C.sub.2 of at least one member of the population of cathode structures in the charged state will not exceed $1.5 \times 10^{10.10}$, for example the second cross-sectional area C.sub.2 in the discharged state may not exceed $1 \times 10^{10.7} \mu\text{m}^2$, and even may not exceed $1 \times 10^{10.6} \mu\text{m}^2$. For example, the second cross-sectional area C.sub.2 may be in the range of from $1.01 \times 10^{10.2} \mu\text{m}^2$ to $1.5 \times 10^{10.10} \mu\text{m}^2$, such as from $1.0 \times 10^{10.3} \mu\text{m}^2$ to $1.0 \times 10^{10.7} \mu\text{m}^2$, and even in the range of from $1.05 \times 10^{10.2} \mu\text{m}^2$ to $1 \times 10^{10.6} \mu\text{m}^2$.

(51) In yet another embodiment, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** in the discharged state to a first cross-sectional area C.sub.1 of the cathode structure **112** in the charged state that is at least 1.05:1. By way of further example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that is at least 1.1:1. By way of further example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that is at least 1.3:1. By way of further example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that is at least 2:1. By way of further example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that is at least 3:1. By way of further example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that is at least 4:1. By way of further example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that is at least 6:1. Generally, the ratio of the second cross-sectional area C.sub.2 to the first cross-sectional area C.sub.1 will not exceed about 15:1, and will even not exceed 10:1, such as for example not exceeding 8:1. For example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that may be in the range of from 1.05:1 to 15:1. By way of further example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that may be in the range of from 1.1:1 to 6:1. By way of further example, in one embodiment at least one member of the population of cathode structures has a ratio of the second cross-sectional area C.sub.2 of the cathode structure **112** to the first cross-sectional area C.sub.1 of the cathode structure **112** that may be in the range of from 1.3:1 to 4:1. Furthermore, in one embodiment, the contraction of first cross-sectional area C.sub.1 with respect to the second cross-sectional area C.sub.2 is in the range of from 2% contraction to 90% contraction, such as from 5% contraction to 75% contraction. That is, the first cross-sectional area C.sub.1 may be contracted by at least 2% with respect to C.sub.2, such as at least 5% and even at least 10% with respect to C.sub.2, but may be contracted less than 90% with respect to C.sub.2, such as less than 80% and even less than 75% with respect to C.sub.2.

(52) Furthermore, in one embodiment, at least one member of the population of anode structures **110** may have a first cross-sectional area A.sub.1 in the charged state that is at least $100 \mu\text{m}^2$. By way of further example, in one embodiment at least one member of the population of anode structures may have a first cross-sectional area A.sub.1 in the charged state that is at least

$1 \times 10^{3.3} \mu\text{m}^2$. By way of yet further example, in one embodiment at least one member of the population of anode structures may have a first cross-sectional area $A_{\text{sub.1}}$ in the charged state that is at least $4.5 \times 10^{3.3} \mu\text{m}^2$. By way of yet further example, at least one member of population of anode structures may have a first cross-sectional area $A_{\text{sub.1}}$ in the charged state that is at least $6 \times 10^{3.3} \mu\text{m}^2$. By way of further example, in one embodiment at least one member of the population of anode structures may have a first cross-sectional area $A_{\text{sub.1}}$ in the charged state that is at least $8 \times 10^{3.3} \mu\text{m}^2$. In general, the first cross-sectional area $A_{\text{sub.1}}$ of at least one member of the population of anode structures in the charged state may not exceed $1.5 \times 10^{3.7} \mu\text{m}^2$, for example the first cross-sectional area $A_{\text{sub.1}}$ in the charged state may not exceed $7.6 \times 10^{3.6} \mu\text{m}^2$, and may even not exceed $5 \times 10^{3.6} \mu\text{m}^2$. For example, the first cross-sectional area $A_{\text{sub.1}}$ may be in the range of from $100 \mu\text{m}^2$ to $1.5 \times 10^{3.7} \mu\text{m}^2$, such as from $4.5 \times 10^{3.3} \mu\text{m}^2$ to $7.6 \times 10^{3.6} \mu\text{m}^2$, and even in the range of from $6 \times 10^{3.3} \mu\text{m}^2$ to $5 \times 10^{3.6} \mu\text{m}^2$.

(53) Furthermore, in one embodiment, at least one member of the population of anode structures have a second cross-sectional area $A_{\text{sub.2}}$ in the discharged state that is no more than $3 \times 10^{3.7} \mu\text{m}^2$. By way of further example, in one embodiment at least one member of the population of anode structures may have a second cross-sectional area $A_{\text{sub.2}}$ in the discharged state that is no more than $1.5 \times 10^{3.7} \mu\text{m}^2$. By way of further example, in one embodiment at least one member of the population of anode structures may have a second cross-sectional area $A_{\text{sub.2}}$ in the discharged state that is no more than $7.5 \times 10^{3.6} \mu\text{m}^2$. By way of further example, in one embodiment at least one member of the population of anode structures may have a second cross-sectional area $A_{\text{sub.2}}$ in the discharged state that is no more than $5 \times 10^{3.6} \mu\text{m}^2$. By way of further example, in one embodiment at least one member of the population of anode structures may have a second cross-sectional area $A_{\text{sub.2}}$ in the discharged state that is no more than $3 \times 10^{3.6} \mu\text{m}^2$. In general, the second cross-sectional area $A_{\text{sub.2}}$ of at least one member of the population of anode structures in the charged state will be at least $500 \mu\text{m}^2$, for example the second cross-sectional area $A_{\text{sub.2}}$ in the discharged state may be at least $1.5 \times 10^{3.3}$, and even at least $3 \times 10^{3.3} \mu\text{m}^2$. For example, the second cross-sectional area $A_{\text{sub.2}}$ may be in the range of from $500 \mu\text{m}^2$ to $3 \times 10^{3.7} \mu\text{m}^2$, such as from $1.5 \times 10^{3.3} \mu\text{m}^2$ to $7.5 \times 10^{3.6} \mu\text{m}^2$, and even in the range of from $3 \times 10^{3.3} \mu\text{m}^2$ to $5 \times 10^{3.6} \mu\text{m}^2$.

(54) In yet another embodiment, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area $A_{\text{sub.1}}$ of the anode structure **110** in the charged state to a second cross-sectional area $A_{\text{sub.2}}$ of the anode structure **110** in the discharged state that is at least 1.01:1. By way of further example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area $A_{\text{sub.1}}$ of the anode structure **110** to the second cross-sectional area $A_{\text{sub.2}}$ of the anode structure **110** that is at least 1.05:1. By way of further example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area $A_{\text{sub.1}}$ of the anode structure **110** to the second cross-sectional area $A_{\text{sub.2}}$ of the anode structure **110** that is at least 1.5:1. By way of further example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area $A_{\text{sub.1}}$ of the anode structure **110** to the second cross-sectional area $A_{\text{sub.2}}$ of the anode structure **110** that is at least 2:1. By way of further example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area $A_{\text{sub.1}}$ of the anode structure **110** to the second cross-sectional area $A_{\text{sub.2}}$ of the anode structure **110** that is at least 3:1. By way of further example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area $A_{\text{sub.1}}$ of the anode structure **110** to the second cross-sectional area $A_{\text{sub.2}}$ of the anode structure **110** that is at least 4:1. By way of further example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area $A_{\text{sub.1}}$ of the anode

structure **110** to the second cross-sectional area A.sub.2 of the anode structure **110** that is at least 5:1. For example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area A.sub.1 of the anode structure **110** to the second cross-sectional area A.sub.2 of the anode structure **110** that may be in the range of from 1.01:1 to 5:1. By way of further example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area A.sub.1 of the anode structure **110** to the second cross-sectional area A.sub.2 of the anode structure **110** that may be in the range of from 1.01 to 4:1. By way of further example, in one embodiment at least one member of the population of anode structures has a ratio of the first cross-sectional area A.sub.1 of the anode structure **110** to the second cross-sectional area A.sub.2 of the anode structure **110** that may be in the range of from 1.01:1 to 3:1, and even in the range of from 1.5:1 to 3:1.

(55) In one embodiment, a subset of the anode structure population has a median cross-sectional area, as measured either according to MA.sub.A, which as used herein refers to a median of cross-sectional areas for more than one anode member, and/or according to ML.sub.A, which as used herein refers to a median of cross-sectional areas at different longitudinal planes long an anode member, and/or according to MO.sub.A, which are used herein refers to a median of MA.sub.A and ML.sub.A. Furthermore, a subset of the cathode structure population has a median cross-sectional area, as measured either according to MA.sub.C, which as used herein refers to a median of cross-sectional areas for more than one cathode member, and/or according to ML.sub.C, which as used herein refers to a median of cross-sectional areas at different longitudinal planes long a cathode member, and/or according to MO.sub.C, which are used herein refers to a median of MA.sub.C and ML.sub.C. Further description of these measures are as follows.

(56) According to one embodiment, a subset of the anode structure population has a median cross-sectional area MA.sub.A, and a subset of the cathode structure population has a median cross-sectional area MA.sub.C, where MA.sub.A and MA.sub.C are the medians of the cross-sectional areas A and C for members of the population of anode structures and cathode structures respectively, as measured across a subset of the anode and/or cathode structure population. That is, MA.sub.A can be understood as the median cross-section as measured in the first longitudinal plane **113** for a subset of members of the population of anode structures, and MA.sub.C can be understood as the median cross-section as measured in the first longitudinal plane **113** for a subset of members of the population of cathode structures. That is, to determine the median cross-sectional area MA.sub.A for the subset, the cross-sectional areas are determined for each member of the anode structure population in the subset, and then the median of the cross-sectional areas are evaluated. Similarly, to determine the median cross-sectional area MA.sub.C for the subset, the cross-sectional areas are determined for each member of the cathode structure population in the subset, and then the median of the cross-sectional areas are evaluated. In one embodiment, the median of the cross-sectional areas as measured in the first longitudinal plane are determined for a subset comprising at least two members. In another embodiment, the median of the cross-sectional areas as measured in the first longitudinal plane are determined for a subset comprising at least five members. In another embodiment, the median of the cross-sectional areas as measured in the first longitudinal plane are determined for a subset comprising at least ten members. In another embodiment, the median of the cross-sectional areas as measured in the first longitudinal plane are determined for a subset comprising at least 20 members. In another embodiment, the median of the cross-sectional areas as measured in the first longitudinal plane are determined for a subset comprising at least 50 members. For example, in one embodiment, the subset of the population can comprise from 1 to 7 members, such as from 2 to 6 members, and even from 3 to 5 members. In yet another embodiment, the subset of the population can comprise a percentage of the total number of members in the electrode assembly **106**. For example, the subset can comprise at least 10% of the members in the electrode assembly, such as at least 25% of the members, and even at least 50%, such as at least 75%, and even at least 90% of the members in the electrode assembly.

(57) In one embodiment, the subset of the population of cathode structures **112** may have a first median cross-sectional area MA.sub.C1 in the charged state that may be the same as and/or similar to values give above for the first cross-sectional area C.sub.1 of a member of the population of cathode structures in the charged state. For example, in one embodiment, the subset of the population of cathode structures **112** may have a first median cross-sectional area MA.sub.C1 that is no more than $3 \times 10^{+7} \mu\text{m}^{+2}$. By way of further example, in one embodiment, the subset of the population of cathode structures **112** may have a first median cross-sectional area MA.sub.C1 in the charged state that is no more than $1 \times 10^{+7} \mu\text{m}^{+2}$. By way of yet further example, in one embodiment the subset of the population of cathode structures **112** may have a first median cross-sectional area MA.sub.C1 in the charged state that is no more than $9.03 \times 10^{+6} \mu\text{m}^{+2}$. By way of yet further example, in one embodiment, the subset of the population of cathode structures **112** may have a first median cross-sectional area MA.sub.C1 in the charged state that is no more than $8 \times 10^{+6} \mu\text{m}^{+2}$. By way of further example, in one embodiment the subset of the population of cathode structures **112** may have a first median cross-sectional area MA.sub.C1 in the charged state that is no more than $5 \times 10^{+6} \mu\text{m}^{+2}$. In general, the first median cross-sectional area MA.sub.C1 of the subset of the population of cathode structure may be at least $2 \times 10^2 \mu\text{m}^{+2}$, for example the first median cross-sectional area MA.sub.C1 of the subset of the population of cathode structures may be at least $2.6 \times 10^{+2} \mu\text{m}^{+2}$, for example the first median cross-sectional area MA.sub.C1 in the charged state may be at least $3 \times 10^{+2} \mu\text{m}^{+2}$. For example, the first median cross-sectional area MA.sub.C1 may be in the range of from $1 \times 10^{+2} \mu\text{m}^{+2}$ to $3 \times 10^{+7} \mu\text{m}^{+2}$, such as from $2.6 \times 10^{+2} \mu\text{m}^{+2}$ to $9.03 \times 10^{+6} \mu\text{m}^{+2}$, and even in the range of from $3 \times 10^{+2} \mu\text{m}^{+2}$ to $8 \times 10^{+6} \mu\text{m}^{+2}$.

(58) Furthermore, in one embodiment, the subset of the population of cathode structures **112** may have a second median cross-sectional area MA.sub.C2 in the discharged state that may be the same as and/or similar to values give above for the second cross-sectional area C.sub.2 of a member of the population of cathode structures in the discharged state. For example, in one embodiment, the subset of the population of cathode structures **112** may have a second median cross-sectional area MA.sub.C2 in the charged state in the discharged state that is at least $1.01 \times 10^{+2} \mu\text{m}^{+2}$. By way of further example, in one embodiment the subset of the population of cathode structures **112** may have a second median cross-sectional area MA.sub.C2 in the discharged state that is at least $1.05 \times 10^{+2} \mu\text{m}^{+2}$. By way of further example, in one embodiment the subset of the population of cathode structures **112** may have a second median cross-sectional area MA.sub.C2 in the discharged state that is at least $1.05 \times 10^{+3} \mu\text{m}^{+2}$. By way of further example, the subset of the population of cathode structures **112** may have a second median cross-sectional area MA.sub.C2 in the discharged state that is at least $1.1 \times 10^{+3} \mu\text{m}^{+2}$. By way of further example, the subset of the population of cathode structures **112** may have a second median cross-sectional area MA.sub.C2 in the discharged state that is at least $1.5 \times 10^{+3} \mu\text{m}^{+2}$. In general, the second median cross-sectional area MA.sub.C2 of the subset of the population of cathode structures in the discharged state will not exceed $1.5 \times 10^{+10} \mu\text{m}^{+2}$, for example the second median cross-sectional area MA.sub.C2 in the discharged state may not exceed $9.5 \times 10^{+6} \mu\text{m}^{+2}$, and may even not exceed $1 \times 10^{+6} \mu\text{m}^{+2}$. For example, the second median cross-sectional area MA.sub.C2 may be in the range of from $1.01 \times 10^{+2} \mu\text{m}^{+2}$ to $1.5 \times 10^{+10} \mu\text{m}^{+2}$, such as from $1.05 \times 10^{+3} \mu\text{m}^{+2}$ to $9.5 \times 10^{+6} \mu\text{m}^{+2}$, and even in the range of from $1.1 \times 10^{+2} \mu\text{m}^{+2}$ to $1 \times 10^{+6} \mu\text{m}^{+2}$.

(59) In yet another embodiment, the subset of the population of cathode structures **112** may have a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that is the same as and/or similar to the values given above for the ratio of the second cross-sectional area C.sub.2 in the discharged state to the first cross-sectional area C.sub.1 in the charged state. For example, in one embodiment the subset

of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that is at least 1.05:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that is at least 1.1:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that is at least 1.3:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that is at least 2:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that is at least 3:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that is at least 4:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that is at least 6:1. Generally, a ratio of MA.sub.C2 to MA.sub.C1 for the subset will not exceed about 15:1 and will even not exceed 10:1, such as for example not exceeding 8:1. For example, the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that may be in the range of from 1.05:1 to 15:1. By way of further example, the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that may be in the range of from 1.1:1 to 6:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MA.sub.C2 in the discharged state to a first median cross-sectional area MA.sub.C1 in the charged state that may be in the range of from 1.3:1 to 4:1. By way of further example, in one embodiment the contraction of the subset of the first median cross-sectional area MA.sub.C1 with respect to the second median cross-sectional area MA.sub.C2 may be in the range of from 2% contraction to 90% contraction, such as from 5% contraction to 75% contraction. That is, the subset of the population of cathode structures may have a first median cross-sectional area MA.sub.C1 that is contracted by at least 2% with respect to the second median cross-sectional area MA.sub.C2, such as at least 5% and even at least 10% with respect to the second median cross-sectional area MA.sub.C2, but may be contracted less than 90% with respect to the second median cross-sectional area MA.sub.C2, such as less than 80% and even less than 75% with respect to the second median cross-sectional area MA.sub.C2.

(60) Furthermore, in one embodiment, the subset of the population of anode structures **110** may have a first median cross-sectional area MA.sub.A1 in the charged state that may be the same as and/or similar to values give above for the first cross-sectional area A.sub.1 of a member of the population of anode structures in the charged state. For example, according to one embodiment, the subset of the population of anode structures **110** may have a first median cross-sectional area MA.sub.A1 in the charged state that is at least $100\ \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a first median cross-sectional area MA.sub.A1 in the charged state that is at least $1 \times 10^3\ \mu\text{m}^2$. By way of yet further example, in one embodiment the subset of the population of anode structures **110** may have a first median cross-sectional area MA.sub.A1 in the charged state that is at least $4.7 \times 10^3\ \mu\text{m}^2$. By way of yet further example, the subset of the population of anode structures **110** may

have a first median cross-sectional area MA.sub.A1 in the charged state that is at least $6 \times 10^3 \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a first median cross-sectional area MA.sub.A1 in the charged state that is at least $8 \times 10^3 \mu\text{m}^2$. In general, the first median cross-sectional area MA.sub.A1 of the subset of the population of anode structures in the charged state may not exceed $1.5 \times 10^7 \mu\text{m}^2$, for example the first median cross-sectional area MA.sub.A1 in the charged state may not exceed $6.8 \times 10^7 \mu\text{m}^2$, and may not even exceed $5 \times 10^6 \mu\text{m}^2$. For example, the first median cross-sectional area MA.sub.A1 in the charged state may be in the range of from $100 \mu\text{m}^2$ to $1.5 \times 10^7 \mu\text{m}^2$, such as from $4.7 \times 10^3 \mu\text{m}^2$ to $6.8 \times 10^6 \mu\text{m}^2$, and even in the range of from $6 \times 10^3 \mu\text{m}^2$ to $5 \times 10^6 \mu\text{m}^2$.

(61) Furthermore, in one embodiment, the subset of the population of anode structures **110** may have a second median cross-sectional area MA.sub.A2 in the discharged state that may be the same as and/or similar to values give above for the second cross-sectional area A.sub.2 of a member of the population of anode structures in the discharged state. For example, in one embodiment, the subset of the population of anode structures **110** may have a second median cross-sectional area MA.sub.A2 in the discharged state that is no more than $3 \times 10^7 \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a second median cross-sectional area MA.sub.A2 in the discharged state that is no more than $1.5 \times 10^7 \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a second median cross-sectional area MA.sub.A2 in the discharged state that is no more than $7.1 \times 10^6 \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a second median cross-sectional area MA.sub.A2 in the discharged state that is no more than $5 \times 10^6 \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a second median cross-sectional area MA.sub.A2 in the discharged state that is no more than $3 \times 10^6 \mu\text{m}^2$. In general, the second median cross-sectional area MA.sub.A2 of the subset of the population of anode structures in the charged state will be at least $1.5 \times 10^3 \mu\text{m}^2$, for example the second median cross-sectional area MA.sub.A2 in the discharged state may be at least $1.6 \times 10^3 \mu\text{m}^2$, and even at least $3 \times 10^3 \mu\text{m}^2$. For example, the second median cross-sectional area MA.sub.A2 in the discharged state may be in the range of from $500 \mu\text{m}^2$ to $3 \times 10^7 \mu\text{m}^2$, such as from $1.6 \times 10^3 \mu\text{m}^2$ to $7.1 \times 10^6 \mu\text{m}^2$, and even in the range of from $3 \times 10^3 \mu\text{m}^2$ to $5 \times 10^6 \mu\text{m}^2$.

(62) In yet another embodiment, the subset of the population of anode structures **110** may have a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that is the same as and/or similar to the values given above for the ratio of the first cross-sectional area A.sub.1 in the charged state to the second cross-sectional area A.sub.2 in the discharged state. For example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that is at least 1.01:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that is at least 1.05:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that is at least 1.5:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that is at least 2:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional

area MA.sub.A2 in the discharged state that is at least 3:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that is at least 4:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that is at least 5:1. For example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that may be the range of from 1.01:1 to 5:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that may be in the range of from 1.01 to 4:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MA.sub.A1 in the charged state to a second median cross-sectional area MA.sub.A2 in the discharged state that may be in the range of from 1.01:1 to 3:1, and even in the range of from 1.5:1 to 3:1.

(63) In yet another embodiment, the members of the population of anode structures can each be understood to have a length LA measured in the transverse direction, a width W.sub.A measured in the longitudinal direction, and a height H.sub.A measured in the vertical direction, as shown for example in FIG. 1A. Similarly, the members of the population of cathode structures can each be understood to have a length L.sub.C measured in the transverse direction, a width W.sub.C measured in the longitudinal direction, and a height H.sub.C measured in the vertical direction. The lengths LA and L.sub.C of the anode and cathode structure members, respectively, may be as measured from a bottom **115a** of each member to a top **115b**, as depicted for example in FIG. 1C, where the bottom **115a** is proximate to a plane **121** from which the member extends, and the top **115b** is distal to the plane **121**. Furthermore, in one embodiment, the length L.sub.A and/or L.sub.C of members of the population of anode and/or cathode structures may be at least 5 times each of the width and the height of the members (e.g., the length of the member may be the longer than either the width or the height). For example, a ratio of the length L (e.g., either L.sub.A or L.sub.C) of members to each of the width W (e.g., either W.sub.A or W.sub.C) and the height H (e.g., either H.sub.A or H.sub.C), may be at least 10:1, and even at least 15:1, such as at least 20:1.

(64) According to one aspect, the cross-sectional area of the at least one member of the cathode and/or anode populations is measured in a first longitudinal plane that is not only parallel to the longitudinal direction, but is also orthogonal to the direction of one or more of the direction of L.sub.A and L.sub.C. For example, referring to the embodiment in FIG. 1C, the first longitudinal plane **113** is depicted as being parallel with the stacking direction (longitudinal direction), while also being perpendicular to the length direction of the members of the anode and cathode structure populations, which is the X direction as depicted in the embodiment therein. For example, according to one embodiment, the first longitudinal plane may be in a Z-Y plane, where Y corresponds to an axis that is parallel to the longitudinal direction, and Z corresponds to an axis that is orthogonal to the longitudinal direction while also being orthogonal to the lengths L.sub.A and/or L.sub.C of the members of the population of anode structures and cathode structures, respectively. In yet another embodiment, the first longitudinal plane in which the cross-sectional area(s) are measured is in a plane that is less than 15 degrees away from the Z-Y plane as rotated along the Y axis (e.g., longitudinal axis). In yet another embodiment, the first longitudinal plane in which the cross-sectional area(s) are measured is in a plane that is less than 45 degrees away from the Z-Y plane as rotated along the Y axis (e.g., longitudinal axis). In yet another embodiment, the first longitudinal plane in which the cross-sectional area(s) are measured is in a plane that is greater than 45 degrees away from the Z-Y plane but less than 90 degrees from the Z-Y plane as rotated along the Y axis (e.g., longitudinal axis). In yet another embodiment, the first longitudinal plane is

in an X-Y plane, where the Y-axis corresponds to an axis that is parallel to the longitudinal direction, and the X-axis corresponds to an axis that is orthogonal to the longitudinal axis, and that is also parallel to the lengths L.sub.A and/or L.sub.C of the members of the population of anode structures and cathode structures, respectively. Furthermore, in one embodiment, the position of the first longitudinal plane **113** along the length L.sub.A or L.sub.C of the anodes and/or cathodes may be selected according to the measurement to be made. For example, in one embodiment, the first longitudinal plane **113** may be positioned in the Z-Y plane about half-way along the length L of the anodes and/or cathodes (e.g., about half-way along the length in the X-direction), as depicted in FIG. **1C**. In another embodiment, the first longitudinal plane may be positioned in the Z-Y plane closer to an end of one or more of the cathode and/or anode structures (e.g., closer to the base or top of the anodes and/or cathodes in the X-direction). In yet another embodiment, cross-sectional areas can be measured in a plurality of longitudinal planes **113a**, **113b** that are parallel to the longitudinal direction.

(65) According to yet another embodiment, at least one member of a subset of the anode structure population can have a median cross-sectional area ML.sub.A that is the median for the member of a plurality of cross-sectional areas A as measured in a plurality of planes parallel to the longitudinal direction for that member. Similarly, at least one member of a subset of the cathode population can have a median cross-sectional area ML.sub.C that is the median for the member of a plurality of cross-sectional areas C as measured in a plurality of planes parallel to the longitudinal direction for that member. For example, referring to FIG. **1C**, the cross-sections A for a member of the population of anode structures may be measured in a plurality of planes **113a,b** parallel to the longitudinal direction for that member, such as for example the first longitudinal plane **113** and one or more planes **113a,b**. In one embodiment, the one or more other planes **113a,b** are planes that are parallel to the first longitudinal plane **113**, and may be located at different positions along the length of the anodes (e.g., at different positions on the X-axis). The median cross-sectional area ML.sub.A may thus be calculated as the median of the cross-sections A measured in each longitudinal plane for the member of the population of anode structures. Similarly, the cross-sections C for a member of the population of cathode structures may be measured in a plurality of planes **113a,b** parallel to the longitudinal direction for that member, such as for example the first longitudinal plane **113** and one or more planes **113a,b**. In one embodiment, the one or more other planes **113a,b** are planes that are parallel to the first longitudinal plane **113**, and may be located at different positions along the length of the cathodes (e.g., at different positions on the X-axis). The median cross-sectional area ML.sub.C may thus be calculated as the median of the cross-sections C measured in each longitudinal plane for the member of the population of cathode structures.

(66) In one embodiment, the median cross-sectional areas ML.sub.A and ML.sub.C are the median cross-sectional areas of the cross-sectional areas as measured in at least two longitudinal planes for the anode and cathode structure population subsets, respectively. In one embodiment, the median cross-sectional areas ML.sub.A and ML.sub.C are the median cross-sectional areas of the cross-sectional areas as measured in at least three longitudinal planes for the anode and cathode structure population subsets, respectively. In one embodiment, the median cross-sectional areas ML.sub.A and ML.sub.C are the median cross-sectional areas of the cross-sectional areas as measured in at least five longitudinal planes for the anode and cathode structure population subsets, respectively. In one embodiment, the median cross-sectional areas ML.sub.A and ML.sub.C are the median cross-sectional areas of the cross-sectional areas as measured in at least ten longitudinal planes for the anode and cathode structure population subsets, respectively. Furthermore, in one embodiment, the median cross-sectional areas M.sub.LA and M.sub.LC may be the median of cross-sectional areas as measured in at least two longitudinal planes that are distanced apart from each other by a predetermined length. For example, in one embodiment, the median cross-sectional areas M.sub.LA and M.sub.LC are the median of cross-sectional areas as measured for a member in at least two longitudinal planes that are spaced apart from one another by at least 10% of the length

L.sub.A and/or L.sub.C of the members (e.g., spaced apart along the X-axis). As another example, in one embodiment, the median cross-sectional areas M.sub.LA and M.sub.LC are the median of cross-sectional areas as measured for a member in at least two longitudinal planes that are spaced apart from one another by at least 15% of the length L.sub.A and/or L.sub.C of the members (e.g., spaced apart along the X-axis). As another example, in one embodiment, the median cross-sectional areas M.sub.LA and M.sub.LC are the median of cross-sectional areas as measured for a member in at least two longitudinal planes that are spaced apart from one another by at least 20% of the length L.sub.A and/or L.sub.C of the members (e.g., spaced apart along the X-axis). For example, in one embodiment, the median cross-sectional areas M.sub.LA and M.sub.LC are the median of cross-sectional areas as measured for a member in at least two longitudinal planes that are spaced apart from one another by at least 25% of the length L.sub.A and/or L.sub.C of the members (e.g., spaced apart along the X-axis). As another example, in one embodiment, the median cross-sectional areas M.sub.LA and M.sub.LC are the median of cross-sectional areas as measured for a member in at least two longitudinal planes that are spaced apart from one another by at least 30% of the length L.sub.A and/or L.sub.C of the members (e.g., spaced apart along the X-axis). As another example, in one embodiment, the median cross-sectional areas M.sub.LA and M.sub.LC are the median of cross-sectional areas as measured for a member in at least two longitudinal planes that are spaced apart from one another by at least 50% of the length L.sub.A and/or L.sub.C of the members (e.g., spaced apart along the X-axis). As another example, in one embodiment, the median cross-sectional areas M.sub.LA and M.sub.LC are the median of cross-sectional areas as measured for a member in at least two longitudinal planes that are spaced apart from one another by at least 75% of the length L.sub.A and/or L.sub.C of the members (e.g., spaced apart along the X-axis).

(67) Accordingly, in one embodiment, at least one member of the anode structure population subset may have a first median cross-sectional area ML.sub.A1 when the secondary battery is in the charged state, and a second median cross-sectional area ML.sub.A2 when the secondary battery is in the discharged state, and similarly at least one member of the cathode structure population subset may have a first median cross-sectional area ML.sub.C1 when the secondary battery is in the charged state, and a second median cross-sectional area ML.sub.C2 when the secondary battery is in the discharged state, where ML.sub.A1 is greater than ML.sub.A2 for each of the members of the subset of the anode structure population, and ML.sub.C1 is less than ML.sub.C2 for each of the members of the subset of the cathode population.

(68) In one embodiment, at least one member of the subset of the population of cathode structures **112** may have a first median cross-sectional area ML.sub.C1 in the charged state that may be the same as and/or similar to values given above for the first cross-sectional area C.sub.1 of a member of the population of cathode structures in the charged state. For example, in one embodiment, the at least one member of the subset of the population of cathode structures **112** may have a first median cross-sectional area ML.sub.C1 in the charged state that is no more than $3 \times 10^{+7} \mu\text{m}^{+2}$. By way of further example, in one embodiment, the at least one member of the subset of the population of cathode structures **112** may have a first median cross-sectional area ML.sub.C1 in the charged state that is no more than $1 \times 10^{+7} \mu\text{m}^{+2}$. By way of yet further example, in one embodiment the at least one member of the subset of the population of cathode structures **112** may have a first median cross-sectional area ML.sub.C1 in the charged state that is no more than $9.03 \times 10^{+6} \mu\text{m}^{+2}$. By way of yet further example, in one embodiment, the at least one member of the subset of the population of cathode structures **112** may have a first median cross-sectional area ML.sub.C1 in the charged state that no more than $8 \times 10^{+6} \mu\text{m}^{+2}$. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures **112** may have a first median cross-sectional area ML.sub.C1 in the charged state that is no more than $5 \times 10^{+6} \mu\text{m}^{+2}$. In general, the first median cross-sectional area ML.sub.C1 of the at least one member of the subset of the population of cathode structures may be at least $2 \times 10^{+2} \mu\text{m}^{+2}$, for example the first median cross-sectional area ML.sub.C1 in the

charged state may be at least $2.6 \times 10^{+2} \mu\text{m}^2$, and even at least $3 \times 10^{+2} \mu\text{m}^2$. For example, the first median cross-sectional area ML.sub.C1 in the charged state may be in the range of from $1 \times 10^{+2} \mu\text{m}^2$ to $3 \times 10^{+7} \mu\text{m}^2$, such as from $2.6 \times 10^{+2} \mu\text{m}^2$ to $9.03 \times 10^{+6} \mu\text{m}^2$, and even in the range of from $3 \times 10^{+2} \mu\text{m}^2$ to $8 \times 10^{+6} \mu\text{m}^2$.

(69) Furthermore, in one embodiment, at least one member of the subset of the population of cathode structures **112** may have a second median cross-sectional area ML.sub.C2 in the discharged state that may be the same as and/or similar to values give above for the second cross-sectional area C.sub.2 of a member of the population of cathode structures in the discharged state. For example, in one embodiment, at least one member of the subset of the population of cathode structures **112** may have a second median cross-sectional area ML.sub.C2 in the discharged state that is at least $1.01 \times 10^{+2} \mu\text{m}^2$. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures **112** may have a second median cross-sectional area ML.sub.C2 in the discharged state that is at least $1.05 \times 10^{+2} \mu\text{m}^2$. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures **112** may have a second median cross-sectional area ML.sub.C2 in the discharged state that is at least $1.05 \times 10^{+3} \mu\text{m}^2$. By way of further example, the at least one member of the subset of the population of cathode structures **112** may have a second median cross-sectional area ML.sub.C2 in the discharged state that is at least $1.1 \times 10^{+3} \mu\text{m}^2$. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures **112** may have a second median cross-sectional area ML.sub.C2 in the discharged state that is at least $1.5 \times 10^{+3} \mu\text{m}^2$. In general, the second median cross-sectional area ML.sub.C2 of the at least one member of the subset of the population of cathode structures in the discharged state will not exceed $1.5 \times 10^{+10} \mu\text{m}^2$, for example the second median cross-sectional area MA.sub.C2 in the discharged state of the at least one member may not exceed $9.5 \times 10^{+6} \mu\text{m}^2$, and even may not exceed $1 \times 10^{+6} \mu\text{m}^2$. For example, the second median cross-sectional area ML.sub.C2 may be in the range of from $1.01 \times 10^{+2} \mu\text{m}^2$ to $1.5 \times 10^{+10} \mu\text{m}^2$, such as from $1.05 \times 10^{+3} \mu\text{m}^2$ to $9.5 \times 10^{+6} \mu\text{m}^2$, and even in the range of from $1.1 \times 10^{+2} \mu\text{m}^2$ to $1 \times 10^{+6} \mu\text{m}^2$.

(70) In yet another embodiment, at least one member of the subset of the population of cathode structures **112** may have a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that is the same as and/or similar to the values given above for the ratio of the second cross-sectional area C.sub.2 in the discharged state to the first cross-sectional area C.sub.1 in the charged state. For example, in one embodiment at least one member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that is at least 1.05:1. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that is at least 1.1:1. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that is at least 1.3:1. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that is at least 2:1. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that is at least 3:1. By way of further example, in one embodiment the at least one

member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that is at least 4:1. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that is at least 6:1. Generally, the ratio of the second median cross-sectional area ML.sub.C2 to the first median cross-sectional area ML.sub.C1 will not exceed about 15:1, and even will not exceed 10:1, such as for example may not exceed 8:1. For example, the at least one member of the subset of the population of cathode structures may have a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that may be in the range of from 1.05:1 to 15:1. By way of further example, the at least one member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that may be in the range of from 1.1:1 to 6:1. By way of further example, in one embodiment the at least one member of the subset of the population of cathode structures has a ratio of the second median cross-sectional area ML.sub.C2 in the discharged state to a first median cross-sectional area ML.sub.C1 in the charged state that may be in the range of from 1.3:1 to 4:1. Furthermore, in one embodiment, the contraction of the first median cross-sectional area ML.sub.C1 with respect to the second median cross-sectional area ML.sub.C2 may be in the range of from 2% contraction to 90% contraction, such as from 5% contraction to 75% contraction, and even from 10% contraction to 70% contraction. That is, the first median cross-sectional area ML.sub.C1 may be contracted by at least 2% with respect to the median cross-sectional area ML.sub.C2, such as at least 5% and even at least 10%, with respect to ML.sub.C2, but may be contracted less than 90% with respect to ML.sub.C2, such as less than 80% and even less than 75% with respect to ML.sub.C2, such as less than 70% with respect to ML.sub.C2.

(71) Furthermore, in one embodiment, at least one member of the subset of the population of anode structures **110** may have a first median cross-sectional area ML.sub.A1 in the charged state that may be the same as and/or similar to values give above for the first cross-sectional area A.sub.1 of a member of the population of anode structures in the charged state. For example, in one embodiment, the at least one member of the subset of the population of anode structures **110** may have a first median cross-sectional area ML.sub.A1 in the charged state that is at least 100 $\mu\text{m}.\text{sup}.2$. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures **110** may have a first median cross-sectional area ML.sub.A1 in the charged state that is at least $1 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$. By way of yet further example, in one embodiment the at least one member of the subset of the population of anode structures **110** may have a first median cross-sectional area ML.sub.A1 in the charged state that is at least $4.7 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$. By way of yet further example, the at least one member of the subset of the population of anode structures **110** may have a first median cross-sectional area ML.sub.A1 in the charged state that is at least $6 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures **110** may have a first median cross-sectional area ML.sub.A1 in the charged state that is at least $8 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$. In general, the first median cross-sectional area ML.sub.A1 of the at least one member of the subset of the population of anode structures in the charged state may not exceed $1.5 \times 10.\text{sup}.7 \mu\text{m}.\text{sup}.2$, for example the first median cross-sectional area ML.sub.A1 in the charged state of the at least one member may not exceed $6.8 \times 10.\text{sup}.7 \mu\text{m}.\text{sup}.2$, and may not even exceed $5 \times 10.\text{sup}.6 \mu\text{m}.\text{sup}.2$. For example, the first median cross-sectional area ML.sub.A1 of the at least one member of the subset of the population of anode structures may be in the range of from 100 $\mu\text{m}.\text{sup}.2$ to $1.5 \times 10.\text{sup}.7 \mu\text{m}.\text{sup}.2$, such as from $4.7 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$ to $6.8 \times 10.\text{sup}.6 \mu\text{m}.\text{sup}.2$, and even in the range of from $6 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$ to $5 \times 10.\text{sup}.6 \mu\text{m}.\text{sup}.2$.

(72) Furthermore, in one embodiment, at least one member of the subset of the population of anode structures **110** may have a second median cross-sectional area ML.sub.A2 in the discharged state that may be the same as and/or similar to values given above for the first cross-sectional area A.sub.2 of a member of the population of anode structures in the charged state. For example, the at least one member of the subset of the population of anode structures **110** may have a second median cross-sectional area ML.sub.A2 in the discharged state that is not more than $3 \times 10^{7.7} \mu\text{m}^2$. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures **110** may have a second median cross-sectional area ML.sub.A2 in the discharged state that is not more than $1.5 \times 10^{7.7} \mu\text{m}^2$. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures **110** may have a second median cross-sectional area ML.sub.A2 in the discharged state that is not more than $7.1 \times 10^{6.6} \mu\text{m}^2$. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures **110** may have a second median cross-sectional area ML.sub.A2 in the discharged state that is not more than $5 \times 10^{6.6} \mu\text{m}^2$. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures **110** may have a second median cross-sectional area ML.sub.A2 in the discharged state that is not more than $3 \times 10^{6.6} \mu\text{m}^2$. In general, the second median cross-sectional area ML.sub.A2 of the at least one member of the subset of the population of anode structures in the charged state will be at least $1.5 \times 10^{3.3} \mu\text{m}^2$, for example the second median cross-sectional area ML.sub.A2 of the at least one member in the discharged state may be at least $1.6 \times 10^{3.3} \mu\text{m}^2$, and even at least $3 \times 10^{3.3} \mu\text{m}^2$. For example, the second median cross-sectional area ML.sub.A2 in the discharged state may be in the range of from $500 \mu\text{m}^2$ to $3 \times 10^{7.7} \mu\text{m}^2$, such as from $1.6 \times 10^{3.3} \mu\text{m}^2$ to $7.1 \times 10^{6.6} \mu\text{m}^2$, and even in the range of from $3 \times 10^{3.3} \mu\text{m}^2$ to $5 \times 10^{6.6} \mu\text{m}^2$.

(73) In yet another embodiment, at least one member of the subset of the population of anode structures **110** may have a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that is the same as and/or similar to the values given above for the ratio of the first cross-sectional area A.sub.1 in the charged state to the second cross-sectional area A.sub.2 in the discharged state. For example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that is at least 1.01:1. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that is at least 1.05:1. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that is at least 1.5:1. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that is at least 2:1. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that is at least 3:1. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that is at least 4:1. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that is

at least 5:1. For example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that may be the range of from 1.01:1 to 5:1. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that may be in the range of from 1.01:1 to 4:1. By way of further example, in one embodiment the at least one member of the subset of the population of anode structures has a ratio of the first median cross-sectional area ML.sub.A1 in the charged state to a second median cross-sectional area ML.sub.A2 in the discharged state that may be in the range of from 1.01:1 to 3:1, and even in the range of from 1.5:1 to 3:1.

(74) According to yet another embodiment, a median cross-sectional area MO.sub.A and/or MO.sub.C can be measured for a subset of the anode structure population and/or cathode structure population, respectively, by evaluating the median of the cross-sectional areas as measured in a plurality of longitudinal planes for each member (e.g., the ML.sub.A and/or ML.sub.C), and then taking the median of this value as measured for a subset, such as at least two members, of the anode structure population or the cathode structure population. That is, the MO.sub.A and/or MO.sub.C may be understood as an “overall” median of the cross-sectional areas as measured in a plurality of longitudinal planes, and across multiple anodes and/or cathodes. The subset of the anodes and/or cathodes across which the median is evaluated to obtain the MO.sub.A and/or MO.sub.C may correspond to any of the subsets described above. Similarly to the MA.sub.A, ML.sub.A, MA.sub.C and ML.sub.C values above, a subset of the population of anode structures has a first median cross-sectional area MO.sub.A1 when the secondary battery is in a charged state, and a second median cross-sectional area MO.sub.A2 when the secondary battery is in the discharged state, and a subset of the population of cathode structures has a first median cross-sectional area MO.sub.C1 when the secondary battery is in a charged state, and a second median cross-sectional area MO.sub.C2 when the secondary battery is in the discharged state, where MO.sub.A1 is greater than MO.sub.A2, and MO.sub.C1 is less than MO.sub.C2.

(75) In one embodiment, the subset of the population of cathode structures **112** may have a first median cross-sectional area MO.sub.C1 in the charged state that may be the same as and/or similar to values given above for the first cross-sectional area C.sub.1 of a member of the population of cathode structures in the charged state. For example, in one embodiment, the subset of the population of cathode structures **112** may have a first median cross-sectional area MO.sub.C1 in the charged state that is not more than $3 \times 10^{+7} \mu\text{m}^2$. By way of further example, in one embodiment, the subset of the population of cathode structures **112** may have a first median cross-sectional area MO.sub.C1 in the charged state that is not more than $1 \times 10^{+7} \mu\text{m}^2$. By way of yet further example, in one embodiment the subset of the population of cathode structures **112** may have a first median cross-sectional area MO.sub.C1 in the charged state that is not more than $9.3 \times 10^{+6} \mu\text{m}^2$. By way of yet further example, in one embodiment, the subset of the population of cathode structures **112** may have a first median cross-sectional area MO.sub.C1 in the charged state that is not more than $8 \times 10^{+6} \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of cathode structures **112** may have a first median cross-sectional area MO.sub.C1 in the charged state that is not more than $5 \times 10^{+6} \mu\text{m}^2$. In general, the first median cross-sectional area MO.sub.C1 of the subset of the population of cathode structures may be at least $2.0 \times 10^{+6} \mu\text{m}^2$, for example the first median cross-sectional area MO.sub.C1 in the charged state may be at least $2.6 \times 10^{+2} \mu\text{m}^2$, and even at least $5 \times 10^{+2} \mu\text{m}^2$. For example, the first median cross-sectional area MO.sub.C1 of the subset of the population of cathode structures may be in the range of from $1 \times 10^{+2} \mu\text{m}^2$ to $3 \times 10^{+7} \mu\text{m}^2$, such as from $2.6 \times 10^{+2} \mu\text{m}^2$ to $9.03 \times 10^{+6} \mu\text{m}^2$, and even in the range of from $3 \times 10^{+2} \mu\text{m}^2$ to $8 \times 10^{+6} \mu\text{m}^2$.

(76) Furthermore, in one embodiment, the subset of the population of cathode structures **112** may have a second median cross-sectional area MO.sub.C2 in the discharged state that may be the same as and/or similar to values give above for the second cross-sectional area C.sub.2 of a member of the population of cathode structures in the discharged state. For example, in one embodiment, the subset of the population of cathode structures **112** may have a second median cross-sectional area MO.sub.C2 in the charged state in the discharged state that is at least $1.01 \times 10^2 \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of cathode structures **112** may have a second median cross-sectional area MO.sub.C2 in the discharged state that is at least $1.05 \times 10^2 \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of cathode structures **112** may have a second median cross-sectional area MO.sub.C2 in the discharged state that is at least $1.05 \times 10^3 \mu\text{m}^2$. By way of further example, the subset of the population of cathode structures **112** may have a second median cross-sectional area MO.sub.C2 in the discharged state that is at least $1.1 \times 10^3 \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of cathode structures **112** may have a second median cross-sectional area MO.sub.C2 in the discharged state that is at least $1.5 \times 10^3 \mu\text{m}^2$. In general, the second median cross-sectional area MO.sub.C2 of the subset of the population of cathode structures in the discharged state will not exceed $1.5 \times 10^{10} \mu\text{m}^2$, for example the second median cross-sectional area MO.sub.C2 in the discharged state may not exceed $9.5 \times 10^6 \mu\text{m}^2$, and may even not exceed $1 \times 10^6 \mu\text{m}^2$. For example, the second median cross-sectional area MO.sub.C2 of the subset of the population of cathode structures in the discharged state may be in the range of from $1.01 \times 10^2 \mu\text{m}^2$ to $1.5 \times 10^{10} \mu\text{m}^2$, such as from $1.05 \times 10^3 \mu\text{m}^2$ to $9.5 \times 10^6 \mu\text{m}^2$, and even in the range of from $1.1 \times 10^2 \mu\text{m}^2$ to $1 \times 10^6 \mu\text{m}^2$.

(77) In yet another embodiment, in one embodiment the subset of the population of cathode structures **112** may have a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that may be the same as and/or similar to values give above for the ratio of the second cross-sectional area C.sub.2 of a member of the population of cathode structures in the discharged state to the first cross-sectional area C1 of the member of the population of cathode structures in the charged state. For example, in one embodiment, the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that is at least 1.05:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that is at least 1.1:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that is at least 1.3:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that is at least 2:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that is at least 3:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that is at least 4:1. By way of further example, in one embodiment the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that is at least 6:1. Generally, the ratio of the second median cross-sectional area MO.sub.C2 to the first median cross-sectional

area MO.sub.C1 will not exceed about 15:1, and will not even exceed 10:1, and may not exceed for example 8:1. For example, the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that may be in the range of from 1.05:1 to 6:1. By way of further example, the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that may be in the range of from 1.1:1 to 4:1. By way of further example, the subset of the population of cathode structures has a ratio of the second median cross-sectional area MO.sub.C2 in the discharged state to a first median cross-sectional area MO.sub.C1 in the charged state that may be in the range of from 1.3:1 to 4:1. Furthermore, in one embodiment, the contraction of the first median cross-sectional area MO.sub.C1 with respect to the second median cross-sectional area MO.sub.C2 may be in the range of from 2% contraction to 90% contraction, such as from 5% contraction to 75% contraction, and even from 10% contraction to 70% contraction. That is, the first median cross-sectional area MO.sub.C1 may be contracted by at least 2% with respect to the median cross-sectional area MO.sub.C2, such as at least 5% and even at least 10%, with respect to MO.sub.C2, but may be contracted less than 90% with respect to MO.sub.C2, such as less than 80% and even less than 75% with respect to MO.sub.C2, such as less than 70% with respect to MO.sub.C2.

(78) Furthermore, in one embodiment, the subset of the population of anode structures **110** may have a first median cross-sectional area MO.sub.A1 in the charged state that may be the same as and/or similar to values give above for the first cross-sectional area A.sub.1 of a member of the population of anode structures in the charged state. For example, in one embodiment, the subset of the population of anode structures **110** may have a first median cross-sectional area MO.sub.A1 in the charged state that is greater than 100. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a first median cross-sectional area MO.sub.A1 in the charged state that is at least 100 $\mu\text{m}.\text{sup}.2$. By way of yet further example, in one embodiment the subset of the population of anode structures **110** may have a first median cross-sectional area MO.sub.A1 in the charged state that is at least $1 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$. By way of yet further example, the subset of the population of anode structures **110** may have a first median cross-sectional area MO.sub.A1 in the charged state that is at least $4.7 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a first median cross-sectional area MO.sub.A1 in the charged state that is at least $6 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a first median cross-sectional area MO.sub.A1 in the charged state that is at least $8 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$. In general, the first median cross-sectional area MO.sub.A1 of the subset of the population of anode structures in the charged state may not exceed $1.5 \times 10.\text{sup}.7 \mu\text{m}.\text{sup}.2$, for example the first median cross-sectional area MO.sub.A1 in the charged state may not exceed $6.8 \times 10.\text{sup}.7 \mu\text{m}.\text{sup}.2$, and may even not exceed $5 \times 10.\text{sup}.6 \mu\text{m}.\text{sup}.2$. For example, the first median cross-sectional area MO.sub.A1 in the charged state may be in the range of from 100 $\mu\text{m}.\text{sup}.2$ to $1.5 \times 10.\text{sup}.7 \mu\text{m}.\text{sup}.2$, such as from $4.7 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$ to $6.8 \times 10.\text{sup}.6 \mu\text{m}.\text{sup}.2$, and may even be in the range of from $6 \times 10.\text{sup}.3 \mu\text{m}.\text{sup}.2$ to $5 \times 10.\text{sup}.6 \mu\text{m}.\text{sup}.2$.

(79) Furthermore, in one embodiment, the subset of the population of anode structures **110** may have a second median cross-sectional area MO.sub.A2 in the discharged state that may be the same as and/or similar to values give above for the second cross-sectional area A.sub.2 of a member of the population of anode structures in the discharged state. For example, in one embodiment, the subset of the population of anode structures **110** may have a second median cross-sectional area MO.sub.A2 in the discharged state that is no more than $3.3 \times 10.\text{sup}.7 \mu\text{m}.\text{sup}.2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a second median cross-sectional area MO.sub.A2 in the discharged state that is no more than $1.5 \times 10.\text{sup}.7 \mu\text{m}.\text{sup}.2$. By way of further example, in one embodiment the subset of the

population of anode structures **110** may have a second median cross-sectional area MO.sub.A2 in the discharged state that is no more than $7.1 \times 10^{+6} \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a second median cross-sectional area MO.sub.A2 in the discharged state that is no more than $5 \times 10^{+6} \mu\text{m}^2$. By way of further example, in one embodiment the subset of the population of anode structures **110** may have a second median cross-sectional area MO.sub.A2 in the discharged state that is no more than $3 \times 10^{+6} \mu\text{m}^2$. In general, the second median cross-sectional area MO.sub.A2 of the subset of the population of anode structures in the charged state will be at least $1.5 \times 10^{+3} \mu\text{m}^2$, for example the second median cross-sectional area MO.sub.A2 in the discharged state may be at least $1.6 \times 10^{+3} \mu\text{m}^2$, and even at least $3 \times 10^{+3} \mu\text{m}^2$. For example, the second median cross-sectional area MO.sub.A2 of the subset of the population of anode structures in the charged state may be in the range of from $500 \mu\text{m}^2$ to $3 \times 10^{+7} \mu\text{m}^2$, such as from $1.6 \times 10^{+3} \mu\text{m}^2$ to $7.1 \times 10^{+6} \mu\text{m}^2$, and even in the range of from $3 \times 10^{+3} \mu\text{m}^2$ to $5 \times 10^{+6} \mu\text{m}^2$.

(80) In yet another embodiment, the subset of the population of anode structures **110** may have a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that may be the same as and/or similar to values give above for the ratio of the first cross-sectional area A.sub.1 of a member of the population of anode structures in the charged state to the second cross-sectional area A.sub.2 of the member of the population of anode structures in the discharged state. For example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that is at least 1.01:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that is at least 1.05:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that is at least 1.5:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that is at least 2:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that is at least 3:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that is at least 4:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that is at least 5:1. For example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that may be the range of from 1.01 to 4:1. By way of further example, in one embodiment the subset of the population of anode structures has a ratio of the first median cross-sectional area MO.sub.A1 in the charged state to a second median cross-sectional area MO.sub.A2 in the discharged state that may be in the range of from 1.01:1 to 3:1, and even in the range of from 1.5:1 to 3:1.

(81) In yet another embodiment, the change in size of the member of the anode and/or cathode structure population that can occur upon charging and/or discharging of the secondary battery is reflected in the change in width of a subset of one or more of the anode and cathode structure population. As has also similarly been discussed above, a subset of the population of anode

structures may have a first width $W_{sub.A1}$ when the secondary battery is in the charged state, and a second width $W_{sub.A2}$ when the secondary battery is in the discharged state, and a subset of the population of cathode structures may have a first width $W_{sub.C1}$ when the secondary battery is in the charged state, and a second width $W_{sub.C2}$ when the secondary battery is in the discharged state, where $W_{sub.A1}$ is greater than $W_{sub.A2}$ and $W_{sub.C1}$ is less than $W_{sub.C2}$. In one embodiment, the widths $W_{sub.A}$ and $W_{sub.C}$ are measured by measuring the distance between points on a line that is formed by bisection of the first longitudinal plane **113** with an orthogonal X-Y plane **123**, where the Y-axis is parallel to the longitudinal direction, and the X-axis is parallel to a direction of the lengths $L_{sub.A}$ and $L_{sub.C}$ of the member of the anode and cathode structure populations, respectively. For example, referring to FIG. **1D**, the widths may be measured along the line that forms from the bisection of the longitudinal plane **113** with an X-Y plane **123**, from a first point **125a** on the first side of the member, to a second point **125b** on the same line on the second side of the member. In one embodiment, the X-Y plane **123** may be located at a midpoint of the height $H_{sub.A}$ or $H_{sub.C}$ of one or more of the members of the anode and/or cathode structure populations, where the height is measured in a direction orthogonal to both the longitudinal direction and the direction of the lengths $L_{sub.A}$ and $L_{sub.C}$ of the members of the anode and/or cathode structure populations. In another embodiment, the X-Y plane is located at a position along the height of the electrodes (e.g., $H_{sub.A}$ and/or $H_{sub.C}$) that is anywhere from 25% to 75% of the total height H of members of the cathode and/or anode structure populations. Alternatively and/or additionally, the width of the member of the anode structure and/or cathode structure population may correspond to the Feret diameter of the member as measured in the width direction (e.g., along the longitudinal axis) of the member, where the Feret diameter is the distance between two parallel planes restricting the member in the width direction, as measured in a direction parallel to the two planes.

(82) Accordingly, in one embodiment, a subset of the population of cathode structures **112** have a first width $W_{sub.C1}$ in the charged state that is no more than 5000 μm . By way of further example, in one embodiment a subset of the members of the population of cathode structures have a first width $W_{sub.C1}$ in the charged state that is no more than 3000 μm . By way of yet further example, in one embodiment a subset of the members of the population of cathode structures have a first width $W_{sub.C1}$ in the charged state that is less than $1.9 \times 10^{sup.3}$ μm . By way of yet further example, in one embodiment a subset of the members of the population of cathode structures have a first width $W_{sub.C1}$ in the charged state that is no more than 1000 μm . By way of further example, in one embodiment a subset of the members of the population of cathode structures have a first width $W_{sub.C1}$ in the charged state that is no more than 500 μm . Generally, the first width $W_{sub.C1}$ in the charged state will be at least 2 μm , such as at least 5 μm , and even at least 15 μm . For example, in one embodiment, a subset of members of the population of cathode structures may have a first width $W_{sub.C1}$ in the charged state that may be in the range of from 2 μm to 5000 μm , such as from 5 μm to 1900 μm , and even from 15 μm to 1000 μm .

(83) In one embodiment, a subset of the members of the population of cathode structures have a second width $W_{sub.C2}$ in the discharged state that is at least 5 μm . By way of further example, in one embodiment a subset of the members of the population of cathode structures have a second width $W_{sub.C2}$ in the discharged state that is at least 10 μm . By way of further example, in one embodiment a subset of the members of the population of cathode structures have a second width $W_{sub.C2}$ in the discharged state that is at least 20 μm . By way of further example, in one embodiment a subset of the members of the population of cathode structures have a second width $W_{sub.C2}$ in the discharged state that is at least 50 μm . By way of further example, in one embodiment a subset of the members of the population of cathode structures have a second width $W_{sub.C2}$ in the discharged state that is at least 100 μm . Generally, the second width $W_{sub.C2}$ in the discharged state will be less than 5,000 μm , such as less than 2,000 μm and even less than 1000 μm . For example, in one embodiment, a subset of members of the population of cathode structures

112 have a second width $W_{sub.C2}$ in the discharged state that is in the range of from 5 μm to 5,000 μm , such as from 20 μm to 2,000 μm , and even from 50 μm to 1000 μm .

(84) In yet another embodiment, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** in the discharged state to a first width $W_{sub.C1}$ of the cathode structure **112** in the charged state for a subset of the population is at least 1.05:1. By way of further example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population is at least 1.1:1. By way of further example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population is at least 1.3:1. By way of further example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population is at least 2:1. By way of further example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population is at least 3:1. By way of further example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population is at least 4:1. By way of further example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population is at least 6:1. Generally a ratio of the second width $W_{sub.C2}$ to the first width $W_{sub.C1}$ will not exceed 15:1, such as not exceeding 10:1, and even not exceeding 8:1. For example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population may be in the range of from 1.05:1 to 15:1. By way of further example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population may be in the range of from 1.1:1 to 6:1. By way of further example, in one embodiment a ratio of the second width $W_{sub.C2}$ of the cathode structure **112** to the first width $W_{sub.C1}$ of the cathode structure **112** for a subset of the population may be in the range of from 1.3:1 to 4:1. By way of further example, in one embodiment the contraction of the first width $W_{sub.C1}$ with respect to the second width $W_{sub.C2}$ may be in the range of from 2% contraction to 90% contraction, such as from 5% contraction to 75% contraction. That is, the first width $W_{sub.C1}$ may be contracted by at least 2% with respect to the second median width $W_{sub.C2}$, such as at least 5% and even at least 10% with respect to the second width $W_{sub.C2}$, but may be contracted less than 90% with respect to the second width $W_{sub.C2}$, such as less than 80% and even less than 75% with respect to the second width $W_{sub.C2}$.

(85) Furthermore, in one embodiment, a subset of the population of anode structures **110** may have a first width $W_{sub.A1}$ in the charged state that is at least 50 μm . By way of further example, in one embodiment a subset of the members of the population of anode structures have a first width $W_{sub.A1}$ in the charged state that is at least 75 μm . By way of yet further example, in one embodiment a subset of the members of the population of anode structures have a first width $W_{sub.A1}$ in the charged state that is at least 90 μm . By way of yet further example, in one embodiment a subset of the members of the population of anode structures have a first width $W_{sub.A1}$ in the charged state that is at least 150 μm . By way of further example, in one embodiment a subset of the members of the population of anode structures have a first width $W_{sub.A1}$ in the charged state that is at least 200 μm . Generally, the first width $W_{sub.A1}$ in the charged state will not exceed 2000 μm , such as not exceeding 1520 μm and even not exceeding 1000 μm . For example, in one embodiment, a subset of members of the population of anode structures **110** have a first width $W_{sub.A1}$ in the charged state that is in the range of from 50 μm to 2000 μm , such as from 90 μm to 1520 μm , and even from 150 μm to 1000 μm .

(86) In one embodiment, a subset of the members of the population of anode structures have a second width $W_{sub.A2}$ in the discharged state that is no more than 2500 μm . By way of further

example, in one embodiment a subset of the members of the population of anode structures have a second width $W_{\text{sub.A2}}$ in the discharged state that is no more than 2000 μm . By way of further example, in one embodiment a subset of the members of the population of anode structures have a second width $W_{\text{sub.A2}}$ in the discharged state that is no more than 1500 μm . By way of further example, in one embodiment a subset of the members of the population of anode structures have a second width $W_{\text{sub.A2}}$ in the discharged state that is no more than 1000 μm . By way of further example, in one embodiment a subset of the members of the population of anode structures have a second width $W_{\text{sub.A2}}$ in the discharged state that is no more than 800 μm . Generally, the second width $W_{\text{sub.A2}}$ in the discharged state will be at least 15 μm , such as at least 30 μm , and even at least 60 μm . For example, in one embodiment, a subset of members of the population of anode structures **110** have a second width $W_{\text{sub.A2}}$ in the discharged state that is in the range of from 15 μm to 2500 μm , such as from 30 μm to 1500 μm , and even from 60 μm to 1000 μm .

(87) In yet another embodiment, a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population is at least 1.01:1. By way of further example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population is at least 1.05:1. By way of further example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population is at least 1.5:1. By way of further example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population is at least 2:1. By way of further example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population is at least 3:1. By way of further example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population is at least 4:1. By way of further example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population is at least 5:1. For example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population may be in the range of from 1.0:1 to 5:1. By way of further example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population may be in the range of from 1.01:1 to 4:1. By way of further example, in one embodiment a ratio of the first width $W_{\text{sub.A1}}$ of the anode structure **110** in the charged state to a second width $W_{\text{sub.A2}}$ of the anode structure **110** in the discharged state for a subset of the population may be in the range of from 1.01:1 to 3:1, and may even be in the range of from 1.5:1 to 3:1.

(88) In one embodiment, the sizes (e.g. dimensions and cross-sectional areas) for the members of the population of anode structures **110** and cathode structures **112** in the charged and discharged states, such as those described above, are those achieved in charging and/or discharging steps that are performed after an initial formation stage for the secondary battery **102** has already been performed. That is, in the manufacture of a secondary battery **102** having the electrode assembly **106**, an initial formation stage may be performed that comprises at least one initial charging cycle of the secondary battery **102**, which may be performed under carefully controlled conditions including one or more of current, temperature and duration, to promote the formation of the desired structure and contact between components of the secondary battery **102**. The initial formation stage can comprise only a single initial charging cycle, or may comprise a plurality of charging cycles,

according to the particular battery structure and composition, and which can be performed as a final stage in manufacturing to bring the secondary battery **102** to its full power and/or capacity. According to one embodiment, one or more dimensions of the anode and/or cathode structures may also change during the initial formation stage, as the secondary battery **102** is charged and/or discharged, as is also discussed in further detail below. Accordingly, in one embodiment, the dimensions of the cathode and anode structures **110**, **112** referred to herein, as well as the changes therein, are those that occur during charging and/or discharging of the secondary battery subsequent to the initial formation stage. However, in another embodiment, the dimensions referred to herein, as well as the changes therein, may also correspond to those that occur as a part of the initial formation stage.

(89) In one embodiment, members of the population of cathode structures **110** comprise a cathode active material layer **138** having a porous structure, where the porosity of the cathode active material layer **138** may change according to the expansion/contraction of the cathode structures **112** upon charging/discharging of the secondary battery **102**. For example, referring to FIG. 3, members of the population of cathode structures **112** may comprise a cathode active material layer **138** having cathode active material **202** distributed in a porous matrix **204** of material, with the porous matrix **204** comprising pores **200** and/or interstices formed therein. In the embodiment as shown in FIG. 3, the cathode active material layer **138** comprises particles **202** of cathode active material that are dispersed in the porous matrix **204**. The cathode active material layer **138** may also optionally comprise filler particles **206** that are similarly dispersed in the porous matrix **204**. In the embodiment as shown, the porous matrix is relatively highly porous, and comprises webs and/or strands of matrix material connecting the particles **202** of cathode active material and/or particles **206** of filler material, with pores **200** and/or interstices formed between adjacent webs and/or strands of matrix material. The porous matrix **204** may thus be understood, in one embodiment, to act as a binder that binds the particles of cathode active material together to form the cathode active material layer **138**. In another embodiment, the porous matrix **204** can also and/or alternatively comprise thicker sections of matrix material having the particles **202** at least partially and even entirely embedded therein, with pores formed in the relatively thick matrix material sections. In certain embodiments the porosity (i.e. void fraction) of the matrix **204**, which may be related to the volume and/or number of pores **202** and/or interstices in the matrix material, and which can vary according to the charge/discharge state of the secondary battery **102**, can also be selected to provide performance of the cathode active material layer **138**, as is discussed in more detail below.

(90) According to one embodiment, compression and/or expansion of members of the population of cathode structures **112** may result in compression and/or expansion of the cathode active material layer **138**, such that the pores and/or interstices **200** increase in size and/or number upon expansion of members of the population of cathode structures **112**, and decrease in size and/or number upon compression of members of the population of cathode structures **112**. That is, the compression and/or expansion of the members of the population of cathode structures **112** during cycling of the secondary battery **102** between charged and discharged states results in a change in porosity of the cathode active material layer **138**. In the embodiment shown in FIGS. 4A-4B, the members of the population of cathode structures **112** are depicted as being in a charged state with a width $W_{sub.C1}$ in FIG. 4A, and a discharged state with a width $W_{sub.C2}$ in FIG. 4B, where the width $W_{sub.C2}$ is greater than the width $W_{sub.C1}$. Similarly, the cross-sectional area $C_{sub.2}$ of the members of the population of cathode structures **112** are higher in the discharged state depicted in FIG. 4B than the cross-sectional area $C_{sub.1}$ in the charged state depicted in FIG. 4A. That is, the members of the population of cathode structures **112** are depicted as being in a more compressed state in FIG. 4A, and a more expanded state in FIG. 4B, corresponding to, e.g., a charged state and discharged state of the secondary battery **102**, respectively. It is noted that FIGS. 4A-4B further depict an anode structure **110** having an anode active material layer **132**, anode current collector **136**, and anode backbone **134**, separators **130** between the anode structure population members **110** and cathode

structure population members **112**, and cathode structures **112** having a cathode backbone **141** and cathode current collectors **140**. However, it should be understood that the electrode assembly **106** having the anode and cathode structures **110**, **112** is not limited thereto, and other structures and/or arrangements of components of the anode and cathode structures can also be provided. As can be seen by the embodiments shown in FIGS. **4A-4B**, the expansion of the members of the population of cathode structures **112** from the charged state as depicted in FIG. **4A** to the discharged state as depicted in FIG. **4B** can result in an increase in the size and/or number of the pores and/or interstices **200**, as the cathode active material layer **138** expands according to the increased volume of the discharged state. Conversely, the contraction of members of the population of the cathode structures **112** from the discharged state as depicted in FIG. **4B** to the charged state as depicted in FIG. **4A**, results in compression of the cathode active material layer **138** and at least partial filling of the pores and/or interstices, as the cathode active material layer **138** is compressed down to the smaller volume of the charged state.

(91) Accordingly, in one embodiment, members of the population of cathode structures **112** have a cathode active material layer **138** with a first porosity $P_{sub.1}$ when the secondary battery **102** is in the charged state, and a second porosity $P_{sub.2}$ when the secondary battery **102** is in the discharged state, with the first porosity being less than the second porosity. For example, in one embodiment, the first porosity may be less than 30%. By way of further example, in one embodiment, the first porosity may be less than 20%. By way of further example, in one embodiment, the first porosity may be less than 10%. By way of further example, in one embodiment, the first porosity may be less than 5%. For example, in one embodiment, the first porosity may be in the range of from 1% to 30%. By way of further example, in one embodiment, the first porosity may be in the range of from 2% to 20%. By way of further example, in one embodiment, the first porosity may be in the range of from 5% to 10%. Furthermore, in one embodiment, the second porosity in the discharged state may be at least 50%. For example, in one embodiment, the second porosity may be at least 60%. By way of further example, in one embodiment, the second porosity may be at least 70%. By way of further example, in one embodiment the second porosity may be at least 75%. For example, in one embodiment, the second porosity may be in the range of from 50% to 90%. By way of further example, in one embodiment, the second porosity may be in the range of from 60% to 80%. By way of further example, in one embodiment, the second porosity may be in the range of from 70% to 75%. The porosity of the cathode active material layer **138** is the ratio of the volume of pores and/or interstices **200** in between cathode active material **202** in the cathode active material layer **138**, to the volume taken up by the entire mass of the cathode active material layer **138**.

(92) In yet another embodiment, a ratio of the porosity $P_{sub.2}$ of the cathode active material layer **138** in the discharged state to the porosity $P_{sub.1}$ of the cathode active material layer **138** in the charged state is at least 1.1:1. By way of further example, in one embodiment, a ratio of the porosity $P_{sub.2}$ of the cathode active material layer **138** in the discharged state to the porosity $P_{sub.1}$ of the cathode active material layer **138** in the charged state is at least 1.5:1. By way of further example, in one embodiment, a ratio of the porosity $P_{sub.2}$ of the cathode active material layer **138** in the discharged state to the porosity $P_{sub.1}$ of the cathode active material layer **138** in the charged state is at least 2:1. By way of further example, in one embodiment, a ratio of the porosity $P_{sub.2}$ of the cathode active material layer **138** in the discharged state to the porosity $P_{sub.1}$ of the cathode active material layer **138** in the charged state is at least 5:1. By way of further example, in one embodiment, a ratio of the porosity $P_{sub.2}$ of the cathode active material layer **138** in the discharged state to the porosity $P_{sub.1}$ of the cathode active material layer **138** in the charged state is at least 10:1. By way of further example, in one embodiment, a ratio of the porosity $P_{sub.2}$ of the cathode active material layer **138** in the discharged state to the porosity $P_{sub.1}$ of the cathode active material layer **138** in the charged state is at least 15:1. For example, in one embodiment, a ratio of the porosity $P_{sub.2}$ of the cathode active material layer **138** in the discharged state to the porosity $P_{sub.1}$ of the cathode active material layer **138** in the charged state

is in the range of from 2:1 to 30:1. For example, in one embodiment, a ratio of the porosity P.sub.2 of the cathode active material layer **138** in the discharged state to the porosity P.sub.1 of the cathode active material layer **138** in the charged state is in the range of from 3:1 to 20:1. By way of further example, in one embodiment, a ratio of the porosity P.sub.2 of the cathode active material layer **138** in the discharged state to the porosity P.sub.1 of the cathode active material layer **138** in the charged state is in the range of from 5:1 to 15:1.

(93) In one embodiment, the cathode active material layer **138** comprises cathode active material in the form of particles **202**. For example, in one embodiment, the cathode active material comprises particles **202** of at least one of transition metal oxides, transition metal sulfides, transition metal nitrides, lithium-transition metal oxides, lithium-transition metal sulfides, and lithium-transition metal nitrides may be selectively used. The transition metal elements of these transition metal oxides, transition metal sulfides, and transition metal nitrides can include metal elements having a d-shell or f-shell. Specific examples of such metal element are Sc, Y, lanthanoids, actinoids, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Tc, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pb, Pt, Cu, Ag, and Au. Additional cathode active materials include LiCoO.sub.2, LiNi.sub.0.5Mn.sub.1.5O.sub.4, Li(Ni.sub.xCo.sub.yAl.sub.2)O.sub.2, LiFePO.sub.4, Li.sub.2MnO.sub.4, V.sub.2O.sub.5, molybdenum oxysulfides, phosphates, silicates, vanadates and combinations thereof. In one embodiment, the cathode active material layer **138** comprises at least 40% by weight of cathode active material **202**. For example, in one embodiment, the cathode active material layer **138** comprises at least 50% by weight of cathode active material. By way of further example, in one embodiment, the cathode active material layer **138** comprises at least 60% by weight of cathode active material. For example, the cathode active material layer **138** may comprise a weight percent of cathode active material in the range of from 40% to 99%. For example, in one embodiment, a weight percent of cathode active material in the cathode active material layer **138** may be in the range of from 50% to 99%. Furthermore, in one embodiment, the cathode active material layer **138** comprises at least one filler material, which may also be in the form of particles. For example, the cathode active material layer **138** may comprise filler particles comprising at least one of carbon-containing material such as carbon black, polymer-containing beads such as beads formed from one or more of polyethylene, polypropylene, polyvinylidene fluoride, polytetrafluoroethylene, polyacrylic acid, carboxymethyl cellulose, polyvinylalcohol, starch, regenerated cellulose, diacetyl cellulose, hydroxypropyl cellulose, polyvinyl chloride, polyvinyl pyrrolidone, polybutadiene, polyethylene oxide, polyacrylates, rubbers, e.g. ethylene-propylene-diene monomer (EPDM) rubber, sulfonated EPDM, fluorinated rubbers, styrene butadiene rubber (SBR), polyacrylonitrile (PAN), polymethyl methacrylate (PMMA), polyacrylic acid (PAA), cross-linked polyethylene (PEX, XLPE), polyethylene (PE), polyethylene terephthalate (PET), polyphenyl ether (PPE), polyvinyl chloride (PVC), polyvinylidene chloride (PVDC), polyamide (PA), polyimide (PI), polycarbonate (PC), polytetrafluoroethylene (PTFE), polystyrene (PS), polyurethane (PU), polyester (PE), acrylonitrile butadiene styrene (ABS), polyoxymethylene (POM), polysulfone (PES), styrene-acrylonitrile (SAN), ethylene vinyl acetate (EVA), styrene maleic anhydride (SMA), combinations of these, and other inert polymers that have elastic modulus between 1E-5 GPa and 10 GPa), and are inert in the battery. In particular, concentrations and particle sizes of these materials can be chosen by engineering design of properties in order to achieve a predetermined compressibility of the cathode structure. For example, in one embodiment, to obtain a cathode structure with a cathode active material layer having a relatively high compressibility, polymers with a relatively low elastic modulus (Young's Modulus) can be provided in relatively high concentrations in the cathode active material layer. The particles of filler and/or cathode active material may be dispersed in the matrix material, as shown for example in FIG. 3.

(94) In one embodiment, the cathode active material **202** comprises particles (e.g., one or more of cathode active material particles and filler particles) having an average particle size in the range of from 0.1 μm to 500 μm . By way of further example, in one embodiment, the cathode active

material **202** comprises particles having a weight average particle size in the range of from 0.15 μm to 300 μm . By way of further example, in one embodiment, the cathode active material **202** comprises particles having an average particle size in the range of from 0.2 μm to 200 μm .

(95) In one embodiment, the cathode active material layer **138** comprises filler material in a range of from 0.05% by weight to 20% by weight of the cathode active material layer. By way of further example, in one embodiment, the cathode active material layer **138** comprises filler material in a range of from 0.1% by weight to 10% by weight. By way of further example, in one embodiment, the cathode active material layer **138** comprises filler material in a range of from 0.5% by weight to 5% by weight.

(96) In yet another embodiment, a ratio by weight of cathode active material to filler material in the cathode active material layer **138** is in a range of from 1.5:1 to 30:1. In yet another embodiment, a ratio by weight of cathode active material to filler in the cathode active material layer **138** is in a range of from 2:1 to 20:1. In yet another embodiment, a ratio by weight of cathode active material to filler in the cathode active material layer **138** is in a range of from 3:1 to 15:1.

(97) According to one embodiment, the cathode active material layer **138** comprises particles of cathode active material and/or filler particles that are dispersed in the matrix of polymeric material. In one embodiment, the particles of cathode active material may be dispersed substantially uniformly throughout the matrix of polymeric material. Alternatively, in another embodiment, the particles of cathode active material may be distributed non-uniformly throughout the matrix of polymeric material, such as to provide a gradient of the cathode active material throughout the cathode active material layer **138**, with a higher concentration of particles on one side of the cathode active material layer **138** than on another side of the cathode active material layer. In one embodiment, the polymeric material may comprise a fluoropolymer derived from monomers comprising at least one of vinylidene fluoride, hexafluoropropylene, tetrafluoropropene, and the like. In another embodiment, the polymeric material may be a polyolefin such as at least one of polyethylene, polypropylene, or polybutene, having any of a range of varying molecular weights and densities. In another embodiment, the polymeric material is selected from the group consisting of ethylene-diene-propene terpolymer, polystyrene, polymethyl methacrylate, polyethylene glycol, polyvinyl acetate, polyvinyl butyral, polyacetal, and polyethyleneglycol diacrylate. In another embodiment, the polymeric material is selected from the group consisting of methyl cellulose, carboxymethyl cellulose, styrene rubber, butadiene rubber, styrene-butadiene rubber, isoprene rubber, polyacrylamide, polyvinyl ether, polyacrylic acid, polymethacrylic acid, and polyethylene oxide. In another embodiment, the polymeric material is selected from the group consisting of acrylates, styrenes, epoxies, and silicones. In yet another embodiment, the polymeric material can comprise one or more of polyethylene, polypropylene, polyvinylidene fluoride, polytetrafluoroethylene, polyacrylic acid, carboxymethyl cellulose, polyvinylalcohol, starch, regenerated cellulose, diacetyl cellulose, hydroxypropyl cellulose, polyvinyl chloride, polyvinyl pyrrolidone, polybutadiene, polyethylene oxide, polyacrylates, rubbers, e.g. ethylene-propylene-diene monomer (EPDM) rubber, sulfonated EPDM, fluorinated rubbers, styrene butadiene rubber (SBR), polyacrylonitrile (PAN), polymethyl methacrylate (PMMA), polyacrylic acid (PAA), cross-linked polyethylene (PEX, XLPE), polyethylene (PE), polyethylene terephthalate (PET), polyphenyl ether (PPE), polyvinyl chloride (PVC), polyvinylidene chloride (PVDC), polyamide (PA), polyimide (PI), polycarbonate (PC), polytetrafluoroethylene (PTFE), polystyrene (PS), polyurethane (PU), polyester (PE), acrylonitrile butadiene styrene (ABS), polyoxymethylene (POM), polysulfone (PES), styrene-acrylonitrile (SAN), ethylene vinyl acetate (EVA), styrene maleic anhydride (SMA), combinations of these, and other inert polymers that have elastic modulus between 1E-5 GPa and 10 GPa), and are inert in the battery. In particular, similarly to the filler particles above, the concentrations these materials can be chosen by engineering design of properties in order to achieve a predetermined compressibility of the cathode structure. For example, in one embodiment, to obtain a cathode structure with a cathode active material layer

having a relatively high compressibility, polymers with a relatively low elastic modulus (Young's Modulus) can be provided in relatively high concentrations in the cathode active material layer. In another embodiment, the polymeric material is a copolymer or blend of two or more of the aforementioned polymers.

(98) In one embodiment, members of the population of cathode structure **112** have a compressibility that imparts good performance during charging/discharging cycles in the secondary battery. For example, in one embodiment, one or more members of the population cathode structures **112** may exhibit a compression, as defined by a

$(\text{Dimension.sub.1} - \text{Dimension.sub.2}) / (\text{Dimension.sub.1}) \times 100$, where Dimension.sub.1 is a dimension of the cathode structures (such as width or cross-section) in the discharged state), and Dimension.sub.2 is a dimension of the cathode structure in the charged state, of at least 5% at a pressure of at least 0.7 MPa (100 psi). By way of further example, one or more members of the population of the cathode structure may exhibit a compression of at least 10% at a pressure of 0.7 MPa (100 psi). By way of further example, one or more members of the population of cathode structures may exhibit a compression of at least 25% at a pressure of 0.7 MPa (100 psi). By way of further example, one or more members of the population of cathode structures may exhibit a compression of at least 5% at a pressure of 70 MPa (10,000 psi). By way of further example, one or more members of the population of cathode structures may exhibit a compression of at least 10% at a pressure of 70 MPa (10,000 psi). For example, in one embodiment, one or more members of the population of cathode structures **112** may exhibit a compression in the range of from 5% to 75% at a pressure of 0.7 MPa (100 psi). By way of further example, in one embodiment, one or more members of the population of cathode structures **112** may exhibit a compression in the range of from 0.5% to 75% at a pressure of 70 MPa (10,000 psi). By way of further example, in one embodiment, one or more members of the population of cathode structures **112** may exhibit a compression in the range of from 20% to 50% at a pressure of 0.7 MPa (100 psi). By way of further example, in one embodiment, one or more members of the population of cathode structures **112** may exhibit a compression in the range of from 20% to 50% at a pressure of 70 MPa (10,000 psi).

(99) In one embodiment, the members of the population of cathode structures **112** have a cathode active material layer **138** with filler particles that are both compressible and elastic. That is, the filler particles can comprise particles such as polymeric beads or other materials that can compress with compression of cathode structure, and that have an elasticity that allows the particles to at least partially recover their shape prior to compression. In one embodiment, the filler particles having a predetermined level of elasticity may help facilitate expansion of the cathode structures during discharge of the secondary battery, without excessively inhibiting compression of the cathode structures during charging of the secondary battery. The filler particles may also comprise an elasticity as measured according to Young's Modulus in the range of from 0.1 GPa to 10 GPa, such as from 0.1 to 4.1 GPa, and even from 2.5 GPa to 10 GPa.

(100) In one embodiment, the members of the population of cathode structures **112** have a cathode active material layer **138** with filler particles that are incompressible and porous. The filler particles can comprise structures such as hollow micro-spheres, micro-fibers, micro-tubes, micro-cylinders, micro-skeletons, and other microscopic and nanoscopic object shapes and sizes that are compatible in the battery. The porous filler particles can comprise an incompressible material such as for example a porous ceramic material, or a porous material having a hard ceramic cell, that resists compression, while also providing a porous interior. These porous, incompressible particles can be used as electrolyte reservoirs in the matrix of the electrode. When the electrode is in its compressed form, the electrolyte stored in the porosity of these particles can act towards reducing the ionic resistance of the matrix electrode.

(101) According to one aspect, the filler materials that act as electrolyte reservoirs can be made from ceramics, polymers, metals, metal oxides, or other compatible materials. The amount, size,

shape, and material properties of the filler particles can be tailored for the particular use and the pressures generated by the battery during operation.

(102) In one embodiment, the compressibility and porosity of the filler material can be tailored to the application and the pressures generated by the battery during operation. In one instance, the filler particles are incompressible under the pressures applied by the battery during operation, and the electrolyte stored inside the filler particles do not appreciably change in volume during charge and discharge. In other embodiments, the filler material is less compressible than the electrode matrix, so that even though the electrolyte volume in the filler particle is lower in the compressed state than in the uncompressed state, it is greater than the electrolyte volume in the matrix, thereby, providing ionic conductivity.

(103) The porosity of the filler material designed for use as an electrolyte reservoir is preferably high in order to maximize the amount of electrolyte in the particle during battery operation. Preferably, the porosity may be greater than 60%, such as greater than 70%, greater than 80%, and even greater than 90% by volume for the filler material. According to one aspect, the pore sizes of the filler material may be generally greater than 5 nm, such as greater than 10 nm, and even greater than 50 nm, in order to facilitate ion transport.

(104) The filler materials that are used to constitute an electrolyte reservoir may, in one embodiment, be made of materials that have a elasticity according to the Young's modulus of greater than 10 GPa, such greater than 50 GPa, and even greater than 100 GPa.

(105) In one embodiment, the secondary battery **102** having the members of the anode and cathode structure population **110**, **112** that are capable of expanding and/or contracting, such as inverse relation to one another, may be capable of providing synergistic effects in terms of simultaneously imparting both a relatively high areal capacity and/or energy density, and a relatively high rate of discharge (e.g., as measured by the rate capability) of the secondary battery. For example, the secondary battery **102** may in certain aspects be capable of preserving porosity of the cathode structure **110** under compression thereof. Without being limited to any one particular theory, it is believed that the expansion/contraction of the members of the population of cathode structures **112** upon discharge/charge of the secondary battery **102** allows for cathode structures **112** to be used that provide a relatively high areal capacity, without sacrificing the rate at which discharge of the secondary battery can occur. By way of clarification, it is noted that the areal capacity of a secondary battery **102** may be related to the relatively high cathode volume per unit geometrical area (i.e., the cathode active material volume) that can be provided. In general, a relatively higher volume of cathode per unit geometrical area will result in a relatively higher areal capacity.

However, batteries with cathodes having a relatively high volume, such as those having a relatively high thickness in the longitudinal direction, may also experience a reduction in discharge as compared to thinner cathodes, due to the larger amount of cathode active material that is present in the interior of the cathode as opposed to at a cathode surface. However, without being limited by any theory, it is believed that the expansion/contraction of the cathode structures **112**, and the change in porosity of the cathode active material layers **138** that occurs with the expansion/contraction, may allow for a rate of discharge that at least partially compensates for any reduction that might otherwise be observed with a cathode structure **112** having a relatively high volume. That is, it is hypothesized that the expansion of the cathode and increased porosity in the cathode during discharge may facilitate contact of the electrolyte with the cathode active material, even at more interior regions of the cathode, thereby facilitating an increased discharge rate.

Accordingly, aspects of the present disclosure may allow for a relatively large volume of cathode active material to be provided (with respect to the total volume of cathode structures, anode structures, and separators), while maintaining a relatively high rate of discharge, and thus a high rate capability of the secondary battery.

(106) For example, in one embodiment, the areal capacity of the secondary battery may be determined as the capacity of the battery per median opposing surface area of members of the

anode structure population of the battery, where the opposing surface area is the area of the portion of the anode surface that faces a cathode surface directly adjacent to the anode in the stacking direction. The areal capacity may be measured in units of $\text{mA}\cdot\text{h}/\text{cm}^2$. For example, referring to FIG. 1D, the opposing surface area OA may be that portion of the anode surface area between points **126a** and **126b** along the length LA of the anode, multiplied by the height H.sub.A, where the point **126b** is a distal end of the anode, and the point **126a** is a point just short of the base of the anode, located across from the distal end of the facing cathode **112**, and thus **126a** and **126b** mark the end of the surface region of the anode that directly faces the opposing cathode **112** surface. Accordingly, in one embodiment, the areal capacity of the secondary battery is at least $3 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. By way of further example, in one embodiment, the energy density of the secondary battery is at least $5 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. By way of further example, in one embodiment, the energy density of the secondary battery is at least $8 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. By way of further example, in one embodiment, the energy density of the secondary battery is at least $10 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. By way of further example, in one embodiment, the energy density of the secondary battery is at least $15 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. By way of further example, in one embodiment, the energy density of the secondary battery is at least $20 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. By way of further example, in one embodiment, the energy density of the secondary battery is at least $25 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. For example, in one embodiment, the energy density of the secondary battery **102** is in a range of from 3 to $50 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. By way of further example, in one embodiment, the energy density of the secondary battery **102** is in a range of from 5 to $25 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C. By way of further example, in one embodiment, the energy density of the secondary battery **102** is in a range of from 8 to $20 \text{ mA}\cdot\text{h}/\text{cm}^2$ at 0.1 C.

(107) In one embodiment, the secondary battery **102** may provide a higher discharge rate that can be quantified according to the rate capability of the secondary battery. The rate capability of the secondary battery refers to the ratio of the capacity of the secondary battery at a first C-rate to the capacity of the secondary battery at a second C-rate, expressed as a percentage. For example, the rate capability may be calculated according to $\text{Capacity.sub.1}/\text{Capacity.sub.2} \times 100$, where Capacity.sub.1 is the capacity for discharge at the first C-rate, such as a C-rate of 1 C, and Capacity.sub.2 is the capacity for discharge at a second C-rate, such as a C-rate of C/10, and may be expressed as the calculated percentage for a specified ratio C.sub.x/C.sub.y, where C.sub.x is the first C-rate, and C.sub.y is the second C-rate. In particular, the rate capability metric may serve as a measure of the efficiency of the rate of discharge of the secondary battery when discharged at a higher rate as compared to a lower rate. By way of clarification, it is noted that practice, increasing the speed of discharge of a secondary battery results in the generation of impedances and other forces that can build up to oppose to higher current. Accordingly, the rate capability may be a measure of the change in capacity that occurs due to changes in discharge rate. In one embodiment, the secondary battery may be capable of providing a rate capability of 1 C:C/10 of at least 75%. By way of further example, the secondary battery may be capable of providing a rate capability of 1 C:C/10 of at least 80%. By way of further example, the secondary battery may be capable of providing a rate capability of 1 C:C/10 of at least 90%. By way of further example, the secondary battery may be capable of providing a rate capability of 1 C:C/10 of at least 95%. By way of further example, the secondary battery may be capable of providing a 2 C:C/10 rate of at least 75%. By way of further example, the secondary battery may be capable of providing a rate capability of 2 C:C/10 of at least 80%. By way of further example, the secondary battery may be capable of providing a rate capability of 2 C:C/10 of at least 90%. By way of further example, the secondary battery may be capable of providing a rate capability of 2 C:C/10 of at least 95%. By way of further example, the secondary battery may be capable of providing a 5:C/10 rate of at least 75%. By way of further example, the secondary battery may be capable of providing a rate capability of 5:C/10 of at least 80%. By way of further example, the secondary battery may be capable of providing a

rate capability of 5 C:C/10 of at least 90%. By way of further example, the secondary battery may be capable of providing a rate capability of 5 C:C/10 of at least 95%.

(108) In one embodiment, the secondary battery has an areal capacity of at least 3 mA.Math.h/cm.sup.2 at 0.1 C, and a rate capability of 1 C/0.1 C of at least 75%. For example, in one embodiment, the secondary battery may have an areal capacity of at least 5 mA.Math.h/cm.sup.2 at 0.1 C, and a rate capability of 1 C/0.1 C of at least 75%, such as a rate capability of 1 C/0.1 C of at least 80% and even at least 90%, such as 95%. By way of further example, in one embodiment, the secondary battery may have an areal capacity of at least 8 mA.Math.h/cm.sup.2 at 0.1 C, and a rate capability of 1 C/0.1 C of at least 75%, such as a rate capability of 1 C/0.1 C of at least 80% and even at least 90%, such as 95%. By way of further example, in one embodiment, the secondary battery may have an areal capacity of at least 10 mA.Math.h/cm.sup.2 at 0.1 C, and a rate capability of 1 C/0.1 C of at least 75%, such as a rate capability of 1 C/0.1 C of at least 80% and even at least 90%, such as 95%. By way of further example, in one embodiment, the secondary battery may have an areal capacity of at least 15 mA.Math.h/cm.sup.2 at 0.1 C, and a rate capability of 1 C/0.1 C of at least 75%, such as a rate capability of 1 C/0.1 C of at least 80% and even at least 90%, such as 95%. By way of further example, in one embodiment, the secondary battery may have an areal capacity of at least 20 mA.Math.h/cm.sup.2 at 0.1 C, and a rate capability of 1 C/0.1 C of at least 75%, such as a rate capability of 1 C/0.1 C of at least 80% and even at least 90%, such as 95%. By way of further example, in one embodiment, the secondary battery may have an areal capacity of at least 25 mA.Math.h/cm.sup.2 at 0.1 C, and a rate capability of 1 C/0.1 C of at least 75%, such as a rate capability of 1 C/0.1 C of at least 80% and even at least 90%, such as 95%.

(109) In yet another embodiment, without being limited to any particular theory, it is believed that the electrode assembly **106** having the expanding/contracting cathode structures **112** may be capable of providing an electrolyte pumping effect that increases movement and flow of electrolyte to the cathode active material in the cathode structures and helps to maintain a high rate of discharge of the secondary battery **102** having the cathode structures **112**. By way of clarification, and without being limited to any one particular theory, it is noted that a volume occupied by the electrolyte in the secondary battery **102** includes the volume occupied by the electrolyte in between members of the population of cathode and anode structures **112**, **110**, and also includes any open volume due to the presence of pores, etc., in the members of the population of anode structures **110**, and the open volume in the members of the population of cathode structures **112**, resulting from the porosity thereof. As the secondary battery **102** is charged, any pores in the members of the population of anode structures **110** become increasingly filled with intercalated and/or inter-alloyed carrier ions, such that a volume of electrolyte occupying the members of the population of anode structures **110** decreases. Furthermore, the increase in size of the members of the population of anode structures **110** due to this intercalation and/or inter-alloying may compress the members of the population of cathode structures **112**, as discussed above, thereby reducing the open pore volume in the cathode structure members such that a volume of electrolyte occupying the cathode structures **112** decreases when the secondary battery **102** is being charged. Conversely, discharging of the secondary battery **102** may result in de-intercalation and/or de-alloying of the carrier ions, to provide more available volume in the anode structure, and may also result in expansion of the cathode structures, which can increase the porosity and the available volume for electrolyte in the pores/open volume of the members of the cathode structure population. That is, the electrolyte may occupy a volume $V_{sub.1}$ in the pores of the members of the population of cathode structures **112** in the charged state that is smaller than a volume $V_{sub.2}$ in the pores of the members of the population of cathode structures **112** in the discharged state. By way of explanation, and not being limited by any theory, it is believed that this change in available volume (between $V_{sub.1}$ and $V_{sub.2}$) for the electrolyte in the members of the population of cathode structures **112** (and even in the anode structure population) in cycling between charged and discharged states may provide an

electrolyte pumping effect whereby the electrolyte is agitated and/or “pumped” into and about the pores of the cathode active material layer **138** during cycling. Thus, the “pumping” of the electrolyte into and about pores of the cathode active material layer **138** may bring the electrolyte into contact with cathode active material, and can enhance the rate of discharge of the cathode active material layer due to the increased contact of the cathode active material with the electrolyte during the discharge process. The volume $V_{sub.2}$ of the pores of the members of the population of cathode structures **112** in the discharged state may be related to the porosity of the cathode active material layer **138** in the discharged state, and the volume $V_{sub.1}$ of the pores of the members of the population of cathode structures **112** in the charged state may be related to the porosity of the cathode active material layer **138** in the charged state. In one embodiment, a ratio $V_{sub.2}:V_1$ of the volume of the cathode active material layer **138** available for the electrolyte in the discharged state to the volume in the charged state may be at least 1.1:1. For example, in one embodiment, the ratio $V_{sub.2}:V_{sub.1}$ may be at least 1.5:1. For example, in one embodiment, the ratio $V_{sub.2}:V_{sub.1}$ may be at least 2:1. For example, in one embodiment, the ratio $V_{sub.2}:V_{sub.1}$ may be at least 5:1. By way of further example, in one embodiment the ratio $V_{sub.2}:V_{sub.1}$ may be at least 10:1. By way of yet a further example, in one embodiment the ratio $V_{sub.2}:V_{sub.1}$ may be at least 15:1. For example, the ratio $V_{sub.2}$ to $V_{sub.1}$ may be in the range of from 1.1:1 to 30:1, such as from 1.5:1 to 20:1, and even from 3:1 to 15:1. In yet another embodiment, porous filler particles may also be provided to facilitate a predetermined pore volume in one or more of the charge and/or discharged states.

(110) In yet another embodiment, a method of formation of a secondary battery for cycling between charged and discharged states may be provided. According to one aspect, the method of formation may comprise at least one initial formation charging step, in which the secondary battery **102** is charged such that members of the population of anode structures **110** expand, with the result that the expanding anode structures **110** compress members of the population of cathode structures **112**. Generally speaking, the formation stage may involve one or more initial charging steps that are performed under conditions that re-arrange and/or optimize internal structures and morphologies, such that the secondary battery can be charged up to its rated capacity. For example, the formation stage may involve one or more charging steps performed under carefully controlled conditions of current, temperature and duration, for example to minimize impedance in the secondary battery and optimize contact between electrolyte and electrodes. In one embodiment, during the formation stage, the members of the population of anode structures **110** may compress the compressible layers **138** of cathode active material to a size that is less than an original size of the cathode active material layers **138** prior to the initial formation stage. The initial formation stage may thus provide for in situ formation of members of the population of cathode structures **112** having a predetermined size, cross-sectional area and/or volume, as well as a predetermined density, porosity, and/or volume % of the cathode active material in the cathode active material layers **138** of the cathode structure population members. In one embodiment, the initial formation stage compresses a subset of the population of cathode structures **112** such that the cross-sectional area decreases from an initial cross-sectional area $C_{sub.i}$ prior to the initial formation step to a post-formation cross-sectional area $C_{sub.f}$ after the initial formation stage that is less than 95% of the initial cross-sectional area $C_{sub.i}$. By way of further example, in one embodiment, the initial formation stage compresses a subset of the population of cathode structures **112** such that the cross-sectional area decreases from an initial cross-sectional area $C_{sub.i}$ prior to the initial formation stage to a post-formation cross-sectional area $C_{sub.f}$ after the initial formation stage that is less than 90% of the initial cross-sectional area $C_{sub.i}$. By way of further example, in one embodiment, the initial formation stage compresses a subset of the population of cathode structures **112** such that the cross-sectional area decreases from an initial cross-sectional area $C_{sub.i}$ prior to the initial formation stage to a post-formation cross-sectional area $C_{sub.f}$ after the initial formation stage that is less than 80% of the initial cross-sectional area $C_{sub.i}$. By way of further example, in one

embodiment, the initial formation stage may compress a subset of the population of cathode structures **112** such that the cross-sectional area decreases from an initial cross-sectional area C.sub.i prior to the initial formation stage to a post-formation cross-sectional area C.sub.f after the initial formation stage that is less than 70% of the initial cross-sectional area C.sub.i. Generally, the post-formation cross-sectional area C.sub.f will be at least 25% of the initial cross-sectional area C.sub.i. For example, the initial formation step may compress a subset of the population of the cathode structures **112** to a cross-sectional area C.sub.f that is in the range of from 25% to 95% of C.sub.i, such as in a range of from 30% to 80% of C.sub.i, and even in a range of from 40% to 60% of C.sub.i. Furthermore, according to one embodiment, a median cross-sectional area, as measured either according to MA.sub.c (e.g., a median of cross-sectional areas for more than one cathode member), ML.sub.c (e.g., a median of cross-sectional areas at different longitudinal planes long a cathode member), and/or MO.sub.C (e.g., a median of MA_c and ML_c), as discussed above, may be used to determine the extent of compression of a subset of the population of cathode structures during the initial formation, and may exhibit median cross-sectional areas post-formation as a % of the median cross-sectional areas pre-formation that are similar to and/or the same as the ranges for C.sub.f as a % of C.sub.i above.

(111) Also, the formation stage may result in the increase in size of the members of the population of anode structures. For example, the initial cross-sectional area A.sub.i of a subset of the population of anode structures may increase to a post-formation cross-sectional area A.sub.f that provides a ratio of A.sub.f:A.sub.i that is at least 1.1:1, such as at least 1.3:1, and even at least 1.5:1. For example, the ratio A.sub.f:A.sub.i may be at least 2:1, and may even be at least 3:1, such as at least 4:1, and even at least 5:1. For example, a cross-sectional area C.sub.i of the subset of the population of cathode structures before the initial formation step may be in the range of from 800 μm^2 to $8 \times 10^6 \mu\text{m}^2$, such as from 1000 μm^2 to $5 \times 10^6 \mu\text{m}^2$, and even from 1500 μm^2 to $3 \times 10^6 \mu\text{m}^2$. By contrast, the cross-sectional area C.sub.f of the subset of the population of cathode structures after the initial formation step may be in the range of from 3500 μm^2 to $8 \times 10^6 \mu\text{m}^2$, such as from 4000 μm^2 to $5.05 \times 10^6 \mu\text{m}^2$, and even from 500 μm^2 to $3 \times 10^6 \mu\text{m}^2$. Furthermore, according to one embodiment, a median cross-sectional area, as measured either according to MA.sub.A (e.g., a median of cross-sectional areas for more than one anode member), ML.sub.A (e.g., a median of cross-sectional areas at different longitudinal planes long an anode member), and/or MO.sub.A (e.g., a median of MA_A and ML_A), as discussed above, may be used to determine the extent of expansion of a subset of the population of anode structures during the initial formation stage, and may exhibit median cross-sectional areas post-formation as a % of the median cross-sectional areas pre-formation that are similar to and/or the same as the ranges for the ratio of A.sub.f to A.sub.i as above.

(112) In yet another embodiment, the initial formation stage may comprise charging the secondary battery **102** to compress the cathode active material layers **138** to decrease the porosity thereof, and/or to increase a volume % of the cathode active material layers **138** occupied by particles of cathode active material and/or filler (e.g., to densify the cathode active material layers). By way of example, in one embodiment, the volume % of particles in the cathode active material layers **138** before the initial formation stage may be no more than 50%, such as no more than 30% and even no more than 25%. By contrast, a volume % of particles in the cathode active material layers **138** after the initial formation stage may be at least 60%, such as at least 75% and even at least 85%, such as at least 95%.

(113) According to yet another embodiment, the initial formation stage may comprise charging the secondary battery **102** such that the members of the population of anode structures **110** expand and compress the microporous separator **130** against the cathode structures **112** and/or anode structures, at a pressure that causes the microporous separator to at least partially adhere to members of the populations of cathode and anode structures. That is, in a case where the microporous separator **130**

comprises a polymeric or other material capable of at least partially plasticizing and/or otherwise adhering to members of the populations of cathode structures **112** and/or anode structure **110**, the compression of the microporous separator **130** against the members can cause the separator and members to at least partially adhere to each other. In one embodiment, the at least partial adhesion of the microporous separator to the cathode structure and/or anode structure members can cause the cathode structure members to expand upon discharge of the secondary battery **102**. By way of clarification, it is noted that charging of the secondary battery expands the members of the population of anode structures **110**, and this expansion may also stretch portions of an elastic microporous separator **130** that are adjacent to the anode structure members. Furthermore, when the members of the population of anode structures **110** contract during discharge of the secondary battery **102**, the elastic microporous separator may also contract back to a more relaxed state, such as substantially conformally with the contracting profile of the anode structure population members **110**. However, as the separator **130** is at least partially adhered to the members, the contraction of the separator also exerts a force to pull a surface of the members of the population of cathode structures **112** that is at least partially adhered to the microporous separator, thereby causing the members to expand in size. That is, the at least partial adhesion of the separator **130** to the members of the population of cathode structures **112** and/or anode structure **110** may thus cause the cathode structure population members **112** to expand in concert with contraction of the members of the population of anode structures **110** during discharge of the secondary battery **102**, for example such that the cathode structure population members **112** expand in size in a manner that is inversely related to the contraction in size of the anode structure population members **110**. In one embodiment, the initial formation stage comprises charging the secondary battery **102** such that the members of the population of anode structures **110** expand and compress the microporous separator **130** against the members of the population of cathode structures **112** at a pressure sufficient to at least partially fuse a polymeric material of the microporous separator at a surface of the microporous separator **130**, to a polymeric matrix material at a contacting surface of the cathode active material layer **138** of the cathode structure **112**, and to a contacting surface of the anode structure **110**, such that the cathode active material layer **138** expands and/or contracts in concert with flexing and/or contracting of the separator, during cycling of the secondary battery **102**.

(114) In one embodiment, the initial formation stage comprises charging the secondary battery such that members of the population of anode structures expand and exert a pressure to compress the microporous separators **130** against members of the population of cathode structures and/or anode structures at a pressure of at least 1,000 psi. In another embodiment, the microporous separators are compressed against the members of the cathode structure population and/or anode structure population during the initial formation stage at a pressure of at least 3,000 psi. In yet another embodiment, the microporous separators are compressed against the members of the population of cathode structures and/or anode structures during the initial formation stage at a pressure of at least 5,000 psi. In yet another embodiment, the microporous separators are compressed against the members of the population of cathode structures and/or anode structures during the initial formation stage at a pressure of at least 10,000 psi.

(115) Embodiments of the energy storage device **100** such as the secondary battery **102** and components thereof, having the compressible cathode structures **112**, are described in further detail below.

(116) Electrode Assembly

(117) Referring again to FIGS. **1A-1B**, in one embodiment, an interdigitated electrode assembly **106** includes a population of anode structures **110**, a population of cathode structures **112**, and an electrically insulating microporous separator **130** electrically insulating the anode structures **110** from the cathode structures **112**. In one embodiment, the anode structures **110** comprise an anode active material layer **132**, an anode backbone **134** that supports the anode active material layer **132**, and an anode current collector **136**, which may be an ionically porous current collector to allow

ions to pass therethrough, as shown in the embodiment depicted in FIG. 7. Similarly, in one embodiment, the cathode structures **112** comprise a cathode active material layer **138**, a cathode current collector **140**, and a cathode backbone **141** that supports one or more of the cathode current collector **140** and/or the cathode active material layer **138**, as shown for example in the embodiment depicted in FIG. 7. The electrically insulating microporous separator **130** allows carrier ions to pass therethrough during charge and/or discharge processes, to travel between the anode structures **110** and cathode structures **112** in the electrode assembly **106**. Furthermore, it should be understood that the anode and cathode structures **110** and **112**, respectively, are not limited to the specific embodiments and structures described herein, and other configurations, structures, and/or materials other than those specifically described herein can also be provided to form the anode structures **110** and cathode structures **112**. For example, the anode and cathode structures **110**, **112** can be provided in a form where the structures are substantially absent any anode and/or cathode backbones **134**, **141**, such as in a case where the region of the anode and/or cathode structures **110**, **112** that would contain the backbones is instead made up of anode active material and/or cathode active material.

(118) According to the embodiment as shown in FIGS. **1A-1B**, the members of the anode and cathode structure populations **110** and **112**, respectively, are arranged in alternating sequence, with a direction of the alternating sequence corresponding to the stacking direction D. The electrode assembly **106** according to this embodiment further comprises mutually perpendicular longitudinal, transverse, and vertical axes, with the longitudinal axis A.sub.EA generally corresponding or parallel to the stacking direction D of the members of the electrode and counter-electrode structure populations. As shown in the embodiment in FIG. **1A**, the longitudinal axis A.sub.EA is depicted as corresponding to the Y axis, the transverse axis is depicted as corresponding to the X axis, and the vertical axis is depicted as corresponding to the Z axis.

(119) Further, the electrode assembly **106** has a maximum width W.sub.EA measured in the longitudinal direction (i.e., along the y-axis), a maximum length L.sub.EA bounded by the lateral surface and measured in the transverse direction (i.e., along the x-axis), and a maximum height H.sub.EA also bounded by the lateral surface and measured in the vertical direction (i.e., along the z-axis). The maximum width W.sub.EA can be understood as corresponding to the greatest width of the electrode assembly **106** as measured from opposing points of the longitudinal end surfaces **116**, **118** of the electrode assembly **106** where the electrode assembly is widest in the longitudinal direction. For example, referring to the embodiment of the electrode assembly **106** in FIG. **1A**, the maximum width W.sub.EA can be understood as corresponding simply to the width of the assembly **106** as measured in the longitudinal direction. However, referring to the embodiment of the electrode assembly **106** shown in FIG. **5H**, it can be seen that the maximum width W.sub.EA corresponds to the width of the electrode assembly as measured from the two opposing points **300a**, **300b**, where the electrode assembly is widest in the longitudinal direction, as opposed to a width as measured from opposing points **301a**, **301b** where the electrode assembly **106** is more narrow. Similarly, the maximum length L.sub.EA can be understood as corresponding to the greatest length of the electrode assembly as measured from opposing points of the lateral surface **142** of the electrode assembly **106** where the electrode assembly is longest in the transverse direction. Referring again to the embodiment in FIG. **1A**, the maximum length L.sub.EA can be understood as simply the length of the electrode assembly **106**, whereas in the embodiment shown in FIG. **5H**, the maximum length L.sub.EA corresponds to the length of the electrode assembly as measured from two opposing points **302a**, **302b**, where the electrode assembly is longest in the transverse direction, as opposed to a length as measured from opposing points **303a**, **303b** where the electrode assembly is shorter. Along similar lines, the maximum height H.sub.EA can be understood as corresponding to the greatest height of the electrode assembly as measured from opposing points of the lateral surface **143** of the electrode assembly where the electrode assembly is highest in the vertical direction. That is, in the embodiment shown in FIG. **1A**, the maximum

height H.sub.EA is simply the height of the electrode assembly. While not specifically depicted in the embodiment shown in FIG. 5H, if the electrode assembly had different heights at points across one or more of the longitudinal and transverse directions, then the maximum height H.sub.EA of the electrode assembly would be understood to correspond to the height of the electrode assembly as measured from two opposing points where the electrode assembly is highest in the vertical direction, as opposed to a height as measured from opposing points where the electrode assembly is shorter, as analogously described for the maximum width W.sub.EA and maximum length L.sub.EA. The maximum length L.sub.EA, maximum width W.sub.EA, and maximum height H.sub.EA of the electrode assembly **106** may vary depending upon the energy storage device **100** and the intended use thereof. For example, in one embodiment, the electrode assembly **106** may include maximum lengths L.sub.EA, widths W.sub.EA, and heights H.sub.EA typical of conventional secondary battery dimensions. By way of further example, in one embodiment, the electrode assembly **106** may include maximum lengths L.sub.EA, widths W.sub.EA, and heights H.sub.EA typical of thin-film battery dimensions.

(120) In some embodiments, the dimensions L.sub.EA, W.sub.EA, and H.sub.EA are selected to provide an electrode assembly **106** having a maximum length L.sub.EA along the transverse axis (X axis) and/or a maximum width W.sub.EA along the longitudinal axis (Y axis) that is longer than the maximum height H.sub.EA along the vertical axis (Z axis). For example, in the embodiment shown in FIG. 1A, the dimensions L.sub.EA, W.sub.EA, and H.sub.EA are selected to provide an electrode assembly **106** having the greatest dimension along the transverse axis (X axis) that is orthogonal with electrode structure stacking direction D, as well as along the longitudinal axis (Y axis) coinciding with the electrode structure stacking direction D. That is, the maximum length L.sub.EA and/or maximum width W.sub.EA may be greater than the maximum height H.sub.EA. For example, in one embodiment, a ratio of the maximum length L.sub.EA to the maximum height H.sub.EA may be at least 2:1. By way of further example, in one embodiment a ratio of the maximum length L.sub.EA to the maximum height H.sub.EA may be at least 5:1. By way of further example, in one embodiment, the ratio of the maximum length L.sub.EA to the maximum height H.sub.EA may be at least 10:1. By way of further example, in one embodiment, the ratio of the maximum length L.sub.EA to the maximum height H.sub.EA may be at least 15:1. By way of further example, in one embodiment, the ratio of the maximum length L.sub.EA to the maximum height H.sub.EA may be at least 20:1. The ratios of the different dimensions may allow for optimal configurations within an energy storage device to maximize the amount of active materials, thereby increasing energy density.

(121) In some embodiments, the maximum width W.sub.EA may be selected to provide a width of the electrode assembly **106** that is greater than the maximum height H.sub.EA. For example, in one embodiment, a ratio of the maximum width W.sub.EA to the maximum height H.sub.EA may be at least 2:1. By way of further example, in one embodiment, the ratio of the maximum width W.sub.EA to the maximum height H.sub.EA may be at least 5:1. By way of further example, in one embodiment, the ratio of the maximum width W.sub.EA to the maximum height H.sub.EA may be at least 10:1. By way of further example, in one embodiment, the ratio of the maximum width W.sub.EA to the maximum height H.sub.EA may be at least 15:1. Byway of further example, in one embodiment, the ratio of the maximum width W.sub.EA to the maximum height H.sub.EA may be at least 20:1.

(122) According to one embodiment, a ratio of the maximum width W.sub.EA to the maximum length L.sub.EA may be selected to be within a predetermined range that provides for an optimal configuration. For example, in one embodiment, a ratio of the maximum width W.sub.EA to the maximum length L.sub.EA may be in the range of from 1:5 to 5:1. By way of further example, in one embodiment a ratio of the maximum width W.sub.EA to the maximum length L.sub.EA may be in the range of from 1:3 to 3:1. By way of yet a further example, in one embodiment a ratio of the maximum width W.sub.EA to the maximum length L.sub.EA may be in the range of from 1:2 to

2:1.

(123) In the embodiment as shown in FIG. 1A, the electrode assembly **106** has the first longitudinal end surface **116** and the opposing second longitudinal end surface **118** that is separated from the first longitudinal end surface **116** along the longitudinal axis A.sub.EA. The electrode assembly **106** further comprises a lateral surface **142** that at least partially surrounds the longitudinal axis A.sub.EA, and that connects the first and second longitudinal end surfaces **116**, **118**. In one embodiment, the maximum width W.sub.EA is the dimension along the longitudinal axis A.sub.EA as measured from the first longitudinal end surface **116** to the second longitudinal end surface **118**. Similarly, the maximum length L.sub.EA may be bounded by the lateral surface **142**, and in one embodiment, may be the dimension as measured from opposing first and second regions **144**, **146** of the lateral surface **142** along the transverse axis that is orthogonal to the longitudinal axis. The maximum height H.sub.EA, in one embodiment, may be bounded by the lateral surface **142** and may be measured from opposing first and second regions **148**, **150** of the lateral surface **142** along the vertical axis that is orthogonal to the longitudinal axis.

(124) For the purposes of clarity, only four anode structures **110** and four cathode structures **112** are illustrated in the embodiment shown in FIG. 1A. For example, the alternating sequence of members of the anode and cathode structure populations **110** and **112**, respectively, may include any number of members for each population, depending on the energy storage device **100** and the intended use thereof, and the alternating sequence of members of the anode and cathode structure populations **110** and **112** may be interdigitated, for example, as shown in FIG. 1A. By way of further example, in one embodiment, each member of the population of anode structures **110** may reside between two members of the population of cathode structures **112**, with the exception of when the alternating sequence terminates along the stacking direction, D. By way of further example, in one embodiment, each member of the population of cathode structures **112** may reside between two members of the population of anode structures **110**, with the exception of when the alternating sequence terminates along the stacking direction, D. By way of further example, in one embodiment, and stated more generally, the population of anode structures **110** and the population of cathode structures **112** each have N members, each of N-1 anode structure members **110** is between two cathode structure members **112**, each of N-1 cathode structure members **112** is between two anode structure members **110**, and N is at least 2. By way of further example, in one embodiment, N is at least 4. By way of further example, in one embodiment, N is at least 5. By way of further example, in one embodiment, N is at least 10. By way of further example, in one embodiment, N is at least 25. By way of further example, in one embodiment, N is at least 50. By way of further example, in one embodiment, N is at least 100 or more. In one embodiment, members of the anode and/or cathode populations extend sufficiently from an imaginary backplane (e.g., a plane substantially coincident with a surface of the anode assembly) to have a surface area (ignoring porosity) that is greater than twice the geometrical footprint (i.e., projection) of the members in the backplane. In certain embodiments, the ratio of the surface area of a non-laminar (i.e., three-dimensional) anode and/or cathode structure to its geometric footprint in the imaginary backplane may be at least about 5, at least about 10, at least about 50, at least about 100, or even at least about 500. In general, however, the ratio will be between about 2 and about 1000. In one such embodiment, members of the anode population are non-laminar in nature. By way of further example, in one such embodiment, members of the cathode population are non-laminar in nature. By way of further example, in one such embodiment, members of the anode population and members of the cathode population are non-laminar in nature.

(125) According to one embodiment, the electrode assembly **106** has longitudinal ends **117**, **119** at which the electrode assembly **106** terminates. According to one embodiment, the alternating sequence of anode and cathode structures **110**, **112**, respectively, in the electrode assembly **106** terminates in a symmetric fashion along the longitudinal direction, such as with anode structures **110** at each end **117**, **119** of the electrode assembly **106** in the longitudinal direction, or with

cathode structures **112** at each end **117**, **119** of the electrode assembly **106**, in the longitudinal direction. In another embodiment, the alternating sequence of anode **110** and cathode structures **112** may terminate in an asymmetric fashion along the longitudinal direction, such as with an anode structure **110** at one end **117** of the longitudinal axis A.sub.EA, and a cathode structure **112** at the other end **119** of the longitudinal axis A.sub.EA. According to yet another embodiment, the electrode assembly **106** may terminate with a substructure of one or more of an anode structure **110** and/or cathode structure **112** at one or more ends **117**, **119** of the electrode assembly **106**. By way of example, according to one embodiment, the alternating sequence of the anode **110** and cathode structures **112** can terminate at one or more substructures of the anode **110** and cathode structures **112**, including an anode backbone **134**, cathode backbone **141**, anode current collector **136**, cathode current collector **140**, anode active material layer **132**, cathode active material layer **138**, and the like, and may also terminate with a structure such as the separator **130**, and the structure at each longitudinal end **117**, **119** of the electrode assembly **106** may be the same (symmetric) or different (asymmetric). The longitudinal terminal ends **117**, **119** of the electrode assembly **106** can comprise the first and second longitudinal end surfaces **116**, **118** that are contacted by the first and second primary growth constraints **154**, **156** to constrain overall growth of the electrode assembly **106**.

(126) According to yet another embodiment, the electrode assembly **106** has first and second transverse ends **145**, **147** (see, e.g., FIG. 1A) that may contact one or more electrode and/or counter electrode tabs **190**, **192** (see, e.g., FIG. 9) that may be used to electrically connect the electrode and/or counter-electrode structures **110**, **112** to a load and/or a voltage supply (not shown). For example, the electrode assembly **106** can comprise an electrode bus **194** (see, e.g., FIG. 1A), to which each anode structure **110** can be connected, and that pools current from each member of the population of electrode structures **110**. Similarly, the electrode assembly **106** can comprise a cathode bus **196** to which each cathode structure **112** may be connected, and that pools current from each member of the population of cathode structures **112**. The anode and/or cathode buses **194**, **196** each have a length measured in direction D, and extending substantially the entire length of the interdigitated series of anode structures **110**, **112**. In the embodiment illustrated in FIG. 9, the anode tab **190** and/or cathode tab **192** includes anode tab extensions **191**, **193** which electrically connect with, and run substantially the entire length of anode and/or cathode bus **194**, **196**.

Alternatively, the anode and/or cathode tabs **190**, **192** may directly connect to the anode and/or cathode bus **194**, **196**, for example, an end or position intermediate thereof along the length of the buses **194**, **196**, without requiring the tab extensions **191**, **193**. Accordingly, in one embodiment, the anode and/or cathode buses **194**, **196** can form at least a portion of the terminal ends **145**, **147** of the electrode assembly **106** in the transverse direction, and connect the electrode assembly to the tabs **190**, **192** for electrical connection to a load and/or voltage supply (not shown). Furthermore, in yet another embodiment, the electrode assembly **106** comprises first and second terminal ends **149**, **153** disposed along the vertical (Z) axis. For example, according to one embodiment, each anode **110** and/or cathode structure **112**, is provided with a top and bottom coating of separator material, as shown in FIG. 1A, where the coatings form the terminal ends **149**, **153** of the electrode assembly **106** in the vertical direction. The terminal ends **149**, **153** that may be formed of the coating of separator material can comprise first and second surface regions **148**, **150** of the lateral surface **142** along the vertical axis that can be placed in contact with the first and second secondary growth constraints **158**, **160** to constrain growth in the vertical direction.

(127) In general, the electrode assembly **106** can comprise longitudinal end surfaces **116**, **118** that are planar, co-planar, or non-planar. For example, in one embodiment the opposing longitudinal end surfaces **116**, **118** may be convex. By way of further example, in one embodiment the opposing longitudinal end surfaces **116**, **118** may be concave. By way of further example, in one embodiment the opposing longitudinal end surfaces **116**, **118** are substantially planar. In certain embodiments, electrode assembly **106** may include opposing longitudinal end surfaces **116**, **118** having any range of two-dimensional shapes when projected onto a plane. For example, the longitudinal end surfaces

116, 118 may independently have a smooth curved shape (e.g., round, elliptical, hyperbolic, or parabolic), they may independently include a series of lines and vertices (e.g., polygonal), or they may independently include a smooth curved shape and include one or more lines and vertices. Similarly, the lateral surface **142** of the electrode assembly **106** may be a smooth curved shape (e.g., the electrode assembly **106** may have a round, elliptical, hyperbolic, or parabolic cross-sectional shape) or the lateral surface **142** may include two or more lines connected at vertices (e.g., the electrode assembly **106** may have a polygonal cross-section). For example, in one embodiment, the electrode assembly **106** has a cylindrical, elliptic cylindrical, parabolic cylindrical, or hyperbolic cylindrical shape. By way of further example, in one such embodiment, the electrode assembly **106** may have a prismatic shape, having opposing longitudinal end surfaces **116, 118** of the same size and shape and a lateral surface **142** (i.e., the faces extending between the opposing longitudinal end surfaces **116** and **118**) being parallelogram-shaped. By way of further example, in one such embodiment, the electrode assembly **106** has a shape that corresponds to a triangular prism, the electrode assembly **106** having two opposing triangular longitudinal end surfaces **116** and **118** and a lateral surface **142** consisting of three parallelograms (e.g., rectangles) extending between the two longitudinal ends. By way of further example, in one such embodiment, the electrode assembly **106** has a shape that corresponds to a rectangular prism, the electrode assembly **106** having two opposing rectangular longitudinal end surfaces **116** and **118**, and a lateral surface **142** comprising four parallelogram (e.g., rectangular) faces. By way of further example, in one such embodiment, the electrode assembly **106** has a shape that corresponds to a pentagonal prism, hexagonal prism, etc. wherein the electrode assembly **106** has two pentagonal, hexagonal, etc., respectively, opposing longitudinal end surfaces **116** and **118**, and a lateral surface comprising five, six, etc., respectively, parallelograms (e.g., rectangular) faces.

(128) Referring now to FIGS. 5A-5H, several exemplary geometric shapes are schematically illustrated for electrode assembly **106**. More specifically, in FIG. 5A, electrode assembly **106** has a triangular prismatic shape with opposing first and second longitudinal end surfaces **116, 118** separated along longitudinal axis A.sub.EA, and a lateral surface **142** including the three rectangular faces connecting the longitudinal end surfaces **116, 118**, that are about the longitudinal axis A.sub.EA. In FIG. 5B, electrode assembly **106** has a parallelepiped shape with opposing first and second parallelogram longitudinal end surfaces **116, 118** separated along longitudinal axis A.sub.EA, and a lateral surface **142** including the four parallelogram-shaped faces connecting the two longitudinal end surfaces **116, 118**, and surrounding longitudinal axis A.sub.EA. In FIG. 5C, electrode assembly **106** has a rectangular prism shape with opposing first and second rectangular longitudinal end surfaces **116, 118** separated along longitudinal axis A.sub.EA, and a lateral surface **142** including the four rectangular faces connecting the two longitudinal end surfaces **116, 118** and surrounding longitudinal axis A.sub.EA. In FIG. 5D, electrode assembly **106** has a pentagonal prismatic shape with opposing first and second pentagonal longitudinal end surfaces **116, 118** separated along longitudinal axis A.sub.EA, and a lateral surface **142** including the five rectangular faces connecting the two longitudinal end surfaces **116, 118** and surrounding longitudinal axis A.sub.EA. In FIG. 5E, electrode assembly **106** has a hexagonal prismatic shape with opposing first and second hexagonal longitudinal end surfaces **116, 118** separated along longitudinal axis A.sub.EA, and a lateral surface **142** including the six rectangular faces connecting the two longitudinal end surfaces **116, 118** and surrounding longitudinal axis A.sub.EA. In FIG. 5F, the electrode assembly has a square pyramidal frustum shape with opposing first and second square end surfaces **116, 118** separated along longitudinal axis A.sub.EA, and a lateral surface **142** including four trapezoidal faces connecting the two longitudinal end surfaces **116, 118** and surrounding longitudinal axis A.sub.EA, with the trapezoidal faces tapering in dimension along the longitudinal axis from a greater dimension at the first surface **116** to a smaller dimension at the second surface **118**, and the size of the second surface being smaller than that of the first surface. In FIG. 5G, the electrode assembly has a pentagonal pyramidal frustum shape with opposing first and

second square end surfaces **116**, **118** separated along longitudinal axis A.sub.EA, and a lateral surface **142** including five trapezoidal faces connecting the two longitudinal end surfaces **116**, **118** and surrounding longitudinal axis A.sub.EA, with the trapezoidal faces tapering in dimension along the longitudinal axis from a greater dimension at the first surface **116** to a smaller dimension at the second surface **118**, and the size of the second surface being smaller than that of the first surface. In FIG. 5H, the electrode assembly **106** has a pyramidal shape in the longitudinal direction, by virtue of electrode and counter-electrode structures **110**, **112** having lengths that decrease from a first length towards the middle of the electrode assembly **106** on the longitudinal axis, to second lengths at the longitudinal ends **117**, **119** of the electrode assembly **106**.

(129) Electrode Constraints

(130) In one embodiment, a set of electrode constraints **108** is provided that that restrains overall macroscopic growth of the electrode assembly **106**, as illustrated for example in FIGS. 1A-1B. The set of electrode constraints **108** may be capable of restraining growth of the electrode assembly **106** along one or more dimensions, such as to reduce swelling and deformation of the electrode assembly **106**, and thereby improve the reliability and cycling lifetime of an energy storage device **100** having the set of electrode constraints **108**. As discussed above, without being limited to any one particular theory, it is believed that carrier ions traveling between the anode structures **110** and cathode structures **112** during charging and/or discharging of a secondary battery **102** can become inserted into anode active material, causing the anode active material and/or the anode structure **110** to expand. This expansion of the anode structure **110** can cause the electrodes and/or electrode assembly **106** to deform and swell, thereby compromising the structural integrity of the electrode assembly **106**, and/or increasing the likelihood of electrical shorting or other failures. In one example, excessive swelling and/or expansion and contraction of the anode active material layer **132** during cycling of an energy storage device **100** can cause fragments of anode active material to break away and/or delaminate from the anode active material layer **132**, thereby compromising the efficiency and cycling lifetime of the energy storage device **100**. In yet another example, excessive swelling and/or expansion and contraction of the anode active material layer **132** can cause anode active material to breach the electrically insulating microporous separator **130**, thereby causing electrical shorting and other failures of the electrode assembly **106**. Accordingly, the set of electrode constraints **108** inhibit this swelling or growth that can otherwise occur with cycling between charged and discharged states to improve the reliability, efficiency, and/or cycling lifetime of the energy storage device **100**.

(131) According to one embodiment, the set of electrode constraints **108** comprises a primary growth constraint system **151** to restrain growth and/or swelling along the longitudinal axis (e.g., Y-axis in FIGS. 1A-1B) of the electrode assembly **106**. In another embodiment, the set of electrode constraints **108** may include a secondary growth constraint system **152** that restrains growth along the vertical axis (e.g., Z-axis in FIG. 1). In yet another embodiment, the set of electrode constraints **108** may include a tertiary growth constraint system **155** that restrains growth along the transverse axis (e.g., X-axis in FIG. 4C). In one embodiment, the set of electrode constraints **108** comprises primary growth and secondary growth constraint systems **151**, **152**, respectively, and even tertiary growth constraint systems **155** that operate cooperatively to simultaneously restrain growth in one or more directions, such as along the longitudinal and vertical axis (e.g., Y axis and Z axis), and even simultaneously along all of the longitudinal, vertical, and transverse axes (e.g., Y, Z, and X axes). For example, the primary growth constraint system **151** may restrain growth that can otherwise occur along the stacking direction D of the electrode assembly **106** during cycling between charged and discharged states, while the secondary growth constraint system **152** may restrain swelling and growth that can occur along the vertical axis, to prevent buckling or other deformation of the electrode assembly **106** in the vertical direction. By way of further example, in one embodiment, the secondary growth constraint system **152** can reduce swelling and/or expansion along the vertical axis that would otherwise be exacerbated by the restraint on growth

imposed by the primary growth constraint system **151**. The tertiary growth constraint system **155** can also optionally reduce swelling and/or expansion along the transverse axis that could occur during cycling processes. That is, according to one embodiment, the primary growth and secondary growth constraint systems **151**, **152**, respectively, and optionally the tertiary growth constraint system **155**, may operate together to cooperatively restrain multi-dimensional growth of the electrode assembly **106**.

(132) Referring to FIGS. **6A-6B**, an embodiment of a set of electrode constraints **108** is shown having a primary growth constraint system **151** and a secondary growth constraint system **152** for an electrode assembly **106**. FIG. **6A** shows a cross-section of the electrode assembly **106** in FIG. **1** taken along the longitudinal axis (Y axis), such that the resulting 2-D cross-section is illustrated with the vertical axis (Z axis) and longitudinal axis (Y axis). FIG. **6B** shows a cross-section of the electrode assembly **106** in FIG. **1** taken along the transverse axis (X axis), such that the resulting 2-D cross-section is illustrated with the vertical axis (Z axis) and transverse axis (X axis). As shown in FIG. **6A**, the primary growth constraint system **151** can generally comprise first and second primary growth constraints **154**, **156**, respectively, that are separated from one another along the longitudinal direction (Y axis). For example, in one embodiment, the first and second primary growth constraints **154**, **156**, respectively, comprise a first primary growth constraint **154** that at least partially or even entirely covers a first longitudinal end surface **116** of the electrode assembly **106**, and a second primary growth constraint **156** that at least partially or even entirely covers a second longitudinal end surface **118** of the electrode assembly **106**. In yet another version, one or more of the first and second primary growth constraints **154**, **156** may be interior to a longitudinal end **117**, **119** of the electrode assembly **106**, such as when one or more of the primary growth constraints comprise an internal structure of the electrode assembly **106**. The primary growth constraint system **151** can further comprise at least one primary connecting member **162** that connects the first and second primary growth constraints **154**, **156**, and that may have a principal axis that is parallel to the longitudinal direction. For example, the primary growth constraint system **151** can comprise first and second primary connecting members **162**, **164**, respectively, that are separated from each other along an axis that is orthogonal to the longitudinal axis, such as along the vertical axis (Z axis) as depicted in the embodiment. The first and second primary connecting members **162**, **164**, respectively, can serve to connect the first and second primary growth constraints **154**, **156**, respectively, to one another, and to maintain the first and second primary growth constraints **154**, **156**, respectively, in tension with one another, so as to restrain growth along the longitudinal axis of the electrode assembly **106**.

(133) According to one embodiment, the set of electrode constraints **108** including the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction (i.e., electrode stacking direction, D) such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 20 consecutive cycles of the secondary battery is less than 20% between charged and discharged states. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 30 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 50 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 80 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable

[illegible]

the electrode assembly in the longitudinal direction over 10,000 consecutive cycles of the secondary battery is less than 10%.

[illegible]

constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 300 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 500 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 800 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 1000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 2000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 3000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 5000 consecutive cycles of the secondary battery is less than 1% between charged and discharged states. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 8000 consecutive cycles of the secondary battery to less than 1%. By way of further example, in one embodiment the primary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the longitudinal direction such that any increase in the Feret diameter of the electrode assembly in the longitudinal direction over 10,000 consecutive cycles of the secondary battery to less than 1%.

(137) By charged state it is meant that the secondary battery **102** is charged to at least 75% of its rated capacity, such as at least 80% of its rated capacity, and even at least 90% of its rated capacity, such as at least 95% of its rated capacity, and even 100% of its rated capacity. By discharged state it is meant that the secondary battery is discharged to less than 25% of its rated capacity, such as less than 20% of its rated capacity, and even less than 10%, such as less than 5%, and even 0% of its rated capacity. Furthermore, it is noted that the actual capacity of the secondary battery **102** may vary over time and with the number of cycles the battery has gone through. That is, while the secondary battery **102** may initially exhibit an actual measured capacity that is close to its rated capacity, the actual capacity of the battery will decrease over time, with the secondary battery **102** being considered to be at the end of its life when the actual capacity drops below 80% of the rated capacity as measured in going from a charged to a discharged state.

(138) Further shown in FIGS. **6A** and **6B**, the set of electrode constraints **108** can further comprise the secondary growth constraint system **152**, that can generally comprise first and second secondary growth constraints **158**, **160**, respectively, that are separated from one another along a second direction orthogonal to the longitudinal direction, such as along the vertical axis (Z axis) in the embodiment as shown. For example, in one embodiment, the first secondary growth constraint **158** at least partially extends across a first region **148** of the lateral surface **142** of the electrode

assembly **106**, and the second secondary growth constraint **160** at least partially extends across a second region **150** of the lateral surface **142** of the electrode assembly **106** that opposes the first region **148**. In yet another version, one or more of the first and second secondary growth constraints **154**, **156** may be interior to the lateral surface **142** of the electrode assembly **106**, such as when one or more of the secondary growth constraints comprise an internal structure of the electrode assembly **106**. In one embodiment, the first and second secondary growth constraints **158**, **160**, respectively, are connected by at least one secondary connecting member **166**, which may have a principal axis that is parallel to the second direction, such as the vertical axis. The secondary connecting member **166** may serve to connect and hold the first and second secondary growth constraints **158**, **160**, respectively, in tension with one another, so as to restrain growth of the electrode assembly **106** along a direction orthogonal to the longitudinal direction, such as for example to restrain growth in the vertical direction (e.g., along the Z axis). In the embodiment depicted in FIG. 6A, the at least one secondary connecting member **166** can correspond to at least one of the first and second primary growth constraints **154**, **156**. However, the secondary connecting member **166** is not limited thereto, and can alternatively and/or in addition comprise other structures and/or configurations.

(139) According to one embodiment, the set of constraints including the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in a second direction orthogonal to the longitudinal direction, such as the vertical direction (Z axis), such that any increase in the Feret diameter of the electrode assembly in the second direction over 20 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 30 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 50 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 80 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 100 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 200 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 300 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 500 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 800 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the

[illegible]

second direction over 5000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the secondary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 8000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the secondary growth constraint system **151** may be capable of restraining growth of the electrode assembly **106** in the second direction such that any increase in the Feret diameter of the electrode assembly in the second direction over 10,000 consecutive cycles of the secondary battery is less than 1%.

(143) FIG. **6C** shows an embodiment of a set of electrode constraints **108** that further includes a tertiary growth constraint system **155** to constrain growth of the electrode assembly in a third direction that is orthogonal to the longitudinal and second directions, such as the transverse direction (X) direction. The tertiary growth constraint system **155** can be provided in addition to the primary and secondary growth constraint systems **151**, **152**, respectively, to constrain overall growth of the electrode assembly **106** in three dimensions, and/or may be provided in combination with one of the primary or secondary growth constraint systems **151**, **152**, respectively, to constrain overall growth of the electrode assembly **106** in two dimensions. FIG. **6C** shows a cross-section of the electrode assembly **106** in FIG. **1A** taken along the transverse axis (X axis), such that the resulting 2-D cross-section is illustrated with the vertical axis (Z axis) and transverse axis (X axis). As shown in FIG. **6C**, the tertiary growth constraint system **155** can generally comprise first and second tertiary growth constraints **157**, **159**, respectively, that are separated from one another along the third direction such as the transverse direction (X axis). For example, in one embodiment, the first tertiary growth constraint **157** at least partially extends across a first region **144** of the lateral surface **142** of the electrode assembly **106**, and the second tertiary growth constraint **159** at least partially extends across a second region **146** of the lateral surface **142** of the electrode assembly **106** that opposes the first region **144** in the transverse direction. In yet another version, one or more of the first and second tertiary growth constraints **157**, **159** may be interior to the lateral surface **142** of the electrode assembly **106**, such as when one or more of the tertiary growth constraints comprise an internal structure of the electrode assembly **106**. In one embodiment, the first and second tertiary growth constraints **157**, **159**, respectively, are connected by at least one tertiary connecting member **165**, which may have a principal axis that is parallel to the third direction. The tertiary connecting member **165** may serve to connect and hold the first and second tertiary growth constraints **157**, **159**, respectively, in tension with one another, so as to restrain growth of the electrode assembly **106** along a direction orthogonal to the longitudinal direction, for example, to restrain growth in the transverse direction (e.g., along the X axis). In the embodiment depicted in FIG. **6C**, the at least one tertiary connecting member **165** can correspond to at least one of the first and second secondary growth constraints **158**, **160**. However, the tertiary connecting member **165** is not limited thereto, and can alternatively and/or in addition comprise other structures and/or configurations. For example, the at least one tertiary connecting member **165** can, in one embodiment, correspond to at least one of the first and second primary growth constraints **154**, **156** (not shown).

(144) According to one embodiment, the set of constraints having the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in a third direction orthogonal to the longitudinal direction, such as the transverse direction (X axis), such that any increase in the Feret diameter of the electrode assembly in the third direction over 20 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 30 consecutive cycles of the secondary battery is less than 20%. By way of further example, in one embodiment the tertiary growth constraint system **155**

[illegible]

[illegible]

electrode assembly in the third direction over 3000 consecutive cycles of the secondary battery is less than 5%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 5000 consecutive cycles of the secondary battery is less than 5%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 8000 consecutive cycles of the secondary battery is less than 5%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 10,000 consecutive cycles of the secondary battery is less than 5%.

[illegible]

secondary battery is less than 1%. By way of further example, in one embodiment the tertiary growth constraint system **152** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 800 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 1000 consecutive cycles of the secondary battery is less than 1% between charged and discharged states. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 2000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 3000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 5000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 8000 consecutive cycles of the secondary battery is less than 1%. By way of further example, in one embodiment the tertiary growth constraint system **155** may be capable of restraining growth of the electrode assembly **106** in the third direction such that any increase in the Feret diameter of the electrode assembly in the third direction over 10,000 consecutive cycles of the secondary battery is less than 1%.

(148) According to one embodiment, the primary and secondary growth constraint systems **151**, **152**, respectively, and optionally the tertiary growth constraint system **155**, are configured to cooperatively operate such that portions of the primary growth constraint system **151** cooperatively act as a part of the secondary growth constraint system **152**, and/or portions of the secondary growth constraint system **152** cooperatively act as a part of the primary growth constraint system **151**, and the portions of any of the primary and/or secondary constraint systems **151**, **152**, respectively, may also cooperatively act as a part of the tertiary growth constraint system, and vice versa. For example, in the embodiment shown in in FIGS. **6A** and **6B**, the first and second primary connecting members **162**, **164**, respectively, of the primary growth constraint system **151** can serve as at least a portion of, or even the entire structure of, the first and second secondary growth constraints **158**, **160** that constrain growth in the second direction orthogonal to the longitudinal direction. In yet another embodiment, as mentioned above, one or more of the first and second primary growth constraints **154**, **156**, respectively, can serve as one or more secondary connecting members **166** to connect the first and second secondary growth constraints **158**, **160**, respectively. Conversely, at least a portion of the first and second secondary growth constraints **158**, **160**, respectively, can act as first and second primary connecting members **162**, **164**, respectively, of the primary growth constraint system **151**, and the at least one secondary connecting member **166** of the secondary growth constraint system **152** can, in one embodiment, act as one or more of the first and second primary growth constraints **154**, **156**, respectively. In yet another embodiment, at least a portion of the first and second primary connecting members **162**, **164**, respectively, of the primary growth constraint system **151**, and/or the at least one secondary connecting member **166** of the secondary growth constraint system **152** can serve as at least a portion of, or even the entire structure of, the first and second tertiary growth constraints **157**, **159**, respectively, that constrain growth in the transverse direction orthogonal to the longitudinal direction. In yet another

embodiment, one or more of the first and second primary growth constraints **154**, **156**, respectively, and/or the first and second secondary growth constraints **158**, **160**, respectively, can serve as one or more tertiary connecting members **166** to connect the first and second tertiary growth constraints **157**, **159**, respectively. Conversely, at least a portion of the first and second tertiary growth constraints **157**, **159**, respectively, can act as first and second primary connecting members **162**, **164**, respectively, of the primary growth constraint system **151**, and/or the at least one secondary connecting member **166** of the secondary growth constraint system **152**, and the at least one tertiary connecting member **165** of the tertiary growth constraint system **155** can in one embodiment act as one or more of the first and second primary growth constraints **154**, **156**, respectively, and/or one or more of the first and second secondary growth constraints **158**, **160**, respectively. Alternatively and/or additionally, the primary and/or secondary and/or tertiary growth constraints can comprise other structures that cooperate to restrain growth of the electrode assembly **106**. Accordingly, the primary and secondary growth constraint systems **151**, **152**, respectively, and optionally the tertiary growth constraint system **155**, can share components and/or structures to exert restraint on the growth of the electrode assembly **106**.

(149) In one embodiment, the set of electrode constraints **108** can comprise structures such as the primary and secondary growth constraints, and primary and secondary connecting members, that are structures that are external to and/or internal to the battery enclosure **104**, or may be a part of the battery enclosure **104** itself. For example, the set of electrode constraints **108** can comprise a combination of structures that includes the battery enclosure **104** as well as other structural components. In one such embodiment, the battery enclosure **104** may be a component of the primary growth constraint system **151** and/or the secondary growth constraint system **152**; stated differently, in one embodiment, the battery enclosure **104**, alone or in combination with one or more other structures (within and/or outside the battery enclosure **104**, for example, the primary growth constraint system **151** and/or a secondary growth constraint system **152**) restrains growth of the electrode assembly **106** in the electrode stacking direction D and/or in the second direction orthogonal to the stacking direction, D. For example, one or more of the primary growth constraints **154**, **156** and secondary growth constraints **158**, **160** can comprise a structure that is internal to the electrode assembly. In another embodiment, the primary growth constraint system **151** and/or secondary growth constraint system **152** does not include the battery enclosure **104**, and instead one or more discrete structures (within and/or outside the battery enclosure **104**) other than the battery enclosure **104** restrains growth of the electrode assembly **106** in the electrode stacking direction, D, and/or in the second direction orthogonal to the stacking direction, D. The electrode assembly **106** may be restrained by the set of electrode constraints **108** at a pressure that is greater than the pressure exerted by growth and/or swelling of the electrode assembly **106** during repeated cycling of an energy storage device **100** or a secondary battery having the electrode assembly **106**.

(150) In one exemplary embodiment, the primary growth constraint system **151** includes one or more discrete structure(s) within the battery enclosure **104** that restrains growth of the anode structure **110** in the stacking direction D by exerting a pressure that exceeds the pressure generated by the anode structure **110** in the stacking direction D upon repeated cycling of a secondary battery **102** having the anode structure **110** as a part of the electrode assembly **106**. In another exemplary embodiment, the primary growth constraint system **151** includes one or more discrete structures within the battery enclosure **104** that restrains growth of the cathode structure **112** in the stacking direction D by exerting a pressure in the stacking direction D that exceeds the pressure generated by the anode structure **112** in the stacking direction D upon repeated cycling of a secondary battery **102** having the cathode structure **112** as a part of the electrode assembly **106**. The secondary growth constraint system **152** can similarly include one or more discrete structures within the battery enclosure **104** that restrain growth of at least one of the anode structures **110** and cathode structures **112** in the second direction orthogonal to the stacking direction D, such as along the vertical axis (Z axis), by exerting a pressure in the second direction that exceeds the pressure

generated by the anode or cathode structure **110**, **112**, respectively, in the second direction upon repeated cycling of a secondary battery **102** having the anode or cathode structures **110**, **112**, respectively.

(151) In yet another embodiment, the first and second primary growth constraints **154**, **156**, respectively, of the primary growth constraint system **151** restrain growth of the electrode assembly **106** by exerting a pressure on the first and second longitudinal end surfaces **116**, **118** of the electrode assembly **106**, meaning, in a longitudinal direction, that exceeds a pressure exerted by the first and second primary growth constraints **154**, **156** on other surfaces of the electrode assembly **106** that would be in a direction orthogonal to the longitudinal direction, such as opposing first and second regions of the lateral surface **142** of the electrode assembly **106** along the transverse axis and/or vertical axis. That is, the first and second primary growth constraints **154**, **156** may exert a pressure in a longitudinal direction (Y axis) that exceeds a pressure generated thereby in directions orthogonal thereto, such as the transverse (X axis) and vertical (Z axis) directions. For example, in one such embodiment, the primary growth constraint system **151** restrains growth of the electrode assembly **106** with a pressure on first and second longitudinal end surfaces **116**, **118** (i.e., in the stacking direction D) that exceeds the pressure maintained on the electrode assembly **106** by the primary growth constraint system **151** in at least one, or even both, of the two directions that are perpendicular to the stacking direction D, by a factor of at least 3. By way of further example, in one such embodiment, the primary growth constraint system **151** restrains growth of the electrode assembly **106** with a pressure on first and second longitudinal end surfaces **116**, **118** (i.e., in the stacking direction D) that exceeds the pressure maintained on the electrode assembly **106** by the primary growth constraint system **151** in at least one, or even both, of the two directions that are perpendicular to the stacking direction D by a factor of at least 4. By way of further example, in one such embodiment, the primary growth constraint system **151** restrains growth of the electrode assembly **106** with a pressure on first and second longitudinal end surfaces **116**, **118** (i.e., in the stacking direction D) that exceeds the pressure maintained on the electrode assembly **106** in at least one, or even both, of the two directions that are perpendicular to the stacking direction D, by a factor of at least 5.

(152) Similarly, in one embodiment, the first and second secondary growth constraints **158**, **160**, respectively, of the primary growth constraint system **151** restrain growth of the electrode assembly **106** by exerting a pressure on first and second opposing regions of the lateral surface **142** of the electrode assembly **106** in a second direction orthogonal to the longitudinal direction, such as first and second opposing surface regions along the vertical axis **148**, **150**, respectively (i.e., in a vertical direction), that exceeds a pressure exerted by the first and second secondary growth constraints **158**, **160**, respectively, on other surfaces of the electrode assembly **106** that would be in a direction orthogonal to the second direction. That is, the first and second secondary growth constraints **158**, **160**, respectively, may exert a pressure in a vertical direction (Z axis) that exceeds a pressure generated thereby in directions orthogonal thereto, such as the transverse (X axis) and longitudinal (Y axis) directions. For example, in one such embodiment, the secondary growth constraint system **152** restrains growth of the electrode assembly **106** with a pressure on first and second opposing surface regions **148**, **150**, respectively (i.e., in the vertical direction), that exceeds the pressure maintained on the electrode assembly **106** by the secondary growth constraint system **152** in at least one, or even both, of the two directions that are perpendicular thereto, by a factor of at least 3. By way of further example, in one such embodiment, the secondary growth constraint system **152** restrains growth of the electrode assembly **106** with a pressure on first and second opposing surface regions **148**, **150**, respectively (i.e., in the vertical direction), that exceeds the pressure maintained on the electrode assembly **106** by the secondary growth constraint system **152** in at least one, or even both, of the two directions that are perpendicular thereto, by a factor of at least 4. By way of further example, in one such embodiment, the secondary growth constraint system **152** restrains growth of the electrode assembly **106** with a pressure on first and second opposing surface regions

148, 150, respectively (i.e., in the vertical direction), that exceeds the pressure maintained on the electrode assembly **106** in at least one, or even both, of the two directions that are perpendicular thereto, by a factor of at least 5.

(153) In yet another embodiment, the first and second tertiary growth constraints **157, 159**, respectively, of the tertiary growth constraint system **155** restrain growth of the electrode assembly **106** by exerting a pressure on first and second opposing regions of the lateral surface **142** of the electrode assembly **106** in a direction orthogonal to the longitudinal direction and the second direction, such as first and second opposing surface regions along the transverse axis **161, 163**, respectively (i.e., in a transverse direction), that exceeds a pressure exerted by the tertiary growth constraint system **155** on other surfaces of the electrode assembly **106** that would be in a direction orthogonal to the transverse direction. That is, the first and second tertiary growth constraints **157, 159**, respectively, may exert a pressure in a transverse direction (X axis) that exceeds a pressure generated thereby in directions orthogonal thereto, such as the vertical (Z axis) and longitudinal (Y axis) directions. For example, in one such embodiment, the tertiary growth constraint system **155** restrains growth of the electrode assembly **106** with a pressure on first and second opposing surface regions **144, 146** (i.e., in the transverse direction) that exceeds the pressure maintained on the electrode assembly **106** by the tertiary growth constraint system **155** in at least one, or even both, of the two directions that are perpendicular thereto, by a factor of at least 3. By way of further example, in one such embodiment, the tertiary growth constraint system **155** restrains growth of the electrode assembly **106** with a pressure on first and second opposing surface regions **144, 146**, respectively (i.e., in the transverse direction), that exceeds the pressure maintained on the electrode assembly **106** by the tertiary growth constraint system **155** in at least one, or even both, of the two directions that are perpendicular thereto, by a factor of at least 4. By way of further example, in one such embodiment, the tertiary growth constraint system **155** restrains growth of the electrode assembly **106** with a pressure on first and second opposing surface regions **144, 146**, respectively (i.e., in the transverse direction), that exceeds the pressure maintained on the electrode assembly **106** in at least one, or even both, of the two directions that are perpendicular thereto, by a factor of at least 5.

(154) In one embodiment, the set of electrode constraints **108**, which may include the primary growth constraint system **151**, the secondary growth constraint system **152**, and optionally the tertiary growth constraint system **155**, is configured to exert pressure on the electrode assembly **106** along two or more dimensions thereof (e.g., along the longitudinal and vertical directions, and optionally along the transverse direction), with a pressure being exerted along the longitudinal direction by the set of electrode constraints **108** being greater than any pressure(s) exerted by the set of electrode constraints **108** in any of the directions orthogonal to the longitudinal direction (e.g., the Z and X directions). That is, when the pressure(s) exerted by the primary, secondary, and optionally tertiary growth constraint systems **151, 152, 155**, respectively, making up the set of electrode constraints **108** are summed together, the pressure exerted on the electrode assembly **106** along the longitudinal axis exceeds the pressure(s) exerted on the electrode assembly **106** in the directions orthogonal thereto. For example, in one such embodiment, the set of electrode constraints **108** exerts a pressure on the first and second longitudinal end surfaces **116, 118** (i.e., in the stacking direction D) that exceeds the pressure maintained on the electrode assembly **106** by the set of electrode constraints **108** in at least one or even both of the two directions that are perpendicular to the stacking direction D, by a factor of at least 3. By way of further example, in one such embodiment, the set of electrode constraints **108** exerts a pressure on first and second longitudinal end surfaces **116, 118** (i.e., in the stacking direction D) that exceeds the pressure maintained on the electrode assembly **106** by the set of electrode constraints **108** in at least one, or even both, of the two directions that are perpendicular to the stacking direction D by a factor of at least 4. By way of further example, in one such embodiment, the set of electrode constraints **108** exerts a pressure on first and second longitudinal end surfaces **116, 118** (i.e., in the stacking

direction D) that exceeds the pressure maintained on the electrode assembly **106** in at least one, or even both, of the two directions that are perpendicular to the stacking direction D, by a factor of at least 5.

(155) According to one embodiment, the first and second longitudinal end surfaces **116**, **118**, respectively, have a combined surface area that is less than a predetermined amount of the overall surface area of the entire electrode assembly **106**. For example, in one embodiment, the electrode assembly **106** may have a geometric shape corresponding to that of a rectangular prism with first and second longitudinal end surfaces **116**, **118**, respectively, and a lateral surface **142** extending between the end surfaces **116**, **118**, respectively, that makes up the remaining surface of the electrode assembly **106**, and that has opposing surface regions **144**, **146** in the X direction (i.e., the side surfaces of the rectangular prism) and opposing surface regions **148**, **150** in the Z direction (i.e., the top and bottom surfaces of the rectangular prism, wherein X, Y and Z are dimensions measured in directions corresponding to the X, Y, and Z axes, respectively). The overall surface area is thus the sum of the surface area covered by the lateral surface **142** (i.e., the surface area of the opposing surfaces **144**, **146**, **148**, and **150** in X and Z), added to the surface area of the first and second longitudinal end surfaces **116**, **118**, respectively. In accordance with one aspect of the present disclosure, the sum of the surface areas of the first and second longitudinal end surfaces **116**, **118**, respectively, is less than 33% of the surface area of the total surface of the electrode assembly **106**. For example, in one such embodiment, the sum of the surface areas of the first and second longitudinal end surfaces **116**, **118**, respectively, is less than 25% of the surface area of the total surface of the electrode assembly **106**. By way of further example, in one embodiment, the sum of the surface areas of the first and second longitudinal end surfaces **116**, **118**, respectively, is less than 20% of the surface area of the total surface of the electrode assembly. By way of further example, in one embodiment, the sum of the surface areas of the first and second longitudinal end surfaces **116**, **118**, respectively, is less than 15% of the surface area of the total surface of the electrode assembly. By way of further example, in one embodiment, the sum of the surface areas of the first and second longitudinal end surfaces **116**, **118**, respectively, is less than 10% of the surface area of the total surface of the electrode assembly.

(156) In yet another embodiment, the electrode assembly **106** is configured such that a surface area of a projection of the electrode assembly **106** in a plane orthogonal to the stacking direction (i.e., the longitudinal direction), is smaller than the surface areas of projections of the electrode assembly **106** onto other orthogonal planes. For example, referring to the electrode assembly **106** embodiment shown in FIG. 1A (e.g., a rectangular prism), it can be seen that surface area of a projection of the electrode assembly **106** into a plane orthogonal to the stacking direction (i.e., the X-Z plane) corresponds to $L_{\text{sub.EA}} \times H_{\text{sub.EA}}$. Similarly, a projection of the electrode assembly **106** into the Z-Y plane corresponds to $W_{\text{sub.EA}} \times H_{\text{sub.EA}}$, and a projection of the electrode assembly **106** into the X-Y plane corresponds to $L_{\text{sub.EA}} \times W_{\text{sub.EA}}$. Accordingly, the electrode assembly **106** is configured such that the stacking direction intersects the plane in which the projection having the smallest surface area lies. Accordingly, in the embodiment in FIG. 2, the electrode assembly **106** is positioned such that the stacking direction intersects the X-Z plane in which the smallest surface area projection corresponding to $H_{\text{sub.EA}} \times L_{\text{sub.EA}}$ lies. That is, the electrode assembly is positioned such that the projection having the smallest surface area (e.g., $H_{\text{sub.EA}} \times L_{\text{sub.EA}}$) is orthogonal to the stacking direction.

(157) In yet another embodiment, the secondary battery **102** can comprise a plurality of electrode assemblies **106** that are stacked together to form an electrode stack, and can be constrained by one or more shared electrode constraints. For example, in one embodiment, at least a portion of one or more of the primary growth constraint system **151** and the secondary growth constraint system **152** can be shared by a plurality of electrode assemblies **106** forming the electrode assembly stack. By way of further example, in one embodiment, a plurality of electrode assemblies forming an electrode assembly stack may be constrained in a vertical direction by a secondary growth

constraint system **152** having a first secondary growth constraint **158** at a top electrode assembly **106** of the stack, and a second secondary growth constraint **160** at a bottom electrode assembly **106** of the stack, such that the plurality of electrode assemblies **106** forming the stack are constrained in the vertical direction by the shared secondary growth constraint system. Similarly, portions of the primary growth constraint system **151** could also be shared. Accordingly, in one embodiment, similarly to the single electrode assembly described above, a surface area of a projection of the stack of electrode assemblies **106** in a plane orthogonal to the stacking direction (i.e., the longitudinal direction), is smaller than the surface areas of projections of the stack of electrode assemblies **106** onto other orthogonal planes. That is, the plurality of electrode assemblies **106** may be configured such that the stacking direction (i.e., longitudinal direction) intersects and is orthogonal to a plane that has a projection of the stack of electrode assemblies **106** that is the smallest of all the other orthogonal projections of the electrode assembly stack.

(158) According to one embodiment, the electrode assembly **106** further comprises anode structures **110** that are configured such that a surface area of a projection of the anode structures **110** into a plane orthogonal to the stacking direction (i.e., the longitudinal direction), is larger than the surface areas of projections of the electrode structures **100** onto other orthogonal planes. For example, referring to the embodiments as shown in FIGS. **1A** and **7**, the anodes **110** can each be understood to have a length $L_{sub.A}$ measured in the transverse direction, a width $W_{sub.A}$ measured in the longitudinal direction, and a height $H_{sub.A}$ measured in the vertical direction. The projection into the X-Z plane as shown in FIGS. **1A** and **7** thus has a surface area $L_{sub.A} \times H_{sub.A}$, the projection into the Y-Z plane has a surface area $W_{sub.A} \times H_{sub.A}$, and the projection into the XY plane has a surface area $L_{sub.A} \times W_{sub.A}$. Of these, the plane corresponding to the projection having the largest surface area is the one that is selected to be orthogonal to the stacking direction. Similarly, the anodes **110** may also be configured such that a surface area of a projection of the anode active material layer **132** into a plane orthogonal to the stacking direction is larger than the surface areas of projections of the electrode active material layer onto other orthogonal planes. For example, in the embodiments shown in FIGS. **1A** and **7**, the anode active material layer may have a length $L_{sub.AA}$ measured in the transverse direction, a width $W_{sub.AA}$ measured in the longitudinal direction, and a height $H_{sub.AA}$ measured in the vertical direction, from the surface areas of projections can be calculated ($L_{sub.A}$, $L_{sub.AA}$, $W_{sub.A}$, $W_{sub.AA}$, $H_{sub.A}$ and $H_{sub.AA}$ may also correspond to the maximum of these dimensions, in a case where the dimensions of the anode structure and/or anode active material layer **132** vary along one or more axes). In one embodiment, by positioning the anode structures **110** such that the plane having the highest projection surface area of the anode structure **110** and/or anode active material layer **132** is orthogonal to the stacking direction, a configuration can be achieved whereby the surface of the anode structure **110** having the greatest surface area of anode active material faces the direction of travel of the carrier ions, and thus experiences the greatest growth during cycling between charged and discharged states due to intercalation and/or alloying.

(159) In one embodiment, the anode structure **110** and electrode assembly **106** can be configured such that the largest surface area projection of the anode structure **110** and/or anode active material layer **132**, and the smallest surface area projection of the electrode assembly **106** are simultaneously in a plane that is orthogonal to the stacking direction. For example, in a case as shown in FIGS. **1A** and **7**, where the projection of the anode active material layer **132** in the X-Z plane ($L_{sub.AA} \times H_{sub.AA}$) of the anode active material layer **132** is the highest, the anode structure **110** and/or anode active material layer **132** is positioned with respect to the smallest surface area projection of the electrode assembly ($L_{sub.EA} \times H_{sub.EA}$) such the projection plane for both projections is orthogonal to the stacking direction. That is, the plane having the greatest surface area projection of the anode structure **110** and/or anode active material is parallel to (and/or in the same plane with) the plane having the smallest surface area projection of the electrode assembly **106**. In this way, according to one embodiment, the surfaces of the anode structures that

are most likely to experience the highest volume growth, i.e., the surfaces having the highest content of anode active material layer, and/or surfaces that intersect (e.g., are orthogonal to) a direction of travel of carrier ions during charge/discharge of a secondary battery, face the surfaces of the electrode assembly **106** having the lowest surface area. An advantage of providing such a configuration may be that the growth constraint system used to constrain in this greatest direction of growth, e.g. along the longitudinal axis, can be implemented with growth constraints that themselves have a relatively small surface area, as compared to the area of other surfaces of the electrode assembly **106**, thereby reducing the volume required for implementing a constraint system to restrain growth of the electrode assembly.

(160) In one embodiment, the constraint system **108** occupies a relatively low volume % of the combined volume of the electrode assembly **106** and constraint system **108**. That is, the electrode assembly **106** can be understood as having a volume bounded by its exterior surfaces (i.e., the displacement volume), namely the volume enclosed by the first and second longitudinal end surfaces **116**, **118** and the lateral surface **42** connecting the end surfaces. Portions of the constraint system **108** that are external to the electrode assembly **106** (i.e., external to the longitudinal end surfaces **116**, **118** and the lateral surface), such as where first and second primary growth constraints **154**, **156** are located at the longitudinal ends **117**, **119** of the electrode assembly **106**, and first and second secondary growth constraints **158**, **160** are at the opposing ends of the lateral surface **142**, the portions of the constrain system **108** similarly occupy a volume corresponding to the displacement volume of the constraint system portions. Accordingly, in one embodiment, the external portions of the set of electrode constraints **108**, which can include external portions of the primary growth constraint system **151** (i.e., any of the first and second primary growth constraints **154**, **156** and at least one primary connecting member that are external, or external portions thereof), as well as external portions of the secondary growth constraint system **152** (i.e., any of the first and second secondary growth constraints **158**, **160** and at least one secondary connecting member that are external, or external portions thereof) occupies no more than 80% of the total combined volume of the electrode assembly **106** and external portion of the set of electrode constraints **108**. By way of further example, in one embodiment the external portions of the set of electrode constraints occupies no more than 60% of the total combined volume of the electrode assembly **106** and the external portion of the set of electrode constraints. By way of yet a further example, in one embodiment the external portion of the set of electrode constraints **106** occupies no more than 40% of the total combined volume of the electrode assembly **106** and the external portion of the set of electrode constraints. By way of yet a further example, in one embodiment the external portion of the set of electrode constraints **106** occupies no more than 20% of the total combined volume of the electrode assembly **106** and the external portion of the set of electrode constraints. In yet another embodiment, the external portion of the primary growth constraint system **151** (i.e., any of the first and second primary growth constraints **154**, **156** and at least one primary connecting member that are external, or external portions thereof) occupies no more than 40% of the total combined volume of the electrode assembly **106** and the external portion of the primary growth constraint system **151**. By way of further example, in one embodiment the external portion of the primary growth constraint system **151** occupies no more than 30% of the total combined volume of the electrode assembly **106** and the external portion of the primary growth constraint system **151**. By way of yet a further example, in one embodiment the external portion of the primary growth constraint system **151** occupies no more than 20% of the total combined volume of the electrode assembly **106** and the external portion of the primary growth constraint system **151**. By way of yet a further example, in one embodiment the external portion of the primary growth constraint system **151** occupies no more than 10% of the total combined volume of the electrode assembly **106** and the external portion of the primary growth constraint system **151**. In yet another embodiment, the external portion of the secondary growth constraint system **152** (i.e., any of the first and second secondary growth constraints **158**, **160** and at least one secondary

connecting member that are external, or external portions thereof) occupies no more than 40% of the total combined volume of the electrode assembly **106** and the external portion of the secondary growth constraint system **152**. By way of further example, in one embodiment, the external portion of the secondary growth constraint system **152** occupies no more than 30% of the total combined volume of the electrode assembly **106** and the external portion of the secondary growth constraint system **152**. By way of yet another example, in one embodiment, the external portion of the secondary growth constraint system **152** occupies no more than 20% of the total combined volume of the electrode assembly **106** and the external portion of the secondary growth constraint system **152**. By way of yet another example, in one embodiment, the external portion of the secondary growth constraint system **152** occupies no more than 10% of the total combined volume of the electrode assembly **106** and the external portion of the secondary growth constraint system **152**.

(161) According to one embodiment, a projection of the members of the anode and cathode populations onto first and second longitudinal end surfaces **116**, **118** circumscribes a first and second projected area **2002a**, **2002b**. In general, first and second projected areas **2002a**, **2002b** will typically comprise a significant fraction of the surface area of the first and second longitudinal end surfaces **122**, **124**, respectively. For example, in one embodiment the first and second projected areas each comprise at least 50% of the surface area of the first and second longitudinal end surfaces, respectively. By way of further example, in one such embodiment the first and second projected areas each comprise at least 75% of the surface area of the first and second longitudinal end surfaces, respectively. By way of further example, in one such embodiment the first and second projected areas each comprise at least 90% of the surface area of the first and second longitudinal end surfaces, respectively.

(162) In certain embodiments, the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a significant compressive load. For example, in some embodiments, each of the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a compressive load of at least 0.7 kPa (e.g., averaged over the total surface area of each of the longitudinal end surfaces, respectively). For example, in one embodiment, each of the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a compressive load of at least 1.75 kPa (e.g., averaged over the total surface area of each of the longitudinal end surfaces, respectively). By way of further example, in one such embodiment, each of the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a compressive load of at least 2.8 kPa (e.g., averaged over the total surface area of each of the longitudinal end surfaces, respectively). By way of further example, in one such embodiment, each of the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a compressive load of at least 3.5 kPa (e.g., averaged over the total surface area of each of the longitudinal end surfaces, respectively). By way of further example, in one such embodiment, each of the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a compressive load of at least 5.25 kPa (e.g., averaged over the total surface area of each of the longitudinal end surfaces, respectively). By way of further example, in one such embodiment, each of the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a compressive load of at least 7 kPa (e.g., averaged over the total surface area of each of the longitudinal end surfaces, respectively). By way of further example, in one such embodiment, each of the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a compressive load of at least 8.75 kPa (e.g., averaged over the total surface area of each of the longitudinal end surfaces, respectively). In general, however, the longitudinal end surfaces **116**, **118** of the electrode assembly **106** will be under a compressive load of no more than about 10 kPa (e.g., averaged over the total surface area of each of the longitudinal end surfaces, respectively). The regions of the longitudinal end surface of the electrode assembly that are coincident with the projection of members of the electrode and counter-electrode populations onto the longitudinal end surfaces (i.e., the projected surface regions) may also be under the above compressive loads (as averaged over the total surface area of each projected surface region, respectively). In each of the foregoing

exemplary embodiments, the longitudinal end surfaces **116, 118** of the electrode assembly **106** will experience such compressive loads when an energy storage device **100** having the electrode assembly **106** is charged to at least about 80% of its rated capacity.

(163) According to one embodiment, the secondary growth constraint system **152** is capable of restraining growth of the electrode assembly **106** in the vertical direction (Z direction) by applying a restraining force at a predetermined value, and without excessive skew of the growth restraints. For example, in one embodiment, the secondary growth constraint system **152** may restrain growth of the electrode assembly **106** in the vertical direction by applying a restraining force to opposing vertical regions **148, 150** of greater than 1000 psi and a skew of less than 0.2 mm/m. By way of further example, in one embodiment, the secondary growth constraint system **152** may restrain growth of the electrode assembly **106** in the vertical direction by applying a restraining force to opposing vertical regions **148, 150** with less than 5% displacement at less than or equal to 10,000 psi and a skew of less than 0.2 mm/m. By way of further example, in one embodiment, the secondary growth constraint system **152** may restrain growth of the electrode assembly **106** in the vertical direction by applying a restraining force to opposing vertical regions **148, 150** with less than 3% displacement at less than or equal to 10,000 psi and a skew of less than 0.2 mm/m. By way of further example, in one embodiment, the secondary growth constraint system **152** may restrain growth of the electrode assembly **106** in the vertical direction by applying a restraining force to opposing vertical regions **148, 150** with less than 1% displacement at less than or equal to 10,000 psi and a skew of less than 0.2 mm/m. By way of further example, in one embodiment, the secondary growth constraint system **152** may restrain growth of the electrode assembly **106** in the vertical direction by applying a restraining force to opposing vertical regions **148, 150** in the vertical direction with less than 15% displacement at less than or equal to 10,000 psi and a skew of less than 0.2 mm/m after 50 battery cycles. By way of further example, in one embodiment, the secondary growth constraint system **152** may restrain growth of the electrode assembly **106** in the vertical direction by applying a restraining force to opposing vertical regions **148, 150** with less than 5% displacement at less than or equal to 10,000 psi and a skew of less than 0.2 mm/m after 150 battery cycles.

(164) Referring now to FIG. 6D, an embodiment of an electrode assembly **106** with a set of electrode constraints **108** is shown, with a cross-section taken along the line A-A' as shown in FIG. 1B. In the embodiment shown in FIG. 6D, the primary growth constraint system **151** can comprise first and second primary growth constraints **154, 156**, respectively, at the longitudinal end surfaces **116, 118** of the electrode assembly **106**, and the secondary growth constraint system **152** comprises first and second secondary growth constraints **158, 160** at the opposing first and second surface regions **148, 150** of the lateral surface **142** of the electrode assembly **106**. According to this embodiment, the first and second primary growth constraints **154, 156** can serve as the at least one secondary connecting member **166** to connect the first and second secondary growth constraints **158, 160** and maintain the growth constraints in tension with one another in the second direction (e.g., vertical direction) that is orthogonal to the longitudinal direction. However, additionally and/or alternatively, the secondary growth constraint system **152** can comprise at least one secondary connecting member **166** that is located at a region other than the longitudinal end surfaces **116, 118** of the electrode assembly **106**. Also, the at least one secondary connecting member **166** can be understood to act as at least one of a first and second primary growth constraint **154, 156** that is internal to the longitudinal ends **116, 118** of the electrode assembly, and that can act in conjunction with either another internal primary growth restraint and/or a primary growth restraint at a longitudinal end **116, 118** of the electrode assembly **106** to restrain growth. Referring to the embodiment shown in FIG. 6D, a secondary connecting member **166** can be provided that is spaced apart along the longitudinal axis away from the first and second longitudinal end surfaces **116, 118**, respectively, of the electrode assembly **106**, such as toward a central region of the electrode assembly **106**. The secondary connecting member **166** can connect the first and second

secondary growth constraints **158, 160**, respectively, at an interior position from the electrode assembly end surfaces **116, 118**, and may be under tension between the secondary growth constraints **158, 160** at that position. In one embodiment, the secondary connecting member **166** that connects the secondary growth constraints **158, 160** at an interior position from the end surfaces **116, 118** is provided in addition to one or more secondary connecting members **166** provided at the electrode assembly end surfaces **116, 118**, such as the secondary connecting members **166** that also serve as primary growth constraints **154, 156** at the longitudinal end surfaces **116, 118**. In another embodiment, the secondary growth constraint system **152** comprises one or more secondary connecting members **166** that connect with first and second secondary growth constraints **158, 160**, respectively, at interior positions that are spaced apart from the longitudinal end surfaces **116, 118**, with or without secondary connecting members **166** at the longitudinal end surfaces **116, 118**. The interior secondary connecting members **166** can also be understood to act as first and second primary growth constraints **154, 156**, according to one embodiment. For example, in one embodiment, at least one of the interior secondary connecting members **166** can comprise at least a portion of an anode or cathode structure **110, 112**, as described in further detail below.

(165) More specifically, with respect to the embodiment shown in FIG. 6D, secondary growth constraint system **152** may include a first secondary growth constraint **158** that overlies an upper region **148** of the lateral surface **142** of electrode assembly **106**, and an opposing second secondary growth constraint **160** that overlies a lower region **150** of the lateral surface **142** of electrode assembly **106**, the first and second secondary growth constraints **158, 160** being separated from each other in the vertical direction (i.e., along the Z-axis). Additionally, secondary growth constraint system **152** may further include at least one interior secondary connecting member **166** that is spaced apart from the longitudinal end surfaces **116, 118** of the electrode assembly **106**. The interior secondary connecting member **166** may be aligned parallel to the Z axis and connects the first and second secondary growth constraints **158, 160**, respectively, to maintain the growth constraints in tension with one another, and to form at least a portion of the secondary constraint system **152**. In one embodiment, the at least one interior secondary connecting member **166**, either alone or with secondary connecting members **166** located at the longitudinal end surfaces **116, 118** of the electrode assembly **106**, may be under tension between the first and second growth constraints **158, 160** in the vertical direction (i.e., along the Z axis), during repeated charge and/or discharge of an energy storage device **100** or a secondary battery **102** having the electrode assembly **106**, to reduce growth of the electrode assembly **106** in the vertical direction.

Furthermore, in the embodiment as shown in FIG. 5, the set of electrode constraints **108** further comprises a primary growth constraint system **151** having first and second primary growth constraints **154, 156**, respectively, at the longitudinal ends **117, 119** of the electrode assembly **106**, that are connected by first and second primary connecting members **162, 164**, respectively, at the upper and lower lateral surface regions **148, 150**, respectively, of the electrode assembly **106**. In one embodiment, the secondary interior connecting member **166** can itself be understood as acting in concert with one or more of the first and second primary growth constraints **154, 156**, respectively, to exert a constraining pressure on each portion of the electrode assembly **106** lying in the longitudinal direction between the secondary interior connecting member **166** and the longitudinal ends **117, 119** of the electrode assembly **106** where the first and second primary growth constraints **154, 156**, respectively, can be located.

(166) In one embodiment, one or more of the primary growth constraint system **151** and secondary growth constraint system **152** includes first and second primary growth constraints **154, 156**, respectively, and/or first and second secondary growth constraints **158, 160**, respectively, that include a plurality of constraint members. That is, each of the primary growth constraints **154, 156** and/or secondary growth constraints **158, 160** may be a single unitary member, or a plurality of members may be used to make up one or more of the growth constraints. For example, in one

embodiment, the first and second secondary growth constraints **158, 160**, respectively, can comprise single constraint members extending along the upper and lower surface regions **148, 150**, respectively, of the electrode assembly lateral surface **142**. In another embodiment, the first and second secondary growth constraints **158, 160**, respectively, comprise a plurality of members extending across the opposing surface regions **148, 150**, of the lateral surface. Similarly, the primary growth constraints **154, 156** may also be made of a plurality of members, or can each comprise a single unitary member at each electrode assembly longitudinal end **117, 119**. To maintain tension between each of the primary growth constraints **154, 156** and secondary growth constraints **158, 160**, the connecting members (e.g., **162, 164, 165, 166**) are provided to connect the one or plurality of members comprising the growth constraints to the opposing growth constraint members in a manner that exerts pressure on the electrode assembly **106** between the growth constraints.

(167) In one embodiment, the at least one secondary connecting member **166** of the secondary growth constraint system **152** forms areas of contact **168, 170** with the first and second secondary growth constraints **158, 160**, respectively, to maintain the growth constraints in tension with one another. The areas of contact **168, 170** are those areas where the surfaces at the ends **172, 174** of the at least one secondary connecting member **166** touches and/or contacts the first and second secondary growth constraints **158, 160**, respectively, such as where a surface of an end of the at least one secondary connecting member **166** is adhered or glued to the first and second secondary growth constraints **158, 160**, respectively. The areas of contact **168, 170** may be at each end **172, 174** and may extend across a surface area of the first and second secondary growth constraints **158, 160**, to provide good contact therebetween. The areas of contact **168, 170** provide contact in the longitudinal direction (Y axis) between the second connecting member **166** and the growth constraints **158, 160**, and the areas of contact **168, 170** can also extend into the transverse direction (X-axis) to provide good contact and connection to maintain the first and second secondary growth constraints **158, 160** in tension with one another. In one embodiment, the areas of contact **168, 170** provide a ratio of the total area of contact (e.g., the sum of all areas **168**, and the sum of all areas **170**) of the one or more secondary connecting members **166** in the longitudinal direction (Y axis) with the growth constraints **158, 160**, per W.sub.EA of the electrode assembly **106** in the longitudinal direction that is at least 1%. For example, in one embodiment, a ratio of the total area of contact of the one or more secondary connecting members **166** in the longitudinal direction (Y axis) with the growth constraints **158, 160**, per W.sub.EA of the electrode assembly **106** in the longitudinal direction is at least 2%. By way of further example, in one embodiment, a ratio of the total area of contact of the one or more secondary connecting members **166** in the longitudinal direction (Y axis) with the growth constraints **158, 160**, per W.sub.EA of the electrode assembly **106** in the longitudinal direction, is at least 5%. By way of further example, in one embodiment, a ratio of the total area of contact of the one or more secondary connecting members **166** in the longitudinal direction (Y axis) with the growth constraints **158, 160**, per W.sub.EA of the electrode assembly **106** in the longitudinal direction, is at least 10%. By way of further example, in one embodiment, a ratio of the total area of contact of the one or more secondary connecting members **166** in the longitudinal direction (Y axis) with the growth constraints **158, 160**, per W.sub.EA of the electrode assembly **106** in the longitudinal direction, is at least 25%. By way of further example, in one embodiment, a ratio of the total area of contact of the one or more secondary connecting members **166** in the longitudinal direction (Y axis) with the growth constraints **158, 160**, per W.sub.EA of the electrode assembly **106** in the longitudinal direction, is at least 50%. In general, a ratio of the total area of contact of the one or more secondary connecting members **166** in the longitudinal direction (Y axis) with the growth constraints **158, 160**, per W.sub.EA of the electrode assembly **106** in the longitudinal direction, will be less than 100%, such as less than 90%, and even less than 75%, as the one or more connecting members **166** typically do not have an area of contact **168, 170** that extends across the entire longitudinal axis. However, in one embodiment, an area of

contact **168**, **170** of the secondary connecting members **166** with the growth constraints **158**, **160**, may extend across a significant portion of the transverse axis (X axis), and may even extend across the entire L.sub.EA of the electrode assembly **106** in the transverse direction. For example, a ratio of the total area of contact (e.g., the sum of all areas **168**, and the sum of all areas **170**) of the one or more secondary connecting members **166** in the transverse direction (X axis) with the growth constraints **158**, **160**, per L.sub.EA of the electrode assembly **106** in the transverse direction, may be at least about 50%. By way of further example, a ratio of the total area of contact of the one or more secondary connecting members **166** in the transverse direction (X axis) with the growth constraints **158**, **160**, per L.sub.EA of the electrode assembly **106** in the transverse direction (X-axis), may be at least about 75%. By way of further example, a ratio of the total area of contact of the one or more secondary connecting members **166** in the transverse direction (X axis) with the growth constraints **158**, **160**, per L.sub.EA of the electrode assembly **106** in the transverse direction (X axis), may be at least about 90%. By way of further example, a ratio of the total area of contact of the one or more secondary connecting members **166** in the transverse direction (X axis) with the growth constraints **158**, **160**, per L.sub.EA of the electrode assembly **106** in the transverse direction (X axis), may be at least about 95%.

(168) According to one embodiment, the areas of contact **168**, **170** between the one or more secondary connecting members **166** and the first and second secondary growth constraints **158**, **160**, respectively, are sufficiently large to provide for adequate hold and tension between the growth constraints **158**, **160** during cycling of an energy storage device **100** or a secondary battery **102** having the electrode assembly **106**. For example, the areas of contact **168**, **170** may form an area of contact with each growth constraint **158**, **160** that makes up at least 2% of the surface area of the lateral surface **142** of the electrode assembly **106**, such as at least 10% of the surface area of the lateral surface **142** of the electrode assembly **106**, and even at least 20% of the surface area of the lateral surface **142** of the electrode assembly **106**. By way of further example, the areas of contact **168**, **170** may form an area of contact with each growth constraint **158**, **160** that makes up at least 35% of the surface area of the lateral surface **142** of the electrode assembly **106**, and even at least 40% of the surface area of the lateral surface **142** of the electrode assembly **106**. For example, for an electrode assembly **106** having upper and lower opposing surface regions **148**, **150**, respectively, the at least one secondary connecting member **166** may form areas of contact **168**, **170** with the growth constraints **158**, **160** along at least 5% of the surface area of the upper and lower opposing surface regions **148**, **150**, respectively, such as along at least 10% of the surface area of the upper and lower opposing surface regions **148**, **150**, respectively, and even at least 20% of the surface area of the upper and lower opposing surface regions **148**, **150**, respectively. By way of further example, an electrode assembly **106** having upper and lower opposing surface regions **148**, **150**, respectively, the at least one secondary connecting member **166** may form areas of contact **168**, **170** with the growth constraints **158**, **160** along at least 40% of the surface area of the upper and lower opposing surface regions **148**, **150**, respectively, such as along at least 50% of the surface area of the upper and lower opposing surface regions **148**, **150**, respectively. By forming a contact between the at least one connecting member **166** and the growth constraints **158**, **160** that makes up a minimum surface area relative to a total surface area of the electrode assembly **106**, proper tension between the growth constraints **158**, **160** can be provided. Furthermore, according to one embodiment, the areas of contact **168**, **170** can be provided by a single secondary connecting member **166**, or the total area of contact may be the sum of multiple areas of contact **168**, **170** provided by a plurality of secondary connecting members **166**, such as one or a plurality of secondary connecting members **166** located at longitudinal ends **117**, **119** of the electrode assembly **106**, and/or one or a plurality of interior secondary connecting members **166** that are spaced apart from the longitudinal ends **117**, **119** of the electrode assembly **106**.

(169) Further still, in one embodiment, the primary and secondary growth constraint systems **151**, **152**, respectively, (and optionally the tertiary growth constraint system) are capable of restraining

growth of the electrode assembly **106** in both the longitudinal direction and the second direction orthogonal to the longitudinal direction, such as the vertical direction (Z axis) (and optionally in the third direction, such as along the X axis), to restrain a volume growth % of the electrode assembly. (170) In certain embodiments, one or more of the primary and secondary growth constraint systems **151, 152**, respectively, comprises a member having pores therein, such as a member made of a porous material. For example, referring to FIG. **8** depicting a top view of a secondary growth constraint **158** over an electrode assembly **106**, the secondary growth constraint **158** can comprise pores **176** that permit electrolyte to pass therethrough, so as to access an electrode assembly **106** that is at least partially covered by the secondary growth constraint **158**. In one embodiment, the first and second secondary growth constraints **158, 160**, respectively, have the pores **176** therein. In another embodiment, each of the first and second primary growth constraints **154, 156**, respectively, and the first and second secondary growth constraints **158, 160**, respectively, have the pores **176** therein. In yet another embodiment, only one or only a portion of the first and second secondary growth constraints **158, 160**, respectively, contain the pores therein. In yet a further embodiment, one or more of the first and second primary connecting members **162, 164**, respectively, and the at least one secondary connecting member **166** contains pores therein. Providing the pores **176** may be advantageous, for example, when the energy storage device **100** or secondary battery **102** contains a plurality of electrode assemblies **106** stacked together in the battery enclosure **104**, to permit electrolyte to flow between the different electrode assemblies **106** in, for example, the secondary battery **102** as shown in the embodiment depicted in FIG. **9**. For example, in one embodiment, a porous member making up at least a portion of the primary and secondary growth constraint system **151, 152**, respectively, may have a void fraction of at least 0.25. By way of further example, in some embodiments, a porous member making up at least a portion of the primary and secondary growth constraint systems **151, 152**, respectively, may have a void fraction of at least 0.375. By way of further example, in some embodiments, a porous member making up at least a portion of the primary and secondary growth constraint systems **151, 152**, respectively, may have a void fraction of at least 0.5. By way of further example, in some embodiments, a porous member making up at least a portion of the primary and secondary growth constraint systems **151, 152**, respectively, may have a void fraction of at least 0.625. By way of further example, in some embodiments, a porous member making up at least a portion of the primary and secondary growth constraint systems **151, 152**, respectively, may have a void fraction of at least 0.75.

(171) In one embodiment, the set of electrode constraints **108** may be assembled and secured to restrain growth of the electrode assembly **106** by at least one of adhering, bonding, and/or gluing components of the primary growth constraint system **151** to components of the secondary growth constraint system **152**. For example, components of the primary growth constraint system **151** may be glued, welded, bonded, or otherwise adhered and secured to components of the secondary growth constraint system **152**. For example, as shown in FIG. **6A**, the first and second primary growth constraints **154, 156**, respectively, can be adhered to first and second primary connecting members **162, 164**, respectively, that may also serve as first and second secondary growth constraints **158, 160**, respectively. Conversely, the first and second secondary growth constraints **158, 160**, respectively, can be adhered to at least one secondary connecting member **166** that serves as at least one of the first and second primary growth constraints **154, 156**, respectively, such as growth constraints at the longitudinal ends **117, 119** of the electrode assembly **106**. Referring to FIG. **6D**, the first and second secondary growth constraints **158, 160**, respectively, can also be adhered to at least one secondary connecting member **166** that is an interior connecting member **166** spaced apart from the longitudinal ends **117, 119**. In one embodiment, by securing portions of the primary and secondary growth constraint systems **151, 152**, respectively, to one another, the cooperative restraint of the electrode assembly **106** growth can be provided.

(172) Constraint System Sub-Architecture

(173) According to one embodiment, as discussed above, one or more of the first and second secondary growth constraints **158**, **160**, respectively, can be connected together via a secondary connecting member **166** that is a part of an interior structure of the electrode assembly **106**, such as a part of an anode **110** and/or cathode structure **112**. In one embodiment, by providing connection between the constraints via structures within the electrode assembly **106**, a tightly constrained structure can be realized that adequately compensates for strain produced by growth of the anode structure **110**. For example, in one embodiment, the first and second secondary growth constraints **158**, **160**, respectively, may constrain growth in a direction orthogonal to the longitudinal direction, such as the vertical direction, by being placed in tension with one another via connection through a connecting member **166** that is a part of an anode **110** or cathode structure **112**. In yet a further embodiment, growth of an anode structure **110** can be countered by connection of the secondary growth constraints **158**, **160** through a cathode structure **112** that serves as the secondary connecting member **166**.

(174) In general, in certain embodiments, components of the primary growth constraint system **151** and the secondary growth constraint system **152** may be attached to the anode **110** and/or cathode structures **112**, respectively, within an electrode assembly **106**, and components of the secondary growth constraint system **152** may also be embodied as the anode **110** and/or cathode structures **112**, respectively, within an electrode assembly **106**, not only to provide effective restraint but also to more efficiently utilize the volume of the electrode assembly **106** without excessively increasing the size of an energy storage device **110** or a secondary battery **102** having the electrode assembly **106**. For example, in one embodiment, the primary growth constraint system **151** and/or secondary growth constraint system **152** may be attached to one or more anode structures **110**. By way of further example, in one embodiment, the primary growth constraint system **151** and/or secondary growth constraint system **152** may be attached to one or more cathode structures **112**. By way of further example, in certain embodiments, the at least one secondary connecting member **166** may be embodied as the population of anode structures **110**. By way of further example, in certain embodiments, the at least one secondary connecting member **166** may be embodied as the population of cathode structures **112**.

(175) Referring now to FIG. 7, a Cartesian coordinate system is shown for reference having a vertical axis (Z axis), a longitudinal axis (Y axis), and a transverse axis (X axis); wherein the X axis is oriented as coming out of the plane of the page; and a designation of the stacking direction D, as described above, co-parallel with the Y axis. More specifically, FIG. 7 shows a cross section, along the line A-A' as in FIG. 1B, of a set of electrode constraints **108**, including one embodiment of both a primary growth constraint system **151** and one embodiment of a secondary growth constraint system **152**. Primary growth constraint system **151** includes a first primary growth constraint **154** and a second primary growth constraint **156**, as described above, and a first primary connecting member **162** and a second primary connecting member **164**, as described above. Secondary growth constraint system **152** includes a first secondary growth constraint **158**, a second secondary growth constraint **160**, and at least one secondary connecting member **166** embodied as the population of anode structures **110** and/or the population of cathode structures **112**; therefore, in this embodiment, the at least one secondary connecting member **166**, anode structures **110**, and/or cathode structures **112** can be understood to be interchangeable. Furthermore, the separator **130** may also form a portion of a secondary connecting member **166**. Further, in this embodiment, first primary connecting member **162** and first secondary growth constraint **158** are interchangeable, as described above. Further still, in this embodiment, second primary connecting member **164** and second secondary growth constraint **160** are interchangeable, as described above. More specifically, illustrated in FIG. 7 is one embodiment of a flush connection of the secondary connecting member **166** corresponding to the anode **110** or cathode structure **112** with the first secondary growth constraint **158** and second secondary growth constraint **160**. The flush connection may further include a layer of glue **182** between the first secondary growth constraint **158** and secondary

connecting member **166**, and a layer of glue **182** between the second secondary growth constraint **160** and secondary connecting member **166**. The layers of glue **182** affix first secondary growth constraint **158** to secondary connecting members **166**, and affix the second secondary growth constraint **160** to secondary connecting member **166**.

(176) Also, one or more of the first and second primary growth constraints **154**, **156**, first and second primary connecting members **162**, **164**, first and second secondary growth constraints **158**, **160**, and at least one secondary connecting member **166** may be provided in the form of a plurality of segments **1088** or parts that can be joined together to form a single member. For example, as shown in the embodiment as illustrated in FIG. 7, a first secondary growth constraint **158** is provided in the form of a main middle segment **1088a** and first and second end segments **1088b** located towards the longitudinal ends **117**, **119** of the electrode assembly **106**, with the middle segment **1088a** being connected to each first and second end segment **1088b** by a connecting portion **1089** provided to connect the segments **1088**, such as notches formed in the segments **1088** that can be interconnected to join the segments **1088** to one another. A second secondary growth constraint **160** may similarly be provided in the form of a plurality of segments **1088** that can be connected together to form the constraint, as shown in FIG. 7. In one embodiment, one or more of the secondary growth constraints **158**, **160**, at least one primary connecting member **162**, and/or at least one secondary connecting member **166** may also be provided in the form of a plurality of segments **1088** that can be connected together via a connecting portions such as notches to form the complete member. According to one embodiment, the connection of the segments **1088** together via the notch or other connecting portion may provide for pre-tensioning of the member formed of the plurality of segments when the segments are connected.

(177) Further illustrated in FIG. 7, in one embodiment, are members of the anode population **110** having an anode active material layer **132**, an ionically porous anode current collector **136**, and an anode backbone **134** that supports the anode active material layer **132** and the anode current collector **136**. Similarly, in one embodiment, illustrated in FIG. 7 are members of the cathode population **112** having a cathode active material layer **138**, a cathode collector **140**, and a cathode backbone **141** that supports the cathode active material layer **138** and the cathode current collector **140**.

(178) While members of the anode population **110** have been illustrated and described herein to include the anode active material layer **132** being directly adjacent to the anode backbone **134**, and the anode current collector **136** directly adjacent to and effectively surrounding the anode backbone **134** and the anode active material layer **132**, those of skill in the art will appreciate other arrangements of the anode population **110** have been contemplated. For example, in one embodiment (not shown), the anode population **110** may include the anode active material layer **132** being directly adjacent to the anode current collector **136**, and the anode current collector **136** being directly adjacent to the anode backbone **134**. Stated alternatively, the anode backbone **134** may be effectively surrounded by the anode current collector **136**, with the anode active material layer **132** flanking and being directly adjacent to the anode current collector **136**. As will be appreciated by those of skill in the art, any suitable configuration of the anode population **110** and/or the cathode population **112** may be applicable to the inventive subject matter described herein, so long as the anode active material layer **132** is separated from the cathode active material layer **138** via separator **130**. Also, the anode current collector **136** is required to be ion permeable if it is located between the anode active material layer **132** and separator **130**; and the cathode current collector **140** is required to be ion permeable if it is located between the cathode active material layer **138** and separator **130**.

(179) For ease of illustration, only three members of the anode population **110** and four members of the cathode population **112** are depicted, in practice, however, an energy storage device **100** or secondary battery **102** using the inventive subject matter herein may include additional members of the anode **110** and cathode **112** populations depending on the application of the energy storage

device **100** or secondary battery **102**, as described above. Further still, illustrated in FIG. 7 is a microporous separator **130** electrically insulating the anode active material layer **132** from the cathode active material layer **138**.

(180) Furthermore, to connect the first and second secondary growth constraints **158**, **160**, respectively, the constraints **158**, **160** can be attached to the at least one connecting member **166** by a suitable means, such as by gluing as shown, or alternatively by being welded, such as by being welded to the current collectors **136**, **140**. For example, the first and/or second secondary growth constraints **158**, **160**, respectively, can be attached to a secondary connecting member **166** corresponding to at least one of an anode structure **110** and/or cathode structure **112**, such as at least one of an anode and/or cathode backbone **134**, **141**, respectively, an anode and/or cathode current collector **136**, **140**, respectively, by at least one of adhering, gluing, bonding, welding, and the like. According to one embodiment, the first and/or second secondary growth constraints **158**, **160**, respectively, can be attached to the secondary connecting member **166** by mechanically pressing the first and/or second secondary growth constraint **158**, **160**, respectively, to an end of one or more secondary connecting member **166**, such as ends of the population of anode **100** and/or cathode structures **112**, while using a glue or other adhesive material to adhere one or more ends of the anode **110** and/or cathode structures **112** to at least one of the first and/or second secondary growth constraints **158**, **160**, respectively.

(181) Population of Anode Structures

(182) Referring again to FIG. 7, each member of the population of anode structures **110** may also include a top **1052** adjacent to the first secondary growth constraint **158**, a bottom **1054** adjacent to the second secondary growth constraint **160**, and a lateral surface (not marked) surrounding a vertical axis A.sub.ES (not marked) parallel to the Z axis, the lateral surface connecting the top **1052** and the bottom **1054**. The anode structures **110** further include a length L.sub.A, a width W.sub.A, and a height H.sub.A. The length L.sub.A being bounded by the lateral surface and measured along the X axis. The width W.sub.A being bounded by the lateral surface and measured along the Y axis, and the height H.sub.A being measured along the vertical axis A.sub.ES or the Z axis from the top **1052** to the bottom **1054**.

(183) The L.sub.A of the members of the anode population **110** will vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, the members of the anode population **110** will typically have a L.sub.A in the range of about 5 mm to about 500 mm. For example, in one such embodiment, the members of the anode population **110** have a L.sub.A of about 10 mm to about 250 mm. By way of further example, in one such embodiment, the members of the anode population **110** have a L.sub.A of about 20 mm to about 100 mm.

(184) The W.sub.A of the members of the anode population **110** will also vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, each member of the anode population **110** will typically have a W.sub.A within the range of about 0.01 mm to 2.5 mm. For example, in one embodiment, the W.sub.A of each member of the anode population **110** will be in the range of about 0.025 mm to about 2 mm. By way of further example, in one embodiment, the W.sub.A of each member of the anode population **110** will be in the range of about 0.05 mm to about 1 mm.

(185) The H.sub.A of the members of the anode population **110** will also vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, members of the anode population **110** will typically have a H.sub.A within the range of about 0.05 mm to about 10 mm. For example, in one embodiment, the H.sub.A of each member of the anode population **110** will be in the range of about 0.05 mm to about 5 mm. By way of further example, in one embodiment, the H.sub.A of each member of the anode population **110** will be in the range of about 0.1 mm to about 1 mm.

(186) In another embodiment, each member of the population of anode structures **110** may include

an anode structure backbone **134** having a vertical axis A.sub.ESB parallel to the Z axis. The anode structure backbone **134** may also include a layer of anode active material **132** surrounding the anode structure backbone **134** about the vertical axis A.sub.ESB. Stated alternatively, the anode structure backbone **134** provides mechanical stability for the layer of anode active material **132**, and may provide a point of attachment for the primary growth constraint system **151** and/or secondary constraint system **152**. In certain embodiments, the layer of anode active material **132** expands upon insertion of carrier ions into the layer of anode active material **132**, and contracts upon extraction of carrier ions from the layer of anode active material **132**. The anode structure backbone **134** may also include a top **1056** adjacent to the first secondary growth constraint **158**, a bottom **1058** adjacent to the second secondary growth constraint **160**, and a lateral surface (not marked) surrounding the vertical axis A.sub.ESB and connecting the top **1056** and the bottom **1058**. The anode structure backbone **134** further includes a length LESB, a width W.sub.ESB, and a height H.sub.ESB. The length LESB being bounded by the lateral surface and measured along the X axis. The width W.sub.ESB being bounded by the lateral surface and measured along the Y axis, and the height H.sub.ESB being measured along the Z axis from the top **1056** to the bottom **1058**. (187) The LESB of the anode structure backbone **134** will vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, the anode structure backbone **134** will typically have a LESB in the range of about 5 mm to about 500 mm. For example, in one such embodiment, the anode structure backbone **134** will have a LESB of about 10 mm to about 250 mm. By way of further example, in one such embodiment, the anode structure backbone **134** will have a LESB of about 20 mm to about 100 mm. According to one embodiment, the anode structure backbone **134** may be the substructure of the anode structure **110** that acts as the at least one connecting member **166**.

(188) The W.sub.ESB of the anode structure backbone **134** will also vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, each anode structure backbone **134** will typically have a W.sub.ESB of at least 1 micrometer. For example, in one embodiment, the W.sub.ESB of each anode structure backbone **134** may be substantially thicker, but generally will not have a thickness in excess of 500 micrometers. By way of further example, in one embodiment, the W.sub.ESB of each anode structure backbone **134** will be in the range of about 1 to about 50 micrometers.

(189) The H.sub.ESB of the anode structure backbone **134** will also vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, the anode structure backbone **134** will typically have a H.sub.ESB of at least about 50 micrometers, more typically at least about 100 micrometers. Further, in general, the anode structure backbone **134** will typically have a H.sub.ESB of no more than about 10,000 micrometers, and more typically no more than about 5,000 micrometers. For example, in one embodiment, the H.sub.ESB of each anode structure backbone **134** will be in the range of about 0.05 mm to about 10 mm. By way of further example, in one embodiment, the H.sub.ESB of each anode structure backbone **134** will be in the range of about 0.05 mm to about 5 mm. By way of further example, in one embodiment, the H.sub.ESB of each anode structure backbone **134** will be in the range of about 0.1 mm to about 1 mm.

(190) Depending upon the application, anode structure backbone **134** may be electrically conductive or insulating. For example, in one embodiment, the anode structure backbone **134** may be electrically conductive and may include anode current collector **136** for anode active material **132**. In one such embodiment, anode structure backbone **134** includes an anode current collector **136** having a conductivity of at least about 10^3 Siemens/cm. By way of further example, in one such embodiment, anode structure backbone **134** includes an anode current collector **136** having a conductivity of at least about 10^4 Siemens/cm. By way of further example, in one such embodiment, anode structure backbone **134** includes an anode current collector **136** having a conductivity of at least about 10^5 Siemens/cm. In other embodiments, anode structure

backbone **134** is relatively nonconductive. For example, in one embodiment, anode structure backbone **134** has an electrical conductivity of less than 10 Siemens/cm. By way of further example, in one embodiment, anode structure backbone **134** has an electrical conductivity of less than 1 Siemens/cm. By way of further example, in one embodiment, anode structure backbone **134** has an electrical conductivity of less than 10^{-1} Siemens/cm.

(191) In certain embodiments, anode structure backbone **134** may include any material that may be shaped, such as metals, semiconductors, organics, ceramics, and glasses. For example, in certain embodiments, materials include semiconductor materials such as silicon and germanium.

Alternatively, however, carbon-based organic materials, or metals, such as aluminum, copper, nickel, cobalt, titanium, and tungsten, may also be incorporated into anode structure backbone **134**. In one exemplary embodiment, anode structure backbone **134** comprises silicon. The silicon, for example, may be single crystal silicon, polycrystalline silicon, amorphous silicon, or a combination thereof.

(192) In certain embodiments, the anode active material layer **132** may have a thickness of at least one micrometer. Typically, however, the anode active material layer **132** thickness typically will not exceed 200 micrometers. For example, in one embodiment, the anode active material layer **132** may have a thickness of about 1 to 50 micrometers. By way of further example, in one embodiment, the anode active material layer **132** may have a thickness of about 2 to about 75 micrometers. By way of further example, in one embodiment, the anode active material layer **132** may have a thickness of about 10 to about 100 micrometers. By way of further example, in one embodiment, the anode active material layer **132** may have a thickness of about 5 to about 50 micrometers.

(193) In certain embodiments, the anode current collector **136** includes an ionically permeable conductor material that has sufficient ionic permeability to carrier ions to facilitate the movement of carrier ions from the separator **130** to the anode active material layer **132**, and sufficient electrical conductivity to enable it to serve as a current collector. Being positioned between the anode active material layer **132** and the separator **130**, the anode current collector **136** may facilitate more uniform carrier ion transport by distributing current from the anode current collector **136** across the surface of the anode active material layer **132**. This, in turn, may facilitate more uniform insertion and extraction of carrier ions and thereby reduce stress in the anode active material layer **132** during cycling, since the anode current collector **136** distributes current to the surface of the anode active material layer **132** facing the separator **130**, the reactivity of the anode active material layer **132** for carrier ions will be the greatest where the carrier ion concentration is the greatest.

(194) The anode current collector **136** includes an ionically permeable conductor material that is both ionically and electrically conductive. Stated differently, the anode current collector **136** has a thickness, an electrical conductivity, and an ionic conductivity for carrier ions that facilitates the movement of carrier ions between an immediately adjacent anode active material layer **132** on one side of the ionically permeable conductor layer and an immediately adjacent separator layer **130** on the other side of the anode current collector **136** in an electrochemical stack or electrode assembly **106**. On a relative basis, the anode current collector **136** has an electrical conductance that is greater than its ionic conductance when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. For example, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the anode current collector **136** will typically be at least 1,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in one such embodiment, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the anode current collector **136** is at least 5,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in one such embodiment, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the

anode current collector **136** is at least 10,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in one such embodiment, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the anode current collector **136** layer is at least 50,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in one such embodiment, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the anode current collector **136** is at least 100,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**.

(195) In one embodiment, and when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**, such as when a secondary battery **102** is charging or discharging, the anode current collector **136** has an ionic conductance that is comparable to the ionic conductance of an adjacent separator layer **130**. For example, in one embodiment, the anode current collector **136** has an ionic conductance (for carrier ions) that is at least 50% of the ionic conductance of the separator layer **130** (i.e., a ratio of 0.5:1, respectively) when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the ionic conductance (for carrier ions) of the anode current collector **136** to the ionic conductance (for carrier ions) of the separator layer **130** is at least 1:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the ionic conductance (for carrier ions) of the anode current collector **136** to the ionic conductance (for carrier ions) of the separator layer **130** is at least 1.25:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the ionic conductance (for carrier ions) of the anode current collector **136** to the ionic conductance (for carrier ions) of the separator layer **130** is at least 1.5:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the ionic conductance (for carrier ions) of the anode current collector **136** to the ionic conductance (for carrier ions) of the separator layer **130** is at least 2:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**.

(196) In one embodiment, the anode current collector **136** also has an electrical conductance that is substantially greater than the electrical conductance of the anode active material layer **132**. For example, in one embodiment, the ratio of the electrical conductance of the anode current collector **136** to the electrical conductance of the anode active material layer **132** is at least 100:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the electrical conductance of the anode current collector **136** to the electrical conductance of the anode active material layer **132** is at least 500:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the electrical conductance of the anode current collector **136** to the electrical conductance of the anode active material layer **132** is at least 1000:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the electrical conductance of the anode current collector **136** to the electrical conductance of the anode active material layer **132** is at least 5000:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the electrical conductance of the anode current collector **136** to the electrical conductance of the anode active material layer **132** is at least 10,000:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**.

(197) The thickness of the anode current collector layer **136** (i.e., the shortest distance between the

separator **130** and, in one embodiment, the anodically active material layer between which the anode current collector layer **136** is sandwiched) in certain embodiments will depend upon the composition of the layer **136** and the performance specifications for the electrochemical stack. In general, when an anode current collector layer **136** is an ionically permeable conductor layer, it will have a thickness of at least about 300 Angstroms. For example, in some embodiments, it may have a thickness in the range of about 300-800 Angstroms. More typically, however, it will have a thickness greater than about 0.1 micrometers. In general, an ionically permeable conductor layer will have a thickness not greater than about 100 micrometers. Thus, for example, in one embodiment, the electrode current collector layer **136** will have a thickness in the range of about 0.1 to about 10 micrometers. By way of further example, in some embodiments, the anode current collector layer **136** will have a thickness in the range of about 0.1 to about 5 micrometers. By way of further example, in some embodiments, the anode current collector layer **136** will have a thickness in the range of about 0.5 to about 3 micrometers. In general, it is preferred that the thickness of the anode current collector layer **136** be approximately uniform. For example, in one embodiment, it is preferred that the anode current collector layer **136** have a thickness non-uniformity of less than about 25%. In certain embodiments, the thickness variation is even less. For example, in some embodiments, the anode current collector layer **136** has a thickness non-uniformity of less than about 20%. By way of further example, in some embodiments, the anode current collector layer **136** has a thickness non-uniformity of less than about 15%. In some embodiments the ionically permeable conductor layer has a thickness non-uniformity of less than about 10%.

(198) In one embodiment, the anode current collector layer **136** is an ionically permeable conductor layer including an electrically conductive component and an ion conductive component that contribute to the ionic permeability and electrical conductivity. Typically, the electrically conductive component will include a continuous electrically conductive material (e.g., a continuous metal or metal alloy) in the form of a mesh or patterned surface, a film, or composite material comprising the continuous electrically conductive material (e.g., a continuous metal or metal alloy). Additionally, the ion conductive component will typically comprise pores, for example, interstices of a mesh, spaces between a patterned metal or metal alloy containing material layer, pores in a metal film, or a solid ion conductor having sufficient diffusivity for carrier ions. In certain embodiments, the ionically permeable conductor layer includes a deposited porous material, an ion-transporting material, an ion-reactive material, a composite material, or a physically porous material. If porous, for example, the ionically permeable conductor layer may have a void fraction of at least about 0.25. In general, however, the void fraction will typically not exceed about 0.95. More typically, when the ionically permeable conductor layer is porous the void fraction may be in the range of about 0.25 to about 0.85. In some embodiments, for example, when the ionically permeable conductor layer is porous the void fraction may be in the range of about 0.35 to about 0.65.

(199) In the embodiment illustrated in FIG. 7, anode current collector layer **136** is the sole anode current collector for electrode active material layer **132**. Stated differently, anode structure backbone **134** may include an anode current collector. In certain other embodiments, however, anode structure backbone **134** may optionally not include an anode current collector.

(200) Population of Cathode Structures

(201) Referring again to FIG. 7, each member of the population of cathode structures **112** may also include a top **1068** adjacent to the first secondary growth constraint **158**, a bottom **1070** adjacent to the second secondary growth constraint **160**, and a lateral surface (not marked) surrounding a vertical axis ACES (not marked) parallel to the Z axis, the lateral surface connecting the top **1068** and the bottom **1070**. The cathode structures **112** further include a length L.sub.C, a width W.sub.C, and a height H.sub.C. The length L.sub.C being bounded by the lateral surface and measured along the X axis. The width W.sub.C being bounded by the lateral surface and measured along the Y axis,

and the height H.sub.C being measured along the vertical axis ACES or the Z axis from the top **1068** to the bottom **1070**.

(202) The L.sub.C of the members of the cathode population **112** will vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, the members of the cathode population **112** will typically have a L.sub.C in the range of about 5 mm to about 500 mm. For example, in one such embodiment, the members of the cathode population **112** have a L.sub.C of about 10 mm to about 250 mm. By way of further example, in one such embodiment, the members of the cathode population **112** have a L.sub.C of about 25 mm to about 100 mm.

(203) The W.sub.C of the members of the cathode population **112** will also vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, each member of the cathode population **112** will typically have a W.sub.C within the range of about 0.01 mm to 2.5 mm. For example, in one embodiment, the W.sub.C of each member of the cathode population **112** will be in the range of about 0.025 mm to about 2 mm. By way of further example, in one embodiment, the W.sub.C of each member of the cathode population **112** will be in the range of about 0.05 mm to about 1 mm.

(204) The H.sub.C of the members of the cathode population **112** will also vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, members of the cathode population **112** will typically have a H.sub.C within the range of about 0.05 mm to about 10 mm. For example, in one embodiment, the H.sub.C of each member of the cathode population **112** will be in the range of about 0.05 mm to about 5 mm. By way of further example, in one embodiment, the H.sub.C of each member of the cathode population **112** will be in the range of about 0.1 mm to about 1 mm.

(205) In another embodiment, each member of the population of cathode structures **112** may include a cathode structure backbone **141** having a vertical axis A.sub.CESB parallel to the Z axis. The cathode structure backbone **141** may also include a layer of cathode active material **138** surrounding the cathode structure backbone **141** about the vertical axis A.sub.CESB. Stated alternatively, the cathode structure backbone **141** provides mechanical stability for the layer of cathode active material **138**, and may provide a point of attachment for the primary growth constraint system **151** and/or secondary growth constraint system **152**. The cathode structure backbone **141** may also include a top **1072** adjacent to the first secondary growth constraint **158**, a bottom **1074** adjacent to the second secondary growth constraint **160**, and a lateral surface (not marked) surrounding the vertical axis A.sub.CESB and connecting the top **1072** and the bottom **1074**. The cathode structure backbone **141** further includes a length L.sub.CESB, a width W.sub.CESB, and a height H.sub.CESB. The length L.sub.CESB being bounded by the lateral surface and measured along the X axis. The width W.sub.CESB being bounded by the lateral surface and measured along the Y axis, and the height H.sub.CESB being measured along the Z axis from the top **1072** to the bottom **1074**.

(206) The L.sub.CESB of the cathode structure backbone **141** will vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, the cathode structure backbone **141** will typically have a L.sub.CESB in the range of about 5 mm to about 500 mm. For example, in one such embodiment, the cathode structure backbone **141** will have a L.sub.CESB of about 10 mm to about 250 mm. By way of further example, in one such embodiment, the cathode structure backbone **141** will have a L.sub.CESB of about 20 mm to about 100 mm.

(207) The W.sub.CESB of the cathode structure backbone **141** will also vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, each cathode structure backbone **141** will typically have a W.sub.CESB of at least 1 micrometer. For example, in one embodiment, the W.sub.CESB of each cathode structure backbone **141** may be substantially thicker, but generally will not have a thickness in excess of 500

micrometers. By way of further example, in one embodiment, the W.sub.CESB of each cathode structure backbone **141** will be in the range of about 1 to about 50 micrometers.

(208) The H.sub.CESB of the cathode structure backbone **141** will also vary depending upon the energy storage device **100** or the secondary battery **102** and their intended use(s). In general, however, the cathode structure backbone **141** will typically have a H.sub.CESB of at least about 50 micrometers, more typically at least about 100 micrometers. Further, in general, the cathode structure backbone **141** will typically have a H.sub.CESB of no more than about 10,000 micrometers, and more typically no more than about 5,000 micrometers. For example, in one embodiment, the H.sub.CESB of each cathode structure backbone **141** will be in the range of about 0.05 mm to about 10 mm. By way of further example, in one embodiment, the H.sub.CESB of each cathode structure backbone **141** will be in the range of about 0.05 mm to about 5 mm. By way of further example, in one embodiment, the H.sub.CESB of each cathode structure backbone **141** will be in the range of about 0.1 mm to about 1 mm.

(209) Depending upon the application, cathode structure backbone **141** may be electrically conductive or insulating. For example, in one embodiment, the cathode structure backbone **141** may be electrically conductive and may include cathode current collector **140** for cathode active material **138**. In one such embodiment, cathode structure backbone **141** includes a cathode current collector **140** having a conductivity of at least about 10^3 Siemens/cm. By way of further example, in one such embodiment, cathode structure backbone **141** includes a cathode current collector **140** having a conductivity of at least about 10^4 Siemens/cm. By way of further example, in one such embodiment, cathode structure backbone **141** includes a cathode current collector **140** having a conductivity of at least about 10^5 Siemens/cm. In other embodiments, cathode structure backbone **141** is relatively nonconductive. For example, in one embodiment, cathode structure backbone **141** has an electrical conductivity of less than 10 Siemens/cm. By way of further example, in one embodiment, cathode structure backbone **141** has an electrical conductivity of less than 1 Siemens/cm. By way of further example, in one embodiment, cathode structure backbone **141** has an electrical conductivity of less than 10^{-1} Siemens/cm.

(210) In certain embodiments, cathode structure backbone **141** may include any material that may be shaped, such as metals, semiconductors, organics, ceramics, and glasses. For example, in certain embodiments, materials include semiconductor materials such as silicon and germanium. Alternatively, however, carbon-based organic materials, or metals, such as aluminum, copper, nickel, cobalt, titanium, and tungsten, may also be incorporated into cathode structure backbone **141**. In one exemplary embodiment, cathode structure backbone **141** comprises silicon. The silicon, for example, may be single crystal silicon, polycrystalline silicon, amorphous silicon, or a combination thereof.

(211) In certain embodiments, the cathode active material layer **138** may have a thickness of at least one micrometer. Typically, however, the cathode active material layer **138** thickness will not exceed 200 micrometers. For example, in one embodiment, the cathode active material layer **138** may have a thickness of about 1 to 50 micrometers. By way of further example, in one embodiment, the cathode active material layer **138** may have a thickness of about 2 to about 75 micrometers. By way of further example, in one embodiment, the cathode active material layer **138** may have a thickness of about 10 to about 100 micrometers. By way of further example, in one embodiment, the cathode active material layer **138** may have a thickness of about 5 to about 50 micrometers.

(212) In certain embodiments, the cathode current collector **140** includes an ionically permeable conductor that has sufficient ionic permeability to carrier ions to facilitate the movement of carrier ions from the separator **130** to the cathode active material layer **138**, and sufficient electrical conductivity to enable it to serve as a current collector. Whether or not positioned between the cathode active material layer **138** and the separator **130**, the cathode current collector **140** may facilitate more uniform carrier ion transport by distributing current from the cathode current

collector **140** across the surface of the cathode active material layer **138**. This, in turn, may facilitate more uniform insertion and extraction of carrier ions and thereby reduce stress in the cathode active material layer **138** during cycling, since the cathode current collector **140** distributes current to the surface of the cathode active material layer **138** facing the separator **130**, the reactivity of the cathode active material layer **138** for carrier ions will be the greatest where the carrier ion concentration is the greatest.

(213) The cathode current collector **140** includes an ionically permeable conductor material that is both ionically and electrically conductive. Stated differently, the cathode current collector **140** has a thickness, an electrical conductivity, and an ionic conductivity for carrier ions that facilitates the movement of carrier ions between an immediately adjacent cathode active material layer **138** on one side of the ionically permeable conductor layer and an immediately adjacent separator layer **130** on the other side of the cathode current collector **140** in an electrochemical stack or electrode assembly **106**. On a relative basis, the cathode current collector **140** has an electrical conductance that is greater than its ionic conductance when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. For example, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the cathode current collector **140** will typically be at least 1,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in one such embodiment, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the cathode current collector **140** is at least 5,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in one such embodiment, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the cathode current collector **140** is at least 10,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in one such embodiment, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the cathode current collector **140** layer is at least 50,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in one such embodiment, the ratio of the electrical conductance to the ionic conductance (for carrier ions) of the cathode current collector **140** is at least 100,000:1, respectively, when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**.

(214) In one embodiment, and when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**, such as when an energy storage device **100** or a secondary battery **102** is charging or discharging, the cathode current collector **140** has an ionic conductance that is comparable to the ionic conductance of an adjacent separator layer **130**. For example, in one embodiment, the cathode current collector **140** has an ionic conductance (for carrier ions) that is at least 50% of the ionic conductance of the separator layer **130** (i.e., a ratio of 0.5:1, respectively) when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the ionic conductance (for carrier ions) of the cathode current collector **140** to the ionic conductance (for carrier ions) of the separator layer **130** is at least 1:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the ionic conductance (for carrier ions) of the cathode current collector **140** to the ionic conductance (for carrier ions) of the separator layer **130** is at least 1.25:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the ionic conductance (for carrier ions) of the cathode current collector **140** to the ionic conductance (for carrier ions) of the separator layer **130** is at least 1.5:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the ionic conductance (for carrier ions) of the cathode

current collector **140** to the ionic conductance (for (anode current collector layer) carrier ions) of the separator layer **130** is at least 2:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**.

(215) In one embodiment, the cathode current collector **140** also has an electrical conductance that is substantially greater than the electrical conductance of the cathode active material layer **138**. For example, in one embodiment, the ratio of the electrical conductance of the cathode current collector **140** to the electrical conductance of the cathode active material layer **138** is at least 100:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the electrical conductance of the cathode current collector **140** to the electrical conductance of the cathode active material layer **138** is at least 500:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the electrical conductance of the cathode current collector **140** to the electrical conductance of the cathode active material layer **138** is at least 1000:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the electrical conductance of the cathode current collector **140** to the electrical conductance of the cathode active material layer **138** is at least 5000:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**. By way of further example, in some embodiments, the ratio of the electrical conductance of the cathode current collector **140** to the electrical conductance of the cathode active material layer **138** is at least 10,000:1 when there is an applied current to store energy in the device **100** or an applied load to discharge the device **100**.

(216) The thickness of the cathode current collector layer **140** (i.e., the shortest distance between the separator **130** and, in one embodiment, the cathodic active material layer **138** between which the cathode current collector layer **140** is sandwiched) in certain embodiments will depend upon the composition of the layer **140** and the performance specifications for the electrochemical stack. In general, when an cathode current collector layer **140** is an ionically permeable conductor layer, it will have a thickness of at least about 300 Angstroms. For example, in some embodiments, it may have a thickness in the range of about 300-800 Angstroms. More typically, however, it will have a thickness greater than about 0.1 micrometers. In general, an ionically permeable conductor layer will have a thickness not greater than about 100 micrometers. Thus, for example, in one embodiment, the cathode current collector layer **140** will have a thickness in the range of about 0.1 to about 10 micrometers. By way of further example, in some embodiments, the cathode current collector layer **140** will have a thickness in the range of about 0.1 to about 5 micrometers. By way of further example, in some embodiments, the cathode current collector layer **140** will have a thickness in the range of about 0.5 to about 3 micrometers. In general, it is preferred that the thickness of the cathode current collector layer **140** be approximately uniform. For example, in one embodiment, it is preferred that the cathode current collector layer **140** have a thickness non-uniformity of less than about 25%. In certain embodiments, the thickness variation is even less. For example, in some embodiments, the cathode current collector layer **140** has a thickness non-uniformity of less than about 20%. By way of further example, in some embodiments, the cathode current collector layer **140** has a thickness non-uniformity of less than about 15%. In some embodiments, the cathode current collector layer **140** has a thickness non-uniformity of less than about 10%.

(217) In one embodiment, the cathode current collector layer **140** is an ionically permeable conductor layer including an electrically conductive component and an ion conductive component that contributes to the ionic permeability and electrical conductivity. Typically, the electrically conductive component will include a continuous electrically conductive material (e.g., a continuous metal or metal alloy) in the form of a mesh or patterned surface, a film, or composite material comprising the continuous electrically conductive material (e.g., a continuous metal or metal alloy).

Additionally, the ion conductive component will typically comprise pores, for example, interstices of a mesh, spaces between a patterned metal or metal alloy containing material layer, pores in a metal film, or a solid ion conductor having sufficient diffusivity for carrier ions. In certain embodiments, the ionically permeable conductor layer includes a deposited porous material, an ion-transporting material, an ion-reactive material, a composite material, or a physically porous material. If porous, for example, the ionically permeable conductor layer may have a void fraction of at least about 0.25. In general, however, the void fraction will typically not exceed about 0.95. More typically, when the ionically permeable conductor layer is porous the void fraction may be in the range of about 0.25 to about 0.85. In some embodiments, for example, when the ionically permeable conductor layer is porous the void fraction may be in the range of about 0.35 to about 0.65.

(218) In the embodiment illustrated in FIG. 7, cathode current collector layer **140** is the sole cathode current collector for cathode active material layer **138**. Stated differently, cathode structure backbone **141** may include a cathode current collector **140**. In certain other embodiments, however, cathode structure backbone **141** may optionally not include a cathode current collector **140**.

(219) In one embodiment, first secondary growth constraint **158** and second secondary growth constraint **160** each may include an inner surface **1060** and **1062**, respectively, and an opposing outer surface **1064** and **1066**, respectively, separated along the z-axis thereby defining a first secondary growth constraint **158** height $H_{sub.158}$ and a second secondary growth constraint **160** height $H_{sub.160}$. According to aspects of the disclosure, increasing the heights of either the first and/or second secondary growth constraints **158**, **160**, respectively, can increase the stiffness of the constraints, but can also require increased volume, thus causing a reduction in energy density for an energy storage device **100** or a secondary battery **102** containing the electrode assembly **106** and set of constraints **108**. Accordingly, the thickness of the constraints **158**, **160** can be selected in accordance with the constraint material properties, the strength of the constraint required to offset pressure from a predetermined expansion of an electrode **100**, and other factors. For example, in one embodiment, the first and second secondary growth constraint heights $H_{sub.158}$ and $H_{sub.160}$, respectively, may be less than 50% of the height $H_{sub.ES}$. By way of further example, in one embodiment, the first and second secondary growth constraint heights $H_{sub.158}$ and $H_{sub.160}$, respectively, may be less than 25% of the height $H_{sub.ES}$. By way of further example, in one embodiment, the first and second secondary growth constraint heights $H_{sub.158}$ and $H_{sub.160}$, respectively, may be less than 10% of the height $H_{sub.ES}$. By way of further example, in one embodiment, the first and second secondary growth constraint heights $H_{sub.158}$ and $H_{sub.160}$ may be less than about 5% of the height $H_{sub.ES}$. In some embodiments, the first secondary growth constraint height $H_{sub.158}$ and the second secondary growth constraint height $H_{sub.160}$ may be different, and the materials used for each of the first and second secondary growth constraints **158**, **160** may also be different.

(220) In certain embodiments, the inner surfaces **1060** and **1062** may include surface features amenable to affixing the population of anode structures **110** and/or the population of cathode structures **112** thereto, and the outer surfaces **1064** and **1066** may include surface features amenable to the stacking of a plurality of constrained electrode assemblies **106** (i.e., inferred within FIG. 7, but not shown for clarity). For example, in one embodiment, the inner surfaces **1060** and **1062** or the outer surfaces **1064** and **1066** may be planar. By way of further example, in one embodiment, the inner surfaces **1060** and **1062** or the outer surfaces **1064** and **1066** may be non-planar. By way of further example, in one embodiment, the inner surfaces **1060** and **1062** and the outer surfaces **1064** and **1066** may be planar. By way of further example, in one embodiment, the inner surfaces **1060** and **1062** and the outer surfaces **1064** and **1066** may be non-planar. By way of further example, in one embodiment, the inner surfaces **1060** and **1062** and the outer surfaces **1064** and **1066** may be substantially planar.

(221) As described elsewhere herein, modes for affixing the at least one secondary connecting

member **166** embodied as anode structures **110** and/or cathode structures **112** to the inner surfaces **1060** and **1062** may vary depending upon the energy storage device **100** or secondary battery **102** and their intended use(s). As one exemplary embodiment shown in FIG. 7, the top **1052** and the bottom **1054** of the population of anode structures **110** (i.e., anode current collector **136**, as shown) and the top **1068** and bottom **1070** of the population of cathode structures **112** (i.e., cathode current collector **140**, as shown) may be affixed to the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160** via a layer of glue **182**. Alternatively, in certain embodiments only the anode current collectors **136**, or only the cathode current collectors **140**, may be affixed to serve as the at least one secondary connecting member **166**, or another sub-structure of the anode and/or cathode structures may serve as the at least one secondary connecting member **166**. Similarly, a top **1076** and a bottom **1078** of the first primary growth constraint **154**, and a top **1080** and a bottom **1082** of the second primary growth constraint **156** may be affixed to the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160** via a layer of glue **182**.

(222) Stated alternatively, in the embodiment shown in FIG. 7, the top **1052** and the bottom **1054** of the population of anode structures **110** include a height $H_{sub.ES}$ that effectively meets both the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160**, and may be affixed to the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160** via a layer of glue **182** in a flush embodiment. In addition, the top **1068** and the bottom **1070** of the population of cathode structures **112** include a height $H_{sub.CES}$ that effectively meets both the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160**, and may be affixed to the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160** via a layer of glue **182** in a flush embodiment.

(223) Further, in another exemplary embodiment, a top **1056** and a bottom **1058** of the anode backbones **134**, and a top **1072** and a bottom **1074** of the cathode backbones **141** may be affixed to the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160** via a layer of glue **182** (not illustrated). Similarly, a top **1076** and a bottom **1078** of the first primary growth constraint **154**, and a top **1080** and a bottom **1082** of the second primary growth constraint **156** may be affixed to the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160** via a layer of glue **182** (not illustrated with respect to the embodiment described in this paragraph). Stated alternatively, the top **1056** and the bottom **1058** of the anode backbones **134** include a height $H_{sub.ESB}$ that effectively meets both the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160**, and may be affixed to the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160** via a layer of glue **182** in a flush embodiment. In addition, the top **1072** and the bottom **1074** of the cathode backbones **141** include a height $H_{sub.CESB}$ that effectively meets both the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160**, and may be affixed to the inner surface **1060** of the first secondary growth constraint **158** and the inner surface **1062** of the second secondary growth constraint **160** via a layer of glue **182** in a flush embodiment.

(224) Accordingly, in one embodiment, at least a portion of the population of anode **110** and/or cathode structures **112**, and/or the separator **130** may serve as one or more secondary connecting members **166** to connect the first and second secondary growth constraints **158**, **160**, respectively, to one another in a secondary growth constraint system **152**, thereby providing a compact and space-efficient constraint system to restrain growth of the electrode assembly **106** during cycling thereof. According to one embodiment, any portion of the anode **110** and/or cathode structures **112**,

and/or separator **130** may serve as the one or more secondary connecting members **166**, with the exception of any portion of the anode **110** and/or cathode structure **112** that swells in volume with charge and discharge cycles. That is, that portion of the anode **110** and/or cathode structure **112**, such as the anode active material **132**, that is the cause of the volume change in the electrode assembly **106**, typically will not serve as a part of the set of electrode constraints **108**. In one embodiment, first and second primary growth constraints **154**, **156**, respectively, provided as a part of the primary growth constraint system **151** further inhibit growth in a longitudinal direction, and may also serve as secondary connecting members **166** to connect the first and second secondary growth constraints **158**, **160**, respectively, of the secondary growth constraint system **152**, thereby providing a cooperative, synergistic constraint system (i.e., set of electrode constraints **108**) for restraint of anode growth/swelling.

(225) Secondary Battery

(226) Referring now to FIG. 9, illustrated is an exploded view of one embodiment of a secondary battery **102**. The secondary battery **102** includes battery enclosure **104** and a set of electrode assemblies **106a** within the battery enclosure **104**, each of the electrode assemblies **106** having a first longitudinal end surface **116**, an opposing second longitudinal end surface **118** (i.e., separated from first longitudinal end surface **116** along the Y axis the Cartesian coordinate system shown), as described above. Each electrode assembly **106** includes a population of anode structures **110** and a population of cathode structures **112**, stacked relative to each other within each of the electrode assemblies **106** in a stacking direction D; stated differently, the populations of anode **110** and cathode **112** structures are arranged in an alternating series of anodes **110** and cathodes **112** with the series progressing in the stacking direction D between first and second longitudinal end surfaces **116**, **118**, respectively (see, e.g., FIG. 2; as illustrated in FIG. 2 and FIG. 9, stacking direction D parallels the Y axis of the Cartesian coordinate system(s) shown), as described above. In addition, the stacking direction D within an individual electrode assembly **106** is perpendicular to the direction of stacking of a collection of electrode assemblies **106** within a set **106a** (i.e., an electrode assembly stacking direction); stated differently, the electrode assemblies **106** are disposed relative to each other in a direction within a set **106a** that is perpendicular to the stacking direction D within an individual electrode assembly **106** (e.g., the electrode assembly stacking direction is in a direction corresponding to the Z axis of the Cartesian coordinate system shown, whereas the stacking direction D within individual electrode assemblies **106** is in a direction corresponding to the Y axis of the Cartesian coordinate system shown).

(227) While the set of electrode assemblies **106a** depicted in the embodiment shown in FIG. 9 contains individual electrode assemblies **106** having the same general size, one or more of the individual electrode assemblies **106** may also and/or alternatively have different sizes in at least one dimension thereof, than the other electrode assemblies **106** in the set **106a**. For example, according to one embodiment, the electrode assemblies **106** that are stacked together to form the set **106a** provided in the secondary battery **102** may have different maximum widths $W_{sub.EA}$ in the longitudinal direction (i.e., stacking direction D) of each assembly **106**. According to another embodiment, the electrode assemblies **106** making up the stacked set **106a** provided in the secondary battery **102** may have different maximum lengths $L_{sub.EA}$ along the transverse axis that is orthogonal to the longitudinal axis. By way of further example, in one embodiment, each electrode assembly **106** that is stacked together to form the set of electrode assemblies **106a** in the secondary battery **102** has a maximum width $W_{sub.EA}$ along the longitudinal axis and a maximum length $L_{sub.EA}$ along the transverse axis that is selected to provide an area of $L_{sub.EA} \times W_{sub.EA}$ that decreases along a direction in which the electrode assemblies **106** are stacked together to form the set of electrode assemblies **106a**. For example, the maximum width $W_{sub.EA}$ and maximum length $L_{sub.EA}$ of each electrode assembly **106** may be selected to be less than that of an electrode assembly **106** adjacent thereto in a first direction in which the assemblies **106** are stacked, and to be greater than that of an electrode assembly **106** adjacent

thereto in a second direction that is opposite thereto, such that the electrode assemblies **106** are stacked together to form a secondary battery **102** having a set of electrode assemblies **106a** in a pyramidal shape. Alternatively, the maximum lengths $L_{\text{sub.EA}}$ and maximum widths $W_{\text{sub.EA}}$ for each electrode assembly **106** can be selected to provide different shapes and/or configurations for the stacked electrode assembly set **106a**. The maximum vertical height $H_{\text{sub.EA}}$ for one or more of the electrode assemblies **106** can also and/or alternatively be selected to be different from other assemblies **106** in the set **106a** and/or to provide a stacked set **106a** having a predetermined shape and/or configuration.

(228) Tabs **190**, **192** project out of the battery enclosure **104** and provide an electrical connection between the electrode assemblies **106** of set **106a** and an energy supply or consumer (not shown). More specifically, in this embodiment tab **190** is electrically connected to tab extension **191** (e.g., using an electrically conductive glue), and tab extension **191** is electrically connected to the electrodes **110** comprised by each of the electrode assemblies **106**. Similarly, tab **192** is electrically connected to tab extension **193** (e.g., using an electrically conductive glue), and tab extension **193** is electrically connected to the counter-electrodes **112** comprised by each of electrode assemblies **106**.

(229) Each electrode assembly **106** in the embodiment illustrated in FIG. 9 may have an associated primary growth constraint system **151** to restrain growth in the longitudinal direction (i.e., stacking direction D). Alternatively, in one embodiment, a plurality of electrode assemblies **106** making up a set **106a** may share at least a portion of the primary growth constraint system **151**. In the embodiment as shown, each primary growth constraint system **151** includes first and second primary growth constraints **154**, **156**, respectively, that may overlie first and second longitudinal end surfaces **116**, **118**, respectively, as described above; and first and second opposing primary connecting members **162**, **164**, respectively, that may overlie lateral surfaces **142**, as described above. First and second opposing primary connecting members **162**, **164**, respectively, may pull first and second primary growth constraints **154**, **156**, respectively, towards each other, or alternatively stated, assist in restraining growth of the electrode assembly **106** in the longitudinal direction, and primary growth constraints **154**, **156** may apply a compressive or restraint force to the opposing first and second longitudinal end surfaces **116**, **118**, respectively. As a result, expansion of the electrode assembly **106** in the longitudinal direction is inhibited during formation and/or cycling of the battery **102** between charged and discharged states. Additionally, primary growth constraint system **151** exerts a pressure on the electrode assembly **106** in the longitudinal direction (i.e., stacking direction D) that exceeds the pressure maintained on the electrode assembly **106** in either of the two directions that are mutually perpendicular to each other and are perpendicular to the longitudinal direction (e.g., as illustrated, the longitudinal direction corresponds to the direction of the Y axis, and the two directions that are mutually perpendicular to each other and to the longitudinal direction correspond to the directions of the X axis and the Z axis, respectively, of the illustrated Cartesian coordinate system).

(230) Further, each electrode assembly **106** in the embodiment illustrated in FIG. 9 has an associated secondary growth constraint system **152** to restrain growth in the vertical direction (i.e., expansion of the electrode assembly **106**, anodes **110**, and/or cathodes **112** in the vertical direction (i.e., along the Z axis of the Cartesian coordinate system)). Alternatively, in one embodiment, a plurality of electrode assemblies **106** making up a set **106a** share at least a portion of the secondary growth constraint system **152**. Each secondary growth constraint system **152** includes first and second secondary growth constraints **158**, **160**, respectively, that may overlie corresponding lateral surfaces **142**, respectively, and at least one secondary connecting member **166**, each as described in more detail above. Secondary connecting members **166** may pull first and second secondary growth constraints **158**, **160**, respectively, towards each other, or alternatively stated, assist in restraining growth of the electrode assembly **106** in the vertical direction, and first and second secondary growth constraints **158**, **160**, respectively, may apply a compressive or restraint force to the lateral

surfaces **142**), each as described above in more detail. As a result, expansion of the electrode assembly **106** in the vertical direction is inhibited during formation and/or cycling of the battery **102** between charged and discharged states. Additionally, secondary growth constraint system **152** exerts a pressure on the electrode assembly **106** in the vertical direction (i.e., parallel to the Z axis of the Cartesian coordinate system) that exceeds the pressure maintained on the electrode assembly **106** in either of the two directions that are mutually perpendicular to each other and are perpendicular to the vertical direction (e.g., as illustrated, the vertical direction corresponds to the direction of the Z axis, and the two directions that are mutually perpendicular to each other and to the vertical direction correspond to the directions of the X axis and the Y axis, respectively, of the illustrated Cartesian coordinate system).

(231) Further still, each electrode assembly **106** in the embodiment illustrated in FIG. **9** may have an associated primary growth constraint system **151**—and an associated secondary growth constraint system **152**—to restrain growth in the longitudinal direction and the vertical direction, as described in more detail above. Furthermore, according to certain embodiments, the anode and/or cathode tabs **190**, **192**, respectively, and tab extensions **191**, **193** can serve as a part of the tertiary growth constraint system **155**. For example, in certain embodiments, the tab extensions **191**, **193** may extend along the opposing transverse surface regions **144**, **146** to act as a part of the tertiary constraint system **155**, such as the first and second tertiary growth constraints **157**, **159**. The tab extensions **191**, **193** can be connected to the primary growth constraints **154**, **156** at the longitudinal ends **117**, **119** of the electrode assembly **106**, such that the primary growth constraints **154**, **156** serve as the at least one tertiary connecting member **165** that places the tab extensions **191**, **193** in tension with one another to compress the electrode assembly **106** along the transverse direction, and act as first and second tertiary growth constraints **157**, **159**, respectively. Conversely, the tabs **190**, **192** and/or tab extensions **191**, **193** can also serve as the first and second primary connecting members **162**, **164**, respectively, for the first and second primary growth constraints **154**, **156**, respectively, according to one embodiment. In yet another embodiment, the tabs **190**, **192** and/or tab extensions **191**, **193** can serve as a part of the secondary growth constraint system **152**, such as by forming a part of the at least one secondary connecting member **166** connecting the secondary growth constraints **158**, **160**. Accordingly, the tabs **190**, **192** and/or tab extensions **191**, **193** can assist in restraining overall macroscopic growth of the electrode assembly **106** by either serving as a part of one or more of the primary and secondary constraint systems **151**, **152**, respectively, and/or by forming a part of a tertiary growth constraint system **155** to constrain the electrode assembly **106** in a direction orthogonal to the direction being constrained by one or more of the primary and secondary growth constraint systems **151**, **152**, respectively.

(232) To complete the assembly of the secondary battery **102**, battery enclosure **104** is filled with a non-aqueous electrolyte (not shown) and lid **104a** is folded over (along fold line, FL) and sealed to upper surface **104b**. When fully assembled, the sealed secondary battery **102** occupies a volume bounded by its exterior surfaces (i.e., the displacement volume), the secondary battery enclosure **104** occupies a volume corresponding to the displacement volume of the battery (including lid **104a**) less its interior volume (i.e., the prismatic volume bounded by interior surfaces **104c**, **104d**, **104e**, **104f**, **104g** and lid **104a**) and each growth constraint **151**, **152** of set **106a** occupies a volume corresponding to its respective displacement volume. In combination, therefore, the battery enclosure **104** and growth constraints **151**, **152** occupy no more than 75% of the volume bounded by the outer surface of the battery enclosure **104** (i.e., the displacement volume of the battery). For example, in one such embodiment, the growth constraints **151**, **152** and battery enclosure **104**, in combination, occupy no more than 60% of the volume bounded by the outer surface of the battery enclosure **104**. By way of further example, in one such embodiment, the constraints **151**, **152** and battery enclosure **104**, in combination, occupy no more than 45% of the volume bounded by the outer surface of the battery enclosure **104**. By way of further example, in one such embodiment, the constraints **151**, **152** and battery enclosure **104**, in combination, occupy no more than 30% of the

volume bounded by the outer surface of the battery enclosure **104**. By way of further example, in one such embodiment, the constraints **151**, **152** and battery enclosure **104**, in combination, occupy no more than 20% of the volume bounded by the outer surface of the battery enclosure.

(233) For ease of illustration in FIG. **9**, secondary battery **102** includes only one set **106a** of electrode assemblies **106** and the set **106a** includes only six electrode assemblies **106**. In practice, the secondary battery **102** may include more than one set of electrode assemblies **106a**, with each of the sets **106a** being disposed laterally relative to each other (e.g., in a relative direction lying within the X-Y plane of the Cartesian coordinate system of FIG. **9**) or vertically relative to each other (e.g., in a direction substantially parallel to the Z axis of the Cartesian coordinate system of FIG. **9**). Additionally, in each of these embodiments, each of the sets of electrode assemblies **106a** may include one or more electrode assemblies **106**. For example, in certain embodiments, the secondary battery **102** may comprise one, two, or more sets of electrode assemblies **106a**, with each such set **106a** including one or more electrode assemblies **106** (e.g., 1, 2, 3, 4, 5, 6, 10, 15, or more electrode assemblies **106** within each such set **106a**) and, when the battery **102** includes two or more such sets **106a**, the sets **106a** may be laterally or vertically disposed relative to other sets of electrode assemblies **106a** included in the secondary battery **102**. In each of these various embodiments, each individual electrode assembly **106** may have its own growth constraint(s), as described above (i.e., a 1:1 relationship between electrode assemblies **106** and constraints **151**, **152**), two more electrode assemblies **106** may have a common growth constraint(s) **151**, **152**, as described above (i.e., a set of constraints **108** for two or more electrode assemblies **106**), or two or more electrode assemblies **106** may share components of a growth constraint(s) **151**, **152** (i.e., two or more electrode assemblies **106** may have a common compression member (e.g., second secondary growth constraint **158**) and/or tension members **166**, for example, as in the fused embodiment, as described above).

(234) Other Battery Components

(235) In certain embodiments, the set of electrode constraints **108**, including a primary growth constraint system **151** and a secondary growth constraint system **152**, as described above, may be derived from a sheet **2000** having a length L.sub.1, width W.sub.1, and thickness t.sub.1, as shown for example in FIG. **9**. More specifically, to form a primary growth constraint system **151**, a sheet **2000** may be wrapped around an electrode assembly **106** and folded at folded at edges **2001** to enclose the electrode assembly **106**. Alternatively, in one embodiment, the sheet **2000** may be wrapped around a plurality of electrode assemblies **106** that are stacked to form an electrode assembly set **106a**. The edges of the sheet may overlap each other, and are welded, glued, or otherwise secured to each other to form a primary growth constraint system **151** including first primary growth constraint **154** and second primary growth constraint **156**, and first primary connecting member **162** and second primary connecting member **164**. In this embodiment, the primary growth constraint system **151** has a volume corresponding to the displacement volume of sheet **2000** (i.e., the multiplication product of L.sub.1, W.sub.1 and t.sub.1). In one embodiment, the at least one primary connecting member is stretched in the stacking direction D to place the member in tension, which causes a compressive force to be exerted by the first and second primary growth constraints. Alternatively, the at least one secondary connecting member can be stretched in the second direction to place the member in tension, which causes a compressive force to be exerted by the first and second secondary growth constraints. In an alternative embodiment, instead of stretching the connecting members to place them in tension, the connecting members and/or growth constraints or other portion of one or more of the primary and secondary growth constraint systems may be pre-tensioned prior to installation over and/or in the electrode assembly. In another alternative embodiment, the connecting members and/or growth constraints and/or other portions of one or more of the primary and secondary growth constraint systems are not initially under tension at the time of installation into and/or over the electrode assembly, but rather, formation of the battery causes the electrode assembly to expand and induce tension in portions of the primary

and/or secondary growth constraint systems such as the connecting members and/or growth constraints. (i.e., self-tensioning).

(236) Sheet **2000** may comprise any of a wide range of compatible materials capable of applying the desired force to the electrode assembly **106**. In general, the primary growth constraint system **151** will typically comprise a material that has an ultimate tensile strength of at least 10,000 psi (>70 MPa), that is compatible with the battery electrolyte, does not significantly corrode at the floating or anode potential for the battery **102**, and does not significantly react or lose mechanical strength at 45° C., and even up to 70° C. For example, the primary growth constraint system **151** may comprise any of a wide range of metals, alloys, ceramics, glass, plastics, or a combination thereof (i.e., a composite). In one exemplary embodiment, primary growth constraint system **151** comprises a metal such as stainless steel (e.g., SS 316, 440 C or 440 C hard), aluminum (e.g., aluminum 7075-T6, hard H18), titanium (e.g., 6Al-4V), beryllium, beryllium copper (hard), copper (O.sub.2 free, hard), nickel; in general, however, when the primary growth constraint system **151** comprises metal it is generally preferred that it be incorporated in a manner that limits corrosion and limits creating an electrical short between the anodes **110** and cathodes **112**. In another exemplary embodiment, the primary growth constraint system **151** comprises a ceramic such as alumina (e.g., sintered or Coorstek AD96), zirconia (e.g., Coorstek YZTP), yttria-stabilized zirconia (e.g., ENrG E-Strate®). In another exemplary embodiment, the primary growth constraint system **151** comprises a glass such as Schott D263 tempered glass. In another exemplary embodiment, the primary growth constraint system **151** comprises a plastic such as polyetheretherketone (PEEK) (e.g., Aptiv 1102), PEEK with carbon (e.g., Victrex 90HMF40 or Xycomp 1000-04), polyphenylene sulfide (PPS) with carbon (e.g., Tepex Dynalite 207), polyetheretherketone (PEEK) with 30% glass, (e.g., Victrex 90HMF40 or Xycomp 1000-04), polyimide (e.g., Kapton®). In another exemplary embodiment, the primary growth constraint system **151** comprises a composite such as E Glass Std Fabric/Epoxy, 0 deg, E Glass UD/Epoxy, 0 deg, Kevlar Std Fabric/Epoxy, 0 deg, Kevlar UD/Epoxy, 0 deg, Carbon Std Fabric/Epoxy, 0 deg, Carbon UD/Epoxy, 0 deg, Toyobo Zylon® HM Fiber/Epoxy. In another exemplary embodiment, the primary growth constraint system **151** comprises fibers such as Kevlar 49 Aramid Fiber, S Glass Fibers, Carbon Fibers, Vectran UM LCP Fibers, Dyneema, Zylon.

(237) Thickness (t.sub.1) of the primary growth constraint system **151** will depend upon a range of factors including, for example, the material(s) of construction of the primary growth constraint system **151**, the overall dimensions of the electrode assembly **106**, and the composition of a battery anode and cathode. In some embodiments, for example, the primary growth constraint system **151** will comprise a sheet having a thickness in the range of about 10 to about 100 micrometers. For example, in one such embodiment, the primary growth constraint system **151** comprises a stainless steel sheet (e.g., SS316) having a thickness of about 30 µm. By way of further example, in another such embodiment, the primary growth constraint system **151** comprises an aluminum sheet (e.g., 7075-T6) having a thickness of about 40 µm. By way of further example, in another such embodiment, the primary growth constraint system **151** comprises a zirconia sheet (e.g., Coorstek YZTP) having a thickness of about 30 µm. By way of further example, in another such embodiment, the primary growth constraint system **151** comprises an E Glass UD/Epoxy 0 deg sheet having a thickness of about 75 µm. By way of further example, in another such embodiment, the primary growth constraint system **151** comprises 12 µm carbon fibers at >50% packing density.

(238) Without being bound to any particular theory, methods for gluing, as described herein, may include gluing, soldering, bonding, sintering, press contacting, brazing, thermal spraying joining, clamping, or combinations thereof. Gluing may include joining the materials with conductive materials such as conducting epoxies, conducting elastomers, mixtures of insulating organic glue filled with conducting metals, such as nickel filled epoxy, carbon filled epoxy etc. Conductive pastes may be used to join the materials together and the joining strength could be tailored by temperature (sintering), light (UV curing, cross-linking), chemical curing (catalyst based cross

linking). Bonding processes may include wire bonding, ribbon bonding, ultrasonic bonding. Welding processes may include ultrasonic welding, resistance welding, laser beam welding, electron beam welding, induction welding, and cold welding. Joining of these materials can also be performed by using a coating process such as a thermal spray coating such as plasma spraying, flame spraying, arc spraying, to join materials together. For example, a nickel or copper mesh can be joined onto a nickel bus using a thermal spray of nickel as a glue.

(239) Members of the anode **110** and cathode structure **112** populations can include an electroactive material capable of absorbing and releasing a carrier ion such as lithium, sodium, potassium, calcium, magnesium or aluminum ions. In some embodiments, members of the anode structure **110** population include an anodically active electroactive material (sometimes referred to as a negative electrode) and members of the cathode structure **112** population include a cathodically active electroactive material (sometimes referred to as a positive electrode). In each of the embodiments and examples recited in this paragraph, negative electrode active material may be a particulate agglomerate electrode or a monolithic electrode.

(240) Exemplary anodically active electroactive materials include carbon materials such as graphite and soft or hard carbons, or any of a range of metals, semi-metals, alloys, oxides and compounds capable of forming an alloy with lithium. Specific examples of the metals or semi-metals capable of constituting the anode material include tin, lead, magnesium, aluminum, boron, gallium, silicon, indium, zirconium, germanium, bismuth, cadmium, antimony, silver, zinc, arsenic, hafnium, yttrium, and palladium. In one exemplary embodiment, the anodically active material comprises aluminum, tin, or silicon, or an oxide thereof, a nitride thereof, a fluoride thereof, or other alloy thereof. In another exemplary embodiment, the anodically active material comprises silicon or an alloy thereof.

(241) Exemplary cathode active materials include any of a wide range of cathode active materials. For example, for a lithium-ion battery, the cathode active material may comprise a cathode material selected from transition metal oxides, transition metal sulfides, transition metal nitrides, lithium-transition metal oxides, lithium-transition metal sulfides, and lithium-transition metal nitrides may be selectively used. The transition metal elements of these transition metal oxides, transition metal sulfides, and transition metal nitrides can include metal elements having a d-shell or f-shell. Specific examples of such metal element are Sc, Y, lanthanoids, actinoids, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Tc, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pb, Pt, Cu, Ag, and Au. Additional cathode active materials include LiCoO_2 , $\text{LiNi}_{0.5}\text{Mn}_{1.5}\text{O}_4$, $\text{Li}_{1-x}\text{Ni}_x\text{Co}_y\text{Al}_2\text{O}_4$, LiFePO_4 , $\text{Li}_{1-x}\text{Mn}_x\text{O}_4$, V_2O_5 , molybdenum oxysulfides, phosphates, silicates, vanadates and combinations thereof.

(242) In one embodiment, the anode active material is microstructured to provide a significant void volume fraction to accommodate volume expansion and contraction as lithium ions (or other carrier ions) are incorporated into or leave the negative electrode active material during charging and discharging processes. In general, the void volume fraction of the anode active material is at least 0.1. Typically, however, the void volume fraction of the negative electrode active material is not greater than 0.8. For example, in one embodiment, the void volume fraction of the negative electrode active material is about 0.15 to about 0.75. By way of the further example, in one embodiment, the void volume fraction of the anode active material is about 0.2 to about 0.7. By way of the further example, in one embodiment, the void volume fraction of the anode active material is about 0.25 to about 0.6.

(243) Depending upon the composition of the microstructured anode active material and the method of its formation, the microstructured anode active material may comprise macroporous, microporous, or mesoporous material layers or a combination thereof, such as a combination of microporous and mesoporous, or a combination of mesoporous and macroporous. Microporous material is typically characterized by a pore dimension of less than 10 nm, a wall dimension of less than 10 nm, a pore depth of 1-50 micrometers, and a pore morphology that is generally

characterized by a “spongy” and irregular appearance, walls that are not smooth, and branched pores. Mesoporous material is typically characterized by a pore dimension of 10-50 nm, a wall dimension of 10-50 nm, a pore depth of 1-100 micrometers, and a pore morphology that is generally characterized by branched pores that are somewhat well defined or dendritic pores. Macroporous material is typically characterized by a pore dimension of greater than 50 nm, a wall dimension of greater than 50 nm, a pore depth of 1-500 micrometers, and a pore morphology that may be varied, straight, branched, or dendritic, and smooth or rough-walled. Additionally, the void volume may comprise open or closed voids, or a combination thereof. In one embodiment, the void volume comprises open voids, that is, the anode active material contains voids having openings at the lateral surface of the anode active material through which lithium ions (or other carrier ions) can enter or leave the anode active material; for example, lithium ions may enter the anode active material through the void openings after leaving the cathode active material. In another embodiment, the void volume comprises closed voids, that is, the anode active material contains voids that are enclosed by anode active material. In general, open voids can provide greater interfacial surface area for the carrier ions whereas closed voids tend to be less susceptible to solid electrolyte interface while each provides room for expansion of the negative electrode active material upon the entry of carrier ions. In certain embodiments, therefore, it is preferred that the anode active material comprise a combination of open and closed voids.

(244) In one embodiment, anode active material comprises porous aluminum, tin or silicon or an alloy thereof. Porous silicon layers may be formed, for example, by anodization, by etching (e.g., by depositing precious metals such as gold, platinum, silver or gold/palladium on the surface of single crystal silicon and etching the surface with a mixture of hydrofluoric acid and hydrogen peroxide), or by other methods known in the art such as patterned chemical etching. Additionally, the porous anode active material will generally have a porosity fraction of at least about 0.1, but less than 0.8 and have a thickness of about 1 to about 100 micrometers. For example, in one embodiment, anode active material comprises porous silicon, has a thickness of about 5 to about 100 micrometers, and has a porosity fraction of about 0.15 to about 0.75. By way of further example, in one embodiment, anode active material comprises porous silicon, has a thickness of about 10 to about 80 micrometers, and has a porosity fraction of about 0.15 to about 0.7. By way of further example, in one such embodiment, anode active material comprises porous silicon, has a thickness of about 20 to about 50 micrometers, and has a porosity fraction of about 0.25 to about 0.6. By way of further example, in one embodiment, anode active material comprises a porous silicon alloy (such as nickel silicide), has a thickness of about 5 to about 100 micrometers, and has a porosity fraction of about 0.15 to about 0.75.

(245) In another embodiment, anode active material comprises fibers of aluminum, tin or silicon, or an alloy thereof. Individual fibers may have a diameter (thickness dimension) of about 5 nm to about 10,000 nm and a length generally corresponding to the thickness of the anode active material. Fibers (nanowires) of silicon may be formed, for example, by chemical vapor deposition or other techniques known in the art such as vapor liquid solid (VLS) growth and solid liquid solid (SLS) growth. Additionally, the anode active material will generally have a porosity fraction of at least about 0.1, but less than 0.8 and have a thickness of about 1 to about 200 micrometers. For example, in one embodiment, anode active material comprises silicon nanowires, has a thickness of about 5 to about 100 micrometers, and has a porosity fraction of about 0.15 to about 0.75. By way of further example, in one embodiment, anode active material comprises silicon nanowires, has a thickness of about 10 to about 80 micrometers, and has a porosity fraction of about 0.15 to about 0.7. By way of further example, in one such embodiment, anode active material comprises silicon nanowires, has a thickness of about 20 to about 50 micrometers, and has a porosity fraction of about 0.25 to about 0.6. By way of further example, in one embodiment, anode active material comprises nanowires of a silicon alloy (such as nickel silicide), has a thickness of about 5 to about 100 micrometers, and has a porosity fraction of about 0.15 to about 0.75.

(246) In one embodiment, each member of the anode **110** population has a bottom, a top, and a longitudinal axis (A.sub.E) extending from the bottom to the top thereof and in a direction generally perpendicular to the direction in which the alternating sequence of anode structures **110** and cathode structures **112** progresses. Additionally, each member of the anode **110** population has a length (L.sub.A) measured along the longitudinal axis (A.sub.E) of the anode, a width (W.sub.A) measured in the direction in which the alternating sequence of anode structures and cathode structures progresses, and a height (H.sub.A) measured in a direction that is perpendicular to each of the directions of measurement of the length (L.sub.A) and the width (W.sub.A). Each member of the anode population also has a perimeter (P.sub.A) that corresponds to the sum of the length(s) of the side(s) of a projection of the electrode in a plane that is normal to its longitudinal axis. Exemplary values for the length L.sub.A, width W.sub.A and height H.sub.A are discussed in greater detail above

(247) According to one embodiment, the members of the anode population include one or more first anode members having a first height, and one or more second anode members having a second height that is other than the first. For example, in one embodiment, the one or more first anode members may have a height selected to allow the anode members to contact a portion of the secondary constraint system in the vertical direction (Z axis). For example, the height of the one or more first anode members may be sufficient such that the first anode members extend between and contact both the first and second secondary growth constraints **158**, **160** along the vertical axis, such as when at least one of the first anode members or a substructure thereof serves as a secondary connecting member **166**. Furthermore, according to one embodiment, one or more second anode members may have a height that is less than the one or more first anode members, such that for example the one or more second anode members do not fully extend to contact both of the first and second secondary growth constraints **158**, **160**. In yet another embodiment, the different heights for the one or more first anode members and one or more second anode members may be selected to accommodate a predetermined shape for the electrode assembly **106**, such as an electrode assembly shape having a different heights along one or more of the longitudinal and/or transverse axis, and/or to provide predetermined performance characteristics for the secondary battery.

(248) The perimeter (P.sub.A) of the members of the anode population will similarly vary depending upon the energy storage device and its intended use. In general, however, members of the anode population will typically have a perimeter (P.sub.A) within the range of about 0.025 mm to about 25 mm. For example, in one embodiment, the perimeter (P.sub.A) of each member of the anode population will be in the range of about 0.1 mm to about 15 mm. By way of further example, in one embodiment, the perimeter (P.sub.A) of each member of the anode population will be in the range of about 0.5 mm to about 10 mm.

(249) In general, members of the anode population have a length (L.sub.A) that is substantially greater than each of its width (W.sub.A) and its height (H.sub.A). For example, in one embodiment, the ratio of L.sub.A to each of W.sub.A and H.sub.A is at least 5:1, respectively (that is, the ratio of L.sub.A to W.sub.A is at least 5:1, respectively and the ratio of L.sub.A to H.sub.A is at least 5:1, respectively), for each member of the anode population. By way of further example, in one embodiment the ratio of L.sub.A to each of W.sub.A and H.sub.A is at least 10:1. By way of further example, in one embodiment, the ratio of L.sub.A to each of W.sub.A and H.sub.A is at least 15:1. By way of further example, in one embodiment, the ratio of L.sub.A to each of W.sub.A and H.sub.A is at least 20:1, for each member of the anode population.

(250) Additionally, it is generally preferred that members of the anode population have a length (L.sub.A) that is substantially greater than its perimeter (P.sub.A), for example, in one embodiment, the ratio of L.sub.A to P.sub.A is at least 1.25:1, respectively, for each member of the anode population. By way of further example, in one embodiment the ratio of L.sub.A to P.sub.A is at least 2.5:1, respectively, for each member of the anode population. By way of further example, in one embodiment, the ratio of L.sub.A to P.sub.A is at least 3.75:1, respectively, for each member of

the anode population.

(251) In one embodiment, the ratio of the height ($H_{sub.A}$) to the width ($W_{sub.A}$) of the members of the anode population is at least 0.4:1, respectively. For example, in one embodiment, the ratio of $H_{sub.A}$ to $W_{sub.A}$ will be at least 2:1, respectively, for each member of the anode population. By way of further example, in one embodiment the ratio of $H_{sub.A}$ to $W_{sub.A}$ will be at least 10:1, respectively. By way of further example, in one embodiment the ratio of $H_{sub.A}$ to $W_{sub.A}$ will be at least 20:1, respectively. Typically, however, the ratio of $H_{sub.A}$ to $W_{sub.A}$ will generally be less than 1,000:1, respectively. For example, in one embodiment the ratio of $H_{sub.A}$ to $W_{sub.A}$ will be less than 500:1, respectively. By way of further example, in one embodiment the ratio of $H_{sub.A}$ to $W_{sub.A}$ will be less than 100:1, respectively. By way of further example, in one embodiment the ratio of $H_{sub.A}$ to $W_{sub.A}$ will be less than 10:1, respectively. By way of further example, in one embodiment the ratio of $H_{sub.A}$ to $W_{sub.A}$ will be in the range of about 2:1 to about 100:1, respectively, for each member of the anode population.

(252) Each member of the cathode population has a bottom, a top, and a longitudinal axis ($A_{sub.CE}$) extending from the bottom to the top thereof and in a direction generally perpendicular to the direction in which the alternating sequence of anode structures and cathode structures progresses. Additionally, each member of the cathode population has a length ($L_{sub.C}$) measured along the longitudinal axis ($A_{sub.CE}$), a width ($W_{sub.C}$) measured in the direction in which the alternating sequence of anode structures and cathode structures progresses, and a height ($H_{sub.C}$) measured in a direction that is perpendicular to each of the directions of measurement of the length ($L_{sub.C}$) and the width ($W_{sub.C}$). Each member of the cathode population also has a perimeter (P_c) that corresponds to the sum of the length(s) of the side(s) of a projection of the cathode in a plane that is normal to its longitudinal axis.

(253) According to one embodiment, the members of the cathode population include one or more first cathode members having a first height, and one or more second cathode members having a second height that is other than the first. For example, in one embodiment, the one or more first cathode members may have a height selected to allow the cathode members to contact a portion of the secondary constraint system in the vertical direction (Z axis). For example, the height of the one or more first cathode members may be sufficient such that the first cathode members extend between and contact both the first and second secondary growth constraints **158**, **160** along the vertical axis, such as when at least one of the first cathode members or a substructure thereof serves as a secondary connecting member **166**. Furthermore, according to one embodiment, one or more second cathode members may have a height that is less than the one or more first cathode members, such that for example the one or more second cathode members do not fully extend to contact both of the first and second secondary growth constraints **158**, **160**. In yet another embodiment, the different heights for the one or more first cathode members and one or more second cathode members may be selected to accommodate a predetermined shape for the electrode assembly **106**, such as an electrode assembly shape having a different heights along one or more of the longitudinal and/or transverse axis, and/or to provide predetermined performance characteristics for the secondary battery.

(254) The perimeter (P_c) of the members of the cathode population will also vary depending upon the energy storage device and its intended use. In general, however, members of the cathode population will typically have a perimeter (P_c) within the range of about 0.025 mm to about 25 mm. For example, in one embodiment, the perimeter (P_c) of each member of the cathode population will be in the range of about 0.1 mm to about 15 mm. By way of further example, in one embodiment, the perimeter (P_c) of each member of the cathode population will be in the range of about 0.5 mm to about 10 mm.

(255) In general, each member of the cathode population has a length ($L_{sub.C}$) that is substantially greater than width ($W_{sub.C}$) and substantially greater than its height ($H_{sub.C}$). For example, in one embodiment, the ratio of $L_{sub.C}$ to each of $W_{sub.C}$ and $H_{sub.C}$ is at least 5:1, respectively

(that is, the ratio of L.sub.C to W.sub.C is at least 5:1, respectively and the ratio of L.sub.C to H.sub.C is at least 5:1, respectively), for each member of the cathode population. By way of further example, in one embodiment the ratio of L.sub.C to each of W.sub.C and H.sub.C is at least 10:1 for each member of the cathode population. By way of further example, in one embodiment, the ratio of L.sub.C to each of W.sub.C and H.sub.C is at least 15:1 for each member of the cathode population. By way of further example, in one embodiment, the ratio of L.sub.C to each of W.sub.C and H.sub.C is at least 20:1 for each member of the cathode population.

(256) Additionally, it is generally preferred that members of the cathode population have a length (L.sub.C) that is substantially greater than its perimeter (Pc); for example, in one embodiment, the ratio of L.sub.C to Pc is at least 1.25:1, respectively, for each member of the cathode population. By way of further example, in one embodiment the ratio of L.sub.C to Pc is at least 2.5:1, respectively, for each member of the cathode population. By way of further example, in one embodiment, the ratio of L.sub.C to Pc is at least 3.75:1, respectively, for each member of the cathode population.

(257) In one embodiment, the ratio of the height (H.sub.C) to the width (W.sub.C) of the members of the cathode population is at least 0.4:1, respectively. For example, in one embodiment, the ratio of H.sub.C to W.sub.C will be at least 2:1, respectively, for each member of the cathode population. By way of further example, in one embodiment the ratio of H.sub.C to W.sub.C will be at least 10:1, respectively, for each member of the cathode population. By way of further example, in one embodiment the ratio of H.sub.C to W.sub.C will be at least 20:1, respectively, for each member of the cathode population. Typically, however, the ratio of H.sub.C to W.sub.C will generally be less than 1,000:1, respectively, for each member of the cathode population. For example, in one embodiment the ratio of H.sub.C to W.sub.C will be less than 500:1, respectively, for each member of the cathode population. By way of further example, in one embodiment the ratio of H.sub.C to W.sub.C will be less than 100:1, respectively. By way of further example, in one embodiment the ratio of H.sub.C to W.sub.C will be less than 10:1, respectively. By way of further example, in one embodiment the ratio of H.sub.C to W.sub.C will be in the range of about 2:1 to about 100:1, respectively, for each member of the cathode population.

(258) In one embodiment the anode current conductor layer **136** comprised by each member of the anode population has a length L.sub.NC that is at least 50% of the length L.sub.NE of the member comprising such anode current collector. By way of further example, in one embodiment the anode current conductor layer **136** comprised by each member of the anode population has a length L.sub.NC that is at least 60% of the length L.sub.NE of the member comprising such anode current collector. By way of further example, in one embodiment the anode current conductor layer **136** comprised by each member of the anode population has a length L.sub.NC that is at least 70% of the length L.sub.NE of the member comprising such anode current collector. By way of further example, in one embodiment the anode current conductor layer **136** comprised by each member of the anode population has a length L.sub.NC that is at least 80% of the length L.sub.NE of the member comprising such anode current collector. By way of further example, in one embodiment the anode current conductor **136** comprised by each member of the anode population has a length L.sub.NC that is at least 90% of the length L.sub.NE of the member comprising such anode current collector.

(259) In one embodiment, the cathode current conductor **140** comprised by each member of the cathode population has a length L.sub.PC that is at least 50% of the length L.sub.PE of the member comprising such cathode current collector. By way of further example, in one embodiment the cathode current conductor **140** comprised by each member of the cathode population has a length L.sub.PC that is at least 60% of the length L.sub.PE of the member comprising such cathode current collector. By way of further example, in one embodiment the cathode current conductor **140** comprised by each member of the cathode population has a length L.sub.PC that is at least 70% of the length L.sub.PE of the member comprising such cathode current collector. By way of further

example, in one embodiment the cathode current conductor **140** comprised by each member of the cathode population has a length $L_{\text{sub.PC}}$ that is at least 80% of the length $L_{\text{sub.PE}}$ of the member comprising such cathode current collector. By way of further example, in one embodiment the cathode current conductor **140** comprised by each member of the cathode population has a length $L_{\text{sub.PC}}$ that is at least 90% of the length $L_{\text{sub.PE}}$ of the member comprising such cathode current collector.

(260) In one embodiment, being positioned between the anode active material layer and the separator, anode current collector **136** may facilitate more uniform carrier ion transport by distributing current from the anode current collector across the surface of the anode active material layer. This, in turn, may facilitate more uniform insertion and extraction of carrier ions and thereby reduce stress in the anode active material during cycling, since anode current collector **136** distributes current to the surface of the anode active material layer facing the separator, the reactivity of the anode active material layer for carrier ions will be the greatest where the carrier ion concentration is the greatest. In yet another embodiment, the positions of the anode current collector **136** and the anode active material layer may be reversed.

(261) According to one embodiment, each member of the cathode structure population has a cathode current collector **140** that may be disposed, for example, between the cathode backbone and the cathode active material layer. Furthermore, one or more of the anode current collector **136** and cathode electrode current collector **140** may comprise a metal such as aluminum, carbon, chromium, gold, nickel, NiP, palladium, platinum, rhodium, ruthenium, an alloy of silicon and nickel, titanium, or a combination thereof (see “Current collectors for positive electrodes of lithium-based batteries” by A. H. Whitehead and M. Schreiber, Journal of the Electrochemical Society, 152(11) A2105-A2113 (2005)). By way of further example, in one embodiment, cathode current collector **140** comprises gold or an alloy thereof such as gold silicide. By way of further example, in one embodiment, cathode current collector **140** comprises nickel or an alloy thereof such as nickel silicide.

(262) In an alternative embodiment, the positions of the cathode current collector layer and the cathode electrode active material layer may be reversed, for example such that the cathode electrode current collector layer is positioned between the separator layer and the cathode active material layer. In such embodiments, the cathode electrode current collector **140** for the immediately adjacent cathode active material layer comprises an ionically permeable conductor having a composition and construction as described in connection with the anode current collector layer; that is, the cathode current collector layer comprises a layer of an ionically permeable conductor material that is both ionically and electrically conductive. In this embodiment, the cathode electrode current collector layer has a thickness, an electrical conductivity, and an ionic conductivity for carrier ions that facilitates the movement of carrier ions between an immediately adjacent cathode electrode active material layer on one side of the cathode electrode current collector layer and an immediately adjacent separator layer on the other side of the cathode electrode current collector layer in an electrochemical stack.

(263) Electrically insulating separator layers **130** may surround and electrically isolate each member of the anode structure **110** population from each member of the cathode structure **112** population. Electrically insulating separator layers **130** will typically include a microporous separator material that can be permeated with a non-aqueous electrolyte; for example, in one embodiment, the microporous separator material includes pores having a diameter of at least 50 Å, more typically in the range of about 2,500 Å, and a porosity in the range of about 25% to about 75%, more typically in the range of about 35-55%. Additionally, the microporous separator material may be permeated with a non-aqueous electrolyte to permit conduction of carrier ions between adjacent members of the anode and cathode populations. In certain embodiments, for example, and ignoring the porosity of the microporous separator material, at least 70 vol % of electrically insulating separator material between a member of the anode structure **110** population

and the nearest member(s) of the cathode structure **112** population (i.e., an “adjacent pair”) for ion exchange during a charging or discharging cycle is a microporous separator material; stated differently, microporous separator material constitutes at least 70 vol % of the electrically insulating material between a member of the anode structure **110** population and the nearest member of the cathode **112** structure population. By way of further example, in one embodiment, and ignoring the porosity of the microporous separator material, microporous separator material constitutes at least 75 vol % of the electrically insulating separator material layer between adjacent pairs of members of the anode structure **110** population and members of the cathode structure **112** population, respectively. By way of further example, in one embodiment, and ignoring the porosity of the microporous separator material, the microporous separator material constitutes at least 80 vol % of the electrically insulating separator material layer between adjacent pairs of members of the anode structure **110** population and members of the cathode structure **112** population, respectively. By way of further example, in one embodiment, and ignoring the porosity of the microporous separator material, the microporous separator material constitutes at least 85 vol % of the electrically insulating separator material layer between adjacent pairs of members of the anode structure **110** population and members of the cathode structure **112** population, respectively. By way of further example, in one embodiment, and ignoring the porosity of the microporous separator material, the microporous separator material constitutes at least 90 vol % of the electrically insulating separator material layer between adjacent pairs of members of the anode structure **110** population and member of the cathode structure **112** population, respectively. By way of further example, in one embodiment, and ignoring the porosity of the microporous separator material, the microporous separator material constitutes at least 95 vol % of the electrically insulating separator material layer between adjacent pairs of members of the anode structure **110** population and members of the cathode structure **112** population, respectively. By way of further example, in one embodiment, and ignoring the porosity of the microporous separator material, the microporous separator material constitutes at least 99 vol % of the electrically insulating separator material layer between adjacent pairs of members of the anode structure **110** population and members of the cathode structure **112** population, respectively.

(264) In one embodiment, the microporous separator material comprises a particulate material and a binder, and has a porosity (void fraction) of at least about 20 vol. % The pores of the microporous separator material will have a diameter of at least 50 Å and will typically fall within the range of about 250 to 2,500 Å. The microporous separator material will typically have a porosity of less than about 75%. In one embodiment, the microporous separator material has a porosity (void fraction) of at least about 25 vol %. In one embodiment, the microporous separator material will have a porosity of about 35-55%.

(265) The binder for the microporous separator material may be selected from a wide range of inorganic or polymeric materials. For example, in one embodiment, the binder is an organic material selected from the group consisting of silicates, phosphates, aluminates, aluminosilicates, and hydroxides such as magnesium hydroxide, calcium hydroxide, etc. For example, in one embodiment, the binder is a fluoropolymer derived from monomers containing vinylidene fluoride, hexafluoropropylene, tetrafluoropropene, and the like. In another embodiment, the binder is a polyolefin such as polyethylene, polypropylene, or polybutene, having any of a range of varying molecular weights and densities. In another embodiment, the binder is selected from the group consisting of ethylene-diene-propene terpolymer, polystyrene, polymethyl methacrylate, polyethylene glycol, polyvinyl acetate, polyvinyl butyral, polyacetal, and polyethyleneglycol diacrylate. In another embodiment, the binder is selected from the group consisting of methyl cellulose, carboxymethyl cellulose, styrene rubber, butadiene rubber, styrene-butadiene rubber, isoprene rubber, polyacrylamide, polyvinyl ether, polyacrylic acid, polymethacrylic acid, and polyethylene oxide. In another embodiment, the binder is selected from the group consisting of acrylates, styrenes, epoxies, and silicones. In another embodiment, the binder is a copolymer or

blend of two or more of the aforementioned polymers.

(266) The particulate material comprised by the microporous separator material may also be selected from a wide range of materials. In general, such materials have a relatively low electronic and ionic conductivity at operating temperatures and do not corrode under the operating voltages of the battery electrode or current collector contacting the microporous separator material. For example, in one embodiment, the particulate material has a conductivity for carrier ions (e.g., lithium) of less than 1×10^{-4} S/cm. By way of further example, in one embodiment, the particulate material has a conductivity for carrier ions of less than 1×10^{-5} S/cm. By way of further example, in one embodiment, the particulate material has a conductivity for carrier ions of less than 1×10^{-6} S/cm. Exemplary particulate materials include particulate polyethylene, polypropylene, a TiO_2 -polymer composite, silica aerogel, fumed silica, silica gel, silica hydrogel, silica xerogel, silica sol, colloidal silica, alumina, titania, magnesia, kaolin, talc, diatomaceous earth, calcium silicate, aluminum silicate, calcium carbonate, magnesium carbonate, or a combination thereof. For example, in one embodiment, the particulate material comprises a particulate oxide or nitride such as TiO_2 , SiO_2 , Al_2O_3 , GeO_2 , B_2O_3 , Bi_2O_3 , BaO , ZnO , ZrO_2 , BN , Si_3N_4 , Ge_3N_4 . See, for example, P. Arora and J. Zhang, "Battery Separators" Chemical Reviews 2004, 104, 4419-4462). In one embodiment, the particulate material will have an average particle size of about 20 nm to 2 micrometers, more typically 200 nm to 1.5 micrometers. In one embodiment, the particulate material will have an average particle size of about 500 nm to 1 micrometer.

(267) In an alternative embodiment, the particulate material comprised by the microporous separator material may be bound by techniques such as sintering, binding, curing, etc. while maintaining the void fraction desired for electrolyte ingress to provide the ionic conductivity for the functioning of the battery.

(268) Microporous separator materials may be deposited, for example, by electrophoretic deposition of a particulate separator material in which particles are coalesced by surface energy such as electrostatic attraction or van der Waals forces, slurry deposition (including spin or spray coating) of a particulate separator material, screen printing, dip coating, and electrostatic spray deposition. Binders may be included in the deposition process; for example, the particulate material may be slurry deposited with a dissolved binder that precipitates upon solvent evaporation, electrophoretically deposited in the presence of a dissolved binder material, or co-electrophoretically deposited with a binder and insulating particles etc. Alternatively, or additionally, binders may be added after the particles are deposited into or onto the electrode structure; for example, the particulate material may be dispersed in an organic binder solution and dip coated or spray-coated, followed by drying, melting, or cross-linking the binder material to provide adhesion strength.

(269) In an assembled energy storage device, the microporous separator material is permeated with a non-aqueous electrolyte suitable for use as a secondary battery electrolyte. Typically, the non-aqueous electrolyte comprises a lithium salt dissolved in an organic solvent. Exemplary lithium salts include inorganic lithium salts such as LiClO_4 , LiBF_4 , LiPF_6 , LiAsF_6 , LiCl , and LiBr ; and organic lithium salts such as $\text{LiB}(\text{C}_6\text{H}_5)_4$, $\text{LiN}(\text{SO}_2\text{CF}_3)_2$, $\text{LiN}(\text{SO}_2\text{CF}_3)_3$, $\text{LiNSO}_2\text{CF}_3$, $\text{LiNSO}_2\text{CF}_5$, $\text{LiNSO}_2\text{C}_4\text{F}_9$, $\text{LiNSO}_2\text{C}_5\text{F}_{11}$, $\text{LiNSO}_2\text{C}_6\text{F}_{13}$, and $\text{LiNSO}_2\text{C}_7\text{F}_{15}$. Exemplary organic solvents to dissolve the lithium salt include cyclic esters, chain esters, cyclic ethers, and chain ethers. Specific examples of the cyclic esters include propylene carbonate, butylene carbonate, γ -butyrolactone, vinylene carbonate, 2-methyl- γ -butyrolactone, acetyl- γ -butyrolactone, and γ -valerolactone. Specific examples of the chain esters include dimethyl carbonate, diethyl carbonate, dibutyl carbonate, dipropyl carbonate, methyl ethyl carbonate, methyl butyl carbonate, methyl propyl carbonate, ethyl butyl carbonate, ethyl propyl carbonate, butyl propyl carbonate, alkyl propionates, dialkyl

malonates, and alkyl acetates. Specific examples of the cyclic ethers include tetrahydrofuran, alkyltetrahydrofurans, dialkyltetrahydrofurans, alkoxytetrahydrofurans, dialkoxytetrahydrofurans, 1,3-dioxolane, alkyl-1,3-dioxolanes, and 1,4-dioxolane. Specific examples of the chain ethers include 1,2-dimethoxyethane, 1,2-diethoxythane, diethyl ether, ethylene glycol dialkyl ethers, diethylene glycol dialkyl ethers, triethylene glycol dialkyl ethers, and tetraethylene glycol dialkyl ethers.

(270) Furthermore, according to one embodiment, components of the secondary battery **102** including the microporous separator **130** and other anode **110** and/or cathode **112** structures comprise a configuration and composition that allow the components to function, even in a case where expansion of anode active material **132** occurs during charge and discharge of the secondary battery **102**. That is, the components may be structured such that failure of the components due to expansion of the electrode active material **132** during charge/discharge thereof is within acceptable limits.

INCORPORATION BY REFERENCE

(271) All publications and patents mentioned herein, including those items listed below, are hereby incorporated by reference in their entirety for all purposes as if each individual publication or patent was specifically and individually incorporated by reference. In case of conflict, the present application, including any definitions herein, will control.

EQUIVALENTS

(272) While specific embodiments have been discussed, the above specification is illustrative, and not restrictive. Many variations will become apparent to those skilled in the art upon review of this specification. The full scope of the embodiments should be determined by reference to the claims, along with their full scope of equivalents, and the specification, along with such variations.

(273) Unless otherwise indicated, all numbers expressing quantities of ingredients, reaction conditions, and so forth used in the specification and claims are to be understood as being modified in all instances by the term “about.” Accordingly, unless indicated to the contrary, the numerical parameters set forth in this specification and attached claims are approximations that may vary depending upon the desired properties sought to be obtained.

Claims

1. A secondary battery for cycling between a charged state and a discharged state, the secondary battery comprising a battery enclosure, an electrode assembly, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure, the electrode assembly comprising a population of anode structures, a population of cathode structures, and an electrically insulating microporous separator material electrically separating members of the population of anode structures and the population of cathode structures, the population of anode structures and the population of cathode structures are arranged in an alternating sequence in a longitudinal direction, each member of the population of anode structures has a first cross-sectional area, $A_{sub.1}$, when the secondary battery is in the charged state and a second cross-sectional area, $A_{sub.2}$, when the secondary battery is in the discharged state, each member of the population of cathode structures has a first cross-sectional area, $C_{sub.1}$, when the secondary battery is in the charged state and a second cross-sectional area, $C_{sub.2}$, when the secondary battery is in the discharged state, and the first cross-sectional area and the second cross-sectional area of the members of the population of anode structures and of the population of cathode structures, are measured in a first longitudinal plane parallel to the longitudinal direction; the electrode assembly further comprising a set of electrode constraints that at least partially restrains growth of the electrode assembly in the longitudinal direction upon cycling of the secondary battery between the charged state and discharged state; and each member of the population of cathode structures comprises a layer of a cathode active material comprising filler particles that are compressible and elastic, and each member of the population of anode

structures comprises a layer of an anode active material having a capacity to accept more than one mole of carrier ion per mole of anode active material when the secondary battery is charged from the discharged state to the charged state, $A_{sub.1}$ being greater than $A_{sub.2}$ for each of the members of a subset of the population of anode structures and $C_{sub.1}$ is less than $C_{sub.2}$ for each of the members of a subset of the population of cathode structures, and a difference $C_{sub.2}-C_{sub.1}$ does not exceed a difference $A_{sub.1}-A_{sub.2}$ during the cycling of the secondary battery.

2. The secondary battery of claim 1, wherein the charged state is at least 75% of a rated capacity of the secondary battery, and the discharged state is less than 25% of the rated capacity of the secondary battery.

3. The secondary battery of claim 1, wherein a ratio $C_{sub.2}$ to $C_{sub.1}$ for each member of the subset of the population of cathode structures is at least 1.1:1.

4. The secondary battery of claim 1, wherein the subset of the population of anode structures has (a) a first median cross-sectional area $MA_{sub.A1}$ when the secondary battery is in the charged state and (b) a second median cross-sectional area $MA_{sub.A2}$ when the secondary battery is in the discharged state, and the subset of the population of cathode structures has a first median cross-sectional area $MA_{sub.C1}$ (c) when the secondary battery is in the charged state and (d) a second median cross-sectional area $MA_{sub.C2}$ when the secondary battery is in the discharged state, wherein $MA_{sub.A1}$ is greater than $MA_{sub.A2}$ and $MA_{sub.C1}$ is less than $MA_{sub.C2}$.

5. The secondary battery of claim 1, wherein at least one member of the subset of the population of anode structure has (a) a first median cross-sectional area $ML_{sub.A1}$ when the secondary battery is in the charged state, and (b) a second median cross-sectional area $ML_{sub.A2}$ when the secondary battery is in the discharged state, and at least one member of the subset of the population of cathode structure has (c) a first median cross-sectional area $ML_{sub.C1}$ when the secondary battery is in the charged state, and (d) a second median cross-sectional area $ML_{sub.C2}$ when the secondary battery is in the discharged state, wherein $ML_{sub.A1}$, $ML_{sub.A2}$, $ML_{sub.C1}$ and $ML_{sub.C2}$, are measured in a plurality of longitudinal planes parallel to the longitudinal direction for each member, and wherein $ML_{sub.A1}$ is greater than $ML_{sub.A2}$ for each of the members of the subset of the population of anode structures and $ML_{sub.C1}$ is less than $ML_{sub.C2}$ for each of the members of the subset of the population of cathode structures.

6. The secondary battery of claim 1, wherein members of the population of cathode structures comprise a layer of cathode active material that is porous, and wherein the layer of cathode active material has a first porosity $P_{sub.1}$ when the secondary battery is in a charged state, and a second porosity $P_{sub.2}$ when the secondary battery is in a discharged state, the first porosity $P_{sub.1}$ being less than the second porosity $P_{sub.2}$.

7. The secondary battery of claim 1, wherein the cathode active material of members of the population of cathode structures comprise particles of cathode active materials dispersed in a matrix.

8. The secondary battery of claim 7, wherein the cathode active material comprises particles of the cathode active material selected from the group consisting of transition metal oxides, transition metal sulfides, transition metal nitrides, lithium-transition metal oxides, lithium-transition metal sulfides, and lithium-transition metal nitrides, dispersed in the matrix, the matrix comprising a polymeric material.

9. The secondary battery of claim 1, wherein the set of electrode constraints comprises: a primary constraint system comprising first and second primary growth constraints and at least one primary connecting member, the first and second primary growth constraints separated from each other in the longitudinal direction and the at least one primary connecting member connecting the first and second primary growth constraints, wherein the primary constraint system at least partially restrains growth of the electrode assembly in the longitudinal direction upon cycling of the secondary battery.

10. The secondary battery of claim 9, wherein the set of electrode constraints further comprises: a secondary constraint system comprising first and second secondary growth constraints separated in a second direction and connected by at least one secondary connecting member, wherein the secondary constraint system at least partially restrains growth of the electrode assembly in a second direction upon cycling of the secondary battery, the second direction being orthogonal to the longitudinal direction.

11. A secondary battery for cycling between a charged state and a discharged state, the secondary battery comprising a battery enclosure, an electrode assembly, carrier ions, and a non-aqueous liquid electrolyte within the battery enclosure, the electrode assembly comprising a population of anode structures, a population of cathode structures, and an electrically insulating microporous separator material electrically separating members of the population of anode structures and the population of cathode structures, the population of anode structures and population of cathode structures are arranged in an alternating sequence in a longitudinal direction, each member of the population of anode structures has a first cross-sectional area, $A_{\text{sub.1}}$, when the secondary battery is in the charged state and a second cross-sectional area, $A_{\text{sub.2}}$, when the secondary battery is in the discharged state, each member of the population of cathode structures has a first cross-sectional area, $C_{\text{sub.1}}$, when the secondary battery is in the charged state and a second cross-sectional area, $C_{\text{sub.2}}$, when the secondary battery is in the discharged state, and the first cross-sectional area and the second cross-sectional area of the members of the population of anode structures and of the population of cathode structures, are measured in a first longitudinal plane that is parallel to the longitudinal direction; the electrode assembly further comprising a set of electrode constraints that at least partially restrains growth of the electrode assembly in the longitudinal direction upon cycling of the secondary battery between the charged state and the discharged state; each member of the population of cathode structures comprising a layer of a cathode active material comprising filler particles, and each member of the population of anode structures comprises a layer of an anode active material having a capacity to accept more than one mole of carrier ion per mole of anode active material when the secondary battery is charged from a discharged state to a charged state, a ratio $C_{\text{sub.2}}$ to $C_{\text{sub.1}}$ for each of the members of a subset of the population of cathode structures being at least 1.1 to 1 (1.1:1), $A_{\text{sub.1}}$ being greater than $A_{\text{sub.2}}$ for each of the members of a subset of the population of anode structures and $C_{\text{sub.1}}$ is less than $C_{\text{sub.2}}$ for each of the members of the subset of the population of cathode structures, and a difference $C_{\text{sub.2}} - C_{\text{sub.1}}$ does not exceed a difference $A_{\text{sub.1}} - A_{\text{sub.2}}$ during cycling of the secondary battery.

12. The secondary battery of claim 11, wherein the charged state is at least 75% of a rated capacity of the secondary battery, and the discharged state is less than 25% of the rated capacity of the secondary battery.

13. The secondary battery of claim 11, wherein the filler particles of the layer of the cathode active material are compressible and elastic.

14. The secondary battery of claim 11, wherein the subset of the population of anode structures has (a) a first median cross-sectional area $MA_{\text{sub.A1}}$ when the secondary battery is in the charged state and (b) a second median cross-sectional area $MA_{\text{sub.A2}}$ when the secondary battery is in the discharged state, and the subset of the population of cathode structure has (c) a first median cross-sectional area $MA_{\text{sub.C1}}$ when the secondary battery is in the charged state and (d) a second median cross-sectional area $MA_{\text{sub.C2}}$ when the secondary battery is in the discharged state, wherein $MA_{\text{sub.A1}}$ is greater than $MA_{\text{sub.A2}}$ and $MA_{\text{sub.C1}}$ is less than $MA_{\text{sub.C2}}$.

15. The secondary battery of claim 11, wherein at least one member of the subset of the population of anode structures has (a) a first median cross-sectional area $ML_{\text{sub.A1}}$ when the secondary battery is in the charged state, and (b) a second median cross-sectional area $ML_{\text{sub.A2}}$ when the secondary battery is in the discharged state, and at least one member of the subset of the population of cathode structure has (c) a first median cross-sectional area $ML_{\text{sub.C1}}$ when the secondary battery is in the charged state, and (d) a second median cross-sectional area $ML_{\text{sub.C2}}$ when the

secondary battery is in the discharged state, where ML.sub.A1, ML.sub.A2, ML.sub.C1 and ML.sub.C2, are measured in a plurality of longitudinal planes parallel to the longitudinal direction for each member, and wherein ML.sub.A1 is greater than ML.sub.A2 for each of the members of the subset of the population of anode structures and ML.sub.C1 is less than ML.sub.C2 for each of the members of the subset of the population of cathode structures.

16. The secondary battery of claim 11, wherein members of the population of cathode structures comprise a layer of cathode active material that is porous, and wherein the layer of cathode active material has a first porosity P.sub.1 when the secondary battery is in a charged state, and a second porosity P.sub.2 when the secondary battery is in a discharged state, the first porosity P.sub.1 being less than the second porosity P.sub.2.

17. The secondary battery of claim 11, wherein the cathode active material layers of members of the population of cathode structures comprise particles of cathode active materials dispersed in a matrix.

18. The secondary battery of claim 17, wherein the cathode active material comprises particles of cathode active material selected from the group consisting of transition metal oxides, transition metal sulfides, transition metal nitrides, lithium-transition metal oxides, lithium-transition metal sulfides, and lithium-transition metal nitrides, dispersed in the matrix, the matrix comprising a polymeric material.

19. The secondary battery of claim 11, wherein the set of electrode constraints comprises: a primary constraint system comprising first and second primary growth constraints and at least one primary connecting member, the first and second primary growth constraints separated from each other in the longitudinal direction and the at least one primary connecting member connecting the first and second primary growth constraints, wherein the primary constraint system at least partially restrains growth of the electrode assembly in the longitudinal direction upon cycling of the secondary battery.

20. The secondary battery of claim 19, wherein the set of electrode constraints further comprises: a secondary constraint system comprising first and second secondary growth constraints separated in a second direction and connected by at least one secondary connecting member, wherein the secondary constraint system at least partially restrains growth of the electrode assembly in a second direction upon cycling of the secondary battery, the second direction being orthogonal to the longitudinal direction.
