



US012419188B2

(12) **United States Patent**
Tsai et al.

(10) **Patent No.:** **US 12,419,188 B2**
(45) **Date of Patent:** **Sep. 16, 2025**

(54) **ORGANIC ELECTROLUMINESCENT MATERIALS AND DEVICES**

(71) Applicant: **Universal Display Corporation**,
Ewing, NJ (US)

(72) Inventors: **Jui-Yi Tsai**, Newtown, PA (US); **Alexey Borisovich Dyatkin**, Ambler, PA (US); **Pierre-Luc T. Boudreault**, Pennington, NJ (US)

(73) Assignee: **UNIVERSAL DISPLAY CORPORATION**, Ewing, NJ (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 901 days.

(21) Appl. No.: **17/322,370**

(22) Filed: **May 17, 2021**

(65) **Prior Publication Data**

US 2023/0029347 A1 Jan. 26, 2023

Related U.S. Application Data

(60) Provisional application No. 63/045,954, filed on Jun. 30, 2020.

(51) **Int. Cl.**
H10K 85/30 (2023.01)
C07F 15/00 (2006.01)

(Continued)

(52) **U.S. Cl.**
CPC **H10K 85/342** (2023.02); **C07F 15/0033** (2013.01); **C09K 11/06** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H10K 85/342; H10K 85/341; H10K 85/344; H10K 85/346; H10K 85/348;
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,769,292 A 9/1988 Tang et al.
5,061,569 A 10/1991 VanSlyke et al.
(Continued)

FOREIGN PATENT DOCUMENTS

EP 0650955 5/1995
EP 1725079 11/2006
(Continued)

OTHER PUBLICATIONS

Adachi, Chihaya et al., "Organic Electroluminescent Device Having a Hole Conductor as an Emitting Layer," Appl. Phys. Lett., 55(15): 1489-1491 (1989).

(Continued)


Primary Examiner — Jennifer A Boyd

Assistant Examiner — Rachel Simbana

(74) *Attorney, Agent, or Firm* — DUANE MORRIS LLP


(57) **ABSTRACT**

Provided are iridium complexes having a ligand L_A of Formula I



Also provided are formulations comprising these iridium complexes. Further provided are OLEDs and related consumer products that utilize these iridium complexes.

20 Claims, 3 Drawing Sheets



- (51) **Int. Cl.**
C09K 11/06 (2006.01)
H10K 50/11 (2023.01)
H10K 101/10 (2023.01)
- (52) **U.S. Cl.**
 CPC C07B 2200/05 (2013.01); C09K 2211/1048 (2013.01); C09K 2211/185 (2013.01); H10K 50/11 (2023.02); H10K 2101/10 (2023.02)
- (58) **Field of Classification Search**
 CPC H10K 85/371; C07F 15/0033; C07F 15/0086; C07F 1/08; C07F 1/10; C07F 1/12; C07F 15/0006; C07F 15/002; C07F 15/0046; C07F 15/006; C07F 15/0073; C09K 2211/1048; C09K 2211/185
 See application file for complete search history.
- (56) **References Cited**

U.S. PATENT DOCUMENTS

5,247,190 A 9/1993 Friend et al.
 5,703,436 A 12/1997 Forrest et al.
 5,707,745 A 1/1998 Forrest et al.
 5,834,893 A 11/1998 Bulovic et al.
 5,844,363 A 12/1998 Gu et al.
 6,013,982 A 1/2000 Thompson et al.
 6,087,196 A 7/2000 Sturm et al.
 6,091,195 A 7/2000 Forrest et al.
 6,097,147 A 8/2000 Baldo et al.
 6,294,398 B1 9/2001 Kim et al.
 6,303,238 B1 10/2001 Thompson et al.
 6,337,102 B1 1/2002 Forrest et al.
 6,468,819 B1 10/2002 Kim et al.
 6,528,187 B1 3/2003 Okada
 6,687,266 B1 2/2004 Ma et al.
 6,835,469 B2 12/2004 Kwong et al.
 6,921,915 B2 7/2005 Takiguchi et al.
 7,087,321 B2 8/2006 Kwong et al.
 7,090,928 B2 8/2006 Thompson et al.
 7,154,114 B2 12/2006 Brooks et al.
 7,250,226 B2 7/2007 Tokito et al.
 7,279,704 B2 10/2007 Walters et al.
 7,332,232 B2 2/2008 Ma et al.
 7,338,722 B2 3/2008 Thompson et al.
 7,393,599 B2 7/2008 Thompson et al.
 7,396,598 B2 7/2008 Takeuchi et al.
 7,431,968 B1 10/2008 Shtein et al.
 7,445,855 B2 11/2008 Mackenzie et al.
 7,534,505 B2 5/2009 Lin et al.
 2002/0034656 A1 3/2002 Thompson et al.
 2002/0134984 A1 9/2002 Igarashi
 2002/0158242 A1 10/2002 Son et al.
 2003/0138657 A1 7/2003 Li et al.
 2003/0152802 A1 8/2003 Tsuboyama et al.
 2003/0162053 A1 8/2003 Marks et al.
 2003/0175553 A1 9/2003 Thompson et al.
 2003/0230980 A1 12/2003 Forrest et al.
 2004/0036077 A1 2/2004 Ise
 2004/0137267 A1 7/2004 Igarashi et al.
 2004/0137268 A1 7/2004 Igarashi et al.
 2004/0174116 A1 9/2004 Lu et al.
 2005/0025993 A1 2/2005 Thompson et al.
 2005/0112407 A1 5/2005 Ogasawara et al.
 2005/0238919 A1 10/2005 Ogasawara
 2005/0244673 A1 11/2005 Satoh et al.
 2005/0260441 A1 11/2005 Thompson et al.
 2005/0260449 A1 11/2005 Walters et al.
 2006/0008670 A1 1/2006 Lin et al.
 2006/0202194 A1 9/2006 Jeong et al.
 2006/0240279 A1 10/2006 Adamovich et al.
 2006/0251923 A1 11/2006 Lin et al.
 2006/0263635 A1 11/2006 Ise
 2006/0280965 A1 12/2006 Kwong et al.
 2007/0190359 A1 8/2007 Knowles et al.
 2007/0278938 A1 12/2007 Yabunouchi et al.

2008/0015355 A1 1/2008 Schafer et al.
 2008/0018221 A1 1/2008 Egen et al.
 2008/0106190 A1 5/2008 Yabunouchi et al.
 2008/0124572 A1 5/2008 Mizuki et al.
 2008/0220265 A1 9/2008 Xia et al.
 2008/0297033 A1 12/2008 Knowles et al.
 2009/0008605 A1 1/2009 Kawamura et al.
 2009/0009065 A1 1/2009 Nishimura et al.
 2009/0017330 A1 1/2009 Iwakuma et al.
 2009/0030202 A1 1/2009 Iwakuma et al.
 2009/0039776 A1 2/2009 Yamada et al.
 2009/0045730 A1 2/2009 Nishimura et al.
 2009/0045731 A1 2/2009 Nishimura et al.
 2009/0101870 A1 4/2009 Prakash et al.
 2009/0108737 A1 4/2009 Kwong et al.
 2009/0115316 A1 5/2009 Zheng et al.
 2009/0165846 A1 7/2009 Johannes et al.
 2009/0167162 A1 7/2009 Lin et al.
 2009/0179554 A1 7/2009 Kuma et al.
 2015/0274762 A1* 10/2015 Li H10K 85/341 546/4
 2020/0361974 A1* 11/2020 Dyatkin C07F 15/0033

FOREIGN PATENT DOCUMENTS

EP 2034538 3/2009
 JP 200511610 1/2005
 JP 2007123392 5/2007
 JP 2007254297 10/2007
 JP 2008074939 4/2008
 WO 01/39234 5/2001
 WO 02/02714 1/2002
 WO 02015654 2/2002
 WO 03040257 5/2003
 WO 03060956 7/2003
 WO 2004093207 10/2004
 WO 2004107822 12/2004
 WO 2005014551 2/2005
 WO 2005019373 3/2005
 WO 2005030900 4/2005
 WO 2005089025 9/2005
 WO 2005123873 12/2005
 WO 2006009024 1/2006
 WO 2006056418 6/2006
 WO 2006072002 7/2006
 WO 2006082742 8/2006
 WO 2006098120 9/2006
 WO 2006100298 9/2006
 WO 2006103874 10/2006
 WO 2006114966 11/2006
 WO 2006132173 12/2006
 WO 2007002683 1/2007
 WO 2007004380 1/2007
 WO 2007063754 6/2007
 WO 2007063796 6/2007
 WO 2008056746 5/2008
 WO 2008101842 8/2008
 WO 2008132085 11/2008
 WO 2009000673 12/2008
 WO 2009003898 1/2009
 WO 2009008311 1/2009
 WO 2009018009 2/2009
 WO 2009021126 2/2009
 WO 2009050290 4/2009
 WO 2009062578 5/2009
 WO 2009063833 5/2009
 WO 2009066778 5/2009
 WO 2009066779 5/2009
 WO 2009086028 7/2009
 WO 2009100991 8/2009

OTHER PUBLICATIONS

Adachi, Chihaya et al., "Nearly 100% Internal Phosphorescence Efficiency in an Organic Light Emitting Device," J. Appl. Phys., 90(10): 5048-5051 (2001).
 Adachi, Chihaya et al., "High-Efficiency Red Electrophosphorescence Devices," Appl. Phys. Lett., 78(11):1622-1624 (2001).

(56)

References Cited

OTHER PUBLICATIONS

- Aonuma, Masaki et al., "Material Design of Hole Transport Materials Capable of Thick-Film Formation in Organic Light Emitting Diodes," *Appl. Phys. Lett.*, 90, Apr. 30, 2007, 183503-1-183503-3.
- Baldo et al., Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices, *Nature*, vol. 395, 151-154, (1998).
- Baldo et al., Very high-efficiency green organic light-emitting devices based on electrophosphorescence, *Appl. Phys. Lett.*, vol. 75, No. 1, 4-6 (1999).
- Gao, Zhiqiang et al., "Bright-Blue Electroluminescence From a Silyl-Substituted ter-(phenylene-vinylene) derivative," *Appl. Phys. Lett.*, 74(6): 865-867 (1999).
- Guo, Tzung-Fang et al., "Highly Efficient Electrophosphorescent Polymer Light-Emitting Devices," *Organic Electronics*, 1: 15-20 (2000).
- Hamada, Yuji et al., "High Luminance in Organic Electroluminescent Devices with Bis(10-hydroxybenzo[h]quinolinato) beryllium as an Emitter," *Chem. Lett.*, 905-906 (1993).
- Holmes, R.J. et al., "Blue Organic Electrophosphorescence Using Exothermic Host-Guest Energy Transfer," *Appl. Phys. Lett.*, 82(15):2422-2424 (2003).
- Hu, Nan-Xing et al., "Novel High Tg Hole-Transport Molecules Based on Indolo[3,2-b]carbazoles for Organic Light-Emitting Devices," *Synthetic Metals*, 111-112:421-424 (2000).
- Huang, Jinsong et al., "Highly Efficient Red-Emission Polymer Phosphorescent Light-Emitting Diodes Based on Two Novel Tris(1-phenylisoquinolinato-C2,N)iridium(III) Derivatives," *Adv. Mater.*, 19:739-743 (2007).
- Huang, Wei-Sheng et al., "Highly Phosphorescent Bis-Cyclometalated Iridium Complexes Containing Benzoimidazole-Based Ligands," *Chem. Mater.*, 16(12):2480-2488 (2004).
- Hung, L.S. et al., "Anode Modification in Organic Light-Emitting Diodes by Low-Frequency Plasma Polymerization of CHF₃," *Appl. Phys. Lett.*, 78(5):673-675 (2001).
- Ikai, Masamichi et al., "Highly Efficient Phosphorescence From Organic Light-Emitting Devices with an Exciton-Block Layer," *Appl. Phys. Lett.*, 79(2):156-158 (2001).
- Ikeda, Hisao et al., "P-185 Low-Drive-Voltage OLEDs with a Buffer Layer Having Molybdenum Oxide," *SID Symposium Digest*, 37:923-926 (2006).
- Inada, Hiroshi and Shirota, Yasuhiko, "1,3,5-Tris[4-(diphenylamino)phenyl]benzene and its Methylsubstituted Derivatives as a Novel Class of Amorphous Molecular Materials," *J. Mater. Chem.*, 3(3):319-320 (1993).
- Kanno, Hiroshi et al., "Highly Efficient and Stable Red Phosphorescent Organic Light-Emitting Device Using bis [2-(2-benzothiazoyl)phenolato]zinc(II) as host material," *Appl. Phys. Lett.*, 90:123509-1-123509-3 (2007).
- Kido, Junji et al., 1,2,4-Triazole Derivative as an Electron Transport Layer in Organic Electroluminescent Devices, *Jpn. J. Appl. Phys.*, 32:L917-L920 (1993).
- Kuwabara, Yoshiyuki et al., "Thermally Stable Multilayered Organic Electroluminescent Devices Using Novel Starburst Molecules, 4,4',4"-Tri(N-carbazoyl)triphenylamine (TCTA) and 4,4',4"-Tris(3-methylphenylphenyl-amino) triphenylamine (m-MTDATA), as Hole-Transport Materials," *Adv. Mater.*, 6(9):677-679 (1994).
- Kwong, Raymond C. et al., "High Operational Stability of Electrophosphorescent Devices," *Appl. Phys. Lett.*, 81(1):162-164 (2002).
- Lamansky, Sergey et al., "Synthesis and Characterization of Phosphorescent Cyclometalated Iridium Complexes," *Inorg. Chem.*, 40(7):1704-1711 (2001).
- Lee, Chang-Lyoul et al., "Polymer Phosphorescent Light-Emitting Devices Doped with Tris(2-phenylpyridine) Iridium as a Triplet Emitter," *Appl. Phys. Lett.*, 77(15):2280-2282 (2000).
- Lo, Shih-Chun et al., "Blue Phosphorescence from Iridium(III) Complexes at Room Temperature," *Chem. Mater.*, 18(21):5119-5129 (2006).
- Ma, Yuguang et al., "Triplet Luminescent Dinuclear-Gold(I) Complex-Based Light-Emitting Diodes with Low Turn-On voltage," *Appl. Phys. Lett.*, 74(10):1361-1363 (1999).
- Mi, Bao-Xiu et al., "Thermally Stable Hole-Transporting Material for Organic Light-Emitting Diode an Isoindole Derivative," *Chem. Mater.*, 15(16):3148-3151 (2003).
- Nishida, Jun-ichi et al., "Preparation, Characterization, and Electroluminescence Characteristics of α -Diimine-type Platinum(II) Complexes with Perfluorinated Phenyl Groups as Ligands," *Chem. Lett.*, 34(4): 592-593 (2005).
- Niu, Yu-Hua et al., "Highly Efficient Electrophosphorescent Devices with Saturated Red Emission from a Neutral Osmium Complex," *Chem. Mater.*, 17(13):3532-3536 (2005).
- Noda, Tetsuya and Shirota, Yasuhiko, "5,5'-Bis(dimesitylboryl)-2,2'-bithiophene and 5,5'-Bis(dimesitylboryl)-2,2',5',2"-terthiophene as a Novel Family of Electron-Transporting Amorphous Molecular Materials," *J. Am. Chem. Soc.*, 120 (37):9714-9715 (1998).
- Okumoto, Kenji et al., "Green Fluorescent Organic Light-Emitting Device with External Quantum Efficiency of Nearly 10%," *Appl. Phys. Lett.*, 89:063504-1-063504-3 (2006).
- Palilis, Leonidas C., "High Efficiency Molecular Organic Light-Emitting Diodes Based on Silole Derivatives and Their Exciplexes," *Organic Electronics*, 4:113-121 (2003).
- Paulose, Betty Marie Jennifer S. et al., "First Examples of Alkenyl Pyridines as Organic Ligands for Phosphorescent Iridium Complexes," *Adv. Mater.*, 16(22):2003-2007 (2004).
- Ranjan, Sudhir et al., "Realizing Green Phosphorescent Light-Emitting Materials from Rhenium(I) Pyrazolato Diimine Complexes," *Inorg. Chem.*, 42(4):1248-1255 (2003).
- Sakamoto, Youichi et al., "Synthesis, Characterization, and Electron-Transport Property of Perfluorinated Phenylene Dendrimers," *J. Am. Chem. Soc.*, 122(8):1832-1833 (2000).
- Salbeck, J. et al., "Low Molecular Organic Glasses for Blue Electroluminescence," *Synthetic Metals*, 91: 209-215 (1997).
- Shirota, Yasuhiko et al., "Starburst Molecules Based on π -Electron Systems as Materials for Organic Electroluminescent Devices," *Journal of Luminescence*, 72-74:985-991 (1997).
- Sotoyama, Wataru et al., "Efficient Organic Light-Emitting Diodes with Phosphorescent Platinum Complexes Containing N/C/N-Coordinating Tridentate Ligand," *Appl. Phys. Lett.*, 86:153505-1-153505-3 (2005).
- Sun, Yiru and Forrest, Stephen R., "High-Efficiency White Organic Light Emitting Devices with Three Separate Phosphorescent Emission Layers," *Appl. Phys. Lett.*, 91:263503-1-263503-3 (2007).
- T. Östergård et al., "Langmuir-Blodgett Light-Emitting Diodes of Poly(3-Hexylthiophene) Electro-Optical Characteristics Related to Structure," *Synthetic Metals*, 88:171-177 (1997).
- Takizawa, Shin-ya et al., "Phosphorescent Iridium Complexes Based on 2-Phenylimidazo[1,2- α]pyridine Ligands Tuning of Emission Color toward the Blue Region and Application to Polymer Light-Emitting Devices," *Inorg. Chem.*, 46(10):4308-4319 (2007).
- Tang, C.W. and VanSlyke, S.A., "Organic Electroluminescent Diodes," *Appl. Phys. Lett.*, 51(12):913-915 (1987).
- Tung, Yung-Liang et al., "Organic Light-Emitting Diodes Based on Charge-Neutral Ru II Phosphorescent Emitters," *Adv. Mater.*, 17(8):1059-1064 (2005).
- Van Slyke, S. A. et al., "Organic Electroluminescent Devices with Improved Stability," *Appl. Phys. Lett.*, 69(15):2160-2162 (1996).
- Wang, Y. et al., "Highly Efficient Electroluminescent Materials Based on Fluorinated Organometallic Iridium Compounds," *Appl. Phys. Lett.*, 79(4):449-451 (2001).
- Wong, Keith Man-Chung et al., A Novel Class of Phosphorescent Gold(III) Alkynyl-Based Organic Light-Emitting Devices with Tunable Colour, *Chem. Commun.*, 2906-2908 (2005).
- Wong, Wai-Yeung, "Multifunctional Iridium Complexes Based on Carbazole Modules as Highly Efficient Electrophosphors," *Angew. Chem. Int. Ed.*, 45:7800-7803 (2006).

* cited by examiner




FIG. 1




FIG. 2




FIG. 3

1

ORGANIC ELECTROLUMINESCENT
MATERIALS AND DEVICESCROSS-REFERENCE TO RELATED
APPLICATIONS

This application claims priority under 35 U.S.C. § 119(e) to U.S. Provisional Application No. 63/045,954, filed on Jun. 30, 2020, the entire contents of which are incorporated herein by reference.

FIELD

The present disclosure generally relates to organometallic compounds and formulations and their various uses including as emitters in devices such as organic light emitting diodes and related electronic devices.

BACKGROUND


Opto-electronic devices that make use of organic materials are becoming increasingly desirable for various reasons. Many of the materials used to make such devices are relatively inexpensive, so organic opto-electronic devices have the potential for cost advantages over inorganic devices. In addition, the inherent properties of organic materials, such as their flexibility, may make them well suited for particular applications such as fabrication on a flexible substrate. Examples of organic opto-electronic devices include organic light emitting diodes/devices (OLEDs), organic phototransistors, organic photovoltaic cells, and organic photodetectors. For OLEDs, the organic materials may have performance advantages over conventional materials.

OLEDs make use of thin organic films that emit light when voltage is applied across the device. OLEDs are becoming an increasingly interesting technology for use in applications such as flat panel displays, illumination, and backlighting.

One application for phosphorescent emissive molecules is a full color display. Industry standards for such a display call for pixels adapted to emit particular colors, referred to as "saturated" colors. In particular, these standards call for saturated red, green, and blue pixels. Alternatively, the OLED can be designed to emit white light. In conventional liquid crystal displays emission from a white backlight is filtered using absorption filters to produce red, green and blue emission. The same technique can also be used with OLEDs. The white OLED can be either a single emissive layer (EML) device or a stack structure. Color may be measured using CIE coordinates, which are well known to the art.

SUMMARY

In one aspect, the present disclosure provides a compound comprising a ligand L_A of Formula I




2

wherein

A^1 and A^2 are each independently a 5-membered or 6-membered carbocyclic or heterocyclic ring;

D^1 , D^2 , and D^3 are each independently selected from the group consisting of O, S, Se, Br, NR, PR, P(O)R, CRR', SiRR', and GeRR';

one of R^A or R^B has the structure of Formula II



wherein Z^1 is connected to C or N on ring A^1 or A^2 or connected to either D^1 , D^2 or D^3 ;

the dashed line in Formula II is coordinated to a metal M; A^3 is a 5-membered or 6-membered carbocyclic or heterocyclic rings;

Z^1 and Z^2 are each independently C or N;

R^A , R^B and R^C represent mono to the maximum allowable substitutions, or no substitution;

each R^A , R^B , R, and R' is independently a hydrogen or a substituent selected from the group R^C , consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, boryl, arylalkyl, alkoxy, aryloxy, amino, silyl, germyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, selenyl, and combinations thereof;

L_A is coordinated to a metal M through the dashed line with Z^2 in Formula II and with one atom from ring A^1 or A^2 that is connected to Formula II to form a 5-membered chelate ring or 6-membered chelate ring;

M is selected from the group consisting of Os, Ir, Rh, Re, Ru, Pd, Pt, Cu, Ag, and Au;

M can be coordinated to other ligands;

L_A can be joined with other ligands to form a tridentate, tetradentate, pentadentate, or hexadentate ligand; and

any two adjacent R^A , R^B , R^C , R, and R' can be joined or fused to form a ring.

In another aspect, the present disclosure provides a formulation of the compound comprising a ligand L_A of Formula I as described herein.

In yet another aspect, the present disclosure provides an OLED having an organic layer comprising the compound of comprising a ligand L_A of Formula I as described herein.

In yet another aspect, the present disclosure provides a consumer product comprising an OLED with an organic layer comprising the compound comprising a ligand L_A of Formula I as described herein.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 shows an organic light emitting device.

FIG. 2 shows an inverted organic light emitting device that does not have a separate electron transport layer.

FIG. 3 shows the photophysical characterization of the comparison compound.

DETAILED DESCRIPTION

A. Terminology

Unless otherwise specified, the below terms used herein are defined as follows:

As used herein, the term “organic” includes polymeric materials as well as small molecule organic materials that may be used to fabricate organic opto-electronic devices. “Small molecule” refers to any organic material that is not a polymer, and “small molecules” may actually be quite large. Small molecules may include repeat units in some circumstances. For example, using a long chain alkyl group as a substituent does not remove a molecule from the “small molecule” class. Small molecules may also be incorporated into polymers, for example as a pendent group on a polymer backbone or as a part of the backbone. Small molecules may also serve as the core moiety of a dendrimer, which consists of a series of chemical shells built on the core moiety. The core moiety of a dendrimer may be a fluorescent or phosphorescent small molecule emitter. A dendrimer may be a “small molecule,” and it is believed that all dendrimers currently used in the field of OLEDs are small molecules.

As used herein, “top” means furthest away from the substrate, while “bottom” means closest to the substrate. Where a first layer is described as “disposed over” a second layer, the first layer is disposed further away from substrate. There may be other layers between the first and second layer, unless it is specified that the first layer is “in contact with” the second layer. For example, a cathode may be described as “disposed over” an anode, even though there are various organic layers in between.

As used herein, “solution processable” means capable of being dissolved, dispersed, or transported in and/or deposited from a liquid medium, either in solution or suspension form.

A ligand may be referred to as “photoactive” when it is believed that the ligand directly contributes to the photoactive properties of an emissive material. A ligand may be referred to as “ancillary” when it is believed that the ligand does not contribute to the photoactive properties of an emissive material, although an ancillary ligand may alter the properties of a photoactive ligand.

As used herein, and as would be generally understood by one skilled in the art, a first “Highest Occupied Molecular Orbital” (HOMO) or “Lowest Unoccupied Molecular Orbital” (LUMO) energy level is “greater than” or “higher than” a second HOMO or LUMO energy level if the first energy level is closer to the vacuum energy level. Since ionization potentials (IP) are measured as a negative energy relative to a vacuum level, a higher HOMO energy level corresponds to an IP having a smaller absolute value (an IP that is less negative). Similarly, a higher LUMO energy level corresponds to an electron affinity (EA) having a smaller absolute value (an EA that is less negative). On a conventional energy level diagram, with the vacuum level at the top, the LUMO energy level of a material is higher than the HOMO energy level of the same material. A “higher” HOMO or LUMO energy level appears closer to the top of such a diagram than a “lower” HOMO or LUMO energy level.

As used herein, and as would be generally understood by one skilled in the art, a first work function is “greater than” or “higher than” a second work function if the first work function has a higher absolute value. Because work functions are generally measured as negative numbers relative to vacuum level, this means that a “higher” work function is

more negative. On a conventional energy level diagram, with the vacuum level at the top, a “higher” work function is illustrated as further away from the vacuum level in the downward direction. Thus, the definitions of HOMO and LUMO energy levels follow a different convention than work functions.

The terms “halo,” “halogen,” and “halide” are used interchangeably and refer to fluorine, chlorine, bromine, and iodine.

The term “acyl” refers to a substituted carbonyl radical ($\text{C}(\text{O})-\text{R}_s$).

The term “ester” refers to a substituted oxycarbonyl ($-\text{O}-\text{C}(\text{O})-\text{R}_s$ or $-\text{C}(\text{O})-\text{O}-\text{R}_s$) radical.

The term “ether” refers to an $-\text{OR}_s$ radical.

The terms “sulfanyl” or “thio-ether” are used interchangeably and refer to a $-\text{SR}_s$ radical.

The terms “selenyl” are used interchangeably and refer to a $-\text{SeR}_s$ radical.

The term “sulfinyl” refers to a $-\text{S}(\text{O})-\text{R}_s$ radical.

The term “sulfonyl” refers to a $-\text{SO}_2-\text{R}_s$ radical.

The term “phosphino” refers to a $-\text{P}(\text{R}_s)_3$ radical, wherein each R_s can be same or different.

The term “silyl” refers to a $-\text{Si}(\text{R}_s)_3$ radical, wherein each R_s can be same or different.

The term “germyl” refers to a $-\text{Ge}(\text{R}_s)_3$ radical, wherein each R_s can be same or different.

The term “boryl” refers to a $-\text{B}(\text{R}_s)_2$ radical or its Lewis adduct $-\text{B}(\text{R}_s)_3$ radical, wherein R_s can be same or different.

In each of the above, R_s can be hydrogen or a substituent selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, and combination thereof. Preferred R_s is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, and combination thereof.

The term “alkyl” refers to and includes both straight and branched chain alkyl radicals. Preferred alkyl groups are those containing from one to fifteen carbon atoms and includes methyl, ethyl, propyl, 1-methylethyl, butyl, 1-methylpropyl, 2-methylpropyl, pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, 1,1-dimethylpropyl, 1,2-dimethylpropyl, 2,2-dimethylpropyl, and the like. Additionally, the alkyl group can be substituted.

The term “cycloalkyl” refers to and includes monocyclic, polycyclic, and spiro alkyl radicals. Preferred cycloalkyl groups are those containing 3 to 12 ring carbon atoms and includes cyclopropyl, cyclopentyl, cyclohexyl, bicyclo [3.1.1]heptyl, spiro[4.5]decyl, spiro[5.5]undecyl, adamantyl, and the like. Additionally, the cycloalkyl group can be substituted.

The terms “heteroalkyl” or “heterocycloalkyl” refer to an alkyl or a cycloalkyl radical, respectively, having at least one carbon atom replaced by a heteroatom. Optionally the at least one heteroatom is selected from O, S, N, P, B, Si and Se, preferably, O, S or N. Additionally, the heteroalkyl or heterocycloalkyl group can be substituted.

The term “alkenyl” refers to and includes both straight and branched chain alkene radicals. Alkenyl groups are essentially alkyl groups that include at least one carbon-carbon double bond in the alkyl chain. Cycloalkenyl groups are essentially cycloalkyl groups that include at least one carbon-carbon double bond in the cycloalkyl ring. The term “heteroalkenyl” as used herein refers to an alkenyl radical having at least one carbon atom replaced by a heteroatom. Optionally the at least one heteroatom is selected from O, S, N, P, B, Si, and Se, preferably, O, S, or N. Preferred alkenyl,

5

cycloalkenyl, or heteroalkenyl groups are those containing two to fifteen carbon atoms. Additionally, the alkenyl, cycloalkenyl, or heteroalkenyl group can be substituted.

The term "alkynyl" refers to and includes both straight and branched chain alkyne radicals. Alkynyl groups are essentially alkyl groups that include at least one carbon-carbon triple bond in the alkyl chain. Preferred alkynyl groups are those containing two to fifteen carbon atoms. Additionally, the alkynyl group can be substituted.

The terms "aralkyl" or "arylalkyl" are used interchangeably and refer to an alkyl group that is substituted with an aryl group. Additionally, the aralkyl group can be substituted.

The term "heterocyclic group" refers to and includes aromatic and non-aromatic cyclic radicals containing at least one heteroatom. Optionally the at least one heteroatom is selected from O, S, N, P, B, Si, and Se, preferably, O, S, or N. Hetero-aromatic cyclic radicals may be used interchangeably with heteroaryl. Preferred hetero-non-aromatic cyclic groups are those containing 3 to 7 ring atoms which includes at least one hetero atom, and includes cyclic amines such as morpholino, piperidino, pyrrolidino, and the like, and cyclic ethers/thio-ethers, such as tetrahydrofuran, tetrahydropyran, tetrahydrothiophene, and the like. Additionally, the heterocyclic group can be substituted.

The term "aryl" refers to and includes both single-ring aromatic hydrocarbyl groups and polycyclic aromatic ring systems. The polycyclic rings may have two or more rings in which two carbons are common to two adjoining rings (the rings are "fused") wherein at least one of the rings is an aromatic hydrocarbyl group, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. Preferred aryl groups are those containing six to thirty carbon atoms, preferably six to twenty carbon atoms, more preferably six to twelve carbon atoms. Especially preferred is an aryl group having six carbons, ten carbons or twelve carbons. Suitable aryl groups include phenyl, biphenyl, triphenyl, triphenylene, tetraphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene, preferably phenyl, biphenyl, triphenyl, triphenylene, fluorene, and naphthalene. Additionally, the aryl group can be substituted.

The term "heteroaryl" refers to and includes both single-ring aromatic groups and polycyclic aromatic ring systems that include at least one heteroatom. The heteroatoms include, but are not limited to O, S, N, P, B, Si, and Se. In many instances, O, S, or N are the preferred heteroatoms. Hetero-single ring aromatic systems are preferably single rings with 5 or 6 ring atoms, and the ring can have from one to six heteroatoms. The hetero-polycyclic ring systems can have two or more rings in which two atoms are common to two adjoining rings (the rings are "fused") wherein at least one of the rings is a heteroaryl, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. The hetero-polycyclic aromatic ring systems can have from one to six heteroatoms per ring of the polycyclic aromatic ring system. Preferred heteroaryl groups are those containing three to thirty carbon atoms, preferably three to twenty carbon atoms, more preferably three to twelve carbon atoms. Suitable heteroaryl groups include dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyrindine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, ben-

6

zioxazole, benzothiazole, quinoline, isoquinoline, cinno-
line, quinazoline, quinoxaline, naphthyridine, phthalazine,
pteridine, xanthene, acridine, phenazine, phenothiazine,
phenoxazine, benzofuopyridine, furodipyrindine, benzoth-
ienopyridine, thienodipyrindine, benzoselenophenopyridine,
and selenophenodipyrindine, preferably dibenzothiophene,
dibenzofuran, dibenzoselenophene, carbazole, indolocarba-
zole, imidazole, pyridine, triazine, benzimidazole, 1,2-aza-
borine, 1,3-azaborine, 1,4-azaborine, borazine, and aza-
analogs thereof. Additionally, the heteroaryl group can be
substituted.

Of the aryl and heteroaryl groups listed above, the groups of triphenylene, naphthalene, anthracene, dibenzothiophene, dibenzofuran, dibenzoselenophene, carbazole, indolocarbazole, imidazole, pyridine, pyrazine, pyrimidine, triazine, and benzimidazole, and the respective aza-analogs of each thereof are of particular interest.

The terms alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, heterocyclic group, aryl, and heteroaryl, as used herein, are independently unsubstituted, or independently substituted, with one or more general substituents.

In many instances, the general substituents are selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, germyl, boryl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, selenyl, and combinations thereof.

In some instances, the preferred general substituents are selected from the group consisting of deuterium, fluorine, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, boryl, alkenyl, cycloalkenyl, heteroalkenyl, aryl, heteroaryl, nitrile, isonitrile, sulfanyl, boryl, and combinations thereof.

In some instances, the more preferred general substituents are selected from the group consisting of deuterium, fluorine, alkyl, cycloalkyl, alkoxy, aryloxy, amino, silyl, aryl, heteroaryl, sulfanyl, and combinations thereof.

In yet other instances, the most preferred general substituents are selected from the group consisting of deuterium, fluorine, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof.

The terms "substituted" and "substitution" refer to a substituent other than H that is bonded to the relevant position, e.g., a carbon or nitrogen. For example, when R¹ represents mono-substitution, then one R¹ must be other than H (i.e., a substitution). Similarly, when R¹ represents di-substitution, then two of R¹ must be other than H. Similarly, when R¹ represents zero or no substitution, R¹, for example, can be a hydrogen for available valencies of ring atoms, as in carbon atoms for benzene and the nitrogen atom in pyrrole, or simply represents nothing for ring atoms with fully filled valencies, e.g., the nitrogen atom in pyridine. The maximum number of substitutions possible in a ring structure will depend on the total number of available valencies in the ring atoms.

As used herein, "combinations thereof" indicates that one or more members of the applicable list are combined to form a known or chemically stable arrangement that one of ordinary skill in the art can envision from the applicable list. For example, an alkyl and deuterium can be combined to form a partial or fully deuterated alkyl group; a halogen and alkyl can be combined to form a halogenated alkyl substituent; and a halogen, alkyl, and aryl can be combined to form a halogenated arylalkyl. In one instance, the term substitution includes a combination of two to four of the listed groups. In another instance, the term substitution includes a

7

combination of two to three groups. In yet another instance, the term substitution includes a combination of two groups. Preferred combinations of substituent groups are those that contain up to fifty atoms that are not hydrogen or deuterium, or those which include up to forty atoms that are not hydrogen or deuterium, or those that include up to thirty atoms that are not hydrogen or deuterium. In many instances, a preferred combination of substituent groups will include up to twenty atoms that are not hydrogen or deuterium.

The “aza” designation in the fragments described herein, i.e. aza-dibenzofuran, aza-dibenzothiophene, etc. means that one or more of the C—H groups in the respective aromatic ring can be replaced by a nitrogen atom, for example, and without any limitation, azatriphenylene encompasses both dibenzof[f,h]quinoxaline and dibenzof[f,h]quinoline. One of ordinary skill in the art can readily envision other nitrogen analogs of the aza-derivatives described above, and all such analogs are intended to be encompassed by the terms as set forth herein.


As used herein, “deuterium” refers to an isotope of hydrogen. Deuterated compounds can be readily prepared using methods known in the art. For example, U.S. Pat. No. 8,557,400, Patent Pub. No. WO 2006/095951, and U.S. Pat. Application Pub. No. US 2011/0037057, which are hereby incorporated by reference in their entireties, describe the making of deuterium-substituted organometallic complexes. Further reference is made to Ming Yan, et al., *Tetrahedron* 2015, 71, 1425-30 and Atzrodt et al., *Angew. Chem. Int. Ed. (Reviews)* 2007, 46, 7744-65, which are incorporated by reference in their entireties, describe the deuteration of the methylene hydrogens in benzyl amines and efficient pathways to replace aromatic ring hydrogens with deuterium, respectively.

It is to be understood that when a molecular fragment is described as being a substituent or otherwise attached to another moiety, its name may be written as if it were a fragment (e.g. phenyl, phenylene, naphthyl, dibenzofuryl) or as if it were the whole molecule (e.g. benzene, naphthalene, dibenzofuran). As used herein, these different ways of designating a substituent or attached fragment are considered to be equivalent.

In some instance, a pair of adjacent substituents can be joined or fused into a ring. The preferred ring is a five, six, or seven-membered carbocyclic or heterocyclic ring, includes both instances where the portion of the ring formed by the pair of substituents is saturated and where the portion of the ring formed by the pair of substituents is unsaturated. As used herein, “adjacent” means that the two substituents involved can be on the same ring next to each other, or on two neighboring rings having the two closest available substitutable positions, such as 2,2' positions in a biphenyl, or 1,8 position in a naphthalene, as long as they can form a stable fused ring system.

B. The Compounds of the Present Disclosure

In one aspect, the present disclosure provides a compound comprising a ligand L_A of Formula I




8

wherein

A^1 and A^2 are each independently a 5-membered or 6-membered carbocyclic or heterocyclic ring;

D^1 , D^2 , and D^3 are each independently selected from the group consisting of O, S, Se, Br, NR, PR, P(O)R, CRR', SiRR', and GeRR';

one of R^A or R^B has the structure of Formula II



wherein Z^1 is connected to C or N on ring A^1 or A^2 or connected to either D^1 , D^2 or D^3 ;

the dashed line in Formula II is coordinated to a metal M; A^3 is a 5-membered or 6-membered carbocyclic or heterocyclic rings;

Z^1 and Z^2 are each independently C or N;

R^A , R^B and R^C represent mono to the maximum allowable substitutions, or no substitution;

each R^A , R^B , R, and R' is independently a hydrogen or a substituent selected from the group consisting of the general substituents disclosed above;

L_A is coordinated to a metal M through the dashed line with Z^2 in Formula II and with one atom from ring A^1 or A^2 that is connected to Formula II to form a 5-membered chelate ring or 6-membered chelate ring;

M is selected from the group consisting of Os, Ir, Rh, Re, Ru, Pd, Pt, Cu, Ag, and Au;

M can be coordinated to other ligands;

L_A can be joined with other ligands to form a tridentate, tetradentate, pentadentate, or hexadentate ligand; and any two adjacent R^A , R^B , R^C , R, and R' can be joined or fused to form a ring.

In some embodiments, each R^A , R^B , R, and R' is independently a hydrogen or a substituent selected from the group consisting of the preferred general substituents disclosed above.

In some embodiments, R and R' are selected from the group consisting of hydrogen, deuterium, aryl, heteroaryl, alkyl, heteroalkyl, cycloalkyl, heterocycloalkyl, and combinations thereof.

In some embodiments, D^1 , D^2 , and D^3 are each independently selected from the group consisting of O, S, BR, NR, CRR' and SiRR'.

In some embodiments, Z^1 is C and Z^2 is N.

In some embodiments, Z^1 is N and Z^2 is C.

In some embodiments, A^1 is a heterocyclic ring comprising C and N.

In some embodiments, A^1 is a carbocyclic ring.

In some embodiments, A^1 is a 5-membered aromatic ring.

In some embodiments, A^1 is selected from the group consisting of imidazole, pyrazole, triazole, and N-heterocyclic carbene.

In some embodiments, A^1 is a 6-membered aromatic ring.

In some embodiments, A^1 is selected from the group consisting of benzene, pyridine, pyrimidine, pyridazine, and triazine.

In some embodiments, A^2 is a heterocyclic ring comprising C and N.

In some embodiments, A^2 is a carbocyclic ring.

In some embodiments, A^2 is a 5-membered aromatic ring.

9

In some embodiments, A^2 is selected from the group consisting of imidazole, pyrazole, triazole, and N-heterocyclic carbene.

In some embodiments, A^2 is a 6-membered aromatic ring.

In some embodiments, A^2 is selected from the group consisting of benzene, pyridine, pyrimidine, pyridazine, and triazine. 5

In some embodiments, A^3 is a heterocyclic ring comprising C and N.

In some embodiments, A^3 is a carbocyclic ring. 10

In some embodiments, A^3 is a 5-membered aromatic ring.

In some embodiments, A^3 is selected from the group consisting of imidazole, pyrazole, triazole, and N-heterocyclic carbene.

In some embodiments, A^3 is a 6-membered aromatic ring. 15

In some embodiments, A^3 is selected from the group consisting of benzene, pyridine, pyrimidine, pyridazine, and triazine.

In some embodiments, A^1 or A^2 comprises at least one nitrogen atom which is coordinated to M. 20

In some embodiments, Z^1 is connected to C on ring A^1 or A^2 .

In some embodiments, Z^1 is connected to D^1 , D^2 or D^3 .


In some embodiments, the maximum number of N atoms that can connect to each other is two. In some embodiments, X^1 - X^8 is C if it is connected to Z^1 . 25

In some embodiments, M is Ir or Pt.

In some embodiments, M is further coordinated to at least one phenylpyridine ligand.


In some embodiments, M is further coordinated to two phenylpyridine ligands. 30

In some embodiments, the ligand L_A is selected from the group consisting of the List A below:










10

-continued










11

-continued


**12**

-continued




13

-continued

**14**


-continued



wherein X^1 to X^{11} are each independently C or N; R^1 to R^3 is independently a hydrogen or a substituent selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, boryl, aryl-alkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof;


Z^1 and Z^2 are C and N; D^1 , D^2 and D^3 are defined above.

In some embodiments, the ligand L_A is selected from the group consisting of the List B below:




15

-continued






**16**

-continued



17

-continued




wherein X^1 to X^4 , Z^1 and Z^2 , R^1 to R^3 , and D^1 to D^3 are as defined above.

In some embodiments, the ligand L_A is selected from the group of structures defined by L_{At-p-r} or L_{As-u-r} , wherein t is an integer from 1 to 16, p is an integer from 1 to 196, r is an integer from 1 to 110, s is an integer from 1 to 12, u is an integer from 1 to 141, wherein for the group represented by L_{At-p-r} each L_{At} represents structures defined in Table 1 below:


18

L_{A1} and L_{A2} have the structure




wherein, for L_{A1} , $Z^1 = C$, $Z^2 = N$, and for L_{A2} , $Z^1 = N$, and $Z^2 = C$;

L_{A3} and L_{A4} have the structure



wherein, for L_{A3} , $Z^1 = C$, $Z^2 = N$, and for L_{A4} , $Z^1 = N$, and $Z^2 = C$;

L_{A5} and L_{A6} have the structure




L_{A5} : $Z^1 = C$, $Z^2 = N$;

L_{A6} : $Z^1 = N$, $Z^2 = C$;

wherein, for L_{A5} , $Z^1 = C$, $Z^2 = N$, and for L_{A6} , $Z^1 = N$, and $Z^2 = C$;


L_{A7} and L_{A8} have the structure




wherein for L_{A7} , $Z^1 = C$, $Z^2 = N$, and for L_{A8} , $Z^1 = N$, and $Z^2 = C$;

19


-continued

 L_{A9} and L_{A10} have the structure


wherein, for L_{A9} , $Z^1 = C$, $Z^2 = N$, and
for L_{A10} , $Z^1 = N$, and $Z^2 = C$;

 L_{A11} and L_{A12} have the structure

wherein, for L_{A11} , $Z^1 = C$, $Z^2 = N$, and
for L_{A12} , $Z^1 = N$, and $Z^2 = C$;

 L_{A13} and L_{A14} have the structure

wherein, for L_{A13} , $Z^1 = C$, $Z^2 = N$, and
for L_{A14} , $Z^1 = N$, and $Z^2 = C$;

 L_{A15} and L_{A16} have the structure

wherein, for L_{A15} , $Z^1 = C$, $Z^2 = N$, and
for L_{A16} , $Z^1 = N$, and $Z^2 = C$;

wherein for each p, D^1 , D^2 and D^3 are defined as shown
in Table 2 below:

p	D^1	D^2	D^3
1.	O	O	O
2.	O	O	O
3.	O	O	O
4.	O	O	O
5.	O	O	O
6.	O	O	O
7.	O	O	O
8.	O	O	O
9.	O	O	O

20

-continued

	p	D^1	D^2	D^3
5	10.	O	O	O
	11.	O	O	O
	12.	O	O	O
	13.	O	O	O
	14.	O	O	O
10	15.	O	O	B-A ¹
	16.	O	O	B-A ²
	17.	O	O	B-A ³
	18.	O	O	B-A ⁴
	19.	O	O	B-A ⁵
15	20.	O	O	B-A ⁶
	21.	O	O	B-A ⁷
	22.	O	O	B-A ⁸
	23.	O	O	B-A ⁹
	24.	O	O	B-A ¹⁰
20	25.	O	O	B-A ¹¹
	26.	O	O	B-A ¹²
	27.	O	O	B-A ¹³
	28.	O	O	B-A ¹⁴
	29.	O	S	B-A ¹
25	30.	O	S	B-A ²
	31.	O	S	B-A ³
	32.	O	S	B-A ⁴
	33.	O	S	B-A ⁵
	34.	O	S	B-A ⁶
30	35.	O	S	B-A ⁷
	36.	O	S	B-A ⁸
	37.	O	S	B-A ⁹
	38.	O	S	B-A ¹⁰
	39.	O	S	B-A ¹¹
35	40.	O	S	B-A ¹²
	41.	O	S	B-A ¹³
	42.	O	S	B-A ¹⁴
	43.	O	SiMe ₂	B-A ¹
	44.	O	SiMe ₂	B-A ²
40	45.	O	SiMe ₂	B-A ³
	46.	O	SiMe ₂	B-A ⁴
	47.	O	SiMe ₂	B-A ⁵
	48.	O	SiMe ₂	B-A ⁶
	49.	O	SiMe ₂	B-A ⁷
45	50.	O	SiMe ₂	B-A ⁸
	51.	O	SiMe ₂	B-A ⁹
	52.	O	SiMe ₂	B-A ¹⁰
	53.	O	SiMe ₂	B-A ¹¹
	54.	O	SiMe ₂	B-A ¹²
50	55.	O	SiMe ₂	B-A ¹³
	56.	O	SiMe ₂	B-A ¹⁴
	57.	O	B-A ¹	O
	58.	O	B-A ²	O
	59.	O	B-A ³	O
55	60.	O	B-A ⁴	O
	61.	O	B-A ⁵	O
	62.	O	B-A ⁶	O
	63.	O	B-A ⁷	O
	64.	O	B-A ⁸	O
60	65.	O	B-A ⁹	O
	66.	O	B-A ¹⁰	O
	67.	O	B-A ¹¹	O
	68.	O	B-A ¹²	O
	69.	O	B-A ¹³	O
65	70.	O	B-A ¹⁴	O
	71.	O	N-A ¹	O
	72.	O	N-A ²	O
	73.	O	N-A ³	O
	74.	O	N-A ⁴	O
70	75.	O	N-A ⁵	O
	76.	O	N-A ⁶	O
	77.	O	N-A ⁷	O
	78.	O	N-A ⁸	O
	79.	O	N-A ⁹	O
75	80.	O	N-A ¹⁰	O
	81.	O	N-A ¹¹	O
	82.	O	N-A ¹²	O
	83.	O	N-A ¹³	O
	84.	O	N-A ¹⁴	O
80	85.	O	O	N-A ¹
	86.	O	O	N-A ²

21


-continued

p	D ¹	D ²	D ³
87.	O	O	N-A ³
88.	O	O	N-A ⁴
89.	O	O	N-A ⁵
90.	O	O	N-A ⁶
91.	O	O	N-A ⁷
92.	O	O	N-A ⁸
93.	O	O	N-A ⁹
94.	O	O	N-A ¹⁰
95.	O	O	N-A ¹¹
96.	O	O	N-A ¹²
97.	O	O	N-A ¹³
98.	O	O	N-A ¹⁴
99.	O	N-A ¹	B-A ¹
100.	O	N-A ²	B-A ¹
101.	O	N-A ³	B-A ¹
102.	O	N-A ⁴	B-A ¹
103.	O	N-A ⁵	B-A ¹
104.	O	N-A ⁶	B-A ¹
105.	O	N-A ⁷	B-A ¹
106.	O	N-A ⁸	B-A ¹
107.	O	N-A ⁹	B-A ¹
108.	O	N-A ¹⁰	B-A ¹
109.	O	N-A ¹¹	B-A ¹
110.	O	N-A ¹²	B-A ¹
111.	O	N-A ¹³	B-A ¹
112.	O	N-A ¹⁴	B-A ¹
113.	S	O	B-A ¹
114.	S	O	B-A ²
115.	S	O	B-A ³
116.	S	O	B-A ⁴
117.	S	O	B-A ⁵
118.	S	O	B-A ⁶
119.	S	O	B-A ⁷
120.	S	O	B-A ⁸
121.	S	O	B-A ⁹
122.	S	O	B-A ¹⁰
123.	S	O	B-A ¹¹
124.	S	O	B-A ¹²
125.	S	O	B-A ¹³
126.	S	O	B-A ¹⁴
127.	S	B-A ¹	O
128.	S	B-A ²	O
129.	S	B-A ³	O
130.	S	B-A ⁴	O
131.	S	B-A ⁵	O
132.	S	B-A ⁶	O
133.	S	B-A ⁷	O
134.	S	B-A ⁸	O
135.	S	B-A ⁹	O
136.	S	B-A ¹⁰	O
137.	S	B-A ¹¹	O
138.	S	B-A ¹²	O
139.	S	B-A ¹³	O
140.	S	B-A ¹⁴	O
141.	CMe ₂	S	B-A ¹
142.	CMe ₂	S	B-A ²
143.	CMe ₂	S	B-A ³
144.	CMe ₂	S	B-A ⁴
145.	CMe ₂	S	B-A ⁵
146.	CMe ₂	S	B-A ⁶
147.	CMe ₂	S	B-A ⁷
148.	CMe ₂	S	B-A ⁸
149.	CMe ₂	S	B-A ⁹
150.	CMe ₂	S	B-A ¹⁰
151.	CMe ₂	S	B-A ¹¹
152.	CMe ₂	S	B-A ¹²
153.	CMe ₂	S	B-A ¹³
154.	CMe ₂	S	B-A ¹⁴
155.	S	O	B-A ¹
156.	S	O	B-A ²
157.	S	O	B-A ³
158.	S	O	B-A ⁴
159.	S	O	B-A ⁵
160.	S	O	B-A ⁶
161.	S	O	B-A ⁷
162.	S	O	B-A ⁸
163.	S	O	B-A ⁹

22









-continued

p	D ¹	D ²	D ³
164.	S	O	B-A ¹⁰
165.	S	O	B-A ¹¹
166.	S	O	B-A ¹²
167.	S	O	B-A ¹³
168.	S	O	B-A ¹⁴
169.	N-A ¹	O	B-A ¹
170.	N-A ²	O	B-A ¹
171.	N-A ³	O	B-A ¹
172.	N-A ⁴	O	B-A ¹
173.	N-A ⁵	O	B-A ¹
174.	N-A ⁶	O	B-A ¹
175.	N-A ⁷	O	B-A ¹
176.	N-A ⁸	O	B-A ¹
177.	N-A ⁹	O	B-A ¹
178.	N-A ¹⁰	O	B-A ¹
179.	N-A ¹¹	O	B-A ¹
180.	N-A ¹²	O	B-A ¹
181.	N-A ¹³	O	B-A ¹
182.	N-A ¹⁴	O	B-A ¹
183.	SiMe ₂	CMe ₂	CMe ₂
184.	SiMe ₂	CMe ₂	CMe ₂
185.	SiMe ₂	CMe ₂	CMe ₂
186.	SiMe ₂	CMe ₂	CMe ₂
187.	SiMe ₂	CMe ₂	CMe ₂
188.	SiMe ₂	CMe ₂	CMe ₂
189.	SiMe ₂	CMe ₂	CMe ₂
190.	SiMe ₂	CMe ₂	CMe ₂
191.	SiMe ₂	CMe ₂	CMe ₂
192.	SiMe ₂	CMe ₂	CMe ₂
193.	SiMe ₂	CMe ₂	CMe ₂
194.	SiMe ₂	CMe ₂	CMe ₂
195.	SiMe ₂	CMe ₂	CMe ₂
196.	SiMe ₂	CMe ₂	CMe ₂

wherein A¹ to A¹⁴ have the following structures

23


-continued

**24**

-continued

A⁵

5




10

A⁶

15

A⁷

20



25

A⁸


and wherein for the group represented by L_A^{s-u-r} , each L_A^s defines structures provided below:

30

L_A^1 , L_A^2 , L_A^3 , and L_A^4 have the structure

A⁹

35



40

A¹⁰

45


wherein,
 for L_A^1 , $D^1 = N$, $Z^1 = C$, $Z^2 = N$;
 for L_A^2 , $D^1 = N$, $Z^1 = N$, $Z^2 = C$;
 for L_A^3 , $D^1 = B$, $Z^1 = C$, $Z^2 = N$;
 and
 for L_A^4 , $D^1 = B$, $Z^1 = N$, $Z^2 = C$;

50

A¹¹

L_A^5 , L_A^6 , L_A^7 , and L_A^8 have the structure

55

A¹²

60


for L_A^5 , $D^1 = N$, $Z^1 = C$, $Z^2 = N$;
 for L_A^6 , $D^1 = N$, $Z^1 = N$, $Z^2 = C$;
 for L_A^7 , $D^1 = B$, $Z^1 = C$, $Z^2 = N$;
 and
 for L_A^8 , $D^1 = B$, $Z^1 = N$, $Z^2 = C$;

65

25

-continued

L_A^9 , L_A^{10} , L_A^{11} , and L_A^{12} have the structure



for L_A^9 , $D^1 = N$, $Z^1 = C$, $Z^2 = N$;

for L_A^{10} , $D^1 = N$, $Z^1 = N$, $Z^2 = C$;

for L_A^{11} , $D^1 = B$, $Z^1 = C$, $Z^2 = N$;

and

for L_A^{12} , $D^1 = B$, $Z^1 = N$, $Z^2 = C$;

wherein for each u, D^1 and D^2 are defined as shown in Table 3 below:

u	D^2	D^3
1.	O	B-A ¹
2.	O	B-A ²
3.	O	B-A ³
4.	O	B-A ⁴
5.	O	B-A ⁵
6.	O	B-A ⁶
7.	O	B-A ⁷
8.	O	B-A ⁸
9.	O	B-A ⁹
10.	O	B-A ¹⁰
11.	O	B-A ¹¹
12.	O	B-A ¹²
13.	O	B-A ¹³
14.	O	B-A ¹⁴
15.	B-A ¹	O
16.	B-A ²	O
17.	B-A ³	O
18.	B-A ⁴	O
19.	B-A ⁵	O
20.	B-A ⁶	O
21.	B-A ⁷	O
22.	B-A ⁸	O
23.	B-A ⁹	O
24.	B-A ¹⁰	O
25.	B-A ¹¹	O
26.	B-A ¹²	O
27.	B-A ¹³	O
28.	B-A ¹⁴	O
29.	CMe ₂	B-A ¹
30.	CMe ₂	B-A ²
31.	CMe ₂	B-A ³
32.	CMe ₂	B-A ⁴
33.	CMe ₂	B-A ⁵
34.	CMe ₂	B-A ⁶
35.	CMe ₂	B-A ⁷
36.	CMe ₂	B-A ⁸
37.	CMe ₂	B-A ⁹
38.	CMe ₂	B-A ¹⁰
39.	CMe ₂	B-A ¹¹
40.	CMe ₂	B-A ¹²
41.	CMe ₂	B-A ¹³
42.	CMe ₂	B-A ¹⁴
43.	B-A ¹	CMe ₂
44.	B-A ²	CMe ₂
45.	B-A ³	CMe ₂
46.	B-A ⁴	CMe ₂
47.	B-A ⁵	CMe ₂
48.	B-A ⁶	CMe ₂
49.	B-A ⁷	CMe ₂
50.	B-A ⁸	CMe ₂
51.	B-A ⁹	CMe ₂
52.	B-A ¹⁰	CMe ₂

26

-continued

u	D^2	D^3
53.	B-A ¹¹	CMe ₂
54.	B-A ¹²	CMe ₂
55.	B-A ¹³	CMe ₂
56.	B-A ¹⁴	CMe ₂
57.	S	B-A ¹
58.	S	B-A ²
59.	S	B-A ³
60.	S	B-A ⁴
61.	S	B-A ⁵
62.	S	B-A ⁶
63.	S	B-A ⁷
64.	S	B-A ⁸
65.	S	B-A ⁹
66.	S	B-A ¹⁰
67.	S	B-A ¹¹
68.	S	B-A ¹²
69.	S	B-A ¹³
70.	S	B-A ¹⁴
71.	N-A ¹	B-A ¹
72.	N-A ¹	B-A ²
73.	N-A ¹	B-A ³
74.	N-A ¹	B-A ⁴
75.	N-A ¹	B-A ⁵
76.	N-A ¹	B-A ⁶
77.	N-A ¹	B-A ⁷
78.	N-A ¹	B-A ⁸
79.	N-A ¹	B-A ⁹
80.	N-A ¹	B-A ¹⁰
81.	N-A ¹	B-A ¹¹
82.	N-A ¹	B-A ¹²
83.	N-A ¹	B-A ¹³
84.	N-A ¹	B-A ¹⁴
85.	O	B-A ¹
86.	O	B-A ²
87.	O	B-A ³
88.	O	B-A ⁴
89.	O	B-A ⁵
90.	O	B-A ⁶
91.	O	B-A ⁷
92.	O	B-A ⁸
93.	O	B-A ⁹
94.	O	B-A ¹⁰
95.	O	B-A ¹¹
96.	O	B-A ¹²
97.	O	B-A ¹³
98.	O	B-A ¹⁴
99.	N-A ¹	B-A ¹
100.	N-A ²	B-A ¹
101.	N-A ³	B-A ¹
102.	N-A ⁴	B-A ¹
103.	N-A ⁵	B-A ¹
104.	N-A ⁶	B-A ¹
105.	N-A ⁷	B-A ¹
106.	N-A ⁸	B-A ¹
107.	N-A ⁹	B-A ¹
108.	N-A ¹⁰	B-A ¹
109.	N-A ¹¹	B-A ¹
110.	N-A ¹²	B-A ¹
111.	N-A ¹³	B-A ¹
112.	N-A ¹⁴	B-A ¹
113.	N-A ¹	B-A ⁴
114.	N-A ²	B-A ⁴
115.	N-A ³	B-A ⁴
116.	N-A ⁴	B-A ⁴
117.	N-A ⁵	B-A ⁴
118.	N-A ⁶	B-A ⁴
119.	N-A ⁷	B-A ⁴
120.	N-A ⁸	B-A ⁴
121.	N-A ⁹	B-A ⁴
122.	N-A ¹⁰	B-A ⁴
123.	N-A ¹¹	B-A ⁴
124.	N-A ¹²	B-A ⁴
125.	N-A ¹³	B-A ⁴
126.	N-A ¹⁴	B-A ⁴
127.	N-A ¹⁴	B-A ⁵
128.	N-A ¹	B-A ⁵
129.	N-A ²	B-A ⁵

27

-continued

u	D ²	D ³
130.	N-A ³	B-A ⁵
131.	N-A ⁴	B-A ⁵
132.	N-A ⁵	B-A ⁵
133.	N-A ⁶	B-A ⁵
134.	N-A ⁷	B-A ⁵
135.	N-A ⁸	B-A ⁵
136.	N-A ⁹	B-A ⁵
137.	N-A ¹⁰	B-A ⁵
138.	N-A ¹¹	B-A ⁵
139.	N-A ¹²	B-A ⁵
140.	N-A ¹³	B-A ⁵
141.	N-A ¹⁴	B-A ⁵

wherein A¹ to A¹⁴ are as defined above, and wherein for each r in L_{At-p-r} and L_{A^{s-ii-r}}, X¹ to X⁴, R² and R³ are defined as shown in Table 4 below:


r	X ¹	X ²	X ³	X ⁴	R ²	R ³
1.	CH	CH	CH	CH	—	—
2.	CH	CMe	CH	CH	—	—
3.	CH	CH	CMe	CH	—	—
4.	CH	CH	CH	CMe	—	—
5.	CH	CMe	CMe	CH	—	—
6.	CH	CH	CH	CH	5,6-H ¹	—
7.	CH	CMe	CH	CH	5,6-H ¹	—
8.	CH	CH	CMe	CH	5,6-H ¹	—
9.	CH	CH	CH	CMe	5,6-H ¹	—
10.	CH	CMe	CMe	CH	5,6-H ¹	—
11.	CH	CH	CH	CH	5,6-H ²	—
12.	CH	CMe	CH	CH	5,6-H ²	—
13.	CH	CH	CMe	CH	5,6-H ²	—
14.	CH	CH	CH	CMe	5,6-H ²	—
15.	CH	CMe	CMe	CH	5,6-H ²	—
16.	CH	CH	CH	CH	5,6-H ³	—
17.	CH	CMe	CH	CH	5,6-H ³	—
18.	CH	CH	CMe	CH	5,6-H ³	—
19.	CH	CH	CH	CMe	5,6-H ³	—
20.	CH	CMe	CMe	CH	5,6-H ³	—
21.	CH	CH	CH	CH	—	9,10-H ¹
22.	CH	CMe	CH	CH	—	9,10-H ¹
23.	CH	CH	CMe	CH	—	9,10-H ¹
24.	CH	CH	CH	CMe	—	9,10-H ¹
25.	CH	CMe	CMe	CH	—	9,10-H ¹
26.	CH	CH	CH	CH	—	9,10-H ¹
27.	CH	CMe	CH	CH	—	9,10-H ¹
28.	CH	CH	CMe	CH	—	9,10-H ¹
29.	CH	CH	CH	CMe	—	9,10-H ¹
30.	CH	CMe	CMe	CH	—	9,10-H ¹
31.	CH	CH	CH	CH	—	9,10-H ¹
32.	CH	CMe	CH	CH	—	9,10-H ¹
33.	CH	CH	CMe	CH	—	9,10-H ¹
34.	CH	CH	CH	CMe	—	9,10-H ¹
35.	CH	CMe	CMe	CH	—	9,10-H ¹
36.	CH	CH	CG ¹	CH	—	—
37.	CH	CH	CG ²	CH	—	—
38.	CH	CH	CG ³	CH	—	—
39.	CH	CH	CG ⁴	CH	—	—
40.	CH	CH	CG ⁵	CH	—	—
41.	CH	CH	CG ⁶	CH	—	—
42.	CH	CH	CG ⁷	CH	—	—
43.	CH	CG ¹	CG ¹	CH	—	—
44.	CH	CG ¹	CG ¹	CH	—	—
45.	E ¹	CH	CH	CH	—	—
46.	E ²	CH	CH	CH	—	—
47.	E ³	CH	CH	CH	—	—
48.	E ⁴	CH	CH	CH	—	—
49.	E ⁵	CH	CH	CH	—	—
50.	E ⁶	CH	CH	CH	—	—
51.	E ¹	CH	CG ¹	CH	—	—
52.	E ²	CH	CG ¹	CH	—	—
53.	E ³	CH	CG ¹	CH	—	—
54.	E ⁴	CH	CG ¹	CH	—	—
55.	E ⁵	CH	CG ¹	CH	—	—
56.	E ⁶	CH	CG ¹	CH	—	—

28

-continued


r	X ¹	X ²	X ³	X ⁴	R ²	R ³
57.	CH	CH		E ¹	—	—
58.	CH	CH		E ²	—	—
59.	CH	CH		E ³	—	—
60.	CH	CH		E ⁴	—	—
61.	CH	CH		E ⁵	—	—
62.	CH	CH		E ⁶	—	—
63.	CH	CMe		E ¹	—	—
64.	CH	CMe		E ²	—	—
65.	CH	CMe		E ³	—	—
66.	CH	CMe		E ⁴	—	—
67.	CH	CMe		E ⁵	—	—
68.	CH	CMe		E ⁶	—	—
69.	CH	CG ¹		E ¹	—	—
70.	CH	CG ¹		E ²	—	—
71.	CH	CG ¹		E ³	—	—
72.	CH	CG ¹		E ⁴	—	—
73.	CH	CG ¹		E ⁵	—	—
74.	CH	CG ¹		E ⁶	—	—
75.	CH	CH		E ¹	5-Me	—
76.	CH	CH		E ²	5-Me	—
77.	CH	CH		E ³	5-Me	—
78.	CH	CH		E ⁴	5-Me	—
79.	CH	CH		E ⁵	5-Me	—
80.	CH	CH		E ⁶	5-Me	—
81.	CH	CH		E ¹	6-Me	—
82.	CH	CH		E ²	6-Me	—
83.	CH	CH		E ³	6-Me	—
84.	CH	CH		E ⁴	6-Me	—
85.	CH	CH		E ⁵	6-Me	—
86.	CH	CH		E ⁶	6-Me	—
87.	CH	CH	CH	CH	—	7-Me
88.	CH	CH	CH	CH	—	8-Me
89.	CH	CH	CH	CH	—	9-Me
90.	CH	CH	CH	CH	—	10-Me
91.	CH		E ¹	CH	—	—
92.	CH		E ²	CH	—	—
93.	CH		E ³	CH	—	—
94.	CH		E ⁴	CH	—	—
95.	CH		E ⁵	CH	—	—
96.	CH		E ⁶	CH	—	—
97.	CH		E ¹	CH	—	8,10-Me
98.	CH		E ²	CH	—	8,10-Me
99.	CH		E ³	CH	—	8,10-Me
100.	CH		E ⁴	CH	—	8,10-Me
101.	CH		E ⁵	CH	—	8,10-Me
102.	CH		E ⁶	CH	—	8,10-Me
103.	N	CH	N	—	—	—
104.	N	CH	CH	—	—	—
105.	CH	N	CH	—	—	—
106.	CH	N	CH	—	—	—
107.	CH	CH	N	—	—	—
108.	CH	CH	N	—	—	—
109.	CH	CH	N	—	—	—
110.	CH	CMe	N	—	—	—

50 wherein E¹ to E⁶, G¹ to G⁷, and H¹ to H³ are defined below




29

-continued


**30**

-continued




31

-continued





**32**

-continued




33

-continued

**34**

-continued

5



10

15

20

25

30

35

40





45

50

55





60

65



35

-continued

**36**

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65








37

-continued



38

-continued



5

10

15

20

25

30

35

40

45

50






55

60






65

39

-continued





**40**

-continued




41

-continued

**42**

-continued

5



10

15

20

25

30

35

40




45

50

55





60

65







43

-continued






**44**

-continued



45

-continued

**46**

-continued

5

10

15

20

25

30

35

40





45

50

55






60

65







47

-continued

**48**

-continued



In some embodiments, the compound has a formula of $M(L_A)_{pp}(L_B)_{qq}(L_C)_{rr}$, wherein L_B and L_C are each a bidentate ligand; and wherein pp is 1, 2, or 3; qq is 0, 1, or 2; rr is 0, 1, or 2; and $pp+qq+rr$ is the oxidation state of the metal M .


In some embodiments, the compound has a formula selected from the group consisting of $Ir(L_A)_3$, $Ir(L_A)(L_B)_2$, $Ir(L_A)_2(L_B)$, $Ir(L_A)_2(L_C)$, and $Ir(L_A)(L_B)(L_C)$; and wherein L_A , L_B , and L_C are different from each other.

In some embodiments, the compound has a formula of $Pt(L_A)(L_B)$; and wherein L_A and L_B can be same or different.


49

In some embodiments, L_A and L_B are connected to form a tetradentate ligand.


In some embodiments, L_B and L_C are each independently selected from the group consisting of the structures in the List D below:

**50**


-continued



51
-continued



52
-continued



wherein:

T is selected from the group consisting of B, Al, Ga, and In;

each of Y^1 to Y^{13} is independently selected from the group consisting of carbon and nitrogen; Y' is selected from the group consisting of BR_e , NR_e , PR_e , O, S, Se, C=O, S=O, SO_2 , CR_eR_{β} , SiR_eR_{β} and GeR_eR_{β} ;



R_e and R_f can be fused or joined to form a ring;

each R_a , R_b , R_c , and R_d independently represent zero, mono, or up to a maximum allowed substitution to its associated ring;

each of R_{a1} , R_{b1} , R_{c1} , R_a , R_b , R_c , R_d , R_e and R_f is 30
independently a hydrogen or a substituent selected
from the group consisting of hydrogen, deuterium,
halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy,
aryloxy, amino, silyl, boryl, alkenyl, cycloalkenyl, het-
eroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, 35
carboxylic acid, ester, nitrile, isonitrile, sulfanyl, sulfi-
nyl, sulfonyl, phosphino, and combinations thereof;
and






two adjacent R_a , R_b , R_c , R_d , R_e and R_f can be fused or joined to form a ring or form a multidentate ligand.

In some embodiments, L_B and L_C are each independently selected from the group consisting of the List E below:








53

-continued


**54**

-continued




56

-continued



57

-continued



5

10

15

20



wherein:

R_a' , R_b' , and R_c' each independently represent zero, mono, 25
or up to a maximum allowed substitution to its associated ring;







each of R_{a1} , R_{b1} , R_{c1} , R_a , R_b , R_c , RN , R_a' , R_b' , and R_c' is 30
independently hydrogen or a substituent selected from the group consisting of deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, boryl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acid, ester, nitrile, isonitrile, sulfanyl, sulfinyl, 35
sulfonyl, phosphino, boryl, and combinations thereof; and

two adjacent R_a' , R_b' , and R_c' are can be fused or joined 40
to form a ring or form a multidentate ligand.

In some embodiments, L_B is selected from the group 45
consisting of L_{B1} to L_{B324} having the structure in the List F below:

 L_{B1}  L_{B2} **58**







-continued

 L_{B3}  L_{B4}  L_{B5}  L_{B6}  L_{B7}  L_{B8}

65

59

-continued

 L_{B9}

5

10

 L_{B10}

15

20

 L_{B11}

25

30

35

 L_{B12}

40

45

 L_{B13}

50

55







 L_{B14}

60

65






60

-continued





 L_{B15} L_{B16} L_{B17} L_{B18} L_{B19} L_{B20}

61

-continued

**62**

-continued

L_{B21}

5

10

L_{B22} 15

20

25

L_{B23} 30

35

40

L_{B24} 45

50

L_{B25} 55







60

65







L_{B26}L_{B27}L_{B28}L_{B29}L_{B30}

63

-continued

**64**

-continued

L_{B31}

5

10

L_{B32}

15

20

25

L_{B33}

30

35

L_{B34}

40

45

L_{B35}

50

55

L_{B36}







60

65







L_{B37}L_{B38}L_{B39}L_{B40}L_{B41}L_{B42}

65

-continued

**66**

-continued

L_{B43}

5

10

L_{B44}

15

20

L_{B45}

25

30

L_{B46}

35

40

L_{B47}

45

50

L_{B48}

55







60

65







L_{B49}L_{B50}L_{B51}L_{B52}L_{B53}L_{B54}

67

-continued

**68**

-continued

L_{B55}

5

10

L_{B56}

15

20

L_{B57}

25

30

35

L_{B58}

40

45

L_{B59}

50

55

L_{B60}







60

65






L_{B61}L_{B62}L_{B63}L_{B64}L_{B65}L_{B66}

69

-continued

**70**

-continued

L_{B67}

5

10

L_{B68}

15

20

L_{B69}

25

30

L_{B70}

35

40

L_{B71}

45

50

L_{B72}

55






60

65







L_{B73}L_{B74}L_{B75}L_{B76}L_{B77}

71

-continued

**72**

-continued

L_{B78}

5

10

L_{B79}

15

20

L_{B80}

25

30

35

L_{B81}

40

45

50

L_{B82}

55







60

65







L_{B83}L_{B84}L_{B85}L_{B86}L_{B87}L_{B88}

73

-continued

**74**

-continued

L_{B89}

5

10

L_{B90}

15

20

L_{B91}

25

30

L_{B92}

35

40

45

L_{B93}

50

55

L_{B94}







60

65






L_{B95}L_{B96}L_{B97}L_{B98}L_{B99}L_{B100}

75

-continued

**76**

-continued

L_{B101}

5

10

L_{B102}

15

20

L_{B103}

25

30

L_{B104}

35

40

L_{B105}

45

50

L_{B106}

55






60

65

L_{B107}L_{B108}L_{B109}L_{B110}L_{B111}

77

-continued



LB112

5

10

LB113

20

25

LB114

30

35

40

LB115

45

50

LB116






55

60

65

78

-continued



LB117

LB118


LB119

LB120

LB121

79

-continued

 L_{B122}


5

10

15

80

-continued



 L_{B126} L_{B123}

20

25

30



35

 L_{B127} L_{B124}

40

45



50

 L_{B128} L_{B125}

55





60

65





 L_{B129}

81

-continued

**82**

-continued

L_{B130}

5

10

15

L_{B131}

20

25

30

L_{B132}

35

40

45

50

L_{B133}

55






60

65





L_{B134}L_{B135}L_{B136}L_{B137}

83

-continued

**84**

-continued



LB138

5

10

LB139

15

20

25

LB140

30

35

LB141

40

45

50

LB142

55

60

65

LB143






LB144

LB145






LB146

85

-continued

**86**

-continued



LB147

5

10

15

LB148

20

25

LB149

30

35

40

LB150

45

50

LB151

55

60

65

LB152

LB153


LB154

LB155

LB156

87

-continued



LB157


5

10

15

88

-continued



LB161



LB158

20

25

30

35





LB162

LB159

40

45

50





LB163

LB160

55

60






65







LB164

89

-continued

**90**

-continued



LB165

5

10

15

LB166

20

25

LB167

30

35

LB168

40

45

50

LB169

55

60

65

LB170


LB171

LB172

LB173

91

-continued

L_{B174}


5

10

15

92

-continued



L_{B178}L_{B175}

20

25

30



35

L_{B179}L_{B176}

40

45



50

L_{B180}L_{B177}

55


60

65

L_{B181}

93

-continued

 L_{B182}

5

10

15

 L_{B183} 20

25

30

35

 L_{B184}

40

45




50

 L_{B185}






55

60

65






**94**

-continued

 L_{B186}  L_{B187}  L_{B188}  L_{B189}  L_{B190}






95

-continued



96

-continued



L_{B191}

5

10

15

L_{B192}

20

25

30

L_{B193}

35

40

45

L_{B194}

50

55

L_{B195}

60

65

L_{B196}

L_{B197}






L_{B198}

L_{B199}





L_{B200}

97

-continued

**98**

-continued

L_{B201}

5

10

L_{B202}

15

20

L_{B203}

25

30

35

L_{B204}

40

45

50

L_{B205}

55





60

65





L_{B206}L_{B207}L_{B208}L_{B209}

99

-continued

**100**

-continued

L_{B210}

5

10

15

L_{B211} 20

25

30

35

L_{B212}

40

45

50

L_{B213} 55





60

65





L_{B214}L_{B215}L_{B216}L_{B217}

101

-continued

**102**

-continued

L_{B218}

5

10

15

L_{B219}

20

25

30

L_{B220}

35

40

45

50

L_{B221}

55





60

65





L_{B222}L_{B223}L_{B224}L_{B225}

103

-continued

**104**

-continued

 L_{B226}

5

10

15

 L_{B227}

20

25

30

 L_{B228}

35

40

45

50

 L_{B229}

55





60

65





 L_{B230} L_{B231} L_{B232} L_{B233}

105

-continued

**106**

-continued

L_{B234}

5

10

15

L_{B235}

20

25

30

35

L_{B236}

40

45

50

L_{B237}

55





60

65





L_{B238}L_{B239}L_{B240}L_{B241}

107

-continued

**108**

-continued

L_{B242}

5

10

15

L_{B243}

20

25

30

L_{B244}

35

40

45

50

L_{B245}

55





60

65





L_{B246}L_{B247}L_{B248}L_{B249}

109

-continued

**110**

-continued

L_{B250}

5

10

15

L_{B251}

20

25

30

35

L_{B252}

40

45

50

L_{B253}

55





60

65

L_{B254}L_{B255}L_{B256}L_{B257}





111

-continued







112

-continued

 L_{B258} L_{B262}L_{B259}L_{B263} L_{B260} L_{B264} L_{B261} L_{B265}

113

-continued

**114**

-continued

 L_{B266}

5

10

15

 L_{B267}

20

25

30

 L_{B268}

35

40

45





 L_{B269}

50

55






60

65





 L_{B270} L_{B270}  L_{B271}  L_{B272} 

115

-continued

**116**

-continued

L_{B273}

5

10

L_{B274}

15

20

25

L_{B275}

30

35

L_{B276}

40

45

50

L_{B277}

55





60

65

L_{B278}L_{B279}L_{B280}L_{B281}

117

-continued

**118**

-continued

L_{B282}

5

10

15

20

L_{B283}

25

30

35

L_{B284}

40

45





50

L_{B285}

55





60

65





L_{B286}L_{B287}L_{B288}L_{B289}

119

-continued

**120**

-continued



LB290

5

10

15

LB291

20

25

30

LB292

35

40

45

50

LB293

55

60

65

LB294





LB295

LB296





LB297

121

-continued

**122**

-continued

L_{B298}

5

10

15

L_{B299}

20

25

30

35

L_{B300}

40

45

50

L_{B301}

55





60

65

L_{B302}L_{B303}L_{B304}L_{B305}

123

-continued

**124**

-continued

L_{B306}

5

10

15

20

L_{B307}

25

30

35

L_{B308}

40

45





50

L_{B309}

55





60

65





L_{B310}*L_{B311}**L_{B312}**L_{B313}*

125

-continued

**126**

-continued

L_{B314}

5

10

15

L_{B315}

20

25

30

35

L_{B316}

40

45

L_{B317}

55


60

65

L_{B318}L_{B319}L_{B320}L_{B321}

127

-continued

**128**


-continued

 L_{B322}

5

10


15

 L_{B324} L_{C1-I} - $L_{C1416-I}$ have the general structure of

20


 L_{B323}

25

 L_{C1-I} - $L_{C1416-I}$ have the general structure of

30

35

wherein R^{201} and R^{202} for L_{Cj-II} and are each independently defined in Table 5 below:

L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}
L_{C1}	R^{D1}	R^{D1}	L_{C193}	R^{D1}	R^{D3}	L_{C385}	R^{D17}	R^{D40}	L_{C577}	R^{D143}	R^{D120}
L_{C2}	R^{D2}	R^{D2}	L_{C194}	R^{D1}	R^{D4}	L_{C386}	R^{D17}	R^{D41}	L_{C578}	R^{D143}	R^{D133}
L_{C3}	R^{D3}	R^{D3}	L_{C195}	R^{D1}	R^{D5}	L_{C387}	R^{D17}	R^{D42}	L_{C579}	R^{D143}	R^{D134}
L_{C4}	R^{D4}	R^{D4}	L_{C196}	R^{D1}	R^{D9}	L_{C388}	R^{D17}	R^{D43}	L_{C580}	R^{D143}	R^{D135}
L_{C5}	R^{D5}	R^{D5}	L_{C197}	R^{D1}	R^{D10}	L_{C389}	R^{D17}	R^{D48}	L_{C581}	R^{D143}	R^{D136}
L_{C6}	R^{D6}	R^{D6}	L_{C198}	R^{D1}	R^{D17}	L_{C390}	R^{D17}	R^{D49}	L_{C582}	R^{D143}	R^{D144}
L_{C7}	R^{D7}	R^{D7}	L_{C199}	R^{D1}	R^{D18}	L_{C391}	R^{D17}	R^{D50}	L_{C583}	R^{D143}	R^{D145}
L_{C8}	R^{D8}	R^{D8}	L_{C200}	R^{D1}	R^{D20}	L_{C392}	R^{D17}	R^{D54}	L_{C584}	R^{D143}	R^{D146}
L_{C9}	R^{D9}	R^{D9}	L_{C201}	R^{D1}	R^{D22}	L_{C393}	R^{D17}	R^{D55}	L_{C585}	R^{D143}	R^{D147}
L_{C10}	R^{D10}	R^{D10}	L_{C202}	R^{D1}	R^{D37}	L_{C394}	R^{D17}	R^{D58}	L_{C586}	R^{D143}	R^{D149}
L_{C11}	R^{D11}	R^{D11}	L_{C203}	R^{D1}	R^{D40}	L_{C395}	R^{D17}	R^{D59}	L_{C587}	R^{D143}	R^{D151}
L_{C12}	R^{D12}	R^{D12}	L_{C204}	R^{D1}	R^{D41}	L_{C396}	R^{D17}	R^{D78}	L_{C588}	R^{D143}	R^{D154}
L_{C13}	R^{D13}	R^{D13}	L_{C205}	R^{D1}	R^{D42}	L_{C397}	R^{D17}	R^{D79}	L_{C589}	R^{D143}	R^{D155}
L_{C14}	R^{D14}	R^{D14}	L_{C206}	R^{D1}	R^{D43}	L_{C398}	R^{D17}	R^{D81}	L_{C590}	R^{D143}	R^{D161}
L_{C15}	R^{D15}	R^{D15}	L_{C207}	R^{D1}	R^{D48}	L_{C399}	R^{D17}	R^{D87}	L_{C591}	R^{D143}	R^{D175}
L_{C16}	R^{D16}	R^{D16}	L_{C208}	R^{D1}	R^{D49}	L_{C400}	R^{D17}	R^{D88}	L_{C592}	R^{D144}	R^{D3}
L_{C17}	R^{D17}	R^{D17}	L_{C209}	R^{D1}	R^{D50}	L_{C401}	R^{D17}	R^{D89}	L_{C593}	R^{D144}	R^{D5}
L_{C18}	R^{D18}	R^{D18}	L_{C210}	R^{D1}	R^{D54}	L_{C402}	R^{D17}	R^{D93}	L_{C594}	R^{D144}	R^{D17}
L_{C19}	R^{D19}	R^{D19}	L_{C211}	R^{D1}	R^{D55}	L_{C403}	R^{D17}	R^{D116}	L_{C595}	R^{D144}	R^{D18}
L_{C20}	R^{D20}	R^{D20}	L_{C212}	R^{D1}	R^{D58}	L_{C404}	R^{D17}	R^{D117}	L_{C596}	R^{D144}	R^{D20}
L_{C21}	R^{D21}	R^{D21}	L_{C213}	R^{D1}	R^{D59}	L_{C405}	R^{D17}	R^{D118}	L_{C597}	R^{D144}	R^{D22}
L_{C22}	R^{D22}	R^{D22}	L_{C214}	R^{D1}	R^{D78}	L_{C406}	R^{D17}	R^{D119}	L_{C598}	R^{D144}	R^{D37}
L_{C23}	R^{D23}	R^{D23}	L_{C215}	R^{D1}	R^{D79}	L_{C407}	R^{D17}	R^{D120}	L_{C599}	R^{D144}	R^{D40}
L_{C24}	R^{D24}	R^{D24}	L_{C216}	R^{D1}	R^{D81}	L_{C408}	R^{D17}	R^{D133}	L_{C600}	R^{D144}	R^{D41}

-continued

L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}
L_{C25}	R^{D25}	R^{D25}	L_{C217}	R^{D1}	R^{D87}	L_{C409}	R^{D17}	R^{D134}	L_{C601}	R^{D144}	R^{D42}
L_{C26}	R^{D26}	R^{D26}	L_{C218}	R^{D1}	R^{D88}	L_{C410}	R^{D17}	R^{D135}	L_{C602}	R^{D144}	R^{D43}
L_{C27}	R^{D27}	R^{D27}	L_{C219}	R^{D1}	R^{D89}	L_{C411}	R^{D17}	R^{D136}	L_{C603}	R^{D144}	R^{D48}
L_{C28}	R^{D28}	R^{D28}	L_{C220}	R^{D1}	R^{D93}	L_{C412}	R^{D17}	R^{D143}	L_{C604}	R^{D144}	R^{D49}
L_{C29}	R^{D29}	R^{D29}	L_{C221}	R^{D1}	R^{D116}	L_{C413}	R^{D17}	R^{D144}	L_{C605}	R^{D144}	R^{D54}
L_{C30}	R^{D30}	R^{D30}	L_{C222}	R^{D1}	R^{D117}	L_{C414}	R^{D17}	R^{D145}	L_{C606}	R^{D144}	R^{D58}
L_{C31}	R^{D31}	R^{D31}	L_{C223}	R^{D1}	R^{D118}	L_{C415}	R^{D17}	R^{D146}	L_{C607}	R^{D144}	R^{D59}
L_{C32}	R^{D32}	R^{D32}	L_{C224}	R^{D1}	R^{D119}	L_{C416}	R^{D17}	R^{D147}	L_{C608}	R^{D144}	R^{D78}
L_{C33}	R^{D33}	R^{D33}	L_{C225}	R^{D1}	R^{D120}	L_{C417}	R^{D17}	R^{D149}	L_{C609}	R^{D144}	R^{D79}
L_{C34}	R^{D34}	R^{D34}	L_{C226}	R^{D1}	R^{D133}	L_{C418}	R^{D17}	R^{D151}	L_{C610}	R^{D144}	R^{D81}
L_{C35}	R^{D35}	R^{D35}	L_{C227}	R^{D1}	R^{D134}	L_{C419}	R^{D17}	R^{D154}	L_{C611}	R^{D144}	R^{D87}
L_{C36}	R^{D36}	R^{D36}	L_{C228}	R^{D1}	R^{D135}	L_{C420}	R^{D17}	R^{D155}	L_{C612}	R^{D144}	R^{D88}
L_{C37}	R^{D37}	R^{D37}	L_{C229}	R^{D1}	R^{D136}	L_{C421}	R^{D17}	R^{D161}	L_{C613}	R^{D144}	R^{D89}
L_{C38}	R^{D38}	R^{D38}	L_{C230}	R^{D1}	R^{D143}	L_{C422}	R^{D17}	R^{D175}	L_{C614}	R^{D144}	R^{D93}
L_{C39}	R^{D39}	R^{D39}	L_{C231}	R^{D1}	R^{D144}	L_{C423}	R^{D50}	R^{D3}	L_{C615}	R^{D144}	R^{D116}
L_{C40}	R^{D40}	R^{D40}	L_{C232}	R^{D1}	R^{D145}	L_{C424}	R^{D50}	R^{D5}	L_{C616}	R^{D144}	R^{D117}
L_{C41}	R^{D41}	R^{D41}	L_{C233}	R^{D1}	R^{D146}	L_{C425}	R^{D50}	R^{D18}	L_{C617}	R^{D144}	R^{D118}
L_{C42}	R^{D42}	R^{D42}	L_{C234}	R^{D1}	R^{D147}	L_{C426}	R^{D50}	R^{D20}	L_{C618}	R^{D144}	R^{D119}
L_{C43}	R^{D43}	R^{D43}	L_{C235}	R^{D1}	R^{D149}	L_{C427}	R^{D50}	R^{D22}	L_{C619}	R^{D144}	R^{D120}
L_{C44}	R^{D44}	R^{D44}	L_{C236}	R^{D1}	R^{D151}	L_{C428}	R^{D50}	R^{D37}	L_{C620}	R^{D144}	R^{D133}
L_{C45}	R^{D45}	R^{D45}	L_{C237}	R^{D1}	R^{D154}	L_{C429}	R^{D50}	R^{D40}	L_{C621}	R^{D144}	R^{D134}
L_{C46}	R^{D46}	R^{D46}	L_{C238}	R^{D1}	R^{D155}	L_{C430}	R^{D50}	R^{D41}	L_{C622}	R^{D144}	R^{D135}
L_{C47}	R^{D47}	R^{D47}	L_{C239}	R^{D1}	R^{D161}	L_{C431}	R^{D50}	R^{D42}	L_{C623}	R^{D144}	R^{D136}
L_{C48}	R^{D48}	R^{D48}	L_{C240}	R^{D1}	R^{D175}	L_{C432}	R^{D50}	R^{D43}	L_{C624}	R^{D144}	R^{D145}
L_{C49}	R^{D49}	R^{D49}	L_{C241}	R^{D4}	R^{D3}	L_{C433}	R^{D50}	R^{D48}	L_{C625}	R^{D144}	R^{D146}
L_{C50}	R^{D50}	R^{D50}	L_{C242}	R^{D4}	R^{D5}	L_{C434}	R^{D50}	R^{D49}	L_{C626}	R^{D144}	R^{D147}
L_{C51}	R^{D51}	R^{D51}	L_{C243}	R^{D4}	R^{D9}	L_{C435}	R^{D50}	R^{D54}	L_{C627}	R^{D144}	R^{D149}
L_{C52}	R^{D52}	R^{D52}	L_{C244}	R^{D4}	R^{D10}	L_{C436}	R^{D50}	R^{D55}	L_{C628}	R^{D144}	R^{D151}
L_{C53}	R^{D53}	R^{D53}	L_{C245}	R^{D4}	R^{D17}	L_{C437}	R^{D50}	R^{D58}	L_{C629}	R^{D144}	R^{D154}
L_{C54}	R^{D54}	R^{D54}	L_{C246}	R^{D4}	R^{D18}	L_{C438}	R^{D50}	R^{D59}	L_{C630}	R^{D144}	R^{D155}
L_{C55}	R^{D55}	R^{D55}	L_{C247}	R^{D4}	R^{D20}	L_{C439}	R^{D50}	R^{D78}	L_{C631}	R^{D144}	R^{D161}
L_{C56}	R^{D56}	R^{D56}	L_{C248}	R^{D4}	R^{D22}	L_{C440}	R^{D50}	R^{D79}	L_{C632}	R^{D144}	R^{D175}
L_{C57}	R^{D57}	R^{D57}	L_{C249}	R^{D4}	R^{D37}	L_{C441}	R^{D50}	R^{D81}	L_{C633}	R^{D145}	R^{D3}
L_{C58}	R^{D58}	R^{D58}	L_{C250}	R^{D4}	R^{D40}	L_{C442}	R^{D50}	R^{D87}	L_{C634}	R^{D145}	R^{D5}
L_{C59}	R^{D59}	R^{D59}	L_{C251}	R^{D4}	R^{D41}	L_{C443}	R^{D50}	R^{D88}	L_{C635}	R^{D145}	R^{D17}
L_{C60}	R^{D60}	R^{D60}	L_{C252}	R^{D4}	R^{D42}	L_{C444}	R^{D50}	R^{D89}	L_{C636}	R^{D145}	R^{D18}
L_{C61}	R^{D61}	R^{D61}	L_{C253}	R^{D4}	R^{D43}	L_{C445}	R^{D50}	R^{D93}	L_{C637}	R^{D145}	R^{D20}
L_{C62}	R^{D62}	R^{D62}	L_{C254}	R^{D4}	R^{D48}	L_{C446}	R^{D50}	R^{D116}	L_{C638}	R^{D145}	R^{D22}
L_{C63}	R^{D63}	R^{D63}	L_{C255}	R^{D4}	R^{D49}	L_{C447}	R^{D50}	R^{D117}	L_{C639}	R^{D145}	R^{D37}
L_{C64}	R^{D64}	R^{D64}	L_{C256}	R^{D4}	R^{D50}	L_{C448}	R^{D50}	R^{D118}	L_{C640}	R^{D145}	R^{D40}
L_{C65}	R^{D65}	R^{D65}	L_{C257}	R^{D4}	R^{D54}	L_{C449}	R^{D50}	R^{D119}	L_{C641}	R^{D145}	R^{D41}
L_{C66}	R^{D66}	R^{D66}	L_{C258}	R^{D4}	R^{D55}	L_{C450}	R^{D50}	R^{D120}	L_{C642}	R^{D145}	R^{D42}
L_{C67}	R^{D67}	R^{D67}	L_{C259}	R^{D4}	R^{D58}	L_{C451}	R^{D50}	R^{D133}	L_{C643}	R^{D145}	R^{D43}
L_{C68}	R^{D68}	R^{D68}	L_{C260}	R^{D4}	R^{D59}	L_{C452}	R^{D50}	R^{D134}	L_{C644}	R^{D145}	R^{D48}
L_{C69}	R^{D69}	R^{D69}	L_{C261}	R^{D4}	R^{D78}	L_{C453}	R^{D50}	R^{D135}	L_{C645}	R^{D145}	R^{D49}
L_{C70}	R^{D70}	R^{D70}	L_{C262}	R^{D4}	R^{D79}	L_{C454}	R^{D50}	R^{D136}	L_{C646}	R^{D145}	R^{D54}
L_{C71}	R^{D71}	R^{D71}	L_{C263}	R^{D4}	R^{D81}	L_{C455}	R^{D50}	R^{D143}	L_{C647}	R^{D145}	R^{D58}
L_{C72}	R^{D72}	R^{D72}	L_{C264}	R^{D4}	R^{D87}	L_{C456}	R^{D50}	R^{D144}	L_{C648}	R^{D145}	R^{D59}
L_{C73}	R^{D73}	R^{D73}	L_{C265}	R^{D4}	R^{D88}	L_{C457}	R^{D50}	R^{D145}	L_{C649}	R^{D145}	R^{D78}
L_{C74}	R^{D74}	R^{D74}	L_{C266}	R^{D4}	R^{D89}	L_{C458}	R^{D50}	R^{D146}	L_{C650}	R^{D145}	R^{D79}
L_{C75}	R^{D75}	R^{D75}	L_{C267}	R^{D4}	R^{D93}	L_{C459}	R^{D50}	R^{D147}	L_{C651}	R^{D145}	R^{D81}
L_{C76}	R^{D76}	R^{D76}	L_{C268}	R^{D4}	R^{D116}	L_{C460}	R^{D50}	R^{D149}	L_{C652}	R^{D145}	R^{D87}
L_{C77}	R^{D77}	R^{D77}	L_{C269}	R^{D4}	R^{D117}	L_{C461}	R^{D50}	R^{D151}	L_{C653}	R^{D145}	R^{D88}
L_{C78}	R^{D78}	R^{D78}	L_{C270}	R^{D4}	R^{D118}	L_{C462}	R^{D50}	R^{D154}	L_{C654}	R^{D145}	R^{D89}
L_{C79}	R^{D79}	R^{D79}	L_{C271}	R^{D4}	R^{D119}	L_{C463}	R^{D50}	R^{D155}	L_{C655}	R^{D145}	R^{D93}
L_{C80}	R^{D80}	R^{D80}	L_{C272}	R^{D4}	R^{D120}	L_{C464}	R^{D50}	R^{D161}	L_{C656}	R^{D145}	R^{D116}
L_{C81}	R^{D81}	R^{D81}	L_{C273}	R^{D4}	R^{D133}	L_{C465}	R^{D50}	R^{D175}	L_{C657}	R^{D145}	R^{D117}
L_{C82}	R^{D82}	R^{D82}	L_{C274}	R^{D4}	R^{D134}	L_{C466}	R^{D55}	R^{D3}	L_{C658}	R^{D145}	R^{D118}
L_{C83}	R^{D83}	R^{D83}	L_{C275}	R^{D4}	R^{D135}	L_{C467}	R^{D55}	R^{D5}	L_{C659}	R^{D145}	R^{D119}
L_{C84}	R^{D84}	R^{D84}	L_{C276}	R^{D4}	R^{D136}	L_{C468}	R^{D55}	R^{D18}	L_{C660}	R^{D145}	R^{D120}
L_{C85}	R^{D85}	R^{D85}	L_{C277}	R^{D4}	R^{D143}	L_{C469}	R^{D55}	R^{D20}	L_{C661}	R^{D145}	R^{D133}
L_{C86}	R^{D86}	R^{D86}	L_{C278}	R^{D4}	R^{D144}	L_{C470}	R^{D55}	R^{D22}	L_{C662}	R^{D145}	R^{D134}
L_{C87}	R^{D87}	R^{D87}	L_{C279}	R^{D4}	R^{D145}	L_{C471}	R^{D55}	R^{D37}	L_{C663}	R^{D145}	R^{D135}
L_{C88}	R^{D88}	R^{D88}	L_{C280}	R^{D4}	R^{D146}	L_{C472}	R^{D55}	R^{D40}	L_{C664}	R^{D145}	R^{D136}
L_{C89}	R^{D89}	R^{D89}	L_{C281}	R^{D4}	R^{D147}	L_{C473}	R^{D55}	R^{D41}	L_{C665}	R^{D145}	R^{D146}
L_{C90}	R^{D90}	R^{D90}	L_{C282}	R^{D4}	R^{D149}	L_{C474}	R^{D55}	R^{D42}	L_{C666}	R^{D145}	R^{D147}
L_{C91}	R^{D91}	R^{D91}	L_{C283}	R^{D4}	R^{D151}	L_{C475}	R^{D55}	R^{D43}	L_{C667}	R^{D145}	R^{D149}
L_{C92}	R^{D92}	R^{D92}	L_{C284}	R^{D4}	R^{D154}	L_{C476}	R^{D55}	R^{D48}	L_{C668}	R^{D145}	R^{D151}
L_{C93}	R^{D93}	R^{D93}	L_{C285}	R^{D4}	R^{D155}	L_{C477}	R^{D55}	R^{D49}	L_{C669}	R^{D145}	R^{D154}
L_{C94}	R^{D94}	R^{D94}	L_{C286}	R^{D4}	R^{D161}	L_{C478}	R^{D55}	R^{D54}	L_{C670}	R^{D145}	R^{D155}
L_{C95}	R^{D95}	R^{D95}	L_{C287}	R^{D4}	R^{D175}	L_{C479}	R^{D55}	R^{D58}	L_{C671}	R^{D145}	R^{D161}
L_{C96}	R^{D96}	R^{D96}	L_{C288}	R^{D9}	R^{D3}	L_{C480}	R^{D55}	R^{D59}	L_{C672}	R^{D145}	R^{D175}
L_{C97}	R^{D97}	R^{D97}	L_{C289}	R^{D9}	R^{D5}	L_{C481}	R^{D55}	R^{D78}	L_{C673}	R^{D146} </	

-continued


L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}
L_{C102}	R^{D102}	R^{D102}	L_{C294}	R^{D9}	R^{D22}	L_{C486}	R^{D55}	R^{D89}	L_{C678}	R^{D146}	R^{D22}
L_{C103}	R^{D103}	R^{D103}	L_{C295}	R^{D9}	R^{D37}	L_{C487}	R^{D55}	R^{D93}	L_{C679}	R^{D146}	R^{D37}
L_{C104}	R^{D104}	R^{D104}	L_{C296}	R^{D9}	R^{D40}	L_{C488}	R^{D55}	R^{D116}	L_{C680}	R^{D146}	R^{D40}
L_{C105}	R^{D105}	R^{D105}	L_{C297}	R^{D9}	R^{D41}	L_{C489}	R^{D55}	R^{D117}	L_{C681}	R^{D146}	R^{D41}
L_{C106}	R^{D106}	R^{D106}	L_{C298}	R^{D9}	R^{D42}	L_{C490}	R^{D55}	R^{D118}	L_{C682}	R^{D146}	R^{D42}
L_{C107}	R^{D107}	R^{D107}	L_{C299}	R^{D9}	R^{D43}	L_{C491}	R^{D55}	R^{D119}	L_{C683}	R^{D146}	R^{D43}
L_{C108}	R^{D108}	R^{D108}	L_{C300}	R^{D9}	R^{D48}	L_{C492}	R^{D55}	R^{D120}	L_{C684}	R^{D146}	R^{D48}
L_{C109}	R^{D109}	R^{D109}	L_{C301}	R^{D9}	R^{D49}	L_{C493}	R^{D55}	R^{D133}	L_{C685}	R^{D146}	R^{D49}
L_{C110}	R^{D110}	R^{D110}	L_{C302}	R^{D9}	R^{D50}	L_{C494}	R^{D55}	R^{D134}	L_{C686}	R^{D146}	R^{D54}
L_{C111}	R^{D111}	R^{D111}	L_{C303}	R^{D9}	R^{D54}	L_{C495}	R^{D55}	R^{D135}	L_{C687}	R^{D146}	R^{D58}
L_{C112}	R^{D112}	R^{D112}	L_{C304}	R^{D9}	R^{D55}	L_{C496}	R^{D55}	R^{D136}	L_{C688}	R^{D146}	R^{D59}
L_{C113}	R^{D113}	R^{D113}	L_{C305}	R^{D9}	R^{D58}	L_{C497}	R^{D55}	R^{D143}	L_{C689}	R^{D146}	R^{D78}
L_{C114}	R^{D114}	R^{D114}	L_{C306}	R^{D9}	R^{D59}	L_{C498}	R^{D55}	R^{D144}	L_{C690}	R^{D146}	R^{D79}
L_{C115}	R^{D115}	R^{D115}	L_{C307}	R^{D9}	R^{D78}	L_{C499}	R^{D55}	R^{D145}	L_{C691}	R^{D146}	R^{D81}
L_{C116}	R^{D116}	R^{D116}	L_{C308}	R^{D9}	R^{D79}	L_{C500}	R^{D55}	R^{D146}	L_{C692}	R^{D146}	R^{D87}
L_{C117}	R^{D117}	R^{D117}	L_{C309}	R^{D9}	R^{D81}	L_{C501}	R^{D55}	R^{D147}	L_{C693}	R^{D146}	R^{D88}
L_{C118}	R^{D118}	R^{D118}	L_{C310}	R^{D9}	R^{D87}	L_{C502}	R^{D55}	R^{D149}	L_{C694}	R^{D146}	R^{D89}
L_{C119}	R^{D119}	R^{D119}	L_{C311}	R^{D9}	R^{D88}	L_{C503}	R^{D55}	R^{D151}	L_{C695}	R^{D146}	R^{D93}
L_{C120}	R^{D120}	R^{D120}	L_{C312}	R^{D9}	R^{D89}	L_{C504}	R^{D55}	R^{D154}	L_{C696}	R^{D146}	R^{D117}
L_{C121}	R^{D121}	R^{D121}	L_{C313}	R^{D9}	R^{D93}	L_{C505}	R^{D55}	R^{D155}	L_{C697}	R^{D146}	R^{D118}
L_{C122}	R^{D122}	R^{D122}	L_{C314}	R^{D9}	R^{D116}	L_{C506}	R^{D55}	R^{D161}	L_{C698}	R^{D146}	R^{D119}
L_{C123}	R^{D123}	R^{D123}	L_{C315}	R^{D9}	R^{D117}	L_{C507}	R^{D55}	R^{D175}	L_{C699}	R^{D146}	R^{D120}
L_{C124}	R^{D124}	R^{D124}	L_{C316}	R^{D9}	R^{D118}	L_{C508}	R^{D116}	R^{D3}	L_{C700}	R^{D146}	R^{D133}
L_{C125}	R^{D125}	R^{D125}	L_{C317}	R^{D9}	R^{D119}	L_{C509}	R^{D116}	R^{D5}	L_{C701}	R^{D146}	R^{D134}
L_{C126}	R^{D126}	R^{D126}	L_{C318}	R^{D9}	R^{D120}	L_{C510}	R^{D116}	R^{D17}	L_{C702}	R^{D146}	R^{D135}
L_{C127}	R^{D127}	R^{D127}	L_{C319}	R^{D9}	R^{D133}	L_{C511}	R^{D116}	R^{D18}	L_{C703}	R^{D146}	R^{D136}
L_{C128}	R^{D128}	R^{D128}	L_{C320}	R^{D9}	R^{D134}	L_{C512}	R^{D116}	R^{D20}	L_{C704}	R^{D146}	R^{D146}
L_{C129}	R^{D129}	R^{D129}	L_{C321}	R^{D9}	R^{D135}	L_{C513}	R^{D116}	R^{D22}	L_{C705}	R^{D146}	R^{D147}
L_{C130}	R^{D130}	R^{D130}	L_{C322}	R^{D9}	R^{D136}	L_{C514}	R^{D116}	R^{D37}	L_{C706}	R^{D146}	R^{D149}
L_{C131}	R^{D131}	R^{D131}	L_{C323}	R^{D9}	R^{D143}	L_{C515}	R^{D116}	R^{D40}	L_{C707}	R^{D146}	R^{D151}
L_{C132}	R^{D132}	R^{D132}	L_{C324}	R^{D9}	R^{D144}	L_{C516}	R^{D116}	R^{D41}	L_{C708}	R^{D146}	R^{D154}
L_{C133}	R^{D133}	R^{D133}	L_{C325}	R^{D9}	R^{D145}	L_{C517}	R^{D116}	R^{D42}	L_{C709}	R^{D146}	R^{D155}
L_{C134}	R^{D134}	R^{D134}	L_{C326}	R^{D9}	R^{D146}	L_{C518}	R^{D116}	R^{D43}	L_{C710}	R^{D146}	R^{D161}
L_{C135}	R^{D135}	R^{D135}	L_{C327}	R^{D9}	R^{D147}	L_{C519}	R^{D116}	R^{D48}	L_{C711}	R^{D146}	R^{D175}
L_{C136}	R^{D136}	R^{D136}	L_{C328}	R^{D9}	R^{D149}	L_{C520}	R^{D116}	R^{D49}	L_{C712}	R^{D133}	R^{D3}
L_{C137}	R^{D137}	R^{D137}	L_{C329}	R^{D9}	R^{D151}	L_{C521}	R^{D116}	R^{D54}	L_{C713}	R^{D133}	R^{D5}
L_{C138}	R^{D138}	R^{D138}	L_{C330}	R^{D9}	R^{D154}	L_{C522}	R^{D116}	R^{D58}	L_{C714}	R^{D133}	R^{D3}
L_{C139}	R^{D139}	R^{D139}	L_{C331}	R^{D9}	R^{D155}	L_{C523}	R^{D116}	R^{D59}	L_{C715}	R^{D133}	R^{D18}
L_{C140}	R^{D140}	R^{D140}	L_{C332}	R^{D9}	R^{D161}	L_{C524}	R^{D116}	R^{D78}	L_{C716}	R^{D133}	R^{D20}
L_{C141}	R^{D141}	R^{D141}	L_{C333}	R^{D9}	R^{D175}	L_{C525}	R^{D116}	R^{D79}	L_{C717}	R^{D133}	R^{D22}
L_{C142}	R^{D142}	R^{D142}	L_{C334}	R^{D10}	R^{D3}	L_{C526}	R^{D116}	R^{D81}	L_{C718}	R^{D133}	R^{D37}
L_{C143}	R^{D143}	R^{D143}	L_{C335}	R^{D10}	R^{D5}	L_{C527}	R^{D116}	R^{D87}	L_{C719}	R^{D133}	R^{D40}
L_{C144}	R^{D144}	R^{D144}	L_{C336}	R^{D10}	R^{D17}	L_{C528}	R^{D116}	R^{D88}	L_{C720}	R^{D133}	R^{D41}
L_{C145}	R^{D145}	R^{D145}	L_{C337}	R^{D10}	R^{D18}	L_{C529}	R^{D116}	R^{D89}	L_{C721}	R^{D133}	R^{D42}
L_{C146}	R^{D146}	R^{D146}	L_{C338}	R^{D10}	R^{D20}	L_{C530}	R^{D116}	R^{D93}	L_{C722}	R^{D133}	R^{D43}
L_{C147}	R^{D147}	R^{D147}	L_{C339}	R^{D10}	R^{D22}	L_{C531}	R^{D116}	R^{D117}	L_{C723}	R^{D133}	R^{D48}
L_{C148}	R^{D148}	R^{D148}	L_{C340}	R^{D10}	R^{D37}	L_{C532}	R^{D116}	R^{D118}	L_{C724}	R^{D133}	R^{D49}
L_{C149}	R^{D149}	R^{D149}	L_{C341}	R^{D10}	R^{D40}	L_{C533}	R^{D116}	R^{D119}	L_{C725}	R^{D133}	R^{D54}
L_{C150}	R^{D150}	R^{D150}	L_{C342}	R^{D10}	R^{D41}	L_{C534}	R^{D116}	R^{D120}	L_{C726}	R^{D133}	R^{D58}
L_{C151}	R^{D151}	R^{D151}	L_{C343}	R^{D10}	R^{D42}	L_{C535}	R^{D116}	R^{D133}	L_{C727}	R^{D133}	R^{D59}
L_{C152}	R^{D152}	R^{D152}	L_{C344}	R^{D10}	R^{D43}	L_{C536}	R^{D116}	R^{D134}	L_{C728}	R^{D133}	R^{D78}
L_{C153}	R^{D153}	R^{D153}	L_{C345}	R^{D10}	R^{D48}	L_{C537}	R^{D116}	R^{D135}	L_{C729}	R^{D133}	R^{D79}
L_{C154}	R^{D154}	R^{D154}	L_{C346}	R^{D10}	R^{D49}	L_{C538}	R^{D116}	R^{D136}	L_{C730}	R^{D133}	R^{D81}
L_{C155}	R^{D155}	R^{D155}	L_{C347}	R^{D10}	R^{D50}	L_{C539}	R^{D116}	R^{D143}	L_{C731}	R^{D133}	R^{D87}
L_{C156}	R^{D156}	R^{D156}	L_{C348}	R^{D10}	R^{D54}	L_{C540}	R^{D116}	R^{D144}	L_{C732}	R^{D133}	R^{D88}
L_{C157}	R^{D157}	R^{D157}	L_{C349}	R^{D10}	R^{D55}	L_{C541}	R^{D116}	R^{D145}	L_{C733}	R^{D133}	R^{D89}
L_{C158}	R^{D158}	R^{D158}	L_{C350}	R^{D10}	R^{D58}	L_{C542}	R^{D116}	R^{D146}	L_{C734}	R^{D133}	R^{D93}
L_{C159}	R^{D159}	R^{D159}	L_{C351}	R^{D10}	R^{D59}	L_{C543}	R^{D116}	R^{D147}	L_{C735}	R^{D133}	R^{D117}
L_{C160}	R^{D160}	R^{D160}	L_{C352}	R^{D10}	R^{D78}	L_{C544}	R^{D116}	R^{D149}	L_{C736}	R^{D133}	R^{D118}
L_{C161}	R^{D161}	R^{D161}	L_{C353}	R^{D10}	R^{D79}	L_{C545}	R^{D116}	R^{D151}	L_{C737}	R^{D133}	R^{D119}
L_{C162}	R^{D162}	R^{D162}	L_{C354}	R^{D10}	R^{D81}	L_{C546}	R^{D116}	R^{D154}	L_{C738}	R^{D133}	R^{D120}
L_{C163}	R^{D163}	R^{D163}	L_{C355}	R^{D10}	R^{D87}	L_{C547}	R^{D116}	R^{D155}	L_{C739}	R^{D133}	R^{D133}
L_{C164}	R^{D164}	R^{D164}	L_{C356}	R^{D10}	R^{D88}	L_{C548}	R^{D116}	R^{D161}	L_{C740}	R^{D133}	R^{D134}
L_{C165}	R^{D165}	R^{D165}	L_{C357}	R^{D10}	R^{D89}	L_{C549}	R^{D116}	R^{D175}	L_{C741}	R^{D133}	R^{D135}
L_{C166}	R^{D166}	R^{D166}	L_{C358}	R^{D10}	R^{D93}	L_{C550}	R^{D143}	R^{D3}	L_{C742}	R^{D133}	R^{D136}
L_{C167}	R^{D167}	R^{D167}	L_{C359}	R^{D10}	R^{D116}	L_{C551}	R^{D143}	R^{D5}	L_{C743}	R^{D133}	R^{D146}
L_{C168}	R^{D168}	R^{D168}	L_{C360}	R^{D10}	R^{D117}	L_{C552}	R^{D143}	R^{D17}	L_{C744}	R^{D133}	R^{D147}
L_{C169}	R^{D169}	R^{D169}	L_{C361}	R^{D10}	R^{D118}	L_{C553}	R^{D143}	R^{D18}	L_{C745}	R^{D133}	R^{D149}
L_{C170}	R^{D170}	R^{D170}	L_{C362}	R^{D10}	R^{D119}	L_{C554}	R^{D143}	R^{D20}	L_{C746}	R^{D133}	R^{D151}
L_{C171}	R^{D171}	R^{D171}	L_{C363}	R^{D10}	R^{D120}	L_{C555}	R^{D143}	R^{D22}	L_{C747}	R^{D133}	R^{D154}
L_{C172}	R^{D172}	R^{D172}	L_{C364}	R^{D10}	R^{D133}	L_{C556}	R^{D143}	R^{D37}	L_{C748}	R^{D133}	R^{D155}
L_{C173}	R^{D173}	R^{D173}	L_{C365}	$R^{$							

L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}
L_{C179}	R^{D179}	R^{D179}	L_{C371}	R^{D10}	R^{D146}	L_{C563}	R^{D143}	R^{D54}	L_{C755}	R^{D175}	R^{D22}
L_{C180}	R^{D180}	R^{D180}	L_{C372}	R^{D10}	R^{D147}	L_{C564}	R^{D143}	R^{D58}	L_{C756}	R^{D175}	R^{D37}
L_{C181}	R^{D181}	R^{D181}	L_{C373}	R^{D10}	R^{D149}	L_{C565}	R^{D143}	R^{D59}	L_{C757}	R^{D175}	R^{D40}
L_{C182}	R^{D182}	R^{D182}	L_{C374}	R^{D10}	R^{D151}	L_{C566}	R^{D143}	R^{D78}	L_{C758}	R^{D175}	R^{D41}
L_{C183}	R^{D183}	R^{D183}	L_{C375}	R^{D10}	R^{D154}	L_{C567}	R^{D143}	R^{D79}	L_{C759}	R^{D175}	R^{D42}
L_{C184}	R^{D184}	R^{D184}	L_{C376}	R^{D10}	R^{D155}	L_{C568}	R^{D143}	R^{D81}	L_{C760}	R^{D175}	R^{D43}
L_{C185}	R^{D185}	R^{D185}	L_{C377}	R^{D10}	R^{D161}	L_{C569}	R^{D143}	R^{D87}	L_{C761}	R^{D175}	R^{D48}
L_{C186}	R^{D186}	R^{D186}	L_{C378}	R^{D10}	R^{D175}	L_{C570}	R^{D143}	R^{D88}	L_{C762}	R^{D175}	R^{D49}
L_{C187}	R^{D187}	R^{D187}	L_{C379}	R^{D17}	R^{D3}	L_{C571}	R^{D143}	R^{D89}	L_{C763}	R^{D175}	R^{D54}
L_{C188}	R^{D188}	R^{D188}	L_{C380}	R^{D17}	R^{D5}	L_{C572}	R^{D143}	R^{D93}	L_{C764}	R^{D175}	R^{D58}
L_{C189}	R^{D189}	R^{D189}	L_{C381}	R^{D17}	R^{D18}	L_{C573}	R^{D143}	R^{D116}	L_{C765}	R^{D175}	R^{D59}
L_{C190}	R^{D190}	R^{D190}	L_{C382}	R^{D17}	R^{D20}	L_{C574}	R^{D143}	R^{D117}	L_{C766}	R^{D175}	R^{D78}
L_{C191}	R^{D191}	R^{D191}	L_{C383}	R^{D17}	R^{D22}	L_{C575}	R^{D143}	R^{D118}	L_{C767}	R^{D175}	R^{D79}
L_{C192}	R^{D192}	R^{D192}	L_{C384}	R^{D17}	R^{D37}	L_{C576}	R^{D143}	R^{D119}	L_{C768}	R^{D175}	R^{D81}
L_{C193}	R^{D193}	R^{D193}	L_{C377}	R^{D1}	R^{D193}	L_{C985}	R^{D4}	R^{D193}	L_{C1093}	R^{D9}	R^{D193}
L_{C194}	R^{D194}	R^{D194}	L_{C378}	R^{D1}	R^{D194}	L_{C986}	R^{D4}	R^{D194}	L_{C1094}	R^{D9}	R^{D194}
L_{C195}	R^{D195}	R^{D195}	L_{C379}	R^{D1}	R^{D195}	L_{C987}	R^{D4}	R^{D195}	L_{C1095}	R^{D9}	R^{D195}
L_{C196}	R^{D196}	R^{D196}	L_{C380}	R^{D1}	R^{D196}	L_{C988}	R^{D4}	R^{D196}	L_{C1096}	R^{D9}	R^{D196}
L_{C197}	R^{D197}	R^{D197}	L_{C381}	R^{D1}	R^{D197}	L_{C989}	R^{D4}	R^{D197}	L_{C1097}	R^{D9}	R^{D197}
L_{C198}	R^{D198}	R^{D198}	L_{C382}	R^{D1}	R^{D198}	L_{C990}	R^{D4}	R^{D198}	L_{C1098}	R^{D9}	R^{D198}
L_{C199}	R^{D199}	R^{D199}	L_{C383}	R^{D1}	R^{D199}	L_{C991}	R^{D4}	R^{D199}	L_{C1099}	R^{D9}	R^{D199}
L_{C200}	R^{D200}	R^{D200}	L_{C384}	R^{D1}	R^{D200}	L_{C992}	R^{D4}	R^{D200}	L_{C1100}	R^{D9}	R^{D200}
L_{C201}	R^{D201}	R^{D201}	L_{C385}	R^{D1}	R^{D201}	L_{C993}	R^{D4}	R^{D201}	L_{C1101}	R^{D9}	R^{D201}
L_{C202}	R^{D202}	R^{D202}	L_{C386}	R^{D1}	R^{D202}	L_{C994}	R^{D4}	R^{D202}	L_{C1102}	R^{D9}	R^{D202}
L_{C203}	R^{D203}	R^{D203}	L_{C387}	R^{D1}	R^{D203}	L_{C995}	R^{D4}	R^{D203}	L_{C1103}	R^{D9}	R^{D203}
L_{C204}	R^{D204}	R^{D204}	L_{C388}	R^{D1}	R^{D204}	L_{C996}	R^{D4}	R^{D204}	L_{C1104}	R^{D9}	R^{D204}
L_{C205}	R^{D205}	R^{D205}	L_{C389}	R^{D1}	R^{D205}	L_{C997}	R^{D4}	R^{D205}	L_{C1105}	R^{D9}	R^{D205}
L_{C206}	R^{D206}	R^{D206}	L_{C390}	R^{D1}	R^{D206}	L_{C998}	R^{D4}	R^{D206}	L_{C1106}	R^{D9}	R^{D206}
L_{C207}	R^{D207}	R^{D207}	L_{C391}	R^{D1}	R^{D207}	L_{C999}	R^{D4}	R^{D207}	L_{C1107}	R^{D9}	R^{D207}
L_{C208}	R^{D208}	R^{D208}	L_{C392}	R^{D1}	R^{D208}	L_{C1000}	R^{D4}	R^{D208}	L_{C1108}	R^{D9}	R^{D208}
L_{C209}	R^{D209}	R^{D209}	L_{C393}	R^{D1}	R^{D209}	L_{C1001}	R^{D4}	R^{D209}	L_{C1109}	R^{D9}	R^{D209}
L_{C210}	R^{D210}	R^{D210}	L_{C394}	R^{D1}	R^{D210}	L_{C1002}	R^{D4}	R^{D210}	L_{C1110}	R^{D9}	R^{D210}
L_{C211}	R^{D211}	R^{D211}	L_{C395}	R^{D1}	R^{D211}	L_{C1003}	R^{D4}	R^{D211}	L_{C1111}	R^{D9}	R^{D211}
L_{C212}	R^{D212}	R^{D212}	L_{C396}	R^{D1}	R^{D212}	L_{C1004}	R^{D4}	R^{D212}	L_{C1112}	R^{D9}	R^{D212}
L_{C213}	R^{D213}	R^{D213}	L_{C397}	R^{D1}	R^{D213}	L_{C1005}	R^{D4}	R^{D213}	L_{C1113}	R^{D9}	R^{D213}
L_{C214}	R^{D214}	R^{D214}	L_{C398}	R^{D1}	R^{D214}	L_{C1006}	R^{D4}	R^{D214}	L_{C1114}	R^{D9}	R^{D214}
L_{C215}	R^{D215}	R^{D215}	L_{C399}	R^{D1}	R^{D215}	L_{C1007}	R^{D4}	R^{D215}	L_{C1115}	R^{D9}	R^{D215}
L_{C216}	R^{D216}	R^{D216}	L_{C400}	R^{D1}	R^{D216}	L_{C1008}	R^{D4}	R^{D216}	L_{C1116}	R^{D9}	R^{D216}
L_{C217}	R^{D217}	R^{D217}	L_{C401}	R^{D1}	R^{D217}	L_{C1009}	R^{D4}	R^{D217}	L_{C1117}	R^{D9}	R^{D217}
L_{C218}	R^{D218}	R^{D218}	L_{C402}	R^{D1}	R^{D218}	L_{C1010}	R^{D4}	R^{D218}	L_{C1118}	R^{D9}	R^{D218}
L_{C219}	R^{D219}	R^{D219}	L_{C403}	R^{D1}	R^{D219}	L_{C1011}	R^{D4}	R^{D219}	L_{C1119}	R^{D9}	R^{D219}
L_{C220}	R^{D220}	R^{D220}	L_{C404}	R^{D1}	R^{D220}	L_{C1012}	R^{D4}	R^{D220}	L_{C1120}	R^{D9}	R^{D220}
L_{C221}	R^{D221}	R^{D221}	L_{C405}	R^{D1}	R^{D221}	L_{C1013}	R^{D4}	R^{D221}	L_{C1121}	R^{D9}	R^{D221}
L_{C222}	R^{D222}	R^{D222}	L_{C406}	R^{D1}	R^{D222}	L_{C1014}	R^{D4}	R^{D222}	L_{C1122}	R^{D9}	R^{D222}
L_{C223}	R^{D223}	R^{D223}	L_{C407}	R^{D1}	R^{D223}	L_{C1015}	R^{D4}	R^{D223}	L_{C1123}	R^{D9}	R^{D223}
L_{C224}	R^{D224}	R^{D224}	L_{C408}	R^{D1}	R^{D224}	L_{C1016}	R^{D4}	R^{D224}	L_{C1124}	R^{D9}	R^{D224}
L_{C225}	R^{D225}	R^{D225}	L_{C409}	R^{D1}	R^{D225}	L_{C1017}	R^{D4}	R^{D225}	L_{C1125}	R^{D9}	R^{D225}
L_{C226}	R^{D226}	R^{D226}	L_{C410}	R^{D1}	R^{D226}	L_{C1018}	R^{D4}	R^{D226}	L_{C1126}	R^{D9}	R^{D226}
L_{C227}	R^{D227}	R^{D227}	L_{C411}	R^{D1}	R^{D227}	L_{C1019}	R^{D4}	R^{D227}	L_{C1127}	R^{D9}	R^{D227}
L_{C228}	R^{D228}	R^{D228}	L_{C412}	R^{D1}	R^{D228}	L_{C1020}	R^{D4}	R^{D228}	L_{C1128}	R^{D9}	R^{D228}
L_{C229}	R^{D229}	R^{D229}	L_{C413}	R^{D1}	R^{D229}	L_{C1021}	R^{D4}	R^{D229}	L_{C1129}	R^{D9}	R^{D229}
L_{C230}	R^{D230}	R^{D230}	L_{C414}	R^{D1}	R^{D230}	L_{C1022}	R^{D4}	R^{D230}	L_{C1130}	R^{D9}	R^{D230}
L_{C231}	R^{D231}	R^{D231}	L_{C415}	R^{D1}	R^{D231}	L_{C1023}	R^{D4}	R^{D231}	L_{C1131}	R^{D9}	R^{D231}
L_{C232}	R^{D232}	R^{D232}	L_{C416}	R^{D1}	R^{D232}	L_{C1024}	R^{D4}	R^{D232}	L_{C1132}	R^{D9}	R^{D232}
L_{C233}	R^{D233}	R^{D233}	L_{C417}	R^{D1}	R^{D233}	L_{C1025}	R^{D4}	R^{D233}	L_{C1133}	R^{D9}	R^{D233}
L_{C234}	R^{D234}	R^{D234}	L_{C418}	R^{D1}	R^{D234}	L_{C1026}	R^{D4}	R^{D234}	L_{C1134}	R^{D9}	R^{D234}
L_{C235}	R^{D235}	R^{D235}	L_{C419}	R^{D1}	R^{D235}	L_{C1027}	R^{D4}	R^{D235}	L_{C1135}	R^{D9}	R^{D235}
L_{C236}	R^{D236}	R^{D236}	L_{C420}	R^{D1}	R^{D236}	L_{C1028}	R^{D4}	R^{D236}	L_{C1136}	R^{D9}	R^{D236}
L_{C237}	R^{D237}	R^{D237}	L_{C421}	R^{D1}	R^{D237}	L_{C1029}	R^{D4}	R^{D237}	L_{C1137}	R^{D9}	R^{D237}
L_{C238}	R^{D238}	R^{D238}	L_{C422}	R^{D1}	R^{D238}	L_{C1030}	R^{D4}	R^{D238}	L_{C1138}	R^{D9}	R^{D238}
L_{C239}	R^{D239}	R^{D239}	L_{C423}	R^{D1}	R^{D239}	L_{C1031}	R^{D4}	R^{D239}	L_{C1139}	R^{D9}	R^{D239}
L_{C240}	R^{D240}	R^{D240}	L_{C424}	R^{D1}	R^{D240}	L_{C1032}	R^{D4}	R^{D240}	L_{C1140}	R^{D9}	R^{D240}
L_{C241}	R^{D241}	R^{D241}	L_{C425}	R^{D1}	R^{D241}	L_{C1033}	R^{D4}	R^{D241}	L_{C1141}	R^{D9}	R^{D241}
L_{C242}	R^{D242}	R^{D242}	L_{C426}	R^{D1}	R^{D242}	L_{C1034}	R^{D4}	R^{D242}	L_{C1142}	R^{D9}	R^{D242}
L_{C243}	R^{D243}	R^{D243}	L_{C427}	R^{D1}	R^{D243}	L_{C1035}	R^{D4}	R^{D243}	L_{C1143}	R^{D9}	R^{D243}
L_{C244}	R^{D244}	R^{D244}	L_{C428}	R^{D1}	R^{D244}	L_{C1036}	R^{D4}	R^{D244}	L_{C1144}	R^{D9}	R^{D244}
L_{C245}	R^{D245}	R^{D245}	L_{C429}	R^{D1}	R^{D245}	L_{C1037}	R^{D4}	R^{D245}	L_{C1145}	R^{D9}	R^{D245}
L_{C246}	R^{D246}	R^{D246}	L_{C430}	R^{D1}	R^{D246}	L_{C1038}	R^{D4}	R^{D246}	L_{C1146}	R^{D9}	R^{D246}
L_{C247}	R^{D247}	R^{D247}	L_{C431}	R^{D50}	R^{D193}	L_{C1039}	R^{D145}	R^{D193}	L_{C1147}	R^{D168}	R^{D193}
L_{C248}	R^{D248}	R^{D248}	L_{C432}	R^{D50}	R^{D194}	L_{C1040}	R^{D145}	R^{D194}	L_{C1148}	R^{D168}	R^{D194}
L_{C249}	R^{D249}	R^{D249}	L_{C433}	R^{D50}	R^{D195}	L_{C1041}	R^{D145}	R^{D195}	L_{C1149}	R^{D168}	R^{D195}
L_{C250}	R^{D250}	R^{D250}	L_{C434}	R^{D50}	R						

L_Q	R^{201}	R^{202}	L_Q	R^{201}	R^{202}	L_Q	R^{201}	R^{202}	L_Q	R^{201}	R^{202}
L_{C832}	R^{D17}	R^{D202}	L_{C940}	R^{D50}	R^{D202}	L_{C1048}	R^{D145}	R^{D202}	L_{C1156}	R^{D168}	R^{D202}
L_{C833}	R^{D17}	R^{D203}	L_{C941}	R^{D50}	R^{D203}	L_{C1049}	R^{D145}	R^{D203}	L_{C1157}	R^{D168}	R^{D203}
L_{C834}	R^{D17}	R^{D204}	L_{C942}	R^{D50}	R^{D204}	L_{C1050}	R^{D145}	R^{D204}	L_{C1158}	R^{D168}	R^{D204}
L_{C835}	R^{D17}	R^{D205}	L_{C943}	R^{D50}	R^{D205}	L_{C1051}	R^{D145}	R^{D205}	L_{C1159}	R^{D168}	R^{D205}
L_{C836}	R^{D17}	R^{D206}	L_{C944}	R^{D50}	R^{D206}	L_{C1052}	R^{D145}	R^{D206}	L_{C1160}	R^{D168}	R^{D206}
L_{C837}	R^{D17}	R^{D207}	L_{C945}	R^{D50}	R^{D207}	L_{C1053}	R^{D145}	R^{D207}	L_{C1161}	R^{D168}	R^{D207}
L_{C838}	R^{D17}	R^{D208}	L_{C946}	R^{D50}	R^{D208}	L_{C1054}	R^{D145}	R^{D208}	L_{C1162}	R^{D168}	R^{D208}
L_{C839}	R^{D17}	R^{D209}	L_{C947}	R^{D50}	R^{D209}	L_{C1055}	R^{D145}	R^{D209}	L_{C1163}	R^{D168}	R^{D209}
L_{C840}	R^{D17}	R^{D210}	L_{C948}	R^{D50}	R^{D210}	L_{C1056}	R^{D145}	R^{D210}	L_{C1164}	R^{D168}	R^{D210}
L_{C841}	R^{D17}	R^{D211}	L_{C949}	R^{D50}	R^{D211}	L_{C1057}	R^{D145}	R^{D211}	L_{C1165}	R^{D168}	R^{D211}
L_{C842}	R^{D17}	R^{D212}	L_{C950}	R^{D50}	R^{D212}	L_{C1058}	R^{D145}	R^{D212}	L_{C1166}	R^{D168}	R^{D212}
L_{C843}	R^{D17}	R^{D213}	L_{C951}	R^{D50}	R^{D213}	L_{C1059}	R^{D145}	R^{D213}	L_{C1167}	R^{D168}	R^{D213}
L_{C844}	R^{D17}	R^{D214}	L_{C952}	R^{D50}	R^{D214}	L_{C1060}	R^{D145}	R^{D214}	L_{C1168}	R^{D168}	R^{D214}
L_{C845}	R^{D17}	R^{D215}	L_{C953}	R^{D50}	R^{D215}	L_{C1061}	R^{D145}	R^{D215}	L_{C1169}	R^{D168}	R^{D215}
L_{C846}	R^{D17}	R^{D216}	L_{C954}	R^{D50}	R^{D216}	L_{C1062}	R^{D145}	R^{D216}	L_{C1170}	R^{D168}	R^{D216}
L_{C847}	R^{D17}	R^{D217}	L_{C955}	R^{D50}	R^{D217}	L_{C1063}	R^{D145}	R^{D217}	L_{C1171}	R^{D168}	R^{D217}
L_{C848}	R^{D17}	R^{D218}	L_{C956}	R^{D50}	R^{D218}	L_{C1064}	R^{D145}	R^{D218}	L_{C1172}	R^{D168}	R^{D218}
L_{C849}	R^{D17}	R^{D219}	L_{C957}	R^{D50}	R^{D219}	L_{C1065}	R^{D145}	R^{D219}	L_{C1173}	R^{D168}	R^{D219}
L_{C850}	R^{D17}	R^{D220}	L_{C958}	R^{D50}	R^{D220}	L_{C1066}	R^{D145}	R^{D220}	L_{C1174}	R^{D168}	R^{D220}
L_{C851}	R^{D17}	R^{D221}	L_{C959}	R^{D50}	R^{D221}	L_{C1067}	R^{D145}	R^{D221}	L_{C1175}	R^{D168}	R^{D221}
L_{C852}	R^{D17}	R^{D222}	L_{C960}	R^{D50}	R^{D222}	L_{C1068}	R^{D145}	R^{D222}	L_{C1176}	R^{D168}	R^{D222}
L_{C853}	R^{D17}	R^{D223}	L_{C961}	R^{D50}	R^{D223}	L_{C1069}	R^{D145}	R^{D223}	L_{C1177}	R^{D168}	R^{D223}
L_{C854}	R^{D17}	R^{D224}	L_{C962}	R^{D50}	R^{D224}	L_{C1070}	R^{D145}	R^{D224}	L_{C1178}	R^{D168}	R^{D


L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}	L_{Cj}	R^{201}	R^{202}
L_{C1233}	R^{D10}	R^{D225}	L_{C1287}	R^{D55}	R^{D225}	L_{C1341}	R^{D37}	R^{D225}	L_{C1395}	R^{D143}	R^{D225}
L_{C1234}	R^{D10}	R^{D226}	L_{C1288}	R^{D55}	R^{D226}	L_{C1342}	R^{D37}	R^{D226}	L_{C1396}	R^{D143}	R^{D226}
L_{C1235}	R^{D10}	R^{D227}	L_{C1289}	R^{D55}	R^{D227}	L_{C1343}	R^{D37}	R^{D227}	L_{C1397}	R^{D143}	R^{D227}
L_{C1236}	R^{D10}	R^{D228}	L_{C1290}	R^{D55}	R^{D228}	L_{C1344}	R^{D37}	R^{D228}	L_{C1398}	R^{D143}	R^{D228}
L_{C1237}	R^{D10}	R^{D229}	L_{C1291}	R^{D55}	R^{D229}	L_{C1345}	R^{D37}	R^{D229}	L_{C1399}	R^{D143}	R^{D229}
L_{C1238}	R^{D10}	R^{D230}	L_{C1292}	R^{D55}	R^{D230}	L_{C1346}	R^{D37}	R^{D230}	L_{C1400}	R^{D143}	R^{D230}
L_{C1239}	R^{D10}	R^{D231}	L_{C1293}	R^{D55}	R^{D231}	L_{C1347}	R^{D37}	R^{D231}	L_{C1401}	R^{D143}	R^{D231}
L_{C1240}	R^{D10}	R^{D232}	L_{C1294}	R^{D55}	R^{D232}	L_{C1348}	R^{D37}	R^{D232}	L_{C1402}	R^{D143}	R^{D232}
L_{C1241}	R^{D10}	R^{D233}	L_{C1295}	R^{D55}	R^{D233}	L_{C1349}	R^{D37}	R^{D233}	L_{C1403}	R^{D143}	R^{D233}
L_{C1242}	R^{D10}	R^{D234}	L_{C1296}	R^{D55}	R^{D234}	L_{C1350}	R^{D37}	R^{D234}	L_{C1404}	R^{D143}	R^{D234}
L_{C1243}	R^{D10}	R^{D235}	L_{C1297}	R^{D55}	R^{D235}	L_{C1351}	R^{D37}	R^{D235}	L_{C1405}	R^{D143}	R^{D235}
L_{C1244}	R^{D10}	R^{D236}	L_{C1298}	R^{D55}	R^{D236}	L_{C1352}	R^{D37}	R^{D236}	L_{C1406}	R^{D143}	R^{D236}
L_{C1245}	R^{D10}	R^{D237}	L_{C1299}	R^{D55}	R^{D237}	L_{C1353}	R^{D37}	R^{D237}	L_{C1407}	R^{D143}	R^{D237}
L_{C1246}	R^{D10}	R^{D238}	L_{C1300}	R^{D55}	R^{D238}	L_{C1354}	R^{D37}	R^{D238}	L_{C1408}	R^{D143}	R^{D238}
L_{C1247}	R^{D10}	R^{D239}	L_{C1301}	R^{D55}	R^{D239}	L_{C1355}	R^{D37}	R^{D239}	L_{C1409}	R^{D143}	R^{D239}
L_{C1248}	R^{D10}	R^{D240}	L_{C1302}	R^{D55}	R^{D240}	L_{C1356}	R^{D37}	R^{D240}	L_{C1410}	R^{D143}	R^{D240}
L_{C1249}	R^{D10}	R^{D241}	L_{C1303}	R^{D55}	R^{D241}	L_{C1357}	R^{D37}	R^{D241}	L_{C1411}	R^{D143}	R^{D241}
L_{C1250}	R^{D10}	R^{D242}	L_{C1304}	R^{D55}	R^{D242}	L_{C1358}	R^{D37}	R^{D242}	L_{C1412}	R^{D143}	R^{D242}
L_{C1251}	R^{D10}	R^{D243}	L_{C1305}	R^{D55}	R^{D243}	L_{C1359}	R^{D37}	R^{D243}	L_{C1413}	R^{D143}	R^{D243}
L_{C1252}	R^{D10}	R^{D244}	L_{C1306}	R^{D55}	R^{D244}	L_{C1360}	R^{D37}	R^{D244}	L_{C1414}	R^{D143}	R^{D244}
L_{C1253}	R^{D10}	R^{D245}	L_{C1307}	R^{D55}	R^{D245}	L_{C1361}	R^{D37}	R^{D245}	L_{C1415}	R^{D143}	R^{D245}
L_{C1254}	R^{D10}	R^{D246}	L_{C1308}	R^{D55}	R^{D246}	L_{C1362}	R^{D37}	R^{D246}	L_{C1416}	R^{D143}	R^{D246}

wherein R^{D1} to R^{D246} have the following structured in List 25 G below:



R^{D1}
30
 R^{D2}
 R^{D3}
35
 R^{D4}
 R^{D5} 40
 R^{D6}
45
 R^{D7}
 R^{D8} 50
 R^{D9} 55
 R^{D10} 60
 R^{D11} 65













-continued















R^{D12}
 R^{D13}
 R^{D14}
 R^{D15}
 R^{D16}
 R^{D17}
 R^{D18}
 R^{D19}
 R^{D20}

139

-continued

**140**

-continued

 R^{D21}

5

 R^{D22}

10

 R^{D24}

15

 R^{D25}

20

 R^{D26}

25

 R^{D27}

30

 R^{D28}

35

 R^{D29}

40

 R^{D30}

45

 R^{D31}

50

 R^{D32}

55

 R^{D33}

60













 R^{D34}

65











 R^{D35} R^{D36} R^{D37} R^{D38} R^{D39} R^{D40} R^{D41} R^{D42} R^{D43} R^{D44} R^{D45} R^{D46} R^{D47} R^{D48}

141

-continued

**142**

-continued

 R^{D49}

5

 R^{D50}

10

 R^{D51}

15

 R^{D52}

20

 R^{D53}

25

 R^{D54}

30

 R^{D55}

35

 R^{D56}

40

 R^{D57}

45

 R^{D58}

50

 R^{D59}

55

 R^{D60}













60

65













 R^{D61} R^{D62} R^{D63} R^{D64} R^{D65} R^{D66} R^{D67} R^{D68} R^{D69} R^{D70} R^{D71} R^{D72} R^{D73}

143

-continued

**144**

-continued

 R^{D74}

5

 R^{D75}

10

 R^{D76}

15

 R^{D77}

20

 R^{D78}

25

 R^{D79}

30

 R^{D80}

35

 R^{D81}

40

 R^{D82}

45

 R^{D83}

50

 R^{D84}

55

 R^{D85}


60

65


 R^{D86} R^{D87} R^{D88} R^{D89} R^{D90} R^{D91} R^{D92} R^{D93} R^{D94} R^{D95} R^{D96} R^{D97}

145


-continued




5




10




15




20




25




30




35




40



45



50












55

60

65









146

-continued

 R^{D109}  R^{D110}  R^{D111}  R^{D112}  R^{D113}  R^{D114}  R^{D115}  R^{D116}  R^{D117}  R^{D118}

147


-continued

**148**


-continued

 R^{D119}

5

 R^{D128} R^{D120}


10

 R^{D129}


15

 R^{D121}


20

 R^{D130} R^{D122}

25

 R^{D131} R^{D123}


30

 R^{D132}


35

 R^{D124}


40

 R^{D133} R^{D125}

45

 R^{D134} R^{D126}


50

 R^{D135}

55

 R^{D127}









60

 R^{D136}

65

153







-continued

**154**


-continued

 R^{D192}




5

 R^{D203} R^{D193} 10 R^{D204} R^{D194} 15 R^{D205} R^{D195} 20 R^{D206} R^{D196} 25 R^{D207} R^{D197} 30 R^{D208} R^{D198}

40

 R^{D209} R^{D199}











45

 R^{D210} R^{D200} 50 R^{D211} R^{D201} 55 R^{D212} R^{D202} 60












65

155

-continued

**156**

-continued

 R^{D213}

5

 R^{D214}

10

15

 R^{D215}

20

25

 R^{D216}

30

35

 R^{D217}

40

 R^{D218}

45

 R^{D219}

50

 R^{D220}

55

 R^{D221}

60


 R^{D222}

65


 R^{D223} R^{D224} R^{D225} R^{D226} R^{D227} R^{D228} R^{D229} R^{D230} R^{D231} R^{D232} R^{D233}

157

-continued

**158**

-continued




In some embodiments, the compound is selected from the group consisting of only those compounds whose L_{Bk} corresponds to one of the following: L_{B1} , L_{B2} , L_{B18} , L_{B28} , L_{B38} , L_{B108} , L_{B118} , L_{B122} , L_{B124} , L_{B126} , L_{B128} , L_{B130} , L_{B132} , L_{B134} , L_{B136} , L_{B138} , L_{B140} , L_{B142} , L_{B144} , L_{B156} , L_{B158} , L_{B160} , L_{B162} , L_{B164} , L_{B168} , L_{B172} , L_{B175} , L_{B204} , L_{B206} , L_{B214} , L_{B216} , L_{B218} , L_{B220} , L_{B222} , L_{B231} , L_{B233} , L_{B235} , L_{B237} , L_{B240} , L_{B242} , L_{B244} , L_{B246} , L_{B248} , L_{B250} , L_{B252} , L_{B254} , L_{B256} , L_{B258} , L_{B260} , L_{B262} , L_{B264} , L_{B265} , L_{B266} , L_{B267} , L_{B268} , L_{B269} , and L_{B270} .

In some embodiments, the compound is selected from the group consisting of only those compounds whose L_{Bk} corresponds to one of the following: L_{B1} , L_{B2} , L_{B18} , L_{B28} , L_{B38} , L_{B108} , L_{B118} , L_{B122} , L_{B126} , L_{B128} , L_{B132} , L_{B136} , L_{B138} , L_{B142} , L_{B156} , L_{B162} , L_{B204} , L_{B206} , L_{B214} , L_{B216} , L_{B218} , L_{B220} , L_{B231} , L_{B233} , L_{B237} , L_{B264} , L_{B265} , L_{B266} , L_{B267} , L_{B268} , L_{B269} , and L_{B270} .


In some embodiments, the compound is selected from the group consisting of only those compounds having L_{Cj-I} or L_{Cj-II} ligand whose corresponding R^{201} and R^{202} are defined to be one of the following structures: R^{D1} , R^{D3} , R^{D4} , R^{D5} , R^{D9} , R^{D10} , R^{D17} , R^{D18} , R^{D20} , R^{D22} , R^{D37} , R^{D40} , R^{D41} , R^{D42} , R^{D43} , R^{D48} , R^{D49} , R^{D50} , R^{D54} , R^{D55} , R^{D58} , R^{D59} , R^{D78} , R^{D79} , R^{D81} , R^{D87} , R^{D88} , R^{D89} , R^{D93} , R^{D116} , R^{D117} , R^{D118} , R^{D119} , R^{D120} , R^{D133} , R^{D134} , R^{D135} , R^{D136} , R^{D143} , R^{D144} , R^{D145} , R^{D146} , R^{D147} , R^{D149} , R^{D151} , R^{D154} , R^{D155} , R^{D161} , R^{D175} , R^{D190} , R^{D193} , R^{D200} , R^{D201} , R^{D206} , R^{D210} , R^{D214} , R^{D215} , R^{D216} , R^{D218} , R^{D219} , R^{D220} , R^{D227} , R^{D237} , R^{D241} , R^{D242} , R^{D245} , and R^{D246} .

In some embodiments, the compound is selected from the group consisting of only those compounds having L_{Cj-I} or L_{Cj-II} ligand whose corresponding R^{201} and R^{202} are defined to be one of the following structures: R^{D1} , R^{D3} , R^{D4} , R^{D5} , R^{D9} , R^{D10} , R^{D17} , R^{D22} , R^{D43} , R^{D50} , R^{D78} , R^{D116} , R^{D118} , R^{D133} , R^{D134} , R^{D135} , R^{D136} , R^{D143} , R^{D144} , R^{D145} , R^{D146} , R^{D149} , R^{D151} , R^{D154} , R^{D155} , R^{D190} , R^{D193} , R^{D200} , R^{D201} , R^{D206} , R^{D210} , R^{D214} , R^{D215} , R^{D216} , R^{D218} , R^{D219} , R^{D220} , R^{D227} , R^{D237} , R^{D241} , R^{D242} , R^{D245} , and R^{D246} .

In some embodiments, the compound is selected from the group consisting of only those compounds having one of the following structures for the L_{Cj-I} ligand:


159**160**

-continued



161


-continued

**162**


-continued

L_{C277-I}

5

L_{C1039-I}L_{C412-I}


10

L_{C1147-I}

15

L_{C231-I}


20

L_{C1012-I}

25

L_{C278-I}


30

L_{C1120-I}


35

L_{C413-I}

40

L_{C850-I}L_{C1066-I}L_{C985-I}


45

L_{C1174-I}


50

L_{C1093-I}

55

L_{C769-I}L_{C823-I}





60

L_{C1201-I}

65

163

-continued



In Some Embodiments, the Compound is Selected from the Group Consisting of:

Compound-A-t-p-r corresponding to each formula $\text{Ir}(\text{L}_{At-p-r})_3$;

Compound-A-s-u-r corresponding to each formula $\text{Ir}(\text{L}_{As-u-r})_3$;

Compound-B-t-p-r-k corresponding to each formula $\text{Ir}(\text{L}_{At-p-r})(\text{L}_{Bk})_2$;

Compound-B-s-u-r-k corresponding to each formula $\text{Ir}(\text{L}_{As-u-r})(\text{L}_{Bk})_2$;

Compound-B'-t-p-r-k corresponding to each formula $\text{Ir}(\text{L}_{At-p-r})_2(\text{L}_{Bk})$;

Compound-B'-s-u-r-k corresponding to each formula $\text{Ir}(\text{L}_{As-u-r})_2(\text{L}_{Bk})$;

Compound-C-t-p-r-j-I corresponding to each formula $\text{Ir}(\text{L}_{At-p-r})_2(\text{L}_{Cj-I})$;






Compound-C-s-u-r-j-I corresponding to each formula $\text{Ir}(\text{L}_{As-u-r})_2(\text{L}_{Cj-I})$;

Compound-C-t-p-r-j-II corresponding to each formula $\text{Ir}(\text{L}_{At-p-r})_2(\text{L}_{Cj-II})$; and

Compound-C-s-u-r-j-I corresponding to each formula $\text{Ir}(\text{L}_{As-u-r})_2(\text{L}_{Cj-I})$.





164

In some embodiments, the compound is selected from the group consisting of the List H below:





 L_{C796-I}  $\text{L}_{C1228-I}$  L_{C803-I}  L_{C776-I} 

165

-continued





**166**

-continued







167

-continued





**168**

-continued







169

-continued


**170**

-continued




171

-continued


**172**

-continued




173

-continued


**174**

-continued




15

In some embodiments, the compound is selected from the group consisting of Formulas III through IX:




20

Formula III




35

Formula IV



50

Formula V




65


175

-continued


Formula VI




Formula VII



Formula VIII



Formula IX



wherein:

M¹ is Pd or Pt;

rings E and F are each independently a 5-membered or 6-membered carbocyclic or heterocyclic ring;

Z¹ and Z² are each independently C or N;

176

K¹ and K² are each independently selected from the group consisting of a direct bond, O, and S, wherein at least one of K¹ and K² is a direct bond;

L¹, L², and L³ are each independently selected from the group consisting of a single bond, absent a bond, O, S, CR'R'', SiR'R'', BR', and NR', wherein at least one of L¹, L² and L³ are present;

X³-X⁵ are each independently C or N;

Rᵀ and Rᵀ each independently represent zero, mono, or up to a maximum allowed substitution to its associated ring;

each of R', R'', Rᵀ, and Rᵀ is independently a hydrogen or a substituent selected from the group consisting of deuterium, fluorine, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, boryl, alkenyl, cycloalkenyl, heteroalkenyl, aryl, heteroaryl, nitrile, isonitrile, sulfanyl, and combinations thereof;

two adjacent R', R'', Rᵀ, and Rᵀ can be joined or fused together to form a ring where chemically feasible; and D¹-D³, Z¹, Z², R⁴, Rᵀ, Rᶜ and rings A¹, A² and A³ are all defined the same as above.

In some embodiments, ring E and ring F are both 6-membered aromatic rings.

In some embodiments, ring F is a 5-membered or 6-membered heteroaromatic ring.

In some embodiments, L¹ is O or CR'R''.

In some embodiments, Z²' is N and Z¹' is C.

In some embodiments, Z²' is C and Z¹' is N.


In some embodiments, L² is a direct bond.

In some embodiments, L² is NR'.

In some embodiments, K¹ and K² are both direct bonds.







In some embodiments, X³-X⁵ are all C.

In some embodiments, the compound is selected from the group consisting of the List I below:








177

-continued






**178**

-continued








179

-continued


**180**

-continued




181

-continued









182

-continued








183

-continued






**184**

-continued








185

-continued






**186**

-continued









188

-continued









189

-continued

**190**

-continued




wherein:

D¹-D³, Z¹-Z⁴, L¹ are all defined the same as above; R^{A'}, R^{B'}, R^{C'}, and R^{D'} are each independently selected from


191

the group consisting of deuterium, fluorine, alkyl, cycloalkyl, heteroalkyl, boryl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, aryl, heteroaryl, nitrile, isonitrile, sulfanyl, and combinations thereof.

In some embodiments, the compound is selected from the group consisting of the List J below:






**192**

-continued







193

-continued




**194**

-continued







195

-continued






**196**

-continued








197

-continued





**198**

-continued







199

-continued





**200**

-continued







201

-continued





**202**

-continued




203

-continued

**204**

-continued



C. The OLEDs and the Devices of the Present Disclosure

In another aspect, the present disclosure also provides an OLED device comprising an anode; a cathode; and an organic layer disposed between the anode and the cathode, wherein the organic layer comprises a compound comprising a ligand L_A of Formula I.


In some embodiments, the compound is a sensitizer, and the OLED further comprises an acceptor selected from the group consisting of a fluorescent emitter, a delayed fluorescence emitter, and combination thereof.

In some embodiments, the organic layer is an emissive layer and the compound is an emissive dopant or a non-emissive dopant.

In some embodiments, the organic layer further comprises a host, wherein the host comprises a triphenylene containing benzo-fused thiophene or benzo-fused furan; wherein any substituent in the host is an unfused substituent independently selected from the group consisting of C_nH_{2n+1} , OC_nH_{2n+1} , OAr_1 , $N(C_nH_{2n+1})_2$, $N(Ar_1)(Ar_2)$, $CH=CH-C_nH_{2n+1}$, $C\equiv CC_nH_{2n+1}$, Ar_1 , Ar_1-Ar_2 , $C_nH_{2n}-Ar_1$, or no substitution; wherein n is from 1 to 10; and wherein Ar_1 and Ar_2 are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof.


In some embodiments, the organic layer further comprises a host, wherein host comprises at least one chemical moiety selected from the group consisting of triphenylene, carbazole, indolocarbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, 5,9-dioxa-13b-boranaphtho[3,2,1-de]anthracene, aza-triphenylene, aza-carbazole, aza-indolocarbazole, aza-dibenzothiophene, aza-dibenzofuran, aza-dibenzoselenophene, and aza-(5,9-dioxa-13b-boranaphtho[3,2,1-de]anthracene).

In some embodiments, the host is selected from the group consisting of:




205

-continued






**206**

-continued









207

-continued






**208**

-continued






209

-continued

**210**

-continued



and combinations thereof.

In some embodiments, the organic layer further comprises a host, wherein the host comprises a metal complex.

In yet another aspect, the present disclosure also provides a consumer product comprising an organic light-emitting device (OLED) comprising: an anode; a cathode; and an organic layer disposed between the anode and the cathode, wherein the organic layer comprises a compound disclosed herein.

Generally, an OLED comprises at least one organic layer disposed between and electrically connected to an anode and a cathode. When a current is applied, the anode injects holes and the cathode injects electrons into the organic layer(s). The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, an "exciton," which is a localized electron-hole pair having an excited energy state, is formed. Light is emitted when the exciton relaxes via a photoemissive mechanism. In some cases, the exciton may

211

be localized on an excimer or an exciplex. Non-radiative mechanisms, such as thermal relaxation, may also occur, but are generally considered undesirable.

Several OLED materials and configurations are described in U.S. Pat. Nos. 5,844,363, 6,303,238, and 5,707,745, which are incorporated herein by reference in their entirety.

The initial OLEDs used emissive molecules that emitted light from their singlet states ("fluorescence") as disclosed, for example, in U.S. Pat. No. 4,769,292, which is incorporated by reference in its entirety. Fluorescent emission generally occurs in a time frame of less than 10 nanoseconds.

More recently, OLEDs having emissive materials that emit light from triplet states ("phosphorescence") have been demonstrated. Baldo et al., "Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices," *Nature*, vol. 395, 151-154, 1998; ("Baldo-I") and Baldo et al., "Very high-efficiency green organic light-emitting devices based on electrophosphorescence," *Appl. Phys. Lett.*, vol. 75, No. 3, 4-6 (1999) ("Baldo-II"), are incorporated by reference in their entireties. Phosphorescence is described in more detail in U.S. Pat. No. 7,279,704 at cols. 5-6, which are incorporated by reference.

FIG. 1 shows an organic light emitting device 100. The figures are not necessarily drawn to scale. Device 100 may include a substrate 110, an anode 115, a hole injection layer 120, a hole transport layer 125, an electron blocking layer 130, an emissive layer 135, a hole blocking layer 140, an electron transport layer 145, an electron injection layer 150, a protective layer 155, a cathode 160, and a barrier layer 170. Cathode 160 is a compound cathode having a first conductive layer 162 and a second conductive layer 164. Device 100 may be fabricated by depositing the layers described, in order. The properties and functions of these various layers, as well as example materials, are described in more detail in U.S. Pat. No. 7,279,704 at cols. 6-10, which are incorporated by reference.

More examples for each of these layers are available. For example, a flexible and transparent substrate-anode combination is disclosed in U.S. Pat. No. 5,844,363, which is incorporated by reference in its entirety. An example of a p-doped hole transport layer is m-MTDATA doped with F₄-TCNQ at a molar ratio of 50:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. Examples of emissive and host materials are disclosed in U.S. Pat. No. 6,303,238 to Thompson et al., which is incorporated by reference in its entirety. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. U.S. Pat. Nos. 5,703,436 and 5,707,745, which are incorporated by reference in their entireties, disclose examples of cathodes including compound cathodes having a thin layer of metal such as Mg:Ag with an overlying transparent, electrically-conductive, sputter-deposited ITO layer. The theory and use of blocking layers is described in more detail in U.S. Pat. No. 6,097,147 and U.S. Patent Application Publication No. 2003/0230980, which are incorporated by reference in their entireties. Examples of injection layers are provided in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety. A description of protective layers may be found in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety.

FIG. 2 shows an inverted OLED 200. The device includes a substrate 210, a cathode 215, an emissive layer 220, a hole

212

transport layer 225, and an anode 230. Device 200 may be fabricated by depositing the layers described, in order. Because the most common OLED configuration has a cathode disposed over the anode, and device 200 has cathode 215 disposed under anode 230, device 200 may be referred to as an "inverted" OLED. Materials similar to those described with respect to device 100 may be used in the corresponding layers of device 200. FIG. 2 provides one example of how some layers may be omitted from the structure of device 100.

The simple layered structure illustrated in FIGS. 1 and 2 is provided by way of non-limiting example, and it is understood that embodiments of the present disclosure may be used in connection with a wide variety of other structures. The specific materials and structures described are exemplary in nature, and other materials and structures may be used. Functional OLEDs may be achieved by combining the various layers described in different ways, or layers may be omitted entirely, based on design, performance, and cost factors. Other layers not specifically described may also be included. Materials other than those specifically described may be used. Although many of the examples provided herein describe various layers as comprising a single material, it is understood that combinations of materials, such as a mixture of host and dopant, or more generally a mixture, may be used. Also, the layers may have various sublayers. The names given to the various layers herein are not intended to be strictly limiting. For example, in device 200, hole transport layer 225 transports holes and injects holes into emissive layer 220, and may be described as a hole transport layer or a hole injection layer. In one embodiment, an OLED may be described as having an "organic layer" disposed between a cathode and an anode. This organic layer may comprise a single layer, or may further comprise multiple layers of different organic materials as described, for example, with respect to FIGS. 1 and 2.

Structures and materials not specifically described may also be used, such as OLEDs comprised of polymeric materials (PLEDs) such as disclosed in U.S. Pat. No. 5,247,190 to Friend et al., which is incorporated by reference in its entirety. By way of further example, OLEDs having a single organic layer may be used. OLEDs may be stacked, for example as described in U.S. Pat. No. 5,707,745 to Forrest et al., which is incorporated by reference in its entirety. The OLED structure may deviate from the simple layered structure illustrated in FIGS. 1 and 2. For example, the substrate may include an angled reflective surface to improve out-coupling, such as a mesa structure as described in U.S. Pat. No. 6,091,195 to Forrest et al., and/or a pit structure as described in U.S. Pat. No. 5,834,893 to Bulovic et al., which are incorporated by reference in their entireties.

Unless otherwise specified, any of the layers of the various embodiments may be deposited by any suitable method. For the organic layers, preferred methods include thermal evaporation, ink-jet, such as described in U.S. Pat. Nos. 6,013,982 and 6,087,196, which are incorporated by reference in their entireties, organic vapor phase deposition (OVPD), such as described in U.S. Pat. No. 6,337,102 to Forrest et al., which is incorporated by reference in its entirety, and deposition by organic vapor jet printing (OVJP), such as described in U.S. Pat. No. 7,431,968, which is incorporated by reference in its entirety. Other suitable deposition methods include spin coating and other solution based processes. Solution based processes are preferably carried out in nitrogen or an inert atmosphere. For the other layers, preferred methods include thermal evaporation. Preferred patterning methods include deposition through a

mask, cold welding such as described in U.S. Pat. Nos. 6,294,398 and 6,468,819, which are incorporated by reference in their entireties, and patterning associated with some of the deposition methods such as ink-jet and organic vapor jet printing (OVJP). Other methods may also be used. The materials to be deposited may be modified to make them compatible with a particular deposition method. For example, substituents such as alkyl and aryl groups, branched or unbranched, and preferably containing at least 3 carbons, may be used in small molecules to enhance their ability to undergo solution processing. Substituents having 20 carbons or more may be used, and 3-20 carbons are a preferred range. Materials with asymmetric structures may have better solution processability than those having symmetric structures, because asymmetric materials may have a lower tendency to recrystallize. Dendrimer substituents may be used to enhance the ability of small molecules to undergo solution processing.

Devices fabricated in accordance with embodiments of the present disclosure may further optionally comprise a barrier layer. One purpose of the barrier layer is to protect the electrodes and organic layers from damaging exposure to harmful species in the environment including moisture, vapor and/or gases, etc. The barrier layer may be deposited over, under or next to a substrate, an electrode, or over any other parts of a device including an edge. The barrier layer may comprise a single layer, or multiple layers. The barrier layer may be formed by various known chemical vapor deposition techniques and may include compositions having a single phase as well as compositions having multiple phases. Any suitable material or combination of materials may be used for the barrier layer. The barrier layer may incorporate an inorganic or an organic compound or both. The preferred barrier layer comprises a mixture of a polymeric material and a non-polymeric material as described in U.S. Pat. No. 7,968,146, PCT Pat. Application Nos. PCT/US2007/023098 and PCT/US2009/042829, which are herein incorporated by reference in their entireties. To be considered a "mixture", the aforesaid polymeric and non-polymeric materials comprising the barrier layer should be deposited under the same reaction conditions and/or at the same time. The weight ratio of polymeric to non-polymeric material may be in the range of 95:5 to 5:95. The polymeric material and the non-polymeric material may be created from the same precursor material. In one example, the mixture of a polymeric material and a non-polymeric material consists essentially of polymeric silicon and inorganic silicon.

Devices fabricated in accordance with embodiments of the present disclosure can be incorporated into a wide variety of electronic component modules (or units) that can be incorporated into a variety of electronic products or intermediate components. Examples of such electronic products or intermediate components include display screens, lighting devices such as discrete light source devices or lighting panels, etc. that can be utilized by the end-user product manufacturers. Such electronic component modules can optionally include the driving electronics and/or power source(s). Devices fabricated in accordance with embodiments of the present disclosure can be incorporated into a wide variety of consumer products that have one or more of the electronic component modules (or units) incorporated therein. A consumer product comprising an OLED that includes the compound of the present disclosure in the organic layer in the OLED is disclosed. Such consumer products would include any kind of products that include one or more light source(s) and/or one or more of some type

of visual displays. Some examples of such consumer products include flat panel displays, curved displays, computer monitors, medical monitors, televisions, billboards, lights for interior or exterior illumination and/or signaling, heads-up displays, fully or partially transparent displays, flexible displays, rollable displays, foldable displays, stretchable displays, laser printers, telephones, mobile phones, tablets, phablets, personal digital assistants (PDAs), wearable devices, laptop computers, digital cameras, camcorders, viewfinders, micro-displays (displays that are less than 2 inches diagonal), 3-D displays, virtual reality or augmented reality displays, vehicles, video walls comprising multiple displays tiled together, theater or stadium screen, a light therapy device, and a sign. Various control mechanisms may be used to control devices fabricated in accordance with the present disclosure, including passive matrix and active matrix. Many of the devices are intended for use in a temperature range comfortable to humans, such as 18 degrees C. to 30 degrees C., and more preferably at room temperature (20-25° C.), but could be used outside this temperature range, for example, from -40 degree C. to +80° C.

More details on OLEDs, and the definitions described above, can be found in U.S. Pat. No. 7,279,704, which is incorporated herein by reference in its entirety.

The materials and structures described herein may have applications in devices other than OLEDs. For example, other optoelectronic devices such as organic solar cells and organic photodetectors may employ the materials and structures. More generally, organic devices, such as organic transistors, may employ the materials and structures.

In some embodiments, the OLED has one or more characteristics selected from the group consisting of being flexible, being rollable, being foldable, being stretchable, and being curved. In some embodiments, the OLED is transparent or semi-transparent. In some embodiments, the OLED further comprises a layer comprising carbon nanotubes.

In some embodiments, the OLED further comprises a layer comprising a delayed fluorescent emitter. In some embodiments, the OLED comprises a RGB pixel arrangement or white plus color filter pixel arrangement. In some embodiments, the OLED is a mobile device, a hand held device, or a wearable device. In some embodiments, the OLED is a display panel having less than 10 inch diagonal or 50 square inch area. In some embodiments, the OLED is a display panel having at least 10 inch diagonal or 50 square inch area. In some embodiments, the OLED is a lighting panel.

In some embodiments, the compound can be an emissive dopant. In some embodiments, the compound can produce emissions via phosphorescence, fluorescence, thermally activated delayed fluorescence, i.e., TADF (also referred to as E-type delayed fluorescence; see, e.g., U.S. application Ser. No. 15/700,352, which is hereby incorporated by reference in its entirety), triplet-triplet annihilation, or combinations of these processes. In some embodiments, the emissive dopant can be a racemic mixture, or can be enriched in one enantiomer. In some embodiments, the compound can be homoleptic (each ligand is the same). In some embodiments, the compound can be heteroleptic (at least one ligand is different from others). When there are more than one ligand coordinated to a metal, the ligands can all be the same in some embodiments. In some other embodiments, at least one ligand is different from the other ligands. In some embodiments, every ligand can be different from each other. This is also true in embodiments where a ligand being

coordinated to a metal can be linked with other ligands being coordinated to that metal to form a tridentate, tetradentate, pentadentate, or hexadentate ligands. Thus, where the coordinating ligands are being linked together, all of the ligands can be the same in some embodiments, and at least one of the ligands being linked can be different from the other ligand(s) in some other embodiments.

In some embodiments, the compound can be used as a phosphorescent sensitizer in an OLED where one or multiple layers in the OLED contains an acceptor in the form of one or more fluorescent and/or delayed fluorescence emitters. In some embodiments, the compound can be used as one component of an exciplex to be used as a sensitizer. As a phosphorescent sensitizer, the compound must be capable of energy transfer to the acceptor and the acceptor will emit the energy or further transfer energy to a final emitter. The acceptor concentrations can range from 0.001% to 100%. The acceptor could be in either the same layer as the phosphorescent sensitizer or in one or more different layers. In some embodiments, the acceptor is a TADF emitter. In some embodiments, the acceptor is a fluorescent emitter. In some embodiments, the emission can arise from any or all of the sensitizer, acceptor, and final emitter.

In some embodiments, at least one of the anode, the cathode, or a new layer disposed over the organic emissive layer functions as an enhancement layer. The enhancement layer comprises a plasmonic material exhibiting surface plasmon resonance that non-radiatively couples to the emitter material and transfers excited state energy from the emitter material to non-radiative mode of surface plasmon polariton. The enhancement layer is provided no more than a threshold distance away from the organic emissive layer, wherein the emitter material has a total non-radiative decay rate constant and a total radiative decay rate constant due to the presence of the enhancement layer and the threshold distance is where the total non-radiative decay rate constant is equal to the total radiative decay rate constant. In some embodiments, the OLED further comprises an outcoupling layer. In some embodiments, the outcoupling layer is disposed over the enhancement layer on the opposite side of the organic emissive layer. In some embodiments, the outcoupling layer is disposed on opposite side of the emissive layer from the enhancement layer but still outcouples energy from the surface plasmon mode of the enhancement layer. The outcoupling layer scatters the energy from the surface plasmon polaritons. In some embodiments this energy is scattered as photons to free space. In other embodiments, the energy is scattered from the surface plasmon mode into other modes of the device such as but not limited to the organic waveguide mode, the substrate mode, or another waveguiding mode. If energy is scattered to the non-free space mode of the OLED other outcoupling schemes could be incorporated to extract that energy to free space. In some embodiments, one or more intervening layer can be disposed between the enhancement layer and the outcoupling layer. The examples for intervening layer(s) can be dielectric materials, including organic, inorganic, perovskites, oxides, and may include stacks and/or mixtures of these materials.

The enhancement layer modifies the effective properties of the medium in which the emitter material resides resulting in any or all of the following: a decreased rate of emission, a modification of emission line-shape, a change in emission intensity with angle, a change in the stability of the emitter material, a change in the efficiency of the OLED, and reduced efficiency roll-off of the OLED device. Placement of the enhancement layer on the cathode side, anode side, or on both sides results in OLED devices which take advantage

of any of the above-mentioned effects. In addition to the specific functional layers mentioned herein and illustrated in the various OLED examples shown in the figures, the OLEDs according to the present disclosure may include any of the other functional layers often found in OLEDs.

The enhancement layer can be comprised of plasmonic materials, optically active metamaterials, or hyperbolic metamaterials. As used herein, a plasmonic material is a material in which the real part of the dielectric constant crosses zero in the visible or ultraviolet region of the electromagnetic spectrum. In some embodiments, the plasmonic material includes at least one metal. In such embodiments the metal may include at least one of Ag, Al, Au, Ir, Pt, Ni, Cu, W, Ta, Fe, Cr, Mg, Ga, Rh, Ti, Ru, Pd, In, Bi, Ca alloys or mixtures of these materials, and stacks of these materials. In general, a metamaterial is a medium composed of different materials where the medium as a whole acts differently than the sum of its material parts. In particular, we define optically active metamaterials as materials which have both negative permittivity and negative permeability. Hyperbolic metamaterials, on the other hand, are anisotropic media in which the permittivity or permeability are of different sign for different spatial directions. Optically active metamaterials and hyperbolic metamaterials are strictly distinguished from many other photonic structures such as Distributed Bragg Reflectors ("DBRs") in that the medium should appear uniform in the direction of propagation on the length scale of the wavelength of light. Using terminology that one skilled in the art can understand: the dielectric constant of the metamaterials in the direction of propagation can be described with the effective medium approximation. Plasmonic materials and metamaterials provide methods for controlling the propagation of light that can enhance OLED performance in a number of ways.

In some embodiments, the enhancement layer is provided as a planar layer. In other embodiments, the enhancement layer has wavelength-sized features that are arranged periodically, quasi-periodically, or randomly, or sub-wavelength-sized features that are arranged periodically, quasi-periodically, or randomly. In some embodiments, the wavelength-sized features and the sub-wavelength-sized features have sharp edges.

In some embodiments, the outcoupling layer has wavelength-sized features that are arranged periodically, quasi-periodically, or randomly, or sub-wavelength-sized features that are arranged periodically, quasi-periodically, or randomly. In some embodiments, the outcoupling layer may be composed of a plurality of nanoparticles and in other embodiments the outcoupling layer is composed of a plurality of nanoparticles disposed over a material. In these embodiments the outcoupling may be tunable by at least one of varying a size of the plurality of nanoparticles, varying a shape of the plurality of nanoparticles, changing a material of the plurality of nanoparticles, adjusting a thickness of the material, changing the refractive index of the material or an additional layer disposed on the plurality of nanoparticles, varying a thickness of the enhancement layer, and/or varying the material of the enhancement layer. The plurality of nanoparticles of the device may be formed from at least one of metal, dielectric material, semiconductor materials, an alloy of metal, a mixture of dielectric materials, a stack or layering of one or more materials, and/or a core of one type of material and that is coated with a shell of a different type of material. In some embodiments, the outcoupling layer is composed of at least metal nanoparticles wherein the metal is selected from the group consisting of Ag, Al, Au, Ir, Pt, Ni, Cu, W, Ta, Fe, Cr, Mg, Ga, Rh, Ti, Ru, Pd, In, Bi, Ca, alloys

217

or mixtures of these materials, and stacks of these materials. The plurality of nanoparticles may have additional layer disposed over them. In some embodiments, the polarization of the emission can be tuned using the outcoupling layer. Varying the dimensionality and periodicity of the outcoupling layer can select a type of polarization that is preferentially outcoupled to air. In some embodiments the outcoupling layer also acts as an electrode of the device.

According to another aspect, a formulation comprising the compound described herein is also disclosed.

The OLED disclosed herein can be incorporated into one or more of a consumer product, an electronic component module, and a lighting panel. The organic layer can be an emissive layer and the compound can be an emissive dopant in some embodiments, while the compound can be a non-emissive dopant in other embodiments.

In yet another aspect of the present disclosure, a formulation that comprises the novel compound disclosed herein is described. The formulation can include one or more components selected from the group consisting of a solvent, a host, a hole injection material, hole transport material, electron blocking material, hole blocking material, and an electron transport material, disclosed herein.

The present disclosure encompasses any chemical structure comprising the novel compound of the present disclosure, or a monovalent or polyvalent variant thereof. In other words, the inventive compound, or a monovalent or polyvalent variant thereof, can be a part of a larger chemical structure. Such chemical structure can be selected from the group consisting of a monomer, a polymer, a macromolecule, and a supramolecule (also known as supermolecule). As used herein, a "monovalent variant of a compound" refers to a moiety that is identical to the compound except that one hydrogen has been removed and replaced with a bond to the rest of the chemical structure. As used herein, a "polyvalent variant of a compound" refers to a moiety that is identical to the compound except that more than one hydrogen has been removed and replaced with a bond or bonds to the rest of the chemical structure. In the instance of a supramolecule, the inventive compound can also be incorporated into the supramolecule complex without covalent bonds.

D. Combination of the Compounds of the Present Disclosure with Other Materials

The materials described herein as useful for a particular layer in an organic light emitting device may be used in combination with a wide variety of other materials present in the device. For example, emissive dopants disclosed herein may be used in conjunction with a wide variety of hosts, transport layers, blocking layers, injection layers, electrodes and other layers that may be present. The materials described or referred to below are non-limiting examples of materials that may be useful in combination with the compounds disclosed herein, and one of skill in the art can readily consult the literature to identify other materials that may be useful in combination.





a) Conductivity Dopants:

A charge transport layer can be doped with conductivity dopants to substantially alter its density of charge carriers, which will in turn alter its conductivity. The conductivity is increased by generating charge carriers in the matrix material, and depending on the type of dopant, a change in the Fermi level of the semiconductor may also be achieved.

218


Hole-transporting layer can be doped by p-type conductivity dopants and n-type conductivity dopants are used in the electron-transporting layer.

Non-limiting examples of the conductivity dopants that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: EP01617493, EP01968131, EP2020694, EP2684932, US20050139810, US20070160905, US20090167167, US2010288362, WO06081780, WO2009003455, WO2009008277, WO2009011327, WO2014009310, US2007252140, US2015060804, US20150123047, and US2012146012.




219

-continued



220


-continued




b) HIL/HTL:

A hole injecting/transporting material to be used in the present disclosure is not particularly limited, and any compound may be used as long as the compound is typically used as a hole injecting/transporting material. Examples of the material include, but are not limited to: a phthalocyanine or porphyrin derivative; an aromatic amine derivative; an indolocarbazole derivative; a polymer containing fluorohydrocarbon; a polymer with conductivity dopants; a conducting polymer, such as PEDOT/PSS; a self-assembly monomer derived from compounds such as phosphonic acid and silane derivatives; a metal oxide derivative, such as MoO₃; a p-type semiconducting organic compound, such as 1,4,5,8,9,12-Hexaazatriphenylenehexacarboxitrile; a metal complex, and a cross-linkable compounds.

Examples of aromatic amine derivatives used in HIL or HTL include, but not limit to the following general structures:




221




Each of Ar¹ to Ar⁹ is selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinazoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuropyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Each Ar may be unsubstituted or may be substituted by a substituent selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acids, ether, ester, nitrile, isonitrile, sulfinyl, sulfonyl, phosphino, and combinations thereof.

In one aspect, Ar¹ to Ar⁹ is independently selected from the group consisting of:



222

-continued



wherein k is an integer from 1 to 20; X¹⁰¹ to X¹⁰⁸ is C (including CH) or N; Z¹⁰¹ is NAr¹, O, or S; Ar¹ has the same group defined above.

Examples of metal complexes used in HIL or HTL include, but are not limited to the following general formula:




wherein Met is a metal, which can have an atomic weight greater than 40; (Y¹⁰¹-Y¹⁰²) is a bidentate ligand, Y¹⁰¹ and Y¹⁰² are independently selected from C, N, O, P, and S; L¹⁰¹ is an ancillary ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and k'+k'' is the maximum number of ligands that may be attached to the metal.



In one aspect, (Y¹⁰¹-Y¹⁰²) is a 2-phenylpyridine derivative. In another aspect, carbene ligand. In another aspect, Met is selected from Ir, Pt, Os, and Zn. In a further aspect, the metal complex has a smallest oxidation potential in solution vs. Fc⁺/Fc couple less than about 0.6 V.

Non-limiting examples of the HIL and HTL materials that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: CN102702075, DE102012005215, EP01624500, EP01698613, EP01806334, EP01930964, EP01972613, EP01997799, EP02011790, EP02055700, EP02055701, EP1725079, EP2085382, EP2660300, EP650955, JP07-073529, JP2005112765, JP2007091719, JP2008021687, JP2014-009196, KR20110088898, KR20130077473, TW201139402, U.S. Ser. No. 06/517,957, US20020158242, US20030162053, US20050123751, US20060182993, US20060240279, US20070145888, US20070181874, US20070278938, US20080014464, US20080091025, US20080106190, US20080124572, US20080145707, US20080220265, US20080233434, US20080303417, US2008107919, US20090115320, US20090167161, US2009066235, US2011007385, US20110163302, US201240968, US2011278551, US2012205642, US2013241401, US20140117329, US2014183517, U.S. Pat. Nos. 5,061,569, 5,639,914, WO05075451, WO07125714, WO08023550, WO08023759, WO2009145016, WO2010061824, WO2011075644, WO2012177006, WO2013018530, WO2013039073, WO2013087142, WO2013118812, WO2013120577, WO2013157367, WO2013175747, WO2014002873, WO2014015935, WO2014015937, WO2014030872, WO2014030921, WO2014034791, WO2014104514, WO2014157018.

223






224



225

226





-continued



227

228






-continued




229

230

-continued






231



-continued




232



233

234




-continued



235

236







-continued



237

-continued






238



239

240





-continued



241

-continued






242




243

244



-continued



245






246



247

248





-continued




249

250

-continued




251




252

-continued



, and



c) EBL:


An electron blocking layer (EBL) may be used to reduce the number of electrons and/or excitons that leave the emissive layer. The presence of such a blocking layer in a device may result in substantially higher efficiencies, and/or longer lifetime, as compared to a similar device lacking a blocking layer. Also, a blocking layer may be used to confine emission to a desired region of an OLED. In some embodiments, the EBL material has a higher LUMO (closer to the vacuum level) and/or higher triplet energy than the emitter closest to the EBL interface. In some embodiments, the EBL material has a higher LUMO (closer to the vacuum level) and/or higher triplet energy than one or more of the hosts closest to the EBL interface. In one aspect, the compound used in EBL contains the same molecule or the same functional groups used as one of the hosts described below.

d) Hosts:

The light emitting layer of the organic EL device of the present disclosure preferably contains at least a metal complex as light emitting material, and may contain a host

material using the metal complex as a dopant material. Examples of the host material are not particularly limited, and any metal complexes or organic compounds may be used as long as the triplet energy of the host is larger than that of the dopant. Any host material may be used with any dopant so long as the triplet criteria is satisfied.


Examples of metal complexes used as host are preferred to have the following general formula:



wherein Met is a metal; (Y^{103} - Y^{104}) is a bidentate ligand, Y^{103} and Y^{104} are independently selected from C, N, O, P, and S; L^{101} is another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and $k'+k''$ is the maximum number of ligands that may be attached to the metal.

253

In one aspect, the metal complexes are:




wherein (O—N) is a bidentate ligand, having metal coordinated to atoms O and N.

In another aspect, Met is selected from Ir and Pt. In a further aspect, (Y¹⁰³-Y¹⁰⁴) is a carbene ligand.


In one aspect, the host compound contains at least one of the following groups selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, tetraphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinazoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuropyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Each option within each group may be unsubstituted or may be substituted by a substituent selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acids, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

In one aspect, the host compound contains at least one of the following groups in the molecule:



254

-continued



wherein R¹⁰¹ is selected from the group consisting of hydrogen, deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alk-


255

enyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acids, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof, and when it is aryl or heteroaryl, it has the similar definition as Ar's mentioned above. k is an integer from 0 to 20 or 1 to 20. X^{101} to X^{108} are independently selected from C (including CH) or N. Z^{101} and Z^{102} are independently selected from NR¹⁰¹, O, or S.

Non-limiting examples of the host materials that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: EP2034538, EP2034538A, EP2757608, JP2007254297, KR20100079458, KR20120088644, KR20120129733, KR20130115564, TW201329200, US20030175553, US20050238919, US20060280965, US20090017330, US20090030202,

256









US20090167162, US20100012931, US2010187984, US2013009543, US2014001446, US2014034914, U.S. Pat. No. 7,154,114, WO2004093207, WO2006072002, WO2008056746, WO2009063833, WO2009086028, WO2011081423, WO2012128298, WO2013024872, WO2013191404, US20160163995, U.S. Pat. No. 9,466,803, US20090309488, US20100187984, US2012126221, US2013175519, US20140225088, WO2001039234, WO2005014551, WO2005089025, WO2007063754, WO2009021126, WO2009066779, WO2010107244, WO2011086863, WO2012133649, WO2013081315, WO2014142472, US20170263869,




257

258

-continued










259



-continued






260



261

262






-continued



263

264








-continued



265

-continued





266



267

268







-continued




269

270

-continued











271



-continued






272



273

274







-continued



275

276

-continued




277

e) Additional Emitters:

One or more additional emitter dopants may be used in conjunction with the compound of the present disclosure. Examples of the additional emitter dopants are not particularly limited, and any compounds may be used as long as the compounds are typically used as emitter materials. Examples of suitable emitter materials include, but are not limited to, compounds which can produce emissions via phosphorescence, fluorescence, thermally activated delayed fluorescence, i.e., TADF (also referred to as E-type delayed fluorescence), triplet-triplet annihilation, or combinations of these processes.






Non-limiting examples of the emitter materials that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: CN103694277, CN1696137, EB01238981, EP01239526, EP01961743, EP1239526, EP1244155, EP1642951, EP1647554, EP1841834, EP1841834B, EP2062907, EP2730583, JP2012074444, JP2013110263, JP4478555, KR1020090133652, KR20120032054, KR20130043460, TW201332980, U.S. Ser. No. 06/699,599, U.S. Ser. No. 06/916,554, US20010019782, US20020034656, US20030068526, US20030072964, US20030138657, US20050123788, US20050244673, US2005123791, US2005260449, US20060008670, US20060065890, US20060127696, US20060134459, US20060134462, US20060202194, US20060251923, US20070034863, US20070087321, US20070103060, US20070111026, US20070190359, US20070231600, US2007034863, US2007104979, US2007104980, US2007138437, US2007224450, US2007278936, US20080020237, US20080233410, US20080261076, US20080297033, US200805851, US2008161567, US2008210930, US20090039776, US20090108737, US20090115322, US20090179555, US2009085476, US2009104472, US20100090591, US20100148663, US20100244004, US20100295032, US2010102716, US2010105902, US2010244004, US2010270916, US20110057559, US20110108822, US20110204333, US2011215710, US2011227049, US2011285275, US2012292601, US20130146848, US2013033172, US2013165653, US2013181190, US2013334521, US20140246656, US2014103305, U.S. Pat. Nos. 6,303,238, 6,413,656, 6,653,654, 6,670,645, 6,687,266, 6,835,469, 6,921,915, 7,279,704, 7,332,232, 7,378,162, 7,534,505, 7,675,228, 7,728,137, 7,740,957, 7,759,489, 7,951,947, 8,067,099, 8,592,586, 8,871,361, WO06081973, WO06121811, WO07018067, WO07108362, WO07115970, WO07115981, WO08035571, WO2002015645, WO2003040257, WO2005019373, WO2006056418, WO2008054584, WO2008078800, WO2008096609, WO2008101842, WO2009000673, WO2009050281, WO2009100991, WO2010028151, WO2010054731, WO2010086089, WO2010118029, WO2011044988, WO2011051404, WO2011107491, WO2012020327, WO2012163471, WO2013094620, WO2013107487, WO2013174471, WO2014007565, WO2014008982, WO2014023377, WO2014024131, WO2014031977, WO2014038456, WO2014112450.

278



279

-continued

**280**

-continued

5

10

15

20

25

30

35

40






45

50

55






60

65








281

-continued






**282**

-continued








283

-continued

**284**

-continued



-continued








-continued








287

-continued





**288**

-continued







289

-continued


**290**

-continued




291

-continued


**292**

-continued




293

-continued






**294**

-continued







295

-continued






**296**

-continued









297

-continued


**298**

-continued



299

-continued




f) HBL:


A hole blocking layer (HBL) may be used to reduce the number of holes and/or excitons that leave the emissive layer. The presence of such a blocking layer in a device may result in substantially higher efficiencies and/or longer life-time as compared to a similar device lacking a blocking layer. Also, a blocking layer may be used to confine emission to a desired region of an OLED. In some embodiments, the HBL material has a lower HOMO (further from the vacuum level) and/or higher triplet energy than the emitter closest to the HBL interface. In some embodiments, the HBL material has a lower HOMO (further from the vacuum level) and/or higher triplet energy than one or more of the hosts closest to the HBL interface.

In one aspect, compound used in HBL contains the same molecule or the same functional groups used as host described above.

In another aspect, compound used in HBL contains at least one of the following groups in the molecule:

**300**

-continued




wherein k is an integer from 1 to 20; L^{101} is another ligand, k' is an integer from 1 to 3.

g) ETL:


Electron transport layer (ETL) may include a material capable of transporting electrons. Electron transport layer may be intrinsic (undoped), or doped. Doping may be used to enhance conductivity. Examples of the ETL material are not particularly limited, and any metal complexes or organic compounds may be used as long as they are typically used to transport electrons.

In one aspect, compound used in ETL contains at least one of the following groups in the molecule:





301

-continued



wherein R^{101} is selected from the group consisting of hydrogen, deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acids, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof, when it is aryl or heteroaryl, it has the similar definition as Ar's mentioned above. Ar^1 to Ar^3 has the similar definition as Ar's mentioned above. k is an integer from 1 to 20. X^{101} to X^{108} is selected from C (including CH) or N.


In another aspect, the metal complexes used in ETL contains, but not limit to the following general formula:



wherein (O—N) or (N—N) is a bidentate ligand, having metal coordinated to atoms O, N or N, N; L^{101} is another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal.





Non-limiting examples of the ETL materials that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: CN103508940, EP01602648, EP01734038, EP01956007, JP2004-022334, JP2005149918, JP2005-268199, KR0117693, KR20130108183, US20040036077, US20070104977, US2007018155, US20090101870, US20090115316, US20090140637, US20090179554, US2009218940, US2010108990, US2011156017, US2011210320, US2012193612, US2012214993, US2014014925, US2014014927, US20140284580, U.S. Pat. Nos. 6,656,612, 8,415,031, WO2003060956, WO2007111263, WO2009148269, WO2010067894, WO2010072300, WO2011074770, WO2011105373, WO2013079217, WO2013145667, WO2013180376, WO2014104499, WO2014104535,

302







303

-continued


**304**

-continued



305

-continued



5


10

15

20

306

-continued




25

30

35

40






45

50

55






60

65







307

-continued



**308**

-continued




309

-continued

**310**

-continued



h) Charge Generation Layer (CGL)


In tandem or stacked OLEDs, the CGL plays an essential role in the performance, which is composed of an n-doped layer and a p-doped layer for injection of electrons and holes, respectively. Electrons and holes are supplied from the CGL and electrodes. The consumed electrons and holes in the CGL are refilled by the electrons and holes injected from the cathode and anode, respectively; then, the bipolar currents reach a steady state gradually. Typical CGL materials include n and p conductivity dopants used in the transport layers.

In any above-mentioned compounds used in each layer of the OLED device, the hydrogen atoms can be partially or fully deuterated. Thus, any specifically listed substituent, such as, without limitation, methyl, phenyl, pyridyl, etc. may be undeuterated, partially deuterated, and fully deuterated versions thereof. Similarly, classes of substituents such as, without limitation, alkyl, aryl, cycloalkyl, heteroaryl, etc. also may be undeuterated, partially deuterated, and fully deuterated versions thereof.


It is understood that the various embodiments described herein are by way of example only and are not intended to limit the scope of the invention. For example, many of the materials and structures described herein may be substituted with other materials and structures without deviating from the spirit of the invention. The present invention as claimed may therefore include variations from the particular examples and preferred embodiments described herein, as will be apparent to one of skill in the art. It is understood that various theories as to why the invention works are not intended to be limiting.

311


Experimental Section Synthesis of Comparison Example



Scheme




IrCl₃
STEP 1



312

-continued



Step 1

Synthesis of Di-*p*-chloro-tetrakis[κ²(C₂,N)-(5-(2,2-dimethylpropyl-1,1-d₂)-2-(phenyl-2'-yl)pyridin-1-yl)]diiridium (III) A 1 L, 4-neck flask was charged with 2-ethoxyethanol (360 mL) and DIUF water (120 mL) and the mixture sparged with nitrogen for 15 minutes. Iridium(III) chloride hydrate (30.2 g, 81.6 mmol, 1.0 equiv) and 5-(2,2-dimethylpropyl-1,1-d₂)-2-phenylpyridine (40.8 g, 179 mmol, 2.2 equiv) were added and the reaction mixture heated at 94° C. for 64 hours. The reaction mixture was cooled to room temperature, the solid filtered, washed thoroughly with methanol then air-dried to give di-μ-chloro-tetrakis-[κ²(C₂, N)-(5-(2,2-dimethylpropyl-1,1-d₂)-2-(phenyl-2'-yl)pyridin-1-yl)]-diiridium (III) (43.3 g, 78% yield), containing 13 mol % unreacted ligands as a bright yellow solid.

Step 2

Synthesis of [Ir(5-(2,2-dimethylpropyl-1,1-d₂)-2-(phenyl-2'-yl)pyridin-1-yl)(-1H)₂(MeOH)₂](trifluoromethanesulfonate): A 5 L, 4-neck flask was charged with di-μ-chloro-tetrakis[κ²(C₂,N)-(5-(2,2-dimethylpropyl-1,1-d₂)-2-(phenyl-2'-yl)pyridin-1-yl)]diiridium(III) (~43.3 g, ~31.8 mmol, 1.0 equiv) in dichloromethane (1.1 L). The flask was wrapped with aluminum foil to exclude light and a solution of silver trifluoromethanesulfonate (18.4 g, 71.6 mmol, 2.37 equiv) in methanol (200 mL) added. The reaction mixture was stirred at room temperature under nitrogen for 24 hours. The reaction mixture was filtered through a pad of silica gel (100 g) topped with Celite® (80 g), rinsing thoroughly with

313


dichloromethane. The filtrate was concentrated under reduced pressure and the residue dried under vacuum at room temperature overnight to give [Ir(5-(2,2-dimethylpropyl-1,1-d₂)-2-(phenyl)-2'-yl)pyridin-1-yl)(-1H)₂(MeOH)₂] (trifluoromethanesulfonate) (46.9 g, 86% yield, >95% ¹H NMR purity) as a dark yellow solid.

Step 3

Synthesis of Bis[(5-(2,2-dimethylpropyl-1,1-d₂)-2-phen-2'-yl)pyridin-1-yl][6-((4,5-bis(methyl-d₃)pyridin-2-yl)-1'-yl)-10-phenyl-10H-benzofuro[3,2-b]indol-7-yl]Iridium(III): To a large amber vial were added, [Ir(5-(2,2-dimethylpropyl-1,1-d₂)-2-(phenyl)-2'-yl)pyridin-1-yl)(-1H)₂(MeOH)₂] (trifluoromethanesulfonate) (0.80 g, 0.932 mmol, 1.0 equiv), 6-((4,5-bis(methyl-d₃)pyridin-2-yl)-1'-yl)-10-phenyl-10H-benzofuro[3,2-b]indole (0.368 g, 0.932 mmol, 1.0 equiv) and ethanol (18.6 mL). The reaction mixture was heated at 76° C. for 1 hour. After cooling to room temperature, the reaction mixture was filtered, and the yellow solids washed with methanol (20 mL). The crude material was purified on a Biotage automated chromatography system (3 stacked 100 g high capacity Biotage cartridges), eluting with a gradient of 10 to 100% tetrahydrofuran in heptanes, then flushing the column with dichloromethane. The combined product fractions were concentrated under reduced pressure. The sample was further purified by chromatography through a column of silica gel (50 g) topped with basic alumina (200 g), eluting with dichloromethane (1.0 L). The recovered product was dissolved in a minimal amount of dichloromethane then precipitated by the addition of methanol (~20 vols) to give bis[(5-(2,2-dimethylpropyl-1,1-d₂)-2-phen-2'-yl)pyridin-1-yl][6-((4,5-bis(methyl-d₃)pyridin-2-yl)-1'-yl)-10-phenyl-10H-benzofuro[3,2-b]indole-7-yl]Iridium(III) (0.396 g, 41% yield, 97.3% UHPLC purity) as a yellow solid. The compound has a λ_{max} of 536 nm at room temperature.


Synthesis of the Inventive Example

Scheme




314

-continued



315

-continued



Inventive example

316

The ligand can be synthesized by repeating the procedure in the following literature: Tetrahedron Letters No. 12, pp 1059-1062, 1978; patent application KR2017/76113; Nature Chem 9, 793-798 (2017). The final complex can be synthesized by repeating the procedure in the comparison example as previously described.

Density Functional Theory (DFT) Data

Calculations were performed using the B3LYP functional with a CEP-31G basis set. Geometry optimizations were performed in vacuum. Excitation energies were obtained at these optimized geometries using time-dependent density functional theory (TDDFT). A continuum solvent model was applied in the TDDFT calculation to simulate tetrahydrofuran solvent. All calculations were carried out using the program Gaussian. Table 6 below shows the calculated values for the HOMO and the LUMO, as well as the respective HOMO-LUMO gap and the wavelengths of light corresponding to the singlet S_1 and triplet T_1 transitions.

TABLE 6

	T1(nm)	S1(nm)	HOMO (eV)	LUMO (eV)
	491	435	-5.006	-1.525
Inventive example				
	543	439	-4.983	-1.524
Comparison example				

* Geometries were determined in the S_0 and T_1 states using Density Functional Theory (DFT). The B3LYP functional was used with an LACVP* basis set. Calculations were performed in vacuum. All calculations were carried out using Jaguar version 2021-1.


317

The calculation result indicated that inventive example is bluer than comparison example (491 nm vs. 543 nm); which has the advantage for blue OLED application. The comparison example has PL of 536 nm experimentally, which is consistent with the theoretical value. This finding was unexpected, that by adding another heteroatom to make one of the fused rings from 5-membered to 6-membered ring, the emission of the final compound can be blue shifted by more than 50 nm from one color zone to another. Although the T_1 energy has more than 50 nm shift, the S_1 energy and the HOMO-LUMO gap are able to stay nearly the same. This is another advantage of these inventive compounds. Without being bound by any theories, it is believed that the best emitter having long device lifetime would have as small S_1 energy as possible while maintaining the necessary T_1 energy. This would normally be very difficult to achieve, because in a regular molecule, increasing T_1 energy would very often result in increasing of S_1 energy. As can be seen here, the current inventive compounds are able to achieve much higher T_1 energy while maintaining the S_1 energy from a conventional stable emitter. With this unexpected property, the inventive compound is expected to perform better than the comparative compound in an OLED device.

The calculations obtained with the above-identified DFT functional set and basis set are theoretical. Computational composite protocols, such as the Gaussian09 with B3LYP and CEP-31G protocol used herein, rely on the assumption that electronic effects are additive and, therefore, larger basis sets can be used to extrapolate to the complete basis set (CBS) limit. However, when the goal of a study is to understand variations in HOMO, LUMO, S_1 , T_1 , bond dissociation energies, etc. over a series of structurally-related compounds, the additive effects are expected to be similar. Accordingly, while absolute errors from using the B3LYP may be significant compared to other computational methods, the relative differences between the HOMO, LUMO, S_1 , T_1 , and bond dissociation energy values calculated with B3LYP protocol are expected to reproduce experiment quite well. See, e.g., Hong et al., *Chem. Mater.* 2016, 28, 5791-98, 5792-93 and Supplemental Information (discussing the reliability of DFT calculations in the context of OLED materials). Moreover, with respect to iridium or platinum complexes that are useful in the OLED art, the data obtained from DFT calculations correlates very well to actual experimental data. See Tavasli et al., *J. Mater. Chem.* 2012, 22, 6419-29, 6422 (Table 6)(showing DFT calculations closely correlating with actual data for a variety of emissive complexes); Morello, G. R., *J. Mol. Model.* 2017, 23:174 (studying of a variety of DFT functional sets and basis sets and concluding the combination of B3LYP and CEP-31G is particularly accurate for emissive complexes).

What is claimed is:

1. A compound comprising a ligand L_A of Formula I




wherein:

A^1 and A^2 are each independently a 5-membered or 6-membered carbocyclic or heterocyclic ring;
 D^1 , D^2 , and D^3 are each independently selected from the group consisting of O, S, Se, BR, NR, PR, P(O)R, CRR', SiRR', and GeRR';

318

one of R^A or R^B has the structure of Formula II



wherein:

Z^1 is connected to C or N on ring A^1 or A^2 or connected to either D^1 , D^2 or D^3 ;

when Z^1 bonds to D^1 , D^2 or D^3 , said D^1 , D^2 or D^3 is selected from the group consisting of BR, NR, PR, P(O)R, CRR', SiRR', and GeRR';

the dashed line in Formula II is coordinated to a metal M; A^3 is a 5-membered or 6-membered carbocyclic or heterocyclic rings;

Z^1 and Z^2 are each independently C or N;

R^A , R^B and R^C represent mono to the maximum allowable substitution, or no substitution;

each R^A , R^B , R^C , R, and R' is independently a hydrogen or a substituent selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, boryl, arylalkyl, aryloxy, amino, silyl, germlyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, selenyl, and combinations thereof;

if D^2 and D^3 are both CRR' and A^3 bonds to A^2 where A^2 is a 6-membered ring, then Z^2 is N, and R and R' are each independently a hydrogen or a substituent selected from the group consisting of deuterium, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, boryl, arylalkyl, aryloxy, amino, silyl, germlyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, selenyl, and combinations thereof;

L_A is coordinated to a metal M through the dashed line with Z^2 in Formula II and with one atom from ring A^1 or A^2 that is connected to Formula II to form a 5-membered chelate ring or 6-membered chelate ring;

M is selected from the group consisting of Os, Ir, Rh, Re, Ru, Pd, Pt, Cu, Ag, and Au;

M can be coordinated to other ligands;

L_A can be joined with other ligands to form a tridentate, tetradentate, pentadentate, or hexadentate ligand; and any two adjacent R^A , R^B , R^C , R, and R' can be joined or fused to form a ring.

2. The compound of claim 1, wherein each R^A , R^B , R^C , R, and R' is independently a hydrogen or a substituent selected from the group consisting of deuterium, fluorine, alkyl, cycloalkyl, heteroalkyl, boryl, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, aryl, heteroaryl, nitrile, isonitrile, sulfanyl, and combinations thereof.

3. The compound of claim 1, wherein:

D^1 , D^2 , and D^3 are each independently selected from the group consisting of O, S, BR, NR, CRR' and SiRR'; and Z^1 is C, and Z^2 is N; or Z^1 is N, and Z^2 is C.

4. The compound of claim 1, wherein one of the following is true:

A^1 is a heterocyclic ring comprising C and N;
 A^1 is a carbocyclic ring;

319

A¹ is a 5-membered aromatic ring selected from the group consisting of imidazole, pyrazole, triazole, and N-heterocyclic carbene; and

A¹ is a 6-membered aromatic ring selected from the group consisting of benzene, pyridine, pyrimidine, pyridazine, and triazine.

5. The compound of claim 1, wherein one of the following is true:

A² is a heterocyclic ring comprising C and N;

A² is a carbocyclic ring;

A² is a 5-membered aromatic ring selected from the group consisting of imidazole, pyrazole, triazole, and N-heterocyclic carbene; and

A² is a 6-membered aromatic ring selected from the group consisting of benzene, pyridine, pyrimidine, pyridazine, and triazine.

6. The compound of claim 1, wherein one of the following is true:

A³ is a heterocyclic ring comprising C and N;

A³ is a carbocyclic ring;


A³ is a 5-membered aromatic ring selected from the group consisting of imidazole, pyrazole, triazole, and N-heterocyclic carbene; and

A³ is a 6-membered aromatic ring selected from the group consisting of benzene, pyridine, pyrimidine, pyridazine, and triazine.

7. The compound of claim 1, wherein Z¹ is connected to C on ring A¹ or A²; or Z¹ is connected to D¹, D² or D³.


8. The compound of claim 1, wherein M is further coordinated to at least one phenylpyridine ligand; or M is further coordinated to two phenylpyridine ligands.

9. The compound of claim 1, wherein the ligand L₄ is selected from the group consisting of:










320

-continued










321

-continued




322

-continued



323

-continued




wherein X^1 to X^{11} are each independently C or N; R^1 to R^3 is independently a hydrogen or a substituent selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, boryl, aryl, alkyl, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof;

Z^1 and Z^2 are C and N; D^1 , D^2 and D^3 are defined above.

10. The compound of claim 1, wherein the ligand L_A is selected from the group of structures defined by $L_{A,t-p-r}$ or $L_{A,s-u-r}$ wherein t is an integer from 1 to 16, p is an integer from 1 to 196, r is an integer from 1 to 110, s is an integer from 1 to 12, u is an integer from 1 to 141, wherein for the group represented by $L_{A,t-p-r}$, each $L_{A,t}$ represents structures defined below:

L_{A1} and L_{A2} have the structure




wherein, for L_{A1} , $Z^1 = C$, $Z^2 = N$, and for L_{A2} , $Z^1 = N$, and $Z^2 = C$;

324


-continued

L_{A3} and L_{A4} have the structure



wherein, for L_{A3} , $Z^1 = C$, $Z^2 = N$, and for L_{A4} , $Z^1 = N$, and $Z^2 = C$;

L_{A5} and L_{A6} have the structure




L_{A5} : $Z^1 = C$, $Z^2 = N$;

L_{A6} : $Z^1 = N$, $Z^2 = C$;


wherein, for L_{A5} , $Z^1 = C$, $Z^2 = N$, and for L_{A6} , $Z^1 = N$, and $Z^2 = C$;

L_{A7} and L_{A8} have the structure




wherein for L_{A7} , $Z^1 = C$, $Z^2 = N$, and for L_{A8} , $Z^1 = N$, and $Z^2 = C$;

L_{A9} and L_{A10} have the structure



wherein, for L_{A9} , $Z^1 = C$, $Z^2 = N$, and for L_{A10} , $Z^1 = N$, and $Z^2 = C$;


L_{A11} and L_{A12} have the structure




wherein, for L_{A11} , $Z^1 = C$, $Z^2 = N$, and for L_{A12} , $Z^1 = N$, and $Z^2 = C$;

325

-continued

 L_{A113} and L_{A114} have the structure

wherein, for L_{A113} , $Z^1 = C$, $Z^2 = N$,
and for L_{A114} , $Z^1 = N$, and $Z^2 = C$;

 L_{A115} and L_{A116} have the structure

wherein, for L_{A115} , $Z^1 = C$, $Z^2 = N$, and
for L_{A116} , $Z^1 = N$, and $Z^2 = C$;

wherein for each p, D^1 , D^2 , and D^3 are defined as follows:

p	D^1	D^2	D^3
1.	O	O	O
2.	O	O	O
3.	O	O	O
4.	O	O	O
5.	O	O	O
6.	O	O	O
7.	O	O	O
8.	O	O	O
9.	O	O	O
10.	O	O	O
11.	O	O	O
12.	O	O	O
13.	O	O	O
14.	O	O	O
15.	O	O	B-A ¹
16.	O	O	B-A ²
17.	O	O	B-A ³
18.	O	O	B-A ⁴
19.	O	O	B-A ⁵
20.	O	O	B-A ⁶
21.	O	O	B-A ⁷
22.	O	O	B-A ⁸
23.	O	O	B-A ⁹
24.	O	O	B-A ¹⁰
25.	O	O	B-A ¹¹
26.	O	O	B-A ¹²
27.	O	O	B-A ¹³
28.	O	O	B-A ¹⁴
29.	O	S	B-A ¹
30.	O	S	B-A ²
31.	O	S	B-A ³
32.	O	S	B-A ⁴
33.	O	S	B-A ⁵
34.	O	S	B-A ⁶
35.	O	S	B-A ⁷
36.	O	S	B-A ⁸
37.	O	S	B-A ⁹
38.	O	S	B-A ¹⁰
39.	O	S	B-A ¹¹

326

-continued

	p	D^1	D^2	D^3
5	40.	O	S	B-A ¹²
	41.	O	S	B-A ¹³
	42.	O	S	B-A ¹⁴
	43.	O	SiMe ₂	B-A ¹
	44.	O	SiMe ₂	B-A ²
10	45.	O	SiMe ₂	B-A ³
	46.	O	SiMe ₂	B-A ⁴
	47.	O	SiMe ₂	B-A ⁵
	48.	O	SiMe ₂	B-A ⁶
	49.	O	SiMe ₂	B-A ⁷
15	50.	O	SiMe ₂	B-A ⁸
	51.	O	SiMe ₂	B-A ⁹
	52.	O	SiMe ₂	B-A ¹⁰
	53.	O	SiMe ₂	B-A ¹¹
	54.	O	SiMe ₂	B-A ¹²
20	55.	O	SiMe ₂	B-A ¹³
	56.	O	SiMe ₂	B-A ¹⁴
	57.	O	B-A ¹	O
	58.	O	B-A ²	O
	59.	O	B-A ³	O
25	60.	O	B-A ⁴	O
	61.	O	B-A ⁵	O
	62.	O	B-A ⁶	O
	63.	O	B-A ⁷	O
	64.	O	B-A ⁸	O
30	65.	O	B-A ⁹	O
	66.	O	B-A ¹⁰	O
	67.	O	B-A ¹¹	O
	68.	O	B-A ¹²	O
	69.	O	B-A ¹³	O
35	70.	O	B-A ¹⁴	O
	71.	O	N-A ¹	O
	72.	O	N-A ²	O
	73.	O	N-A ³	O
	74.	O	N-A ⁴	O
40	75.	O	N-A ⁵	O
	76.	O	N-A ⁶	O
	77.	O	N-A ⁷	O
	78.	O	N-A ⁸	O
	79.	O	N-A ⁹	O
45	80.	O	N-A ¹⁰	O
	81.	O	N-A ¹¹	O
	82.	O	N-A ¹²	O
	83.	O	N-A ¹³	O
	84.	O	N-A ¹⁴	O
50	85.	O	O	N-A ¹
	86.	O	O	N-A ²
	87.	O	O	N-A ³
	88.	O	O	N-A ⁴
	89.	O	O	N-A ⁵
55	90.	O	O	N-A ⁶
	91.	O	O	N-A ⁷
	92.	O	O	N-A ⁸
	93.	O	O	N-A ⁹
	94.	O	O	N-A ¹⁰
60	95.	O	O	N-A ¹¹
	96.	O	O	N-A ¹²
	97.	O	O	N-A ¹³
	98.	O	O	N-A ¹⁴
	99.	O	N-A ¹	B-A ¹
65	100.	O	N-A ²	B-A ¹
	101.	O	N-A ³	B-A ¹
	102.	O	N-A ⁴	B-A ¹
	103.	O	N-A ⁵	B-A ¹
	104.	O	N-A ⁶	B-A ¹
	105.	O	N-A ⁷	B-A ¹
	106.	O	N-A ⁸	B-A ¹
	107.	O	N-A ⁹	B-A ¹
	108.	O	N-A ¹⁰	B-A ¹
	109.	O	N-A ¹¹	B-A ¹
	110.	O	N-A ¹²	B-A ¹
	111.	O	N-A ¹³	B-A ¹
	112.	O	N-A ¹⁴	B-A ¹
	113.	S	O	B-A ¹
	114.	S	O	B-A ²
	115.	S	O	B-A ³
	116.	S	O	B-A ⁴

327

-continued








p	D ¹	D ²	D ³
117.	S	O	B-A ⁵
118.	S	O	B-A ⁶
119.	S	O	B-A ⁷
120.	S	O	B-A ⁸
121.	S	O	B-A ⁹
122.	S	O	B-A ¹⁰
123.	S	O	B-A ¹¹
124.	S	O	B-A ¹²
125.	S	O	B-A ¹³
126.	S	O	B-A ¹⁴
127.	S	B-A ¹	O
128.	S	B-A ²	O
129.	S	B-A ³	O
130.	S	B-A ⁴	O
131.	S	B-A ⁵	O
132.	S	B-A ⁶	O
133.	S	B-A ⁷	O
134.	S	B-A ⁸	O
135.	S	B-A ⁹	O
136.	S	B-A ¹⁰	O
137.	S	B-A ¹¹	O
138.	S	B-A ¹²	O
139.	S	B-A ¹³	O
140.	S	B-A ¹⁴	O
141.	CMe ₂	S	B-A ¹
142.	CMe ₂	S	B-A ²
143.	CMe ₂	S	B-A ³
144.	CMe ₂	S	B-A ⁴
145.	CMe ₂	S	B-A ⁵
146.	CMe ₂	S	B-A ⁶
147.	CMe ₂	S	B-A ⁷
148.	CMe ₂	S	B-A ⁸
149.	CMe ₂	S	B-A ⁹
150.	CMe ₂	S	B-A ¹⁰
151.	CMe ₂	S	B-A ¹¹
152.	CMe ₂	S	B-A ¹²
153.	CMe ₂	S	B-A ¹³
154.	CMe ₂	S	B-A ¹⁴
155.	S	O	B-A ¹
156.	S	O	B-A ²
157.	S	O	B-A ³
158.	S	O	B-A ⁴
159.	S	O	B-A ⁵
160.	S	O	B-A ⁶
161.	S	O	B-A ⁷
162.	S	O	B-A ⁸
163.	S	O	B-A ⁹
164.	S	O	B-A ¹⁰
165.	S	O	B-A ¹¹
166.	S	O	B-A ¹²
167.	S	O	B-A ¹³
168.	S	O	B-A ¹⁴
169.	N-A ¹	O	B-A ¹
170.	N-A ²	O	B-A ¹
171.	N-A ³	O	B-A ¹
172.	N-A ⁴	O	B-A ¹
173.	N-A ⁵	O	B-A ¹
174.	N-A ⁶	O	B-A ¹
175.	N-A ⁷	O	B-A ¹
176.	N-A ⁸	O	B-A ¹
177.	N-A ⁹	O	B-A ¹
178.	N-A ¹⁰	O	B-A ¹
179.	N-A ¹¹	O	B-A ¹
180.	N-A ¹²	O	B-A ¹
181.	N-A ¹³	O	B-A ¹
182.	N-A ¹⁴	O	B-A ¹
183.	SiMe ₂	CMe ₂	CMe ₂
184.	SiMe ₂	CMe ₂	CMe ₂
185.	SiMe ₂	CMe ₂	CMe ₂
186.	SiMe ₂	CMe ₂	CMe ₂
187.	SiMe ₂	CMe ₂	CMe ₂
188.	SiMe ₂	CMe ₂	CMe ₂
189.	SiMe ₂	CMe ₂	CMe ₂
190.	SiMe ₂	CMe ₂	CMe ₂
191.	SiMe ₂	CMe ₂	CMe ₂
192.	SiMe ₂	CMe ₂	CMe ₂
193.	SiMe ₂	CMe ₂	CMe ₂

328

-continued








p	D ¹	D ²	D ³
5	194.	SiMe ₂	CMe ₂
	195.	SiMe ₂	CMe ₂
	196.	SiMe ₂	CMe ₂
10			

wherein, A¹ to A¹⁴ are defined as

15		A ¹
20		A ²
25		A ³
30		A ⁴
35		A ⁵
40		A ⁶
45		A ⁷
50		
55		
60		
65		

329

-continued

**330**

and wherein for the group represented by L_A^{s-u-r} , each L_A^s defines structures defined below:

A⁸


5

L_A^1 , L_A^2 , L_A^3 , and L_A^4 have the structure

10

A⁹

15



wherein,

for L_A^1 , $D^1 = N$, $Z^1 = C$, $Z^2 = N$;for L_A^2 , $D^1 = N$, $Z^1 = N$, $Z^2 = C$;for L_A^3 , $D^1 = B$, $Z^1 = C$, $Z^2 = N$;

and

for L_A^4 , $D^1 = B$, $Z^1 = N$, $Z^2 = C$;

20

A¹⁰


25

L_A^5 , L_A^6 , L_A^7 , and L_A^8 have the structure

30

A¹¹

35

for L_A^5 , $D^1 = N$, $Z^1 = C$, $Z^2 = N$;for L_A^6 , $D^1 = N$, $Z^1 = N$, $Z^2 = C$;for L_A^7 , $D^1 = B$, $Z^1 = C$, $Z^2 = N$;

and

for L_A^8 , $D^1 = B$, $Z^1 = N$, $Z^2 = C$;A¹²


40

L_A^9 , L_A^{10} , L_A^{11} , and L_A^{12} have the structure

45

A¹³

50

for L_A^9 , $D^1 = N$, $Z^1 = C$, $Z^2 = N$;for L_A^{10} , $D^1 = N$, $Z^1 = N$, $Z^2 = C$;for L_A^{11} , $D^1 = B$, $Z^1 = C$, $Z^2 = N$;

and

for L_A^{12} , $D^1 = B$, $Z^1 = N$, $Z^2 = C$;

wherein for each u, D^1 and D^2 are defined as follows:

A¹⁴

60

65

u	D^2	D^3
1.	O	B-A ¹
2.	O	B-A ²
3.	O	B-A ³
4.	O	B-A ⁴
5.	O	B-A ⁵
6.	O	B-A ⁶
7.	O	B-A ⁷
8.	O	B-A ⁸
9.	O	B-A ⁹

331

-continued

u	D ²	D ³
10.	O	B-A ¹⁰
11.	O	B-A ¹¹
12.	O	B-A ¹²
13.	O	B-A ¹³
14.	O	B-A ¹⁴
15.	B-A ¹	O
16.	B-A ²	O
17.	B-A ³	O
18.	B-A ⁴	O
19.	B-A ⁵	O
20.	B-A ⁶	O
21.	B-A ⁷	O
22.	B-A ⁸	O
23.	B-A ⁹	O
24.	B-A ¹⁰	O
25.	B-A ¹¹	O
26.	B-A ¹²	O
27.	B-A ¹³	O
28.	B-A ¹⁴	O
29.	CMe ₂	B-A ¹
30.	CMe ₂	B-A ²
31.	CMe ₂	B-A ³
32.	CMe ₂	B-A ⁴
33.	CMe ₂	B-A ⁵
34.	CMe ₂	B-A ⁶
35.	CMe ₂	B-A ⁷
36.	CMe ₂	B-A ⁸
37.	CMe ₂	B-A ⁹
38.	CMe ₂	B-A ¹⁰
39.	CMe ₂	B-A ¹¹
40.	CMe ₂	B-A ¹²
41.	CMe ₂	B-A ¹³
42.	CMe ₂	B-A ¹⁴
43.	B-A ¹	CMe ₂
44.	B-A ²	CMe ₂
45.	B-A ³	CMe ₂
46.	B-A ⁴	CMe ₂
47.	B-A ⁵	CMe ₂
48.	B-A ⁶	CMe ₂
49.	B-A ⁷	CMe ₂
50.	B-A ⁸	CMe ₂
51.	B-A ⁹	CMe ₂
52.	B-A ¹⁰	CMe ₂
53.	B-A ¹¹	CMe ₂
54.	B-A ¹²	CMe ₂
55.	B-A ¹³	CMe ₂
56.	B-A ¹⁴	CMe ₂
57.	S	B-A ¹
58.	S	B-A ²
59.	S	B-A ³
60.	S	B-A ⁴
61.	S	B-A ⁵
62.	S	B-A ⁶
63.	S	B-A ⁷
64.	S	B-A ⁸
65.	S	B-A ⁹
66.	S	B-A ¹⁰
67.	S	B-A ¹¹
68.	S	B-A ¹²
69.	S	B-A ¹³
70.	S	B-A ¹⁴
71.	N-A ¹	B-A ¹
72.	N-A ¹	B-A ²
73.	N-A ¹	B-A ³
74.	N-A ¹	B-A ⁴
75.	N-A ¹	B-A ⁵
76.	N-A ¹	B-A ⁶
77.	N-A ¹	B-A ⁷
78.	N-A ¹	B-A ⁸
79.	N-A ¹	B-A ⁹
80.	N-A ¹	B-A ¹⁰
81.	N-A ¹	B-A ¹¹
82.	N-A ¹	B-A ¹²
83.	N-A ¹	B-A ¹³
84.	N-A ¹	B-A ¹⁴
85.	O	B-A ¹
86.	O	B-A ²

332

-continued

u	D ²	D ³
87.	O	B-A ³
88.	O	B-A ⁴
89.	O	B-A ⁵
90.	O	B-A ⁶
91.	O	B-A ⁷
92.	O	B-A ⁸
93.	O	B-A ⁹
94.	O	B-A ¹⁰
95.	O	B-A ¹¹
96.	O	B-A ¹²
97.	O	B-A ¹³
98.	O	B-A ¹⁴
99.	N-A ¹	B-A ¹
100.	N-A ²	B-A ¹
101.	N-A ³	B-A ¹
102.	N-A ⁴	B-A ¹
103.	N-A ⁵	B-A ¹
104.	N-A ⁶	B-A ¹
105.	N-A ⁷	B-A ¹
106.	N-A ⁸	B-A ¹
107.	N-A ⁹	B-A ¹
108.	N-A ¹⁰	B-A ¹
109.	N-A ¹¹	B-A ¹
110.	N-A ¹²	B-A ¹
111.	N-A ¹³	B-A ¹
112.	N-A ¹⁴	B-A ¹
113.	N-A ¹	B-A ⁴
114.	N-A ²	B-A ⁴
115.	N-A ³	B-A ⁴
116.	N-A ⁴	B-A ⁴
117.	N-A ⁵	B-A ⁴
118.	N-A ⁶	B-A ⁴
119.	N-A ⁷	B-A ⁴
120.	N-A ⁸	B-A ⁴
121.	N-A ⁹	B-A ⁴
122.	N-A ¹⁰	B-A ⁴
123.	N-A ¹¹	B-A ⁴
124.	N-A ¹²	B-A ⁴
125.	N-A ¹³	B-A ⁴
126.	N-A ¹⁴	B-A ⁴
127.	N-A ¹⁴	B-A ⁵
128.	N-A ¹	B-A ⁵
129.	N-A ²	B-A ⁵
130.	N-A ³	B-A ⁵
131.	N-A ⁴	B-A ⁵
132.	N-A ⁵	B-A ⁵
133.	N-A ⁶	B-A ⁵
134.	N-A ⁷	B-A ⁵
135.	N-A ⁸	B-A ⁵
136.	N-A ⁹	B-A ⁵
137.	N-A ¹⁰	B-A ⁵
138.	N-A ¹¹	B-A ⁵
139.	N-A ¹²	B-A ⁵
140.	N-A ¹³	B-A ⁵
141.	N-A ¹⁴	B-A ⁵

50 wherein for each r in L_{At-p-r} and $L_{A^{S-U-r}}$, X¹ to X⁴, R² and R³ are defined as follows:

r	X ¹	X ²	X ³	X ⁴	R ²	R ³
55	1. CH	CH	CH	CH	—	—
	2. CH	CMe	CH	CH	—	—
	3. CH	CH	CMe	CH	—	—
	4. CH	CH	CH	CMe	—	—
	5. CH	CMe	CMe	CH	—	—
60	6. CH	CH	CH	CH	5,6-H ¹	—
	7. CH	CMe	CH	CH	5,6-H ¹	—
	8. CH	CH	CMe	CH	5,6-H ¹	—
	9. CH	CH	CH	CMe	5,6-H ¹	—
	10. CH	CMe	CMe	CH	5,6-H ¹	—
	11. CH	CH	CH	CH	5,6-H ²	—
	12. CH	CMe	CH	CH	5,6-H ²	—
65	13. CH	CH	CMe	CH	5,6-H ²	—
	14. CH	CH	CH	CMe	5,6-H ²	—

333

-continued

r	X ¹	X ²	X ³	X ⁴	R ²	R ³
15.	CH	CMe	CMe	CH	5,6-H ²	—
16.	CH	CH	CH	CH	5,6-H ³	—
17.	CH	CMe	CH	CH	5,6-H ³	—
18.	CH	CH	CMe	CH	5,6-H ³	—
19.	CH	CH	CH	CMe	5,6-H ³	—
20.	CH	CMe	CMe	CH	5,6-H ³	—
21.	CH	CH	CH	CH	—	9,10-H ¹
22.	CH	CMe	CH	CH	—	9,10-H ¹
23.	CH	CH	CMe	CH	—	9,10-H ¹
24.	CH	CH	CH	CMe	—	9,10-H ¹
25.	CH	CMe	CMe	CH	—	9,10-H ¹
26.	CH	CH	CH	CH	—	9,10-H ¹
27.	CH	CMe	CH	CH	—	9,10-H ¹
28.	CH	CH	CMe	CH	—	9,10-H ¹
29.	CH	CH	CH	CMe	—	9,10-H ¹
30.	CH	CMe	CMe	CH	—	9,10-H ¹
31.	CH	CH	CH	CH	—	9,10-H ¹
32.	CH	CMe	CH	CH	—	9,10-H ¹
33.	CH	CH	CMe	CH	—	9,10-H ¹
34.	CH	CH	CH	CMe	—	9,10-H ¹
35.	CH	CMe	CMe	CH	—	9,10-H ¹
36.	CH	CH	CG ¹	CH	—	—
37.	CH	CH	CG ²	CH	—	—
38.	CH	CH	CG ³	CH	—	—
39.	CH	CH	CG ⁴	CH	—	—
40.	CH	CH	CG ⁵	CH	—	—
41.	CH	CH	CG ⁶	CH	—	—
42.	CH	CH	CG ⁷	CH	—	—
43.	CH	CG ¹	CG ¹	CH	—	—
44.	CH	CG ¹	CG ¹	CH	—	—
45.		E ¹	CH	CH	—	—
46.		E ²	CH	CH	—	—
47.		E ³	CH	CH	—	—
48.		E ⁴	CH	CH	—	—
49.		E ⁵	CH	CH	—	—
50.		E ⁶	CH	CH	—	—
51.		E ¹	CH	CG ¹	—	—
52.		E ²	CH	CG ¹	—	—
53.		E ³	CH	CG ¹	—	—
54.		E ⁴	CH	CG ¹	—	—
55.		E ⁵	CH	CG ¹	—	—
56.		E ⁶	CH	CG ¹	—	—
57.	CH	CH		E ¹	—	—
58.	CH	CH		E ²	—	—
59.	CH	CH		E ³	—	—
60.	CH	CH		E ⁴	—	—
61.	CH	CH		E ⁵	—	—
62.	CH	CH		E ⁶	—	—
63.	CH	CMe		E ¹	—	—
64.	CH	CMe		E ²	—	—
65.	CH	CMe		E ³	—	—
66.	CH	CMe		E ⁴	—	—
67.	CH	CMe		E ⁵	—	—
68.	CH	CMe		E ⁶	—	—
69.	CH	CG ¹		E ¹	—	—
70.	CH	CG ¹		E ²	—	—
71.	CH	CG ¹		E ³	—	—
72.	CH	CG ¹		E ⁴	—	—
73.	CH	CG ¹		E ⁵	—	—
74.	CH	CG ¹		E ⁶	—	—
75.	CH	CH		E ¹	5-Me	—
76.	CH	CH		E ²	5-Me	—
77.	CH	CH		E ³	5-Me	—
78.	CH	CH		E ⁴	5-Me	—
79.	CH	CH		E ⁵	5-Me	—
80.	CH	CH		E ⁶	5-Me	—
81.	CH	CH		E ¹	6-Me	—
82.	CH	CH		E ²	6-Me	—
83.	CH	CH		E ³	6-Me	—
84.	CH	CH		E ⁴	6-Me	—
85.	CH	CH		E ⁵	6-Me	—
86.	CH	CH		E ⁶	6-Me	—
87.	CH	CH	CH	CH	—	7-Me
88.	CH	CH	CH	CH	—	8-Me
89.	CH	CH	CH	CH	—	9-Me
90.	CH	CH	CH	CH	—	10-Me
91.	CH		E ¹	CH	—	—

334

-continued

r	X ¹	X ²	X ³	X ⁴	R ²	R ³
5	92.	CH	E ²	CH	—	—
	93.	CH	E ³	CH	—	—
	94.	CH	E ⁴	CH	—	—
	95.	CH	E ⁵	CH	—	—
	96.	CH	E ⁶	CH	—	—
10	97.	CH	E ¹	CH	—	8,10-Me
	98.	CH	E ²	CH	—	8,10-Me
	99.	CH	E ³	CH	—	8,10-Me
	100.	CH	E ⁴	CH	—	8,10-Me
	101.	CH	E ⁵	CH	—	8,10-Me
	102.	CH	E ⁶	CH	—	8,10-Me
15	103.	N	CH	N	CH	—
	104.	N	CH	CH	CH	—
	105.	CH	N	CH	CH	—
	106.	CH	N	CH	N	—
	107.	CH	CH	N	CH	—
20	108.	CH	CH	N	CMe	—
	109.	CH	CH	N	CG ¹	—
	110.	CH	CMe	N	CH	—, —

wherein E¹ to E⁶, G¹ to G⁷ and H¹ to H³ are defined below

25

30

35

40









45

50

55






60

65


E¹E²E³E⁴E⁵E⁶G¹G²

335

-continued



and

**336**

11. The compound of claim 1, wherein the ligand L_A is selected from the group consisting of the following structures:

 G^3

5

10

 G^4

15

20

 G^5

25

30

 G^6

35

40

 G^7

45

 H^1

50






 H^2

55

 H^3





60

65



337

-continued

**338**

-continued

5

10

15

20

25

30

35

40





45

50

55


60

65




339

-continued





**340**

-continued







341

-continued







342

-continued




343

-continued

**344**


-continued

5




10

15



20

25




30

35

40

45




50

55






60

65



345

-continued

**346**

-continued

5

10

15

20

25

30

35

40





45

50

55





60

65








347

-continued


**348**

-continued




349

-continued


**350**

-continued




351

-continued






**352**

-continued







353

-continued


**354**

-continued



355

-continued



12. The compound of claim 1, wherein the compound has a formula of $M(L_A)_{pp}(L_B)_{qq}(L_C)_{rr}$, wherein L_B and L_C are each a bidentate ligand; and wherein pp is 1, 2, or 3; qq is 0, 1, or 2; rr is 0, 1, or 2; and p+q+r is the oxidation state of the metal M.

13. The compound of claim 10, wherein the compound is selected from the group consisting of:

Compound-A-t-p-r corresponding to each formula $Ir(L_{At-p-r})_3$;

Compound-A-s-u-r corresponding to each formula $Ir(L_A^{s-u-r})_3$;

Compound-B-t-p-r-k corresponding to each formula $Ir(L_{At-p-r})_2(L_{Bk})_2$;

Compound-B-s-u-r-k corresponding to each formula $Ir(L_A^{s-u-r})_2(L_{Bk})_2$;

Compound-B'-t-p-r-k corresponding to each formula $Ir(L_{At-p-r})_2(L_{Bk})$;

Compound-B'-s-u-r-k corresponding to each formula $Ir(L_A^{s-u-r})_2(L_{Bk})$;

Compound-C-t-p-r-j-I corresponding to each formula $Ir(L_{At-p-r})_2(L_{Cj-I})$;

Compound-C-s-u-r-j-I corresponding to each formula $Ir(L_A^{s-u-r})_2(L_{Cj-I})$;


Compound-C-t-p-r-j-II corresponding to each formula $Ir(L_{At-p-r})_2(L_{Cj-II})$;

Compound-C-s-u-r-j-I corresponding to each formula $Ir(L_A^{s-u-r})_2(L_{Cj-I})$;

wherein k is an integer between 1 and 324;







j is an integer from 1 to 1416);

wherein L_{B1} to L_{B324} have the structures as defined as follows:









356

-continued









357

-continued

**358**

-continued

L_{B8}

5

10

L_{B9}

15

20

25

L_{B10}

30

35

L_{B11}

40

45

L_{B12}

50

55

L_{B13}






60

65






L_{B14}L_{B15}L_{B16}L_{B17}L_{B18}L_{B19}

359

-continued

**360**

-continued

 L_{B20}

5

10

15

 L_{B21}

20

25

 L_{B22}

30

35

40

 L_{B23}

45

50

55

 L_{B24}







60

65







 L_{B25} L_{B26} L_{B27} L_{B28} L_{B29}

361

-continued

**362**

-continued

 L_{B30}

5

10

 L_{B31}

15

20

 L_{B32}

25

30

 L_{B33}

35

40

45

 L_{B34}

50

55

 L_{B35}







60

65

 L_{B36} L_{B37} L_{B38} L_{B39} L_{B40} L_{B41}

363

-continued

L_{B42}

5

10

L_{B43}

15

20

L_{B44} 25

30

L_{B45} 35

40

45

L_{B46}

50

55







L_{B47}

60

65







364

-continued

L_{B48}L_{B49}L_{B50}L_{B51}L_{B52}L_{B53}

365

-continued

L_{B54}

5

10

L_{B55}

15

20

L_{B56}

25

30

35

L_{B57}

40

45

L_{B58}

50

55







L_{B59}

60

65







366

-continued






L_{B60}L_{B61}L_{B62}L_{B63}L_{B64}L_{B65}

367

-continued

**368**

-continued

L_{B66}

5

10

L_{B67}

15

20

L_{B68} 25

30

L_{B69} 35

40

L_{B70} 45

50

55

L_{B71}






60

65






L_{B72}L_{B73}L_{B74}L_{B75}L_{B76}

369

-continued

**370**

-continued

L_{B77}

5

10

15

L_{B78}

20

25

L_{B79}

35

40

L_{B80}

45

50

L_{B81}







60

65







L_{B82}L_{B83}L_{B84}L_{B85}L_{B86}L_{B87}

371

-continued

**372**

-continued

 L_{B88}

5

10

 L_{B89}

15

20

 L_{B90}

25

30

35

 L_{B91}

40

45

 L_{B92}

50

55

 L_{B93}







60

65

 L_{B94} L_{B95} L_{B96} L_{B97} L_{B98} L_{B99}

373

-continued



LB100

5

10

LB101

15

20

LB102

25

30

LB103

35

40

LB104

45

50

LB105






55

60

65

374

-continued



LB106

LB107






LB108

LB109






LB110

375

-continued

**376**

-continued

 L_{B111}

5

10

 L_{B112}

15

20

25

 L_{B113}

30

35

 L_{B114}

40

45

50

 L_{B115}

55






60

65





 L_{B116} L_{B117} L_{B118} L_{B119} L_{B120}

377

-continued

**378**

-continued

 L_{B121}

5

10

 L_{B122}

15

20

25

 L_{B123}

30

35

40

 L_{B124}

45

50

 L_{B125}

55





60

65





 L_{B126} L_{B127} L_{B128} L_{B129}

379

-continued

**380**

-continued

 L_{B130}

5

10

15

 L_{B131}

20

25

30

35

 L_{B132}

40

45

50

 L_{B133}

55






60

65





 L_{B134} L_{B135} L_{B136} L_{B137}

381

-continued

**382**

-continued



LB138

5

10

LB139

15

20

25

LB140

30

35

40

LB141

45

50

LB142

55

60

65

LB143






LB144

LB145






LB146

383

-continued

**384**

-continued



LB147

5

10

LB148

15

20

25

LB149

30

35

40

LB150

45

50

LB151

55

60

65

LB152

LB153


LB154

LB155

LB156

385

-continued



LB157


5

10

15

386

-continued



LB161



LB158

20

25

30

35





LB162

LB159

40

45

50





LB163

LB160

55

60






65







LB164

387

-continued

**388**

-continued



LB165

5

10

15

LB166

20

25

LB167

30

35

LB168

40

45

50

LB169

55

60

65

LB170


LB171

LB172

LB173

389

-continued

 L_{B174}


5

10

15

390



-continued

 L_{B178} L_{B175}

20

25

30

 L_{B179}



35

 L_{B176}

40

45



50

 L_{B180} L_{B177}

55


60

65

 L_{B181}

391

-continued

L_{B182}

5

10

15

L_{B183} 20

25

30

35

L_{B184}

40

45




50

L_{B185}






55

60

65






**392**

-continued






L_{B186}L_{B187}L_{B188}L_{B189}L_{B190}

393

-continued

**394**

-continued

L_{B191}

5

10

15

L_{B192}

20

25

30

L_{B193}

35

40

L_{B194}

45

50

55

L_{B195}






60

65





L_{B196}L_{B197}L_{B198}L_{B199}L_{B200}

395

-continued

**396**

-continued

L_{B201}

5

10

L_{B202} 15

20

25

L_{B203} 30

35

40

L_{B204}

45

50

L_{B205} 55





60

65





L_{B206}L_{B207}L_{B208}L_{B209}

397

-continued

**398**

-continued

L_{B210}

5

10

15

L_{B211} 20

25

30

35

L_{B212}

40

45

50

L_{B213}

55





60

65





L_{B214}L_{B215}L_{B216}L_{B217}

399

-continued

**400**

-continued

L_{B218}

5

10

15

L_{B219}

20

25

30

L_{B220}

35

40

45

50

L_{B221}

55





60

65





L_{B222}L_{B223}L_{B224}L_{B225}

401

-continued

**402**

-continued

L_{B226}

5

10

15

L_{B227}

20

25

30

L_{B228}

35

40

45

50

L_{B229}

55






60

65

L_{B230}L_{B231}L_{B232}L_{B233}





403

-continued



404

-continued



L_{B234}

5

10

L_{B235}

15

20

25

L_{B236}

30

35

40

L_{B237}

45

50

L_{B238}

55

60

65

L_{B239}





L_{B240}

L_{B241}





L_{B242}

405

-continued

**406**

-continued

L_{B243}

5

10

15

L_{B244}

20

25

30

L_{B245}

35

40

45

50

L_{B246}

55





60

65





L_{B247}L_{B248}L_{B249}L_{B250}

407

-continued

**408**

-continued

L_{B251}

5

10

15

L_{B252}

20

25

30

35

L_{B253}

40

45

50

L_{B254}

55


60

65

L_{B255}L_{B256}L_{B257}L_{B258}

409

-continued

L_{B259}


5

10

15

410


-continued

L_{B263}L_{B260} 20

25

30

35

L_{B261}

40






45

L_{B262}

55




60

65

L_{B264}L_{B265}L_{B266}

411

-continued

**412**

-continued

L_{B267}

5

10

15

20

L_{B268}

25

30

35

40

45





L_{B269}

50

55






60

65





L_{B270}L_{B270}L_{B271}L_{B272}

413

-continued

**414**

-continued

L_{B273}

5

10

15

L_{B274}

20

25

L_{B275}

30

35

L_{B276}

40

45

50

L_{B277}

55





60

65





L_{B278}L_{B279}L_{B280}L_{B281}

415

-continued

**416**

-continued



LB282

5

10

15

LB283

20

25

30

35

LB284

40

45

50

LB285

55

60

65

LB286





LB287

LB288





LB289

417

-continued

**418**

-continued



LB290

5

10

15

LB291

20

25

30

LB292

35

40

45

50

LB293

55

60

65

LB294





LB295

LB296





LB297

419

-continued

**420**

-continued



LB298

5

10

15

20

LB299

25

30

35

LB300

40

45

50

LB301

55

60

65

LB302





LB303

LB304

LB305

421

-continued

**422**


-continued

LB306

5

10

15



LB310


LB307

20

25

30

35




LB311

LB308

40

45

50




LB312

LB309

55

60





65







LB313

423

-continued

**424**

-continued

 L_{B314}

5

10

15

 L_{B315}

20

25

30

35

 L_{B316}

40

45

 L_{B317}

55




60

65

 L_{B318} L_{B319} L_{B320} L_{B321}


425

-continued




wherein,

L_{C1-I} - $L_{C1416-I}$ have the general structure of



L_{C1-H} - $L_{C1416-H}$ have the general structure of



426

wherein R^{201} and R^{202} for L_{Cj-I} and L_{Cj-II} are each independently defined as follows:

L_{B322}		L_{Cj}	R^{201}	R^{202}
5		L_{C1}	R^{D1}	R^{D1}
		L_{C2}	R^{D2}	R^{D2}
		L_{C3}	R^{D3}	R^{D3}
		L_{C4}	R^{D4}	R^{D4}
10		L_{C5}	R^{D5}	R^{D5}
		L_{C6}	R^{D6}	R^{D6}
		L_{C7}	R^{D7}	R^{D7}
		L_{C8}	R^{D8}	R^{D8}
		L_{C9}	R^{D9}	R^{D9}
		L_{C10}	R^{D10}	R^{D10}
15	L_{B323}	L_{C11}	R^{D11}	R^{D11}
		L_{C12}	R^{D12}	R^{D12}
		L_{C13}	R^{D13}	R^{D13}
		L_{C14}	R^{D14}	R^{D14}
		L_{C15}	R^{D15}	R^{D15}
		L_{C16}	R^{D16}	R^{D16}
		L_{C17}	R^{D17}	R^{D17}
20		L_{C18}	R^{D18}	R^{D18}
		L_{C19}	R^{D19}	R^{D19}
		L_{C20}	R^{D20}	R^{D20}
		L_{C21}	R^{D21}	R^{D21}
		L_{C22}	R^{D22}	R^{D22}
		L_{C23}	R^{D23}	R^{D23}
25		L_{C24}	R^{D24}	R^{D24}
		L_{C25}	R^{D25}	R^{D25}
		L_{C26}	R^{D26}	R^{D26}
		L_{C27}	R^{D27}	R^{D27}
		L_{C28}	R^{D28}	R^{D28}
		L_{C29}	R^{D29}	R^{D29}
30	L_{B324}	L_{C30}	R^{D30}	R^{D30}
		L_{C31}	R^{D31}	R^{D31}
		L_{C32}	R^{D32}	R^{D32}
		L_{C33}	R^{D33}	R^{D33}
		L_{C34}	R^{D34}	R^{D34}
		L_{C35}	R^{D35}	R^{D35}
		L_{C36}	R^{D36}	R^{D36}
35		L_{C37}	R^{D37}	R^{D37}
		L_{C38}	R^{D38}	R^{D38}
		L_{C39}	R^{D39}	R^{D39}
		L_{C40}	R^{D40}	R^{D40}
		L_{C41}	R^{D41}	R^{D41}
		L_{C42}	R^{D42}	R^{D42}
40		L_{C43}	R^{D43}	R^{D43}
		L_{C44}	R^{D44}	R^{D44}
		L_{C45}	R^{D45}	R^{D45}
		L_{C46}	R^{D46}	R^{D46}
		L_{C47}	R^{D47}	R^{D47}
		L_{C48}	R^{D48}	R^{D48}
45		L_{C49}	R^{D49}	R^{D49}
		L_{C50}	R^{D50}	R^{D50}
		L_{C51}	R^{D51}	R^{D51}
		L_{C52}	R^{D52}	R^{D52}
		L_{C53}	R^{D53}	R^{D53}
		L_{C54}	R^{D54}	R^{D54}
50		L_{C55}	R^{D55}	R^{D55}
		L_{C56}	R^{D56}	R^{D56}
		L_{C57}	R^{D57}	R^{D57}
		L_{C58}	R^{D58}	R^{D58}
		L_{C59}	R^{D59}	R^{D59}
		L_{C60}	R^{D60}	R^{D60}
55		L_{C61}	R^{D61}	R^{D61}
		L_{C62}	R^{D62}	R^{D62}
		L_{C63}	R^{D63}	R^{D63}
		L_{C64}	R^{D64}	R^{D64}
		L_{C65}	R^{D65}	R^{D65}
		L_{C66}	R^{D66}	R^{D66}
		L_{C67}	R^{D67}	R^{D67}
60		L_{C68}	R^{D68}	R^{D68}
		L_{C69}	R^{D69}	R^{D69}
		L_{C70}	R^{D70}	R^{D70}
		L_{C71}	R^{D71}	R^{D71}
		L_{C72}	R^{D72}	R^{D72}
		L_{C73}	R^{D73}	R^{D73}
65		L_{C74}	R^{D74}	R^{D74}
		L_{C75}	R^{D75}	R^{D75}

427

-continued

L ^{C76}	R ^{D76}	R ^{D76}	
L ^{C77}	R ^{D77}	R ^{D77}	
L ^{C78}	R ^{D78}	R ^{D78}	
L ^{C79}	R ^{D79}	R ^{D79}	5
L ^{C80}	R ^{D80}	R ^{D80}	
L ^{C81}	R ^{D81}	R ^{D81}	
L ^{C82}	R ^{D82}	R ^{D82}	
L ^{C83}	R ^{D83}	R ^{D83}	
L ^{C84}	R ^{D84}	R ^{D84}	
L ^{C85}	R ^{D85}	R ^{D85}	10
L ^{C86}	R ^{D86}	R ^{D86}	
L ^{C87}	R ^{D87}	R ^{D87}	
L ^{C88}	R ^{D88}	R ^{D88}	
L ^{C89}	R ^{D89}	R ^{D89}	
L ^{C90}	R ^{D90}	R ^{D90}	
L ^{C91}	R ^{D91}	R ^{D91}	15
L ^{C92}	R ^{D92}	R ^{D92}	
L ^{C93}	R ^{D93}	R ^{D93}	
L ^{C94}	R ^{D94}	R ^{D94}	
L ^{C95}	R ^{D95}	R ^{D95}	
L ^{C96}	R ^{D96}	R ^{D96}	
L ^{C97}	R ^{D97}	R ^{D97}	20
L ^{C98}	R ^{D98}	R ^{D98}	
L ^{C99}	R ^{D99}	R ^{D99}	
L ^{C100}	R ^{D100}	R ^{D100}	
L ^{C101}	R ^{D101}	R ^{D101}	
L ^{C102}	R ^{D102}	R ^{D102}	
L ^{C103}	R ^{D103}	R ^{D103}	
L ^{C104}	R ^{D104}	R ^{D104}	25
L ^{C105}	R ^{D105}	R ^{D105}	
L ^{C106}	R ^{D106}	R ^{D106}	
L ^{C107}	R ^{D107}	R ^{D107}	
L ^{C108}	R ^{D108}	R ^{D108}	
L ^{C109}	R ^{D109}	R ^{D109}	
L ^{C110}	R ^{D110}	R ^{D110}	30
L ^{C111}	R ^{D111}	R ^{D111}	
L ^{C112}	R ^{D112}	R ^{D112}	
L ^{C113}	R ^{D113}	R ^{D113}	
L ^{C114}	R ^{D114}	R ^{D114}	
L ^{C115}	R ^{D115}	R ^{D115}	
L ^{C116}	R ^{D116}	R ^{D116}	35
L ^{C117}	R ^{D117}	R ^{D117}	
L ^{C118}	R ^{D118}	R ^{D118}	
L ^{C119}	R ^{D119}	R ^{D119}	
L ^{C120}	R ^{D120}	R ^{D120}	
L ^{C121}	R ^{D121}	R ^{D121}	
L ^{C122}	R ^{D122}	R ^{D122}	40
L ^{C123}	R ^{D123}	R ^{D123}	
L ^{C124}	R ^{D124}	R ^{D124}	
L ^{C125}	R ^{D125}	R ^{D125}	
L ^{C126}	R ^{D126}	R ^{D126}	
L ^{C127}	R ^{D127}	R ^{D127}	
L ^{C128}	R ^{D128}	R ^{D128}	45
L ^{C129}	R ^{D129}	R ^{D129}	
L ^{C130}	R ^{D130}	R ^{D130}	
L ^{C131}	R ^{D131}	R ^{D131}	
L ^{C132}	R ^{D132}	R ^{D132}	
L ^{C133}	R ^{D133}	R ^{D133}	
L ^{C134}	R ^{D134}	R ^{D134}	
L ^{C135}	R ^{D135}	R ^{D135}	50
L ^{C136}	R ^{D136}	R ^{D136}	
L ^{C137}	R ^{D137}	R ^{D137}	
L ^{C138}	R ^{D138}	R ^{D138}	
L ^{C139}	R ^{D139}	R ^{D139}	
L ^{C140}	R ^{D140}	R ^{D140}	
L ^{C141}	R ^{D141}	R ^{D141}	55
L ^{C142}	R ^{D142}	R ^{D142}	
L ^{C143}	R ^{D143}	R ^{D143}	
L ^{C144}	R ^{D144}	R ^{D144}	
L ^{C145}	R ^{D145}	R ^{D145}	
L ^{C146}	R ^{D146}	R ^{D146}	
L ^{C147}	R ^{D147}	R ^{D147}	60
L ^{C148}	R ^{D148}	R ^{D148}	
L ^{C149}	R ^{D149}	R ^{D149}	
L ^{C150}	R ^{D150}	R ^{D150}	
L ^{C151}	R ^{D151}	R ^{D151}	
L ^{C152}	R ^{D152}	R ^{D152}	
L ^{C153}	R ^{D153}	R ^{D153}	65
L ^{C154}	R ^{D154}	R ^{D154}	

428

-continued

L ^{C155}	R ^{D155}	R ^{D155}
L ^{C156}	R ^{D156}	R ^{D156}
L ^{C157}	R ^{D157}	R ^{D157}
L ^{C158}	R ^{D158}	R ^{D158}
L ^{C159}	R ^{D159}	R ^{D159}
L ^{C160}	R ^{D160}	R ^{D160}
L ^{C161}	R ^{D161}	R ^{D161}
L ^{C162}	R ^{D162}	R ^{D162}
L ^{C163}	R ^{D163}	R ^{D163}
L ^{C164}	R ^{D164}	R ^{D164}
L ^{C165}	R ^{D165}	R ^{D165}
L ^{C166}	R ^{D166}	R ^{D166}
L ^{C167}	R ^{D167}	R ^{D167}
L ^{C168}	R ^{D168}	R ^{D168}
L ^{C169}	R ^{D169}	R ^{D169}
L ^{C170}	R ^{D170}	R ^{D170}
L ^{C171}	R ^{D171}	R ^{D171}
L ^{C172}	R ^{D172}	R ^{D172}
L ^{C173}	R ^{D173}	R ^{D173}
L ^{C174}	R ^{D174}	R ^{D174}
L ^{C175}	R ^{D175}	R ^{D175}
L ^{C176}	R ^{D176}	R ^{D176}
L ^{C177}	R ^{D177}	R ^{D177}
L ^{C178}	R ^{D178}	R ^{D178}
L ^{C179}	R ^{D179}	R ^{D179}
L ^{C180}	R ^{D180}	R ^{D180}
L ^{C181}	R ^{D181}	R ^{D181}
L ^{C182}	R ^{D182}	R ^{D182}
L ^{C183}	R ^{D183}	R ^{D183}
L ^{C184}	R ^{D184}	R ^{D184}
L ^{C185}	R ^{D185}	R ^{D185}
L ^{C186}	R ^{D186}	R ^{D186}
L ^{C187}	R ^{D187}	R ^{D187}
L ^{C188}	R ^{D188}	R ^{D188}
L ^{C189}	R ^{D189}	R ^{D189}
L ^{C190}	R ^{D190}	R ^{D190}
L ^{C191}	R ^{D191}	R ^{D191}
L ^{C192}	R ^{D192}	R ^{D192}
L ^{C193}	R ^{D193}	R ^{D193}
L ^{C194}	R ^{D194}	R ^{D194}
L ^{C195}	R ^{D195}	R ^{D195}
L ^{C196}	R ^{D196}	R ^{D196}
L ^{C197}	R ^{D197}	R ^{D197}
L ^{C198}	R ^{D198}	R ^{D198}
L ^{C199}	R ^{D199}	R ^{D199}
L ^{C200}	R ^{D200}	R ^{D200}
L ^{C201}	R ^{D201}	R ^{D201}
L ^{C202}	R ^{D202}	R ^{D202}
L ^{C203}	R ^{D203}	R ^{D203}
L ^{C204}	R ^{D204}	R ^{D204}
L ^{C205}	R ^{D205}	R ^{D205}
L ^{C206}	R ^{D206}	R ^{D206}
L ^{C207}	R ^{D207}	R ^{D207}
L ^{C208}	R ^{D208}	R ^{D208}
L ^{C209}	R ^{D209}	R ^{D209}
L ^{C210}	R ^{D210}	R ^{D210}
L ^{C211}	R ^{D211}	R ^{D211}
L ^{C212}	R ^{D212}	R ^{D212}
L ^{C213}	R ^{D213}	R ^{D213}
L ^{C214}	R ^{D214}	R ^{D214}
L ^{C215}	R ^{D215}	R ^{D215}
L ^{C216}	R ^{D216}	R ^{D216}
L ^{C217}	R ^{D217}	R ^{D217}
L ^{C218}	R ^{D218}	R ^{D218}
L ^{C219}	R ^{D219}	R ^{D219}
L ^{C220}	R ^{D220}	R ^{D220}
L ^{C221}	R ^{D221}	R ^{D221}
L ^{C222}	R ^{D222}	R ^{D222}
L ^{C223}	R ^{D223}	R ^{D223}
L ^{C224}	R ^{D224}	R ^{D224}
L ^{C225}	R ^{D225}	R ^{D225}
L ^{C226}	R ^{D226}	R ^{D226}
L ^{C227}	R ^{D227}	R ^{D227}
L ^{C228}	R ^{D228}	R ^{D228}
L ^{C229}	R ^{D229}	R ^{D229}
L ^{C230}	R ^{D230}	R ^{D230}
L ^{C231}	R ^{D231}	R ^{D231}
L ^{C232}	R ^{D232}	R ^{D232}
L ^{C233}	R ^{D233}	R ^{D233}

429

-continued

L _{C810}	R ^{D234}	R ^{D234}	
L _{C811}	R ^{D235}	R ^{D235}	
L _{C812}	R ^{D236}	R ^{D236}	
L _{C813}	R ^{D237}	R ^{D237}	5
L _{C814}	R ^{D238}	R ^{D238}	
L _{C815}	R ^{D239}	R ^{D239}	
L _{C816}	R ^{D240}	R ^{D240}	
L _{C817}	R ^{D241}	R ^{D241}	
L _{C818}	R ^{D242}	R ^{D242}	
L _{C819}	R ^{D243}	R ^{D243}	10
L _{C820}	R ^{D244}	R ^{D244}	
L _{C821}	R ^{D245}	R ^{D245}	
L _{C822}	R ^{D246}	R ^{D246}	
L _{C823}	R ^{D17}	R ^{D193}	
L _{C824}	R ^{D17}	R ^{D194}	
L _{C825}	R ^{D17}	R ^{D195}	15
L _{C826}	R ^{D17}	R ^{D196}	
L _{C827}	R ^{D17}	R ^{D197}	
L _{C828}	R ^{D17}	R ^{D198}	
L _{C829}	R ^{D17}	R ^{D199}	
L _{C830}	R ^{D17}	R ^{D200}	
L _{C831}	R ^{D17}	R ^{D201}	20
L _{C832}	R ^{D17}	R ^{D202}	
L _{C833}	R ^{D17}	R ^{D203}	
L _{C834}	R ^{D17}	R ^{D204}	
L _{C835}	R ^{D17}	R ^{D205}	
L _{C836}	R ^{D17}	R ^{D206}	
L _{C837}	R ^{D17}	R ^{D207}	25
L _{C838}	R ^{D17}	R ^{D208}	
L _{C839}	R ^{D17}	R ^{D209}	
L _{C840}	R ^{D17}	R ^{D210}	
L _{C841}	R ^{D17}	R ^{D211}	
L _{C842}	R ^{D17}	R ^{D212}	
L _{C843}	R ^{D17}	R ^{D213}	30
L _{C844}	R ^{D17}	R ^{D214}	
L _{C845}	R ^{D17}	R ^{D215}	
L _{C846}	R ^{D17}	R ^{D216}	
L _{C847}	R ^{D17}	R ^{D217}	
L _{C848}	R ^{D17}	R ^{D218}	
L _{C849}	R ^{D17}	R ^{D219}	
L _{C850}	R ^{D17}	R ^{D220}	35
L _{C851}	R ^{D17}	R ^{D221}	
L _{C852}	R ^{D17}	R ^{D222}	
L _{C853}	R ^{D17}	R ^{D223}	
L _{C854}	R ^{D17}	R ^{D224}	
L _{C855}	R ^{D17}	R ^{D225}	40
L _{C856}	R ^{D17}	R ^{D226}	
L _{C857}	R ^{D17}	R ^{D227}	
L _{C858}	R ^{D17}	R ^{D228}	
L _{C859}	R ^{D17}	R ^{D229}	
L _{C860}	R ^{D17}	R ^{D230}	
L _{C861}	R ^{D17}	R ^{D231}	
L _{C862}	R ^{D17}	R ^{D232}	45
L _{C863}	R ^{D17}	R ^{D233}	
L _{C864}	R ^{D17}	R ^{D234}	
L _{C865}	R ^{D17}	R ^{D235}	
L _{C866}	R ^{D17}	R ^{D236}	
L _{C867}	R ^{D17}	R ^{D237}	
L _{C868}	R ^{D17}	R ^{D238}	
L _{C869}	R ^{D17}	R ^{D239}	50
L _{C870}	R ^{D17}	R ^{D240}	
L _{C871}	R ^{D17}	R ^{D241}	
L _{C872}	R ^{D17}	R ^{D242}	
L _{C873}	R ^{D17}	R ^{D243}	
L _{C874}	R ^{D17}	R ^{D244}	
L _{C875}	R ^{D17}	R ^{D245}	55
L _{C876}	R ^{D17}	R ^{D246}	
L _{C1201}	R ^{D10}	R ^{D193}	
L _{C1202}	R ^{D10}	R ^{D194}	
L _{C1203}	R ^{D10}	R ^{D195}	
L _{C1204}	R ^{D10}	R ^{D196}	
L _{C1205}	R ^{D10}	R ^{D197}	60
L _{C1206}	R ^{D10}	R ^{D198}	
L _{C1207}	R ^{D10}	R ^{D199}	
L _{C1208}	R ^{D10}	R ^{D200}	
L _{C1209}	R ^{D10}	R ^{D201}	
L _{C1210}	R ^{D10}	R ^{D202}	
L _{C1211}	R ^{D10}	R ^{D203}	65
L _{C1212}	R ^{D10}	R ^{D204}	

430

-continued

L _{C1213}	R ^{D10}	R ^{D205}
L _{C1214}	R ^{D10}	R ^{D206}
L _{C1215}	R ^{D10}	R ^{D207}
L _{C1216}	R ^{D10}	R ^{D208}
L _{C1217}	R ^{D10}	R ^{D209}
L _{C1218}	R ^{D10}	R ^{D210}
L _{C1219}	R ^{D10}	R ^{D211}
L _{C1220}	R ^{D10}	R ^{D212}
L _{C1221}	R ^{D10}	R ^{D213}
L _{C1222}	R ^{D10}	R ^{D214}
L _{C1223}	R ^{D10}	R ^{D215}
L _{C1224}	R ^{D10}	R ^{D216}
L _{C1225}	R ^{D10}	R ^{D217}
L _{C1226}	R ^{D10}	R ^{D218}
L _{C1227}	R ^{D10}	R ^{D219}
L _{C1228}	R ^{D10}	R ^{D220}
L _{C1229}	R ^{D10}	R ^{D221}
L _{C1230}	R ^{D10}	R ^{D222}
L _{C1231}	R ^{D10}	R ^{D223}
L _{C1232}	R ^{D10}	R ^{D224}
L _{C1233}	R ^{D10}	R ^{D225}
L _{C1234}	R ^{D10}	R ^{D226}
L _{C1235}	R ^{D10}	R ^{D227}
L _{C1236}	R ^{D10}	R ^{D228}
L _{C1237}	R ^{D10}	R ^{D229}
L _{C1238}	R ^{D10}	R ^{D230}
L _{C1239}	R ^{D10}	R ^{D231}
L _{C1240}	R ^{D10}	R ^{D232}
L _{C1241}	R ^{D10}	R ^{D233}
L _{C1242}	R ^{D10}	R ^{D234}
L _{C1243}	R ^{D10}	R ^{D235}
L _{C1244}	R ^{D10}	R ^{D236}
L _{C1245}	R ^{D10}	R ^{D237}
L _{C1246}	R ^{D10}	R ^{D238}
L _{C1247}	R ^{D10}	R ^{D239}
L _{C1248}	R ^{D10}	R ^{D240}
L _{C1249}	R ^{D10}	R ^{D241}
L _{C1250}	R ^{D10}	R ^{D242}
L _{C1251}	R ^{D10}	R ^{D243}
L _{C1252}	R ^{D10}	R ^{D244}
L _{C1253}	R ^{D10}	R ^{D245}
L _{C1254}	R ^{D10}	R ^{D246}
L _{Cj}	R ²⁰¹	R ²⁰²
L _{C193}	R ^{D1}	R ^{D3}
L _{C194}	R ^{D1}	R ^{D4}
L _{C195}	R ^{D1}	R ^{D5}
L _{C196}	R ^{D1}	R ^{D9}
L _{C197}	R ^{D1}	R ^{D10}
L _{C198}	R ^{D1}	R ^{D17}
L _{C199}	R ^{D1}	R ^{D18}
L _{C200}	R ^{D1}	R ^{D20}
L _{C201}	R ^{D1}	R ^{D22}
L _{C202}	R ^{D1}	R ^{D37}
L _{C203}	R ^{D1}	R ^{D40}
L _{C204}	R ^{D1}	R ^{D41}
L _{C205}	R ^{D1}	R ^{D42}
L _{C206}	R ^{D1}	R ^{D43}
L _{C207}	R ^{D1}	R ^{D48}
L _{C208}	R ^{D1}	R ^{D49}
L _{C209}	R ^{D1}	R ^{D50}
L _{C210}	R ^{D1}	R ^{D54}
L _{C211}	R ^{D1}	R ^{D55}
L _{C212}	R ^{D1}	R ^{D58}
L _{C213}	R ^{D1}	R ^{D59}
L _{C214}	R ^{D1}	R ^{D78}
L _{C215}	R ^{D1}	R ^{D79}
L _{C216}	R ^{D1}	R ^{D81}
L _{C217}	R ^{D1}	R ^{D87}
L _{C218}	R ^{D1}	R ^{D88}
L _{C219}	R ^{D1}	R ^{D89}
L _{C220}	R ^{D1}	R ^{D93}
L _{C221}	R ^{D1}	R ^{D116}
L _{C222}	R ^{D1}	R ^{D117}
L _{C223}	R ^{D1}	R ^{D118}
L _{C224}	R ^{D1}	R ^{D119}
L _{C225}	R ^{D1}	R ^{D120}
L _{C226}	R ^{D1}	R ^{D133}

431

-continued

L _{C227}	R ^{D1}	R ^{D134}	
L _{C228}	R ^{D1}	R ^{D135}	
L _{C229}	R ^{D1}	R ^{D136}	
L _{C230}	R ^{D1}	R ^{D143}	5
L _{C231}	R ^{D1}	R ^{D144}	
L _{C232}	R ^{D1}	R ^{D145}	
L _{C233}	R ^{D1}	R ^{D146}	
L _{C234}	R ^{D1}	R ^{D147}	
L _{C235}	R ^{D1}	R ^{D149}	
L _{C236}	R ^{D1}	R ^{D151}	10
L _{C237}	R ^{D1}	R ^{D154}	
L _{C238}	R ^{D1}	R ^{D155}	
L _{C239}	R ^{D1}	R ^{D161}	
L _{C240}	R ^{D1}	R ^{D175}	
L _{C241}	R ^{D4}	R ^{D3}	
L _{C242}	R ^{D4}	R ^{D5}	15
L _{C243}	R ^{D4}	R ^{D9}	
L _{C244}	R ^{D4}	R ^{D10}	
L _{C245}	R ^{D4}	R ^{D17}	
L _{C246}	R ^{D4}	R ^{D18}	
L _{C247}	R ^{D4}	R ^{D20}	
L _{C248}	R ^{D4}	R ^{D22}	
L _{C249}	R ^{D4}	R ^{D37}	20
L _{C250}	R ^{D4}	R ^{D40}	
L _{C251}	R ^{D4}	R ^{D41}	
L _{C252}	R ^{D4}	R ^{D42}	
L _{C253}	R ^{D4}	R ^{D43}	
L _{C254}	R ^{D4}	R ^{D48}	
L _{C255}	R ^{D4}	R ^{D49}	25
L _{C256}	R ^{D4}	R ^{D50}	
L _{C257}	R ^{D4}	R ^{D54}	
L _{C258}	R ^{D4}	R ^{D55}	
L _{C259}	R ^{D4}	R ^{D58}	
L _{C260}	R ^{D4}	R ^{D59}	
L _{C261}	R ^{D4}	R ^{D78}	30
L _{C262}	R ^{D4}	R ^{D79}	
L _{C263}	R ^{D4}	R ^{D81}	
L _{C264}	R ^{D4}	R ^{D87}	
L _{C265}	R ^{D4}	R ^{D88}	
L _{C266}	R ^{D4}	R ^{D89}	
L _{C267}	R ^{D4}	R ^{D93}	35
L _{C268}	R ^{D4}	R ^{D116}	
L _{C269}	R ^{D4}	R ^{D117}	
L _{C270}	R ^{D4}	R ^{D118}	
L _{C271}	R ^{D4}	R ^{D119}	
L _{C272}	R ^{D4}	R ^{D120}	
L _{C273}	R ^{D4}	R ^{D133}	40
L _{C274}	R ^{D4}	R ^{D134}	
L _{C275}	R ^{D4}	R ^{D135}	
L _{C276}	R ^{D4}	R ^{D136}	
L _{C277}	R ^{D4}	R ^{D143}	
L _{C278}	R ^{D4}	R ^{D144}	
L _{C279}	R ^{D4}	R ^{D145}	
L _{C280}	R ^{D4}	R ^{D146}	45
L _{C281}	R ^{D4}	R ^{D147}	
L _{C282}	R ^{D4}	R ^{D149}	
L _{C283}	R ^{D4}	R ^{D151}	
L _{C284}	R ^{D4}	R ^{D154}	
L _{C285}	R ^{D4}	R ^{D155}	
L _{C286}	R ^{D4}	R ^{D161}	50
L _{C287}	R ^{D4}	R ^{D175}	
L _{C288}	R ^{D9}	R ^{D3}	
L _{C289}	R ^{D9}	R ^{D5}	
L _{C290}	R ^{D9}	R ^{D10}	
L _{C291}	R ^{D9}	R ^{D17}	
L _{C292}	R ^{D9}	R ^{D18}	55
L _{C293}	R ^{D9}	R ^{D20}	
L _{C294}	R ^{D9}	R ^{D22}	
L _{C295}	R ^{D9}	R ^{D37}	
L _{C296}	R ^{D9}	R ^{D40}	
L _{C297}	R ^{D9}	R ^{D41}	
L _{C298}	R ^{D9}	R ^{D42}	60
L _{C299}	R ^{D9}	R ^{D43}	
L _{C300}	R ^{D9}	R ^{D48}	
L _{C301}	R ^{D9}	R ^{D49}	
L _{C302}	R ^{D9}	R ^{D50}	
L _{C303}	R ^{D9}	R ^{D54}	
L _{C304}	R ^{D9}	R ^{D55}	65
L _{C305}	R ^{D9}	R ^{D58}	

432

-continued

L _{C306}	R ^{D9}	R ^{D59}
L _{C307}	R ^{D9}	R ^{D78}
L _{C308}	R ^{D9}	R ^{D79}
L _{C309}	R ^{D9}	R ^{D81}
L _{C310}	R ^{D9}	R ^{D87}
L _{C311}	R ^{D9}	R ^{D88}
L _{C312}	R ^{D9}	R ^{D89}
L _{C313}	R ^{D9}	R ^{D93}
L _{C314}	R ^{D9}	R ^{D116}
L _{C315}	R ^{D9}	R ^{D117}
L _{C316}	R ^{D9}	R ^{D118}
L _{C317}	R ^{D9}	R ^{D119}
L _{C318}	R ^{D9}	R ^{D120}
L _{C319}	R ^{D9}	R ^{D133}
L _{C320}	R ^{D9}	R ^{D134}
L _{C321}	R ^{D9}	R ^{D135}
L _{C322}	R ^{D9}	R ^{D136}
L _{C323}	R ^{D9}	R ^{D143}
L _{C324}	R ^{D9}	R ^{D144}
L _{C325}	R ^{D9}	R ^{D145}
L _{C326}	R ^{D9}	R ^{D146}
L _{C327}	R ^{D9}	R ^{D147}
L _{C328}	R ^{D9}	R ^{D149}
L _{C329}	R ^{D9}	R ^{D151}
L _{C330}	R ^{D9}	R ^{D154}
L _{C331}	R ^{D9}	R ^{D155}
L _{C332}	R ^{D9}	R ^{D161}
L _{C333}	R ^{D9}	R ^{D175}
L _{C334}	R ^{D10}	R ^{D3}
L _{C335}	R ^{D10}	R ^{D5}
L _{C336}	R ^{D10}	R ^{D17}
L _{C337}	R ^{D10}	R ^{D18}
L _{C338}	R ^{D10}	R ^{D20}
L _{C339}	R ^{D10}	R ^{D22}
L _{C340}	R ^{D10}	R ^{D37}
L _{C341}	R ^{D10}	R ^{D40}
L _{C342}	R ^{D10}	R ^{D41}
L _{C343}	R ^{D10}	R ^{D42}
L _{C344}	R ^{D10}	R ^{D43}
L _{C345}	R ^{D10}	R ^{D48}
L _{C346}	R ^{D10}	R ^{D49}
L _{C347}	R ^{D10}	R ^{D50}
L _{C348}	R ^{D10}	R ^{D54}
L _{C349}	R ^{D10}	R ^{D55}
L _{C350}	R ^{D10}	R ^{D58}
L _{C351}	R ^{D10}	R ^{D59}
L _{C352}	R ^{D10}	R ^{D78}
L _{C353}	R ^{D10}	R ^{D79}
L _{C354}	R ^{D10}	R ^{D81}
L _{C355}	R ^{D10}	R ^{D87}
L _{C356}	R ^{D10}	R ^{D88}
L _{C357}	R ^{D10}	R ^{D89}
L _{C358}	R ^{D10}	R ^{D93}
L _{C359}	R ^{D10}	R ^{D116}
L _{C360}	R ^{D10}	R ^{D117}
L _{C361}	R ^{D10}	R ^{D118}
L _{C362}	R ^{D10}	R ^{D119}
L _{C363}	R ^{D10}	R ^{D120}
L _{C364}	R ^{D10}	R ^{D133}
L _{C365}	R ^{D10}	R ^{D134}
L _{C366}	R ^{D10}	R ^{D135}
L _{C367}	R ^{D10}	R ^{D136}
L _{C368}	R ^{D10}	R ^{D143}
L _{C369}	R ^{D10}	R ^{D144}
L _{C370}	R ^{D10}	R ^{D145}
L _{C371}	R ^{D10}	R ^{D146}
L _{C372}	R ^{D10}	R ^{D147}
L _{C373}	R ^{D10}	R ^{D149}
L _{C374}	R ^{D10}	R ^{D151}
L _{C375}	R ^{D10}	R ^{D154}
L _{C376}	R ^{D10}	R ^{D155}
L _{C377}	R ^{D10}	R ^{D161}
L _{C378}	R ^{D10}	R ^{D175}
L _{C379}	R ^{D17}	R ^{D3}
L _{C380}	R ^{D17}	R ^{D5}
L _{C381}	R ^{D18}	R ^{D18}
L _{C382}	R ^{D19}	R ^{D20}
L _{C383}	R ^{D20}	R ^{D22}
L _{C384}	R ^{D21}	R ^{D37}

433

-continued

L _{C877}	R ^{D1}	R ^{D193}	
L _{C878}	R ^{D1}	R ^{D194}	
L _{C879}	R ^{D1}	R ^{D195}	
L _{C880}	R ^{D1}	R ^{D196}	5
L _{C881}	R ^{D1}	R ^{D197}	
L _{C882}	R ^{D1}	R ^{D198}	
L _{C883}	R ^{D1}	R ^{D199}	
L _{C884}	R ^{D1}	R ^{D200}	
L _{C885}	R ^{D1}	R ^{D201}	
L _{C886}	R ^{D1}	R ^{D202}	10
L _{C887}	R ^{D1}	R ^{D203}	
L _{C888}	R ^{D1}	R ^{D204}	
L _{C889}	R ^{D1}	R ^{D205}	
L _{C890}	R ^{D1}	R ^{D206}	
L _{C891}	R ^{D1}	R ^{D207}	
L _{C892}	R ^{D1}	R ^{D208}	15
L _{C893}	R ^{D1}	R ^{D209}	
L _{C894}	R ^{D1}	R ^{D210}	
L _{C895}	R ^{D1}	R ^{D211}	
L _{C896}	R ^{D1}	R ^{D212}	
L _{C897}	R ^{D1}	R ^{D213}	
L _{C898}	R ^{D1}	R ^{D214}	
L _{C899}	R ^{D1}	R ^{D215}	20
L _{C900}	R ^{D1}	R ^{D216}	
L _{C901}	R ^{D1}	R ^{D217}	
L _{C902}	R ^{D1}	R ^{D218}	
L _{C903}	R ^{D1}	R ^{D219}	
L _{C904}	R ^{D1}	R ^{D220}	
L _{C905}	R ^{D1}	R ^{D221}	25
L _{C906}	R ^{D1}	R ^{D222}	
L _{C907}	R ^{D1}	R ^{D223}	
L _{C908}	R ^{D1}	R ^{D224}	
L _{C909}	R ^{D1}	R ^{D225}	
L _{C910}	R ^{D1}	R ^{D226}	
L _{C911}	R ^{D1}	R ^{D227}	30
L _{C912}	R ^{D1}	R ^{D228}	
L _{C913}	R ^{D1}	R ^{D229}	
L _{C914}	R ^{D1}	R ^{D230}	
L _{C915}	R ^{D1}	R ^{D231}	
L _{C916}	R ^{D1}	R ^{D232}	
L _{C917}	R ^{D1}	R ^{D233}	35
L _{C918}	R ^{D1}	R ^{D234}	
L _{C919}	R ^{D1}	R ^{D235}	
L _{C920}	R ^{D1}	R ^{D236}	
L _{C921}	R ^{D1}	R ^{D237}	
L _{C922}	R ^{D1}	R ^{D238}	
L _{C923}	R ^{D1}	R ^{D239}	40
L _{C924}	R ^{D1}	R ^{D240}	
L _{C925}	R ^{D1}	R ^{D241}	
L _{C926}	R ^{D1}	R ^{D242}	
L _{C927}	R ^{D1}	R ^{D243}	
L _{C928}	R ^{D1}	R ^{D244}	
L _{C929}	R ^{D1}	R ^{D245}	
L _{C930}	R ^{D1}	R ^{D246}	45
L _{C931}	R ^{D50}	R ^{D193}	
L _{C932}	R ^{D50}	R ^{D194}	
L _{C933}	R ^{D50}	R ^{D195}	
L _{C934}	R ^{D50}	R ^{D196}	
L _{C935}	R ^{D50}	R ^{D197}	
L _{C936}	R ^{D50}	R ^{D198}	50
L _{C937}	R ^{D50}	R ^{D199}	
L _{C938}	R ^{D50}	R ^{D200}	
L _{C939}	R ^{D50}	R ^{D201}	
L _{C940}	R ^{D50}	R ^{D202}	
L _{C941}	R ^{D50}	R ^{D203}	
L _{C942}	R ^{D50}	R ^{D204}	55
L _{C943}	R ^{D50}	R ^{D205}	
L _{C944}	R ^{D50}	R ^{D206}	
L _{C945}	R ^{D50}	R ^{D207}	
L _{C946}	R ^{D50}	R ^{D208}	
L _{C947}	R ^{D50}	R ^{D209}	
L _{C948}	R ^{D50}	R ^{D210}	60
L _{C949}	R ^{D50}	R ^{D211}	
L _{C950}	R ^{D50}	R ^{D212}	
L _{C951}	R ^{D50}	R ^{D213}	
L _{C952}	R ^{D50}	R ^{D214}	
L _{C953}	R ^{D50}	R ^{D215}	
L _{C954}	R ^{D50}	R ^{D216}	65
L _{C955}	R ^{D50}	R ^{D217}	

434

-continued

L _{C956}	R ^{D50}	R ^{D218}
L _{C957}	R ^{D50}	R ^{D219}
L _{C958}	R ^{D50}	R ^{D220}
L _{C959}	R ^{D50}	R ^{D221}
L _{C960}	R ^{D50}	R ^{D222}
L _{C961}	R ^{D50}	R ^{D223}
L _{C962}	R ^{D50}	R ^{D224}
L _{C963}	R ^{D50}	R ^{D225}
L _{C964}	R ^{D50}	R ^{D226}
L _{C965}	R ^{D50}	R ^{D227}
L _{C966}	R ^{D50}	R ^{D228}
L _{C967}	R ^{D50}	R ^{D229}
L _{C968}	R ^{D50}	R ^{D230}
L _{C969}	R ^{D50}	R ^{D231}
L _{C970}	R ^{D50}	R ^{D232}
L _{C971}	R ^{D50}	R ^{D233}
L _{C972}	R ^{D50}	R ^{D234}
L _{C973}	R ^{D50}	R ^{D235}
L _{C974}	R ^{D50}	R ^{D236}
L _{C975}	R ^{D50}	R ^{D237}
L _{C976}	R ^{D50}	R ^{D238}
L _{C977}	R ^{D50}	R ^{D239}
L _{C978}	R ^{D50}	R ^{D240}
L _{C979}	R ^{D50}	R ^{D241}
L _{C980}	R ^{D50}	R ^{D242}
L _{C981}	R ^{D50}	R ^{D243}
L _{C982}	R ^{D50}	R ^{D244}
L _{C983}	R ^{D50}	R ^{D245}
L _{C984}	R ^{D50}	R ^{D246}
L _{C1255}	R ^{D55}	R ^{D193}
L _{C1256}	R ^{D55}	R ^{D194}
L _{C1257}	R ^{D55}	R ^{D195}
L _{C1258}	R ^{D55}	R ^{D196}
L _{C1259}	R ^{D55}	R ^{D197}
L _{C1260}	R ^{D55}	R ^{D198}
L _{C1261}	R ^{D55}	R ^{D199}
L _{C1262}	R ^{D55}	R ^{D200}
L _{C1263}	R ^{D55}	R ^{D201}
L _{C1264}	R ^{D55}	R ^{D202}
L _{C1265}	R ^{D55}	R ^{D203}
L _{C1266}	R ^{D55}	R ^{D204}
L _{C1267}	R ^{D55}	R ^{D205}
L _{C1268}	R ^{D55}	R ^{D206}
L _{C1269}	R ^{D55}	R ^{D207}
L _{C1270}	R ^{D55}	R ^{D208}
L _{C1271}	R ^{D55}	R ^{D209}
L _{C1272}	R ^{D55}	R ^{D210}
L _{C1273}	R ^{D55}	R ^{D211}
L _{C1274}	R ^{D55}	R ^{D212}
L _{C1275}	R ^{D55}	R ^{D213}
L _{C1276}	R ^{D55}	R ^{D214}
L _{C1277}	R ^{D55}	R ^{D215}
L _{C1278}	R ^{D55}	R ^{D216}
L _{C1279}	R ^{D55}	R ^{D217}
L _{C1280}	R ^{D55}	R ^{D218}
L _{C1281}	R ^{D55}	R ^{D219}
L _{C1282}	R ^{D55}	R ^{D220}
L _{C1283}	R ^{D55}	R ^{D221}
L _{C1284}	R ^{D55}	R ^{D222}
L _{C1285}	R ^{D55}	R ^{D223}
L _{C1286}	R ^{D55}	R ^{D224}
L _{C1287}	R ^{D55}	R ^{D225}
L _{C1288}	R ^{D55}	R ^{D226}
L _{C1289}	R ^{D55}	R ^{D227}
L _{C1290}	R ^{D55}	R ^{D228}
L _{C1291}	R ^{D55}	R ^{D229}
L _{C1292}	R ^{D55}	R ^{D230}
L _{C1293}	R ^{D55}	R ^{D231}
L _{C1294}	R ^{D55}	R ^{D232}
L _{C1295}	R ^{D55}	R ^{D233}
L _{C1296}	R ^{D55}	R ^{D234}
L _{C1297}	R ^{D55}	R ^{D235}
L _{C1298}	R ^{D55}	R ^{D236}
L _{C1299}	R ^{D55}	R ^{D237}
L _{C1300}	R ^{D55}	R ^{D238}
L _{C1301}	R ^{D55}	R ^{D239}
L _{C1302}	R ^{D55}	R ^{D240}
L _{C1303}	R ^{D55}	R ^{D241}
L _{C1304}	R ^{D55}	R ^{D242}

435

-continued

L_{C1305}	R^{D55}	R^{D243}	5
L_{C1306}	R^{D55}	R^{D244}	
L_{C1307}	R^{D55}	R^{D245}	
L_{C1308}	R^{D55}	R^{D246}	
L_{Cj}	R^{201}	R^{202}	
L_{C385}	R^{D17}	R^{D40}	10
L_{C386}	R^{D17}	R^{D41}	
L_{C387}	R^{D17}	R^{D42}	
L_{C388}	R^{D17}	R^{D43}	
L_{C389}	R^{D17}	R^{D48}	15
L_{C390}	R^{D17}	R^{D49}	
L_{C391}	R^{D17}	R^{D50}	
L_{C392}	R^{D17}	R^{D54}	
L_{C393}	R^{D17}	R^{D55}	20
L_{C394}	R^{D17}	R^{D58}	
L_{C395}	R^{D17}	R^{D59}	
L_{C396}	R^{D17}	R^{D78}	
L_{C397}	R^{D17}	R^{D79}	25
L_{C398}	R^{D17}	R^{D81}	
L_{C399}	R^{D17}	R^{D87}	
L_{C400}	R^{D17}	R^{D88}	
L_{C401}	R^{D17}	R^{D89}	30
L_{C402}	R^{D17}	R^{D93}	
L_{C403}	R^{D17}	R^{D116}	
L_{C404}	R^{D17}	R^{D117}	
L_{C405}	R^{D17}	R^{D118}	35
L_{C406}	R^{D17}	R^{D119}	
L_{C407}	R^{D17}	R^{D120}	
L_{C408}	R^{D17}	R^{D133}	
L_{C409}	R^{D17}	R^{D134}	40
L_{C410}	R^{D17}	R^{D135}	
L_{C411}	R^{D17}	R^{D136}	
L_{C412}	R^{D17}	R^{D143}	
L_{C413}	R^{D17}	R^{D144}	45
L_{C414}	R^{D17}	R^{D145}	
L_{C415}	R^{D17}	R^{D146}	
L_{C416}	R^{D17}	R^{D147}	
L_{C417}	R^{D17}	R^{D149}	50
L_{C418}	R^{D17}	R^{D151}	
L_{C419}	R^{D17}	R^{D154}	
L_{C420}	R^{D17}	R^{D155}	
L_{C421}	R^{D17}	R^{D161}	55
L_{C422}	R^{D17}	R^{D175}	
L_{C423}	R^{D50}	R^{D3}	
L_{C424}	R^{D50}	R^{D5}	
L_{C425}	R^{D50}	R^{D18}	60
L_{C426}	R^{D50}	R^{D20}	
L_{C427}	R^{D50}	R^{D22}	
L_{C428}	R^{D50}	R^{D37}	
L_{C429}	R^{D50}	R^{D40}	65
L_{C430}	R^{D50}	R^{D41}	
L_{C431}	R^{D50}	R^{D42}	
L_{C432}	R^{D50}	R^{D43}	
L_{C433}	R^{D50}	R^{D48}	50
L_{C434}	R^{D50}	R^{D49}	
L_{C435}	R^{D50}	R^{D54}	
L_{C436}	R^{D50}	R^{D55}	
L_{C437}	R^{D50}	R^{D58}	55
L_{C438}	R^{D50}	R^{D59}	
L_{C439}	R^{D50}	R^{D78}	
L_{C440}	R^{D50}	R^{D79}	
L_{C441}	R^{D50}	R^{D81}	60
L_{C442}	R^{D50}	R^{D87}	
L_{C443}	R^{D50}	R^{D88}	
L_{C444}	R^{D50}	R^{D89}	
L_{C445}	R^{D50}	R^{D93}	65
L_{C446}	R^{D50}	R^{D116}	
L_{C447}	R^{D50}	R^{D117}	
L_{C448}	R^{D50}	R^{D118}	
L_{C449}	R^{D50}	R^{D119}	60
L_{C450}	R^{D50}	R^{D120}	
L_{C451}	R^{D50}	R^{D133}	
L_{C452}	R^{D50}	R^{D134}	
L_{C453}	R^{D50}	R^{D135}	65
L_{C454}	R^{D50}	R^{D136}	
L_{C455}	R^{D50}	R^{D143}	
L_{C456}	R^{D50}	R^{D144}	

436

-continued

L_{C457}	R^{D50}	R^{D145}
L_{C458}	R^{D50}	R^{D146}
L_{C459}	R^{D50}	R^{D147}
L_{C460}	R^{D50}	R^{D149}
L_{C461}	R^{D50}	R^{D151}
L_{C462}	R^{D50}	R^{D154}
L_{C463}	R^{D50}	R^{D155}
L_{C464}	R^{D50}	R^{D161}
L_{C465}	R^{D50}	R^{D175}
L_{C466}	R^{D55}	R^{D3}
L_{C467}	R^{D55}	R^{D5}
L_{C468}	R^{D55}	R^{D18}
L_{C469}	R^{D55}	R^{D20}
L_{C470}	R^{D55}	R^{D22}
L_{C471}	R^{D55}	R^{D37}
L_{C472}	R^{D55}	R^{D40}
L_{C473}	R^{D55}	R^{D41}
L_{C474}	R^{D55}	R^{D42}
L_{C475}	R^{D55}	R^{D43}
L_{C476}	R^{D55}	R^{D48}
L_{C477}	R^{D55}	R^{D49}
L_{C478}	R^{D55}	R^{D54}
L_{C479}	R^{D55}	R^{D58}
L_{C480}	R^{D55}	R^{D59}
L_{C481}	R^{D55}	R^{D78}
L_{C482}	R^{D55}	R^{D79}
L_{C483}	R^{D55}	R^{D81}
L_{C484}	R^{D55}	R^{D87}
L_{C485}	R^{D55}	R^{D88}
L_{C486}	R^{D55}	R^{D89}
L_{C487}	R^{D55}	R^{D93}
L_{C488}	R^{D55}	R^{D116}
L_{C489}	R^{D55}	R^{D117}
L_{C490}	R^{D55}	R^{D118}
L_{C491}	R^{D55}	R^{D119}
L_{C492}	R^{D55}	R^{D120}
L_{C493}	R^{D55}	R^{D133}
L_{C494}	R^{D55}	R^{D134}
L_{C495}	R^{D55}	R^{D135}
L_{C496}	R^{D55}	R^{D136}
L_{C497}	R^{D55}	R^{D143}
L_{C498}	R^{D55}	R^{D144}
L_{C499}	R^{D55}	R^{D145}
L_{C500}	R^{D55}	R^{D146}
L_{C501}	R^{D55}	R^{D147}
L_{C502}	R^{D55}	R^{D149}
L_{C503}	R^{D55}	R^{D151}
L_{C504}	R^{D55}	R^{D154}
L_{C505}	R^{D55}	R^{D155}
L_{C506}	R^{D55}	R^{D161}
L_{C507}	R^{D55}	R^{D175}
L_{C508}	R^{D116}	R^{D3}
L_{C509}	R^{D116}	R^{D5}
L_{C510}	R^{D116}	R^{D17}
L_{C511}	R^{D116}	R^{D18}
L_{C512}	R^{D116}	R^{D20}
L_{C513}	R^{D116}	R^{D22}
L_{C514}	R^{D116}	R^{D37}
L_{C515}	R^{D116}	R^{D40}
L_{C516}	R^{D116}	R^{D41}
L_{C517}	R^{D116}	R^{D42}
L_{C518}	R^{D116}	R^{D43}
L_{C519}	R^{D116}	R^{D48}
L_{C520}	R^{D116}	R^{D49}
L_{C521}	R^{D116}	R^{D54}
L_{C522}	R^{D116}	R^{D58}
L_{C523}	R^{D116}	R^{D59}
L_{C524}	R^{D116}	R^{D78}
L_{C525}	R^{D116}	R^{D79}
L_{C526}	R^{D116}	R^{D81}
L_{C527}	R^{D116}	R^{D87}
L_{C528}	R^{D116}	R^{D88}
L_{C529}	R^{D116}	R^{D89}
L_{C530}	R^{D116}	R^{D93}
L_{C531}	R^{D116}	R^{D117}
L_{C532}	R^{D116}	R^{D118}
L_{C533}	R^{D116}	R^{D119}
L_{C534}	R^{D116}	R^{D120}
L_{C535}	R^{D116}	R^{D133}

437

-continued

L _{C536}	R ^{D116}	R ^{D134}	
L _{C537}	R ^{D116}	R ^{D135}	
L _{C538}	R ^{D116}	R ^{D136}	
L _{C539}	R ^{D116}	R ^{D143}	5
L _{C540}	R ^{D116}	R ^{D144}	
L _{C541}	R ^{D116}	R ^{D145}	
L _{C542}	R ^{D116}	R ^{D146}	
L _{C543}	R ^{D116}	R ^{D147}	
L _{C544}	R ^{D116}	R ^{D149}	
L _{C545}	R ^{D116}	R ^{D151}	10
L _{C546}	R ^{D116}	R ^{D154}	
L _{C547}	R ^{D116}	R ^{D155}	
L _{C548}	R ^{D116}	R ^{D161}	
L _{C549}	R ^{D116}	R ^{D175}	
L _{C550}	R ^{D143}	R ^{D3}	
L _{C551}	R ^{D143}	R ^{D5}	15
L _{C552}	R ^{D143}	R ^{D17}	
L _{C553}	R ^{D143}	R ^{D18}	
L _{C554}	R ^{D143}	R ^{D20}	
L _{C555}	R ^{D143}	R ^{D22}	
L _{C556}	R ^{D143}	R ^{D37}	
L _{C557}	R ^{D143}	R ^{D40}	20
L _{C558}	R ^{D143}	R ^{D41}	
L _{C559}	R ^{D143}	R ^{D42}	
L _{C560}	R ^{D143}	R ^{D43}	
L _{C561}	R ^{D143}	R ^{D48}	
L _{C562}	R ^{D143}	R ^{D49}	
L _{C563}	R ^{D143}	R ^{D54}	
L _{C564}	R ^{D143}	R ^{D58}	25
L _{C565}	R ^{D143}	R ^{D59}	
L _{C566}	R ^{D143}	R ^{D78}	
L _{C567}	R ^{D143}	R ^{D79}	
L _{C568}	R ^{D143}	R ^{D81}	
L _{C569}	R ^{D143}	R ^{D87}	
L _{C570}	R ^{D143}	R ^{D88}	30
L _{C571}	R ^{D143}	R ^{D89}	
L _{C572}	R ^{D143}	R ^{D93}	
L _{C573}	R ^{D143}	R ^{D116}	
L _{C574}	R ^{D143}	R ^{D117}	
L _{C575}	R ^{D143}	R ^{D118}	
L _{C576}	R ^{D143}	R ^{D119}	35
L _{C985}	R ^{D4}	R ^{D193}	
L _{C986}	R ^{D4}	R ^{D194}	
L _{C987}	R ^{D4}	R ^{D195}	
L _{C988}	R ^{D4}	R ^{D196}	
L _{C989}	R ^{D4}	R ^{D197}	
L _{C990}	R ^{D4}	R ^{D198}	40
L _{C991}	R ^{D4}	R ^{D199}	
L _{C992}	R ^{D4}	R ^{D200}	
L _{C993}	R ^{D4}	R ^{D201}	
L _{C994}	R ^{D4}	R ^{D202}	
L _{C995}	R ^{D4}	R ^{D203}	
L _{C996}	R ^{D4}	R ^{D204}	45
L _{C997}	R ^{D4}	R ^{D205}	
L _{C998}	R ^{D4}	R ^{D206}	
L _{C999}	R ^{D4}	R ^{D207}	
L _{C1000}	R ^{D4}	R ^{D208}	
L _{C1001}	R ^{D4}	R ^{D209}	
L _{C1002}	R ^{D4}	R ^{D210}	
L _{C1003}	R ^{D4}	R ^{D211}	50
L _{C1004}	R ^{D4}	R ^{D212}	
L _{C1005}	R ^{D4}	R ^{D213}	
L _{C1006}	R ^{D4}	R ^{D214}	
L _{C1007}	R ^{D4}	R ^{D215}	
L _{C1008}	R ^{D4}	R ^{D216}	
L _{C1009}	R ^{D4}	R ^{D217}	55
L _{C1010}	R ^{D4}	R ^{D218}	
L _{C1011}	R ^{D4}	R ^{D219}	
L _{C1012}	R ^{D4}	R ^{D220}	
L _{C1013}	R ^{D4}	R ^{D221}	
L _{C1014}	R ^{D4}	R ^{D222}	
L _{C1015}	R ^{D4}	R ^{D223}	60
L _{C1016}	R ^{D4}	R ^{D224}	
L _{C1017}	R ^{D4}	R ^{D225}	
L _{C1018}	R ^{D4}	R ^{D226}	
L _{C1019}	R ^{D4}	R ^{D227}	
L _{C1020}	R ^{D4}	R ^{D228}	
L _{C1021}	R ^{D4}	R ^{D229}	65
L _{C1022}	R ^{D4}	R ^{D230}	

438

-continued

L _{C1023}	R ^{D4}	R ^{D231}
L _{C1024}	R ^{D4}	R ^{D232}
L _{C1025}	R ^{D4}	R ^{D233}
L _{C1026}	R ^{D4}	R ^{D234}
L _{C1027}	R ^{D4}	R ^{D235}
L _{C1028}	R ^{D4}	R ^{D236}
L _{C1029}	R ^{D4}	R ^{D237}
L _{C1030}	R ^{D4}	R ^{D238}
L _{C1031}	R ^{D4}	R ^{D239}
L _{C1032}	R ^{D4}	R ^{D240}
L _{C1033}	R ^{D4}	R ^{D241}
L _{C1034}	R ^{D4}	R ^{D242}
L _{C1035}	R ^{D4}	R ^{D243}
L _{C1036}	R ^{D4}	R ^{D244}
L _{C1037}	R ^{D4}	R ^{D245}
L _{C1038}	R ^{D4}	R ^{D246}
L _{C1039}	R ^{D145}	R ^{D193}
L _{C1040}	R ^{D145}	R ^{D194}
L _{C1041}	R ^{D145}	R ^{D195}
L _{C1042}	R ^{D145}	R ^{D196}
L _{C1043}	R ^{D145}	R ^{D197}
L _{C1044}	R ^{D145}	R ^{D198}
L _{C1045}	R ^{D145}	R ^{D199}
L _{C1046}	R ^{D145}	R ^{D200}
L _{C1047}	R ^{D145}	R ^{D201}
L _{C1048}	R ^{D145}	R ^{D202}
L _{C1049}	R ^{D145}	R ^{D203}
L _{C1050}	R ^{D145}	R ^{D204}
L _{C1051}	R ^{D145}	R ^{D205}
L _{C1052}	R ^{D145}	R ^{D206}
L _{C1053}	R ^{D145}	R ^{D207}
L _{C1054}	R ^{D145}	R ^{D208}
L _{C1055}	R ^{D145}	R ^{D209}
L _{C1056}	R ^{D145}	R ^{D210}
L _{C1057}	R ^{D145}	R ^{D211}
L _{C1058}	R ^{D145}	R ^{D212}
L _{C1059}	R ^{D145}	R ^{D213}
L _{C1060}	R ^{D145}	R ^{D214}
L _{C1061}	R ^{D145}	R ^{D215}
L _{C1062}	R ^{D145}	R ^{D216}
L _{C1063}	R ^{D145}	R ^{D217}
L _{C1064}	R ^{D145}	R ^{D218}
L _{C1065}	R ^{D145}	R ^{D219}
L _{C1066}	R ^{D145}	R ^{D220}
L _{C1067}	R ^{D145}	R ^{D221}
L _{C1068}	R ^{D145}	R ^{D222}
L _{C1069}	R ^{D145}	R ^{D223}
L _{C1070}	R ^{D145}	R ^{D224}
L _{C1071}	R ^{D145}	R ^{D225}
L _{C1072}	R ^{D145}	R ^{D226}
L _{C1073}	R ^{D145}	R ^{D227}
L _{C1074}	R ^{D145}	R ^{D228}
L _{C1075}	R ^{D145}	R ^{D229}
L _{C1076}	R ^{D145}	R ^{D230}
L _{C1077}	R ^{D145}	R ^{D231}
L _{C1078}	R ^{D145}	R ^{D232}
L _{C1079}	R ^{D145}	R ^{D233}
L _{C1080}	R ^{D145}	R ^{D234}
L _{C1081}	R ^{D145}	R ^{D235}
L _{C1082}	R ^{D145}	R ^{D236}
L _{C1083}	R ^{D145}	R ^{D237}
L _{C1084}	R ^{D145}	R ^{D238}
L _{C1085}	R ^{D145}	R ^{D239}
L _{C1086}	R ^{D145}	R ^{D240}
L _{C1087}	R ^{D145}	R ^{D241}
L _{C1088}	R ^{D145}	R ^{D242}
L _{C1089}	R ^{D145}	R ^{D243}
L _{C1090}	R ^{D145}	R ^{D244}
L _{C1091}	R ^{D145}	R ^{D245}
L _{C1092}	R ^{D145}	R ^{D246}
L _{C1309}	R ^{D37}	R ^{D193}
L _{C1310}	R ^{D37}	R ^{D194}
L _{C1311}	R ^{D37}	R ^{D195}
L _{C1312}	R ^{D37}	R ^{D196}
L _{C1313}	R ^{D37}	R ^{D197}
L _{C1314}	R ^{D37}	R ^{D198}
L _{C1315}	R ^{D37}	R ^{D199}
L _{C1316}	R ^{D37}	R ^{D200}
L _{C1317}	R ^{D37}	R ^{D201}

439

-continued

L_{C1318}	R^{D37}	R^{D202}	
L_{C1319}	R^{D37}	R^{D203}	
L_{C1320}	R^{D37}	R^{D204}	
L_{C1321}	R^{D37}	R^{D205}	5
L_{C1322}	R^{D37}	R^{D206}	
L_{C1323}	R^{D37}	R^{D207}	
L_{C1324}	R^{D37}	R^{D208}	
L_{C1325}	R^{D37}	R^{D209}	
L_{C1326}	R^{D37}	R^{D210}	
L_{C1327}	R^{D37}	R^{D211}	10
L_{C1328}	R^{D37}	R^{D212}	
L_{C1329}	R^{D37}	R^{D213}	
L_{C1330}	R^{D37}	R^{D214}	
L_{C1331}	R^{D37}	R^{D215}	
L_{C1332}	R^{D37}	R^{D216}	
L_{C1333}	R^{D37}	R^{D217}	15
L_{C1334}	R^{D37}	R^{D218}	
L_{C1335}	R^{D37}	R^{D219}	
L_{C1336}	R^{D37}	R^{D220}	
L_{C1337}	R^{D37}	R^{D221}	
L_{C1338}	R^{D37}	R^{D222}	
L_{C1339}	R^{D37}	R^{D223}	20
L_{C1340}	R^{D37}	R^{D224}	
L_{C1341}	R^{D37}	R^{D225}	
L_{C1342}	R^{D37}	R^{D226}	
L_{C1343}	R^{D37}	R^{D227}	
L_{C1344}	R^{D37}	R^{D228}	
L_{C1345}	R^{D37}	R^{D229}	
L_{C1346}	R^{D37}	R^{D230}	25
L_{C1347}	R^{D37}	R^{D231}	
L_{C1348}	R^{D37}	R^{D232}	
L_{C1349}	R^{D37}	R^{D233}	
L_{C1350}	R^{D37}	R^{D234}	
L_{C1351}	R^{D37}	R^{D235}	
L_{C1352}	R^{D37}	R^{D236}	30
L_{C1353}	R^{D37}	R^{D237}	
L_{C1354}	R^{D37}	R^{D238}	
L_{C1355}	R^{D37}	R^{D239}	
L_{C1356}	R^{D37}	R^{D240}	
L_{C1357}	R^{D37}	R^{D241}	
L_{C1358}	R^{D37}	R^{D242}	35
L_{C1359}	R^{D37}	R^{D243}	
L_{C1360}	R^{D37}	R^{D244}	
L_{C1361}	R^{D37}	R^{D245}	
L_{C1362}	R^{D37}	R^{D246}	
L_{Cj}	R^{201}	R^{202}	40
L_{C577}	R^{D143}	R^{D120}	
L_{C578}	R^{D143}	R^{D133}	
L_{C579}	R^{D143}	R^{D134}	
L_{C580}	R^{D143}	R^{D135}	
L_{C581}	R^{D143}	R^{D136}	45
L_{C582}	R^{D143}	R^{D144}	
L_{C583}	R^{D143}	R^{D145}	
L_{C584}	R^{D143}	R^{D146}	
L_{C585}	R^{D143}	R^{D147}	
L_{C586}	R^{D143}	R^{D149}	
L_{C587}	R^{D143}	R^{D151}	
L_{C588}	R^{D143}	R^{D154}	50
L_{C589}	R^{D143}	R^{D155}	
L_{C590}	R^{D143}	R^{D161}	
L_{C591}	R^{D143}	R^{D175}	
L_{C592}	R^{D144}	R^D	
L_{C593}	R^{D144}	R^D	
L_{C594}	R^{D144}	R^{D17}	55
L_{C595}	R^{D144}	R^{D18}	
L_{C596}	R^{D144}	R^{D20}	
L_{C597}	R^{D144}	R^{D22}	
L_{C598}	R^{D144}	R^{D37}	
L_{C599}	R^{D144}	R^{D40}	
L_{C600}	R^{D144}	R^{D41}	60
L_{C601}	R^{D144}	R^{D42}	
L_{C602}	R^{D144}	R^{D43}	
L_{C603}	R^{D144}	R^{D48}	
L_{C604}	R^{D144}	R^{D49}	
L_{C605}	R^{D144}	R^{D54}	
L_{C606}	R^{D144}	R^{D58}	65
L_{C607}	R^{D144}	R^{D59}	

440

-continued

L_{C608}	R^{D144}	R^{D78}
L_{C609}	R^{D144}	R^{D79}
L_{C610}	R^{D144}	R^{D81}
L_{C611}	R^{D144}	R^{D87}
L_{C612}	R^{D144}	R^{D88}
L_{C613}	R^{D144}	R^{D89}
L_{C614}	R^{D144}	R^{D93}
L_{C615}	R^{D144}	R^{D116}
L_{C616}	R^{D144}	R^{D117}
L_{C617}	R^{D144}	R^{D118}
L_{C618}	R^{D144}	R^{D119}
L_{C619}	R^{D144}	R^{D120}
L_{C620}	R^{D144}	R^{D133}
L_{C621}	R^{D144}	R^{D134}
L_{C622}	R^{D144}	R^{D135}
L_{C623}	R^{D144}	R^{D136}
L_{C624}	R^{D144}	R^{D145}
L_{C625}	R^{D144}	R^{D146}
L_{C626}	R^{D144}	R^{D147}
L_{C627}	R^{D144}	R^{D149}
L_{C628}	R^{D144}	R^{D151}
L_{C629}	R^{D144}	R^{D154}
L_{C630}	R^{D144}	R^{D155}
L_{C631}	R^{D144}	R^{D161}
L_{C632}	R^{D144}	R^{D175}
L_{C633}	R^{D145}	R^D
L_{C634}	R^{D145}	R^D
L_{C635}	R^{D145}	R^{D17}
L_{C636}	R^{D145}	R^{D18}
L_{C637}	R^{D145}	R^{D20}
L_{C638}	R^{D145}	R^{D22}
L_{C639}	R^{D145}	R^{D37}
L_{C640}	R^{D145}	R^{D40}
L_{C641}	R^{D145}	R^{D41}
L_{C642}	R^{D145}	R^{D42}
L_{C643}	R^{D145}	R^{D43}
L_{C644}	R^{D145}	R^{D48}
L_{C645}	R^{D145}	R^{D49}
L_{C646}	R^{D145}	R^{D54}
L_{C647}	R^{D145}	R^{D58}
L_{C648}	R^{D145}	R^{D59}
L_{C649}	R^{D145}	R^{D78}
L_{C650}	R^{D145}	R^{D79}
L_{C651}	R^{D145}	R^{D81}
L_{C652}	R^{D145}	R^{D87}
L_{C653}	R^{D145}	R^{D88}
L_{C654}	R^{D145}	R^{D89}
L_{C655}	R^{D145}	R^{D93}
L_{C656}	R^{D145}	R^{D116}
L_{C657}	R^{D145}	R^{D117}
L_{C658}	R^{D145}	R^{D118}
L_{C659}	R^{D145}	R^{D119}
L_{C660}	R^{D145}	R^{D120}
L_{C661}	R^{D145}	R^{D133}
L_{C662}	R^{D145}	R^{D134}
L_{C663}	R^{D145}	R^{D135}
L_{C664}	R^{D145}	R^{D136}
L_{C665}	R^{D145}	R^{D146}
L_{C666}	R^{D145}	R^{D147}
L_{C667}	R^{D145}	R^{D149}
L_{C668}	R^{D145}	R^{D151}
L_{C669}	R^{D145}	R^{D154}
L_{C670}	R^{D145}	R^{D155}
L_{C671}	R^{D145}	R^{D161}
L_{C672}	R^{D145}	R^{D175}
L_{C673}	R^{D146}	R^D
L_{C674}	R^{D146}	R^D
L_{C675}	R^{D146}	R^{D17}
L_{C676}	R^{D146}	R^{D18}
L_{C677}	R^{D146}	R^{D20}
L_{C678}	R^{D146}	R^{D22}
L_{C679}	R^{D146}	R^{D37}
L_{C680}	R^{D146}	R^{D40}
L_{C681}	R^{D146}	R^{D41}
L_{C682}	R^{D146}	R^{D42}
L_{C683}	R^{D146}	R^{D43}
L_{C684}	R^{D146}	R^{D48}
L_{C685}	R^{D146}	R^{D49}
L_{C686}	R^{D146}	R^{D54}

441

-continued

L _{C687}	R ^{D146}	R ^{D58}	
L _{C688}	R ^{D146}	R ^{D59}	
L _{C689}	R ^{D146}	R ^{D78}	
L _{C690}	R ^{D146}	R ^{D79}	5
L _{C691}	R ^{D146}	R ^{D81}	
L _{C692}	R ^{D146}	R ^{D87}	
L _{C693}	R ^{D146}	R ^{D88}	
L _{C694}	R ^{D146}	R ^{D89}	
L _{C695}	R ^{D146}	R ^{D93}	
L _{C696}	R ^{D146}	R ^{D117}	10
L _{C697}	R ^{D146}	R ^{D118}	
L _{C698}	R ^{D146}	R ^{D119}	
L _{C699}	R ^{D146}	R ^{D120}	
L _{C700}	R ^{D146}	R ^{D133}	
L _{C701}	R ^{D146}	R ^{D134}	
L _{C702}	R ^{D146}	R ^{D135}	15
L _{C703}	R ^{D146}	R ^{D136}	
L _{C704}	R ^{D146}	R ^{D146}	
L _{C705}	R ^{D146}	R ^{D147}	
L _{C706}	R ^{D146}	R ^{D149}	
L _{C707}	R ^{D146}	R ^{D151}	
L _{C708}	R ^{D146}	R ^{D154}	20
L _{C709}	R ^{D146}	R ^{D155}	
L _{C710}	R ^{D146}	R ^{D161}	
L _{C711}	R ^{D146}	R ^{D175}	
L _{C712}	R ^{D133}	R ^{D3}	25
L _{C713}	R ^{D133}	R ^{D5}	
L _{C714}	R ^{D133}	R ^{D3}	
L _{C715}	R ^{D133}	R ^{D18}	
L _{C716}	R ^{D133}	R ^{D20}	
L _{C717}	R ^{D133}	R ^{D22}	
L _{C718}	R ^{D133}	R ^{D37}	
L _{C719}	R ^{D133}	R ^{D40}	
L _{C720}	R ^{D133}	R ^{D41}	30
L _{C721}	R ^{D133}	R ^{D42}	
L _{C722}	R ^{D133}	R ^{D43}	
L _{C723}	R ^{D133}	R ^{D48}	
L _{C724}	R ^{D133}	R ^{D49}	
L _{C725}	R ^{D133}	R ^{D54}	
L _{C726}	R ^{D133}	R ^{D58}	35
L _{C727}	R ^{D133}	R ^{D59}	
L _{C728}	R ^{D133}	R ^{D78}	
L _{C729}	R ^{D133}	R ^{D79}	
L _{C730}	R ^{D133}	R ^{D81}	
L _{C731}	R ^{D133}	R ^{D87}	
L _{C732}	R ^{D133}	R ^{D88}	
L _{C733}	R ^{D133}	R ^{D89}	40
L _{C734}	R ^{D133}	R ^{D93}	
L _{C735}	R ^{D133}	R ^{D117}	
L _{C736}	R ^{D133}	R ^{D118}	
L _{C737}	R ^{D133}	R ^{D119}	
L _{C738}	R ^{D133}	R ^{D120}	
L _{C739}	R ^{D133}	R ^{D133}	45
L _{C740}	R ^{D133}	R ^{D134}	
L _{C741}	R ^{D133}	R ^{D135}	
L _{C742}	R ^{D133}	R ^{D136}	
L _{C743}	R ^{D133}	R ^{D146}	
L _{C744}	R ^{D133}	R ^{D147}	
L _{C745}	R ^{D133}	R ^{D149}	50
L _{C746}	R ^{D133}	R ^{D151}	
L _{C747}	R ^{D133}	R ^{D154}	
L _{C748}	R ^{D133}	R ^{D155}	
L _{C749}	R ^{D133}	R ^{D161}	
L _{C750}	R ^{D133}	R ^{D175}	
L _{C751}	R ^{D175}	R ^{D3}	55
L _{C752}	R ^{D175}	R ^{D5}	
L _{C753}	R ^{D175}	R ^{D18}	
L _{C754}	R ^{D175}	R ^{D20}	
L _{C755}	R ^{D175}	R ^{D22}	
L _{C756}	R ^{D175}	R ^{D37}	
L _{C757}	R ^{D175}	R ^{D40}	60
L _{C758}	R ^{D175}	R ^{D41}	
L _{C759}	R ^{D175}	R ^{D42}	
L _{C760}	R ^{D175}	R ^{D43}	
L _{C761}	R ^{D175}	R ^{D48}	
L _{C762}	R ^{D175}	R ^{D49}	
L _{C763}	R ^{D175}	R ^{D54}	65
L _{C764}	R ^{D175}	R ^{D58}	
L _{C765}	R ^{D175}	R ^{D59}	

442

-continued

L _{C766}	R ^{D175}	R ^{D78}
L _{C767}	R ^{D175}	R ^{D79}
L _{C768}	R ^{D175}	R ^{D81}
L _{C1093}	R ^{D9}	R ^{D193}
L _{C1094}	R ^{D9}	R ^{D194}
L _{C1095}	R ^{D9}	R ^{D195}
L _{C1096}	R ^{D9}	R ^{D196}
L _{C1097}	R ^{D9}	R ^{D197}
L _{C1098}	R ^{D9}	R ^{D198}
L _{C1099}	R ^{D9}	R ^{D199}
L _{C1100}	R ^{D9}	R ^{D200}
L _{C1101}	R ^{D9}	R ^{D201}
L _{C1102}	R ^{D9}	R ^{D202}
L _{C1103}	R ^{D9}	R ^{D203}
L _{C1104}	R ^{D9}	R ^{D204}
L _{C1105}	R ^{D9}	R ^{D205}
L _{C1106}	R ^{D9}	R ^{D206}
L _{C1107}	R ^{D9}	R ^{D207}
L _{C1108}	R ^{D9}	R ^{D208}
L _{C1109}	R ^{D9}	R ^{D209}
L _{C1110}	R ^{D9}	R ^{D210}
L _{C1111}	R ^{D9}	R ^{D211}
L _{C1112}	R ^{D9}	R ^{D212}
L _{C1113}	R ^{D9}	R ^{D213}
L _{C1114}	R ^{D9}	R ^{D214}
L _{C1115}	R ^{D9}	R ^{D215}
L _{C1116}	R ^{D9}	R ^{D216}
L _{C1117}	R ^{D9}	R ^{D217}
L _{C1118}	R ^{D9}	R ^{D218}
L _{C1119}	R ^{D9}	R ^{D219}
L _{C1120}	R ^{D9}	R ^{D220}
L _{C1121}	R ^{D9}	R ^{D221}
L _{C1122}	R ^{D9}	R ^{D222}
L _{C1123}	R ^{D9}	R ^{D223}
L _{C1124}	R ^{D9}	R ^{D224}
L _{C1125}	R ^{D9}	R ^{D225}
L _{C1126}	R ^{D9}	R ^{D226}
L _{C1127}	R ^{D9}	R ^{D227}
L _{C1128}	R ^{D9}	R ^{D228}
L _{C1129}	R ^{D9}	R ^{D229}
L _{C1130}	R ^{D9}	R ^{D230}
L _{C1131}	R ^{D9}	R ^{D231}
L _{C1132}	R ^{D9}	R ^{D232}
L _{C1133}	R ^{D9}	R ^{D233}
L _{C1134}	R ^{D9}	R ^{D234}
L _{C1135}	R ^{D9}	R ^{D235}
L _{C1136}	R ^{D9}	R ^{D236}
L _{C1137}	R ^{D9}	R ^{D237}
L _{C1138}	R ^{D9}	R ^{D238}
L _{C1139}	R ^{D9}	R ^{D239}
L _{C1140}	R ^{D9}	R ^{D240}
L _{C1141}	R ^{D9}	R ^{D241}
L _{C1142}	R ^{D9}	R ^{D242}
L _{C1143}	R ^{D9}	R ^{D243}
L _{C1144}	R ^{D9}	R ^{D244}
L _{C1145}	R ^{D9}	R ^{D245}
L _{C1146}	R ^{D9}	R ^{D246}
L _{C1147}	R ^{D168}	R ^{D193}
L _{C1148}	R ^{D168}	R ^{D194}
L _{C1149}	R ^{D168}	R ^{D195}
L _{C1150}	R ^{D168}	R ^{D196}
L _{C1151}	R ^{D168}	R ^{D197}
L _{C1152}	R ^{D168}	R ^{D198}
L _{C1153}	R ^{D168}	R ^{D199}
L _{C1154}	R ^{D168}	R ^{D200}
L _{C1155}	R ^{D168}	R ^{D201}
L _{C1156}	R ^{D168}	R ^{D202}
L _{C1157}	R ^{D168}	R ^{D203}
L _{C1158}	R ^{D168}	R ^{D204}
L _{C1159}	R ^{D168}	R ^{D205}
L _{C1160}	R ^{D168}	R ^{D206}
L _{C1161}	R ^{D168}	R ^{D207}
L _{C1162}	R ^{D168}	R ^{D208}
L _{C1163}	R ^{D168}	R ^{D209}
L _{C1164}	R ^{D168}	R ^{D210}
L _{C1165}	R ^{D168}	R ^{D211}
L _{C1166}	R ^{D168}	R ^{D212}
L _{C1167}	R ^{D168}	R ^{D213}
L _{C1168}	R ^{D168}	R ^{D214}

443

-continued

L _{C1169}	R ^{D168}	R ^{D215}
L _{C1170}	R ^{D168}	R ^{D216}
L _{C1171}	R ^{D168}	R ^{D217}
L _{C1172}	R ^{D168}	R ^{D218}
L _{C1173}	R ^{D168}	R ^{D219}
L _{C1174}	R ^{D168}	R ^{D220}
L _{C1175}	R ^{D168}	R ^{D221}
L _{C1176}	R ^{D168}	R ^{D222}
L _{C1177}	R ^{D168}	R ^{D223}
L _{C1178}	R ^{D168}	R ^{D224}
L _{C1179}	R ^{D168}	R ^{D225}
L _{C1180}	R ^{D168}	R ^{D226}
L _{C1181}	R ^{D168}	R ^{D227}
L _{C1182}	R ^{D168}	R ^{D228}
L _{C1183}	R ^{D168}	R ^{D229}
L _{C1184}	R ^{D168}	R ^{D230}
L _{C1185}	R ^{D168}	R ^{D231}
L _{C1186}	R ^{D168}	R ^{D232}
L _{C1187}	R ^{D168}	R ^{D233}
L _{C1188}	R ^{D168}	R ^{D234}
L _{C1189}	R ^{D168}	R ^{D235}
L _{C1190}	R ^{D168}	R ^{D236}
L _{C1191}	R ^{D168}	R ^{D237}
L _{C1192}	R ^{D168}	R ^{D238}
L _{C1193}	R ^{D168}	R ^{D239}
L _{C1194}	R ^{D168}	R ^{D240}
L _{C1195}	R ^{D168}	R ^{D241}
L _{C1196}	R ^{D168}	R ^{D242}
L _{C1197}	R ^{D168}	R ^{D243}
L _{C1198}	R ^{D168}	R ^{D244}
L _{C1199}	R ^{D168}	R ^{D245}
L _{C1200}	R ^{D168}	R ^{D246}
L _{C1363}	R ^{D143}	R ^{D193}
L _{C1364}	R ^{D143}	R ^{D194}
L _{C1365}	R ^{D143}	R ^{D195}
L _{C1366}	R ^{D143}	R ^{D196}
L _{C1367}	R ^{D143}	R ^{D197}
L _{C1368}	R ^{D143}	R ^{D198}
L _{C1369}	R ^{D143}	R ^{D199}
L _{C1370}	R ^{D143}	R ^{D200}
L _{C1371}	R ^{D143}	R ^{D201}
L _{C1372}	R ^{D143}	R ^{D202}
L _{C1373}	R ^{D143}	R ^{D203}
L _{C1374}	R ^{D143}	R ^{D204}
L _{C1375}	R ^{D143}	R ^{D205}
L _{C1376}	R ^{D143}	R ^{D206}
L _{C1377}	R ^{D143}	R ^{D207}
L _{C1378}	R ^{D143}	R ^{D208}
L _{C1379}	R ^{D143}	R ^{D209}
L _{C1380}	R ^{D143}	R ^{D210}
L _{C1381}	R ^{D143}	R ^{D211}
L _{C1382}	R ^{D143}	R ^{D212}
L _{C1383}	R ^{D143}	R ^{D213}
L _{C1384}	R ^{D143}	R ^{D214}
L _{C1385}	R ^{D143}	R ^{D215}
L _{C1386}	R ^{D143}	R ^{D216}
L _{C1387}	R ^{D143}	R ^{D217}
L _{C1388}	R ^{D143}	R ^{D218}
L _{C1389}	R ^{D143}	R ^{D219}
L _{C1390}	R ^{D143}	R ^{D220}
L _{C1391}	R ^{D143}	R ^{D221}
L _{C1392}	R ^{D143}	R ^{D222}
L _{C1393}	R ^{D143}	R ^{D223}
L _{C1394}	R ^{D143}	R ^{D224}
L _{C1395}	R ^{D143}	R ^{D225}
L _{C1396}	R ^{D143}	R ^{D226}
L _{C1397}	R ^{D143}	R ^{D227}
L _{C1398}	R ^{D143}	R ^{D228}
L _{C1399}	R ^{D143}	R ^{D229}
L _{C1400}	R ^{D143}	R ^{D230}
L _{C1401}	R ^{D143}	R ^{D231}
L _{C1402}	R ^{D143}	R ^{D232}
L _{C1403}	R ^{D143}	R ^{D233}
L _{C1404}	R ^{D143}	R ^{D234}
L _{C1405}	R ^{D143}	R ^{D235}
L _{C1406}	R ^{D143}	R ^{D236}
L _{C1407}	R ^{D143}	R ^{D237}
L _{C1408}	R ^{D143}	R ^{D238}
L _{C1409}	R ^{D143}	R ^{D239}

444

-continued















L _{C1410}	R ^{D143}	R ^{D240}
L _{C1411}	R ^{D143}	R ^{D241}
L _{C1412}	R ^{D143}	R ^{D242}
L _{C1413}	R ^{D143}	R ^{D243}
L _{C1414}	R ^{D143}	R ^{D244}
L _{C1415}	R ^{D143}	R ^{D245}
L _{C1416}	R ^{D143}	R ^{D246}

10 and R^{D1} to R^{D246} have the following structures:

15		R ^{D1}
		R ^{D2}
		R ^{D3}
20		R ^{D4}
		R ^{D5}
25		R ^{D6}
		R ^{D7}
30		R ^{D8}
35		R ^{D9}
		R ^{D10}
40		R ^{D11}
45		R ^{D12}
		R ^{D13}
50		R ^{D14}
55		R ^{D15}
60		R ^{D16}
65		

445

-continued

 R^{D17}

5

 R^{D18}

10

 R^{D19}

15

 R^{D20}

20

 R^{D21} R^{D22} 25 R^{D23}

30

 R^{D24}

35

 R^{D25}

40

 R^{D26}

45

 R^{D27}

50

 R^{D28}

55

 R^{D29}













60

 R^{D30}

65














446

-continued











 R^{D31} R^{D32} R^{D33} R^{D34} R^{D35} R^{D36} R^{D37} R^{D38} R^{D39} R^{D40} R^{D41} R^{D42} R^{D43} R^{D44} R^{D45}

447

-continued

**448**

-continued

 R^{D46}

5

 R^{D47}

10

 R^{D48}

15

 R^{D49}

20

 R^{D50}

25

 R^{D51}

30

 R^{D52}

35

 R^{D53}

40

 R^{D54}

45

 R^{D55}

50

 R^{D56}

55

 R^{D57}

60













 R^{D58}

65

 R^{D59} R^{D60} R^{D61} R^{D62} R^{D63} R^{D64} R^{D65} R^{D66} R^{D67} R^{D68} R^{D69} R^{D70}

449

-continued

 R^{D71}

5

 R^{D72} R^{D73} 10 R^{D74} 15 R^{D75} 20 R^{D76}

25

 R^{D77}

30

 R^{D78}

35

 R^{D79}

40

 R^{D80}

45

 R^{D81}

50

 R^{D82}

55













 R^{D83}

60

65












450

-continued

 R^{D84} R^{D85} R^{D86} R^{D87} R^{D88} R^{D89} R^{D90} R^{D91} R^{D92} R^{D93} R^{D94} R^{D95}

451

-continued

 R^{D96}

5

 R^{D97}

10

 R^{D98}

15

 R^{D99}

20

 R^{D100}

25

 R^{D101}

30

35

 R^{D102}

40

 R^{D103}

45

 R^{D104}

50

 R^{D105}

55











 R^{D106}

60

65


452

-continued

 R^{D107} R^{D108} R^{D109} R^{D110} R^{D111} R^{D112} R^{D113} R^{D114} R^{D115} R^{D116} R^{D117}

453

-continued

R^{D118}

5

R^{D119}

10

 R^{D120}

15

20

R^{D121} 25

30

 R^{D122}

35

 R^{D123}

40

R^{D124} 45

50

R^{D125}

55


R^{D126}

60

65














454

-continued
















 R^{D127} $\mathbb{R}^{D128}$ R^{D129}R^{D130}R^{D131}R^{D132}R^{D133}R^{D134}R^{D135}

455

-continued

**456**

-continued

 R^{D136}

5

 R^{D137}

10

 R^{D138}

15

 R^{D139}

20

 R^{D140}

25

 R^{D141}

30

 R^{D142}

35

 R^{D143}

40

 R^{D144}

45

 R^{D145} R^{D146} 50 R^{D147} R^{D148} 55 R^{D149}

60














 R^{D150}

65

 R^{D151} R^{D152} R^{D153} R^{D154} R^{D155} R^{D156} R^{D157} R^{D158} R^{D159} R^{D160} R^{D161} R^{D162} R^{D163} R^{D164} R^{D165}

457













-continued

 R^{D166} R^{D167} 5 R^{D168} 10 R^{D169} 15 R^{D170} 20 R^{D171} 25 R^{D172} 30 R^{D173} 35 R^{D174} 40 R^{D175} 45 R^{D176} 50 R^{D177} 55 R^{D178} 60

65


458

-continued


 R^{D179} R^{D180} R^{D181} R^{D182} R^{D183} R^{D184} R^{D185} R^{D186} R^{D187} R^{D188} R^{D189} R^{D190}

459

-continued


**460**

-continued




463

-continued






**464**

-continued






465

-continued





**466**

-continued








467

-continued







468

-continued







469

-continued






**470**

-continued







471

-continued


**472**

-continued




473

-continued

**474**

-continued




15

15. The compound of claim 1 wherein the compound is selected from the group consisting of Formulas III through IX:


20

Formula III




35

Formula IV




50

Formula V




65




475

-continued


Formula VI




Formula VII



Formula VIII



Formula IX



wherein:

M¹ is Pd or Pt;

rings E and F are each independently a 5-membered or 6-membered carbocyclic or heterocyclic ring;

Z¹' and Z²' are each independently C or N;

476

K¹ and K² are each independently selected from the group consisting of a direct bond, O, and S, wherein at least one of K¹ and K² is a direct bond;

L¹, L², and L³ are each independently selected from the group consisting of a single bond, absent a bond, O, S, CR'R'', SiR'R'', BR', and NR', wherein at least one of L¹, L² and L³ are present;

X³-X⁵ are each independently C or N;

Rᵈ and Rᵉ each independently represent zero, mono, or up to a maximum allowed substitution to its associated ring;


each of R', R'', Rᵈ, and Rᵉ is independently a hydrogen or a substituent selected from the group consisting of deuterium, fluorine, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, boryl, alkenyl, cycloalkenyl, heteroalkenyl, aryl, heteroaryl, nitrile, isonitrile, sulfanyl, and combinations thereof;

two adjacent R', R'', Rᵈ, and Rᵉ can be joined or fused together to form a ring where chemically feasible; and D¹-D³, Z¹, Z², Rᵈ, Rᶜ, Rᶜ and rings A¹, A² and A³ are all defined the same as above.

16. The compound of claim 15, wherein ring E and ring F are both 6-membered aromatic rings; or






ring F is a 5-membered or 6-membered heteroaromatic ring.

17. The compound of claim 15, wherein the compound is selected from the group consisting of:








477

-continued








478

-continued








479

-continued






**480**

-continued








481

-continued


**482**

-continued




483

-continued






**484**

-continued


















485

-continued

**486**






-continued











489

-continued


**490**

-continued




491

-continued




wherein $R^{A'}$, $R^{B'}$, $R^{C'}$, and $R^{D'}$ are each independently selected from the group consisting of deuterium, fluorine, alkyl, cycloalkyl, heteroalkyl, boryl, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, aryl, heteroaryl, nitrile, isonitrile, sulfanyl, and combinations thereof.

18. An organic light emitting device (OLED) comprising:
an anode;
a cathode; and
an organic layer disposed between the anode and the cathode, wherein the organic layer comprises a compound comprising a ligand L_A of Formula I



wherein:

A^1 and A^2 are each independently a 5-membered or 6-membered carbocyclic or heterocyclic ring;
 D^1 , D^2 , and D^3 are each independently selected from the group consisting of O, S, Se, BR, NR, PR, P(O)R, CRR', SiRR', and GeRR';
one of R^A or R^B has the structure of Formula II



wherein:

Z^1 is connected to C or N on ring A^1 or A^2 or connected to either D^1 , D^2 or D^3 ;
when Z^1 bonds to D^1 , D^2 or D^3 , said D^1 , D^2 or D^3 is selected from the group consisting of BR, NR, PR, P(O)R, CRR', SiRR', and GeRR';
the dashed line in Formula II is coordinated to a metal M;

492

A^3 is a 5-membered or 6-membered carbocyclic or heterocyclic rings;

Z^1 and Z^2 are each independently C or N;

R^A , R^B and R^C represent mono to the maximum allowable substitution, or no substitution;

each R^A , R^B , R^C , R, and R' is independently a hydrogen or a substituent selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, boryl, arylalkyl, aryloxy, amino, silyl, germly, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, selenyl, and combinations thereof;

if D^2 and D^3 are both CRR' and A^3 bonds to A^2 where A^2 is a 6-membered ring, then Z^2 is N, and R and R' are each independently a hydrogen or a substituent selected from the group consisting of deuterium, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, boryl, arylalkyl, aryloxy, amino, silyl, germly, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, selenyl, and combinations thereof;

L_A is coordinated to a metal M through the dashed line with Z^2 in Formula II and with one atom from ring A^1 or A^2 that is connected to Formula II to form a 5-membered chelate ring or 6-membered chelate ring;

M is selected from the group consisting of Os, Ir, Rh, Re, Ru, Pd, Pt, Cu, Ag, and Au;

M can be coordinated to other ligands;

L_A can be joined with other ligands to form a tridentate, tetradentate, pentadentate, or hexadentate ligand; and

any two adjacent R^A , R^B , R^C , R, and R' can be joined or fused to form a ring.


19. The OLED of claim 18, wherein the organic layer further comprises a host, wherein host comprises at least one chemical moiety selected from the group consisting of triphenylene, carbazole, indolocarbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, 5,9-dioxa-13b-boranaphtho[3,2,1-de]anthracene, aza-triphenylene, aza-carbazole, aza-indolocarbazole, aza-dibenzothiophene, aza-dibenzofuran, aza-dibenzoselenophene, and aza-(5,9-dioxa-13b-boranaphtho[3,2,1-de]anthracene).

20. A consumer product comprising an organic light-emitting device (OLED) comprising:

an anode;

a cathode; and

an organic layer disposed between the anode and the cathode, wherein the organic layer comprises a compound comprising a ligand L_A of Formula I




wherein:

A^1 and A^2 are each independently a 5-membered or 6-membered carbocyclic or heterocyclic ring;

D^1 , D^2 , and D^3 are each independently selected from the group consisting of O, S, Se, BR, NR, PR, P(O)R, CRR', SiRR', and GeRR';

493

one of R^A or R^B has the structure of Formula II



wherein:

Z^1 is connected to C or N on ring A^1 or A^2 or connected to either D^1 , D^2 or D^3 ;

when Z^1 bonds to D^1 , D^2 or D^3 , said D^1 , D^2 or D^3 is selected from the group consisting of BR, NR, PR, P(O)R, CRR', SiRR', and GeRR';

the dashed line in Formula II is coordinated to a metal M; A^3 is a 5-membered or 6-membered carbocyclic or heterocyclic rings;

Z^1 and Z^2 are each independently C or N;

R^A , R^B and R^C represent mono to the maximum allowable substitution, or no substitution;

each R^A , R^B , R^C , R, and R' is independently a hydrogen or a substituent selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, het-

494

erocycloalkyl, boryl, arylalkyl, aryloxy, amino, silyl, germyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, selenyl, and combinations thereof;

if D^2 and D^3 are both CRR' and A^3 bonds to A^2 where A^2 is a 6-membered ring, then Z^2 is N, and R and R' are each independently a hydrogen or a substituent selected from the group consisting of deuterium, alkyl, cycloalkyl, heteroalkyl, heterocycloalkyl, boryl, arylalkyl, aryloxy, amino, silyl, germyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, selenyl, and combinations thereof;

L_A is coordinated to a metal M through the dashed line with Z^2 in Formula II and with one atom from ring A^1 or A^2 that is connected to Formula II to form a 5-membered chelate ring or 6-membered chelate ring;

M is selected from the group consisting of Os, Ir, Rh, Re, Ru, Pd, Pt, Cu, Ag, and Au;

M can be coordinated to other ligands;

L_A can be joined with other ligands to form a tridentate, tetradentate, pentadentate, or hexadentate ligand; and any two adjacent R^A , R^B , R^C , R, and R' can be joined or fused to form a ring.

* * * * *