

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412792
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Hwang; Bokyeong et al.

Compartment shielding with metal frame and cap

Abstract

A semiconductor device has a substrate and a first semiconductor die disposed over the substrate. A first metal frame is disposed over the substrate around the first semiconductor die. A first metal lid is disposed over the first metal frame. A flap of the first metal lid includes an elastic characteristic to latch onto the first metal frame. An edge of the flap can have a castellated edge. A recess in the first metal frame and a protrusion on the first metal lid can be used to latch the first metal lid onto the first metal frame. A second metal frame and second metal lid can be disposed over an opposite surface of the substrate from the first metal frame.

Inventors: Hwang; Bokyeong (Incheon, KR), Kim; Jingwan (Incheon, KR), Kim; Minjung (Incheon, KR)

Applicant: STATS ChipPAC Pte. Ltd. (Singapore, SG)

Family ID: 85385504

Assignee: STATS ChipPAC Pte. Ltd. (Singapore, SG)

Appl. No.: 18/454709

Filed: August 23, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230402332 A1	Dec. 14, 2023

Related U.S. Application Data

continuation parent-doc US 17447041 20210907 US 11776861 child-doc US 18454709

Publication Classification

Int. Cl.: H01L23/051 (20060101); H01L21/60 (20060101); H01L23/049 (20060101); H05K9/00 (20060101)

U.S. Cl.:

CPC H01L23/051 (20130101); H01L21/60 (20210801); H01L23/049 (20130101); H05K9/0024 (20130101); H05K9/0032 (20130101); H05K9/0033 (20130101); H01L2021/60082 (20130101)

Field of Classification Search

CPC: H05K (9/0032); H05K (9/0033); H05K (9/0024)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
5895884	12/1998	Davidson	N/A	N/A
9070793	12/2014	Liao et al.	N/A	N/A
9924616	12/2017	Song et al.	N/A	N/A
10660246	12/2019	Huang et al.	N/A	N/A
2007/0094977	12/2006	Zuehlsdorf et al.	N/A	N/A
2009/0190321	12/2008	Yamazaki	361/818	H05K 9/0032
2009/0273912	12/2008	Myers et al.	N/A	N/A
2011/0037169	12/2010	Pagaila	257/E21.705	H01L 25/0657
2012/0025356	12/2011	Liao et al.	N/A	N/A
2013/0010435	12/2012	Ogatsu	N/A	N/A
2015/0264842	12/2014	Song et al.	N/A	N/A
2016/0044835	12/2015	Lee et al.	N/A	N/A
2016/0066482	12/2015	Chi et al.	N/A	N/A
2017/0181336	12/2016	Robinson et al.	N/A	N/A
2018/0323170	12/2017	Kim et al.	N/A	N/A
2019/0189565	12/2018	Chen	N/A	N/A
2019/0252756	12/2018	Lee et al.	N/A	N/A
2020/0093041	12/2019	Jung	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
102176438	12/2010	CN	N/A
109935523	12/2018	CN	N/A
110461138	12/2018	CN	H05K 9/0024
110911390	12/2019	CN	N/A
210136870	12/2019	CN	N/A
20160164267	12/2015	KR	N/A
20170006527	12/2016	KR	N/A
20170110941	12/2016	KR	N/A
20170111803	12/2016	KR	N/A
I351741	12/2008	TW	N/A

OTHER PUBLICATIONS

Primary Examiner: Kielin; Erik

Attorney, Agent or Firm: PATENT LAW GROUP: Atkins and Associates, P.C.

Background/Summary

CLAIM TO DOMESTIC PRIORITY (1) The present application is a continuation of U.S. patent application Ser. No. 17/447,041, now U.S. Pat. No. 11,776,861, filed Sep. 7, 2021, which application is incorporated herein by reference.

FIELD OF THE INVENTION

(1) The present invention relates in general to semiconductor devices and, more particularly, to a semiconductor device and method of forming a shielded semiconductor device using compartment shielding with a metal frame and cap.

BACKGROUND OF THE INVENTION

(2) Semiconductor devices are commonly found in modern electronic products. Semiconductor devices perform a wide range of functions such as signal processing, high-speed calculations, transmitting and receiving electromagnetic signals, controlling electronic devices, transforming sunlight to electricity, and creating visual images for television displays. Semiconductor devices are found in the fields of communications, power conversion, networks, computers, entertainment, and consumer products. Semiconductor devices are also found in military applications, aviation, automotive, industrial controllers, and office equipment.

(3) Semiconductor devices are often susceptible to electromagnetic interference (EMI), radio frequency interference (RFI), harmonic distortion, or other inter-device interference, such as capacitive, inductive, or conductive coupling, also known as cross-talk, which can interfere with their operation. High-speed analog circuits, e.g., radio frequency (RF) filters, or digital circuits also generate interference.

(4) Conductive layers are commonly formed over semiconductor packages to shield electronic parts within the package from EMI and other interference. The shielded components are encapsulated in an insulating molding compound, and then a conductive layer is sputtered onto the molding compound to form a shielding layer around the components. Shielding layers absorb EMI before the signals can hit semiconductor die and discrete components within the package, which might otherwise malfunction. Shielding layers are also formed over packages with components that are expected to generate EMI to protect nearby devices.

(5) One problem with prior art methods of semiconductor package shielding is that forming the shielding layer over encapsulated components is a complicated process involving several costly steps. Shielding components from intra-package interference is especially costly, requiring trenching of the encapsulant and deposition of metal to fill the trench. The encapsulant also limits thermal release of the underlying components, which causes problems for thermal budgets of devices. Moreover, the shielding layers formed on molding compound have durability issues and are susceptible to peeling off. Therefore, a need exists for an improved shielding mechanism for semiconductor packages.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) FIGS. **1a-1c** illustrate a semiconductor wafer with a plurality of semiconductor die separated by a saw street;
- (2) FIGS. **2a-2k** illustrate formation of a shielded semiconductor package using a metal frame and lid;
- (3) FIG. **3** illustrates a double-sided embodiment; and
- (4) FIGS. **4a** and **4b** illustrate integrating the shielded packages into an electronic device.

DETAILED DESCRIPTION OF THE DRAWINGS

(5) The present invention is described in one or more embodiments in the following description with reference to the figures, in which like numerals represent the same or similar elements. While the invention is described in terms of the best mode for achieving the invention's objectives, it will be appreciated by those skilled in the art that it is intended to cover alternatives, modifications, and equivalents as may be included within the spirit and scope of the invention as defined by the appended claims and their equivalents as supported by the following disclosure and drawings. The term "semiconductor die" as used herein refers to both the singular and plural form of the words, and accordingly, can refer to both a single semiconductor device and multiple semiconductor devices.

(6) Semiconductor devices are generally manufactured using two complex manufacturing processes: front-end manufacturing and back-end manufacturing. Front-end manufacturing involves the formation of a plurality of die on the surface of a semiconductor wafer. Each die on the wafer contains active and passive electrical components, which are electrically connected to form functional electrical circuits. Active electrical components, such as transistors and diodes, have the ability to control the flow of electrical current. Passive electrical components, such as capacitors, inductors, and resistors, create a relationship between voltage and current necessary to perform electrical circuit functions.

(7) Back-end manufacturing refers to cutting or singulating the finished wafer into the individual semiconductor die and packaging the semiconductor die for structural support, electrical interconnect, and environmental isolation. To singulate the semiconductor die, the wafer is scored and broken along non-functional regions of the wafer called saw streets or scribes. The wafer is singulated using a laser cutting tool or saw blade. After singulation, the individual semiconductor die are mounted to a package substrate that includes pins or contact pads for interconnection with other system components. Contact pads formed over the semiconductor die are then connected to contact pads within the package. The electrical connections can be made with conductive layers, bumps, stud bumps, conductive paste, bond wires, or other suitable interconnect structure. An encapsulant or other molding compound is deposited over the package to provide physical support and electrical isolation. The finished package is then inserted into an electrical system and the functionality of the semiconductor device is made available to the other system components.

(8) FIG. **1a** shows a semiconductor wafer **100** with a base substrate material **102**, such as silicon, germanium, aluminum phosphide, aluminum arsenide, gallium arsenide, gallium nitride, indium phosphide, silicon carbide, or other bulk semiconductor material. A plurality of semiconductor die or components **104** is formed on wafer **100** separated by a non-active, inter-die wafer area or saw street **106** as described above. Saw street **106** provides cutting areas to singulate semiconductor wafer **100** into individual semiconductor die **104**. In one embodiment, semiconductor wafer **100** has a width or diameter of 100-450 millimeters (mm).

(9) FIG. **1b** shows a cross-sectional view of a portion of semiconductor wafer **100**. Each semiconductor die **104** has a back or non-active surface **108** and an active surface **110** containing analog or digital circuits implemented as active devices, passive devices, conductive layers, and dielectric layers formed within or over the die and electrically interconnected according to the electrical design and function of the die. For example, the circuit may include one or more

transistors, diodes, and other circuit elements formed within active surface **110** to implement analog circuits or digital circuits, such as digital signal processor (DSP), ASIC, MEMS, memory, or other signal processing circuit. Semiconductor die **104** may also contain integrated passive devices (IPDs), such as inductors, capacitors, and resistors, for RF signal processing. Back surface **108** of semiconductor wafer **100** may undergo an optional backgrinding operation with a mechanical grinding or etching process to remove a portion of base material **102** and reduce the thickness of semiconductor wafer **100** and semiconductor die **104**.

(10) An electrically conductive layer **112** is formed over active surface **110** using PVD, CVD, electrolytic plating, electroless plating process, or other suitable metal deposition process. Conductive layers **112** include one or more layers of aluminum (Al), copper (Cu), tin (Sn), nickel (Ni), gold (Au), silver (Ag), or other suitable electrically conductive material. Conductive layer **112** operates as contact pads electrically connected to the circuits on active surface **110**.

(11) Conductive layer **112** can be formed as contact pads disposed side-by-side a first distance from the edge of semiconductor die **104**, as shown in FIG. **1b**. Alternatively, conductive layer **112** can be formed as contact pads that are offset in multiple rows such that a first row of contact pads is disposed a first distance from the edge of the die, and a second row of contact pads alternating with the first row disposed a second distance from the edge of the die. Conductive layer **112** represents the last conductive layer formed over semiconductor die **104** with contact pads for subsequent electrical interconnect to a larger system. However, there may be one or more intermediate conductive and insulating layers formed between the actual semiconductor devices on active surface **110** and contact pads **112** for signal routing.

(12) An electrically conductive bump material is deposited over conductive layer **112** using an evaporation, electrolytic plating, electroless plating, ball drop, or screen printing process. The bump material can be Al, Sn, Ni, Au, Ag, Pb, Bi, Cu, solder, and combinations thereof, with an optional flux solution. For example, the bump material can be eutectic Sn/Pb, high-lead solder, or lead-free solder. The bump material is bonded to conductive layer **112** using a suitable attachment or bonding process. In one embodiment, the bump material is reflowed by heating the material above its melting point to form conductive balls or bumps **114**. In one embodiment, conductive bumps **114** are formed over an under bump metallization (UBM) having a wetting layer, barrier layer, and adhesion layer. Conductive bumps **114** can also be compression bonded or thermocompression bonded to conductive layer **112**. Conductive bumps **114** represent one type of interconnect structure that can be formed over conductive layer **112** for electrical connection to a substrate. The interconnect structure can also use bond wires, conductive paste, stud bump, micro bump, or other electrical interconnect.

(13) In FIG. **1c**, semiconductor wafer **100** is singulated through saw street **106** using a saw blade or laser cutting tool **118** into individual semiconductor die **104**. The individual semiconductor die **104** can be inspected and electrically tested for identification of KGD post-singulation.

(14) FIGS. **2a-2k** illustrate forming shielded semiconductor packages **150** with semiconductor die **104**. FIG. **2a** is a partial cross-sectional view of a substrate **152** used as a base for manufacturing the packages. Substrate **152** can be a unit substrate singulated from a larger panel or remain as part of a larger substrate panel. Hundreds or thousands of packages are commonly formed in a single panel using the same steps described herein.

(15) Substrate **152** includes one or more insulating layers **154** interleaved with one or more conductive layers **156**. Insulating layer **154** is a core insulating board in one embodiment, with conductive layers **156** patterned over the top and bottom surfaces, e.g., a copper-clad laminate substrate. Conductive layers **156** also include conductive vias electrically coupled through insulating layers **154**. Substrate **152** can include any number of conductive and insulating layers interleaved over each other. A solder mask or passivation layer can be formed over either side of substrate **152**. Any suitable type of substrate or leadframe is used for substrate **152** in other embodiments.

(16) Any components desired to implement the intended functionality of packages **150** are mounted to or disposed over substrate **152** and electrically connected to conductive layers **156**. Substrate **152** has two major surfaces: top surface **157** and bottom surface **159**. Components can be mounted onto top surface **157** and bottom surface **159** in any suitable configuration.

(17) In FIG. **2b**, manufacturing of package **150** on substrate **152** commences with surface mounting of semiconductor die **104a** and discrete component **164** on bottom surface **159**. Bottom components are mounted first, but manufacturing could also proceed with components disposed on top surface **157** first. Discrete components **164**, e.g., resistors, capacitors, inductors, transistors, or diodes, are mounted on bottom surface **159** using solder paste or another suitable attachment and connection mechanism. Solder paste is reflowed between terminals of discrete components **164** and contact pads of conductive layers **156** on bottom surface **159**.

(18) In FIG. **2c**, substrate **152** is flipped and semiconductor die **104b**, semiconductor die **104c**, and additional discrete components **164** are mounted on top surface **157**. Semiconductor die **104a-104c** can all be identical semiconductor die from the same wafer **100**. In other embodiments, semiconductor die **104a** is a digital processor chip and semiconductor die **104b** and **104c** are flash memory or RAM chips that are connected to semiconductor die **104a** for use by the processor. Any suitable combination of active, passive, and integrated components can be mounted on top surface **157** and bottom surface **159** in any suitable configuration.

(19) FIGS. **2d** and **2e** show a metal frame **200** that will be mounted to top surface **157** of substrate **152** to facilitate shielding. FIG. **2d** is a view from below frame **200**, while FIG. **2e** is a view from above. Frame **200** is formed from a piece of sheet metal in one embodiment. The metal can be aluminum, steel, copper, titanium, gold, silver, alloys thereof, or any other suitable metal material. Non-metallic materials can be used in other embodiments. The sheet metal is cut to the proper shape and then folded into the structure seen in FIGS. **2d** and **2e**. The remaining flat sheet metal pieces after cutting and folding operate as a roof **202** for the frame.

(20) Cutting is used to form a plurality of openings **204** and flaps **206** in frame **200** prior to folding. Divots **208** are optionally formed into the sheet metal at the edges of flaps **206** to improve reliability of folding the flaps while the remainder of sheet metal remains flat. Divots **208** are semicircular shaped in the illustrated embodiment but could also be any suitable polygon. Notches **210** are formed at the edge of each flap **206**. Notches **210** result in flaps **206** having castellated edges. Flaps **206** are castellated. Notches **210** that are formed around the perimeter of frame **200** have holes **212** formed therethrough, which will be used to hold a lid onto frame **200**.

(21) The cutting of sheet metal into frame **200** can be performed using a laser cutter, die punch, or other suitable method. Flaps **206** are all folded at a 90-degree angle toward the bottom of frame **200** after cutting using any suitable manufacturing process. Alternatively, frame **200** can be molded, machined, or otherwise formed into the desired shape.

(22) FIG. **2f** shows a cross-section of frame **200** disposed or mounted onto or over top surface **157** of substrate **152** using, e.g., a pick and place operation. Flaps **206** are oriented downward around and between the mounted components so that the ends of the flaps contact substrate **152**. Roof **202** is oriented away from substrate **152**. Roof **202** reinforces the strength of frame **200** and makes handling during manufacture without damaging the frame more reliable.

(23) Flaps **206** are formed around the full perimeter of frame **200** to surround all components to be shielded. In addition, flaps **206** are optionally formed within frame **200** to separate the shielded area into multiple separately shielded compartments. Flaps **206** internal to frame **200**, i.e., not on the perimeter, provide shielding between components on top surface **157**, e.g., between die **104b** and die **104c**, so that the different components do not cause interference in each other.

(24) The areas of flaps **206** without notches **210** can be attached to conductive layer **156** of substrate **152** using solder **220** as shown in the partial cross-section of FIG. **2g**. The soldering can be performed using any suitable surface mount or other soldering technique. In one embodiment, solder **220** is disposed on contact pads of conductive layer **156** as solder paste prior to disposing

frame **200** onto the substrate and then reflowed to physically and electrically couple the frame to substrate **152**. Flaps **206** can be soldered continuously everywhere that the flaps meet substrate **200** or only a few select points can be soldered, e.g., just one point of solder **220** for each of the four corners.

(25) FIG. **2h** shows another partial cross-section through a notch **210**. Notches **210** provide gaps between frame **200** and substrate **152** so that de-ionized water used during flux cleaning flows out of the frame as indicated by arrow **224** rather than being trapped between substrate **152**, flaps **206**, and roof **202**. Any fluid used to clean or otherwise process packages **150** is able to escape frame **200** via notches **210**. Conductive layer **156** may extend under notches **210** or may include breaks as illustrated.

(26) FIG. **2i** shows a lid **230** that will be installed on frame **200** to complete the shielding functionality. Lid **230** is formed from sheet metal similarly to frame **200**. No holes are formed through top **232** as was done with holes **204** of frame **200** so that the sheet metal of the lid will create a complete cover over the components on substrate **152**. Alternatively, openings could be formed resulting in select underlying components not being shielded by lid **230**.

(27) Flaps **236** are formed around the perimeter of lid **230** by cutting the sheet metal into the desired shape as with frame **200**. Flaps **236** are folded at a 90-degree angle to form sidewalls for lid **230**. Indentations **242** are formed in the flaps **236** at locations that correspond in position to openings **212** of frame **200**. Flaps **236** are folded so that indentations **242** extend inward toward the interior of the lid.

(28) An inner width between flaps **236** of lid **230** is approximately equal to or slightly larger than an outer width between the perimeter flaps **206** of frame **200**. When lid **230** is disposed on frame **200** as shown in FIG. **2j**, flaps **236** slide around flaps **206**. Indentations **242** press against the outsides of flaps **206**, expanding flaps **236** of lid **230**. Once lid **230** is fully pressed down as shown in FIG. **2k**, flaps **236** spring inward with indentations **242** of the lid pressing partially into openings **212** of frame **200**. Lid **230** is secured by the elastic characteristic of the lid keeping indentations **242** pressed into openings **212**. While an indentation **242** is shown which is pressed into the outside of lid **230** creating a bump toward the inside, a protrusion could also be created oriented inward while leaving the outer surfaces of flaps **236** flat. Moreover, openings **212** could simply be an indentation instead of a hole formed completely through flaps **206**. Openings **212** and indentations **242** operate as a latch to secure lid **230**.

(29) Bumps **248** are added in FIG. **2k** for mounting package **140** onto a larger substrate of a device being manufactured. Bumps **248** are formed similarly to bumps **114** of die **104**. Substrate **152** is singulated if necessary. Package **150** in FIG. **2k** is a completed semiconductor package. The combination metal shield frame **200** and can lid **230** creates a complete compartmentalized EMI shield for package **150**. The combination of frame **200** and lid **230** extends over and around all components on top surface **157** of substrate **152** to provide thorough shielding. Flaps **206** also extend down between different components to compartmentalize the shielding and thereby reduce intra-package interference.

(30) Utilizing frame **200** and lid **230** eliminates the encapsulant that is commonly used for shielded components and reduces complexity of creating compartment shielding within the encapsulant. Frame **200** and lid **230** are also more reliable than the prior art methods due to the lid not being susceptible to peeling from encapsulant.

(31) FIG. **3** shows another embodiment where a second shield is formed over the components on bottom surface **159**. The bottom shield includes a frame with flaps **260** and roof **262** just as with frame **200** on top surface **157**. Additional flaps **260** are formed within the middle of the frame if desired to create compartmentalized shielding. Flaps **260** include all the same features from flaps **206**, e.g., castellated edges and openings to interface with bumps or indentations on lid **270**. Lid **270** including flaps **272** is disposed over the bottom frame to complete the bottom shield. Flaps **272** include bumps or indentations that extend into an opening or dent in flaps **260**. Bottom shield **260**-

272 can be disposed on bottom surface **159** immediately after the other bottom components are mounted in FIG. **2b**, or at any other manufacturing stage.

(32) FIGS. **4a** and **4b** illustrate incorporating the above-described semiconductor packages, e.g., package **150**, into an electronic device **300**. FIG. **4a** illustrates a partial cross-section of package **150** mounted onto a printed circuit board (PCB) or other substrate **302** as part of electronic device **300**. Bumps **248** are reflowed onto conductive layer **304** of PCB **302** to physically attach and electrically connect package **150** to the PCB. In other embodiments, thermocompression or other suitable attachment and connection methods are used. In some embodiments, an adhesive or underfill layer is used between package **150** and PCB **302**. Semiconductor die **104** are electrically coupled to conductive layer **304** through substrate **152** and bumps **248**.

(33) FIG. **4b** illustrates electronic device **300** including PCB **302** with a plurality of semiconductor packages mounted on a surface of the PCB, including package **150**. Electronic device **300** can have one type of semiconductor package, or multiple types of semiconductor packages, depending on the application. Electronic device **300** can be a stand-alone system that uses the semiconductor packages to perform one or more electrical functions. Alternatively, electronic device **300** can be a subcomponent of a larger system. For example, electronic device **300** can be part of a tablet computer, cellular phone, digital camera, communication system, or other electronic device. Electronic device **300** can also be a graphics card, network interface card, or another signal processing card that is inserted into a computer. The semiconductor packages can include microprocessors, memories, ASICs, logic circuits, analog circuits, RF circuits, discrete active or passive devices, or other semiconductor die or electrical components.

(34) In FIG. **4b**, PCB **302** provides a general substrate for structural support and electrical interconnection of the semiconductor packages mounted on the PCB. Conductive signal traces **304** are formed over a surface or within layers of PCB **302** using evaporation, electrolytic plating, electroless plating, screen printing, or other suitable metal deposition process. Signal traces **304** provide for electrical communication between the semiconductor packages, mounted components, and other external systems or components. Traces **304** also provide power and ground connections to the semiconductor packages as needed.

(35) In some embodiments, a semiconductor device has two packaging levels. First level packaging is a technique for mechanically and electrically attaching the semiconductor die to an intermediate substrate. Second level packaging involves mechanically and electrically attaching the intermediate substrate to PCB **302**. In other embodiments, a semiconductor device may only have the first level packaging where the die is mechanically and electrically mounted directly to PCB **302**.

(36) For the purpose of illustration, several types of first level packaging, including bond wire package **346** and flipchip **348**, are shown on PCB **302**. Additionally, several types of second level packaging, including ball grid array (BGA) **350**, bump chip carrier (BCC) **352**, land grid array (LGA) **356**, multi-chip module (MCM) **358**, quad flat non-leaded package (QFN) **360**, quad flat package **362**, and embedded wafer level ball grid array (eWLB) **364** are shown mounted on PCB **302** along with package **150**. Conductive traces **304** electrically couple the various packages and components disposed on PCB **302** to package **150**, giving use of the components within package **150** to other components on the PCB.

(37) Depending upon the system requirements, any combination of semiconductor packages, configured with any combination of first and second level packaging styles, as well as other electronic components, can be connected to PCB **302**. In some embodiments, electronic device **300** includes a single attached semiconductor package, while other embodiments call for multiple interconnected packages. By combining one or more semiconductor packages over a single substrate, manufacturers can incorporate pre-made components into electronic devices and systems. Because the semiconductor packages include sophisticated functionality, electronic devices can be manufactured using less expensive components and a streamlined manufacturing process. The resulting devices are less likely to fail and less expensive to manufacture resulting in a lower cost

for consumers.

(38) While one or more embodiments of the present invention have been illustrated in detail, the skilled artisan will appreciate that modifications and adaptations to those embodiments may be made without departing from the scope of the present invention as set forth in the following claims.

Claims

1. A method of making a semiconductor device, comprising: providing a substrate including a conductive layer formed on an external surface of the substrate; disposing a first semiconductor die on the external surface of the substrate, wherein the first semiconductor die is a bare die as singulated from a semiconductor wafer with base semiconductor material exposed at a back surface and a plurality of side surfaces of the first semiconductor die without encapsulant deposited over the first semiconductor die; forming a first metal frame by, forming a first opening through a sheet of metal including a first flap of the sheet extending into the first opening, wherein the first flap includes a castellated edge, and wherein the first opening includes a first divot directly adjacent to a first side of the first flap and a second divot directly adjacent to a second side of the first flap, forming a second opening through the sheet of metal including a second flap of the sheet extending into the second opening along a first edge of the second opening and a third flap of the sheet extending into the second opening along a second edge of the second opening perpendicular to the first edge, wherein a linear portion of the sheet metal between the first opening and second opening extends for an entire length or width of the first metal frame, wherein the first flap and second flap both extend in parallel with the linear portion, wherein the first flap includes a first long side physically contacting the linear portion for an entire length of the first flap and the second flap includes a second long side physically contacting the linear portion for an entire length of the second flap, and wherein the second flap and third flap include castellated edges, folding the first flap along the first long side relative to the linear portion, wherein the first flap remains connected to the linear portion along the entire first long side, and wherein the first divot and second divot remain extending into the linear portion after folding the first flap, folding the second flap along the second long side relative to the linear portion, wherein the second flap remains connected to the linear portion along the entire second long side, wherein the linear portion remains as a portion of a roof for the first metal frame after folding the first flap and second flap, folding the third flap, and folding an outer edge of the first metal frame as a fourth flap, wherein the fourth flap includes a castellated edge including a plurality of notches formed in the castellated edge; disposing the first metal frame over the substrate around the first semiconductor die, wherein the fourth flap is physically and electrically coupled to the substrate by a solder reflowed between the fourth flap and conductive layer, and wherein the conductive layer includes breaks under the notches of the castellated edge such that the conductive layer does not extend under the notches; and disposing a first metal lid over the first metal frame, wherein a flap of the first metal lid includes an elastic characteristic to latch onto the first metal frame.

2. The method of claim 1, further including: forming the first flap by, cutting across a first end of the first flap; cutting across a second end of the first flap opposite the second end, and cutting a second long side of the first flap from the first end to the second end, wherein the first long side of the first flap remains contacting the linear portion for an entire length of the first flap; and forming the second flap by, cutting across a first end of the second flap; cutting across a second end of the second flap opposite the second end, and cutting a second long side of the second flap from the first end to the second end, wherein the first long side of the second flap remains contacting the linear portion for an entire length of the second flap.

3. The method of claim 1, further including: forming a recess in the first metal frame; and forming a protrusion on the first metal lid, wherein the protrusion aligns to the recess when the first metal lid is latched onto the first metal frame.

4. The method of claim 1, further including forming a plurality of fourth flaps as part of the first metal frame, wherein each of the plurality of fourth flaps is folded to create sidewalls extending around a perimeter of the first metal frame.
5. The method of claim 1, wherein the first edge of the second opening is oriented toward a center of the first metal frame.
6. The method of claim 1, further including: disposing a second metal frame over an opposite surface of the substrate from the first metal frame; and disposing a second metal lid over the second metal frame, wherein a flap of the second metal lid includes an elastic characteristic to latch onto the second metal frame.
7. The method of claim 6, further including disposing a solder bump over the opposite surface of the substrate, wherein the solder bump extends from the opposite surface of the substrate to a height over the opposite surface of the substrate that is greater than a height of the second frame and second lid over the opposite surface of the substrate.
8. A method of making a semiconductor device, comprising: providing a substrate; disposing a first semiconductor die and second semiconductor die over a first surface of the substrate; disposing a first discrete component on the first surface of the substrate adjacent to the first semiconductor die; disposing a second discrete component on the first surface of the substrate adjacent to the second semiconductor die; disposing a first frame over the first surface of the substrate around the semiconductor die, wherein the first frame includes an opening and a flap formed at an edge of the opening, and wherein the flap includes a castellated edge, and wherein the flap is disposed with the first discrete component and first semiconductor die on a first side of the flap and the second discrete component and second semiconductor die on a second side of the flap; disposing a first lid over the first frame, wherein a sidewall of the first lid includes an elastic characteristic to latch onto the first frame; disposing a third semiconductor die over a second surface of the substrate opposite the first surface, wherein the first semiconductor die, second semiconductor die, and third semiconductor die are identical semiconductor die singulated from a common semiconductor wafer; disposing a third discrete component on the second surface of the substrate adjacent to the third semiconductor die; disposing a second frame over the second surface of the substrate, wherein the second frame includes an internal flap to compartmentalize shielding provided by the second frame; disposing a second lid over the second frame, wherein a sidewall of the second lid includes an elastic characteristic to latch onto the second frame; and disposing a solder bump over the second surface of the substrate, wherein the solder bump is a continuous body of solder that extends from the substrate to a height over the second surface of the substrate that is greater than a height of the second frame and second lid over the second surface of the substrate.
9. The method of claim 8, further including forming a notch in a sidewall of the first frame.
10. The method of claim 8, wherein a portion of the first frame remains between the opening and the sidewall as a roof.
11. The method of claim 8, further including: forming an indentation in the first lid; and pressing the first lid onto the first frame until the indentation aligns to a second opening of the first frame.
12. The method of claim 8, wherein the frame includes a plurality of compartments.
13. The method of claim 8, further including attaching the first frame to the substrate using solder.
14. A semiconductor device, comprising: a substrate; a first semiconductor die disposed over the substrate, wherein the first semiconductor die is a bare die as singulated from a semiconductor wafer with base semiconductor material exposed at a back surface and a plurality of side surfaces of the first semiconductor die without encapsulant deposited over the first semiconductor die; a metal frame disposed over the substrate around the first semiconductor die, wherein the metal frame includes, a first opening, a first flap formed at an edge of the first opening, wherein the first opening includes a first divot directly adjacent to a first side of the first flap and a second divot directly adjacent to a second side of the first flap, and wherein the first flap includes a castellated edge, a second opening, a second flap formed at an edge of the second opening, wherein the second

flap includes a castellated edge, and a linear portion that extends for an entire length or width of the first metal frame between the first opening and second opening, wherein the first flap and second flap both extend in parallel with the linear portion and include respective long sides physically contacting the linear portion for an entire length of the respective first flap or second flap, and wherein the first divot and second divot extend into the linear portion; and a metal lid disposed over the metal frame, wherein a sidewall of the metal lid includes an elastic characteristic to latch onto the metal frame.

15. The semiconductor device of claim 14, further including a second semiconductor die disposed over the substrate, wherein the first flap or second flap is disposed between the first semiconductor die and second semiconductor die.

16. The semiconductor device of claim 14, further including: a recess formed in the metal frame; and a protrusion formed on the metal lid, wherein the protrusion extends into the recess.

17. The semiconductor device of claim 14, wherein the metal frame includes a plurality of third flaps, and wherein each of the plurality of third flaps is folded to create sidewalls extending around a perimeter of the metal frame.

18. The semiconductor device of claim 14, wherein the edge of the first opening is oriented toward a center of the frame.

19. A semiconductor device, comprising: a substrate; a first semiconductor die disposed over a first surface of the substrate; a second semiconductor die disposed over the first surface of the substrate; a first discrete component disposed on the first surface of the substrate adjacent to the first semiconductor die; a second discrete component disposed on the first surface of the substrate adjacent to the second semiconductor die; a first frame disposed over the first surface of the substrate around the semiconductor die, wherein the first frame includes a flap folded down with the first discrete component and first semiconductor die on a first side of the flap and the second discrete component and second semiconductor die on a second side of the flap, and wherein the flap includes a castellated edge; a first lid disposed over the first frame, wherein a sidewall of the first lid includes an elastic characteristic to latch onto the first frame; a third semiconductor die disposed over a second surface of the substrate opposite the first surface; a third discrete component disposed on the second surface of the substrate adjacent to the third semiconductor die; a second frame disposed over the second surface of the substrate around the third semiconductor die and third discrete component, wherein the second frame includes an internal flap to compartmentalize shielding provided by the second frame; a second lid disposed over the second frame, wherein a sidewall of the second lid includes an elastic characteristic to latch onto the second frame; and a solder bump directly attached to the second surface of the substrate, wherein a height of the solder bump over the second surface is greater than a height of the second frame and second lid.

20. The semiconductor device of claim 19, further including a notch in a sidewall of the first frame.

21. The semiconductor device of claim 20, further including an opening formed through the first frame, wherein a portion of the first frame remains between the opening and the sidewall of the first frame as a roof.

22. The semiconductor device of claim 19, further including: an opening formed in the first frame; and an indentation formed in the first lid, wherein the indentation extends into the opening.

23. The semiconductor device of claim 19, wherein the first frame includes a plurality of compartments.

24. The semiconductor device of claim 19, further including a solder material connecting the first frame to the substrate.
