

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12414359
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Leng; Yaojian

Integrated circuit structure including a metal-insulator-metal (MIM) capacitor module and a thin-film resistor (TFR) module

Abstract

An integrated circuit structure including a metal-insulator-metal (MIM) capacitor module and a thin-film resistor (TFR) module is provided. The MIM capacitor module includes a bottom electrode base formed in a lower metal layer, a bottom electrode formed in a dielectric region between the lower metal layer and an upper metal layer, an insulator formed over the bottom electrode, and a top electrode formed in the upper metal layer over the insulator. The bottom electrode includes a cup-shaped bottom electrode component and a bottom electrode fill component formed in an interior opening defined by the cup-shaped bottom electrode component. The TFR module includes a pair of metal heads formed in the dielectric region and a resistor element connected across the pair of metal heads. Each metal head includes a cup-shaped head component and a head fill component formed in an interior opening defined by the cup-shaped head component.

Inventors:	Leng; Yaojian (Vancouver, WA)
Applicant:	Microchip Technology Incorporated (Chandler, AZ)
Family ID:	85480318
Assignee:	Microchip Technology Incorporated (Chandler, AZ)
Appl. No.:	17/536597
Filed:	November 29, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20230081749 A1	Mar. 16, 2023

Related U.S. Application Data

Publication Classification

Int. Cl.: **H10D84/80** (20250101); **H01L23/522** (20060101); **H01L23/532** (20060101); **H10D1/00** (20250101); **H10D1/68** (20250101); **H10D84/01** (20250101); H01L21/768 (20060101); H10D1/47 (20250101); H10D84/00 (20250101); H10D86/80 (20250101)

U.S. Cl.:

CPC **H10D84/811** (20250101); **H01L23/5223** (20130101); **H01L23/5226** (20130101); **H01L23/5228** (20130101); **H01L23/53266** (20130101); **H10D1/00** (20250101); **H10D1/696** (20250101); **H10D84/01** (20250101); H01L21/7684 (20130101); H01L21/76843 (20130101); H01L21/76885 (20130101); H10D1/47 (20250101); H10D1/68 (20250101); H10D1/692 (20250101); H10D84/206 (20250101); H10D86/80 (20250101)

Field of Classification Search

CPC: H01L (23/481); H01L (21/76898); H01L (2225/06544); H01L (25/0657); H01L (28/40); H01L (28/20); H01L (28/60); H01L (21/7687); H01L (23/5226); H01L (28/00); H01L (21/7684); H01L (21/76843); H01L (21/76885); H01L (23/5223); H01L (23/5228); H01L (23/53266); H01L (23/647); H01L (27/016); H10D (84/206); H10D (1/00); H10D (1/696); H10D (84/01); H10D (1/47); H10D (1/68); H10D (1/692); H10D (86/80); H10D (84/811)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
6365480	12/2001	Huppert et al.	438/381	N/A
11769793	12/2022	Leng	257/532	H01L 23/5226
2002/0163029	12/2001	Dirnecker et al.	257/306	N/A
2002/0179955	12/2001	Morimoto	257/E21.582	H01L 23/5223
2002/0197844	12/2001	Johnson	257/E21.582	H01L 23/5228
2005/0067701	12/2004	Coolbaugh et al.	257/751	N/A
2007/0138531	12/2006	Tu	257/E27.087	H10D 1/716
2007/0152258	12/2006	Kim	257/E21.011	H01L 23/5223
2011/0032659	12/2010	Dunn	216/6	H01G 4/1209
2015/0348908	12/2014	Nagakura	257/536	H01L 23/528
2016/0197135	12/2015	Hao et al.	257/537	N/A
2016/0218062	12/2015	Aggarwal et al.	257/537	N/A
2019/0392967	12/2018	Leng et al.	N/A	N/A

OTHER PUBLICATIONS

International Search Report and Written Opinion, Application No. PCT/US2022/019450, 11 pages, Jun. 13, 2022. cited by applicant
German Office Action, Application No. 112022004397.0, 9 pages Jun. 27, 2025. cited by applicant

Primary Examiner: Feliciano; Eliseo Ramos

Assistant Examiner: Knudson; Brad A

Attorney, Agent or Firm: SLAYDEN GRUBERT BEARD PLLC

Background/Summary

RELATED PATENT APPLICATION (1) This application claims priority to commonly owned U.S. Provisional Patent Application No. 63/244,366 filed Sep. 15, 2021, the entire contents of which are hereby incorporated by reference for all purposes.

TECHNICAL FIELD

(1) The present disclosure relates to analog components formed in integrated circuit devices, and more particularly to an integrated circuit structure including a metal-insulator-metal (MIM) capacitor module and a thin-film resistor (TFR) module.

BACKGROUND

(2) Capacitors and resistors formed monolithically in integrated circuit devices are referred to as integrated capacitors and resistors, respectively. Integrated capacitors and resistors are common elements in many integrated circuit devices. For example, various analog, mixed signal, and RF-CMOS (radio-frequency complimentary metal-oxide-semiconductor) integrated circuit devices use integrated capacitors and resistors, either separately or in combination with each other. Integrated capacitors and resistors may offer various advantages over discrete counterparts (i.e., off-chip capacitors and resistors). For example, as compared with typical discrete (off-chip) capacitors and resistors, integrated capacitors and resistors may often be produced at lower cost. Additionally, system-on-chip devices including integrated capacitors and resistors may have a reduced pin count (which may provide improved ease-of-use and form factor), and may exhibit a reduced parasitic capacitance.

(3) MIM capacitor modules are typically constructed between two interconnect metal layers (e.g., aluminum layers), referred to as metal layers $M_{\text{sub}.x}$ and $M_{\text{sub}.x+1}$. For example, a MIM capacitor module may be formed using an existing metal layer $M_{\text{sub}.x}$ as the bottom electrode (bottom plate), constructing an insulator and a top electrode (top plate) over the bottom electrode, and connecting an overlying metal layer $M_{\text{sub}.x+1}$ to the top and bottom electrodes by respective vias. The top electrode formed between the two metal layers $M_{\text{sub}.x}$ and $M_{\text{sub}.x+1}$ may be formed from a different metal than the metal layers $M_{\text{sub}.x}$ and $M_{\text{sub}.x+1}$. For example, the metal layers $M_{\text{sub}.x}$ and $M_{\text{sub}.x+1}$ may be formed from aluminum, whereas the top electrode may be formed from titanium/titanium nitride (Ti/TiN), tantalum/tantalum nitride (Ta/TaN), or tungsten (W), for example.

(4) The top electrode typically has a higher resistance than the bottom electrode, for example because the top electrode may be limited by thickness constraints and the material of choice, thus limiting the performance of conventional MIM capacitor modules. MIM capacitor modules typically have very narrow process margins, particularly for a metal etch used to form the top electrode.

(5) In addition, for MIM capacitor modules formed in aluminum interconnect (i.e., where metal layers $M_{\text{sub}.x}$ and $M_{\text{sub}.x+1}$ comprise aluminum interconnect layers), the aluminum bottom electrode may be susceptible to hillock formation at a top side of the bottom electrode, e.g., resulting from high-temperature processing of aluminum, a low-melting-point metal. Hillocks formed on the bottom electrode may negatively or unpredictably affect the breakdown voltage of the MIM capacitor module.

(6) FIGS. 1A-1F show cross-sectional side views of an example prior art process for forming an MIM capacitor module **10**. As shown in FIG. 1A, a metal interconnect layer M.sub.x is formed over a dielectric region, e.g., an inter-metal dielectric (IMD) layer indicated as IMD.sub.x. Metal layer M.sub.x may be formed from aluminum or other suitable metal.

(7) Next, as shown in FIG. 1B, an insulator layer **100** is deposited, followed by a top electrode layer **102** from which a top electrode (top plate) of the MIM capacitor module **10** is formed, as shown in FIG. 1C discussed below. The insulator layer **100** may comprise silicon nitride (Si.sub.3N.sub.4, also referred to more simply as SiN) with a thickness T.sub.ins of about 500 Å, which may be deposited by a plasma enhanced chemical vapor deposition (PECVD) process. The top electrode layer **102** may comprise titanium nitride (TiN), tantalum (Ta), tantalum nitride (TaN), or other suitable metal with thickness T.sub.te of about 2000 Å. The thickness T.sub.te of the top electrode layer **102**, which defines the thickness of the capacitor top electrode **108** (see FIG. 1C), is typically limited by the thickness of a subsequently formed IMD layer IMD.sub.x+1 (shown in FIG. 1F discussed below). In addition, an etch margin of the top electrode etch (see FIG. 1C, discussed below), and a process margin of a subsequent chemical mechanical planarization (CMP), for example, may contribute to the limitation on the thickness T.sub.te of the top electrode layer **102**. For a typical IMD.sub.x+1 layer thickness of 8000 Å, the thickness T.sub.te of the top electrode **102** may be limited to about 3000 Å or less. This limited thickness T.sub.te of the top electrode layer **102** (and thus capacitor top electrode **108**) can result in a high series resistance and low quality factor (Q-factor) for certain applications, e.g., radio frequency (RF) applications.

(8) After the insulator layer **100** and top electrode layer **102** are deposited, information printed in the wafer scribe region of the underlying silicon substrate may be very difficult to read (through top electrode layer **102**, the insulator layer **100**, and underlying metal layer M.sub.x), which can cause manufacturing problems. For example, the wafer lot number and/or wafer number printed in the wafer scribe region may be difficult to read, which may cause various problems, e.g., inability to run controlled experiments with designated wafers split among different process conditions or record wafer activities (e.g., scrap or incident events) tied to wafer number.

(9) Next, as shown in FIG. 1C, a photoresist layer is deposited and patterned to form a first photomask **106** over the top electrode layer **102**, and an etch is performed to define the MIM capacitor top electrode **108** from the top electrode layer **102**, wherein the portion of the insulator layer **100** below the MIM capacitor top electrode **108** defines the MIM capacitor insulator, indicated at **100a**. The top electrode etch typically has a very small process margin. In particular, the etch is designed to stop approximately halfway through the thickness T.sub.ins of the insulator layer **100**.

(10) The precise depth of the top electrode etch, which defines the thickness T.sub.ins_etched of the remaining insulator layer **100** outside the footprint of the top electrode **108**, indicated as etched insulator layer region **100b**, is typically sensitive to specific process parameters, such as silicon nitride deposition thickness and non-uniformity, and etch uniformity and selectivity, for example. If the etch is insufficiently deep (such that T.sub.ins_etched of the etched insulator layer region **100b** is too thick), the top electrode layer **102** may not be completely removed in some areas on the wafer (e.g., due to non-uniformity of the etch across the wafer), thus leaving metal residue or stringers on the wafer. These metal residue or stringers may cause incomplete etching in a subsequent metal etch step, create metal shorts, and lead to device yield loss or reliability failure.

(11) On the other hand, if the top electrode etch is too deep (such that T.sub.ins_etched of the etched insulator layer region **100b** is too thin), the resulting MIM capacitor module **10** may have an unsuitably low breakdown voltage, in particular due to the corner “C” formed in the insulator layer **100** by the top electrode etch discussed above, as discussed below with respect to FIG. 1F.

(12) Thus, the effective margin for the thickness T.sub.ins_etched of the etched insulator layer region **100b** may be very small, thereby defining small process margins for the top electrode etch. For example, for a deposited silicon nitride insulator layer having a thickness T.sub.ins of 500A, an

effective target thickness $T_{\text{sub.ins_etched}}$ of the etched insulator layer region **100b** may have a very small margin, for example between 230-270 Å.

(13) Next, as shown in FIG. 1D, remaining portions of the first photomask **106** are removed and a new photoresist layer is deposited and patterned to form a second photomask **112** over the top electrode **108** and extending beyond the top electrode **108** in a first lateral direction.

(14) Next, as shown in FIG. 1E, a metal etch is performed to define the MIM capacitor bottom electrode **116**.

(15) Finally, as shown in FIG. 1F, construction of the MIM capacitor module **10** is completed by removing the second photomask **112**, forming an IMD layer (IMD.sub.x+1), forming vias **120** respectively contacting the top electrode **108** and bottom electrode **116**, and forming a top electrode contact **122** and a bottom electrode contact **124** in a metal layer M.sub.x+1 over the IMD.sub.x+1 layer.

(16) The prior art MIM capacitor module **10** may suffer from various shortcomings. For example, as noted above, the thickness $T_{\text{sub.te}}$ of the top electrode **108** may be limited due to a vertical spacing limitation between metal layers M.sub.x and M.sub.x+1, represented by the thickness $T_{\text{sub.IMDx+1}}$ of the IMD.sub.x+1 region. The limited thickness $T_{\text{sub.te}}$ of the top electrode **108** may result in high serial resistance unsuitable for certain applications (e.g., RF applications).

(17) In addition, the MIM capacitor module **10** may have a low and/or unpredictable breakdown voltage. For example, the capacitor breakdown voltage may be very sensitive to the thickness $T_{\text{sub.ins_etched}}$ of the etched insulator layer region **100b**, particularly at the corner C below the lateral edge of the top electrode **108**, as discussed above. In addition, the capacitor breakdown voltage may also be sensitive to hillocks “H” formed on the capacitor bottom electrode **116**. Hillock formation may be very difficult to control in the fabrication process discussed above. For example, hillocks H may form on the bottom electrode **116** as a result of various heated process steps during and after the capacitor module fabrication, including heat treatment steps and/or heated aluminum deposition steps (e.g., performed at 400° C.). These hillocks H may create an uncontrolled low breakdown voltage of the capacitor module **10**.

(18) In addition, as noted above, the deposition of the various material layers (lower metal layer, insulation layer, and top electrode layer) over the wafer scribe region may hinder the ability to read information printed in the wafer scribe region (e.g., wafer number and lot number), which may complicate the manufacturing process.

(19) Turning now to integrated resistors, one common type is the thin-film resistor (TFR) module, which includes a pair of metal heads connected by a resistor element, or TFR film.

(20) FIG. 2 shows a cross-sectional view of two example TFR modules **200A** and **200B** implemented using conventional techniques. The fabrication of a conventional TFR module **200A** or **200B** typically requires three added mask layers, with reference to a background fabrication process for the relevant IC device. In particular, a first added mask layer may be used to create metal heads **202A** and **202B**, a second added mask layer may be used to create a resistor element **204**, and a third added mask layer may be used to create TFR vias **206A** and **206B**. As shown, the resistor element **204** of TFR module **200A** is formed across the top of the metal heads **202A** and **202B**, while the resistor element **204** of TFR module **200B** is formed across the bottom of the metal heads **202A** and **202B**, but each design typically uses three added mask layers.

(21) TFR modules and MIM capacitor modules are often expensive to construct. For example, as discussed above, the process for forming an MIM capacitor module or TFR module often includes multiple additional mask layer to the background IC fabrication process. Also, MIM capacitor modules and TFR modules are typically constructed independent of each other, further compounding the number of additional mask layers needed to form both types of devices in an integrated circuit device.

(22) There is a need to build integrated capacitors and resistors, in particular to construct MIM capacitor modules and TFR modules together, efficiently and at reduced cost as compared with

conventional processes.

SUMMARY

(23) The present disclosure provides an integrated circuit (IC) structure including both an MIM capacitor module and a TFR module formed concurrently in a dielectric region between two metal layers in the IC structure, e.g., an inter-metal dielectric (IMD) region or a pre-metal dielectric (PMD) region. In some examples, the IC structure also includes at least one interconnect structure formed in the dielectric region between the two metal layers in the IC structure, concurrently with the MIM capacitor module and the TFR module.

(24) As used herein, a structure formed “between” two metal layers (e.g., an MIM capacitor module, TFR module, and/or interconnect structure formed between two layers, as disclosed herein) refers to a structure including (a) at least one component formed in a dielectric region between two metal layers and (b) at least one component formed in one or both of the two metal layers.

(25) One aspect provides an integrated circuit structure including an MIM capacitor module and a TFR module. The MIM capacitor module includes a bottom electrode base formed in a lower metal layer, a bottom electrode formed in a dielectric region between the lower metal layer and an upper metal layer, an insulator formed over the bottom electrode, and a top electrode formed in the upper metal layer over the insulator. The bottom electrode includes a cup-shaped bottom electrode component, and a bottom electrode fill component formed in an interior opening defined by the cup-shaped bottom electrode component. The TFR module includes a pair of metal heads formed in the dielectric region between the lower metal layer and the upper metal layer, and a resistor element connected across the pair of metal heads. Each metal head of the pair of metal heads includes a cup-shaped head component, and a head fill component formed in an interior opening defined by the cup-shaped head component.

(26) In one example, the TFR module includes a pair of head bases formed in the lower metal layer, wherein each metal head is conductively connected to a respective head base.

(27) In one example, the cup-shaped head component of each metal head and the cup-shaped bottom electrode component are formed from a conformal metal, and the head fill component of each metal head and the bottom electrode fill component are formed from a fill metal different than the conformal metal. In one example, the conformal metal comprises tungsten, and the fill metal comprises titanium nitride.

(28) In one example, the insulator has a uniform vertical thickness across a full lateral width of the insulator.

(29) In one example, the insulator is formed over a planarized support surface including a planarized top surface of the cup-shaped bottom electrode component and a planarized top surface of the bottom electrode fill component.

(30) In one example, the insulator is formed on a planarized support surface including (a) a planarized top surface of the cup-shaped bottom electrode component, (b) a planarized top surface of the bottom electrode fill component, and (c) planarized top surface areas of the dielectric region on opposite sides of the bottom electrode, and the insulator extends laterally across and beyond a full width of the bottom electrode, such that the insulator extends over the planarized top surface areas of the dielectric region on opposite sides of the bottom electrode.

(31) In one example, the thin-film resistor module includes a resistor element insulator cap element formed on the resistor element, and the resistor element insulator cap element is formed from a common insulator material as the insulator.

(32) In one example, the lower metal layer comprises a lower interconnect layer, and the upper metal layer comprises an upper interconnect layer. In another example, the lower metal layer comprises a silicided polysilicon layer, wherein the bottom electrode base formed in the lower metal layer comprises a metal silicide region formed on a polysilicon region, and the upper metal layer comprises a first metal interconnect layer.

- (33) In one example, the metal-insulator-metal capacitor module includes a bottom electrode connection element formed in the upper metal layer, and a bottom electrode contact formed in the dielectric region between the lower metal layer and the upper metal layer. The bottom electrode contact provides a conductive connection between the bottom electrode connection element formed in the upper metal layer and the bottom electrode base formed in the lower metal layer.
- (34) In some examples, the integrated circuit structure includes an interconnect structure including a lower interconnect element formed in the lower metal layer, and an upper interconnect contact formed in the upper metal layer and connected to the lower interconnect element by at least one interconnect via. In one example, the at least one interconnect via and the cup-shaped bottom electrode component are formed from a common conformal metal.
- (35) Another aspect provides a method of forming an integrated circuit structure. The method includes forming a lower metal layer including a bottom electrode base, depositing a dielectric region over the lower metal layer, patterning and etching the dielectric region to form a bottom electrode tub opening and a pair of head tub openings, and forming a bottom electrode in the bottom electrode tub opening, wherein the bottom electrode includes a cup-shaped bottom electrode component and a bottom electrode fill component in an interior opening defined by the cup-shaped bottom electrode component. The method also includes forming a metal head in each of the pair of head tub openings, wherein each metal head includes a cup-shaped head component and a head fill component in an interior opening defined by the cup-shaped head component. The method also includes forming an insulator over the bottom electrode, forming a resistor element connected across the pair of metal heads, and forming an upper metal layer including a top electrode over the insulator.
- (36) In one example, the method includes performing a planarization process to define a planarized support surface including a planarized top surface of the cup-shaped bottom electrode component and a planarized top surface of the bottom electrode fill component, and forming the insulator over the planarized support surface.
- (37) In one example, the method includes forming the insulator with a uniform vertical thickness across a full lateral width of the insulator.
- (38) In one example, the method includes performing a planarization process to define a planarized support surface including (a) a planarized top surface of the cup-shaped bottom electrode component, (b) a planarized top surface of the bottom electrode fill component, and (c) planarized top surface areas of the dielectric region on opposite sides of the bottom electrode. The insulator extends laterally across and beyond a full width of the bottom electrode, such that the insulator extends over the planarized top surface areas of the dielectric region on opposite sides of the bottom electrode.
- (39) Another aspect provides a method of forming an integrated circuit structure. The method includes forming a lower metal layer including a bottom electrode base and a pair of head bases, forming a dielectric region over the lower metal layer, forming openings in the dielectric region, including (a) a bottom electrode opening and (b) a pair of head openings, depositing a conformal metal extending into the bottom electrode opening and into each head opening, and depositing a fill metal over the conformal metal layer and extending into the electrode opening and into each head opening. The method also includes performing a planarization process to remove portions of both the conformal metal and the fill metal, wherein (a) remaining portions of the conformal metal and fill metal in the bottom electrode opening define a bottom electrode including (i) a cup-shaped bottom electrode component and (ii) a bottom electrode fill component in an interior opening defined by the cup-shaped bottom electrode component, and (b) remaining portions of the conformal metal and fill metal in each of the pair of head openings define a pair of metal heads, each metal head including (i) a cup-shaped head component and (ii) a head fill component in an interior opening defined by the cup-shaped head component. The method also includes forming an insulator over the bottom electrode, forming a resistor element spanning the pair of metal heads,

and forming an upper metal layer including a top electrode over the insulator.

(40) In one example, the method includes forming the insulator with a uniform vertical thickness across a full lateral width of the insulator.

(41) In one example, the planarization process defines a planarized support surface including a planarized top surface of the cup-shaped bottom electrode component and a planarized top surface of the bottom electrode fill component, and the insulator is formed on the planarized support surface.

(42) In one example, the planarization process defines a planarized support surface including (a) a planarized top surface of the cup-shaped bottom electrode component, (b) a planarized top surface of the bottom electrode fill component, and (c) planarized top surface areas of the dielectric region on opposite sides of the bottom electrode. The insulator extends laterally across and beyond a full width of the bottom electrode, such that the insulator extends over the planarized top surface areas of the dielectric region on opposite sides of the bottom electrode.

(43) In one example, the method includes forming an insulator layer over the bottom electrode and over the pair of metal heads, and etching the insulator layer to form (a) the insulator over the bottom electrode and (b) an insulator cap element over the resistor element.

(44) In one example, forming the upper metal layer includes forming (a) the top electrode over the insulator and (b) a metal cap element over the insulator cap element.

(45) In one example, the method includes depositing a resistor film over the bottom electrode and over the pair of metal heads, depositing an insulator layer over the resistor film, and after depositing an insulator layer over the resistor film, patterning and etching the resistor film and the insulator layer. Remaining portions of the resistor film define (a) a resistor film region over the bottom electrode and (b) the resistor element spanning the pair of metal heads, and remaining portions of the insulator layer define (a) the insulator over the bottom electrode and (b) an insulator cap element over the resistor element.

(46) In one example, the lower metal layer comprises a lower interconnect layer, and the upper metal layer comprises an upper interconnect layer.

(47) In one example, the lower metal layer comprises a silicided polysilicon layer, wherein each of (a) the bottom electrode base and (b) each head base comprises a metal silicide region formed on a respective polysilicon region, and the upper metal layer comprises a first metal interconnect layer.

(48) In one example, the method includes forming an interconnect via opening in the dielectric region, and depositing the conformal metal into the interconnect via opening, wherein a portion of the conformal metal in the interconnect via opening after the planarization process defines an interconnect via, and wherein the interconnect via conductively connects a lower interconnect element formed in the lower metal layer to an upper interconnect element formed in the upper metal layer.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Example aspects of the present disclosure are described below in conjunction with the figures, in which:

(2) FIGS. 1A-1F are cross-sectional side views showing an example prior art process for forming an example MIM capacitor module;

(3) FIG. 2 is a cross-sectional view of two example prior art thin-film resistors (TFR);

(4) FIG. 3A is a cross-sectional side view an example integrated structure including an example MIM capacitor module, TFR module, and interconnect structure formed between two metal interconnect layers in an integrated circuit structure, according to one example;

(5) FIG. 3B is a cross-sectional side view an example integrated structure including an example

MIM capacitor module, TFR module, and interconnect structure formed between a silicided polysilicon layer and a first metal interconnect layer in an integrated circuit structure, according to one example;

(6) FIGS. 4-13 are cross-sectional side views showing an example process of forming an integrated circuit structure including the example MIM capacitor module, TFR module and interconnect structure shown in FIG. 3A along with an example interconnect structure;

(7) FIG. 14 is a flowchart showing an example method of forming an example integrated circuit structure including an example MIM capacitor module and an example TFR module, according to one example; and

(8) FIGS. 15A-15B illustrate a flowchart showing another example method of forming an example integrated circuit structure including an example MIM capacitor module and an example TFR module, according to another example.

(9) It should be understood the reference number for any illustrated element that appears in multiple different figures has the same meaning across the multiple figures, and the mention or discussion herein of any illustrated element in the context of any particular figure also applies to each other figure, if any, in which that same illustrated element is shown.

DETAILED DESCRIPTION

(10) The present disclosure provides an integrated circuit (IC) structure including both an MIM capacitor module and a TFR module formed in a dielectric region between two metal layers in the IC structure, e.g., an inter-metal dielectric (IMD) region or a pre-metal dielectric (PMD) region.

(11) The MIM capacitor module includes (a) a bottom electrode base formed in a lower metal layer M.sub.x, (b) a bottom electrode conductively coupled to the bottom electrode base, (c) an insulator formed over the bottom electrode, and (d) a top electrode formed in an upper metal layer M.sub.x+1 over the insulator. The MIM capacitor module may also include (e) a bottom electrode connection element formed in the upper metal layer M.sub.x+1, and (f) a bottom electrode contact conductively connecting the bottom electrode connection element to the bottom electrode base.

(12) The TFR module includes (a) a pair of head bases formed in the lower metal layer M.sub.x, (b) a pair of metal heads, each conductively connected to one of the head bases, and (c) a resistor element spanning across and conductively connected to the pair of metal heads. The TFR module may also include a resistor element insulator cap element over the resistor element, and a metal cap element over the resistor element insulator cap element, wherein the resistor element insulator cap element is formed from a common resistor film as the insulator of the MIM capacitor module and the metal cap element is formed in the same upper metal layer M.sub.x+1 as the top electrode and bottom electrode contact of the MIM capacitor module.

(13) Thus, the bottom electrode of the MIM capacitor module and each metal head of the TFR module are formed between the lower metal layer M.sub.x and upper metal layer M.sub.x+1. In addition, the bottom electrode and each metal head may be formed as a multi-component structure using a damascene process. The bottom electrode of the MIM capacitor module may include a cup-shaped bottom electrode component and a bottom electrode fill component formed in an interior opening defined by the cup-shaped bottom electrode component. Similarly, each metal head of the TFR module may include a cup-shaped head component and a head fill component formed in an interior opening defined by the cup-shaped head component. The cup-shaped bottom electrode component of the bottom electrode, and the cup-shaped head component of each metal head of the TFR module, may be formed from a common conformal metal, e.g., tungsten. The bottom electrode fill component of the bottom electrode, and the head fill component of each metal head of the TFR module, may be formed from a fill metal, e.g., titanium nitride.

(14) The insulator of the MIM capacitor module may be formed on a planarized support surface (e.g., including a planarized upper surface of the bottom electrode). The insulator may have a uniform thickness across a full lateral width of the insulator, which may provide an improved capacitor breakdown voltage as compared with certain conventional capacitor modules. In addition,

by forming the bottom electrode from refractory metals, e.g., tungsten and titanium nitride, the top surface of the bottom electrode that interfaces the insulator may be free of hillocks that are common in certain conventional capacitors (e.g., capacitor modules using an aluminum bottom electrode), which may provide a higher and more consistent capacitor breakdown voltage as compared with such conventional capacitor modules. Also, the top electrode and the bottom electrode may each have a substantial thickness, e.g., a thickness of at least 4000 Å, which may provide improved performance in particular applications (e.g., RF applications) as compared with certain conventional capacitor modules having a thinner top electrode and/or bottom electrode.

(15) As mentioned above, the MIM capacitor module and TFR module are formed between two metal layers, in particular the lower metal layer M.sub.x (in which the bottom electrode base of the MIM capacitor, and the pair of head bases of the TFR module, are formed) and an upper metal layer M.sub.x+1 (in which the top electrode and bottom electrode connection element of the MIM capacitor module, and the metal cap element over the resistor element of the TFR module, are formed). As used herein, a “metal layer,” for example in the context of the lower metal layer M.sub.x and upper metal layer M.sub.x+1, may comprise any metal or metalized layer or layers, including: (a) a metal interconnect layer, e.g., comprising aluminum, copper, or other metal formed by a damascene process or deposited by a subtractive patterning process (e.g., deposition, patterning, and etching of a metal layer), or (b) a silicided polysilicon layer including a number of silicided polysilicon structures (i.e., polysilicon structures having a metal silicide layer formed thereon), for example a silicided polysilicon gate of a metal-oxide-semiconductor field-effect transistor (MOSFET).

(16) For example, as shown in FIG. 3A, an MIM capacitor module and TFR module may be constructed between two adjacent metal interconnect layers M.sub.x and M.sub.x+1 at any depth in an integrated circuit structure. As another example, as shown in FIG. 3B, an MIM capacitor module and TFR module may be constructed between a silicided polysilicon layer and a first metal interconnect layer (commonly referred to as the metal-1 layer), wherein the silicided polysilicon layer defines the lower metal layer M.sub.x where x=0 (i.e., M.sub.0) and the first metal interconnect layer (Metal-1 layer) defines the upper metal layer M.sub.x+1 (i.e., M.sub.1).

(17) FIG. 3A is a cross-sectional side view an example integrated circuit structure 300a including an example MIM capacitor module 302a, an example TFR module 304a, and (optionally) an example interconnect structure 306a, all formed between two metal interconnect layers M.sub.x and M.sub.x+1, according to some examples. In some examples, integrated circuit structure 300a includes the MIM capacitor module 302a, TFR module 304a, and interconnect structure 306a. In other examples, integrated circuit structure 300a includes the MIM capacitor module 302a and TFR module 304a, but not the interconnect structure 306a. Thus, the optional interconnect structure 306a is indicated in FIG. 3A with a dashed line.

(18) The example MIM capacitor module 300a includes (a) a bottom electrode base 310 formed in a lower metal interconnect layer M.sub.x, (b) a bottom electrode 312 conductively coupled to the bottom electrode base 310, (c) an insulator 314 formed over the bottom electrode 312, and (d) a top electrode 316 formed in an upper metal interconnect layer M.sub.x+1 over the insulator 314. A resistor film region 322 may be arranged between the insulator 314 and underlying bottom electrode 312. The MIM capacitor module 302a also includes a bottom electrode connection element 318 formed in the upper metal interconnect layer M.sub.x+1, and a bottom electrode contact 320 conductively connecting the bottom electrode connection element 318 to the bottom electrode base 310.

(19) The bottom electrode 312 is formed in a dielectric region 324 formed in a via layer V.sub.x between the metal interconnect layer M.sub.x and upper metal interconnect layer M.sub.x+1. The bottom electrode 312 may be formed using a damascene process, as described below. In the illustrated example, the bottom electrode 312 includes (a) a cup-shaped bottom electrode component 330 formed in a tub opening 331 formed in the dielectric region 324 and (b) a bottom

electrode fill component **332** formed in an interior opening **333** defined by the cup-shaped bottom electrode component **330**.

(20) In some examples, the bottom electrode contact **320** is formed as a via, and may also be referred to as a bottom electrode via.

(21) In some examples, the insulator **314** may be formed over a planarized support surface **340**. For example, as shown in FIG. 3A, the insulator **314** may be formed on the resistor film region **322** formed on the planarized support surface **340**. The planarized support surface **340**, which may be formed by a chemical mechanical planarization (CMP) or other planarization process, includes (a) a planarized top surface **341** of the cup-shaped bottom electrode component **330**, (b) a planarized top surface **342** of the bottom electrode fill component **332**, and (c) a planarized top surface **347** of the dielectric region **324**, including top surface areas of the dielectric region **324** on opposite lateral sides (in the x-direction, or in both the x-direction and y-direction) of each of the bottom electrode **312**.

(22) The planarized support surface **340** may be free of metal hillocks, as the bottom electrode **312** is formed from refractory metals (e.g., tungsten and titanium nitride) which resist the formation of hillocks, unlike the aluminum bottom electrode of the example prior art MIM capacitor module **10** shown in FIG. 1F discussed above. Forming the insulator **314** on a surface free of hillocks may provide a higher and more consistent capacitor breakdown voltage, e.g., as compared with a conventional capacitor module having a bottom electrode including hillocks.

(23) The surface roughness of the planarized support surface **340** may depend on the specific process parameters implemented (e.g., CMP process parameters). In some examples, the planarized support surface **340** has a root-mean-square (RMS) surface roughness of less than 50 Å. In some examples, the planarized support surface **340** has an RMS surface roughness of less than 20 Å.

(24) As mentioned above, insulator **314** may be formed on resistor film region **322** formed on the planarized support surface **340**. The lateral width $W_{sub.ins}$ of the insulator **314** in the x-direction may be coextensive with the lateral width $W_{sub.te}$ of the overlying top electrode **316**, as a result of an anisotropic metal etch extending through both the top electrode **316** and insulator **314**, e.g., as shown in FIG. 13 discussed below.

(25) In some examples, e.g., as shown in FIG. 3A, a lateral width $W_{sub.te}$ of the top electrode **316** and a corresponding lateral width $W_{sub.ins}$ of insulator **314** are greater than a lateral width $W_{sub.be}$ of the underlying bottom electrode **312** in the x-direction, such that the insulator **314** extends across and beyond the full lateral width $W_{sub.be}$ of the bottom electrode **312** and onto the planarized top surface areas **347** of dielectric region **324** on opposite sides of the bottom electrode **312** in the x-direction. In other words, the insulator **314** extends across the planarized top surface **341** of the cup-shaped bottom electrode component **330**, the planarized top surface **342** of the bottom electrode fill component **332**, and the planarized top surface areas **347** of the dielectric region **324**. In some examples, the insulator **314** extends laterally across the full lateral width $W_{sub.be}$ of the bottom electrode **312** in both the x-direction and y-direction, and additionally extends over portions of the dielectric region **324** on all lateral sides of the bottom electrode **312**, such that a perimeter of the insulator **314** surrounds a perimeter of the bottom electrode **312**, from a top view.

(26) The insulator **314** has a uniform thickness $T_{sub.ins}$ across the full lateral width $W_{sub.ins}$ of the insulator **314**. For example, in some examples the thickness $T_{sub.ins}$ of the insulator **314** varies by less than 10% across the full lateral width $W_{sub.ins}$ of the insulator **314**. In some implementations the thickness $T_{sub.ins}$ of the insulator **314** varies by less than 5%, or even less than 1%, across the full lateral width $W_{sub.ins}$ of the insulator **314**.

(27) This uniform thickness $T_{sub.ins}$ across the full lateral width $W_{sub.ins}$ of the insulator **314** may provide an increased and predictable breakdown voltage for the resulting MIM capacitor module **302a**, e.g., as compared with a capacitor module having a partially etched thickness or otherwise varying thickness, e.g., the prior art MIM capacitor module **10** shown in FIG. 1F and

discussed above.

(28) Further, by forming the bottom electrode **312** between two metal layers $M.sub.x$ and $M.sub.x+1$ the bottom electrode **312** may have a thickness $T.sub.be$ extending across the full thickness of the dielectric region **324** between the metal layers $M.sub.x$ and $M.sub.x+1$. In addition, by forming the top electrode **316** from the metal interconnect layer $M.sub.x+1$, the top electrode **316** may have a thickness $T.sub.te$ defined by the thickness of the metal interconnect layer $M.sub.x+1$. Thus, the bottom electrode thickness $T.sub.be$ and top electrode thickness $T.sub.te$ may be sufficient to provide target performance characteristics for various applications (e.g., including RF applications), as compared with certain conventional capacitor modules having a thinner top electrode and/or bottom electrode. In some examples, the bottom electrode thickness $T.sub.be$ may be at least 4000 Å, and the top electrode thickness $T.sub.te$ may be at least 4000 Å.

(29) Next, as shown in FIG. 3A, the example TFR module **304a** includes (a) a pair of head bases **350a** and **350b** formed in the lower metal interconnect layer $M.sub.x$, (b) a pair of metal heads **352a** and **352b**, each conductively coupled to a respective head base **350a**, **350b**, and (c) a resistor element **354** connected across the pair of metal heads **352a** and **352b**. The example TFR module **304a** also includes (a) an insulator cap element **360** (formed from an insulator layer used to form the insulator **314** of the MIM capacitor module **302a**), and (b) a metal resistor cap element **362** formed in the upper metal interconnect layer $M.sub.x+1$ over the insulator cap element **360**.

(30) Metal heads **352a** and **352b** are formed in the via layer $V.sub.x$ between the lower metal interconnect layer $M.sub.x$ and upper metal interconnect layer $M.sub.x+1$, e.g., using a damascene process. For example, each metal head **352a** and **352b** may include (a) a cup-shaped head component **364** formed in a head opening **365** formed in the dielectric region **324** and (b) a head fill component **368** formed in an interior opening **369** defined by the cup-shaped head component **364**.

(31) The resistor element **354** is formed on the polished, planarized support surface **340**. For example, as shown in FIG. 3A, the resistor element **354** may be formed on a portion of the planarized support surface **340** including (a) a planarized top surface **345** of each cup-shaped head component **364**, (b) a planarized top surface **346** of each head fill component **368**, and (c) a planarized top surface areas **347** of the dielectric region **324** laterally between and adjacent the pair of metal heads **352a** and **352b**.

(32) The resistor element **354** of the TFR module **304a** may be formed from a common resistor film as the resistor film region **322** formed between the insulator **314** and underlying bottom electrode **312** of the MIM capacitor module **302a**, as described below. Further, the insulator cap element **360** of the TFR module **304a** may be formed from a common insulator layer as the insulator **314** of the MIM capacitor module **302a**, as described below.

(33) The (optional) interconnect structure **306a** includes a lower interconnect element **380** formed in the lower metal interconnect layer $M.sub.x$, an upper interconnect contact **382** formed in the upper metal interconnect layer $M.sub.x+1$, and an interconnect via **384** formed in the via layer $V.sub.x$ and conductively connected between the lower interconnect element **380** and upper interconnect contact **382**.

(34) The cup-shaped bottom electrode component **330** of the bottom electrode **312**, the cup-shaped head component **364** of each metal head **352a**, **352b**, the bottom electrode contact **320**, and the interconnect via **384** may be formed from a conformal metal, e.g., tungsten. In some examples, the cup-shaped bottom electrode component **330**, the cup-shaped head components **364** of metal heads **352a** and **352b**, the bottom electrode contact **320**, and the interconnect via **384** may be formed simultaneously by deposition of tungsten or other conformal metal, as discussed below with reference to FIG. 6. In some examples, an adhesive layer **326** (e.g., a TiN layer with a thickness in the range of 50-300 Å) is deposited prior to deposition of the conformal metal to improve adhesion between the conformal metal and surrounding areas of the dielectric region **324**, in particular in the tub opening **331** and head openings **365**.

(35) The bottom electrode fill component **332** of the bottom electrode **312**, and the head fill

component **368** of each metal head **352a**, **352b** may be formed from a “fill metal” that may be different than the conformal metal that forms the cup-shaped bottom electrode component **330**, each cup-shaped head component **364**, the bottom electrode contact **320**, and the interconnect via **384**. For example, the fill metal forming the bottom electrode fill component **332** and each head fill component **368** may comprise TiN or other refractory metal different than the conformal metal. In some examples, the bottom electrode fill component **332** and the head fill components **368** may be formed simultaneously by deposition of the fill metal, as discussed below with reference to FIG. 7.

(36) The example TFR module **304a** shown in FIG. 3A may include various advantages or improvements over certain conventional designs, e.g., the example prior art TFR designs shown in FIG. 2. First, the construction of TFR module **304a** may be simplified, as compared with conventional methods. For example, the TFR module **304a** may be constructed using only a single added mask added to the relevant background IC fabrication process. In addition, the metal heads **352a**, **352b** of the TFR module **304a** may be built concurrently with the bottom electrode **312** of the MIM capacitor module **302a** and/or interconnect via **384**. The metal heads **352a**, **352b** may be formed with a relatively large contact areas and low resistance.

(37) FIG. 3B is a cross-sectional side view an example integrated circuit structure **300b** including an example MIM capacitor module **302b**, an example TFR module **304b**, and (optionally) an example interconnect structure **306b**, all formed between a silicided polysilicon layer and a first metal interconnect layer (commonly referred to as the metal-1 layer), according to one example. In this example, the silicided polysilicon layer defines a lower metal layer M.sub.0 (i.e., lower metal layer M.sub.x where x=0) and the first metal interconnect layer (Metal-1) defines an upper metal layer M.sub.1.

(38) Integrated circuit structure **300b** is similar to integrated circuit structure **300a** shown in FIG. 3A and discussed above, with the exception that the illustrated structures of integrated circuit structure **300b** (MIM capacitor module **302b**, TFR module **304b**, and optional interconnect structure **306b**) are formed between the silicided polysilicon layer M.sub.0 and first metal interconnect layer M.sub.1, rather than between two metal interconnect layers M.sub.x and M.sub.x+1.

(39) In some examples, integrated circuit structure **300b** includes the MIM capacitor module **302b**, TFR module **304b**, and interconnect structure **306b**. In other examples, integrated circuit structure **300b** includes the MIM capacitor module **302b** and TFR module **304b**, but not the interconnect structure **306b**. Thus, the optional interconnect structure **306b** is indicated in FIG. 3B with a dashed line.

(40) As shown in FIG. 3B, a bottom electrode base **310'** of the MIM capacitor module **300b**, a pair of head bases **350a'** and **350b'** of the TFR module **304b**, and a lower interconnect element **380'** of the interconnect structure **306b** are each formed as a silicided polysilicon structure including a metal silicide layer formed on a respective polysilicon structure in the silicided polysilicon layer M.sub.0. More particularly, bottom electrode base **310'** comprises a metal silicide layer **392a** formed on a top surface of a polysilicon structure **390a**; head base **350a'** comprises a metal silicide layer **392b** formed on a top surface of a polysilicon structure **390b**; head base **350b'** comprises a metal silicide layer **392c** formed on a top surface of a polysilicon structure **390c**; and lower interconnect element **380'** comprises a metal silicide layer **392d** formed on a top surface of a polysilicon structure **390d**. Metal silicide layers **392a-392d** may comprise any suitable metal silicide layer, for example titanium silicide (TiSi₂), cobalt silicide (CoSi₂), or nickel silicide (NiSi), having a thickness in the range of 100-300 Å or other suitable thickness.

(41) FIGS. 4-13 are cross-sectional side views showing an example process for forming the example integrated circuit structure **300a** shown in FIG. 3A, including the example MIM capacitor module **302a**, the example TFR module **304a**, and the example interconnect structure **306a**, according to one example.

(42) First, as shown in FIG. 4, a lower metal interconnect layer M.sub.x is formed over a dielectric

region **402**, e.g., a pre-metal dielectric (PMD) region or inter-metal dielectric (IMD) region. Metal layer M.sub.x may be formed from aluminum, copper, or other suitable metal. Metal layer M.sub.x may be deposited, patterned, and etched to form (a) the bottom electrode base **310** of the MIM capacitor module **302a**, (b) the pair of head bases **350a** and **350b** of the TFR module **304a**, and (c) the lower interconnect element **380** of the interconnect structure **306a**. Alternatively, the bottom electrode base **310**, head bases **350a** and **350b**, and lower interconnect element **380** may be formed by a damascene process. Each of the bottom electrode base **310**, head bases **350a** and **350b**, and lower interconnect element **380** may comprise a wire or other laterally elongated structure (e.g., elongated in the y-axis direction), or a discrete pad (e.g., having a square, circular, or substantially square or circular shape in the x-y plane), or any other suitable shape and structure.

(43) A resist strip may be performed to remove remaining portions of the photomask used for patterning the metal layer M.sub.x. A dielectric region **324** may be formed over metal layer M.sub.x, e.g., by performing an oxide deposition (e.g., using high density plasma (HDP) and PECVD processes) followed by a CMP process to planarize the oxide. Dielectric region **324** may be an inter-metal dielectric (IMD) region.

(44) Next, as shown in FIG. 5A (cross-sectional side view) and corresponding FIG. 5B (top view), the dielectric region **324** is patterned and etched (e.g., using a plasma etch) to concurrently form (a) at least one interconnect via opening **410** for various interconnect structures, (b) a bottom electrode contact opening **412**, (c) the tub opening **331** for forming the bottom electrode **312** of the MIM capacitor module **302a**, and (d) the pair of head openings **365** for forming the pair of metal heads **352a** and **352b** of the TFR module **304a**.

(45) The interconnect via opening **410** and bottom electrode contact opening **412** may each be formed as a narrow via opening with a lateral diameter or width W.sub.via. In contrast, the tub opening **331** and each head opening **365** may have a substantially larger width (x-direction) and/or length (y-direction) than the narrow via openings **310** and **312**. The shape and dimensions of the tub opening **331** and head openings **365** may be selected based on various parameters, e.g., for effective manufacturing of the MIM capacitor module **302a** and TFR module **304a** (e.g., effective deposition of the conformal metal and fill metal (e.g., tungsten and TiN, respectively) into the openings **331** and **365**) and/or for desired performance characteristics of the resulting MIM capacitor module **302a** and TFR module **304a**. In some examples, the tub opening **331** and head openings **365** may each have a square or rectangular shape from a top view, e.g., as shown in FIG. 5B. In other examples, the tub opening **331** may have a circular or oval shape from the top view.

(46) As noted above, an x-direction width W.sub.tub and/or y-direction length L.sub.tub of the tub opening **331** may be substantially larger than the width W.sub.via of each via opening. For example, in some embodiments, the width W.sub.tub and/or length L.sub.tub of the tub opening **331** is at least twice as large as the width W.sub.via of each via opening. In particular embodiments, the width W.sub.tub and/or length L.sub.tub of the tub opening **331** is at least five times as large, ten times as large, or 20 times as large, as the width W.sub.via of each via opening. In some examples, the width W.sub.via of each via opening is in the range of 0.1-0.5 μm , whereas the width W.sub.tub and length L.sub.tub of the tub opening **331** are each the range of 1-100 μm .

(47) In addition, an x-direction width W.sub.head and/or y-direction length L.sub.head of each head opening **365** may be substantially larger than the width W.sub.via of each via opening. For example, in some embodiments, the width W.sub.head and/or length L.sub.head of the tub opening **365** is at least twice as large as the width W.sub.via of each via opening. In particular embodiments, the width W.sub.head and/or length L.sub.head of each head opening **365** is at least five times as large, ten times as large, or 20 times as large as the width W.sub.via of each via opening. In some examples, the width W.sub.via of each via opening is in the range of 0.1-0.5 μm , whereas the width W.sub.head and length L.sub.head of each head opening **365** are each the range of 0.5-10 μm .

(48) After the etch to create the openings **410**, **412**, **331**, and **365**, any remaining photoresist material may be removed by a resist strip.

(49) Next, as shown in FIG. 6, adhesive layer **326** (e.g., comprising titanium nitride, TiN) is deposited over the integrated circuit structure **300a** and into the openings **410**, **412**, **331**, and **365**, e.g., with a thickness in the range of 50-300 Å, in one example. A conformal metal layer **420**, e.g., tungsten (W), is then deposited over adhesive layer **326**, e.g., by Chemical Vapor Deposition (CVD) deposition, with a thickness, in one example, in the range of 1000-5000 Å. As shown, the conformal metal layer **420** (a) fills the interconnect via opening **410** to form an interconnect via **384**, (b) fills the bottom electrode contact opening **412** to form the bottom electrode contact **320**, (c) partially fills the tub opening **331** to form the cup-shaped bottom electrode component **330** in the tub opening **331**, and (d) partially fills each head opening **365** to form the cup-shaped head component **364** in each head opening **365**. The cup-shaped bottom electrode component **330** defines an interior opening **333**, and each cup-shaped head component **364** defines an interior opening **369**.

(50) The interconnect via **384**, bottom electrode contact **320**, cup-shaped bottom electrode component **330**, and cup-shaped head components **364** are further processed as discussed below, including a CMP process shown in FIG. 8A, which defines a final form of each respective element **384**, **320**, and **330**, and **364**.

(51) The deposited conformal metal layer **420** layer may have high tensile stresses, due to inherent material properties of the conformal metal, e.g., tungsten. As a result, a deposition thickness substantially above about 5000 Å (e.g., a thickness of 7000 Å) may result in a cracking or peeling of the conformal metal layer **420**, or a warping or breakage of the underlying silicon wafer (not shown), e.g., during a subsequent CMP process. However, these dimensions are not meant to be limiting in any way.

(52) Next, as shown in FIG. 7, a fill metal layer **430** is deposited over the integrated circuit structure **300** to fill the interior opening **333** of the cup-shaped bottom electrode component **330** and the interior opening **369** of each cup-shaped head component **364**. The fill metal layer **430** may be deposited with sufficient thickness to fill the interior openings **333** and **369** at least to the top of the dielectric region **324**. The portion of the fill metal layer **430** filling interior opening **333** of the cup-shaped bottom electrode component **330** defines the bottom electrode fill component **332**, and the portion of the fill metal layer **430** filling the interior opening **369** of each cup-shaped head component **364** defines a respective head fill component **368**.

(53) The fill metal layer **430** may be deposited by a reactive PVD or CVD process without generating hillocks, which may provide an increased breakdown voltage for the resulting MIM capacitor module **302a**, as compared with prior art designs that enable or encourage hillock formation on the capacitor bottom electrode (and/or other capacitor components), e.g., as discussed above regarding the example prior art capacitor module **10** shown in FIG. 1F.

(54) In some examples, the fill metal layer **430** comprises titanium nitride (TiN) or other refractory metal (different from the conformal metal of the conformal metal layer **420**) that has inherent compressive stresses (e.g., for a layer thickness of less than 1 μm). The inherent compressive stresses of the fill metal layer **430** (e.g., titanium nitride layer) may counteract the inherent tensile stresses of the underlying conformal metal layer **420** (e.g., tungsten layer), to thereby reduce the risk of inter-layer peeling, silicon wafer breakage, or other mechanical failure. In another example, the fill metal layer **430** is formed of aluminum, which may provide reduced resistance for the resulting bottom electrode **312** and metal heads **352a**, **352b**, but may introduce the possibility of hillock formation.

(55) Next, as shown in FIG. 8A (cross-sectional side view) and corresponding FIG. 8B (top view), a planarization process (e.g., CMP process) is performed to remove upper portions of the fill metal layer **430**, the conformal metal layer **420**, and adhesive layer **326**, and thereby define the final form of (a) the interconnect via **384**, (b) the bottom electrode contact **320**, (c) the cup-shaped bottom electrode component **330** and bottom electrode fill component **332** of the bottom electrode **312** of the MIM capacitor module **302a**, and (d) the cup-shaped head component **364** and head fill

component 368 of each metal head 352a, 352b of the TFR module 304a. The planarization process may be designed to stop on the dielectric region 324.

(56) The planarization process (e.g., CMP process) defines a polished, planarized support surface 340 that includes (a) the planarized top surface 341 of the cup-shaped bottom electrode component 330, (b) the planarized top surface 342 of the bottom electrode fill component 332, (c) the planarized top surface 345 of each cup-shaped head component 368, (d) the planarized top surface 346 of each head fill component 368, and (e) the planarized top surface 347 of the dielectric region 324, including top surface areas of the dielectric region 324 on opposite lateral sides (in the x-direction, or in both the x-direction and y-direction) of each of the bottom electrode 312 and each metal head 352a, 352b.

(57) The planarized support surface 340 provides a smooth, planarized surface free of hillocks. For example, the planarized top surfaces 341, 342, 345, and 346 (components of the planarized support surface 340) provide smooth, planarized surfaces of refractory metals used as the conformal metal layer 420 and fill metal layer 430 (e.g., tungsten and titanium nitride, as discussed above) that are free of hillocks, suitable for supporting the insulator 314 and resistor element 354. As discussed below, the resistor element 354 is formed from a resistor film 404 formed directly on the planarized support surface 340, whereas the insulator 314 is formed on a resistor film region 322 formed from the same resistor film 404. As discussed below, the resistor film 404 is formed as a planar layer with a uniform thickness across the planarized support surface 340; thus, the insulator 314 formed on the resistor film region 322 is also formed as a planar structure with a uniform thickness across the lateral width of the insulator 314 (in the x-direction, or both the x-direction and y-direction).

(58) Next, as shown in FIG. 9, a resistor film 404 is deposited over the structure 300, followed by deposition of an insulator layer 406. In some examples, the resistor film 404 may comprise SiCCr, SiCr, NiCr, TaN, or other suitable material, deposited with a thickness $T_{\text{sub.resistor}}$, which in one example may be in the range of 100-1000 Å, for example by a physical vapor deposition (PVD) process, and having a sheet resistance, in one example, in the range of 200-1,000 ohms per square. The insulator layer 406 may comprise silicon nitride ($\text{Si}_{\text{sub.3}}\text{N}_{\text{sub.4}}$, $\kappa \sim 7$) deposited with a thickness $T_{\text{sub.ins}}$, in one example in the range of 400-600 Å, for example by a PECVD deposition process. In other examples, the insulator layer 406 may comprise silicon oxide (Sift) or a high-k dielectric material, e.g., $\text{Al}_{\text{sub.2}}\text{O}_{\text{sub.3}}$ ($\kappa \sim 10$), $\text{Ta}_{\text{sub.2}}\text{O}_{\text{sub.5}}$ ($\kappa \sim 25$), $\text{HfO}_{\text{sub.2}}$ ($\kappa \sim 22$), or $\text{ZrO}_{\text{sub.2}}$ ($\kappa \sim 35$), e.g., deposited by a PECVD deposition process or an ALD (atomic layer deposition) process.

(59) A photoresist layer is then deposited and patterned to form a photomask 410 over the insulator layer 406. The patterned photomask 410 includes a first photomask region 410a over the bottom electrode 312 of the MIM capacitor module 302a, and a second photomask 410b extending over the pair of metal heads 352a, 352b of the TFR module 304a. A lateral width $W_{\text{sub.be resist}}$ of the first photomask region 410a extends laterally across and beyond a lateral width $W_{\text{sub.be}}$ of the bottom electrode 312 in the x-direction, or in both the x-direction and y-direction. Similarly, a lateral width $W_{\text{sub.tfr_resist}}$ of the second photomask region 410b extends laterally across and beyond a lateral width $W_{\text{sub.heads}}$ extending across both metal heads 352a, 352b in the x-direction, or in both the x-direction and y-direction.

(60) Next, as shown in FIG. 10, an etch is performed to remove portions of the insulator layer 406 and the resistor film 404 uncovered by the patterned photomask 410, leaving (a) a first resistor film region 404a and a first insulator layer region 406a below the first photomask region 410a and (b) a second resistor film region 404b and a second insulator layer region 406b below the second photomask region 410b. A lateral width of each of the first resistor film region 404a ($W_{\text{sub.region_404a}}$) and the first insulator layer region 406a ($W_{\text{sub.region_406a}}$) corresponds with the lateral width $W_{\text{sub.be resist}}$ of the first photomask region 410a, such that each extends laterally across and beyond the lateral width $W_{\text{sub.be}}$ of the bottom electrode in the x-direction, or in both the x-direction and y-direction. Similarly, a lateral width of each of the second resistor film

region **404b** (W.sub.region_404b) and the second insulator layer region **406b** (W.sub.region_406b) corresponds with the lateral width W.sub.tfr_resist of the second photomask region **410b**, such that each extends laterally across and beyond the lateral width W.sub.heads extending across both metal heads **352a**, **352b** in the x-direction, or in both the x-direction and y-direction.

(61) Next an upper metal interconnect layer M.sub.x+1 is formed over the integrated circuit structure **300a**. First, as shown in FIG. **11**, an upper metal layer **430**, e.g., comprising aluminum, copper, or other suitable metal, is deposited over the dielectric region **324** and the first and second insulator layer region **406a**, **406bb**.

(62) Next, as shown in FIG. **12**, a photoresist layer is deposited and patterned to form a photomask **440** including (a) a first photomask element **440a** for forming an upper interconnect contact **382**, as discussed below), (b) a second photomask element **440b** (for forming the bottom electrode connection element **318**, as discussed below), (c) a third photomask element **440c** (for forming the top electrode **316** and underlying insulator **314** and resistor film region **322**, as discussed below), and (d) a fourth photomask element **440d** (for forming the metal resistor cap element **362** and underlying insulator cap element **360** and resistor element **354**, as discussed below).

(63) As shown, a width W.sub.te_resist of the third photomask element **440c** may be larger than the width W.sub.be of the bottom electrode **312** but smaller than the width of the first resistor film region **404a** and first insulator layer region **406a** (W.sub.region_404a=W.sub.region_406a), such that the subsequent metal etch to form the top electrode **316** (see FIG. **13**) self-aligns the lateral edges (in the x-direction, or both the x-direction and y-direction) of the top electrode **316** with the underlying insulator **314** and resistor film region **322** (see FIG. **13**), while also preventing any etching of the bottom electrode **312**.

(64) Similarly, a width W.sub.tfr_cap_resist of the third photomask element **440d** may be larger than the width W.sub.heads extending across both metal heads **352a**, **352b** but smaller than the width of the second resistor film region **404b** and second insulator layer region **406b** (W.sub.region_404b=W.sub.region_406b), such that the subsequent metal etch to form the metal resistor cap element **362** (see FIG. **13**) self-aligns the lateral edges (in the x-direction, or both the x-direction and y-direction) of the metal resistor cap element **362** with the underlying resistor element **354** and insulator cap element **360** (see FIG. **13**), while also preventing any etching of the metal heads **352a**, **352b**.

(65) FIG. **13** shows the results of the metal etch through the photomask **440** shown in FIG. **12**, and after removal of the photomask **440**, e.g., by a resist strip process. The etch may be selective to etch through structures not covered by the photomask **440** (including portions of the upper metal layer **430**, first and second insulator layer regions **406a**, **406b**, and portions of the first and second resistor film regions **404a**, **404b** not covered by the photomask **440**, as shown in FIG. **12**), but stop in the dielectric region **324**, e.g., at a depth of 500-1000 Å into the dielectric region **324**, for example. As shown, the etch forms (a) the upper interconnect element **382** in contact with the interconnect via **384**, (b) the bottom electrode connection element **318** in contact with the bottom electrode contact **320**, (c) the top electrode **316** and underlying insulator **314** and underlying resistor film region **322**, and (d) the metal resistor cap element **362** and underlying insulator cap element **360** and resistor element **354**.

(66) As shown, as a result of the metal etch, the lateral edges of the top electrode **316** are aligned with corresponding lateral edges of the insulator **314** and the resistor film region **322**. A lateral width of the top electrode **316** (W.sub.te), the insulator **314** (W.sub.ins), and the resistor film region **322** (W.sub.resistor_film_region) each extends laterally across and beyond the lateral width W.sub.be of the bottom electrode in the x-direction, or in both the x-direction and y-direction.

(67) Similarly, the lateral edges of the metal resistor cap element **362** are aligned with corresponding lateral edges of the underlying insulator cap element **360** and resistor element **354**. A lateral width of metal resistor cap element **362** (W.sub.metal_cap), the insulator cap element **360** (W.sub.ins_cap), and the resistor element **354** (W.sub.tfr_element) each extends laterally across and

beyond the lateral width $W_{\text{sub.heads}}$ extending across both metal heads **352a**, **352b** in the x-direction, or in both the x-direction and y-direction.

(68) Each of the resistor film region **322** and the resistor element **354** has the thickness ($T_{\text{sub.resistor}}$) of the resistor film **404** from which they are formed, which thickness $T_{\text{sub.resistor}}$ is uniform across the full lateral width (in the x-direction, or in both the x-direction and y-direction) of the resistor film region **322** and resistor element **354**, respectively. Similarly, each of the insulator **314** and the insulator cap element **360** has the thickness ($T_{\text{sub.ins}}$) of the insulator layer **406** from which they are formed, which thickness $T_{\text{sub.ins}}$ is uniform across the full lateral width (in the x-direction, or in both the x-direction and y-direction) of the insulator **314** and insulator cap element **360**, respectively.

(69) In some examples, FIG. **13** shows the completed of MIM capacitor module **302a**, TFR module **304a** and interconnect structure **306a**. After forming the MIM capacitor module **302a**, TFR module **304a** and interconnect structure **306a** the process may continue with construction of additional interconnect structures, e.g., by forming further metal interconnect layers and/or dielectric layers.

(70) FIG. **14** is a flowchart showing an example method **1400** of forming an example integrated circuit structure including an example MIM capacitor module and an example TFR module, according to one example. At **1402**, a lower metal layer $M_{\text{sub.x}}$ is formed, including a bottom electrode base. In one example, the lower metal layer $M_{\text{sub.x}}$ comprise a lower interconnect metal layer (e.g., comprising aluminum). In another example, the lower metal layer $M_{\text{sub.x}}$ comprises a silicided polysilicon layer. At **1404**, a dielectric region (e.g., an oxide region) is deposited over the lower metal layer $M_{\text{sub.x}}$, and planarized, for example by a CMP process.

(71) Next, as indicated by the dashed line box in FIG. **14**, a damascene process may be performed at **1406-1412** to form a bottom electrode and a bottom electrode contact of the MIM capacitor module and a pair of metal heads of the TFR module.

(72) First, at **1406**, the dielectric region is patterned and etched to form a tub opening and a pair of head openings. At **1408**, a bottom electrode is formed in the bottom electrode tub opening, the bottom electrode including (a) a cup-shaped bottom electrode component and (b) a bottom electrode fill component in an interior opening defined by the cup-shaped bottom electrode component.

(73) At **1410**, which may be performed concurrently with **1408**, a metal head is formed in each of the pair of head tub openings, each metal head including (a) a cup-shaped head component; and (b) a head fill component in an interior opening defined by the cup-shaped head component.

(74) At **1412**, a planarization process is performed to define a planarized support surface including (a) a planarized top surface of the cup-shaped bottom electrode component, (b) a planarized top surface of the bottom electrode fill component, and (c) planarized top surface areas of the dielectric region on opposite sides of the bottom electrode.

(75) At **1414**, a resistor element connected across the pair of metal heads is formed from a resistor film formed on the planarized support surface.

(76) At **1416**, an insulator is formed on the bottom electrode of the MIM capacitor module. The insulator may be formed over the planarized support surface, and may extend laterally across and beyond a full width of the bottom electrode, such that the insulator extends over the planarized top surface areas of the dielectric region on opposite sides of the bottom electrode, in the x-direction or in both the x-direction and y-direction. The insulator may have a uniform vertical thickness across a full lateral width of the insulator. In some examples, as explained above, the insulator is formed over the resistor film, such that a resistor film region (formed on the planarized support surface) is arranged between the insulator and the planarized support surface. Like the insulator, the resistor film region may have a uniform vertical thickness across a full lateral width of the resistor film region.

(77) At **1418**, an upper metal layer is formed over the dielectric region, the upper metal layer including a top electrode over the insulator.

(78) FIGS. 15A-15B illustrate a flowchart showing an example method 1500 of forming an example integrated circuit structure including an example MIM capacitor module and a TFR module, according to one example. At 1502, a lower metal layer M.sub.x is formed, including a bottom electrode base and a pair of head bases. In one example, the lower metal layer M.sub.x comprise a lower interconnect metal layer (e.g., comprising aluminum). In another example, the lower metal layer M.sub.x comprises a silicided polysilicon layer. At 1504, a dielectric region (e.g., an oxide region) is deposited over the lower metal layer M.sub.x, and planarized, for example by a CMP process.

(79) Next, as indicated by the dashed line box in FIG. 15A, a damascene process may be performed at 1506-1512 to form a bottom electrode and a pair of metal heads. At 1506, the dielectric region is patterned and etched to form (a) a tub opening and a pair of head openings. At 1508, a conformal metal (e.g., tungsten) is deposited and extends into the bottom electrode opening and the pair of head openings. At 1510, a fill metal (e.g., titanium nitride (TiN)) is deposited over the conformal metal and extends into the tub opening and the pair of head openings.

(80) At 1512, a planarization process is performed to remove portions of conformal metal and fill metal, wherein (a) remaining portions of conformal metal and fill metal in bottom electrode opening define a bottom electrode including a cup-shaped bottom electrode component and a bottom electrode fill component in an interior opening defined by the cup-shaped bottom electrode component and (b) remaining portions of conformal metal and fill metal in each head opening define a metal head including a cup-shaped head component and a head fill component in an interior opening defined by the cup-shaped head component. The planarization process may define a planarized support surface including (a) a planarized top surface of the cup-shaped bottom electrode component, (b) a planarized top surface of the bottom electrode fill component, (c) planarized top surface areas of the dielectric region on opposite sides of the bottom electrode, (d) a planarized top surface area of the cup-shaped head component of each metal head, (e) a planarized top surface area of the fill component of each metal head, and (f) planarized top surface areas of the dielectric region laterally between and adjacent the pair of metal heads.

(81) At 1514, a resistor element connected across the pair of metal heads is formed from a resistor film formed on the planarized support surface.

(82) At 1516, an insulator is formed over the bottom electrode. The insulator may be formed over the planarized support surface, and may extend laterally across and beyond a full width of the bottom electrode, such that the insulator extends over the planarized top surface areas of the dielectric region on opposite sides of the bottom electrode (in x-direction or in both x-direction and y-direction). In some examples, the insulator may be formed as a planar insulator having a uniform vertical thickness across a full lateral width of the insulator. In some examples, as explained above, the insulator is formed over the resistor film, such that a resistor film region (arranged on the planarized support surface) is arranged between the insulator and the planarized support surface. Like the insulator, the resistor film region may have a uniform vertical thickness across a full lateral width of the resistor film region.

(83) At 1518, an upper metal layer is formed over the dielectric region, the upper metal layer including a top electrode over the insulator.

Claims

1. An integrated circuit structure, comprising: (a) a metal-insulator-metal capacitor module, comprising: a bottom electrode base formed in a lower metal layer; a bottom electrode formed in a dielectric region between the lower metal layer and an upper metal layer, the bottom electrode comprising: a cup-shaped bottom electrode component; and a bottom electrode fill component formed in an interior opening defined by the cup-shaped bottom electrode component; an insulator formed over the bottom electrode; and a top electrode formed in the upper metal layer over the

insulator; and (b) a thin-film resistor module, comprising: a pair of metal heads formed in the dielectric region between the lower metal layer and the upper metal layer, wherein each metal head comprises: a cup-shaped head component; and a head fill component formed in an interior opening defined by the cup-shaped head component; and a resistor element connected across the pair of metal heads; wherein the cup-shaped bottom electrode component of the bottom electrode and the cup-shaped head component of each metal head comprise respective portions of the same conformal metal layer comprising a conformal metal; and wherein the bottom electrode fill component of the bottom electrode and the head fill component of each metal head comprise respective portions of the same fill metal layer comprising a fill metal different than the conformal metal; and (c) an interconnect via extending vertically through the dielectric region between the lower metal layer and the upper metal layer, wherein the interconnect via is formed from a further respective portion of the conformal metal layer, and wherein the interconnect via is free of the fill metal.

2. The integrated circuit structure of claim 1, wherein the thin-film resistor module includes a pair of head bases formed in the lower metal layer, wherein each metal head is conductively connected to a respective head base.
3. The integrated circuit structure of claim 1, wherein the conformal metal comprises tungsten, and the fill metal comprises titanium nitride.
4. The integrated circuit structure of claim 1, wherein the insulator has a uniform vertical thickness across a full lateral width of the insulator.
5. The integrated circuit structure of claim 1, wherein the insulator is formed over a planarized support surface including a planarized top surface of the cup-shaped bottom electrode component and a planarized top surface of the bottom electrode fill component.
6. The integrated circuit structure of claim 5, comprising a resistor film region formed on the planarized support surface, the resistor film region having a uniform vertical thickness across a full lateral width of the resistor film region; wherein the insulator is formed on the resistor film region, the insulator having a uniform vertical thickness across a full lateral width of the insulator.
7. The integrated circuit structure of claim 1, wherein: the insulator is formed on a planarized support surface including (a) a planarized top surface of the cup-shaped bottom electrode component, (b) a planarized top surface of the bottom electrode fill component, and (c) planarized top surface areas of the dielectric region on opposite sides of the bottom electrode; and the insulator extends laterally across and beyond a full width of the bottom electrode, such that the insulator extends over the planarized top surface areas of the dielectric region on opposite sides of the bottom electrode.
8. The integrated circuit structure of claim 1, wherein: the thin-film resistor module includes a resistor element insulator cap element formed on the resistor element; and the resistor element insulator cap element is formed from a common insulator material as the insulator.
9. The integrated circuit structure of claim 1, wherein: the lower metal layer comprises a lower interconnect layer; and the upper metal layer comprises an upper interconnect layer.
10. The integrated circuit structure of claim 1, wherein: the lower metal layer comprises a silicided polysilicon layer, wherein the bottom electrode base formed in the lower metal layer comprises a metal silicide region formed on a polysilicon region; and the upper metal layer comprises a first metal interconnect layer.
11. The integrated circuit structure of claim 1, wherein the metal-insulator-metal capacitor module comprises: a bottom electrode connection element formed in the upper metal layer; and a bottom electrode contact formed in the dielectric region between the lower metal layer and the upper metal layer; wherein the bottom electrode contact provides a conductive connection between the bottom electrode connection element formed in the upper metal layer and the bottom electrode base formed in the lower metal layer.
12. The integrated circuit structure of claim 1, further comprising an interconnect structure

including: a lower interconnect element formed in the lower metal layer; and an upper interconnect contact formed in the upper metal layer and connected to the lower interconnect element by at least the interconnect via.

13. The integrated circuit structure of claim 12, wherein the at least one interconnect via and the cup-shaped bottom electrode component are formed from a common conformal metal.

14. An integrated circuit structure, comprising: (a) a metal-insulator-metal capacitor module, comprising: a bottom electrode formed in a dielectric region, the bottom electrode comprising: a cup-shaped bottom electrode component; and a bottom electrode fill component formed in an interior opening defined by the cup-shaped bottom electrode component; an insulator formed over the bottom electrode; and a top electrode formed over the insulator; and (b) a thin-film resistor module, comprising: a pair of metal heads formed in the dielectric region, wherein each metal head comprises: a cup-shaped head component; and a head fill component formed in an interior opening defined by the cup-shaped head component; and a resistor element connected across the pair of metal heads; wherein the cup-shaped head component of each metal head and the cup-shaped bottom electrode component comprise respective portions of the same conformal metal layer comprising a conformal metal deposited in respective openings in the dielectric region; and wherein the head fill component of each metal head and the bottom electrode fill component comprise respective portions of the same fill metal layer comprising a fill metal different than the conformal metal; and (c) an interconnect via extending vertically through the dielectric region between the lower metal layer and the upper metal layer, wherein the interconnect via is formed from a further respective portion of the conformal metal layer, and wherein the interconnect via is free of the fill metal.
