

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12397317
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Carty; Neal Robert

Surface treatment system and method for subcutaneous device

Abstract

Methods of modifying a medical device and manufacturing a medical device are disclosed. One embodiment of a method of modifying a medical device includes treating a portion of the medical device with cold plasma and functionalizing the plasma-treated portion with a polymer. One embodiment of a method of manufacturing a medical device includes providing a subcutaneous part configured to be positioned subcutaneously in a user and performing a surface treatment on a portion of the subcutaneous part.

Inventors:	Carty; Neal Robert (Chicago, IL)
Applicant:	ConvaTec Technologies Inc. (Las Vegas, NV)
Family ID:	1000008781678
Assignee:	CONVATEC TECHNOLOGIES INC. (Las Vegas, NV)
Appl. No.:	18/407552
Filed:	January 09, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240181493 A1	Jun. 06, 2024

Related U.S. Application Data

continuation parent-doc US 17564586 20211229 US 11890642 child-doc US 18407552
continuation parent-doc WO PCT/US2021/065461 20211229 PENDING child-doc US 17564586
us-provisional-application US 63132071 20201230

Publication Classification

Int. Cl.: B05D3/14 (20060101); A61L24/00 (20060101); A61L31/10 (20060101)

U.S. Cl.:

CPC B05D3/142 (20130101); A61L31/10 (20130101); A61L2420/02 (20130101)

Field of Classification Search

CPC: B05D (3/14)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
4141973	12/1978	Balazs	N/A	N/A
4656083	12/1986	Hoffman et al.	N/A	N/A
6033582	12/1999	Lee et al.	N/A	N/A
6200626	12/2000	Grobe et al.	N/A	N/A
6451003	12/2001	Prosl et al.	N/A	N/A
8070797	12/2010	Flanagan	623/1.1	A61L 31/146
11963766	12/2023	Doyle et al.	N/A	N/A
11980738	12/2023	Lipman et al.	N/A	N/A
2007/0003603	12/2006	Karandikar et al.	N/A	N/A
2007/0118211	12/2006	Gazza	623/1.42	A61L 29/16
2008/0003374	12/2007	Borra et al.	N/A	N/A
2008/0142038	12/2007	Kunzler et al.	N/A	N/A
2009/0065485	12/2008	O'Neill et al.	N/A	N/A
2009/0118423	12/2008	Kumar	549/415	C08J 3/246
2010/0014286	12/2009	Yoneda et al.	N/A	N/A
2010/0047532	12/2009	Mozetic et al.	N/A	N/A
2010/0139663	12/2009	O'Neil	N/A	N/A
2010/0145286	12/2009	Zhang	525/453	C09D 5/1693
2011/0033540	12/2010	Daniloff	424/484	A61L 27/20
2012/0046735	12/2011	Sill et al.	N/A	N/A
2012/0149983	12/2011	Chin	600/114	A61B 17/3421
2018/0042742	12/2017	Venkatraman	N/A	A61F 2/94
2018/0208735	12/2017	Nash et al.	N/A	N/A
2019/0217023	12/2018	Chattaraj et al.	N/A	N/A

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2673323	12/2007	CA	N/A
1878579	12/2005	CN	N/A
2172295	12/1985	GB	N/A
H07100744	12/1994	JP	N/A
2006130122	12/2005	WO	N/A
2016025945	12/2015	WO	N/A
2018198051	12/2017	WO	N/A
2019038378	12/2018	WO	N/A
2019243631	12/2018	WO	N/A

OTHER PUBLICATIONS

Hirota et al. Coating of a surface with 2-methacryloyloxyethyl phosphorylcholine (MPC) c-polymer significantly reduced retention of human pathogenic microorganisms. FEMS Microbiology Letters. May 31, 2005. vol. 248 pp. 37-45 (Year: 2005). cited by examiner
International Search Report; International Searching Authority; International Patent Application No. PCT/US2022/014847; Mar. 15, 2022; 2 pages. cited by applicant

Written Opinion of the International Searching Authority; International Searching Authority; International Patent Application No. PCT/US2022/014847; Mar. 15, 2022; 5 pages. cited by applicant

Hirota et al. "Coating of a surface with 2-methacryloyloxyethyl phosphorylcholine {MPC} co- 2, 7, 13, 17-18 polymer significantly reduces retention of human pathogenic microorganisms" FEMS Microbiology Letters. May 31, 2005 (May 31, 2005) vol. 248, p. 37-45. cited by applicant
Extended European Search Report, European Patent Office, European Patent Application No. 21916395.3, Oct. 11, 2024, 16 pages. cited by applicant

Pavesio et al., "Anit-Adhesive Surfaces Through Hyaluronan Coatings," Medical Device Technology, Sep. 1997, pp. 20-27. cited by applicant

Desmet et al., "Nonthermal Plasma Technology as a Versatile Strategy for Polymeric Biomaterials Surface Modification: A Review," BioMacromolecules, Sep. 2009, vol. 10 No. 9, The American Chemical Society, pp. 2351-2378. cited by applicant

Chinese Office Action, China National Intellectual Property Administration, Chinese Patent Application No. 1 2021800884937, Apr. 28, 2025, 13 pages. cited by applicant

Primary Examiner: Proctor; Cachet I

Attorney, Agent or Firm: TAFT STETTINIUS HOLLISTER LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S) (1) The present application is a continuation application of, and claims priority to, U.S. application Ser. No. 17/564,586, which was filed on Dec. 29, 2021, and which claims priority to U.S. Provisional Patent Application No. 63/132,071, which was filed on Dec. 30, 2020. The contents of those applications are incorporated by reference herein in their entireties.

FIELD OF THE DISCLOSURE

(1) The present disclosure relates to a subcutaneous device, and more specifically, to a subcutaneous device with a treated surface.

BACKGROUND OF THE DISCLOSURE

(2) An inserter device, which may be referred to as an inserter or injector, may be used in the medical field for inserting medical devices (e.g., infusion sets, sensors, or the like) through the skin of a patient in a more or less automated fashion.

(3) In some cases, when using an inserter, the user (e.g., a patient or a treatment provider) has to apply a force towards the surface of the user's skin to inject the medical device or a part of the medical device having the form of a needle, a cannula, a sensor, or the like. This may cause physiological or psychological distress and/or discomfort, and may lead to inappropriate application of the medical device. Many people are afraid of sharp objects, such as injection needles and other penetrating devices used for medical treatment and therapy, for example. This

fear may be irrational and may hamper an appropriate medical treatment. In one example, in the case of self-medication, a lack of administration of an appropriate dose of a required medical composition may lead to potentially life-threatening complications. In another example, when treating diabetes (e.g., in juveniles), there is a risk that the required insulin dose may not be self-administered due to irrational fear of the insertion needle and/or a general lack of knowledge and awareness concerning the consequences of omitting the correct application of the device and dosage.

(4) Another issue with insertion of medical devices may be the risk of contamination of the penetrating member before or during application. This may lead to an infection of the patient (e.g., through a contaminated insertion needle). The longer a needle is exposed, the higher the risk of accidental contamination, which may result from touching the needle with a finger, from bringing the needle in contact with an unclean surface, from airborne contamination, from aerosol contamination, or from the like. Depending on the nature of the contamination (e.g., contamination from a virus, bacteria, fungus, yeast, and/or prion) combined with the general health status of the patient, the resulting infection may rapidly turn into a life threatening situation.

(5) Because contact with a contaminated insertion needle may be life-threatening, especially in hospital environments, the risk of accidental exposure to contaminated material in the form of a used insertion needle should be minimized. Thus, there is a need in the art for a robust, reliable, accurate, safe, hygienic, and user friendly inserter device, which addresses the issues discussed above.

(6) Some inserter devices include a cannula and/or needle placed within a body section for insertion into the subcutaneous layer of skin. The cannula may remain in place for up to three days, or perhaps longer, at least in some cases. If the cannula remains in place longer than approximately three days in one location in the subcutaneous layer of skin, the patient's body may identify the cannula as a foreign body and respond by rejecting the cannula. The rejection of the foreign body may cause a reduction in absorption of any drug being administered through the cannula. As a result, it may be advantageous to provide a solution to allow for increasing the length of time it takes for a body to begin to reject the cannula. Even more, it may be desirable to provide a cannula and related components which may remain undetected by the patient's body while the cannula is subcutaneously inserted.

SUMMARY

(7) The present disclosure may comprise one or more of the following features and combinations thereof.

(8) According to one aspect of the present disclosure, a method of modifying a medical device may include treating a portion of the medical device with cold plasma and functionalizing the plasma-treated portion with a polymer.

(9) In some embodiments, the polymer may include a zwitterionic polymer.

(10) In some embodiments, the zwitterionic polymer may be a sulfobetaine polymer or a carboxybetaine polymer.

(11) In some embodiments, the polymer may include a phosphorylcholine species.

(12) In some embodiments, the polymer may include a compound having the formula:

(13) ##STR00001##

(14) In some embodiments, the polymer may be a hyaluraonic acid species.

(15) In some embodiments, the polymer may include a compound having the formula:

(16) ##STR00002##

(17) In some embodiments, the plasma-treated portion of the medical device may be disposed at least partially along a surface of a subcutaneous part of the medical device that is configured for subcutaneous positioning in a user.

(18) In some embodiments, the plasma-treated portion of the medical device may be at least partially defined along a surface of a cannula and configured for subcutaneous positioning in a user.

- (19) In some embodiments, the polymer may include a phosphorylcholine species, and the plasma-treated portion of the medical device may be at least partially defined along a surface of a cannula and configured for subcutaneous positioning in a user.
- (20) In some embodiments, the polymer may include a hyaluronic acid species, and the plasma-treated portion of the medical device may be at least partially defined along a surface of a cannula and configured for subcutaneous positioning in a user.
- (21) In some embodiments, treating the portion of the medical device may include treating the portion at temperatures of about 0-60 degrees Celsius.
- (22) In some embodiments, treating the portion of the medical device may include treating the portion at pressures of around 1 atmosphere.
- (23) In some embodiments, treating the portion of the medical device may include treating the portion at temperatures of about 0-60 degrees Celsius and at pressures of around 1 atmosphere.
- (24) In some embodiments, functionalizing the plasma-treated portion with the polymer may include functionalizing the plasma-treated portion subsequent to treating the portion of the medical device.
- (25) In some embodiments, functionalizing the plasma-treated portion with the polymer may include functionalizing the plasma-treated portion simultaneously with treating the portion of the medical device.
- (26) In some embodiments, the method may include immobilizing a biomolecule through a linking molecule located on a surface of the plasma-treated treated portion by generating and maintaining a non-thermal atmospheric pressure plasma at a temperature at or below about 60° C., and the linking molecule may be deposited onto the plasma-treated portion by exposing the plasma-treated portion to a first plasma jet and the linking molecule to generate a linking layer on the plasma-treated portion.
- (27) In some embodiments, the method may include depositing the biomolecule onto the linking layer by exposing the linking layer to a second plasma jet and the biomolecule.
- (28) In some embodiments, the biomolecule may include a phosphorylcholine species.
- (29) In some embodiments, the biomolecule may include a compound having the formula:
- (30) ##STR00003##
- (31) In some embodiments, the biomolecule may include a hyaluraonic acid species.
- (32) In some embodiments, the biomolecule may include a formulation compound having the formula:
- (33) ##STR00004##
- (34) In some embodiments, the polymer may include a methacrylated HLA.
- (35) In some embodiments, the polymer may include a methacrylated HLA compound having the formula:
- (36) ##STR00005##
- (37) In some embodiments, the polymer may include one or more hydrophilic polyalkylene glycol polymers.
- (38) In some embodiments, the one or more hydrophilic polyalkylene glycol polymers may include PEG or related PEG-like polymers with different architectures.
- (39) In some embodiments, the architectures may be one or more of networked, branched, dendritic, or hyperbranched.
- (40) According to another aspect of the present disclosure, a method of manufacturing a medical device may include providing a subcutaneous part configured to be positioned subcutaneously in a user and performing a surface treatment on a portion of the subcutaneous part. Performing a surface treatment on the portion of the subcutaneous part may include exposing a treated portion of the subcutaneous part to cold atmospheric plasma to create a linking layer thereon and functionalizing the linking layer with a biomolecule configured to reduce a foreign body response to the subcutaneous part when the subcutaneous part is subcutaneously positioned in the user.

- (41) In some embodiments, the method may include forming one or more apertures through the subcutaneous part prior to performing the surface treatment on the portion of the subcutaneous part, and performing the surface treatment on the portion of the subcutaneous part may not close the one or more apertures.
- (42) In some embodiments, the biomolecule may include a phosphorylcholine species.
- (43) In some embodiments, the biomolecule may include a compound having the formula:
- (44) ##STR00006##
- (45) In some embodiments, the biomolecule may include a hyaluraonic acid species.
- (46) In some embodiments, the biomolecule may include a compound having the formula:
- (47) ##STR00007##
- (48) According to yet another aspect of the present disclosure, a method of manufacturing a medical device may include providing a subcutaneous part configured to be positioned subcutaneously in a user and performing a surface treatment on a portion of the subcutaneous part. Performing the surface treatment on the portion of the subcutaneous part may include exposing a treated portion of the subcutaneous part to cold atmospheric plasma to create a linking layer thereon, functionalizing the linking layer with a biomolecule configured to reduce a foreign body response to the subcutaneous part when the subcutaneous part is subcutaneously positioned in the user, and immobilizing the biomolecule through a linking molecule located on a surface of the treated portion.
- (49) In some embodiments, immobilizing the biomolecule through the linking molecule may include generating and maintaining a non-thermal atmospheric pressure plasma at a temperature at or below about 60° C.
- (50) In some embodiments, immobilizing the biomolecule through the linking molecule may include depositing the linking molecule onto the treated portion by exposing the treated portion to a first plasma jet and the linking molecule to generate the linking layer on the plasma-treated portion.
- (51) In some embodiments, the method may include depositing the biomolecule onto the linking layer by exposing the linking layer to a second plasma jet and the biomolecule.
- (52) In some embodiments, the method may include forming one or more apertures through the subcutaneous part prior to performing the surface treatment on the portion of the subcutaneous part, and performing the surface treatment on the portion of the subcutaneous part may not close the one or more apertures.
- (53) These and other features of the present disclosure will become more apparent from the following description of the illustrative embodiments.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) The invention described herein is illustrated by way of example and not by way of limitation in the accompanying figures. For simplicity and clarity of illustration, elements illustrated in the figures are not necessarily drawn to scale. For example, the dimensions of some elements may be exaggerated relative to other elements for clarity. Further, where considered appropriate, reference labels have been repeated among the figures to indicate corresponding or analogous elements.
- (2) FIG. 1 is a perspective view of an assembled inserter device;
- (3) FIG. 2A is a front perspective view of a housing of the inserter device of FIG. 1;
- (4) FIG. 2B is a sectional view of the housing taken about axis J-J;
- (5) FIG. 2C is a end view of the housing from a proximal end thereof;
- (6) FIG. 3A is a front perspective view of an outer part of the inserter device of FIG. 1;
- (7) FIG. 3B is a sectional view of the outer part taken about axis L-L;
- (8) FIG. 4A is a front perspective view of a first part of the inserter device of FIG. 1;

- (9) FIG. 4B is a sectional view of the first part taken about axis K-K;
- (10) FIG. 4C is an end view of the outer part from a distal end thereof;
- (11) FIG. 5A is a front perspective view of a second part of the inserter device of FIG. 1;
- (12) FIG. 5B is a sectional view of the second part taken about an axis connecting locking members of the second part;
- (13) FIG. 6 is a perspective view of an embodiment of a port site adapted for use with the inserter device of FIG. 1;
- (14) FIG. 7 is a sectional view of the inserter device of FIG. 1 in a shelf position;
- (15) FIG. 8 is a sectional view of the inserter device of FIG. 1 in an inserted position;
- (16) FIG. 9 is a sectional view of the inserter device of FIG. 1 in a retracted position;
- (17) FIG. 10A is a perspective view of the first part and the second part of the inserter device of FIG. 1 in one state subsequent to insertion of an insertion needle;
- (18) FIG. 10B is a perspective end view of the first part and the second part of the inserter device of FIG. 1 in another state subsequent to insertion of the insertion needle;
- (19) FIG. 10C is a perspective view of the first part and the second part of the inserter device of FIG. 1 in yet another state subsequent to insertion of the insertion needle;
- (20) FIG. 11A is a perspective view of the first part and the second part of the inserter device of FIG. 1 in one state immediately prior to retraction of the insertion needle;
- (21) FIG. 11B is a perspective end view of the first part and the second part of the inserter device of FIG. 1 in another state immediately prior to retraction of the insertion needle;
- (22) FIG. 11C is a perspective view of the first part and the second part of the inserter device of FIG. 1 in yet another state immediately prior to retraction of the insertion needle;
- (23) FIG. 12 is a simplified flowchart of a surface treatment method; and
- (24) FIG. 13 is a perspective view of an embodiment of a subcutaneous device having one or more apertures or slits defined therethrough.

DETAILED DESCRIPTION

(25) While the concepts of the present disclosure are susceptible to various modifications and alternative forms, specific embodiments thereof have been shown by way of example in the drawings and will be described herein in detail. It should be understood, however, that there is no intent to limit the concepts of the present disclosure to the particular forms disclosed, but on the contrary, the intention is to cover all modifications, equivalents, and alternatives consistent with the present disclosure and the appended claims.

(26) References in the specification to “one embodiment,” “an embodiment,” “an illustrative embodiment,” etc., indicate that the embodiment described may include a particular feature, structure, or characteristic, but every embodiment may or may not necessarily include that particular feature, structure, or characteristic. Moreover, such phrases are not necessarily referring to the same embodiment. Further, when a particular feature, structure, or characteristic is described in connection with an embodiment, it is submitted that it is within the knowledge of one skilled in the art to effect such feature, structure, or characteristic in connection with other embodiments whether or not explicitly described. Additionally, it should be appreciated that items included in a list in the form of “at least one A, B, and C” can mean (A); (B); (C); (A and B); (A and C); (B and C); or (A, B, and C). Similarly, items listed in the form of “at least one of A, B, or C” can mean (A); (B); (C); (A and B); (A and C); (B and C); or (A, B, and C).

(27) In the drawings, some structural or method features, such as those representing devices, modules, instructions blocks and data elements, may be shown in specific arrangements and/or orderings for ease of description. However, it should be appreciated that such specific arrangements and/or orderings may not be required. Rather, in some embodiments, such features may be arranged in a different manner and/or order than shown in the illustrative figures. Additionally, the inclusion of a structural or method feature in a particular figure is not meant to imply that such feature is required in all embodiments and, in some embodiments, may not be included or may be combined

with other features.

(28) In some embodiments, schematic elements used to represent blocks of a method may be manually performed by a user. In other embodiments, implementation of those schematic elements may be automated using any suitable form of machine-readable instruction, such as software or firmware applications, programs, functions, modules, routines, processes, procedures, plug-ins, applets, widgets, code fragments and/or others, for example, and each such instruction may be implemented using any suitable programming language, library, application programming interface (API), and/or other software development tools. For instance, in some embodiments, the schematic elements may be implemented using Java, C++, and/or other programming languages. Similarly, schematic elements used to represent data or information may be implemented using any suitable electronic arrangement or structure, such as a register, data store, table, record, array, index, hash, map, tree, list, graph, file (of any file type), folder, directory, database, and/or others, for example.

(29) Further, in the drawings, where connecting elements, such as solid or dashed lines or arrows, are used to illustrate a connection, relationship, or association between or among two or more other schematic elements, the absence of any such connection elements is not meant to imply that no connection, relationship, or association can exist. In other words, some connections, relationships, or associations between elements may not be shown in the drawings so as not to obscure the disclosure. In addition, for ease of illustration, a single connecting element may be used to represent multiple connections, relationships, or associations between elements. For example, where a connecting element represents a communication of signals, data or instructions, it should be understood by those skilled in the art that such element may represent one or multiple signal paths (e.g., a bus), as may be needed, to effect the communication.

(30) Referring now to FIG. 1, an embodiment of an inserter device **100** having automatic insertion and automatic retraction of an insertion needle **102** is shown. The inserter device **100** is used for placing a port site **104** combined with a subcutaneous part **106** (see FIGS. 7-9) subcutaneously in a patient. The port site **104** may be used for injecting portions of medication over a time period, such as a time period of up to 3 days, at least in some embodiments. The port site **104** may include, or otherwise be embodied as, an infusion device, a sensor device, a patch device, or a similar device.

(31) The inserter device **100** is shown in FIG. 1 in an assembled shelf state. In the illustrative embodiment, the inserter device **100** includes an outer part **300** and a housing **200**, and the housing **200** is partly covered by the outer part **300**. A functional part is accommodated inside the housing **200**. The illustrative functional part includes a first part **400**, a second part **500**, an insertion spring **402**, a retraction spring **502**, and an insertion needle **102** attached to the second part **500**. The inserter device **100** is adapted for use with a port site **104** (e.g., an infusion device) attached thereto, but it should be appreciated that other suitable port sites could also be used. Throughout the description, the term 'distal' refers to the end/surface/element farthest away from the port site **104** and the term 'proximal' refers to the end/surface/element closest to the port site **104**. Additionally, for the purposes of the present disclosure, discussion of the 'vertical' plane/direction refers to the plane/direction extending parallel with the insertion needle **102**, and discussion of the 'horizontal' plane/direction refers to the plane/direction parallel with the patient's skin surface that is perpendicular to the vertical plane/direction.

(32) In the illustrative embodiment, FIG. 2A shows the housing **200** in a front view, FIG. 2B shows the housing **200** in a cut-through view along the axis J-J, and FIG. 2C shows the housing **200** in a view from the proximal end **201** of the housing **200**. The shape and/or diameter of the proximal end **201** may have different designs depending on the port site **104** attached to the proximal end **201**, and it should be appreciated that the invention is not limited to the shape and/or diameter depicted. Rather, the proximal end **201** may have various dimensions and take the shape of one or more suitable geometric forms depending on the port site **104**.

(33) The illustrative housing **200** includes, or is otherwise embodied as, an elongated tube comprising a sidewall **203** with an inner surface forming a cavity. The housing **200** has an oval

shape to ensure that the first part **400** cannot rotate in the horizontal plane before, during, or after activation of the insertion device **100**. Of course, in other embodiments, it should be appreciated that the housing **200** may take the shape of other suitable geometric forms.

(34) The housing **200** illustratively includes two proximal protrusions **202** positioned opposite one another at the distal end **205** of the housing **200**. The proximal protrusions **202** are adapted for engaging with (e.g., being received in) two corresponding openings **304** in the outer part **300**. The housing **200** additionally includes two openings **204** positioned horizontally opposite one another approximately in the middle (e.g., lengthwise) of the housing **200**. The openings **204** are adapted for engaging with locking elements **312** on the outer part **300**. The proximal protrusions **202** and the openings **204** are aligned pairwise along vertical axes extending from the proximal end **201** to the distal end **205**, thus extending in a direction parallel to the direction of insertion.

(35) In the illustrative embodiment, on the inside of the housing **200**, a housing guide member **206** is disposed that extends from the proximal end **201** to approximately the middle (e.g., lengthwise) of the housing **200**. The housing guide member **206** extends along an axis parallel to the vertical axes defined by the pairs of proximal protrusions **202** and openings **204** and is circumferentially displaced approximately 80-110 degrees in relation thereto. The housing guide member **206** is adapted for being received by a slit **412** of the first part **400**, and the housing guide member **206** is dimensioned such that when the guide member **206** is received in the slit **412**, part of the guide member **206** extends through the slit **412** and into the interior of the first part **400**.

(36) FIG. 3A illustrates a front view of the outer part **300** and FIG. 3B shows the outer part **300** in a cut-through view along the axis L-L. The outer part **300** illustratively includes, or is otherwise embodied as, a first section **302** and a second section **303**. The first section **302** includes two openings **304** disposed at the distal end **306** of the first section **302**. The two openings **304** are sized for interaction with the corresponding proximal protrusions **202** of the housing **200**, thereby interlocking the housing **200** and the outer part **300**. On the inside of the distal end **306**, a protruding annular collar **314** is provided that is surrounded by a distal end of the insertion spring **402**. As a result, the insertion spring **402** cannot be displaced horizontally before, during, or after insertion and/or retraction of the insertion needle **102**.

(37) The second section **303** illustratively includes two outwardly extending arms **307**, an engaging device **310**, release elements **308**, and locking elements **312**. The arms **307** are positioned opposite one another in the horizontal plane and are directly attached to the first section **302** at their distal ends. The engaging device **310** is illustratively embodied as a ring, which may be either circular or oval. Of course, in other embodiments, the engaging device **310** may take the shape of other suitable geometric forms. The release elements **308** extend partly along the arms **307** and partly along the engaging device **310**.

(38) In the illustrative embodiment, the locking elements **312** include two inwardly pointing parts for engaging with the openings **204** in the housing **200**. The locking elements **312** are positioned opposite one another on the engaging device **310** and are circumferentially displaced approximately 90 degrees in relation to the release elements **308** and the arms **307**. The locking elements **312** ensure that the insertion spring **402** stays in a pre-loaded position before activation of the inserter device **100** by engaging with corresponding locking members **410** on the first part **400**, thereby fixing the first part **400** at the top of the distal end **205** of the housing **200** and on top of the locking elements **312**.

(39) FIG. 4A illustrates the first part **400** in a front view, FIG. 4B illustrates the first part **400** in a cut-through view along the axis K-K, and FIG. 4C illustrates the first part **400** from the distal end **401** of the first part **400**. The first part **400** illustratively includes a tube comprising a first section **404** and a second section **408**. The outer diameter of the first section **404** is smaller than the outer diameter of the second section **408** such that a support surface **403** is formed. One end of the insertion spring **402** rests on the support surface **403**.

(40) The first section **404** illustratively includes two releasing slits **406** for engaging with

corresponding locking members **508**, **508'** of the second part **500**. The releasing slits **406** each extend from the distal end **401** along a vertical axis parallel to the insertion direction. The first section **404** further comprises a recess **405** on the inner surface to facilitate interaction with an inclining guide member **510** of the second part **500**.

(41) In the illustrative embodiment, the second section **408** has locking members **410** (e.g., two protrusions) arranged opposite one another in the horizontal plane on the outside of the second section **408**. In the pre-loaded shelf position shown in FIG. 7, the locking members **410** are engaging with the locking elements **312** of the outer part **300**. That interaction secures the insertion spring **402** in the pre-loaded position to prevent the insertion needle **102** from being activated during transportation. Between the two locking members **410**, a slit **412** is arranged for receiving the inner housing guide member **206** of the housing **200** during activation of the inserter device **100**.

(42) The illustrative proximal surface **414** of the first part **400** is provided with a central annular opening **416** (see FIGS. 4B and 7) through which the insertion needle **102** may pass when inserting the subcutaneous part **106** in a patient. The opening **416** is illustratively sized to allow only the insertion needle **102** to pass through. In some cases, the diameter of the opening **416** is only 10-20% larger than the diameter of the insertion needle **102**. This is advantageous to prevent a user from accidentally putting a finger through the opening **416** and contacting with the insertion needle **102** in use of the device **100**. Further, due to a small opening **416**, the insertion needle **102** is hardly visible, which may have a positive psychological effect on patients/users that are afraid of needles.

(43) Openings **418** are illustratively disposed on the inside of the second section **408** for engaging with corresponding locking members **508**, **508'** of the second part **500**. In the shelf and the insertion positions, the locking members **508**, **508'** of the second part **500** are supported by a support rim **419**, thereby fixing the retraction spring **502** and the second part **500** in the pre-loaded state. An annular recess **420** (see FIGS. 4B and 7) is provided on the surface **422** of the proximal end accommodating one end of the retraction spring **502**, thereby ensuring that it cannot be displaced horizontally before, during, or after insertion and/or retraction.

(44) Upon insertion of the insertion needle **102**, in the illustrative embodiment, the proximal surface **414** applies a pressure to the subcutaneous part **106** and thereby locks the subcutaneous body part **110** inside a cavity of the port site **104**. Further, since the first part **400** presses against the distal surface **114** of the subcutaneous part **106** due to the relaxed insertion spring **402** after insertion of the insertion needle **102**, the proximal surface **414** assists in releasing the subcutaneous part **106** from the insertion needle **102** as the insertion needle **102** is retracted into the inserter device **100**.

(45) Optionally, in some embodiments, the first part **400** may be provided with additional mechanisms for releasing the subcutaneous part **106** from the insertion needle **102**. In one example, those mechanism(s) may take the form of a distance piece, which assures that the subcutaneous part **106** is pushed down into the opening of the base **104** with such a force that the subcutaneous part **106** contacts, or is positioned past, a locking mechanism inside the opening of the base **104**. In particular, one mechanism for releasing the subcutaneous part **106** includes a flat spring arranged between the proximal surface **414** of the first part **400** and the distal surface **114** of the subcutaneous part **106**. The flat spring is attached to or is a part of the first part **400** at one end, at least in some embodiments. As the first part **400** is pushed down towards the base **104** by the insertion spring **402**, the flat spring will be loaded as the first part **400** gets close enough to the base **104**. The flat spring will then apply a pressure to the subcutaneous part **106** to lock the subcutaneous body part **100** inside the opening of the base **104**.

(46) FIG. 5A illustrates the second part **500** in a front view and FIG. 5B illustrates the second part **500** in a cut-through view along the axis connecting the locking members **508**, **508'**. The second part **500** includes a relatively small elongated tube sized to fit inside the first part **400**. The second part **500** includes a first section **504** and a second section **506**. The outer diameter of the first

section **504** is larger than the diameter of the second section **506** to form a support surface for accommodating one end of the retraction spring **502** as shown in FIGS. **10C** and **11C**, thereby ensuring that the retraction spring **502** remains positioned around the second section **506** at one end at all times.

(47) The locking members **508**, **508'** (in this embodiment two protrusions) illustratively arranged on the outside of the first section **504** are configured to slide inside the corresponding releasing slits **406** in the first part **400** during activation of the inserter device **100**. In between the locking members **508**, **508'** is the inclining guide member **510**. The second part **500** includes recesses **512** for guiding the second part **500** relative to the first part **400** during use of the inserter device **100**. The insertion needle **102** is attached to the second part **500** and extends vertically upward inside the normally solid second part **500**. Of course, it should be appreciated that in some embodiments, the positions of the first part **400** and the second part **500** could be reversed.

(48) FIG. **6** depicts an embodiment of the illustrative port site **104** (e.g., an infusion port) in which the subcutaneous part **106** includes a cannula **108** and a body part **110**. The body part **110** is shaped to secure the subcutaneous part **106** in the port site **104** upon insertion of the subcutaneous part **106** in the patient's skin **112**. The subcutaneous part **106** is positioned on the insertion needle **102** and kept in position due to friction between the insertion needle **102** and the soft contact parts of the subcutaneous part **106**, such as the cannula **108**, for example. The insertion needle **102** may be located inside, alongside, or outside the cannula **108**.

(49) In some embodiments, one or more surfaces of the port site **104** and/or the subcutaneous part **106** may include a treated portion **116**. The treated portion **116** may be disposed along a surface of the port site **104** and/or the subcutaneous part **106** that directly contacts the user and/or is positioned subcutaneously in the user. The treated portion **116** may undergo a surface treatment process to introduce special performance characteristics into the treated portion **116**. Consequently, interfacial phenomena (e.g., lubricity, wettability, or adhesiveness) may be controlled without modifying bulk properties of the underlying parts **104**, **106**, such as tensile strength or flexibility, for example. The surface treatment process may be a cost-effective mechanism for incorporating active agents such as drugs, antimicrobial agents, or peptides in minimal quantities that are localized only to the surfaces where they are needed (i.e., the treated portion **116**). For the subcutaneous part **106**, the treated portion **116** may include a polymeric form to render the subcutaneous part **106** less susceptible to foreign body response and thereby increase tolerability over longer wear times.

(50) In one aspect of this disclosure, the surface treatment process for the treated portion **116** may utilize cold atmospheric plasma. The cold atmospheric plasma surface treatment process may provide a surface treatment process that is versatile and implemented in mild process conditions. For example, cold atmospheric plasma may operate with low energy at room temperature (i.e., about 10-30 degrees Celsius) and atmospheric conditions (i.e., 1 atmosphere of pressure, no vacuum). Accordingly, as used herein, the term "surface treatment process" includes any cold atmospheric plasma process. One example contemplated herein implements a two-step method for the immobilization of a biomolecule through a linking molecule on the surface of the treated portion **116** by generating and maintaining a non-thermal atmospheric pressure plasma at a temperature between about room temperature and about 60° C. In one embodiment, the biomolecule may be a biopolymer or biocompatible polymer.

(51) Cold plasma, which may be referred to as non-thermal or non-equilibrium plasma, refers to cold temperature plasma formation at atmospheric pressures. It should be appreciated that cold plasma is a plasma which is not in thermodynamic equilibrium because the electron temperature is hotter than the temperature of heavy species (e.g., ions and neutrals) in the plasma. In some cases, cold plasma may be created when a sufficient amount of energy (e.g., higher than the ionization energy) is added to gaseous atoms and/or molecules, causing ionization and subsequently generating free electrons, photons, free radicals, and ionic species. The excitation energy supplied

to a gas to form a cold plasma may originate from electrical discharges, direct currents, radio frequencies, microwaves, or other forms of electromagnetic radiation. By selecting the reaction conditions accordingly (e.g., activation energy, pressure, power input, carrier gases, and initial organic compounds such as polymer or monomers), suitable modified surfaces may be created for different applications or requirements. Non-limiting examples of cold plasma technologies and methodologies for generating cold plasma include atmospheric pressure plasma jet, dielectric barrier discharge, direct current (DC) glow discharge, electrical discharge plasma, microwave discharge, pulsed power discharge, radiofrequency (RF) discharge, and the like.

(52) Polymerization of the surface in any of the embodiments described herein may include, or otherwise be embodied as, any suitable polymerization process, such as conventional condensation, addition or free radical graft polymerization (FRGP), or controlled radical polymerization (CRP) (e.g., ATRGP, RAFT, or NMGP). The surface activity may be controlled by adjusting the plasma operating parameters such as the plasma source, plasma precursor and carrier gas, gas flow rate, gas partial pressure, high frequency power, and applied voltage, as well as the preparation of the surface treatment time and substrate surface.

(53) In some embodiments, the cold plasma is cold atmospheric plasma (CAP). The cold plasma is an atmospheric pressure discharge cold plasma, at least in some embodiments.

(54) In some embodiments, the cold atmospheric plasma is at a pressure of between around 50 kPa and 150 kPa. Additionally, in some embodiments, the CAP is at a pressure of between around 60 kPa and 140 kPa, between around 70 kPa and 130 kPa, or between around 80 kPa and 120 kPa. Further, in some embodiments, the CAP is at a pressure of between around 100 kPa and 103 kPa. In other embodiments, however, the cold plasma may be applied under reduced pressure, such as below 50 kPa (e.g., between 0.01 kPa and 40 kPa or between 0.1 kPa and 25 kPa).

(55) In some embodiments, a cold plasma stream is applied to the surface to cause the formation of surface-bound active sites that function as polymerization initiators or covalent binding sites. When contacted with a polymer, monomer, or monomer solution, the active sites may facilitate formation of a dense array of graft polymers covalently bound to the substrate surface, at least in some embodiments.

(56) The surface of the medical device (e.g., the inserter device **100**) may be placed either directly into contact with the plasma as it is generated, or in a separate post-plasma area. If the surface is placed directly in contact with the plasma during generation, such placement may occur in a plasma reactor. For the purposes of the present disclosure, a post-plasma (post-discharge) area refers to an area outside of the plasma that is located downstream of a plasma forming gas flow in which reactive species such as radicals are still present. That post-plasma area is particularly useful for delicate substrate surfaces such as polymers.

(57) The cold plasma treatment may be performed at an RF power of at least 1 W, 5 W, 10 W, 15 W, or at least 20 W, at least in some embodiments. Additionally, in some embodiments, the cold plasma treatment may be performed at an RF power of no more than 2000 W, 1500 W, 1000 W, 500 W, 400 W, 300 W, 200 W, 100 W, 90 W, 80 W, 70 W, or no more than 60 W. Furthermore, in some embodiments, the treatment may be performed at an RF power of about 20 to 60 W.

(58) The temperature of the cold plasma may be at least 5° C. or at least 10° C., in some embodiments. The temperature of the cold plasma may be no more than 60° or no more than 50° C., at least in some embodiments. Further, in some embodiments, the cold plasma is at ambient temperature, such as between 15° C. and 35° C., for example.

(59) In some embodiments, the cold plasma treatment may be performed for at least 1 second, 2 seconds, 3 seconds, 4 seconds, 5 seconds, or at least 10 seconds. Additionally, in some embodiments, the cold plasma treatment may be performed for no more than 240 seconds, 180 seconds, or no more than 120 seconds. Further, in some embodiments, the treatment may be performed for about 5 to 120 seconds.

(60) In some embodiments, the cold plasma treatment may be performed at an RF power of

between about 10 W to about 60 W and for a period of between about 5 seconds to about 120 seconds. Additionally, in some embodiments, the cold plasma treatment may be performed using the aforesaid RF and time ranges with a precursor gas selected from the group including hydrogen, oxygen, nitrogen, argon, or helium.

(61) In one embodiment illustrated in FIG. 12, the surface treatment process **1200** includes a first block **1202** and a second block **1204**, which may be sequentially or simultaneously carried out. In the first block **1202**, the linking molecule is deposited onto the treated portion **116** through exposing the treated portion **116** to a first plasma jet and the linking molecule, thereby generating a linking layer on the treated portion **116**. In the second block **1204** of the process **1200**, the biomolecule is deposited onto the linking layer through exposing the linking layer to a second plasma jet and the bio molecule. International Publication Nos. WO2020099434A1, WO2019243631A1, and WO2019038378A1, all naming Molecular Plasma Group SA as the Applicant, discuss surface treatment processes considered herein and are hereby incorporated by reference herein in their entireties.

(62) The surface treatment processes contemplated herein may be implemented on any treated portion **116** to reduce foreign body response, among other things. In one aspect of this disclosure, the biomolecule deposited on the linking layer may include phosphorylcholine in order to mimic the natural chemistry of a cell's phospholipid membrane. In this example, a reactive phosphorylcholine species (such as acrylate-functionalized phosphorylcholine) is dispersed into a gas stream and then combined with cold, atmospheric plasma. The reactive species/plasma is directed onto the treated portion **116** to be modified as the plasma-activated surface reacts with the phosphorylcholine species, thereby creating covalent bonds and yielding a surface that is chemically functionalized with phosphorylcholine moieties. An exemplary phosphorylcholine species in accordance with one illustrated aspect herein is:

(63) ##STR00008##

(64) The above-described process may provide increased efficiency as to the amount of phosphorylcholine required, that is compared to a dip-coating process, among others. Further, it should be appreciated that all exposed surfaces of the treated portion **116** could be functionalized in one pass without adding a layer of material that might seal off any desirable apertures.

(65) In one aspect of this disclosure, the biomolecule deposited on the linking layer may include hyaluronic acid. Hyaluronic acid is a molecule that may be effective in reducing foreign body response, among other things. More specifically, any treated portion **116** presenting hyaluronic acid may avoid activating the macrophages responsible for initiating the foreign body response. In one example, a reactive hyaluraonic acid species is dispersed into a gas stream and then combined with cold, atmospheric plasma. The reactive species/plasma is directed onto the treated portion **116** to be modified as the plasma-activated surface reacts with the hyaluraonic acid species creating covalent bonds and yielding a surface that is chemically functionalized with hyaluraonic acid moieties. One illustrative example of a hyaluraonic acid species in accordance with the present disclosure is:

(66) ##STR00009##

(67) In one embodiment, the biomolecule polymer may be a biopolymer or biocompatible polymer. The polymer may be a homopolymer or a copolymer. An example of a biopolymer may include a glycosaminoglycan or mixtures thereof. Glycosaminoglycans are naturally occurring polysaccharides containing disaccharide repeating units of hexosamine and hexose or hexuronic acid, and may contain one or more sulphate groups or be non-sulphonated. Typically, the Glycosaminoglycan is non-sulphonated. The Glycosaminoglycan may be anionic, or cationic, or non-ionic. Typically, the Glycosaminoglycan is anionic. In one specific embodiment, the Glycosaminoglycan is an anionic, non-sulphonated Glycosaminoglycan or mixtures thereof.

(68) This disclosure contemplates using Glycosaminoglycan having any known size, type, or form. The molecular weight of the Glycosaminoglycan may range from about 5,000 to about 20,000,000, from about 10,000 to about 12,000,000, or from about 1,000,000 to about 10,000,000 Da (Daltons),

among other ranges.

(69) Glycosaminoglycan may be provided in free acid or salt form. The glycosaminoglycate may be associated with any suitable cation, including, but not limited to, alkali metals, such as sodium and potassium, alkaline earth metals, nitrogen-containing cations, such as ammonium, substituted ammonium and quaternized derivatives thereof, and other suitable cations. Preferred salts of Glycosaminoglycan and derivatives thereof include alkali metal or alkaline earth metal glycosaminoglycates. The Glycosaminoglycan may be provided in pure form, as a mixture of Glycosaminoglycan with proteins and naturally occurring substances derived by the production of Glycosaminoglycan from natural material, or as a chemically modified, Glycosaminoglycan derivative. Mixtures of such glycosaminoglycans may also be provided.

(70) Representative glycosaminoglycans include hyaluronan or derivatives thereof, such as hylan, heparin, heparin, chondroitin, keratin, dermatan, and sulfates of such materials. A particularly preferred Glycosaminoglycan is hyaluronan, and derivatives thereof, which contain repeating disaccharide structure of D-glucuronic acid and 2-acetamido-2-desoxy-D-glucose joined by alternating β 1,3 glucuronidic and β 1,4 glucosaminidic bonds. Representative hyaluronan and derivatives thereof which may be provided include, but are not limited to: BIOMATRIX® hyaluronan provided by Biomatrix, Inc., such as described in U.S. Pat. No. 4,303,676 (Balazs) which is incorporated herein by reference, HYLADERM® hylan provided by Biomatrix, Inc., such as described in U.K. Published Patent Application No. 2,172,295A (Balazs, et al.) which is incorporated herein by reference; and substantially pure hyaluronan such as described in U.S. Pat. No. 4,141,973 (Balazs) which is incorporated herein by reference.

(71) In some embodiments, the polymer may be biocompatible. A biocompatible polymer may be polymer having a phospholipid group, typically a phosphorylcholine group. The presence of the phospholipid group may mimic the natural chemistry of a cell's phospholipid membrane.

(72) The biomolecule polymer may be any hydrophilic polyalkylene glycol polymer as well, at least in some embodiments. This biomolecule polymer may be PEG, or related PEG-like polymers with different architectures (networked, branched, dendritic, hyperbranched, etc.)

(73) In another example, the biomolecule polymer may include methacrylated HLA such as:

(74) ##STR00010##

(75) In some embodiments, the biocompatible polymer may be obtained/obtainable by synthesizing a monomer having a phosphorylcholine structure and polymerizing it with an (meth)acrylic monomer. In the case of a (meth)acrylic ester monomer, the alkyl ester of acrylic acid and methacrylic acid alkyl esters of 1 to 20 carbon atoms may be used. In the case of copolymer production, or (meth)acrylic ester monomer, the alkyl ester of acrylic acid and methacrylic acid alkyl esters of 1 to 8 alkyl esters may typically be used. Specific examples of the (meth)acrylic ester monomer include methyl acrylate, ethyl acrylate, butyl acrylate, 2-ethylhexyl acrylate (2-ethylhexyl acrylate), lauryl acrylate, and stearyl, the alkyl ester of methacrylic acid and methyl methacrylate for example methyl methacrylate, ethyl methacrylate, butyl methacrylate, 2-ethylhexyl methacrylate (2-ethylhexyl methacrylate), lauryl methacrylate, and stearyl methacrylate. As used herein, the term “(meth)acrylic” is intended to refer to acrylic or methacrylic, typically acrylic being typical for biological applications.

(76) In various embodiments, the biocompatible polymer may have a molecular weight of about 5,000 to about 20,000,000, from about 10,000 to about 12,000,000, or from about 1,000,000 to about 10,000,000 Da (Daltons).

(77) While phosphorylcholine and hyaluraonic acid are specifically discussed herein as being part of the biomolecule deposited on the linking layer during the surface treatment process, this disclosure contemplates other molecules as well. For example, other peptides, proteins, polysaccharides, and hydrophilic polymers (such as poly(ethylene oxide)) are also considered herein for biomolecules to be deposited on the linking layer during the surface treatment process.

(78) Referring now to FIG. 13, one embodiment of a subcutaneous device considered herein

includes a cannula **108** that has a plurality of apertures or slits **1302** defined therethrough. The apertures or slits **1302** may be configured to deliver a flow path for medicament or the like through the cannula **108** to the user. The apertures or slits **1302** may be laser cut into the cannula **108** through the treated portion **116**. While dip-coating the cannula **108** of FIG. **13** is one possible way of introducing the coating onto its surface, such a process can potentially result in the coating sealing the apertures or slits **1302**, thereby impacting their ability to function as intended. Accordingly, the present disclosure also envisions the surface treatment process **1200** as discussed herein, which instead utilizes the cold atmospheric plasma process to surface treat the cannula **108** at the molecular level. Such a process can be implemented without the risk of sealing any apertures or slits **1302** in the cannula **108**.

(79) In some embodiments, the surface treatment process includes introducing an phosphorylcholine species (such as acrylate-functionalized phosphorylcholine) to the treated portion **116**. The surface treatment process may involve introducing other phosphorylcholine species or other phospholipid materials as the biomolecule to the treated portion **116** as well. In some embodiments, the hydrophilic material includes, e.g., polyvinyl chloride (PVC) plasticized with dioctyl terephthalate (bis(2-ethylhexyl) benzene-1,4-dicarboxylate or di(2-ethylhexyl) terephthalate, (DOTP) or (DEHT), respectively. In some embodiments, the hydrophilic material incorporated into a TPE may include a polyolefin based synthetic thermoplastic polyolefin elastomer containing a hydrophilic additive.

(80) In some embodiments, the treatment process may introduce a hydrogel material including polyvinylpolypyrrolidone (PVPP) and/or polyvinylpyrrolidone (PVP) to the treated surface **116** as the biomolecule. In some embodiments, a silver or silver chloride material may be any one or more of those described in U.S. application Ser. No. 11/194,951 and U.S. Pat. No. 6,451,003, each of which are incorporated herein by reference in their entireties.

(81) In FIGS. **7-9**, the inserter device **100** is displayed in a cut-through view along line AA. In some embodiments, the four parts of the inserter device **100** (i.e., the housing **200**, the outer part **300**, the first part **400**, and the second part **500**) are constructed from a hard plastic possibly combined with sections of a softer material to prevent the parts from breaking during activation of the inserter device **100**. The insertion spring **402** and the retraction spring **502** may have a metallic construction, but other types of materials could also be used.

(82) FIG. **7** shows the inserter device **100** in a shelf state before activation of the inserter device **100**. Both springs **402**, **502** are in a pre-loaded position. The insertion spring **402** and first part **400** are secured in the pre-loaded shelf position by the locking elements **312**, which prevent the first part **400** from being displaced in relation to the housing **200**. The second part **500** is kept in the pre-loaded shelf position by the locking members **508**, **508'**, which are engaging with the two openings **418** and the support rim **419** on the inside of the first part **400**. The pre-loading of the two springs **402**, **502** in the shelf state ensures an advantageous compact design of the inserter device **100**.

(83) FIG. **8** shows the inserter device **100** in the inserted position in which the cannula **108** has been inserted into the patient's skin **112** and the body part **110** is secured inside the port site **104**. The port site **104** includes a proximal surface **118** configured to contact the patient's skin **112**. In some embodiments, the treated portion **116** is positioned on the proximal surface **118** of the port site **104**.

(84) As shown in FIG. **7**, the port site **104** includes inner surfaces **120** and an outer surfaces **122**. The inner surfaces **120** include the surfaces arranged to surround the body part **110** when the body part **110** is inserted in a cavity of the port site **104**. The inner surfaces **120** also include the surfaces which define an opening in the port site **104** through which the cannula **108** extends. The remaining surfaces of the port site **104** define the outer surfaces **122** (including the proximal surface **118**). The treated portion **116** may include any one or more of the surfaces **120** and the surfaces **122** of the port site **104**.

(85) Referring now to FIG. **9**, the cannula **108** includes an inner surface **124** and an outer surface

126. The inner surface is configured to contact the insertion needle **102** to maintain the insertion needle **102** in position due to the friction therebetween as described above. The outer surface **126** is positioned opposite the inner surface **124**. The treated portion **116** may be positioned on one or both of the inner surface **124** and the outer surface **126** of the cannula **108**.

(86) As shown in FIG. 7, the body part **110** may include outer surfaces **128** including a ribbed portion configured to maintain the body part **100** within the cavity of the port site **104**. Further, the body part **110** may include inner surfaces **130** configured to receive an external device such as an injection needle or a supporting structure thereof. The treated portion **116** may include any one or more of the surfaces included in the inner surfaces **130** and the outer surfaces **128** of the body part **110**.

(87) In some embodiments, the port site **104** includes an adhesive surface, which may be used for attaching the port site **104** releasably to the patient's skin **112**. A release paper may be removed from the port site **104** prior to placing it on the patient's skin **112**. In such embodiments, the adhesive material may be part of the treated portion or may be separate and/or distinct from the treated surface.

(88) In the inserted position shown in FIG. 8, the insertion needle **102** is still inserted in the patient, thus it has not yet returned to a retracted position. The insertion spring **402** is in a relaxed position, whereas the retraction spring **502** is still in the pre-loaded position.

(89) FIG. 9 shows the inserter device **100** in a retracted position after the cannula **108** has been inserted into the patient's skin **112** and the insertion needle **102** attached to the second part **500** has been retracted to a position at the distal end **205** of the housing **200** such that the insertion needle is no longer positioned inside the first part **400**. The retraction spring **502** is in the relaxed position in which it cannot be re-loaded again without breaking apart the inserter device **100**. This ensures that the insertion needle **102** is contained inside the inserter device **100** and unable to extend outside of it.

(90) Insertion of the subcutaneous part **106** into a patient's skin **112** is done by placing the inserter device **100** on the patient's skin **112** with the port site **104** positioned directly on top of the patient's skin **112**, and then activating the inserter device **100**. Typically, a protective release paper has to be removed from the port site **104** prior to placing it on the patient's skin **112**, thereby exposing an adhesive layer underneath the port site **104** for fastening the port site **104** to the patient's skin **112**.

(91) Activation of the inserter device **100** is done by applying a pressure on the two release elements **308** on the outer part **300**, i.e. deforming the engaging device **310** by pressing the two release elements **308** closer together. The distance between the locking elements **312** thereby increases such that there is enough space to allow for the locking members **410** on the first part **400** to pass by the locking elements **312** at the aid of the insertion spring **402**, the latter which in this manner is allowed to relax.

(92) The clock-wise turning of the second part **500** prompted by the housing guide member **206** progressing inside the slit **412** and turning the inclining guide member **510** is observable when comparing FIGS. 10A-C and FIGS. 11A-C, in particular the FIGS. 10A-B and FIGS. 11A-B. The release of the locking members **508**, **508'** from the inner openings **418** is seen most clearly in the FIGS. 10C and 11C, where FIG. 10C shows the locking members **508**, **508'** being secured underneath the inner openings **418**, and FIG. 11C shows the locking members **508**, **508'** positioned in the releasing slits **406** in first part **400**, allowing the retraction spring **502** to relax and thereby push the second part **500** to an extracted position, where it is no longer contained inside the first part **400**.

(93) The second part **500** is normally turned 10-40 degrees in relation to the first part upon release of the second part **500** from the first part **400**.

(94) The inserter device **100** is constructed such that it can only be used once, since it is impossible to re-load the springs **402**, **502** after activation of the inserter device **100**. This is advantageous as the user cannot be tempted to use the device more than once and thereby expose himself/herself to

an unnecessary health risk.

(95) Construction of the inserter device **100** from essentially four interconnected parts **200**, **300**, **400**, **500** combined with two springs **402**, **502** and an insertion needle **102** allows for a simple construction, whereby a rather compacted device is obtained. This reduces production costs.

(96) Normally, the inserter device **100** is contained in a protective bag during transportation. The conditions inside the bag are sterile ensuring that the inserter device **100** can be kept sterile up until the time where it is going to be used. The only time, the inserter needle **102** is exposed is in the brief moment of insertion. This makes the inserter device **100** safe to handle as the user cannot get in contact with the insertion needle **100** prior to activation of the device and/or after the automatic retraction of the insertion needle **100**. It is thereby safe to dispose the inserter device **100** along with ordinary household waste without protecting it beforehand.

(97) The automatic insertion and automatic retraction of an insertion needle **102**, prompted by applying a pressure in the horizontal plane, is easy to perform by the user, since it essentially involves one action. Further, as the insertion process does not involve applying a pressure in the direction towards to skin, the procedure is more appealing to users that have a fear of injection needles and other penetrating devices, as these users often find it significantly more difficult to insert an insertion needle if they have to apply a pressure towards the skin at the same time.

(98) Various plasma coating types (e.g., PEG, Phosphorocholine (PC), and Hyaluronic acid (HLA)) were applied onto PTFE cannulas. The results are summarized in Table 1 below.

(99) TABLE-US-00001 TABLE 1 Sheet Canula Sample Coating WCA WCA # Type Precursor [°]
[°] 0 None untreated 105-110 113-115 1 PEG 3EGDVE 27-28 81-84 2 PEG Activation 27-28 N/A
3EGDVE 3 PC MA-PC 40-45 91-92 4 PC MA-PC 40-45 N/A 5 PC MA-PC 45-50 72-75 6 PC
Activation 40-45 80-83 MA-PC 7 HLA HAM-201c/ 33-45 85-87 EGDMA 8 HLA HAM-201c/ 39-
45 N/A EGDMA 9 HLA HAM-201c/ 38-42 80-81 EGDMA 10 HLA Activation 40-43 82-84
HAM-201c/ EGDMA 3EGDVE = Tri(ethylene glycol) divinyl ether (CAS 765-12-8) EGDMA =
Ethylene glycol dimethacrylate (CAS 97-90-5) MA-PC = 2-Methacryloyloxyethyl
phosphorylcholine (CAS 67881-98-5) 10 wt % in EGDMA/EtOH 50/50 HAM-20k = Hyaluronic
acid methacrylate (Mw 20,000-30,000) 2 wt % in H.sub.2O Activation: 8 slm CO.sub.2 in 80 slm
N.sub.2-5 b-a-f - Plasma power = 450 W 3EGDVE=Tri(ethylene glycol) divinyl ether (CAS 765-
12-8). Precursor for the plasma deposition of anti-fouling PEG-like coatings. 3EG units. Vinyl
groups tend to enhance grafting and deposition rate. MA-PC=2-Methacryloyloxyethyl
phosphorylcholine (CAS 67881-98-5) 10 wt % in EGDMA/EtOH 50/50. Methacrylate-
functionalized phosphorylcholine. Suggested by ConvaTec, to mimic cell walls. MA-PC was
poorly soluble in EGDMA (crosslinker). It was very soluble in ethanol. It was then decided to
dissolve 10 wt % of MA-PC, in a 50/50 (wt) mixture of EGDMA and ethanol. Plasma deposition of
this formulation should lead to a MA-PC-rich, EGDMA-based plasma-polymer matrix. HAM-
20k/EGDMA=HAM-20k=Hyaluronic acid methacrylate (Mw 20,000-30,000) 2 wt % in H.sub.2O.
HAM-20k was only soluble in water. We also tried to dissolve it in EtOH and EGDMA,
unsuccessfully. It was then decided to co-inject the HAM-20k solution and EGDMA, using
separate atomizers simultaneously. Plasma co-deposition of the water-based HAM-20k solution and
EGDMA should lead to a HAM-20k-rich, EGDMA-based plasma-polymer matrix. UV1 and
UV2=Rhodamine 6G (R6G) was used as UV-tracer for Q&D testing. The UV1 solution was
prepared by adding 0.1 wt % of R6G in a 3EGDVE/EtOH 90/10 (wt) solution. Addition of EtOH
was necessary to completely dissolve R6G. The UV2 solution was prepared by adding 1 wt % of
R6G in a EGDMA/EtOH 80/20 (wt) solution.

MPG's PlasmaSpotR equipment was used for all treatments (see FIG. 2). A specific nozzle, designed and printed by MPG (ref: 20 000106), enabled uniform treatment of the outer walls of the cannulas. Cannulas were mounted on a rotating (ca. 5 RPM) sample holder system by means of a long, gauge 27 needle (OD=0.4 mm) passing through the cannula. The plasma head was then scanned across the surface to be treated. The plasma power was fixed to 300 W in the case of

3EGDVE (see experimental table above). This value should lead to optimal grafting and highest crosslinking degree of the PEG-like plasma coating. For the MA-PC and HAM-20k/EGDMA cases, two different plasma power settings were tested: 300 W and 450 W. Line speed was arbitrarily set to 0.6 m/min, and the number of passes (.fwdarw.coating thickness) was arbitrarily set to a relative high value of 20 (10 back-and-forth scans). Coating thickness can be optimized at a later stage of the research. The mass feed of the precursor was controlled by the “precursor flow” parameter. This parameter was fixed in the 3EGDVE case to the already known optimal precursor feed, while it was varied in other cases. Nitrogen (N.sub.2; 80 slm) was the main plasma and carrier gas.

The power-to-precursor feed ratio, in other words the energy-per-molecule, influences the retention of key chemical moieties along with the degree of cross-linking. While higher power potentially induces a more cross-linked and better grafted plasma-coating, it also leads to more fragmentation of the precursor, thus, a loss of chemical moieties.

“Sheet WCA” were measured immediately after treatment, on flat PTFE sheets that underwent the same treatment as the cannulas. “Cannula WCA” were measured on the cannulas themselves.

Cannulas were stored in the lab for approximately 7 months between treatment and measurement.

Q&D Testing Several tests were performed at MPG, during the Discovery Day. A portable water contact angle (WCA) equipment was used to evaluate the hydrophilicity of treated model PTFE surfaces (PTFE tape). In addition, as requested by ConvaTec, extra sacrificial samples (with UV tracer) were produced to evaluate the homogeneity and resistance of the coatings to the silicone block penetration test. WCA: The values are reported in the experimental table, for every precursor and condition tested. Untreated PTFE tape: 105-110°; CO.sub.2-activated PTFE tape: 85-90°.

3EGDVE led to WCA values around 27-28°, regardless of the activation step, MA-PC-based coatings led to angles in the 40-45° range. Higher power and higher precursor flow condition #5 led to a slight increase in WCA, 45-50°. HAM-20k: condition #7 (medium power, lower precursor flow) led to WCA in the 33-35° range. Increasing power and precursor flow led to a slight increase in WCA, 40-45°. IMPORTANT NOTE: we re-checked the WCA values after wetting-drying of the samples. The measured WCA values remained in the same range as for the freshly-treated ones.

This is an indication that the plasma coatings are well-grafted, and do not release/dissolve upon humidification or, to the least, not completely. Qualitative “silicone block” test: Extra samples were prepared using UV tracer-doped chemical precursors (UV1 and UV2, see Experimental section).

The UV-tracer enabled assessing the uniformity of the coatings, and their resistance to penetration in a silicone block. As shown in FIG. 3, both PEG-like and EGDMA types of plasma coatings exhibited remarkable resistance to penetration, even in absence of CO.sub.2 plasma activation.

Conclusions Successful deposition of all types of chemistries; all conditions led to persistently wettable surfaces. The silicone block test has shown very good resistance of the coatings to penetration, even in absence of the plasma pre-activation step. This was judged very promising by ConvaTec. Samples to be tested at ConvaTec have been produced as follows: 20 replicates (9 mm cannulas) for the PEG-like coatings, conditions #1 and #2. 6 replicates (6 mm cannulas) per condition for the other two chemistries (MA-PC and HAM-20k). replicates of UV1- and UV2-type coatings have also been included in the package (6 mm cannulas). In total, 94 cannulas were treated and will be tested by ConvaTec.

(100) While this disclosure has been described with respect to at least one embodiment, the present disclosure can be further modified within the spirit and scope of this disclosure. This application is therefore intended to cover any variations, uses, or adaptations of the disclosure using its general principles. Further, this application is intended to cover such departures from the present disclosure as come within known or customary practice in the art to which this disclosure pertains and which fall within the limits of the appended claims.

Claims

1. A method of modifying a medical device, the method comprising: forming one or more apertures through the medical device; and performing a surface treatment on a portion of the medical device comprising one or more of the apertures such that the surface treatment does not close the one or more apertures, wherein performing the surface treatment on the portion of the medical device includes exposing said portion of the medical device to cold atmospheric plasma to create a linking layer thereon and functionalizing the linking layer with a biomolecule.
2. The method of claim 1, wherein the biomolecule comprises a compound comprising the formula: ##STR00011##
3. The method of claim 1, wherein the biomolecule comprises a compound comprising the formula: ##STR00012##
4. The method of claim 1, wherein the biomolecule comprises a compound comprising the formula: ##STR00013##
5. The method of claim 1, wherein exposing the treated portion of the medical device to cold atmospheric plasma comprises subjecting the treated portion to temperatures of 0-60 degrees Celsius and to pressures of 1 atmosphere.
6. The method of claim 5, wherein performing the surface treatment comprises functionalizing the linking layer with the biomolecule simultaneously with exposing the treated portion to cold atmospheric plasma.
7. The method of claim 1, wherein: the biomolecule comprises multiple hydrophilic polyalkylene glycol polymers with different architectures, and the different architectures include at least two different architectures.
8. The method of claim 7, wherein: the at least two different architectures include three different architectures, and the three different architectures are selected from the group consisting of networked, branched, dendritic, and hyperbranched.
9. The method of claim 8, wherein the multiple hydrophilic polyalkylene glycol polymers include PEG.
10. A medical device comprising: a cannula for subcutaneous positioning in a user; wherein: the cannula is formed to include a plurality of apertures, the cannula includes a portion comprising one or more of the apertures that is treated with cold plasma and functionalized with a polymer, and treatment of the portion with cold plasma and functionalization of the portion with the polymer does not close the plurality of apertures.
11. The medical device of claim 10, wherein the polymer comprises a compound comprising the formula: ##STR00014##
12. The medical device of claim 10, wherein the polymer comprises a compound comprising the formula: ##STR00015##
13. The medical device of claim 10, wherein the polymer comprises a compound comprising the formula: ##STR00016##
14. The medical device of claim 10, wherein: the polymer comprises multiple hydrophilic polyalkylene glycol polymers with different architectures, and the different architectures include at least two different architectures.
15. The medical device of claim 14, wherein: the at least two different architectures include three different architectures, and the three different architectures are selected from the group consisting of networked, branched, dendritic, and hyperbranched.
16. The medical device of claim 15, wherein the multiple hydrophilic polyalkylene glycol polymers include PEG.
17. A method of modifying a medical device, the method comprising: treating a portion of the

medical device with cold plasma; and functionalizing the plasma-treated portion with a polymer, wherein the polymer comprises a compound comprising the formula: ##STR00017##
