

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250277302

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

CHIEN; SHIH-PAO

METHOD OF MANUFACTURING HIGH CAPACITANCE ANODE AND CATHODE FILMS OF CAPACITOR

Abstract

A method of manufacturing high capacitance anode and cathode films of capacitors is revealed. Perform sputter deposition on a cathode aluminum foil in a vacuum chamber to form a cathode metal layer which is a first titanium layer on a surface of the cathode aluminum foil. Then titanium continuously reacts with nitrogen to form cathode columnar crystal deposition on a surface of the cathode metal layer and produce a cathode film. Perform sputter deposition on an anode aluminum foil in a vacuum chamber to form an anode metal layer which is a second titanium layer on a surface of the anode aluminum foil. Then titanium continuously reacts with oxygen and nitrogen to form anode columnar crystal deposition on a surface of the anode metal layer and produce an anode film. Next use the cathode and anode films with high capacitance to form cathode and anode electrodes of the capacitor.

Inventors: CHIEN; SHIH-PAO (MIAOLI COUNTY, TW)

Applicant: TRUSVAL TECHNOLOGY CO., LTD. (MIAOLI COUNTY, TW)

Family ID: 96880949

Appl. No.: 19/210088

Filed: May 16, 2025

Related U.S. Application Data

parent US continuation-in-part 17371634 20210709 PENDING child US 19210088

Publication Classification

Int. Cl.: C23C14/35 (20060101); C23C14/16 (20060101); C23C14/58 (20060101); H01G9/00 (20060101)

U.S. Cl.:

CPC **C23C14/35** (20130101); **C23C14/165** (20130101); **C23C14/5806** (20130101);
C23C14/586 (20130101); **H01G9/0029** (20130101);

Background/Summary

BACKGROUND OF THE INVENTION

Field of the Invention

[0001] The present invention relates to a method of manufacturing anode and cathode films of capacitors, especially to a method of manufacturing high capacitance anode and cathode films of capacitors, which makes capacitors formed by the manufactured anode and cathode films more convenient to use due to the high capacitance of the anode and cathode films.

Description of Related Art

[0002] Capacitors, which are passive electronic components used for storage of electrical energy in an electric field, are common on integrated circuits (ICs). The capacitors are broadly used in electronic circuits for blocking direct current while allowing alternating current to pass. In analog filter networks, they smooth the output of power supplies. In personal computer (PC) circuits, they work together with inductors to tune radios to particular frequencies. In electric power transmission systems, they stabilize voltage and power flow.

[0003] As to conductive terminals of the capacitor, two terminals connected to and arranged at the bottom of the capacitor are directly pressed and bent outward for being used conveniently in the subsequent processes. Although the above conductive terminals of the capacitor can be connected and conducted to other electronic components as expected, the conductive terminals made of metals have the problem of low capacitance, which makes the conductive terminals inconvenient to use.

[0004] Thus, there is room for improvement, and there is a need to provide a method of manufacturing anode and cathode films of capacitors that makes the capacitors formed by the anode and cathode films manufactured more convenient to use.

SUMMARY OF THE INVENTION

[0005] Therefore, it is a primary object of the present invention to provide a method of manufacturing high capacitance anode and cathode films of capacitors, which makes the capacitors formed by the manufactured anode and cathode films more convenient to use due to the high capacitance of the anode and cathode films.

[0006] In order to achieve the above object, a method of manufacturing high capacitance anode and cathode films of capacitors according to the present invention includes the following steps. [0007]

A. manufacturing a cathode film. Perform sputter deposition of a first titanium (Ti) layer on a cathode aluminum foil in a vacuum chamber. By control of power density and temperature, a cathode metal layer which is a titanium (Ti) layer with a thickness of 10-100 nm is formed on a surface of the cathode aluminum foil. Then titanium (Ti) continuously reacts with nitrogen (N) to carry out combination and deposition, while the manufacturing parameters are controlled simultaneously. Thus, titanium and nitrogen form a cathode columnar crystal structure on a surface of the cathode metal layer. The chemical formula of the cathode columnar crystal structure is $\text{Ti}_{x_1}\text{N}_{y_1}$, wherein x_1 and y_1 are selected from a group consisting of $x_1=y_1$ and $y_1<x_1<1.15$.

[0008] B. manufacturing an anode film. Perform sputter deposition of a second titanium (Ti) layer on an anode aluminum foil in a vacuum chamber. By controlling the manufacturing parameters, an anode metal layer which is the second titanium (Ti) layer having a thickness of 10-1000 nm is formed on a surface of the anode aluminum foil. Then the second titanium (Ti) layer continuously

reacts with oxygen (O) and nitrogen (N) to carry out combination and deposition while the manufacturing parameters are controlled simultaneously. Thus, titanium (Ti), oxygen (O), and nitrogen (N) form an anode columnar crystal structure on a surface of the anode metal layer. The chemical formula of the anode columnar crystal structure is $\text{Ti}_{x}\text{O}_{2-y}\text{N}_y$, and wherein $x=y$ and $0<y\leq 0.3$. [0009] C. producing capacitors. Use the cathode film and the anode film in manufacturing steps A and B, respectively, to form a cathode and an anode of the capacitor, respectively.

[0010] Preferably, the sputter deposition is performed on the cathode aluminum foil with high purity and high cleanliness in a vacuum chamber by magnetron sputtering deposition equipment or multi arc and magnetron sputtering integrated equipment in the step A.

[0011] Preferably, a thickness of the cathode metal layer formed in the step A is 30-50 nm.

[0012] Preferably, a chemical formula of the cathode columnar crystal structure formed in the step A is Ti_xN_y and $x:y=1$.

[0013] Preferably, the sputter deposition is carried out on the anode aluminum foil with high purity and high cleanliness in a vacuum chamber by magnetron sputtering deposition equipment or multi arc and magnetron sputtering integrated equipment in the step B.

[0014] Preferably, a thickness of the anode metal layer depends on the voltage applied to the anode, and is equal to the product of the voltage (in volts) and 1.4 (in nm) in the step B.

[0015] Preferably, in the step B, after completing the sputter deposition, the anode aluminum foil provided with the anode metal layer and the anode columnar crystal structure is moved to a high temperature vacuum annealing furnace for annealing at a vacuum of at least 10^{-3} Mpa and the highest temperature of 550° C. for at least 8 hours. Then cool down naturally to room temperature and take out from the furnace.

[0016] Preferably, in the step B, after completing the sputter deposition, the anode aluminum foil provided with the anode metal layer and the anode columnar crystal structure is moved to a high temperature vacuum annealing furnace for annealing at a vacuum of at least 10^{-3} Mpa and the highest temperature of 550° C. for at least 8 hours. Then cool down naturally to temperature below 100° C. and take out from the furnace.

[0017] Preferably, the anode film in the step B is manufactured in a continuous manner to form an anode ribbon which is cut into the required size and then treated by reforming and electrochemical protection.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0018] The structure and the technical means adopted by the present invention to achieve the above and other objects can be best understood by referring to the following detailed description of the preferred embodiments and the accompanying drawings, wherein:

[0019] FIG. 1 is a schematic drawing showing a manufacturing process flow chart of an embodiment according to the present invention;

[0020] FIG. 2 is a schematic drawing showing formation of a cathode film of an embodiment according to the present invention; and

[0021] FIG. 3 is a schematic drawing showing formation of an anode film of an embodiment according to the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

[0022] In order to learn technical content, features, and functions of the present invention more completely and clearly, please refer to the following detailed description with reference to the accompanying figures and reference signs.

[0023] Refer to FIG. 1, a method of manufacturing high capacitance anode and cathode films of

capacitors includes the following steps. [0024] A. manufacturing a cathode film **1**. Refer to FIG. **1** and FIG. **2**, perform sputter deposition of a first titanium (Ti) layer on a cathode aluminum foil **11** with high purity and high cleanliness in a vacuum chamber by magnetron sputtering deposition equipment or multi arc and magnetron sputtering integrated equipment and also control power density and temperature. Thus, a cathode metal layer **12** which is a titanium (Ti) layer with a thickness of 10-100 nm is formed on a surface of the cathode aluminum foil **11** while the thickness of 30-50 nm is preferred. Then titanium (Ti) continuously reacts with nitrogen (N) to carry out combination and deposition while the manufacturing parameters including power density and temperature are controlled simultaneously. Thus titanium (Ti) and nitrogen (N) form cathode columnar crystal structure **13** on a surface of the cathode metal layer **12**. The chemical formula of the cathode columnar crystal structure **13** is Ti.sub.xN.sub.y , wherein $x=y$ or when $x>y$, x is no larger than $1.15y$ while $x:y=1$ is preferred. The aforementioned manufacturing parameters are as follows: [0025] Base pressure of vacuum chamber: [00001] $1.7 \sim 4 \times 10^{-5}$ torr [0026] Operating pressure: [00002] $2.2 \sim 5. \times 10^{-3}$ torr [0027] Coating cooling drum temperature: $25 \sim 70^{\circ}$ C. [0028] B. manufacturing an anode film **2**. Also refer to FIG. **3**, perform sputter deposition of a second titanium (Ti) layer on an anode aluminum foil **21** with high purity and high cleanliness in a vacuum chamber by magnetron sputtering deposition equipment or multi arc and magnetron sputtering integrated equipment and also controlling the manufacturing parameters including power density and temperature. Thus, an anode metal layer **22** which is a second titanium (Ti) layer with a thickness of 10-1000 nm is formed on a surface of the anode aluminum foil **21**. The optimal thickness of the anode metal layer **22** depends on the voltage, equal to the product of the voltage (in volts) and 1.4 (in nm) (the voltage times 1.4). For example, the thickness is 140 nm and 280 nm when the voltage is 100V and 200V, respectively. Then titanium (Ti) continuously reacts with oxygen (O) and nitrogen (N) to carry out combination and deposition while various manufacturing parameters are controlled simultaneously. The aforementioned manufacturing parameters are as follows: [0029] Base pressure of vacuum chamber: [00003] $1.7 \sim 4 \times 10^{-5}$ torr [0030] Operating pressure: [00004] $2.2 \sim 5. \times 10^{-3}$ torr [0031] Coating cooling drum temperature: $25 \sim 70^{\circ}$ C. [0032] Thus titanium (Ti), oxygen (O), and nitrogen (N) form anode columnar crystal structure **23** on a surface of the anode metal layer **22**. The chemical formula of the anode columnar crystal structure **23** is $\text{Ti.sub.xO.sub.2-yN.sub.y}$, wherein $x=y$ and $0 \leq y \leq 0.3$. After completing sputter deposition, the anode aluminum foil **21** with the anode metal layer **22** and the anode columnar crystal structure **23** is moved to a high temperature vacuum annealing furnace for annealing at a vacuum of at least $10.\text{sup.}-3\text{Mpa}$ and the highest temperature of 550° C. for at least 8 hours. Then cool down naturally to temperature below 100° C. or room temperature and take a final product out from the furnace. The anode film **2** can be manufactured in a continuous manner to form a ribbon which is cut into the required size and then treated by reforming and electrochemical protection. [0033] C. producing capacitors. Use the cathode film **1** and the anode film **2** in manufacturing steps A and B, respectively, to form a cathode and an anode of the capacitor respectively. [0034] Therefore, the capacitors formed by the cathode film **1** and the anode film **2** are much more convenient to use due to the high capacitance of both the anode film and the cathode film. [0035] Additional advantages and modifications will readily occur to those skilled in the art. Therefore, the invention in its broader aspects is not limited to the specific details, and representative devices shown and described herein. Accordingly, various modifications may be made without departing from the spirit or scope of the general inventive concept as defined by the appended claims and their equivalent.

Claims

1. A method of manufacturing high capacitance anode and cathode films of capacitors comprising the steps of: A. manufacturing a cathode film by: performing sputter deposition of a first titanium (Ti) layer on a cathode aluminum foil in a vacuum chamber and controlling manufacturing parameters including power density and temperature, thus forming a cathode metal layer which is said first titanium (Ti) layer having a thickness of 10-100 nm formed on a surface of the cathode aluminum foil, and subsequent to the sputter deposition, continuously reacting said first titanium (Ti) layer with nitrogen (N) to carry out combination and deposition, while controlling the manufacturing parameters simultaneously to form a cathode columnar crystal structure on a surface of the cathode metal layer, wherein a chemical formula of the cathode columnar crystal structure is $\text{Ti}_{x-y}\text{N}_y$, and wherein x and y are selected from a group consisting of $x=y$ and $y < x < 1.15y$; B. manufacturing an anode film by: performing sputter deposition of a second titanium (Ti) layer on an anode aluminum foil in a vacuum chamber and controlling the manufacturing parameters, thus forming an anode metal layer which is the second titanium (Ti) layer having a thickness of 10-1000 nm formed on a surface of the anode aluminum foil, and subsequent to the sputter deposition, continuously reacting said second titanium (Ti) layer with oxygen (O) and nitrogen (N) to carry out combination and deposition, while controlling the manufacturing parameters simultaneously to form an anode columnar crystal structure on a surface of the anode metal layer, wherein a chemical formula of the anode columnar crystal structure is $\text{Ti}_{x-y}\text{O}_{2-y}\text{N}_y$, and wherein $x=y$ and $0 < y \leq 0.3$; and C. producing capacitors by using the cathode film and the anode film manufactured in the steps A and B, respectively, as a capacitor cathode and a capacitor anode, respectively.
2. The method as claimed in claim 1, wherein magnetron sputtering deposition equipment or multi arc and magnetron sputtering integrated equipment is used to perform the sputter deposition on the cathode aluminum foil with high purity and high cleanliness in the vacuum chamber in the step A.
3. The method as claimed in claim 1, wherein the thickness of the cathode metal layer formed in the step A is 30-50 nm.
4. The method as claimed in claim 1, wherein x and y in the chemical formula of the cathode columnar crystal structure formed in the step A is $x:y=1$.
5. The method as claimed in claim 1, wherein magnetron sputtering deposition equipment or multi arc and magnetron sputtering integrated equipment is used to perform the sputter deposition on the anode aluminum foil with high purity and high cleanliness in the vacuum chamber in the step B.
6. The method as claimed in claim 1, wherein the thickness of the anode metal layer is 1.4 (in nm) times a voltage (in volts) applied to the anode metal layer in the step B.
7. The method as claimed in claim 1, further comprising the steps of: fabricating the anode film in the step B in a continuous manner to form an anode ribbon, cutting the anode ribbon in anode ribbon pieces, and treating the anode pieces for protection by electrochemical protection processes.
8. The method as claimed in claim 1, further comprising: in the step B, after completing the sputter deposition, moving the anode aluminum foil configured with the anode metal layer and the anode columnar crystal structure to a high temperature vacuum annealing furnace for annealing at a vacuum of at least 10^{-3} Mpa and a temperature up to 550° C. for at least 8 hours, cooling down to room temperature or below 100° C. the anode aluminum foil configured with the anode metal layer and the anode columnar crystal structure, and removing the anode aluminum foil configured with the anode metal layer and the anode columnar crystal structure from the furnace.
9. The method as claimed in claim 8, further comprising the steps of: fabricating the anode film in the step B in a continuous manner to form an anode ribbon, cutting the anode ribbon in anode ribbon pieces, and treating the anode pieces for protection by electrochemical protection processes.
10. The method as claimed in claim 1, further comprising: in the step B, after completing the sputter deposition, moving the anode aluminum foil configured with the anode metal layer and the anode columnar crystal structure to a high temperature vacuum annealing furnace for annealing at a vacuum of at least 10^{-3} Mpa and a temperature up to 550° C. for at least 8 hours, cooling

down the anode aluminum foil configured with the anode metal layer and the anode columnar crystal structure to a temperature below 100° C., and removing the anode aluminum foil configured with the anode metal layer and the anode columnar crystal structure from the furnace.

11. The method as claimed in claim 10, further comprising the steps of: fabricating the anode film in the step B in a continuous manner to form an anode ribbon, cutting the anode ribbon in anode ribbon pieces, and treating the anode pieces for protection by electrochemical protection processes.
