

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250287747

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

SONG; Juneo et al.

EPITAXIAL DIE FOR SEMICONDUCTOR LIGHT-EMITTING DEVICE, SEMICONDUCTOR LIGHT-EMITTING DEVICE INCLUDING SAME, AND MANUFACTURING METHODS THEREOF

Abstract

The present invention relates to an epitaxial die for a semiconductor light-emitting device emitting red light, a semiconductor light-emitting device including same, and manufacturing methods thereof, wherein in the epitaxial die only one of two electrodes is exposed to the outside, and a process of forming an ohmic contact electrode can be completed in an epitaxial die manufacturing step.

Inventors: SONG; Juneo (Suwon-si, KR), YUN; Hyeong Seon (Paju-si, KR), HAN; Young Hun (Osan-si, KR), MOON; Ji Hyung (Gunpo-si, KR)

Applicant: WAVELOD CO., LTD (Hwaseong-si, KR)

Family ID: 86994708

Assignee: WAVELOD CO., LTD (Hwaseong-si, KR)

Appl. No.: 18/860630

Filed (or PCT Filed): September 18, 2023

PCT No.: PCT/KR2023/014067

Foreign Application Priority Data

KR	10-2022-0117788	Sep. 19, 2022
KR	10-2022-0169551	Dec. 07, 2022

Publication Classification

Int. Cl.: H10H20/857 (20250101); H10H20/01 (20250101); H10H20/84 (20250101)

U.S. Cl.:

CPC H10H20/857 (20250101); H10H20/034 (20250101); H10H20/0364 (20250101); H10H20/84 (20250101);

Background/Summary

TECHNICAL FIELD

[0001] The present invention relates to an epitaxial die for a semiconductor light-emitting device and a semiconductor light-emitting device including the same.

BACKGROUND ART

[0002] In general, micro light-emitting diode (LED) displays (including mini LED displays) can be classified into micro LED displays with a passive matrix (PM) driving method and micro LED displays with an active matrix (AM) driving method.

[0003] Here, PM-driven micro LED displays typically have a sapphire support substrate, which finally remains, and use sorted thick BGR (Blue, Green, and Red) chips (with both fully fabricated positive and negative electrodes of the LED), which are transferred using a chip die-level process in which either horizontal chips or flip chips can be generally utilized.

[0004] In addition, AM-driven micro LED displays typically do not have a sapphire support substrate, which finally remains, and use unsorted thin BGR (Blue, Green, and Red) chips (with both fully fabricated positive and negative electrodes of the LED), which are transferred using a wafer-level process in which horizontal chips, flip chips, or vertical chips can all be generally utilized.

[0005] These conventional typical PM- and AM-driven micro LED displays have the following common issues.

[0006] First, when considering the application of vertical chips to reduce chip die size, there is a problem that, unlike flip chips, which allow defects to be immediately confirmed after bonding, in the case of vertical chips, defects can only be confirmed after bonding and subsequent top-level wiring.

[0007] Further, in terms of a bonding process, higher precision is required in the bonding process due to the reduction in chip die size, and improved bonding strength is required due to the reduction in bonding area.

[0008] Further, in terms of a tiling process in which a plurality of unit displays are combined like tiles, there is an issue in which boundaries between the unit displays become distinct when the displays are turned off or show a black screen, and this is more noticeable in the PM driving method compared to the AM driving method. In addition, although many aspects have been improved, there is still an issue in which boundaries are visible on monochromatic screens and still images, and when using thin-film transistor (TFT) glass panels for tiling, the process is challenging due to the risk of glass breakage. Furthermore, due to the tolerance relationship between pixel pitch and tiling boundaries, various issues exist, including the expectation that the tiling process will be difficult to apply to products smaller than 100 inches.

[0009] Meanwhile, in the conventional PM-driven micro LED displays, the reduction in chip die size is the greatest challenge. That is, from an aspect ratio perspective, achieving a reduction in chip die size essentially requires decreasing a thickness of a sapphire final support substrate, but the current limit for the thickness of the sapphire support substrate is about 80 μm to 70 μm , and when reducing the thickness below 50 μm , a substrate breaking issue occurs. Further, there are complex

issues related to chip measurement and classification in this type of micro LED display, and it is expected that flip chips will be mainly used in this type of display rather than horizontal and vertical chips, but when the flip chips are used, high-precision and high-speed bonding processes, as well as materials for them, are separately required.

[0010] Further, in conventional AM-driven micro LED displays, in which the final support substrate is not present and chip die size reduction is possible, there are issues related to resolving defects (No Good, NG). That is, the fundamental issues in epitaxy and fab processes, such as yield improvement related to wavelength and electrical characteristics at the chip-on-wafer (COW) level, have not been resolved, and there is difficulty in 100% sorting and removal of defective (NG) chips. In order to address these issues, approaches such as redundancy have been recently attempted, but have not provided a fundamental solution.

DISCLOSURE

Technical Problem

[0011] The present invention is directed to solving the above-mentioned conventional problems and providing an epitaxial die for a semiconductor light-emitting device that emits red light, in which only one of two electrodes is exposed to the outside, and a process of forming a p-ohmic contact electrode or an n-ohmic contact electrode is completed at the operation of manufacturing the epitaxial die, thereby enabling a significant reduction in thickness and chip die size to improve light output, a semiconductor light-emitting device including the same, and a method of manufacturing the same.

Technical Solution

[0012] One aspect of the present invention provides an epitaxial die for a semiconductor light-emitting device, the epitaxial die including a light-emitting part configured to generate red light, a first ohmic electrode formed on the light-emitting part and electrically connected to the light-emitting part, a contact electrode formed on the first ohmic electrode and electrically connected to the first ohmic electrode, a temporary bonding layer formed to cover the contact electrode, a temporary substrate bonded on the temporary bonding layer, and a bonding pad layer formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part and functioning as a vertical chip bonding pad, wherein the contact electrode is interposed between the temporary bonding layer and the first ohmic electrode and thus is not exposed.

[0013] Another aspect of the present invention provides a semiconductor light-emitting device including a substrate part on which a first electrode pad and a second electrode pad are each formed, an epitaxial die that includes a light-emitting part configured to generate red light, a first ohmic electrode formed on the light-emitting part and electrically connected to the light-emitting part, a contact electrode formed on the first ohmic electrode and electrically connected to the first ohmic electrode, and a bonding pad layer that is formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part, functions as a vertical chip bonding pad, and is placed on the first electrode pad, a bonding layer bonding and electrically connecting the first electrode pad and the bonding pad layer, an extension electrode electrically connecting the second electrode pad and the contact electrode exposed to the outside, and a mold part surrounding the epitaxial die and the extension electrode.

[0014] Still another aspect of the present invention provides a method of manufacturing an epitaxial die for a semiconductor light-emitting device, including a first operation of preparing a growth substrate and a temporary substrate, a second operation of forming a light-emitting part, which generates red light, on the growth substrate, a third operation of forming a first ohmic electrode on the light-emitting part, a fourth operation of forming a passivation layer that covers the first ohmic electrode, a fifth operation of etching a portion of the passivation layer to expose the first ohmic electrode and forming a contact electrode to come into contact with the exposed first ohmic electrode, a sixth operation of bonding the temporary substrate and the passivation layer, in

which the contact electrode is exposed, through a temporary bonding layer, a seventh operation of separating the growth substrate, and an eighth operation of forming a bonding pad layer formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part and functioning as a vertical chip bonding pad.

[0015] Yet another aspect of the present invention provides a method of manufacturing a semiconductor light-emitting device, including a first operation of preparing an epitaxial die that includes a light-emitting part configured to generate red light, a first ohmic electrode formed on the light-emitting part and electrically connected to the light-emitting part, a passivation layer covering the first ohmic electrode and partially open to expose a portion of the first ohmic electrode, a contact electrode formed on the exposed first ohmic electrode and electrically connected to the first ohmic electrode, a temporary bonding layer formed on the passivation layer to cover the contact electrode, a temporary substrate bonded on the temporary bonding layer, and a bonding pad layer formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part and functioning as a vertical chip bonding pad, and preparing a substrate part on which a first electrode pad and a second electrode pad are each formed, a second operation of placing the epitaxial die on the first electrode pad and bonding and electrically connecting the first electrode pad and the bonding pad layer through a bonding layer, a third operation of separating the temporary substrate and etching the temporary bonding layer to expose the contact electrode, a fourth operation of forming a mold part that surrounds the epitaxial die so that the contact electrode is exposed, a fifth operation of etching the mold part so that the second electrode pad is exposed, and a sixth operation of forming an extension electrode that electrically connects the second electrode pad and the exposed contact electrode.

[0016] Yet another aspect of the present invention provides an epitaxial die for a semiconductor light-emitting device, including a light-emitting part configured to generate red light, a first ohmic electrode formed on the light-emitting part and electrically connected to the light-emitting part, a bonding pad layer formed on the first ohmic electrode and electrically connected to the first ohmic electrode and functioning as a vertical chip bonding pad, a contact electrode formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part, a temporary bonding layer formed on the lower surface of the light-emitting part to cover the contact electrode, and a temporary substrate bonded to a lower surface of the temporary bonding layer, wherein the contact electrode is interposed between the temporary bonding layer and the light-emitting part and thus is not exposed.

[0017] Yet another aspect of the present invention provides a semiconductor light-emitting device including a substrate part on which a first electrode pad and a second electrode pad are each formed, an epitaxial die that includes a light-emitting part configured to generate red light, a first ohmic electrode formed on the light-emitting part and electrically connected to the light-emitting part, a bonding pad layer formed on the first ohmic electrode and electrically connected to the first ohmic electrode and functioning as a vertical chip bonding pad, and a contact electrode that is formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part and is placed upside down on the first electrode pad, a bonding layer bonding and electrically connecting the first electrode pad and the bonding pad layer, an extension electrode electrically connecting the second electrode pad and the contact electrode exposed to the outside, and a mold part surrounding the epitaxial die and the extension electrode.

[0018] Yet another aspect of the present invention provides a method of manufacturing an epitaxial die for a semiconductor light-emitting device, including a first operation of preparing a growth substrate, a first temporary substrate, and a second temporary substrate, a second operation of forming a light-emitting part, which generates red light, on the growth substrate and forming a first ohmic electrode on the light-emitting part, a third operation of forming a passivation layer that covers the first ohmic electrode, a fourth operation of etching a portion of the passivation layer to expose the first ohmic electrode and forming a bonding pad layer, which functions as a vertical

chip bonding pad, to come into contact with the exposed first ohmic electrode, a fifth operation of bonding the first temporary substrate and the passivation layer, in which the bonding pad layer is exposed, through a first temporary bonding layer, a sixth operation of separating the growth substrate, a seventh operation of forming a contact electrode to come into contact with a lower surface of the light-emitting part, an eighth operation of bonding the second temporary substrate and the lower surface of the light-emitting part, in which the contact electrode is exposed, through a second temporary bonding layer, and a ninth operation of separating the first temporary substrate and etching the first temporary bonding layer to expose the bonding pad layer.

[0019] Yet another aspect of the present invention provides a method of manufacturing a semiconductor light-emitting device, including a first operation of preparing an epitaxial die including a light-emitting part configured to generate red light, a first ohmic electrode formed on the light-emitting part and electrically connected to the light-emitting part, a passivation layer covering the first ohmic electrode and partially open to expose a portion of the first ohmic electrode, a bonding pad layer formed on the exposed first ohmic electrode to be electrically connected to the first ohmic electrode and functioning as a vertical chip bonding pad, a contact electrode formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part, a temporary bonding layer formed on the lower surface of the light-emitting part to cover the contact electrode, and a temporary substrate bonded to a lower surface of the temporary bonding layer, and preparing a substrate part on which a first electrode pad and a second electrode pad are each formed, a second operation of placing the epitaxial die upside down on the first electrode pad and bonding and electrically connecting the first electrode pad and the bonding pad layer through a bonding layer, a third operation of separating the temporary substrate and etching the temporary bonding layer to expose the contact electrode, a fourth operation of forming a mold part that surrounds the epitaxial die so that the contact electrode is exposed, a fifth operation of etching the mold part so that the second electrode pad is exposed, and a sixth operation of forming an extension electrode that electrically connects the second electrode pad and the exposed contact electrode.

Advantageous Effects

[0020] According to the present invention, it is possible to simultaneously satisfy both the advantage of a mini light-emitting diode (LED) manufacturing process, such as ease of defect classification, and low process and capital investment costs due to the use of existing general-purpose transfer equipment as is, and the advantage of a micro LED manufacturing process, such as a dramatic reduction in thickness and a reduction in chip die size by removing a sapphire final support substrate, thereby improving light output.

[0021] In addition, according to the present invention, unlike conventional chip dies, in which two electrodes, i.e., a positive electrode and a negative electrode, are exposed to the outside, an epitaxial die of the present invention has a structure in which only one electrode is exposed to the outside, and thus, although electrical sorting through an electro luminescence (EL) measurement method is not possible, the epitaxial die can be optically sorted through a high-speed photo luminescence (PL) measurement method, allowing defects (No Good, NG) to be easily identified initially using only optical characteristics (such as wavelength, full-width at half maximum (FWHM), and intensity).

[0022] Further, according to the present invention, an epitaxial die of the present invention has the advantage that a process of forming a p-ohmic contact electrode or an n-ohmic contact electrode, which requires high-temperature heat treatment of 300° C. or higher, is completed at the operation of manufacturing the epitaxial die, so that the epitaxial die of the present invention does not require a high-temperature heat treatment process after transfer.

[0023] Further, according to the present invention, an epitaxial die of the present invention has the advantage of having a sapphire final support substrate attached, which can be removed after being transferred onto a targeted wafer, thereby enabling the die to be repositioned through conventional

chip die transfer processes such as pick-and-place and replace.

[0024] Meanwhile, the effects of the present invention are not limited to the above-mentioned effects, and various effects may be included within the scope which is apparent to those skilled in the art from contents to be described below.

Description

DESCRIPTION OF DRAWINGS

[0025] FIG. 1 illustrates an overall view of an epitaxial die for a semiconductor light-emitting device according to a first embodiment of the present invention.

[0026] FIG. 2 illustrates an overall view of a semiconductor light-emitting device according to the first embodiment of the present invention.

[0027] FIG. 3 is a flowchart of a method of manufacturing the epitaxial die for a semiconductor light-emitting device according to the first embodiment of the present invention.

[0028] FIG. 4 illustrates a process of manufacturing the epitaxial die for a semiconductor light-emitting device according to the first embodiment of the present invention.

[0029] FIG. 5 is a flowchart of a method of manufacturing the semiconductor light-emitting device according to the first embodiment of the present invention.

[0030] FIG. 6 illustrates a process of manufacturing the semiconductor light-emitting device according to the first embodiment of the present invention.

[0031] FIG. 7 illustrates an overall view of an epitaxial die for a semiconductor light-emitting device according to a second embodiment of the present invention.

[0032] FIG. 8 illustrates an overall view of a semiconductor light-emitting device according to the second embodiment of the present invention.

[0033] FIG. 9 is a flowchart of a method of manufacturing the epitaxial die for a semiconductor light-emitting device according to the second embodiment of the present invention.

[0034] FIG. 10 illustrates a process of manufacturing the epitaxial die for a semiconductor light-emitting device according to the second embodiment of the present invention.

[0035] FIG. 11 is a flowchart of a method of manufacturing the semiconductor light-emitting device according to the second embodiment of the present invention.

[0036] FIG. 12 illustrates a process of manufacturing the semiconductor light-emitting device according to the second embodiment of the present invention.

MODES OF THE INVENTION

[0037] Hereinafter, some embodiments of the present invention will be described in detail with reference to exemplary drawings. It should be noted that in adding reference numerals to the components of each drawing, the same components have the same number when possible, even though the same components are shown in different drawings

[0038] In addition, in describing the embodiments of the present invention, when detailed descriptions of related known structures or functions may obscure the gist of the present invention, the detailed description thereof will be omitted.

[0039] In addition, terms such as first, second, A, B, (a), (b), and the like may be used herein to describe components of the embodiments of the present invention. Each of these terms is not used to define an essence, order, or sequence of a corresponding component but used merely to distinguish the corresponding component from other component(s).

[0040] The present invention relates to an epitaxial die for a semiconductor light-emitting device that emits blue, green, or red light, particularly red light, and a semiconductor light-emitting device including the same. In the present invention, a semi-finished light source die with a size less than or equal to that of a mini light-emitting diode (LED), which can be sorted and has the following characteristics, is defined as the epitaxial die of the present invention.

[0041] First, unlike conventional chip dies in which two electrodes, i.e., a positive electrode and a negative electrode, are both exposed to the outside, the epitaxial die of the present invention has a structure in which only one electrode is exposed to the outside. Accordingly, since the epitaxial die of the present invention has only one (contact electrode) of the two electrodes exposed to the outside, although the epitaxial die is not electrically sorted by an electro luminescence (EL) measurement method, the epitaxial die can be optically sorted by a high-speed photo luminescence (PL) measurement method, allowing defects (NG) to be detected initially using only optical characteristics (wavelength, full-width half maximum (FWHM), intensity, and the like).

[0042] Second, in the epitaxial die of the present invention, a process of forming a p-ohmic contact electrode or an n-ohmic contact electrode, which requires high-temperature heat treatment of 300° C. or higher, is completed at the operation of manufacturing the epitaxial die. Accordingly, the epitaxial die of the present invention has the advantage of not requiring a high-temperature heat treatment process after transfer.

[0043] Third, the epitaxial die of the present invention includes a sapphire final support substrate attached thereto, which is removed after transfer. Accordingly, the epitaxial die of the present invention has the advantage of being repositionable through conventional chip die transfer processes such as pick-and-place and replace.

[0044] That is, the epitaxial die of the present invention can simultaneously satisfy both the advantage of a mini light-emitting diode (LED) manufacturing process, such as ease of defect classification, and low process and capital investment costs due to the use of existing general-purpose transfer equipment as is, and the advantage of a micro LED manufacturing process, such as a dramatic reduction in thickness and a reduction in chip die size by removing a support substrate, which is the final substrate, thereby improving light output.

[0045] Hereinafter, with reference to the accompanying drawings, an epitaxial die **100** for a semiconductor light-emitting device according to a first embodiment of the present invention will be described in detail.

[0046] FIG. **1** illustrates an overall view of the epitaxial die for a semiconductor light-emitting device according to the first embodiment of the present invention.

[0047] As shown in FIG. **1**, the epitaxial die **100** for a semiconductor light-emitting device according to the first embodiment of the present invention includes a light-emitting part **120**, a first ohmic electrode **130**, a passivation layer **150**, a contact electrode **160**, a bonding pad layer **170**, a temporary bonding layer **180**, and an intermediate temporary substrate **190**.

[0048] The light-emitting part **120** generates light, and in the present invention, in order to emit red light, binary, ternary, and quaternary compounds of Group III (Al, Ga, and In) phosphide semiconductors, such as indium phosphide (InP), indium gallium phosphide (InGaP), gallium phosphide (GaP), aluminum indium phosphide (AlInP), aluminum gallium phosphide (AlGaP), aluminum phosphide (AlP), and aluminum gallium indium phosphide (AlGaInP), are placed in appropriate positions and sequences on an initial growth substrate **110** and epitaxially grown (in the structure of the epitaxial die **100** of the present invention, the initial growth substrate **110** is separated after the intermediate temporary substrate **190** is bonded).

[0049] In particular, in order to emit red light, a Group III phosphide semiconductor with a high indium (In) composition, such as high-quality indium gallium phosphide (InGaP), should preferentially be formed on Group III phosphide semiconductors composed of gallium phosphide (GaP), aluminum indium phosphide (AlInP), aluminum gallium phosphide (AlGaP), aluminum phosphide (AlP), and aluminum gallium indium phosphide (AlGaInP), but the present invention is not limited thereto.

[0050] More specifically, the light-emitting part **120** includes a first semiconductor region **121** (e.g., a p-type semiconductor region), an active region **123** (e.g., multi-quantum wells (MQWs)), and a second semiconductor region **122** (e.g., an n-type semiconductor region), and the light-emitting part **120** may have a structure in which the second semiconductor region **122**, the active

region **123**, and the first semiconductor region **121** are epitaxially grown in this order on the initial growth substrate **110**, and ultimately, may have an overall thickness typically ranging from about 5.0 to 8.0 μm , including multiple layers of group III phosphides, but the present invention is not limited thereto.

[0051] Each of the first semiconductor region **121**, the active region **123**, and the second semiconductor region **122** may be formed as either a single layer or multiple layers, and although not shown in the drawing, necessary layers, such as buffer regions, may be added before epitaxially growing the light-emitting part **120** on the gallium arsenide (GaAs) initial growth substrate **110** to ensure the high quality of the epitaxially grown light-emitting part **120**. For example, the buffer regions may include a nucleation layer and a compliant layer composed of an un-doped semiconductor region to relieve stress and improve thin-film quality and typically have a thickness of about 4.0 μm . In addition, since the initial growth substrate **110** must be removed using a chemical lift-off (CLO) technique, it is preferable to grow an etching-stop layer (ESL) composed of gallium indium phosphide (GaInP) as a single-crystal thin film with a thickness of about 200 nm directly on the GaAs initial growth substrate **110** before the doped first semiconductor region **121** or second semiconductor region **122** is formed.

[0052] The second semiconductor region **122** has a second conductivity type (n-type), and is formed on the initial growth substrate **110**. The second semiconductor region **122** is primarily composed of gallium arsenide (GaAs) and aluminum gallium indium phosphide (AlGaInP) semiconductors, and may have a thickness ranging from 2.0 to 3.5 μm .

[0053] The active region **123** generates light, i.e., red light, by using the recombination of electrons and holes, and is formed on the second semiconductor region **122**. The active region **123** is composed of multiple layers of semiconductors, including primarily gallium indium phosphide (GaInP) and aluminum gallium indium phosphide (AlGaInP), and may have a thickness of several tens of nanometers (nm).

[0054] The first semiconductor region **121** has a first conductivity type (p-type), and is formed on the active region **123**. The first semiconductor region **121** is composed of multiple layers of semiconductors, including primarily aluminum indium phosphide (AlInP), aluminum gallium indium phosphide (AlGaInP), and gallium phosphide (GaP), and may have a thickness ranging from several tens of nanometers (nm) to several micrometers (μm).

[0055] That is, the active region **123** is interposed between the first semiconductor region **121** and the second semiconductor region **122**, and light is generated when holes in the first semiconductor region **121**, which is a p-type semiconductor region, and electrons in the second semiconductor region **122**, which is an n-type semiconductor region, recombine in the active region **123**.

[0056] Meanwhile, the light-emitting part **120**, which is epitaxially grown on the initial growth substrate **110** in the order of the second semiconductor region **122**, the active region **123**, and the first semiconductor region **121**, has a structure in which the first semiconductor region **121**, the active region **123**, and the second semiconductor region **122** are stacked in that order on the intermediate temporary substrate **190** when the first semiconductor region **121** is bonded to the intermediate temporary substrate **190**, which is made of sapphire, through the temporary bonding layer **180**.

[0057] At this time, both sides of the light-emitting part **120** formed on the initial growth substrate **110** may have a shape etched to a predetermined depth, and the predetermined depth may refer to a depth up to the second semiconductor region **122**, but the present invention is not limited thereto.

[0058] The first ohmic electrode **130** is electrically connected to the first semiconductor region **121** of the light-emitting part **120** and is formed on the first semiconductor region **121** so as to cover and come into surface contact with an upper surface of the first semiconductor region **121**. In this case, the first semiconductor region **121**, which is a p-type semiconductor region, is electrically connected to the first ohmic electrode **130** through a p-ohmic contact.

[0059] This first ohmic electrode **130** may be basically formed of a material with high transparency

and excellent electrical conductivity, but the present invention is not limited thereto. The first ohmic electrode **130** may be made of optically transparent materials such as indium tin oxide (ITO), zinc oxide (ZnO), indium zinc oxide (IZO), indium gallium zinc oxide (IGZO), titanium nitride (TiN), Ni(O)—Au, Ni(O)—AuBe, Ni(O)—Ag, and the like.

[0060] The passivation layer **150** covers the first ohmic electrode **130** from the etched portions on both sides of the light-emitting part **120**, and a portion of the first ohmic electrode **130** is exposed as a portion of the passivation layer **150** is etched and is opened.

[0061] The passivation layer **150** may be implemented with electrically insulating materials, and may include a single layer or multiple layers including at least one material from among silicon oxide, silicon nitride, metallic oxides including Al₂O₃, and organic insulators.

[0062] The contact electrode **160** is electrically connected to the first ohmic electrode **130** and is formed on the first ohmic electrode **130** exposed by opening a portion of the passivation layer **150**.

[0063] The materials of the contact electrode **160** are not limited as long as they have strong adhesion to the first ohmic electrode **130**, but may include Ti, TiN, Cr, CrN, V, VN, NiCr, Al, Rh, Pt, Ni, Pd, Ru, Cu, Ag, Au, AuBe, and the like.

[0064] The temporary bonding layer **180** bonds the passivation layer **150** formed as the contact electrode **160** is exposed to the intermediate temporary substrate **190**, and is formed above the passivation layer **150** and the contact electrode **160**. Due to the shape of the temporary bonding layer **180** that encloses the contact electrode **160**, the contact electrode **160** is interposed between the temporary bonding layer **180** and the first ohmic electrode **130** and thus is not exposed.

[0065] The temporary bonding layer **180** may include materials such as benzocyclobutene (BCB), SU-8 polymers, flowable oxides (FOx) such as spin-on-glass (SOG) and hydrogen silsesquioxane (HSQ), and alloys including low melting point metals (e.g., In, Sn, and Zn) and noble metals (e.g., Au, Ag, Cu, and Pd).

[0066] The intermediate temporary substrate **190** is bonded to the passivation layer **150** by the temporary bonding layer **180** to support the light-emitting part **120**, the first ohmic electrode **130**, the passivation layer **150**, the contact electrode **160**, and the bonding pad layer **170** to be described below, and it is preferable that the intermediate temporary substrate **190** is formed of a material that has a thermal expansion coefficient equal or similar to that of the initial growth substrate **110** and is simultaneously optically transparent, as long as the difference in thermal expansion coefficient does not exceed 2 ppm. The most preferable materials for the intermediate temporary substrate **190** that meet these criteria may include sapphire, or glass that has been adjusted to have a difference in thermal expansion coefficient of 2 ppm or less from the initial growth substrate **110**.

[0067] Meanwhile, in the present invention, the intermediate temporary substrate **190** functions as a final support substrate that supports the light-emitting part **120**, the first ohmic electrode **130**, the passivation layer **150**, the contact electrode **160**, and the bonding pad layer **170** to be described below after the epitaxial die **100** of the present invention is finally completed. At this time, it is preferable that an LLO sacrificial separation layer (not shown), which is a functional material that can be easily separated and removed by an LLO technique in the process of a third operation of a method (S10) of manufacturing the semiconductor light-emitting device, which will be described below, is formed between the intermediate temporary substrate **190** and the temporary bonding layer **180**. The above-described LLO sacrificial separation layer (not shown) may be made of materials such as ZnO, ITO, IZO, IGO, IGZO, InGaN, InGaON, GaON, TiN, SiO₂, SiN_x, and the like.

[0068] The bonding pad layer **170** functions as a vertical chip die bonding pad, and is formed to come into contact with a lower surface of the light-emitting part **120** to be electrically connected to the light-emitting part **120**. At this time, the bonding pad layer **170** is electrically connected to a lower surface of the second semiconductor region **122**, which is an n-type semiconductor region, through an n-ohmic contact, is exposed to the outside, and functions as a negative electrode while also serving as an active reflector.

[0069] It is preferable that the bonding pad layer **170** basically includes three regions (not shown). A first region may include transparent electrically conductive materials (i.e., ITO, IZO, ZnO, IGZO, TiN, and (O)-AuGe) with strong adhesion to the light-emitting part **120**. A second region may include highly reflective materials (i.e., Al, Ag, AgCu, Rh, Pt, Ni, and Pd). A third region may include low melting point metals and noble metals such as gold (Au), silver (Ag), copper (Cu), and palladium (Pd), but the present invention is not limited thereto. In addition, the low melting point metals of the bonding pad layer **170** may be formed of metals such as In, Sn, Zn, and Pb alone or an alloy including these metals.

[0070] Furthermore, although not shown in the drawing, before forming the bonding pad layer **170** on the lower surface of the light-emitting part **120**, a surface texture pattern with a predetermined shape or an irregular shape may be formed on the lower surface of the second semiconductor region **122** to extract as much light generated in the active region **123** into the air as possible.

[0071] Accordingly, in the epitaxial die **100** for a semiconductor light-emitting device according to the first embodiment of the present invention, the contact electrode **160** serving as a positive electrode and the first ohmic electrode **130** are interposed between the temporary bonding layer **180** and the light-emitting part **120** and thus are not exposed, and only the bonding pad layer **170** functioning as a negative electrode is exposed to the outside.

[0072] Hereinafter, with reference to the accompanying drawings, a semiconductor light-emitting device **10** according to the first embodiment of the present invention will be described in detail.

[0073] The semiconductor light-emitting device **10** of the present invention may be formed as a chip-on-board (COB) in which individual chips or epitaxial die units are directly transferred and connected to a substrate (such as a semiconductor wafer, printed circuit board (PCB), or thin-film transistor (TFT) glass) on which circuit wiring and driving element regions are completed, a package-on-board (POB) in which package units (including 1, 2, 4, 9, 16, . . . , and n^2 chips or epitaxial die units) manufactured using a fan-out package process known in conventional memory semiconductor technology are directly transferred and connected to a substrate on which circuit wiring and driving element regions (such as a semiconductor wafer, a PCB, or TFT glass) are completed, or an interposer using the intermediate temporary substrate **190** on which circuit wiring and driving element regions are not completed, but is not limited thereto, and will be described herein as being formed as the COB type for convenience of description.

[0074] FIG. 2 illustrates an overall view of the semiconductor light-emitting device according to the first embodiment of the present invention.

[0075] As shown in FIG. 2, the semiconductor light-emitting device **10** according to the first embodiment of the present invention includes a substrate part **11**, the epitaxial die **100**, a bonding layer **12**, an extension electrode **13**, a mold part **14**, and a black matrix **15**.

[0076] The substrate part **11** supports the epitaxial die **100** that is bonded thereto, and a first electrode pad **11a** and a second electrode pad **11b** are each formed on an upper surface of the substrate part **11**. The substrate part **11** may refer to a semiconductor wafer, a PCB, TFT glass, an interposer, or the like, but the present invention is not limited thereto.

[0077] Further, the first electrode pad **11a** may refer to an individual negative electrode, and the second electrode pad **11b** may refer to a common positive electrode. For example, after three epitaxial dies emitting blue, green, and red light are respectively placed on three individual negative electrodes and bonded to form a single pixel, each of the epitaxial dies may be electrically connected the common positive electrode.

[0078] The epitaxial die **100** is placed on the first electrode pad **11a** of the substrate part **11** such that a bonding pad layer **170** comes into contact with the first electrode pad **11a**, and includes a light-emitting part **120**, a first ohmic electrode **130**, a passivation layer **150**, a contact electrode **160**, and a bonding pad layer **170**.

[0079] Here, the light-emitting part **120** configured to generate red light, the first ohmic electrode **130**, the passivation layer **150**, the contact electrode **160**, and the bonding pad layer **170** are the

same as those of the above-described epitaxial die **100** for a semiconductor light-emitting device according to the first embodiment of the present invention, and thus redundant descriptions will be omitted.

[0080] Meanwhile, after the intermediate temporary substrate **190** is separated, the temporary bonding layer **180** is etched and removed, thereby exposing the contact electrode **160**.

[0081] The bonding layer **12** electrically connects the first electrode pad **11a** of the substrate part **11** and the bonding pad layer **170** of the epitaxial die **100** by bonding them together, and may include low melting point metals and noble metals such as gold (Au), silver (Ag), copper (Cu), and palladium (Pd) similar to or the same as the bonding pad layer **170** of the epitaxial die **100**, but the present invention is not limited thereto.

[0082] The extension electrode **13** electrically connects the second electrode pad **11b** of the substrate part **11** to the contact electrode **160** of the epitaxial die **100**, and is formed to extend vertically from an upper portion of the second electrode pad **11b** to above the mold part **14** through a through hole H of the mold part **14**, which will be described below, and then extend horizontally by being bent toward the contact electrode **160** to come into contact with and be electrically connected to the contact electrode **160**.

[0083] The extension electrode **13** may be formed of optically transparent and electrically conductive ceramics such as ITO, TiN, carbon nanotubes (CNT), and silver nanowires (Ag nanowires), or low melting point metals and noble metals such as gold (Au), silver (Ag), copper (Cu), and palladium (Pd) similar to or the same as the above-described materials of the bonding layer **12**, but the present invention is not limited thereto.

[0084] The mold part **14** surrounds and supports the epitaxial die **100** and the extension electrode **13**, which are disposed to form a vertical structure, and is formed so that an upper surface of the extension electrode **13** is exposed. In the mold part **14**, the through hole H is formed above the second electrode pad **11b**, and the extension electrode **13** is electrically connected to the second electrode pad **11b** and the contact electrode **160** through the through hole H.

[0085] Meanwhile, laser drilling may be used to form the through hole H, and in this case, the mold part **14** may be made of materials that enable laser direct structuring (LDS) or laser direct imaging (LDI).

[0086] The black matrix (BM) **15** covers the exposed upper surfaces of the extension electrode **13** and the mold part **14**, and may be formed using photolithography and spin coating processes, but the present invention is not limited thereto.

[0087] In addition, the black matrix **15** may be formed of a metal thin film or carbon-based organic material with an optical density of 3.5 or higher, but the present invention is not limited thereto. More specifically, representative examples thereof include a chromium (Cr) monolayer film, a chromium (Cr)/chromium oxide (CrOx) bilayer film, manganese dioxide (MnO₂), an organic black matrix, graphite, and a pigment dispersion composition (prepared by blending a high molecular weight block copolymer resin with pigment-affinity groups such as amino, hydroxyl, and carboxyl groups, with carbon black as a medium, and mixing the blend with a solvent and a dispersing agent).

[0088] Hereinafter, with reference to the accompanying drawings, a method (S**100**) of manufacturing the epitaxial die for a semiconductor light-emitting device according to the first embodiment of the present invention will be described in detail.

[0089] FIG. **3** is a flowchart of the method of manufacturing the epitaxial die for a semiconductor light-emitting device according to the first embodiment of the present invention, and FIG. **4** illustrates a process of manufacturing the epitaxial die for a semiconductor light-emitting device according to the first embodiment of the present invention.

[0090] As shown in FIGS. **3** and **4**, the method (S**100**) of manufacturing the epitaxial die for a semiconductor light-emitting device according to the first embodiment of the present invention includes a first operation S**110**, a second operation S**120**, a third operation S**130**, a fourth operation

S140, a fifth operation **S150**, a sixth operation **S160**, a seventh operation **S170**, and an eighth operation **S180**. However, it is of course possible that the order of the processes shown in FIGS. 3 and 4 can be changed.

[0091] The first operation **S110** is an operation of preparing an initial growth substrate **110** and an intermediate temporary substrate **190**. The initial growth substrate **110** is a substrate on which a light-emitting part **120** to be described below is epitaxially grown, and the initial growth substrate **110** made of gallium arsenide (GaAs) may be used.

[0092] The intermediate temporary substrate **190** is bonded to a passivation layer **150** by a temporary bonding layer **180**, which will be described below, and supports the light-emitting part **120**, a first ohmic electrode **130**, the passivation layer **150**, a contact electrode **160**, and a bonding pad layer **170**, and may include sapphire, or glass that has been adjusted to have a difference in thermal expansion coefficient of 2 ppm or less from the initial growth substrate **110**.

[0093] Meanwhile, in the present invention, after the epitaxial die **100** of the present invention is finally completed, the intermediate temporary substrate **190** functions as a final support substrate that supports the light-emitting part **120**, the first ohmic electrode **130**, the passivation layer **150**, the contact electrode **160**, and the bonding pad layer **170**.

[0094] The second operation **S120** is an operation of forming the light-emitting part **120**, which generates red light, on the initial growth substrate **110**. That is, more specifically, the light-emitting part **120** includes a first semiconductor region **121** (e.g., a p-type semiconductor region), an active region **123** (e.g., MQWs), and a second semiconductor region **122** (e.g., an n-type semiconductor region), and in the second operation **S120**, the second semiconductor region **122**, the active region **123**, and the first semiconductor region **121** are epitaxially grown in this order on the initial growth substrate **110**.

[0095] The third operation **S130** is an operation of forming the first ohmic electrode **130** that is electrically connected to the first semiconductor region **121** by covering so as to come into surface contact with an upper surface of the first semiconductor region **121** of the light-emitting part **120**. At this time, heat treatment is selectively performed at a high temperature of 300° C. or higher so that the first semiconductor region **121** forms a p-ohmic contact with the first ohmic electrode **130**.

[0096] The fourth operation **S140** is an operation of etching both sides of each of the light-emitting part **120** and the first ohmic electrode **130** to a predetermined depth and forming the passivation layer **150**, which covers the first ohmic electrode **130** from the etched portions on both sides of the light-emitting part **120**.

[0097] The fifth operation **S150** is an operation of etching a portion of the passivation layer **150** to expose the first ohmic electrode **130** and forming the contact electrode **160** to come into contact with the exposed first ohmic electrode **130**.

[0098] The sixth operation **S160** is an operation of bonding the intermediate temporary substrate **190** and the passivation layer **150** in which the contact electrode **160** is exposed, through the temporary bonding layer **180**. Due to the shape of the temporary bonding layer **180** that encloses the contact electrode **160**, the contact electrode **160** is interposed between the temporary bonding layer **180** and the first ohmic electrode **130** and thus is not exposed.

[0099] The seventh operation **S170** is an operation of removing the initial growth substrate **110**. At this time, in the seventh operation **S170**, the growth substrate **110** may be separated from the light-emitting part **120**, i.e., the second semiconductor region **122**, using a CLO technique, thereby exposing an upper surface of the second semiconductor region **122**. Here, the CLO technique refers to a technique of separating the light-emitting part **120** by completely etching the GaAs initial growth substrate **110** using an etching solution (NH₄OH:H₂O₂) so that the above-described GaInP ESL is exposed.

[0100] The eighth operation **S180** is an operation of forming the bonding pad layer **170** that is formed to come into contact with a lower surface of the light-emitting part **120** to be electrically connected to the light-emitting part **120**, and functions as a vertical chip bonding pad. At this time,

the bonding pad layer **170** is electrically connected to the lower surface of the light-emitting part through an n-ohmic contact and is exposed to the outside, thereby functioning as a negative electrode. Meanwhile, in the eighth operation **S180**, the bonding pad layer **170** needs to be heat treated at a high temperature of 300° C. or higher to form an n-ohmic contact with the lower surface of the light-emitting part **120**.

[0101] After the basic structure of the epitaxial die **100** is formed through the above-described first operation **S110** to eighth operation **S180**, processes such as grinding, dicing, probing, and sorting are performed.

[0102] Hereinafter, with reference to the accompanying drawings, a method (**S10**) of manufacturing the semiconductor light-emitting device according to the first embodiment of the present invention will be described in detail.

[0103] The semiconductor light-emitting device **10** of the present invention may be formed as a COB in which individual chips or epitaxial die units are directly transferred and connected to a substrate (such as a semiconductor wafer, a PCB, or TFT glass) on which circuit wiring and driving element regions are completed, a POB in which package units (including 1, 2, 4, 9, 46, . . . , and n^2 chips or epitaxial die units) manufactured using a fan-out package process known in conventional memory semiconductor technology are directly transferred and connected to a substrate on which circuit wiring and driving element regions (such as a semiconductor wafer, a PCB, or TFT glass) are completed, or an interposer using the temporary substrate **190** on which circuit wiring and driving element regions are not completed, but is not limited thereto, and will be described herein as being formed as the COB type for convenience of description.

[0104] FIG. **5** is a flowchart of the method of manufacturing the semiconductor light-emitting device according to the first embodiment of the present invention, and FIG. **6** illustrates a process of manufacturing the semiconductor light-emitting device according to the first embodiment of the present invention.

[0105] As shown in FIGS. **5** and **6**, the method (**S10**) of manufacturing the semiconductor light-emitting device according to the first embodiment of the present invention includes a first operation **S11**, a second operation **S12**, a third operation **S13**, a fourth operation **S14**, a fifth operation **S15**, a sixth operation **S16**, and a seventh operation **S17**. However, it is of course possible that the order of the processes shown in FIGS. **5** and **6** can be changed.

[0106] The first operation **S11** is an operation of preparing the epitaxial die **100** for a semiconductor light-emitting device according to the first embodiment of the present invention and a substrate part **11** on which a first electrode pad **11a** and a second electrode pad **11b** are each formed. The substrate part **11** may refer to a semiconductor wafer, a PCB, TFT glass, an interposer, or the like, but the present invention is not limited thereto.

[0107] The second operation **S12** is an operation of placing the epitaxial die **100** on the first electrode pad **11a**, which is an individual negative electrode, and electrically connecting the first electrode pad **11a** and the bonding pad layer **170** by bonding them through a bonding layer **12**. At this time, the placement and bonding of the epitaxial die **100** can be accomplished through typical chip die transfer processes such as pick-and-place, roll to roll (R2R), and stamps (made from materials such as polydimethylsiloxane (PDMS), silicon (Si), quartz, and glass), which are commonly known tools used in representative processes of massive transfer.

[0108] Meanwhile, when it is necessary to achieve objectives such as (1) high precision placement of an epitaxial die **100**, (2) an epitaxial die **100** with a ultra-small size of less than 50 μm ×50 μm , and (3) an epitaxial die **100** having a self-assembly structure, additional masking media (such as a photoresist, ceramics (like glass, quartz, and alumina), or an invar fine metal mask (FMM) or processes may be employed before the placement and bonding of the epitaxial die **100**.

[0109] The third operation **S13** is an operation of separating the intermediate temporary substrate **190** of the epitaxial die **100** and etching the temporary bonding layer **180** to expose the contact electrode **160**. At this time, in the third operation **S13**, the intermediate temporary substrate **190**

may be separated from the temporary bonding layer **180** using an LLO technique. Here, the LLO technique refers to a technique of separating the intermediate temporary substrate **190** from the temporary bonding layer **180** by irradiating a rear surface of the transparent intermediate temporary substrate **190** with a UV laser beam having a uniform output and beam profile, and a single wavelength.

[0110] The fourth operation **S14** is an operation of forming a mold part **14** surrounding the epitaxial die **100** so that the contact electrode **160** is exposed. At this time, the mold part **14** may be made of materials that enable LDS or LDI to allow laser drilling in the fifth operation **S15** to be described below.

[0111] The fifth operation **S15** is an operation of etching the mold part **14** to expose the second electrode pad **11b**. That is, in the fifth operation **S15**, a through hole **H** is formed above the second electrode pad **11b** by etching the mold part **14** above the second electrode pad **11b** using laser drilling.

[0112] The sixth operation **S16** is an operation of forming an extension electrode **13** that electrically connects the second electrode pad **11b** and the exposed contact electrode **160**. That is, the extension electrode **13** is formed to extend vertically from an upper portion of the second electrode pad **11b** to above the mold part **14** through the through hole **H**, and then extend horizontally by being bent toward the contact electrode **160** to come into contact with and be electrically connected to the contact electrode **160**.

[0113] The seventh operation **S17** is an operation of forming a black matrix **15** that covers the extension electrode **13** and the mold part **14**. The black matrix **15** may be formed using photolithography and spin coating processes, but the present invention is not limited thereto.

[0114] Hereinafter, with reference to the accompanying drawings, an epitaxial die **200** for a semiconductor light-emitting device according to a second embodiment of the present invention will be described in detail.

[0115] FIG. **7** illustrates an overall view of the epitaxial die for a semiconductor light-emitting device according to the second embodiment of the present invention.

[0116] As shown in FIG. **7**, the epitaxial die **200** for a semiconductor light-emitting device according to the second embodiment of the present invention includes a light-emitting part **220**, a first ohmic electrode **230**, a passivation layer **250**, a contact electrode **260**, a bonding pad layer **270**, a temporary bonding layer **280**, and an intermediate temporary substrate **290**.

[0117] Here, the temporary bonding layer **280** includes a first temporary bonding layer **281** and a second temporary bonding layer **282**, and the intermediate temporary substrate **290** includes a first intermediate temporary substrate **291** and a second intermediate temporary substrate **292**.

[0118] The light-emitting part **220** generates light, and in the present invention, in order to emit red light, binary, ternary, and quaternary compounds of Group III (Al, Ga, and In) phosphide semiconductors, such as indium phosphide (InP), indium gallium phosphide (InGaP), gallium phosphide (GaP), aluminum indium phosphide (AlInP), aluminum gallium phosphide (AlGaP), aluminum phosphide (AlP), and aluminum gallium indium phosphide (AlGaInP), are placed in appropriate positions and sequences on an initial growth substrate **210** and epitaxially grown (in the structure of the epitaxial die **200** of the present invention, the initial growth substrate **210** is first separated after bonding to the first intermediate temporary substrate **291**, and then the second intermediate temporary substrate **292** is bonded and the first intermediate temporary substrate **291** is separated).

[0119] In particular, in order to emit red light, a high-quality Group III phosphide semiconductor with a high indium (In) composition, such as indium gallium phosphide (InGaP), should preferably be formed on Group III phosphide semiconductors composed of gallium phosphide (GaP), aluminum indium phosphide (AlInP), aluminum gallium phosphide (AlGaP), aluminum phosphide (AlP), and aluminum gallium indium phosphide (AlGaInP), but the present invention is not limited thereto.

[0120] More specifically, the light-emitting part **220** includes a first semiconductor region **221** (e.g., a p-type semiconductor region), an active region **223** (e.g., MQWs), and a second semiconductor region **222** (e.g., an n-type semiconductor region), and the light-emitting part **220** may have a structure in which the second semiconductor region **222**, the active region **223**, and the first semiconductor region **221** are epitaxially grown in this order on the initial growth substrate **210**, and ultimately, may have an overall thickness typically ranging from about 5.0 to 8.0 μm , including multiple layers of group III phosphides, but the present invention is not limited thereto.

[0121] Each of the first semiconductor region **221**, the active region **223**, and the second semiconductor region **222** may be formed as either a single layer or multiple layers, and although not shown in the drawing, necessary layers such as buffer regions may be added before epitaxially growing the light-emitting part **220** on the gallium arsenide (GaAs) initial growth substrate **210** to ensure the high quality of the epitaxially grown light-emitting part **220**. For example, the buffer regions may include a nucleation layer and a compliant layer composed of an un-doped semiconductor region to relieve stress and improve thin-film quality and typically have a thickness of about 4.0 μm . In addition, since the initial growth substrate **210** must be removed using a CLO technique, it is preferable to grow an ESL composed of gallium indium phosphide (GaInP) as a single-crystal thin film with a thickness of about 200 nm directly on the GaAs initial growth substrate **210** before the doped first semiconductor region **221** or second semiconductor region **222** is formed.

[0122] The second semiconductor region **222** has a second conductivity type (n-type), and is formed on the initial growth substrate **210**. The second semiconductor region **222** is primarily composed of gallium arsenide (GaAs) and aluminum gallium indium phosphide (AlGaInP) semiconductors, and may have a thickness ranging from 2.0 to 3.5 μm .

[0123] The active region **223** generates light, i.e., red light, by using the recombination of electrons and holes, and is formed on the second semiconductor region **222**. The active region **223** is composed of multiple layers of semiconductors, including primarily gallium indium phosphide (GaInP) and aluminum gallium indium phosphide (AlGaInP), and may have a thickness of several tens of nanometers (nm).

[0124] The first semiconductor region **221** has a first conductivity type (p-type), and is formed on the active region **223**. The first semiconductor region **221** is composed of multiple layers of semiconductors, including primarily aluminum indium phosphide (AlInP), aluminum gallium indium phosphide (AlGaInP), and gallium phosphide (GaP), and may have a thickness ranging from several tens of nanometers (nm) to several micrometers (μm).

[0125] That is, the active region **223** is interposed between the first semiconductor region **221** and the second semiconductor region **222**, and generates light when holes in the first semiconductor region **221**, which is a p-type semiconductor region, and electrons in the second semiconductor region **222**, which is an n-type semiconductor region, recombine in the active region **223**.

[0126] Meanwhile, the light-emitting part **220**, which is epitaxially grown on the initial growth substrate **210** in the order of the second semiconductor region **222**, the active region **223**, and the first semiconductor region **221** is implemented by a process in which the first intermediate temporary substrate **291**, which is made of sapphire, is bonded to the first semiconductor region **221** through the first temporary bonding layer **281**, and the initial growth substrate **210** is separated, and then, the second intermediate temporary substrate **292**, which is also made of sapphire, is bonded to a lower surface of the second semiconductor region **222** through the second temporary bonding layer **282**, resulting in a structure in which the second semiconductor region **222**, the active region **223**, and the first semiconductor region **221** are stacked in this order on the second intermediate temporary substrate **292**.

[0127] At this time, both sides of the light-emitting part **220** formed on the initial growth substrate **210** may have a shape etched to a predetermined depth, and the predetermined depth may refer to a depth up to the second semiconductor region **222**, but the present invention is not limited thereto.

[0128] The first ohmic electrode **230** is electrically connected to the first semiconductor region **221** of the light-emitting part **220** and is formed on the first semiconductor region **221** so as to cover and come into surface contact with an upper surface of the first semiconductor region **221**. At this time, the first semiconductor region **221**, which is a p-type semiconductor region, is electrically connected to the first ohmic electrode **230** through a p-ohmic contact.

[0129] Although the first ohmic electrode **230** may be basically formed solely of a material with high reflectance and excellent electrical conductivity, the first ohmic electrode **230** may also be formed in combination with a material that has high transparency, but the present invention is not limited thereto. The materials for the first ohmic electrode **230** with high reflectance described above may include metals such as Ag, Al, Rh, Pt, Ni, Pd, Ru, Cu, Au, AuBe, AgBe, and AlBe, and the materials for the first ohmic electrode **230** with high transparency described above may include indium tin oxide (ITO), zinc oxide (ZnO), indium zinc oxide (IZO), indium gallium zinc oxide (IGZO), titanium nitride (TiN), Ni(O)—Au, Ni(O)—AuBe, Ni(O)—Ag, and the like.

[0130] The passivation layer **250** covers the first ohmic electrode **230** from the etched portions on both sides of the light-emitting part **220**, and a portion of the first ohmic electrode **230** is exposed as a portion of the passivation layer **250** is etched and is opened.

[0131] The passivation layer **250** may be implemented with electrically insulating materials, and may include a single layer or multiple layers including at least one material from among silicon oxide, silicon nitride, metallic oxides including Al₂O₃, and organic insulators.

[0132] The bonding pad layer **270** functions as a vertical chip die bonding pad and is formed on the first ohmic electrode **230**, which is exposed by the partial opening of the passivation layer **250**. The bonding pad layer **270** is electrically connected to the first ohmic electrode **230**, is exposed to the outside, and functions as a positive electrode.

[0133] The bonding pad layer **270** may basically include low melting point metals and noble metals such as gold (Au), silver (Ag), copper (Cu), and palladium (Pd), but the present invention is not limited thereto. In addition, the above-described low melting point metals may be formed of metals such as In, Sn, Zn, and Pb alone or an alloy including these metals.

[0134] The contact electrode **260** is formed to come into contact with a lower surface of the light-emitting part **220** to be electrically connected to the light-emitting part **220**, and in this case, the contact electrode **260** is electrically connected to a lower surface of the second semiconductor region **222**, which is an n-type semiconductor region, through an n-ohmic contact, and functions as a negative electrode.

[0135] The materials for the contact electrode **260** are not limited as long as they are compatible with the lower surface of the second semiconductor region **222**, which is an n-type semiconductor region, and may include Ti, TiN, Cr, CrN, V, VN, NiCr, Al, Rh, Pt, Ni, Pd, Ru, Cu, Ag, Au, NiO, AuGe, and the like.

[0136] Meanwhile, although not shown in the drawing, before bonding the intermediate temporary substrate **290** on the lower surface of the light-emitting part **220**, a surface texture pattern with a predetermined shape or an irregular shape may be formed on the lower surface of the second semiconductor region **222** to extract as much light generated in the active region **223** into the air as possible.

[0137] The temporary bonding layer **280** (i.e., the second temporary bonding layer **282**) bonds the lower surface of the light-emitting part **220**, on which the contact electrode **260** is formed, and the intermediate temporary substrate **290** to each other, and is formed on the lower surface of the light-emitting part **220** to cover the contact electrode **260**. Due to the shape of the temporary bonding layer **280** that encloses the contact electrode **260**, the contact electrode **260** is interposed between the temporary bonding layer **280** and the light-emitting part **220** and thus is not exposed.

[0138] The temporary bonding layer **280** may include materials such as benzocyclobutene (BCB), SU-8 polymers, flowable oxides (FOx) such as spin-on-glass (SOG) and hydrogen silsesquioxane (HSQ), and alloys including low melting point metals (e.g., In, Sn, and Zn) and noble metals (e.g.,

Au, Ag, Cu, and Pd).

[0139] The intermediate temporary substrate **290** (i.e., the second intermediate temporary substrate **292**) is bonded to the passivation layer **250** by the temporary bonding layer **280** to support the light-emitting part **220**, the first ohmic electrode **230**, the passivation layer **250**, the contact electrode **260**, and the bonding pad layer **270**, and it is preferable that the intermediate temporary substrate **290** is formed of a material that has a thermal expansion coefficient equal or similar to that of the initial growth substrate **210** and is simultaneously optically transparent, as long as the difference in thermal expansion coefficient does not exceed 2 ppm. The most preferable materials for the intermediate temporary substrate **290** that meet these criteria may include sapphire, or glass that has been adjusted to have a difference in thermal expansion coefficient of 2 ppm or less from the initial growth substrate **210**.

[0140] Meanwhile, in the present invention, the second intermediate temporary substrate **292** functions as a final support substrate that supports the light-emitting part **220**, the first ohmic electrode **230**, the passivation layer **250**, the contact electrode **260**, and the bonding pad layer **270** after the epitaxial die **200** of the present invention is finally completed. At this time, it is preferable that an LLO sacrificial separation layer (not shown), which is a functional material that can be easily separated and removed by an LLO technique in the process of a third operation of a method (S20) of manufacturing the semiconductor light-emitting device, which will be described below, is formed between the intermediate temporary substrate **290** and the temporary bonding layer **280**. The above-described LLO sacrificial separation layer (not shown) may be made of materials such as ZnO, ITO, IZO, IGO, IGZO, InGaN, InGaON, GaON, TiN, SiO₂, SiN_x, and the like.

[0141] Accordingly, the epitaxial die **200** for a semiconductor light-emitting device according to the second embodiment of the present invention has a form in which the contact electrode **260**, which is a negative electrode, is interposed between the temporary bonding layer **280** and the light-emitting part **220** and thus is not exposed, and only the bonding pad layer **270**, which functions as a positive electrode, is exposed to the outside.

[0142] Hereinafter, with reference to the accompanying drawings, a semiconductor light-emitting device **20** according to the second embodiment of the present invention will be described in detail.

[0143] The semiconductor light-emitting device **20** of the present invention may be formed as a COB in which individual chips or epitaxial die units are directly transferred and connected to a substrate (such as a semiconductor wafer, a PCB, or TFT glass) on which circuit wiring and driving element regions are completed, a POB in which package units (including 1, 2, 2, 9, 26, . . . , and n² chips or epitaxial die units) manufactured using a fan-out package process known in conventional memory semiconductor technology are directly transferred and connected to a substrate on which circuit wiring and driving element regions (such as a semiconductor wafer, a PCB, or TFT glass) are completed, or an interposer using the intermediate temporary substrate **290** on which circuit wiring and driving element regions are not completed, but is not limited thereto, and will be described herein as being formed as the COB type for convenience of description.

[0144] FIG. **8** illustrates an overall view of the semiconductor light-emitting device according to the second embodiment of the present invention.

[0145] As shown in FIG. **8**, the semiconductor light-emitting device **20** according to the second embodiment of the present invention includes a substrate part **21**, the epitaxial die **200**, a bonding layer **22**, an extension electrode **23**, a mold part **24**, and a black matrix **25**.

[0146] The substrate part **21** supports the epitaxial die **200** that is bonded thereto, and a first electrode pad **21a** and a second electrode pad **21b** are each formed on an upper surface of the substrate part **21**. The substrate part **21** may refer to a semiconductor wafer, a PCB, TFT glass, an interposer, or the like, but the present invention is not limited thereto.

[0147] Further, the first electrode pad **21a** may refer to an individual positive electrode, and the second electrode pad **21b** may refer to a common negative electrode. For example, after three epitaxial dies emitting blue, green, and red light are respectively placed on three individual positive

electrodes and bonded to form a single pixel, each of the epitaxial dies may be electrically connected to the common negative electrode.

[0148] The epitaxial die **200** is placed upside down on the first electrode pad **21a** of the substrate part **21** such that the bonding pad layer **270** comes into contact with the first electrode pad **21a**, and includes a light-emitting part **220**, a first ohmic electrode **230**, a passivation layer **250**, a contact electrode **260**, and a bonding pad layer **270**.

[0149] Here, the light-emitting part **220** configured to generate red light, the first ohmic electrode **230**, the passivation layer **250**, the contact electrode **260**, and the bonding pad layer **270** are the same as those of the above-described epitaxial die **200** for a semiconductor light-emitting device according to the second embodiment of the present invention, and thus redundant descriptions will be omitted.

[0150] Meanwhile, in the light-emitting part **220**, after the intermediate temporary substrate **290** is separated, the temporary bonding layer **280** is etched and removed, thereby exposing the contact electrode **260**.

[0151] Meanwhile, in the upside-down epitaxial die **200**, a surface texture pattern of a predetermined shape or an irregular shape may be formed on an upper surface of the light-emitting part **220**, i.e., an upper surface of the second semiconductor region **222**, in order to extract as much light generated in the active region **223** into the air as possible.

[0152] The bonding layer **22** electrically connects the first electrode pad **21a** of the substrate part **21** and the bonding pad layer **270** of the epitaxial die **200** by bonding them together, and may include low melting point metals and noble metals such as gold (Au), silver (Ag), copper (Cu), and palladium (Pd) similar to or the same as the bonding pad layer **270** of the epitaxial die **200**, but the present invention is not limited thereto.

[0153] The extension electrode **23** electrically connects the second electrode pad **21b** of the substrate part **21** to the contact electrode **260** of the epitaxial die **200**, and is formed to extend vertically from an upper portion of the second electrode pad **21b** to above the mold part **24** through a through hole H of the mold part **24**, which will be described below, and then extend horizontally by being bent toward the contact electrode **260** to come into contact with and be electrically connected to the contact electrode **260**.

[0154] The extension electrode **23** may be formed of optically transparent and electrically conductive ceramics such as ITO, TiN, carbon nanotubes (CNT), and silver nanowires (Ag nanowires), or low melting point metals and noble metals such as gold (Au), silver (Ag), copper (Cu), and palladium (Pd) similar to or the same as the above-described materials of the bonding layer **22**, but the present invention is not limited thereto.

[0155] The mold part **24** surrounds and supports the epitaxial die **200** and the extension electrode **23**, which are disposed to form a vertical structure, and is formed so that an upper surface of the extension electrode **23** is exposed. In the mold part **24**, the through hole H is formed above the second electrode pad **21b**, and the extension electrode **23** is electrically connected to the second electrode pad **21b** and the contact electrode **260** through the through hole H.

[0156] Meanwhile, laser drilling may be used to form the through hole H, and in this case, the mold part **24** may be made of materials that enable LDS or LDI.

[0157] The black matrix (BM) **25** covers the exposed upper surfaces of the extension electrode **23** and the mold part **24**, and may be formed using photolithography and spin coating processes, but the present invention is not limited thereto.

[0158] In addition, the black matrix **25** may be formed of a metal thin film or carbon-based organic material with an optical density of 3.5 or higher, but the present invention is not limited thereto. More specifically, representative examples thereof include a chromium (Cr) monolayer film, a chromium (Cr)/chromium oxide (CrOx) bilayer film, manganese dioxide (MnO₂), an organic black matrix, graphite, and a pigment dispersion composition (prepared by blending a high molecular weight block copolymer resin with pigment-affinity groups such as amino, hydroxyl, and carboxyl

groups, with carbon black as a medium, and mixing the blend with a solvent and a dispersing agent).

[0159] Hereinafter, with reference to the accompanying drawings, a method (S200) of manufacturing the epitaxial die for a semiconductor light-emitting device according to the second embodiment of the present invention will be described in detail.

[0160] FIG. 9 is a flowchart of the method of manufacturing the epitaxial die for a semiconductor light-emitting device according to the second embodiment of the present invention, and FIG. 10 illustrates a process of manufacturing the epitaxial die for a semiconductor light-emitting device according to the second embodiment of the present invention.

[0161] As shown in FIGS. 9 and 10, the method (S200) of manufacturing the epitaxial die for a semiconductor light-emitting device according to the second embodiment of the present invention includes a first operation S210, a second operation S220, a third operation S230, a fourth operation S240, a fifth operation S250, a sixth operation S260, a seventh operation S270, an eighth operation S280, and a ninth operation S290. However, it is of course possible that the order of the processes shown in FIGS. 9 and 10 can be changed.

[0162] The first operation S210 is an operation of preparing an initial growth substrate 210, a first intermediate temporary substrate 291, and a second intermediate temporary substrate 292. The initial growth substrate 210 is a substrate on which a light-emitting part 220 to be described below is epitaxially grown, and the initial growth substrate 210 made of gallium arsenide (GaAs) may be used.

[0163] The first intermediate temporary substrate 291 and the second intermediate temporary substrate 292 are respectively bonded to lower surfaces of a passivation layer 250 and the light-emitting part 220 by a first temporary bonding layer 281 and a second temporary bonding layer 282, which will be described below, and the second intermediate temporary substrate 292 supports the light-emitting part 220, a first ohmic electrode 230, a passivation layer 250, a contact electrode 260, and a bonding pad layer 270, and may include sapphire, or glass adjusted to have a difference in thermal expansion coefficient of 2 ppm or less from the initial growth substrate 210.

[0164] Meanwhile, in the present invention, after the epitaxial die 200 of the present invention is finally completed, the second intermediate temporary substrate 292 functions as a final support substrate that supports the light-emitting part 220, the first ohmic electrode 230, the passivation layer 250, the contact electrode 260, and the bonding pad layer 270.

[0165] The second operation S220 is an operation of forming the light-emitting part 220, which generates red light, on the initial growth substrate 210, and forming the first ohmic electrode 230 that is electrically connected to a first semiconductor region 221 by covering so as to come into surface contact with an upper surface of the first semiconductor region 221 of the light-emitting part 220.

[0166] That is, more specifically, the light-emitting part 220 includes the first semiconductor region 221 (e.g., a p-type semiconductor region), an active region 223 (e.g., MQWs), and a second semiconductor region 222 (e.g., an n-type semiconductor region), and in the second operation S220, the second semiconductor region 222, the active region 223, and the first semiconductor region 221 are epitaxially grown in this order on the initial growth substrate 210.

[0167] Further, in the second operation S220, heat treatment is selectively performed at a high temperature of 300° C. or higher so that the first semiconductor region 221 forms a p-ohmic contact with the first ohmic electrode 230.

[0168] The third operation S230 is an operation of etching both sides of each of the light-emitting part 220 and the first ohmic electrode 230 to a predetermined depth and forming the passivation layer 250, which covers the first ohmic electrode 230 from the etched portions on both sides of the light-emitting part 220.

[0169] The fourth operation S240 is an operation of etching a portion of the passivation layer 250 to expose the first ohmic electrode 230 and forming the bonding pad layer 270, which functions as

a vertical chip bonding pad, to come into contact with the exposed first ohmic electrode **230**.

[0170] The fifth operation **S250** is an operation of bonding the first intermediate temporary substrate **291** and the passivation layer **250**, in which the bonding pad layer **270** is exposed, through the first temporary bonding layer **281**.

[0171] The sixth operation **S260** is an operation of removing the initial growth substrate **210**. At this time, in the sixth operation **S260**, the initial growth substrate **210** may be separated from the light-emitting part **220**, i.e., the second semiconductor region **222**, using a CLO technique, thereby exposing an upper surface of the second semiconductor region **222**. Here, the CLO technique refers to a technique of separating the light-emitting part **220** by completely etching the GaAs initial growth substrate **210** using an etching solution (NH₄OH:H₂O₂) so that the above-described GaInP ESL is exposed.

[0172] The seventh operation **S270** is an operation of forming the contact electrode **260** that is formed to come into contact with a lower surface of the light-emitting part **220** to be electrically connected to the light-emitting part **220**. In this case, the contact electrode **260** is electrically connected to the lower surface of the second semiconductor region **222**, which is an n-type type semiconductor region, through an n-ohmic contact and functions as a negative electrode.

Meanwhile, in the seventh operation **S270**, the contact electrode **260** needs to be heat treated at a high temperature of 300° C. or higher to form an n-ohmic contact with the lower surface of the light-emitting part **220**.

[0173] The eighth operation **S280** is an operation of bonding the second intermediate temporary substrate **292** to the lower surface of the light-emitting part **220**, in which the contact electrode **260** is exposed, through the second temporary bonding layer **282**. Due to the shape of the second temporary bonding layer **282** that encloses the contact electrode **260**, the contact electrode **260** is interposed between the second temporary bonding layer **282** and the light-emitting part **220** and thus is not exposed.

[0174] The ninth operation **S290** is an operation of removing the first intermediate temporary substrate **291**, and etching the first temporary bonding layer **281** to expose the bonding pad layer **270**. In this case, in the ninth operation **S290**, the first intermediate temporary substrate **291** may be separated from the first temporary bonding layer **281** using an LLO technique.

[0175] After the basic structure of the epitaxial die **200** is formed through the above-described first operation **S210** to ninth operation **S290**, processes such as grinding, dicing, probing, and sorting are performed.

[0176] Hereinafter, with reference to the accompanying drawings, a method (**S20**) of manufacturing the semiconductor light-emitting device according to the second embodiment of the present invention will be described in detail.

[0177] The semiconductor light-emitting device **20** of the present invention may be formed as a COB in which individual chips or epitaxial die units are directly transferred and connected to a substrate (such as a semiconductor wafer, a PCB, or TFT glass) on which circuit wiring and driving element regions are completed, a POB in which package units (including 1, 2, 2, 9, 26, . . . , and n² chips or epitaxial die units) manufactured using a fan-out package process known in conventional memory semiconductor technology are directly transferred and connected to a substrate on which circuit wiring and driving element regions (such as a semiconductor wafer, a PCB, or TFT glass) are completed, or an interposer using an intermediate temporary substrate **290** on which circuit wiring and driving element regions are not completed, but is not limited thereto, and will be described herein as being formed as the COB type for convenience of description.

[0178] FIG. **11** is a flowchart of the method of manufacturing the semiconductor light-emitting device according to the second embodiment of the present invention, and FIG. **12** illustrates a process of manufacturing the semiconductor light-emitting device according to the second embodiment of the present invention.

[0179] As shown in FIGS. **11** and **12**, the method (**S20**) of manufacturing the semiconductor light-

emitting device according to the second embodiment of the present invention includes a first operation **S21**, a second operation **S22**, a third operation **S23**, a fourth operation **S24**, a fifth operation **S25**, a sixth operation **S26**, and a seventh operation **S27**. However, it is of course possible that the order of the processes shown in FIGS. **11** and **12** can be changed.

[0180] The first operation **S21** is an operation of preparing the epitaxial die **200** for a semiconductor light-emitting device according to the second embodiment of the present invention and a substrate part **21** on which a first electrode pad **21a** and a second electrode pad **21b** are each formed. The substrate part **21** may refer to a semiconductor wafer, a PCB, TFT glass, an interposer, or the like, but the present invention is not limited thereto.

[0181] The second operation **S22** is an operation of placing the epitaxial die **200** upside down on the first electrode pad **21a**, which is an individual negative electrode, and electrically connecting the first electrode pad **21a** and the bonding pad layer **270** by bonding them through a bonding layer **22**. At this time, the placement and bonding of the epitaxial die **200** can be accomplished through typical chip die transfer processes such as pick-and-place, roll to roll (R2R), and stamps (made from materials such as polydimethylsiloxane (PDMS), silicon (Si), quartz, and glass), which are commonly known tools used in representative processes of massive transfer.

[0182] Meanwhile, when it is necessary to achieve objectives such as (1) high precision placement of an epitaxial die **200**, (2) an epitaxial die **200** with a ultra-small size of less than $50\ \mu\text{m} \times 50\ \mu\text{m}$, and (3) an epitaxial die **200** having a self-assembly structure, additional masking media (such as a photoresist, ceramics (like glass, quartz, and alumina), or an invar FMM or processes may be employed before the placement and bonding of the epitaxial die **200**.

[0183] The third operation **S23** is an operation of removing the intermediate temporary substrate **290** (i.e., the second intermediate temporary substrate **292**) of the epitaxial die **200**, and etching the temporary bonding layer **280** (i.e., the second temporary bonding layer **282**) to expose the contact electrode **260**. At this time, in the third operation **S23**, the intermediate temporary substrate **290** may be separated from the temporary bonding layer **280** using an LLO technique. Here, the LLO technique refers to a technique of separating the intermediate temporary substrate **290** from the temporary bonding layer **280** by irradiating a rear surface of the transparent intermediate temporary substrate **290** with a UV laser beam having a uniform output and beam profile, and a single wavelength.

[0184] The fourth operation **S24** is an operation of forming a mold part **24** surrounding the epitaxial die **200** so that the contact electrode **260** is exposed. At this time, the mold part **24** may be made of materials that enable LDS or LDI to allow laser drilling in the fifth operation **S25** to be described below.

[0185] The fifth operation **S25** is an operation of etching the mold part **24** to expose the second electrode pad **21b**. That is, in the fifth operation **S25**, a through hole **H** is formed above the second electrode pad **21b** by etching the mold part **24** above the second electrode pad **21b** using laser drilling.

[0186] The sixth operation **S26** is an operation of forming an extension electrode **23** that electrically connects the second electrode pad **21b** and the exposed contact electrode **260**. That is, the extension electrode **23** is formed to extend vertically from an upper portion of the second electrode pad **21b** to above the mold part **24** through the through hole **H**, and then extend horizontally by being bent toward the contact electrode **260** to come into contact with and be electrically connected to the contact electrode **260**.

[0187] The seventh operation **S27** is an operation of forming a black matrix **25** that covers the extension electrode **23** and the mold part **24**. The black matrix **25** may be formed using photolithography and spin coating processes, but the present invention is not limited thereto.

[0188] Although all the components constituting the embodiments of the present invention have been described as being combined or combined to operate as one, the present invention is not necessarily limited to the embodiments. That is, one or more of all the components may be

combined to operate as one within the scope of the present invention.

[0189] Further, since the terms, such as “comprising”, “including”, or “having” may mean that the corresponding component can be included unless otherwise stated, it should be construed that another component is not excluded but may be further included. Unless defined otherwise, all terms used herein, including technical or scientific terms, have the same meanings as those generally understood by those skilled in the art to which the present invention pertains. Commonly used terms, such as terms defined in dictionaries, should be interpreted as being consistent with the contextual meaning of the related art and are not interpreted in an ideal or excessively formal meaning unless explicitly defined herein.

[0190] In addition, the above description is merely an exemplary description of the technical spirit of the present invention, and the present invention may be subjected to various modifications and variations made by those skilled in the art to which the present invention pertains without departing from the essential features of the present invention.

[0191] Accordingly, the embodiments disclosed in the present invention are not provided to limit the technical spirit of the embodiments of the present invention but are provided to describe the present invention, and the scope of the technical spirit of the present invention is not limited by the embodiments. The scope of protection of the present invention should be construed by the attached claims, and all the technical ideas within the equivalent ranges fall within the scope of the present invention.

Claims

1. An epitaxial die for a semiconductor light-emitting device, wherein the epitaxial die is formed by separating into die units, and functions as a pixel after being individually transferred to a substrate part. comprising: a light-emitting part configured to generate red light; a first ohmic electrode formed on the light-emitting part and electrically connected to the light-emitting part; a passivation layer formed to cover the first ohmic electrode, and having a portion opened to expose a portion of the first ohmic electrode; a contact electrode formed on the exposed first ohmic electrode and electrically connected to the first ohmic electrode; a temporary bonding layer formed over the contact electrode and the passivation layer to cover the contact electrode; a temporary substrate bonded on the temporary bonding layer; and a bonding pad layer formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part and functioning as a vertical chip bonding pad and is exposed to the outside, wherein the contact electrode is interposed between the temporary bonding layer and the first ohmic electrode and thus is not exposed is not exposed to the outside before the epitaxial die is transferred to the substrate part, wherein the temporary substrate is optically transparent, and it is possible to determine optical defects of the epitaxial die before the epitaxial die is transferred to the substrate part.

2-8. (canceled)

9. The epitaxial die of claim 1, wherein the light-emitting part is etched on both sides to a preset depth, and the passivation layer covers the first ohmic electrode from the etched portion on both sides of the light-emitting part.

10. The epitaxial die of claim 1, wherein the light-emitting part includes: a first semiconductor region having first conductivity; a second semiconductor region having second conductivity that is different from the first conductivity; and an active region interposed between the first semiconductor region and the second semiconductor region and configured to generate light using recombination of electrons and holes.

11. The epitaxial die of claim 1, wherein the bonding pad layer is electrically connected by making a negative ohmic contact (n-ohmic contact) to the lower surface of the light-emitting part.

12. A method of manufacturing an epitaxial die for a semiconductor light-emitting device, wherein the epitaxial die is formed by separating into die units, and functions as a pixel after being

individually transferred to a substrate part, comprising: a first operation of preparing a growth substrate and a temporary substrate; a second operation of forming a light-emitting part, which generates red light, on the growth substrate; a third operation of forming a first ohmic electrode on the light-emitting part; a fourth operation of forming a passivation layer that covers the first ohmic electrode; a fifth operation of etching a portion of the passivation layer to expose the first ohmic electrode and forming a contact electrode to come into contact with the exposed first ohmic electrode; a sixth operation of bonding the temporary substrate and the passivation layer, in which the contact electrode is exposed, through a temporary bonding layer; a seventh operation of separating the growth substrate; and an eighth operation of forming a bonding pad layer formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part and functioning as a vertical chip bonding pad, wherein the temporary bonding layer formed over the contact electrode and the passivation layer to cover the contact electrode, wherein the contact electrode is interposed between the temporary bonding layer and the first ohmic electrode and is not exposed to the outside before the epitaxial die is transferred to the substrate part, wherein the temporary substrate is optically transparent, and it is possible to determine optical defects of the epitaxial die before the epitaxial die is transferred to the substrate part.

13. An epitaxial die for a semiconductor light-emitting device, wherein the epitaxial die is formed by separating into die units, and functions as a pixel after being individually transferred to a substrate part, comprising: a light-emitting part configured to generate red light; a first ohmic electrode formed on the light-emitting part and electrically connected to the light-emitting part; a passivation layer formed to cover the first ohmic electrode, and having a portion opened to expose a portion of the first ohmic electrode; a bonding pad layer formed on the exposed first ohmic electrode and electrically connected to the first ohmic electrode, and functioning as a vertical chip bonding pad; a contact electrode formed to come into contact with a lower surface of the light-emitting part to be electrically connected to the light-emitting part, wherein the contact electrode is electrically connected by making a negative ohmic contact (n-ohmic contact) to the lower surface of the light-emitting part; a temporary bonding layer formed on the lower surface of the light-emitting part to cover the contact electrode; and a temporary substrate bonded to a lower surface of the temporary bonding layer, wherein the contact electrode is interposed between the temporary bonding layer and the light-emitting part and is not exposed to the outside before the epitaxial die is transferred to the substrate part, wherein the temporary substrate is optically transparent, and it is possible to determine optical defects of the epitaxial die before the epitaxial die is transferred to the substrate part.

14. The epitaxial die of claim 13, wherein the light-emitting part is etched on both sides to a preset depth, and the passivation layer covers the first ohmic electrode from the etched portion on both sides of the light-emitting part.

15. The epitaxial die of claim 13, wherein the light-emitting part includes: a first semiconductor region having first conductivity; a second semiconductor region having second conductivity that is different from the first conductivity; and an active region interposed between the first semiconductor region and the second semiconductor region and configured to generate light using recombination of electrons and holes.
