

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12398838
Kind Code	B2
Date of Patent	August 26, 2025
Inventor(s)	Kim; Dongwan et al.

Insulation structure, insulated piping device including the same, and method of fabricating the same

Abstract

Insulation structures, insulated piping devices including the same, and methods of fabricating the same are disclosed. The insulation structure includes a first insulation layer on an outer surface of a pipe, a second insulation layer on an outer surface of the first insulation layer that includes a material different from a material of the first insulation layer, and a third insulation layer on an outer surface of the second insulation layer that includes a material different from the material of the second insulation layer. A thickness of the second insulation layer is greater than a thickness of the first insulation layer and a thickness of the third insulation layer. The second insulation layer includes a porous foam.

Inventors: Kim; Dongwan (Suwon-si, KR), Kim; Jeong-Hyun (Pyeongtaek-si, KR), An; Seung-Hyeok (Hwaseong-si, KR), Lee; Saya (Osan-si, KR), Chung; Yoong (Suwon-si, KR), Jeon; Jiho (Yeosu-si, KR), Cho; Yongjun (Pyeongtaek-si, KR), Choi; Injun (Hwaseong-si, KR)

Applicant: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Family ID: 1000008778984

Assignee: SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR); TECHNICAL COATING SOLUTION LINE-X CO., LTD. (Hwaseong-si, KR)

Appl. No.: 17/863843

Filed: July 13, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230081831 A1	Mar. 16, 2023

Foreign Application Priority Data

Publication Classification

Int. Cl.: F16L59/02 (20060101); F16L59/10 (20060101); F16L59/14 (20060101)

U.S. Cl.:

CPC F16L59/029 (20130101); F16L59/028 (20130101); F16L59/10 (20130101); F16L59/14 (20130101);

Field of Classification Search

CPC: F16L (59/141); F16L (59/143); F16L (59/12)

USPC: 138/149; 138/140; 138/137

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
3355572	12/1966	Chrow	219/535	F16L 53/38
3359351	12/1966	Bender	264/45.5	F16L 59/22
3665968	12/1971	De Putter	138/DIG.2	F16L 59/14
3812886	12/1973	Hallwood	138/149	F16L 59/06
4429213	12/1983	Mathieu	428/920	F24H 1/142
5160769	12/1991	Garrett	138/143	F16L 59/04
6058979	12/1999	Watkins	428/36.5	B29C 70/66
8371338	12/2012	Princell	138/131	F16L 59/147
8522829	12/2012	D'Souza	138/146	C04B 26/10
2010/0071797	12/2009	Jungers	138/149	F16L 9/14
2014/0220277	12/2013	Lewis	428/319.3	F16L 59/021
2017/0059080	12/2016	Zheng	N/A	B32B 5/18
2019/0329486	12/2018	Goulet	N/A	N/A
2023/0228362	12/2022	Pilone	138/149	B29C 63/0017

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
2010190388	12/2009	JP	N/A
2020159476	12/2019	JP	N/A
2021001659	12/2020	JP	N/A
20040081416	12/2003	KR	N/A
20100013834	12/2009	KR	N/A
20110123919	12/2010	KR	N/A
101174309	12/2011	KR	N/A
101781123	12/2016	KR	N/A
102050809	12/2018	KR	N/A
102142823	12/2019	KR	N/A
102191257	12/2019	KR	N/A
102216580	12/2020	KR	N/A

Primary Examiner: Deal; David R

Attorney, Agent or Firm: Myers Bigel, P.A.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

(1) This U.S. nonprovisional application claims priority under 35 U.S.C. § 119 to Korean Patent Application No. 10-2021-0121121 filed on Sep. 10, 2021 in the Korean Intellectual Property Office, the disclosure of which is hereby incorporated by reference in its entirety.

FIELD

(2) The present inventive concepts relate to an insulation structure, an insulated piping device including the same, and a method of fabricating the same, and more particularly, to an insulation structure that can prevent dew condensation, an insulated piping device including the same, and a method of fabricating the same.

BACKGROUND

(3) Various processes may be performed to fabricate a semiconductor device. For example, the semiconductor device may be fabricated by performing a photolithography process, an etching process, and a deposition process on a wafer. Such processes may require a low-temperature environment. A cryogenic coolant may be used to accomplish the low-temperature environment. The cryogenic coolant may flow through a pipe toward a process chamber. The cryogenic coolant may reduce a temperature of the pipe through which the coolant flows.

SUMMARY

(4) Some embodiments of the present inventive concepts provide an insulation structure that can reduce or prevent water vapor from condensation, an insulated piping device including the same, and a method of fabricating the same.

(5) Some embodiments of the present inventive concepts provide an insulation structure that can reduce or prevent an insulation layer from damage and can increase a life span, an insulated piping device including the same, and a method of fabricating the same.

(6) Some embodiments of the present inventive concepts provide an insulation structure that is applicable to variously shaped pipes, an insulated piping device including the same, and a method of fabricating the same.

(7) The object of the present inventive concepts is not limited to the mentioned above, and other objects which have not been mentioned above will be clearly understood to those skilled in the art from the following description.

(8) According to some embodiments of the present inventive concepts, an insulated piping device may comprise: a pipe; and an insulation structure on the pipe. The insulation structure may include: a first insulation layer on an outer surface of the pipe; a second insulation layer on an outer surface of the first insulation layer that includes a material different from a material of the first insulation layer; and a third insulation layer on an outer surface of the second insulation layer that includes a material different from the material of the second insulation layer. A thickness of the second insulation layer may be greater than a thickness of the first insulation layer and a thickness of the third insulation layer. The second insulation layer may include a porous foam.

(9) According to some embodiments of the present inventive concepts, an insulation structure may comprise: a first insulation layer on an outer surface of an insulation target; a second insulation layer on the first insulation layer; and a third insulation layer on the second insulation layer. The

second insulation layer may include a porous foam. A thickness of the second insulation layer may be greater than a thickness of the first insulation layer. A thermal conductivity of the first insulation layer may be less than a thermal conductivity of the second insulation layer. A hardness of the third insulation layer may be greater than a hardness of the second insulation layer.

(10) According to some embodiments of the present inventive concepts, a method of fabricating an insulated device may comprise: forming a first insulation layer on an outer surface of an insulation target; forming a second insulation layer on the first insulation layer that includes a material different from a material of the first insulation layer; and forming a third insulation layer on the second insulation layer that includes a material different from the material of the second insulation layer. A thickness of the second insulation layer may be greater than a thickness of the first insulation layer. The second insulation layer may include a porous foam.

(11) Details of other example embodiments are included in the description and drawings.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) FIG. 1 illustrates a schematic diagram showing a semiconductor fabrication system according to some embodiments of the present inventive concepts.

(2) FIG. 2 illustrates a cutaway perspective view showing an insulated piping device according to some embodiments of the present inventive concepts.

(3) FIG. 3 illustrates an exploded perspective view showing an insulated piping device according to some embodiments of the present inventive concepts.

(4) FIG. 4 illustrates a cross-sectional view showing an insulated piping device according to some embodiments of the present inventive concepts.

(5) FIG. 5 illustrates a flow chart showing a method of fabricating an insulated piping device according to some embodiments of the present inventive concepts.

(6) FIGS. 6 to 9 illustrate perspective views showing an insulated piping device fabrication method according to some embodiments of FIG. 5.

(7) FIG. 10 illustrates a graph showing a temperature gradient of an insulated piping device according to some embodiments of the present inventive concepts.

(8) FIG. 11 illustrates a cross-sectional view showing an insulated piping device according to some embodiments of the present inventive concepts.

(9) FIG. 12 illustrates a cross-sectional view showing an insulated piping device according to some embodiments of the present inventive concepts.

(10) FIG. 13 illustrates a cross-sectional view showing an example of an insulated piping device according to some embodiments of the present inventive concepts.

DETAILED DESCRIPTION OF EMBODIMENTS

(11) The following will now describe some embodiments of the present inventive concepts with reference to the accompanying drawings. Like reference numerals may indicate like components throughout the description.

(12) FIG. 1 illustrates a schematic diagram showing a semiconductor fabrication system according to some embodiments of the present inventive concepts.

(13) Referring to FIG. 1, a semiconductor fabrication system may be provided. The semiconductor fabrication system may perform a process that forms an integrated circuit (IC) on a substrate such as a wafer. A cryogenic coolant may be used in semiconductor fabrication process. The semiconductor fabrication system may include a coolant tank T, a process chamber PC, and an insulated piping device D.

(14) The coolant tank T may provide a space in which a coolant is stored. The coolant tank T may provide the process chamber PC with the coolant as needed. The coolant tank T may be connected

to the process chamber PC. For example, the coolant tank T may be connected through the insulated piping device D to the process chamber PC.

(15) The process chamber PC may be configured to provide a space in which a process that forms an integrated circuit on a substrate is performed. A photolithography process, an etching process, a deposition process, a cleaning process, a test process and/or other processes for forming an integrated circuit on a substrate may be executed in the process chamber PC.

(16) The insulated piping device D may connect the coolant tank T to the process chamber PC. The coolant may flow from the coolant tank T to the process chamber PC along the insulated piping device D. The insulated piping device D may block external heat from being transferred to the coolant. The insulated piping device D may include an insulating material. A detailed description thereof will be further discussed below. Although as described herein, the insulated piping device D connects the coolant tank T to the process chamber PC, the present inventive concepts are not limited thereto. For example, the insulated piping device D may be used in a different system that allows flow of low-temperature fluid.

(17) FIG. 2 illustrates a cutaway perspective view showing an insulated piping device according to some embodiments of the present inventive concepts. FIG. 3 illustrates an exploded perspective view showing an insulated piping device according to some embodiments of the present inventive concepts.

(18) Referring to FIGS. 2 and 3, the insulated piping device D may include a pipe P and an insulation structure A.

(19) The pipe P may provide an internal passage Ph. The pipe P may extend in one direction. Therefore, the internal passage Ph may also extend in one direction. The pipe P may have an annular shape at its cross section that is perpendicular to the direction that the pipe P extends; however, the present inventive concepts are not limited thereto. The coolant may flow along the internal passage Ph of the pipe P. The pipe P may be surrounded by the insulation structure A. Therefore, an outer surface of the pipe P may not be exposed externally.

(20) The insulation structure A may surround the pipe P. The insulation structure A may block or reduce a heat exchange between an external space and a fluid that flows through the internal passage Ph of the pipe P. The insulation structure A may include a first insulation layer 1, a second insulation layer 3, and a third insulation layer 5.

(21) The first insulation layer 1 may be on the pipe P. For example, the first insulation layer 1 may surround the external surface of the pipe P. For example, the first insulation layer 1 may surround the pipe P while being in contact with the external surface of the pipe P. The first insulation layer 1 may be used even at low temperatures. The phrase “used at low temperatures” means that there is little or no degeneration of materials in the component or layer even at low temperatures. For example, the first insulation layer 1 may have little or no degeneration of materials even at low temperatures. The first insulation layer 1 may be used at lower temperatures than the second insulation layer 3. For example, the first insulation layer may be used at temperatures equal to or less than about -50°C . For more detail, the first insulation layer 1 may be used with little or no degeneration of materials at temperatures in the vicinity of about -100°C . The first insulation layer 1 may include a material whose thermal conductivity is low. The first insulation layer 1 may have a thermal conductivity less than that of the second insulation layer 3. For example, the thermal conductivity of the first insulation layer 1 may range from about 0.010 W/mK to about 0.040 W/mK . The first insulation layer 1 may include a silica aerogel. The silica aerogel may be used in a temperature range of about -100°C . to about 120°C . with little or no degradation. The silicon aerogel may have a thermal conductivity of about 0.020 W/mK to about 0.030 W/mK . The present inventive concepts, however, are not limited thereto, and the first insulation layer 1 may include a material other than silicon aerogel.

(22) The second insulation layer 3 may be on the first insulation layer 1. For example, the second insulation layer 3 may surround the first insulation layer 1. The second insulation layer 3 may

include a different material from that of the first insulation layer **1**. The second insulation layer **3** may be used at a temperature greater than that of the first insulation layer **1** with little to no degradation of materials. For example, the second insulation layer **3** may have a use temperature of about -70°C . to about 180°C . The second insulation layer **3** may have a thermal conductivity greater than that of the first insulation layer **1**. For example, the thermal conductivity of the second insulation layer **3** may range from about 0.03 W/mK to about 0.06 W/mK . The second insulation layer **3** may include foam. For example, second insulation layer **3** may have a porous structure. The second insulation layer **3** may have fine pores therein. Air may fill the fine pores in the second insulation layer **3**. Therefore, the second insulation layer **3** may increase in insulation performance. The second insulation layer **3** may include a polyethylene-based material. For example, the second insulation layer **3** may include an ethylene propylene diene monomer (EPDM). The EPDM may have a thermal conductivity of about 0.033 W/mK to about 0.05 W/mK . The EPDM may have a use temperature of about -50°C . to about 165°C . The present inventive concepts, however, are not limited thereto, and the second insulation layer **3** may include a material other than EPDM.

(23) The third insulation layer **5** may be positioned on the second insulation layer **3**. For example, the third insulation layer **5** may surround the second insulation layer **3**. The third insulation layer **5** may include a different material from that of the second insulation layer **3**. The third insulation layer **5** may have a hardness greater than that of the second insulation layer **3**. For example, the third insulation layer **5** may have a Shore hardness of about 60 Shore D to about 66 Shore D. The second insulation layer **3** may have a Shore hardness less than that of the third insulation layer **5**. The present inventive concepts, however, are not limited thereto. Moreover, a hardness value other than the Shore hardness may be employed for comparison. For example, the third insulation layer **5** may have a hardness (e.g., a Mohs hardness) greater than that of the second insulation layer **3**. The third insulation layer **5** may be water resistant or waterproof. That is, the third insulation layer **5** may reduce or generally prevent water from passing through an outer surface of the third insulation layer **5**. The third insulation layer **5** may have moisture permeance less than that of the second insulation layer **3**. Therefore, water vapor in the air or environment surrounding the device **D** may not pass through the third insulation layer **5**. The third insulation layer **5** may be used at a temperature equal to or less than about -32°C . with little to no degradation of materials. The third insulation layer **5** may include a polyurea-based material. The polyurea may have a Shore hardness of about 62 Shore D to about 64 Shore D. The polyurea may be used at a temperature equal to less than about -34°C . The polyurea may have a thermal conductivity of about 0.134 W/mK to about 0.154 W/mK . The present inventive concepts, however, are not limited thereto, and the third insulation layer **5** may include a material other than polyurea.

(24) As illustrated, the insulation structure **A** surrounds the pipe **P**; however, the present inventive concepts are not limited thereto. For example, the insulation structure **A** may surround a different insulation object other than a pipe **P**. For example, the insulation structure **A** may be used to surround a low-temperature tank, a compressor, and/or a chiller. A detailed description thereof will be further discussed below.

(25) FIG. 4 illustrates a cross-sectional view showing an insulated piping device according to some embodiments of the present inventive concepts.

(26) Referring to FIG. 4, each of the pipe **P**, the first insulation layer **1**, the second insulation layer **3**, and the third insulation layer **5** may form a concentric circle around a central axis **CA**.

(27) A zeroth radius r_0 may indicate an inner radius of the pipe **P**. A first radius r_1 may indicate an outer radius of the pipe **P**. A second radius r_2 may indicate an outer radius of the first insulation layer **1**. A third radius r_3 may indicate an outer radius of the second insulation layer **3**. A fourth radius r_4 may indicate an outer radius of the third insulation layer **5**.

(28) A zeroth thickness t_p may indicate a thickness of the pipe **P**. The zeroth thickness t_p may be substantially the same as a difference between the first radius r_1 and the zeroth radius r_0 .

(29) A first thickness t_1 may indicate a thickness of the first insulation layer **1**. The first thickness

t1 may be substantially the same as a difference between the second radius **r2** and the first radius **r1**.

(30) A second thickness **t2** may indicate a thickness of the second insulation layer **3**. The second thickness **t2** may be substantially the same as a difference between the third radius **r3** and the second radius **r2**.

(31) A third thickness **t3** may indicate a thickness of the third insulation layer **5**. The third thickness **t3** may be substantially the same as a difference between the fourth radius **r4** and the third radius **r3**.

(32) The second insulation layer **3** may be thicker than each of the first insulation layer **1** and the third insulation layer **5**. For example, the second thickness **t2** may be greater than each of the first thickness **t1** and the third thickness **t3**. The second thickness **t2** may range from about 7 mm to about 11 mm. For example, the second thickness **t2** may be about 9 mm. The third thickness **t3** may range from about 3 mm to about 7 mm. For example, the third thickness **t3** may be about 5 mm. The first thickness **t1** may range from about 0.5 mm to about 3.5 mm. For example, the first thickness **t1** may be about 2 mm. The present inventive concepts, however, are not limited to the values mentioned above.

(33) FIG. 5 illustrates a flow chart showing a method of fabricating an insulated piping device according to some embodiments of the present inventive concepts.

(34) Referring to FIG. 5, there may be provided a method **S** of fabricating an insulated piping device. The insulated piping device fabrication method **S** may be a method of fabricating the insulated piping device **D** discussed with reference to FIG. 2. The insulated piping device fabrication method **S** may include a step **S1** of preparing a pipe, a step **S2** of forming a first insulation layer, a step **S3** of forming a second insulation layer, and a step **S4** of forming a third insulation layer.

(35) With reference to FIGS. 6 to 9, the following will describe in detail each step of the insulated piping device fabrication method **S** of FIG. 5.

(36) FIGS. 6 to 9 illustrate perspective views showing an insulated piping device fabrication method according to some embodiments of FIG. 5.

(37) Referring to FIGS. 5 and 6, the pipe preparation step **S1** may include preparing the pipe **P** that provides the internal passage **Ph**. The pipe **P** may be fabricated by various methods. For example, an injection method may be employed to fabricate the pipe **P**. The present inventive concepts, however, are not limited thereto, and other methods may be employed to fabricate the pipe **P**.

(38) Referring to FIGS. 5 and 7, the first insulation layer forming step **S2** may include forming the first insulation layer **1** on the outer surface of the pipe **P**. In some embodiments, a taping process may be performed to form the first insulation layer **1**. For example, the first insulation layer **1** may be wound around the outer surface of the pipe **P**. When the first insulation layer **1** includes silicon aerogel, the first insulation layer forming step **S2** may include winding a silica aerogel tape around the outer surface of the pipe **P**. The present inventive concepts, however, are not limited thereto, and the first insulation layer forming step **S2** may be performed by using other methods.

(39) Referring to FIGS. 5 and 8, the second insulation layer forming step **S3** may include allowing the second insulation layer **3** to cover the pipe **P** on which the first insulation layer **1** is coated. In some embodiments, the second insulation layer **3** may be previously formed in the shape of a hollow tube. The pipe **P** on which the first insulation layer **1** is previously formed may be inserted into an internal space **3h** of the second insulation layer **3**. The present inventive concepts, however, are not limited thereto, and the second insulation layer forming step **S3** may be performed by using other methods.

(40) Referring to FIGS. 5 and 9, the third insulation layer forming step **S4** may include forming the third insulation layer **5** on the second insulation layer **3** using a material that constitutes the third insulation layer **5**. The material which constitutes the third insulation layer **5** may be sprayed on an outer surface of the second insulation layer **3**. For example, when the third insulation layer **5**

includes a polyurea-based material, the polyurea-based material may be sprayed on the second insulation layer **3**. The third insulation layer forming step **S4** may further include curing the material coated on the second insulation layer **3**. For example, the material sprayed on the outer surface of the second insulation layer **3** may be cured by a passage of an amount of time. When the third insulation layer **5** includes a polyurea-based material, the polyurea-based material sprayed on the outer surface of the second insulation layer **3** may be cured in about 5 minutes to about 10 minutes. Therefore, the third insulation layer **5** may increase in hardness during the curing process. The present inventive concepts, however, are not limited thereto, and the third insulation layer coating step **S4** may be performed by using other methods. When the curing of the third insulation layer **5** is terminated, the insulation structure **A** may be formed.

(41) FIG. **10** illustrates a graph showing a temperature gradient of an insulated piping device according to some embodiments of the present inventive concepts.

(42) Referring to FIGS. **4** and **10**, when a low-temperature coolant flows through the internal passage **Ph** of the pipe **P**, a temperature gradient of the pipe **P** and the insulation structure **A** that are affected by the low-temperature coolant may be represented by the graph of FIG. **10**. In the graph of FIG. **10**, a horizontal axis may indicate a distance **d** from the central axis **CA** discussed with reference to FIG. **4**. A vertical axis may denote a temperature.

(43) A region away from the central axis **CA** at a distance equal to or less than the zeroth radius **r0** may signify the internal passage **Ph**. The internal passage **Ph** may have a zeroth temperature **T0**. The zeroth temperature **T0** may be substantially the same as or similar to a temperature of the coolant.

(44) A region away from the central axis **CA** at a distance between the zeroth radius **r0** and the first radius **r1** may signify an area within the pipe **P**. The area within the pipe **P** may have a temperature ranging from the zeroth temperature **T0** to a first temperature **T1**. The first temperature **T1** may be greater than the zeroth temperature **T0**.

(45) A region away from the central axis **CA** at a distance between the first radius **r1** and the second radius **r2** may signify an area within the first insulation layer **1**. The area within the first insulation layer **1** may have a temperature ranging from the first temperature **T1** to a second temperature **T2**. The second temperature **T2** may be greater than the first temperature **T1**.

(46) A region away from the central axis **CA** at a distance between the second radius **r2** and the third radius **r3** may signify an area within the second insulation layer **3**. The area within the second insulation layer **3** may have a temperature ranging from the second temperature **T2** to a third temperature **T3**. The third temperature **T3** may be greater than the second temperature **T2**.

(47) A region away from the central axis **CA** at a distance between the third radius **r3** and the fourth radius **r4** may signify an area within the third insulation layer **5**. The area within the third insulation layer **5** may have a temperature ranging from the third temperature **T3** to a fourth temperature **T4**. The fourth temperature **T4** may be greater than the third temperature **T3**.

(48) Because the thermal conductivity of the first insulation layer **1** is less than that of the second insulation layer **3**, a slope of the graph in a region between the first radius **r1** and the second radius **r2** may be greater than a slope of the graph in a region between the second radius **r2** and the third radius **r3**.

(49) The temperature gradient is illustrated linearly in the graph of FIG. **10**, but the present inventive concepts are not limited thereto. For example, based on shapes and materials of the pipe **P** and the insulation structure **A**, the temperature gradient may not be illustrated linearly, but may be illustrated curvedly.

(50) According to some embodiments of an insulation structure, an insulated piping device including the same, and a method of fabricating the same in accordance with some embodiments of the present inventive concepts, the thermal conductivity of the first insulation layer **1** may be less than that of the second insulation layer **3**. Therefore, even when the first insulation layer has a small thickness, there may be a large difference in temperature between inner and outer surfaces of

the first insulation layer **1**. Thus, the first insulation layer **1** may have an excellent insulation effect. Even when an inside of the first insulation layer becomes cryogenic, the outer surface of the first insulation layer **1** may have a significantly large temperature. For example, the temperature at the outer surface of the first insulation layer **1** may be greater than the temperature in which the second insulation layer **3** may be used without significant degradation. Even when the first insulation layer **1** has a small thickness, the temperature at the outer surface of the first insulation layer **1** may be greater than the temperature in which the second insulation layer **3** may be used without significant degradation in a state where the cryogenic coolant flows through the internal passage Ph.

Therefore, the second insulation layer **3** may be prevented from being cured and fractured under a cryogenic environment. Moreover, fine particles that can disrupt the semiconductor fabrication processes and occur due to a fracture of the second insulation layer **3** may be reduced or prevented.

(51) According to some embodiments of an insulation structure, an insulated piping device including the same, and a method of fabricating the same in accordance with some embodiments of the present inventive concepts, the second insulation layer **3** may include a porous foam. Thus, an air layer may be formed in the second insulation layer **3**. Accordingly, the second insulation layer **3** may increase in insulation effect. In addition, the use of the porous foam may obtain an excellent insulation effect at low cost. Moreover, there may be simplicity and promptness in the fabrication of the second insulation layer **3** including the porous foam. The process time may then decrease.

(52) According to some embodiments of an insulation structure, an insulated piping device including the same, and a method of fabricating the same in accordance with some embodiments of the present inventive concepts, the third insulation layer **5** may have a hardness greater than that of the second insulation layer **3**. Thus, the second insulation layer **3** may be protected from external impact. In some embodiments, vibration may occur due to the coolant that flows through the internal passage Ph, and the third insulation layer **5**, whose hardness is high, may reduce or prevent fractures in the second insulation layer **3**. Therefore, the second insulation layer **3** may increase a life span of the insulation structure. Furthermore, fine particles produced by fractures of the second insulation layer **3**, which may disturb the semiconductor fabrication process, may be reduced or prevented.

(53) According to some embodiments of an insulation structure, an insulated piping device including the same, and a method of fabricating the same in accordance with some embodiments of the present inventive concepts, the third insulation layer **5** may be water resistant or waterproof. Thus, the second insulation layer **3** may reduce or prevent the absorption of external moisture. For example, because external moisture does not pass through the third insulation layer **5**, the moisture may be prevented from being introduced into the air in the porous structure of the second insulation layer **3**. Thus, even when the second insulation layer **3** has a low temperature therein, moisture may be prevented from condensing. Accordingly, condensed moisture, which may disturb a semiconductor fabrication process, may be reduced or prevented.

(54) According to some embodiments of an insulation structure, an insulated piping device including the same, and a method of fabricating the same in accordance with some embodiments of the present inventive concepts, because the first insulation layer **1** is formed by a taping process, the first insulation layer **1** may be installed on pipes made of soft material. In addition, because the third insulation layer **5** is coated by spray method, the third insulation layer **5** may be installed on pipes made of soft material.

(55) FIG. **11** illustrates a cross-sectional view showing an insulated piping device according to some embodiments of the present inventive concepts.

(56) Hereinafter, components substantially the same as or similar to those discussed with reference FIGS. **1** to **10** will be omitted in the interest of convenience.

(57) Referring to FIG. **11**, an insulated piping device D' may be provided. The insulated piping device D' of FIG. **11** may be fabricated by a different method from that for fabricating the insulated piping device D discussed with reference to FIG. **2**. For example, a different method may be

employed to couple a second insulation layer **3a'** and **3b'** to the first insulation layer **1**. The second insulation layer **3a'** and **3b'** may be divided into two pieces. The divided two second insulation layers **3a'** and **3b'** may be coupled to the first insulation layer **1** while overlying and underlying the first insulation layer **1**. Therefore, the divided two second insulation layers **3a'** and **3b'** may be jointed into a single piece to surround the first insulation layer **1**. A tape may be used to join to each other the two second insulation layers **3a'** and **3b'**, but the present inventive concepts are not limited thereto.

(58) FIG. **12** illustrates a cross-sectional view showing an insulated piping device according to some embodiments of the present inventive concepts.

(59) Hereinafter, components substantially the same as or similar to those discussed with reference FIGS. **1** to **11** will be omitted in the interest of convenience.

(60) Referring to FIG. **12**, an insulated piping device **D''** may be provided. The insulated piping device **D''** may be different from the insulated piping device **D** discussed with reference to FIG. **2**. In some embodiments, the insulated piping device **D''** of FIG. **11** may further include an adhesion layer **2**. For example, an insulation structure **A''** may further include the adhesion layer **2** between the first insulation layer **1** and the second insulation layer **3**. Therefore, an air layer may be reduced or removed between the first insulation layer **1** and the second insulation layer **3**. Accordingly, condensation of water vapor may be reduced or prevented around the first insulation layer **1**.

(61) FIG. **13** illustrates a cross-sectional view showing an example of an insulated piping device according to some embodiments of the present inventive concepts.

(62) Hereinafter, components substantially the same as or similar to those discussed with reference FIGS. **1** to **12** will be omitted in the interest of convenience.

(63) Referring to FIG. **13**, an insulation structure **A'''** may be used to surround a chiller **CT**. The chiller **CT** may be used to reduce a temperature of a fluid in the chiller **CT**. An inlet pipe **IP** and an outlet pipe **OP** may be coupled to the chiller **CT**. The insulation structure **A'''** may insulate the chiller **CT** from outside, while surrounding a body of the chiller **CT**. In addition, the insulation structure **A'''** may be used to surround a body of a compressor.

(64) According to some embodiments of an insulation structure, an insulated piping device including the same, and a method of fabricating the same in accordance with the present inventive concepts, it may be possible to reduce or prevent a fabrication process from being disturbed due to condensation of water vapor.

(65) According to some embodiments of an insulation structure, an insulated piping device including the same, and a method of fabricating the same in accordance with the present inventive concepts, fractures in an insulation layer may be reduced or prevented and may increase in life span.

(66) According to some embodiments of an insulation structure, an insulated piping device including the same, and a method of fabricating the same in accordance with the present inventive concepts, an insulation structure may be applied to variously shaped pipes.

(67) Effects of the present inventive concepts are not limited to the mentioned above, other effects which have not been mentioned above will be clearly understood to those skilled in the art from the following description.

(68) Although the present inventive concepts have been described in connection with some embodiments of the present inventive concepts illustrated in the accompanying drawings, it will be understood to those skilled in the art that various changes and modifications may be made without departing from the technical spirit and essential feature of the present inventive concepts. It therefore will be understood that the embodiments described above are just illustrative but not limitative in all aspects.

Claims

1. An insulated piping device, comprising: a pipe; and an insulation structure on an outer surface of the pipe, wherein the insulation structure includes: a first insulation layer on the outer surface of the pipe; a second insulation layer on an outer surface of the first insulation layer comprising a porous foam material that is different from a material of the first insulation layer; and a third insulation layer on an outer surface of the second insulation layer comprising a material different from the material of the second insulation layer, wherein a thickness of the second insulation layer is greater than a thickness of the first insulation layer and a thickness of the third insulation layer, and wherein a thermal conductivity of the first insulation layer is less than a thermal conductivity of the second insulation layer.
2. The insulated piping device of claim 1, wherein a hardness of the third insulation layer is greater than a hardness of the second insulation layer.
3. The insulated piping device of claim 1, wherein the third insulation layer is water resistant or waterproof.
4. The insulated piping device of claim 1, wherein the second insulation layer includes an ethylene propylene diene monomer (EPDM).
5. The insulated piping device of claim 1, wherein the first insulation layer includes silica aerogel.
6. The insulated piping device of claim 1, wherein the third insulation layer includes a polyurea-based material.
7. The insulated piping device of claim 1, wherein the thickness of the first insulation layer is about 2 mm, the thickness of the second insulation layer is about 9 mm, and the thickness of the third insulation layer is about 5 mm.
8. The insulated piping device of claim 1, further comprising an adhesion layer between the first insulation layer and the second insulation layer.
9. An insulation structure, comprising: a first insulation layer on an outer surface of an insulation target; a second insulation layer on the first insulation layer; and a third insulation layer on the second insulation layer, wherein the second insulation layer includes a porous foam, wherein a thickness of the second insulation layer is greater than a thickness of the first insulation layer, wherein a thermal conductivity of the first insulation layer is less than a thermal conductivity of the second insulation layer, wherein a hardness of the third insulation layer is greater than a hardness of the second insulation layer, and wherein the first insulation layer includes silica aerogel, the second insulation layer includes an ethylene propylene diene monomer (EPDM), and the third insulation layer includes a polyurea-based material.
10. The insulation structure of claim 9, wherein the third insulation layer is water resistant or waterproof, and a thickness of the third insulation layer is less than the thickness of the second insulation layer.
11. The insulation structure of claim 9, wherein the thickness of the first insulation layer is in a range of about 0.5 mm to about 3.5 mm, the thickness of the second insulation layer is in a range of about 7 mm to about 11 mm, and a thickness of the third insulation layer is in a range of about 3 mm to about 7 mm.
12. A method of fabricating an insulated device, the method comprising: forming a first insulation layer on an outer surface of an insulation target; forming a second insulation layer on the first insulation layer, the second insulation layer including a material different from a material of the first insulation layer; and forming a third insulation layer on the second insulation layer, the third insulation layer including a material different from the material of the second insulation layer, wherein a thickness of the second insulation layer is greater than a thickness of the first insulation layer, wherein the second insulation layer includes a porous foam, and wherein forming the first insulation layer includes taping a silica aerogel tape on the outer surface of the insulation target.
13. The method of claim 12, wherein forming the third insulation layer includes: coating a polyurea-based material on the second insulation layer; and curing the polyurea-based material on

the second insulation layer.

14. The method of claim 13, wherein coating the polyurea-based material on the second insulation layer includes spraying the polyurea-based material on the second insulation layer.

15. The method of claim 12, wherein the thickness of the first insulation layer is in a range of about 0.5 mm to about 3.5 mm, the thickness of the second insulation layer is in a range of about 7 mm to about 11 mm, and a thickness of the third insulation layer is in a range of about 3 mm to about 7 mm.

16. The method of claim 12, wherein the insulated device comprises an and insulated piping device, and a thermal conductivity of the first insulation layer is less than a thermal conductivity of the second insulation layer.

17. The method of claim 12, wherein a hardness of the third insulation layer is greater than a hardness of the second insulation layer.
