

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12406827
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Yoo; Hyobin

Microscopic specimen and analysis method thereof using microscope

Abstract

Provided is a microscopic specimen including a lower plate that includes a lower opening portion, an upper plate that covers the lower opening portion, a target material layer on the upper plate, a lower electrode layer between the upper plate and the target material layer, an upper electrode layer on the target material layer, and a wiring pattern electrically connected to each of the upper electrode layer and the lower electrode layer.

Inventors: Yoo; Hyobin (Seoul, KR)

Applicant: Sogang University Research & Business Development Foundation (Seoul, KR)

Family ID: 88096449

Assignee: Sogang University Research & Business Development Foundation (Seoul, KR)

Appl. No.: 18/184761

Filed: March 16, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20230307208 A1	Sep. 28, 2023

Foreign Application Priority Data

KR	10-2022-0036294	Mar. 23, 2022
KR	10-2022-0107068	Aug. 25, 2022

Publication Classification

Int. Cl.: H01J37/28 (20060101); H01J37/20 (20060101); H01J37/244 (20060101)

U.S. Cl.:

CPC **H01J37/28** (20130101); **H01J37/20** (20130101); **H01J37/244** (20130101);

Field of Classification Search

CPC: H01J (37/28); H01J (37/20); H01J (37/244); H01J (37/26); H01J (37/295); H01J (2237/2008); G01N (23/2251)

USPC: 250/306; 250/307; 250/310; 250/311

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
9716295	12/2016	Jung et al.	N/A	N/A
10636581	12/2019	Kobayashi et al.	N/A	N/A
11817564	12/2022	Jung et al.	N/A	N/A
2010/0193398	12/2009	Marsh	29/428	H01J 37/20
2012/0298883	12/2011	Grogan	156/60	H01J 37/28
2018/0372672	12/2017	Walden, II	N/A	H01J 37/20
2019/0074498	12/2018	Chung et al.	N/A	N/A
2019/0237295	12/2018	Camino	N/A	H01J 37/26

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
104237567	12/2013	CN	N/A
10-2016-0129612	12/2015	KR	N/A
10-2018-0037064	12/2017	KR	N/A
2020-0033192	12/2019	KR	N/A
20210026997	12/2020	KR	N/A

OTHER PUBLICATIONS

Rebecca Engelke et al., Topologically protected moiré domain antiferroelectrics in twisted van der Waals homobilayers , Park Group @ Harvard (2022). cited by applicant

B. L. Mehdi, et al., Observation and Quantification of Nanoscale Processes in Lithium Batteries by Operando Electrochemical (S)TEM, 10.1021/acs.nanolett.5b00175 (DOI) Nano Lett. 2015. cited by applicant

Primary Examiner: McCormack; Jason L

Attorney, Agent or Firm: Harness, Dickey & Pierce, P.L.C.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS

(1) This U.S. non-provisional patent application claims priority under 35 U.S.C. § 119 of Korean Patent Application Nos. 10-2022-0036294, filed on Mar. 23, 2022, and 10-2022-0107068, filed on Aug. 25, 2022, the entire contents of which are hereby incorporated by reference.

BACKGROUND

(2) The present disclosure herein relates to a microscopic specimen and an analysis method thereof using a microscope, and more particularly, to a multilayer microscopic specimen including a target material layer, and a method of analyzing the target material layer of the multilayer microscopic specimen using a microscope.

(3) As the modern industry highly develops, the trend of high integration of electronic devices, etc., increases. The high integration of the electronic devices, etc., requires the development of various analysis methods utilizable in the development of the electronic devices, etc. Representative examples of such analysis methods include analyses of material structures, etc., through an electron microscope. Among the analyses, an analysis method through an electron microscope, which analyzes a diffraction pattern obtained by allowing electrons to pass through a specimen, is widely utilized. Such a method requires machining of a specimen to a thin thickness so that electrons may effectively pass through the specimen. Accordingly, utilizing the electron microscope entails using a destructive method to prepare a specimen. As the structure of the specimen is newly machined, an actual driving environment of electronic devices is difficult to realize.

SUMMARY

(4) The present disclosure provides a microscopic specimen, in which an actual driving environment of semiconductor devices, or the like, is realized, and a method of analyzing the microscopic specimen using a microscope.

(5) The present disclosure also provides a microscopic specimen, with which changes in structure of a target material layer according to an external factor is analyzable in real time, and a method of analyzing the microscopic specimen using a microscope.

(6) The objectives of the present invention are not limited to the aforesaid, but other objectives not described herein would be clearly understood by those skilled in the art from descriptions below.

(7) An embodiment of the inventive concept provides a microscopic specimen including a lower plate that includes a lower opening portion, an upper plate that covers the lower opening portion, a target material layer on the upper plate, a lower electrode layer between the upper plate and the target material layer, an upper electrode layer on the target material layer, and a wiring pattern electrically connected to each of the upper electrode layer and the lower electrode layer.

(8) In an embodiment of the inventive concept, an analysis method may include a process (a) of disposing a specimen in a microscope, a process (b) of emitting an electron beam passing through the specimen, and a process (c) of obtaining analysis information from a diffracted electron beam of the passed electron beam. The specimen may include a lower plate that includes a lower opening portion, an upper plate that covers the lower opening portion, a target material layer on the upper plate, and a lower electrode layer between the upper plate and the target material layer. In the process (b), the electron beam may pass through the target material layer, the lower electrode layer, the upper plate, and the lower plate in sequence.

Description

BRIEF DESCRIPTION OF THE FIGURES

(1) The accompanying drawings are included to provide a further understanding of the inventive concept, and are incorporated in and constitute a part of this specification. The drawings illustrate embodiments of the inventive concept and, together with the description, serve to explain principles of the inventive concept. In the drawings:

(2) FIG. 1 is a perspective view illustrating a specimen according to an embodiment of the inventive concept;

(3) FIGS. 2 to 7 are views illustrating a specimen according to an embodiment of the inventive concept, where FIGS. 2, 4 and 6 are plan views of a specimen according to an embodiment of the inventive concept, FIGS. 3A and 3B are cross-sectional views corresponding to line A-A' in FIG. 2,

FIG. 5 is a cross-sectional view corresponding to line A-A' in FIG. 4, and FIG. 7 is a cross-sectional view corresponding to line A-A' in FIG. 6;

(4) FIG. 8 is a flowchart for explaining an analysis method according to an embodiment of the inventive concept;

(5) FIG. 9 is a schematic diagram of a microscope for explaining an analysis method according to an embodiment of the inventive concept; and

(6) FIG. 10 is a flowchart for explaining an analysis method according to an embodiment of the inventive concept.

DETAILED DESCRIPTION

(7) Hereinafter, embodiments of the inventive concept will be described in detail with reference to the accompanying drawings.

(8) FIG. 1 is a perspective view illustrating a specimen according to an embodiment of the inventive concept. FIG. 2 is a plan view of a specimen according to an embodiment of the inventive concept. FIGS. 3A and 3B are cross-sectional views corresponding to line A-A' in FIG. 2.

(9) Referring to FIGS. 1 to 3A, a specimen 1 may be provided which is used in performing an analysis method using a microscope. The microscope may be an electron microscope. For example, the microscope may be any one of a transmission electron microscope (TEM) and a scanning transmission electron microscope (STEM), but is not limited thereto.

(10) The specimen 1 may include a lower plate 10, an upper plate 20, a target material layer 30, a lower electrode layer 40, an upper electrode layer 50, and a wiring pattern 60. The lower plate 10 may include a lower opening portion 12 passing therethrough. The lower opening portion 12 may be an empty space extending from a top surface to a bottom surface of the lower plate 10, and may be provided in plurality. The lower plate 10 may include, for example, silicone, but is not limited thereto.

(11) The upper plate 20 may be disposed on the lower plate 10. The upper plate 20 may cover the lower opening portion 12 of the lower plate 10, and may extend onto the top surface of the lower plate 10. For example, the upper plate 20 may fully cover the lower plate 10, but is not limited thereto. The upper plate 20 may have a bottom surface that is exposed to the outside by the lower opening portion 12. The upper plate 20 may have a thickness t_1 that is, for example, greater than about 0 nm and less than or equal to about 300 nm. As the upper plate 20 has a thin thickness of about 300 nm or less, an electron beam of the microscope may pass through the upper plate 20 in the analysis method to be described later. For example, the upper plate 20 may include a silicon nitride, but is not limited thereto. In one example, the upper plate 20 may include a monocrystalline material, but is not limited thereto. In another example, the upper plate 20 may include an amorphous material.

(12) The target material layer 30 may be disposed on the upper plate 20. In one example, the target material layer 30 may cover at least a portion of a top surface of the upper plate 20. The target material layer 30 may vertically overlap the lower opening portion 12 of the lower plate 10. In one example, the entire area of the target material layer 30 may vertically overlap the lower opening portion 12. In another example, although not illustrated, a portion of the target material layer 30 may vertically overlap the lower opening portion 12. The target material layer 30 may be a layer including a material to be observed through the microscope in the analysis method to be described later.

(13) The target material layer 30 may have a thickness t_4 that is, for example, greater than about 0 nm and less than or equal to about 300 nm. As the target material layer 30 has a thin thickness of about 300 nm or less, the electron beam of the microscope may pass through the target material layer 30 in the analysis method to be described later. The target material layer 30 may include at least one of a chalcogenide, a metal oxide, a nitride, graphene, and graphite. For example, the target material layer 30 may include a two-dimensional material such as a transition metal dichalcogenide (TMD). The target material layer 30 may exhibit, for example, ferroelectricity, but is not limited

thereto.

(14) The lower electrode layer **40** may be disposed on the upper plate **20**. The lower electrode layer **40** may be interposed between the upper plate **20** and the target material layer **30**. At least a portion of the target material layer **30** may vertically overlap the lower electrode layer **40**. In one example, as illustrated in FIG. 3A, the entire area of the target material layer **30** may vertically overlap the lower electrode layer **40**, but an embodiment of the inventive concept is not limited thereto. The lower electrode layer **40** may have a thickness t_2 that is, for example, greater than about 0 nm and less than or equal to about 300 nm. As the lower electrode layer **40** has a thin thickness of about 300 nm or less, the electron beam of the microscope may pass through the lower electrode layer **40** in the analysis method to be described later.

(15) The upper electrode layer **50** may be disposed on the target material layer **30**. At least a portion of the upper electrode layer **50** may vertically overlap the target material layer **30**. In one example, as illustrated in FIG. 3A, the entire area of the upper electrode layer **50** may vertically overlap the target material layer **30**. The upper electrode layer **50** may have a thickness t_6 that is, for example, greater than about 0 nm and less than or equal to about 300 nm. As the upper electrode layer **50** has a thin thickness of about 300 nm or less, the electron beam of the microscope may pass through the upper electrode layer **50** in the analysis method to be described later.

(16) The lower electrode layer **40** and the upper electrode layer **50** may each include a conductive material. In one example, the lower electrode layer **40** and the upper electrode layer **50** may each include conductive graphite. In another example, the lower electrode layer **40** and the upper electrode layer **50** may each include a conductive metal material (e.g., copper, aluminum, gold, silver, titanium, tungsten, or the like). In one example, each of the lower electrode layer **40** and the upper electrode layer **50** may include at least one of a monocrystalline material and an amorphous material, but is not limited thereto. The lower electrode layer **40** and the upper electrode layer **50** may include the same material or may include different materials.

(17) In one example, a lower insulation layer **45** may be interposed between the lower electrode layer **40** and the target material layer **30**, and an upper insulation layer **55** may be interposed between the upper electrode layer **50** and the target material layer **30**. The lower insulation layer **45** may separate the lower electrode layer **40** and the target material layer **30** from each other, and the upper insulation layer **55** may separate the upper electrode layer **50** and the target material layer **30** from each other. The lower insulation layer **45** may electrically insulate the lower electrode layer **40** and the target material layer **30** from each other, and the upper insulation layer **55** may electrically insulate the upper electrode layer **50** and the target material layer **30** from each other. The lower insulation layer **45** and the upper insulation layer **55** may each include an insulating material. For example, each of the lower insulation layer **45** and the upper insulation layer **55** may include a hexagonal boron nitride (h-BN), but is not limited thereto. In one example, each of the lower insulation layer **45** and the upper insulation layer **55** may include at least one of a monocrystalline material and an amorphous material, but is not limited thereto. The lower insulation layer **45** and the upper insulation layer **55** may include the same material or may include different materials.

(18) The lower insulation layer **45** and the upper insulation layer **55** may have a thickness t_3 and a thickness t_5 , respectively, each of which is, for example, greater than about 0 nm and less than or equal to about 300 nm. As each of the lower insulation layer **45** and the upper insulation layer **55** has a thin thickness of about 300 nm or less, the electron beam of the microscope may pass through the lower insulation layer **45** and the upper insulation layer **55** in the analysis method to be described later.

(19) The wiring pattern **60** may be electrically connected to each of the lower electrode layer **40** and the upper electrode layer **50**. In one example, the wiring pattern **60** may be disposed on the lower plate **10** (e.g., a portion of the lower plate **10**, which is not covered by the upper plate **20**), but is not limited thereto. In one example, the wiring pattern **60** may be electrically connected to

each of the lower electrode layer **40** and the upper electrode layer **50** through a connection part **70**, but is not limited thereto. In another example, the wiring pattern **60** may be in direct contact with and electrically connected to each of the lower electrode layer **40** and the upper electrode layer **50**. The wiring pattern **60** may include a plurality of conductive lines. The wiring pattern **60** and the connection part **70** may each include a conductive material.

(20) A voltage may be applied to the wiring pattern **60** to generate a potential difference between the upper electrode layer **50** and the wiring pattern **60** and consequently, an electric field may be applied to the target material layer **30**. In one example, a polarization state in the target material layer **30** may be changed by the electric field and accordingly, a domain structure of the target material layer **30** may be changed. Changes in domain structure of the target material layer **30** according to the electric field may be observed in real time through the analysis method to be described later.

(21) According to an embodiment of the inventive concept, when the specimen **1** is observed through the analysis method to be described later, the domain structure of the target material layer **30** may be analyzed even though the target material layer **30** is disposed inside a stacked structure of the specimen **1**. In other words, the domain structure of the target material layer **30** on an x-y plane may be analyzed even though the target material layer **30** is provided in the specimen **1** stacked in a z direction. Here, the z direction is a direction crossing (for example, perpendicular to) the x-y plane. Moreover, it is not required to cut the target material layer **30** in an x-z plane or y-z plane in order to observe changes in structure of the target material layer **30**. Consequently, the target material layer **30** may be analyzed using a non-destructive method in an extending direction of the x-y plane crossing a stacked direction (i.e., the z direction).

(22) Referring to FIG. 3B, the specimen **1** may include the lower insulation layer **45** and the upper insulation layer **55** in FIG. 3A. That is, the lower electrode layer **40** may be in contact with a bottom surface of the target material layer **30**, and the upper electrode layer **50** may be in contact with a top surface of the target material layer **30**. Although not illustrated, the specimen **1** may include only one of the lower insulation layer **45** and the upper insulation layer **55** in FIG. 3A.

(23) FIGS. 4 to 7 are views illustrating a specimen according to an embodiment of the inventive concept. FIGS. 4 and 6 are plan views of a specimen according to an embodiment of the inventive concept. FIGS. 5 and 7 are cross-sectional views corresponding to lines A-A' in FIGS. 4 and 6, respectively. The contents in common with the contents described with reference to FIGS. 1 to 3B will be omitted to avoid redundancy and the description will be focused on differences.

(24) Referring to FIGS. 4 and 5, an upper plate **20** may include an upper opening portion **22** passing therethrough. The upper opening portion **22** may be an empty space extending from a top surface to a bottom surface of the upper plate **20**, and may be provided in plurality. The upper opening portion **22** may vertically overlap a lower opening portion **12** and a target material layer **30**. For example, the upper opening portion **22** may expose a bottom surface of a lower electrode layer **40** to the outside.

(25) In the analysis method to be described later, an electron beam may pass through the upper plate **20**, and may pass through, for example, the upper opening portion **22** of the upper plate **20**. As the upper opening portion **22** is disposed in a path of the electron beam, reflection or diffraction of the electron beam by the upper plate **20** may be minimized. Consequently, an image of the target material layer **30** to be analyzed may be more easily obtained during the observation using a microscope.

(26) Referring to FIGS. 6 and 7, the target material layer **30** may have a portion vertically overlapping an upper electrode layer **50**. The target material layer **30** may have the other portion vertically non-overlapping the upper electrode layer **50**. For example, the target material layer **30** may have a top surface, of which a portion is covered by the upper electrode layer **50**, but is not limited thereto. An upper insulation layer **55** may be interposed between the upper electrode layer **50** and the target material layer **30**. In one example, the entire area of the upper insulation layer **55**

may be interposed between the upper electrode layer **50** and the target material layer **30**. In another example, although not illustrated, the upper insulation layer **55** may have a portion, which is interposed between the upper electrode layer **50** and the target material layer **30**, and the other portion which is not interposed between the upper electrode layer **50** and the target material layer **30**.

(27) In the analysis method to be described later, the electron beam may pass through the target material layer **30**. In one example, the electron beam may pass through a region of the target material layer **30**, which vertically non-overlaps the upper electrode layer **50**. Accordingly, reflection or diffraction of the electron beam by the upper electrode layer **50** may be minimized. Consequently, the image of the target material layer **30** to be analyzed may be more easily obtained during the observation using the microscope.

(28) However, an embodiment of the inventive concept is not limited to each of the embodiments described above. An embodiment of the inventive concept may include embodiments, each of which is a combination of some or all of the characteristics of the embodiments described with reference to FIGS. **1** to **7**.

(29) FIG. **8** is a flowchart for explaining an analysis method according to an embodiment of the inventive concept. FIG. **9** is a schematic diagram of a microscope for explaining an analysis method according to an embodiment of the inventive concept. FIG. **10** is a flowchart for explaining an analysis method according to an embodiment of the inventive concept. Hereinafter, an analysis method of observing, through a microscope, the specimen described with reference to FIGS. **1** to **7**. The contents in common with the contents described above will be omitted to avoid redundancy and the description will be focused on differences.

(30) Referring to FIGS. **8** and **9**, a specimen **1** may be disposed in a microscope (**S10**). The specimen **1** may be substantially the same as the specimen **1** described with reference to FIGS. **1** to **7**. The microscope may include an electron gun **2**, condenser lenses **3** and **4**, an objective lens **5**, a focal plane **6**, and an image screen **7**.

(31) The electron gun **2** may generate an electron beam, and the electron beam may pass through the specimen **1** (**S20**). In more detail, a voltage may be applied to the electron gun **2** to accelerate an electron, and an initial electron beam IE may be generated. The voltage applied to the electron gun **2** may be about 2 MV or less. The initial electron beam IE generated from the electron gun **2** may be directed towards the specimen **1** through the condenser lenses **3** and **4**. The condenser lenses **3** and **4** may collect the initial electron beam IE so that the initial electron beam IE is directed towards the specimen **1**.

(32) The initial electron beam IE may pass through layers of the specimen **1** in sequence. In one example, when the specimen **1** in FIG. **3A** is provided, the initial electron beam IE may pass through the upper electrode layer **50**, the upper insulation layer **55**, the target material layer **30**, the lower insulation layer **45**, the lower electrode layer **40**, the upper plate **20**, and the lower plate **10** in sequence. Here, the initial electron beam IE may pass through the lower opening portion **12** of the lower plate **10**. In another example, when the specimen **1** in FIG. **3B** is provided, the initial electron beam IE may pass through the upper electrode layer **50**, the target material layer **30**, the lower electrode layer **40**, the upper plate **20**, and the lower plate **10** in sequence. In still another example, when the specimen **1** in FIG. **7** is provided, the initial electron beam IE may pass through the target material layer **30**, the lower insulation layer **45**, the lower electrode layer **40**, the upper plate **20**, and the lower plate **10** in sequence. Here, the initial electron beam IE may pass through the upper opening portion **22** of the upper plate **20**.

(33) The initial electron beam IE may be diffracted while passing through the specimen **1**. The initial electron beam IE may be diffracted by respective materials included in the layers of the specimen. In one example, at least a portion of the initial electron beam IE may be diffracted by the respective materials included in the layers of the specimen. The initial electron beam IE passes through the specimen **1** and then, the at least a portion of the passed electron beam may be divided

into a plurality of diffracted electron beams DE1, DE2 and DE3 according to the respective materials of the layers in the specimen **1**, which cause diffraction. The number of the diffracted electron beams DE1, DE2 and DE3 is not limited, but the diffracted electron beams DE1, DE2 and DE3 will be defined and described as first to third diffracted electron beams DE1, DE2 and DE3 for convenience of explanation. In one example, the first diffracted electron beam DE1 may refer to electron beams that are diffracted by the target material layer **30** in the same direction. In another example, the second diffracted electron beam DE2 may refer to electron beams that are diffracted by a layer (e.g., the lower electrode layer **40**) other than the target material layer **30** in the same direction, and the direction in which the second diffracted electron beam DE2 is diffracted may be different from the direction in which the first diffracted electron beam DE1 is diffracted. In still another example, the third diffracted electron beam DE3 may refer to electron beams that are diffracted by a layer (e.g., the upper electrode layer **50**) other than the target material layer **30** in the same direction, and the direction in which the third diffracted electron beam DE3 is diffracted may be different from the direction in which each of the first and second diffracted electron beams DE1 and DE2 is diffracted. When the target material layer **30** is intended to be observed, an analysis of the first diffracted electron beam DE1 is required. Accordingly, it may require an operation of filtering the first and second diffracted electron beams DE1 and DE2 to observe the target material layer **30**.

(34) Thereafter, analysis information of the target material layer **30** may be obtained from the diffracted electron beams DE1, DE2 and DE3 of the passed electron beam (S**30**). For example, a filtering operation may be performed on the diffracted electron beams DE1, DE2 and DE3.

(35) In one example, in more detail, the objective lens **5** may collect the first to third diffracted electron beams DE1, DE2 and DE3 on the same regions of the focal plane **6**, respectively. For example, the electron beams constituting the first diffracted electron beam DE1 may be collected on one region of the focal plane **6**. Likewise, the electron beams constituting the second diffracted electron beams DE2 may be collected on another region of the focal plane **6**, and the electron beams constituting the third diffracted electron beams DE3 may be collected on still another region of the focal plane **6**.

(36) The focal plane **6** may include a diffraction opening portion **6a**, and the diffraction opening portion **6a** may be provided in plurality. Here, the first diffracted electron beam DE1 requiring the analysis may be collected in the diffraction opening portion **6a** of the focal plane **6**. The first diffracted electron beam DE1 may pass through the focal plane **6** via the diffraction opening portion **6a**. Each of the second and third diffracted electron beams DE2 and DE3 may be collected on a region other than the diffraction opening portion **6a** of the focal plane **6**. The second and third diffracted electron beams DE2 and DE3 may fail to pass through the focal plane **6**. Accordingly, only the first diffracted electron beam DE1 of the plurality of diffracted electron beams DE1, DE2 and DE3 may pass through the focal plane **6** toward the image screen **7**. The information of the target material layer **30** may be analyzed based on a diffraction pattern of the first diffracted electron beam DE1, which is formed on the image screen **7**.

(37) However, an embodiment of the inventive concept is not limited to the filing method above, and various filtering methods may be used unrestrictedly within a range in which those skilled in the art could easily modify the filing methods.

(38) Referring to FIGS. **9** and **10**, emitting an electron beam (S**20**) and obtaining analysis information (S**30**) may be repeatedly performed on one specimen **1**. Accordingly, the analysis information of the target material layer **30** may be obtained multiple times. For example, applying a voltage to the specimen **1** (e.g., the lower electrode layer **40** and the upper electrode layer **50**) (S**40**) may be further performed when repeating the emitting of the electron beam (S**20**) and the obtaining of the analysis information (S**30**).

(39) In one example, the voltage may be continuously applied to each of the lower electrode layer **40** and the upper electrode layer **50** of the specimen **1** when repeating the emitting of the electron

beam (S20) and the obtaining of the analysis information (S30). The voltage applied to each of the lower electrode layer 40 and the upper electrode layer 50 may change in magnitude and direction according to time. Accordingly, an electric field formed in each of the lower electrode layer 40 and the upper electrode layer 50 may cause continuous changes in domain structure of the target material layer 30, and the changes in domain structure of the target material layer 30 may be analyzed in real time.

(40) In another example, the voltage may be discontinuously applied to each of the lower electrode layer 40 and the upper electrode layer 50 of the specimen 1 when repeating the emitting of the electron beam (S20) and the obtaining of the analysis information (S30). For example, the voltage may be temporarily applied to each of the lower electrode layer 40 and the upper electrode layer 50 after the obtaining of the analysis information (S30), and the voltage may be removed before the electron beam is re-emitted (S20). Accordingly, an electric field formed in each of the lower electrode layer 40 and the upper electrode layer 50 may cause changes in domain structure of the target material layer 30, and the changes in domain structure of the target material layer 30 may be analyzed.

(41) According to an embodiment of the inventive concept, when the electric field is generated in the z direction, the changes in domain structure of the target material layer 30 on the x-y plane may be analyzed in real time. Consequently, it may be easily to analyze the real-time structural change, etc., under the actual driving environment of semiconductor devices, etc.

(42) According to an embodiment of the inventive concept, in the microscope specimen having the stacked structure, the target material layer disposed in the stacked structure of the specimen may be analyzed using the non-destructive method. When the electric field is formed with respect to the target material layer in the stacked direction, the changes in the target material layer in the extending direction of the plane crossing the stacked direction may be analyzed in real time. Consequently, it may be easy to analyze the real-time structural changes, etc., under the actual driving environment of semiconductor devices, etc.

(43) Although the embodiments of the present invention have been described, it is understood that the present invention should not be limited to these embodiments but various changes and modifications can be made by one ordinary skilled in the art within the spirit and scope of the present invention as hereinafter claimed.

Claims

1. A microscopic specimen comprising: a lower plate including a lower opening portion; an upper plate configured to cover the lower opening portion; a target material layer on the upper plate; a lower electrode layer between the upper plate and the target material layer; an upper electrode layer on the target material layer; and a wiring pattern electrically connected to each of the upper electrode layer and the lower electrode layer.
2. The microscopic specimen of claim 1, wherein the target material layer vertically overlaps the lower opening portion.
3. The microscopic specimen of claim 1, wherein the upper plate comprises an upper opening portion, wherein the target material layer vertically overlaps the upper opening portion.
4. The microscopic specimen of claim 1, wherein at least a portion of the upper electrode layer vertically overlaps the target material layer.
5. The microscopic specimen of claim 1, wherein the upper plate has a thickness that is greater than about 0 nm and less than or equal to about 300 nm.
6. The microscopic specimen of claim 1, wherein the target material layer comprises at least one of a chalcogenide, a metal oxide, a nitride, graphene, and graphite.
7. The microscopic specimen of claim 1, wherein the target material layer has a thickness that is greater than about 0 nm and less than or equal to about 300 nm.

8. The microscopic specimen of claim 1, wherein each of the upper electrode layer and the lower electrode layer has a thickness that is greater than about 0 nm and less than or equal to about 300 nm.
9. The microscopic specimen of claim 1, wherein each of the lower electrode layer and the upper electrode layer comprises at least one of a monocrystalline material and an amorphous material.
10. The microscopic specimen of claim 1, further comprising at least one of a lower insulation layer and an upper insulation layer, wherein the lower insulation layer is interposed between the target material layer and the lower electrode layer, and the upper insulation layer is interposed between the target material layer and the upper electrode layer.
11. The microscopic specimen of claim 10, wherein each of the lower insulation layer and the upper insulation layer comprises at least one of a monocrystalline material and an amorphous material.
12. An analysis method comprising: a process (a) of disposing a specimen in a microscope; a process (b) of emitting an electron beam passing through the specimen; and a process (c) of obtaining analysis information from a diffracted electron beam of the passed electron beam, wherein the specimen comprises: a lower plate including a lower opening portion; an upper plate configured to cover the lower opening portion; a target material layer on the upper plate; and a lower electrode layer between the upper plate and the target material layer, wherein, in the process (b), the electron beam passes through the target material layer, the lower electrode layer, the upper plate, and the lower plate in sequence.
13. The analysis method of claim 12, wherein, in the process (b), the electron beam passes through the lower opening portion of the lower plate.
14. The analysis method of claim 12, wherein the upper plate comprises an upper opening portion, wherein, in the process (b), the electron beam passes through the upper opening portion of the upper plate.
15. The analysis method of claim 12, wherein the specimen further comprises an upper electrode layer on the target material layer, wherein at least a portion of the upper electrode layer vertically overlaps the target material layer.
16. The analysis method of claim 15, wherein, in the process (b), the electron beam further passes through the upper electrode layer.
17. The analysis method of claim 12, wherein the process (b) and the process (c) are alternately and repeatedly performed.
18. The analysis method of claim 17, further comprising a process (d) of applying a voltage to the lower electrode layer, wherein, in the process (d), the voltage is continuously applied while the process (b) and the process (c) are repeatedly performed.
19. The analysis method of claim 17, further comprising a process (d) of applying a voltage to the lower electrode layer, wherein the process (d) is performed after performing the process (c) and before reperforming the process (b).
20. The analysis method of claim 12, wherein the process (b) comprises accelerating an electron by a voltage of about 2 MV or less to generate the electron beam.
-