

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12408324
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Lee; Yongjin et al.

Semiconductor memory device

Abstract

A semiconductor memory device includes a substrate, a conductive line extending in a first horizontal direction above the substrate, an isolation insulating layer including a channel trench extending in a second horizontal direction intersecting with the first horizontal direction and extending from an upper surface to a lower surface of the isolation insulating layer, above the conductive line, a channel structure disposed above the conductive line, a gate electrode extending in the second horizontal direction, in the channel trench, a capacitor structure above the isolation insulating layer, and a contact structure interposed between the channel structure and the capacitor structure, wherein the channel structure includes an amorphous oxide semiconductor layer disposed in the channel trench above the conductive line, and an upper crystalline oxide semiconductor layer interposed between the amorphous oxide semiconductor layer and the contact structure.

Inventors: Lee; Yongjin (Hwaseong-si, KR), Kim; Yongseok (Suwon-si, KR), Ryu; Mintae (Hwaseong-si, KR), Ryu; Huije (Suwon-si, KR), Yoo; Sungwon (Hwaseong-si, KR), Lee; Wonsok (Suwon-si, KR), Cho; Minhee (Suwon-si, KR)

Applicant: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Family ID: 87910237

Assignee: SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)

Appl. No.: 18/081905

Filed: December 15, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230292490 A1	Sep. 14, 2023

Foreign Application Priority Data

KR	10-2022-0030326	Mar. 10, 2022
----	-----------------	---------------

Publication Classification

Int. Cl.: H10B12/00 (20230101)

U.S. Cl.:

CPC H10B12/315 (20230201); H10B12/482 (20230201);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8614479	12/2012	Weng et al.	N/A	N/A
9246013	12/2015	Ahmed	N/A	N/A
9287408	12/2015	Yamazaki et al.	N/A	N/A
11139396	12/2020	Karda et al.	N/A	N/A
11887986	12/2023	Yoo	N/A	H10D 87/00
2012/0248434	12/2011	Kato	257/532	H10B 12/315
2013/0069132	12/2012	Atsumi et al.	N/A	N/A
2016/0064525	12/2015	Yamazaki et al.	N/A	N/A
2017/0125436	12/2016	Sharangpani	N/A	H01L 21/02178
2020/0098930	12/2019	Le et al.	N/A	N/A
2020/0111800	12/2019	Ramaswamy	N/A	H10B 12/033
2020/0111908	12/2019	Sills et al.	N/A	N/A
2020/0111917	12/2019	Ramaswamy et al.	N/A	N/A
2022/0037504	12/2021	Sills	N/A	H10B 53/10

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
114664830	12/2021	CN	G11C 11/4023
102247029	12/2020	KR	N/A

OTHER PUBLICATIONS

First Office Action issued Dec. 22, 2023 for corresponding TW Patent Application No. 112104592. cited by applicant

Primary Examiner: Page; Steven M

Attorney, Agent or Firm: Muir Patent Law, PLLC

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S)

(1) This application is based on and claims priority under 35 U.S.C. § 119 to Korean Patent Application No. 10-2022-0030326, filed on Mar. 10, 2022, in the Korean Intellectual Property Office, the disclosure of which is incorporated by reference herein in its entirety.

BACKGROUND

(2) The inventive concept relates to a semiconductor memory device. More particularly, the inventive concept relates to a semiconductor memory device including an oxide semiconductor.

(3) As semiconductor memory devices are increasingly highly integrated, a control of a leakage current characteristic of a semiconductor memory device becomes more important. In order to reduce the leakage current of the semiconductor memory device, a channel layer including an oxide semiconductor material has been studied. The oxide semiconductor material has an on-current similar to that of silicon (Si) and high bandgap energy and thus has an excellent leakage current characteristic.

SUMMARY

(4) The inventive concept provides a semiconductor memory device with improved performance and reliability due to improved electrical characteristics.

(5) According to an aspect of the inventive concept, there is provided a semiconductor memory including a substrate, a conductive line extending in a first horizontal direction above the substrate, an isolation insulating layer including a channel trench extending in a second horizontal direction intersecting the first horizontal direction and extending from an upper surface to a lower surface of the isolation insulating layer, above the conductive line, a channel structure disposed above the conductive line, a gate electrode extending in the second horizontal direction, in the channel trench, a capacitor structure above the isolation insulating layer, and a contact structure interposed between the channel structure and the capacitor structure. The channel structure includes an amorphous oxide semiconductor layer disposed in the channel trench above the conductive line, and an upper crystalline oxide semiconductor layer interposed between the amorphous oxide semiconductor layer and the contact structure.

(6) According to another aspect of the inventive concept, there is provided a semiconductor memory including a substrate, a conductive line extending in a first horizontal direction above the substrate, an isolation insulating layer including a channel trench extending in a second horizontal direction intersecting the first horizontal direction and extending from an upper surface to a lower surface of the isolation insulating layer, above the conductive line, a channel structure disposed above the conductive line, a gate electrode extending in the second horizontal direction, in the channel trench, a gate dielectric layer interposed between the channel structure and the gate electrode, in the channel trench, a capacitor structure above the isolation insulating layer, and a contact structure interposed between the channel structure and the capacitor structure. The channel structure includes a lower crystalline oxide semiconductor layer extending in the first horizontal direction above the conductive line, an amorphous oxide semiconductor layer disposed in the channel trench above the lower crystalline oxide semiconductor layer, and an upper crystalline oxide semiconductor layer interposed between the amorphous oxide semiconductor layer and the contact structure.

(7) According to another aspect of the inventive concept, there is provided a semiconductor memory including a substrate, a conductive line extending in a first horizontal direction above the substrate, an isolation insulating layer including a channel trench extending in a second horizontal direction intersecting the first horizontal direction and extending from an upper surface to a lower surface of the isolation insulating layer, above the conductive line, a channel structure disposed

above the conductive line, a gate electrode including a first gate electrode and a second gate electrode spaced apart from each other in the first horizontal direction to face each other in the channel trench and extending in the second horizontal direction, a gate dielectric layer interposed between the channel structure and the gate electrode, in the channel trench, a barrier insulating layer disposed between the first gate electrode and the second gate electrode, a gap-fill insulating layer formed on the barrier insulating layer and filling a region between the first gate electrode and the second gate electrode, a gate capping pattern covering upper surfaces of the gate electrode, the barrier insulating layer, and the gap-fill insulating layer, a capacitor structure above the isolation insulating layer and the gate capping pattern, and a contact structure interposed between the channel structure and the capacitor structure. The channel structure includes a lower crystalline oxide semiconductor layer having a lower surface covering an upper surface of the conductive line and extending in the first horizontal direction, an amorphous oxide semiconductor layer disposed in the channel trench above the lower crystalline oxide semiconductor layer and having a U-shaped vertical cross-section in the first horizontal direction, and first and second upper crystalline oxide semiconductor layers spaced apart from each other and interposed between the amorphous oxide semiconductor layer and the contact structure. The first upper crystalline oxide semiconductor is disposed above a first upper surface of the amorphous oxide semiconductor layer, and the second upper crystalline oxide semiconductor is disposed above a second upper surface of the amorphous oxide semiconductor layer.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) Embodiments of the inventive concept will be more clearly understood from the following detailed description taken in conjunction with the accompanying drawings in which:
- (2) FIG. 1 is a layout diagram illustrating a semiconductor memory device according to example embodiments;
- (3) FIG. 2A is a cross-sectional view taken along line A-A' of FIG. 1 according to example embodiments;
- (4) FIG. 2B is a cross-sectional view taken along line B-B' of FIG. 1 according to example embodiments;
- (5) FIGS. 3A, 3B, 4A, 4B, 5A, 5B, 6A, 6B, 7A, 7B, 8A, 8B, 9A, 9B, 10A, 10B, 11A, 11B, 12A, 12B, 13A, 13B, 14A, 14B, 15A, 15B, 16, 17, 18A, 18B, 19A, 19B, 20A, and 20B are cross-sectional views illustrating a method of manufacturing a semiconductor memory device, according to example embodiments;
- (6) FIG. 21 is a cross-sectional view illustrating a semiconductor memory device according to example embodiments;
- (7) FIGS. 22 to 26 are cross-sectional views illustrating a method of manufacturing a semiconductor memory device, according to example embodiments; and
- (8) FIGS. 27 to 30 are cross-sectional views illustrating semiconductor memory devices according to example embodiments.

DETAILED DESCRIPTION OF THE EMBODIMENTS

- (9) FIG. 1 is a layout diagram illustrating a semiconductor memory device 1 according to example embodiments, FIG. 2A is a cross-sectional view taken along line A-A' of FIG. 1 according to example embodiments, and FIG. 2B is a cross-sectional view taken along line B-B' of FIG. 1 according to example embodiments.
- (10) Referring to FIGS. 1, 2A, and 2B together, the semiconductor memory device 1 may include a substrate 100, an interlayer insulating layer 110, a conductive line 120 (bit line BL), an isolation insulating layer 115, a channel structure 10, a gate dielectric layer 140, a gate electrode 150 (word

line WL), a contact structure **170**, and a capacitor structure **190**.

(11) The substrate **100** may include a semiconductor material, such as a group IV semiconductor material, a group III-V semiconductor material, or a group II-VI semiconductor material. The group IV semiconductor material may include, for example, silicon (Si), germanium (Ge), or silicon-germanium (Si—Ge). The group III-V semiconductor material may include, for example, gallium arsenide (GaAs), indium phosphate (InP), gallium phosphate (GaP), indium arsenide (InAs), indium antimony (InSb), or indium gallium arsenide (InGaAs). The group II-VI semiconductor material may include, for example, zinc telluride (ZnTe) or cadmium sulfide (CdS). The substrate **100** may be a bulk wafer or an epitaxial layer. The substrate **100** may have a structure in which a base substrate and an epitaxial layer are stacked, but is not limited thereto.

(12) In some embodiments, logic cells constituting a core circuit, such as a sense amplifier, and electrically connected to the conductive line **120** may be disposed on the substrate **100** to overlap the channel structure **10**, the gate electrode **150**, and the capacitor structure **190** in a vertical direction (Z direction), but are not limited thereto. In some other embodiments, the logic cells constituting the core circuit may be disposed on a part of the substrate **100** that does not overlap the channel structure **10**, the gate electrode **150**, and the capacitor structure **190** in the vertical direction (Z direction).

(13) A plurality of conductive lines **120** may be formed above the substrate **100**. For example, the interlayer insulating layer **110** may be formed above the substrate **100**, and the plurality of conductive lines **120** may be disposed on the interlayer insulating layer **110**. For example, the interlayer insulating layer **110** may cover a lower surface and side surfaces of each of the plurality of conductive lines **120**. The plurality of conductive lines **120** may be spaced apart from each other at equal intervals in a first horizontal direction (X direction), and may each extend in a second horizontal direction (Y direction) crossing the first horizontal direction (X direction). Each of the plurality of conductive lines **120** may extend long in the second horizontal direction (Y direction). The first horizontal direction (X direction) and the second horizontal direction (Y direction) may be orthogonal to each other.

(14) The interlayer insulating layer **110** may be formed to cover side surfaces of the plurality of conductive lines **120** and to fill spaces between the plurality of conductive lines **120**. The interlayer insulating layer **110** may be a single layer including one type of insulating material, or a multilayer including a combination of several types of insulating materials. For example, the interlayer insulating layer **110** may be configured as a multi-layer including at least one layer covering the lower surface of the conductive line **120** and at a lower vertical level than that of the conductive line **120**, and at least one layer covering the side surfaces of the conductive line **120** and at a higher vertical level than that of the lower surface of the conductive line **120**. The conductive line **120** may function as a bit line BL of the semiconductor memory device **1**.

(15) The conductive line **120** may include doped polysilicon, metal, conductive metal nitride, conductive metal silicide, conductive metal oxide, or a combination thereof. For example, the conductive line **120** may include doped polysilicon, Al, Cu, Ti, Ta, Ru, W, Mo, Pt, Ni, Co, TiN, TaN, WN, WSi, NbN, TiAl, TiAlN, TiSi, TiSiN, TaSi, TaSiN, RuTiN, NiSi, CoSi, IrO.sub.x, RuO.sub.x, or a combination thereof, but is not limited thereto. Alternatively, the conductive line **120** may include a 2D semiconductor material. The 2D semiconductor material may include, for example, graphene, carbon nanotube, or a combination thereof. The conductive line **120** may include a single layer or a multi-layer of the described conductive materials above.

(16) The channel structure **10** may be disposed above the conductive line **120**. The channel structure **10** may include a quaternary oxide semiconductor material including a first metal element, a second metal element, and a third metal element that is different from the first metal element and the second metal element. The channel structure **10** may include a lower crystalline oxide semiconductor layer **12**, an amorphous oxide semiconductor layer **14**, and an upper crystalline oxide semiconductor layer **16**. The lower crystalline oxide semiconductor layer **12** may

be in contact with a lower surface of the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** may be in contact with an upper surface of the amorphous oxide semiconductor layer **14**. It will be understood that when an element is referred to as being “connected” or “coupled” to or “on” another element, it can be directly connected or coupled to or on the other element or intervening elements may be present. In contrast, when an element is referred to as being “directly connected” or “directly coupled” to another element, or as “contacting” or “in contact with” another element, there are no intervening elements present at the point of contact.

(17) Each of the lower crystalline oxide semiconductor layer **12**, the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** may include a binary oxide semiconductor material including a first metal element, a ternary oxide semiconductor material including a first metal element and a second metal element that are different from each other, or a quaternary oxide semiconductor material including a first metal element, a second metal element, and a third metal element that is different from the first metal element and the second metal element. The lower crystalline oxide semiconductor layer **12** may include a crystalline binary oxide semiconductor material, a crystalline ternary oxide semiconductor material, or a crystalline quaternary oxide semiconductor material. The amorphous oxide semiconductor layer **14** may include an amorphous binary oxide semiconductor material, an amorphous ternary oxide semiconductor material, or an amorphous quaternary oxide semiconductor material. The upper crystalline oxide semiconductor layer **16** may include a crystalline binary oxide semiconductor material, a crystalline ternary oxide semiconductor material, or a crystalline quaternary oxide semiconductor material.

(18) The binary or ternary oxide semiconductor material may be one of, for example, ZnO (zinc oxide, Zn_xO), GaO (gallium oxide, Ga_xO), TO (tin oxide, Sn_xO), ZnON (zinc oxynitride, Zn.sub.xOyN), IZO (indium zinc oxide, In.sub.xZn.yO), GZO (gallium zinc oxide, Ga.sub.xZn.sub.yO), TZO (tin zinc oxide, Sn.sub.xZn.sub.yO), and TGO (tin gallium oxide, $\text{Sn}_x\text{Ga}_y\text{O}$), but is not limited thereto. The quaternary oxide semiconductor material may be any one of, for example, IGZO (indium gallium zinc oxide, $\text{In.sub.xGa.sub.yZn.sub.zO}$), IGSO (indium gallium silicon oxide, $\text{In.sub.xGa.sub.ySi.sub.zO}$), ITZO (indium tin zinc oxide, $\text{In.sub.xSn.sub.yZn.sub.zO}$), ITGO (indium tin gallium oxide, $\text{In.sub.xSn.sub.yGa.sub.zO}$), ZZTO (zirconium zinc tin oxide, $\text{Zr.sub.xZn.sub.ySn.sub.zO}$), HIZO (hafnium indium zinc oxide, $\text{Hf.sub.xIn.sub.yZn.sub.zO}$), GZTO (gallium zinc tin oxide, $\text{Ga.sub.xZn.sub.ySn.sub.zO}$), AZTO (aluminium zinc tin oxide, $\text{Al.sub.xZn.sub.ySn.sub.zO}$), and YGZO (ytterbium gallium zinc oxide, $\text{Yb.sub.xGa.sub.yZn.sub.zO}$), but is not limited thereto.

(19) In some embodiments, each of the lower crystalline oxide semiconductor layer **12**, the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** may include a quaternary oxide semiconductor material. For example, the lower crystalline oxide semiconductor layer **12** may include at least one of single crystalline IGZO (IGZO), polycrystalline IGZO, spinel IGZO, or c-axis aligned crystalline IGZO (CAAC IGZO). For example, the amorphous oxide semiconductor layer **14** may include amorphous IGZO (IGZO). For example, the upper crystalline oxide semiconductor layer **16** may include at least one of monocrystalline or single crystalline IGZO, polycrystalline IGZO, spinel IGZO, or CAAC IGZO.

(20) The lower crystalline oxide semiconductor layer **12** may be between the conductive line **120** and the amorphous oxide semiconductor layer **14**. The lower crystalline oxide semiconductor layer **12** may have a thickness of several nm in the vertical direction (Z direction). For example, the lower crystalline oxide semiconductor layer **12** may have a thickness of about 5 nm to about 9 nm in the vertical direction (Z direction). The lower crystalline oxide semiconductor layer **12** may extend long in the second horizontal direction (Y direction). The lower crystalline oxide semiconductor layer **12** may include a plurality of lower crystalline oxide semiconductor layers **12** respectively corresponding to the plurality of conductive lines **120**. The plurality of lower

crystalline oxide semiconductor layers **12** may respectively cover upper surfaces of the plurality of corresponding conductive lines **120**. In some embodiments, the plurality of lower crystalline oxide semiconductor layers **12** may entirely and respectively cover upper surfaces of the plurality of corresponding conductive lines **120**. The plurality of lower crystalline oxide semiconductor layers **12** and the plurality of conductive lines **120**, which respectively correspond to one another, may overlap each other in the vertical direction (Z direction). For example, both sides of the plurality of lower crystalline oxide semiconductor layers **12** and both sides of the plurality of conductive lines **120**, which respectively correspond to one another, in the first horizontal direction (X direction) may be aligned in the vertical direction (Z direction). The plurality of lower crystalline oxide semiconductor layers **12** may each extend in the second horizontal direction (Y direction) and may be spaced apart from each other at equal intervals in the first horizontal direction (X direction). Side surfaces of the plurality of lower crystalline oxide semiconductor layers **12** may be covered by the interlayer insulating layer **110**. An upper surface of the interlayer insulating layer **110** and the upper surfaces of the plurality of lower crystalline oxide semiconductor layers **12** may be at the same vertical level to be coplanar with each other.

(21) The isolation insulating layer **115** may be disposed above the conductive line **120**. For example, the isolation insulating layer **115** may be disposed above the lower crystalline oxide semiconductor layer **12** covering the upper surface of the conductive line **120**. In some embodiments, a lower surface of the isolation insulating layer **115**, that is, the lower surface of the lower isolation insulating layer **115A**, may be in contact with the upper surface of the lower crystalline oxide semiconductor layer **12**. For example, the lower surface of the lower isolation insulating layer **115A** and the upper surface of the lower crystalline oxide semiconductor layer **12** may be positioned at the same vertical level.

(22) The isolation insulating layer **115** may have a channel trench **115t** extending long in the first horizontal direction (X direction). In some embodiments, the horizontal width of the channel trench **115t** may be several tens nm to several hundreds nm. For example, the horizontal width of the channel trench **115t** may be about 100 nm. The channel trench **115t** may extend from the upper surface to the lower surface of the isolation insulating layer **115**. For example, the isolation insulating layer **115** may include a plurality of isolation insulating layers **115** each extending in the first horizontal direction (X direction) and spaced apart from each other by the channel trench **115t**. The channel trench **115t** may expose at least a part of the lower crystalline oxide semiconductor layer **12**. For example, the upper surface of the lower crystalline oxide semiconductor layer **12** may be exposed on the bottom surface of the channel trench **115t**.

(23) The isolation insulating layer **115** may include at least one of, for example, silicon oxide, silicon oxynitride, silicon nitride, or a low-k material having a dielectric constant smaller than that of silicon oxide, but is not limited thereto. In some embodiments, the isolation insulating layer **115** may have a stack structure of a lower isolation insulating layer **115A** and an upper isolation insulating layer **115B**. In some embodiments, the lower isolation insulating layer **115A** may include nitride, and the upper isolation insulating layer **115B** may include oxide.

(24) The amorphous oxide semiconductor layer **14** may be disposed in the channel trench **115t** above the conductive line **120**. For example, the amorphous oxide semiconductor layer **14** may be disposed above the lower crystalline oxide semiconductor layer **12** covering the upper surface of the conductive line **120**. The lower crystalline oxide semiconductor layer **12** may be between the amorphous oxide semiconductor layer **14** and the conductive line **120**. The amorphous oxide semiconductor layer **14** may have a thickness of several tens nm in the vertical direction (Z direction), and may have a thickness of several nm in the second horizontal direction (Y direction). For example, the amorphous oxide semiconductor layer **14** may have a thickness of about 5 nm to about 9 nm in the second horizontal direction (Y direction).

(25) The amorphous oxide semiconductor layer **14** may be formed in the channel trench **115t**. For example, the amorphous oxide semiconductor layer **14** may extend along side surfaces and the

bottom surface of the channel trench **115t**. For example, the amorphous oxide semiconductor layer **14** may extend on a part of the isolation insulating layer **115** positioned on the side surfaces of the channel trench **115t** and a part of the lower crystalline oxide semiconductor layer **12** positioned on the bottom surface of the channel trench **115t**. The amorphous oxide semiconductor layer **14** may be electrically connected to the conductive line **120**. For example, the lower surface of the amorphous oxide semiconductor layer **14** extending along the lower surface of the channel trench **115t** may be in contact with the upper surface of the lower crystalline oxide semiconductor layer **12**.

(26) In some embodiments, a plurality of amorphous oxide semiconductor layers **14** spaced apart from each other may be disposed above the conductive line **120**. The plurality of amorphous oxide semiconductor layers **14** may be spaced apart from each other in the first horizontal direction (X direction) and the second horizontal direction (Y direction) to be arranged in a matrix form. For example, above one lower crystalline oxide semiconductor layer **12** covering the upper surface of one conductive line **120**, the plurality of amorphous oxide semiconductor layers **14** may be disposed to be spaced apart from each other in the second horizontal direction (Y direction). Each of the plurality of amorphous oxide semiconductor layers **14** may have a U-shaped vertical cross-section. For example, each of the plurality of amorphous oxide semiconductor layers **14** may have a U-shape in a cross-section (Y-Z plane) in the second horizontal direction (Y direction) and the vertical direction (Z direction).

(27) In the present specification, unless otherwise specified, the vertical cross-section is a vertical cross-section in an extension direction of the conductive line **120** and the lower crystalline oxide semiconductor layer **12**, that is, a vertical cross-section (Y-Z plane) in the second horizontal direction (Y direction).

(28) The upper crystalline oxide semiconductor layer **16** may be disposed above the amorphous oxide semiconductor layer **14**. For example, the upper crystalline oxide semiconductor layer **16** may be disposed above the uppermost surface of the amorphous oxide semiconductor layer **14**. The upper crystalline oxide semiconductor layer **16** may have a thickness of several nm in the vertical direction (Z direction). For example, the upper crystalline oxide semiconductor layer **16** may have a thickness of about 5 nm to about 9 nm in the vertical direction (Z direction). When the amorphous oxide semiconductor layer **14** has a U-shaped vertical cross-section, two upper crystalline oxide semiconductor layers **16** spaced apart from each other may be disposed above one amorphous oxide semiconductor layer **14**. For example, one upper crystalline oxide semiconductor layer **16** may be disposed above a first upper surface of the amorphous oxide semiconductor layer **14**, and another upper crystalline oxide semiconductor layer **16** may be disposed above a second upper surface of the amorphous oxide semiconductor layer **14**. For example, one amorphous oxide semiconductor layer **14** and two upper crystalline oxide semiconductor layers **16** may have the U-shaped vertical cross-section together.

(29) The lower surface of the upper crystalline oxide semiconductor layer **16** and the uppermost surface of the amorphous oxide semiconductor layer **14** may overlap and contact each other. The upper crystalline oxide semiconductor layer **16** may be positioned above a part of the lower crystalline oxide semiconductor layer **12** positioned on the side surface of the channel trench **115t**. For example, along the upper surface from the lower surface of the isolation insulating layer **115**, the amorphous oxide semiconductor layer **14** and the upper crystalline oxide semiconductor layer **16** may be arranged sequentially while contacting a part of the isolation insulating layer **115** positioned on the side surfaces of the channel trench **115t**. In some embodiments, the upper surface of the upper crystalline oxide semiconductor layer **16** may be positioned at a lower vertical level than that of an upper surface of the isolation insulating layer **115**. In some embodiments, the upper surface of the upper crystalline oxide semiconductor layer **16** may be positioned at a lower vertical level than that of the upper surface of the gate electrode **150**.

(30) The semiconductor memory device **1** may be a semiconductor memory device including a

vertical channel transistor (VCT). The VCT may refer to a structure in which a channel length of a channel layer, for example, the channel structure **10**, extends in the vertical direction (Z direction) perpendicular to the upper surface of the substrate **100**. For example, the channel structure **10** may include a first source/drain region and a second source/drain region that are arranged in the vertical direction (Z direction).

(31) The lower crystalline oxide semiconductor layer **12** of the channel structure **10** may function as a lower contact layer for reducing a contact resistance between the conductive line **120** and the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** of the channel structure **10** may function as an upper contact layer for reducing a contact resistance between the amorphous oxide semiconductor layer **14** and the contact structure **170**.

(32) In some embodiments, the amorphous oxide semiconductor layer **14** may include a first source/drain region and a second source/drain region that are arranged in the vertical direction (Z direction). For example, the lower portion of the amorphous oxide semiconductor layer **14** may function as the first source/drain region, and the upper portion of the amorphous oxide semiconductor layer **14** may function as the second source/drain region. A part of the amorphous oxide semiconductor layer **14** between the first source/drain region and the second source/drain region may function as a channel region.

(33) In some other embodiments, the lower crystalline oxide semiconductor layer **12** may function as the first source/drain region, the upper crystalline oxide semiconductor layer **16** may function as the second source/drain region, and the amorphous oxide semiconductor layer **14** may entirely function as a channel region.

(34) The gate dielectric layer **140** may be formed on the channel structure **10** in the channel trench **115t**. The gate dielectric layer **140** may be between the channel structure **10** and the gate electrode **150**. In some embodiments, the uppermost end of the gate dielectric layer **140** may be positioned at a higher vertical level than that of the uppermost end of the gate electrode **150**. The gate dielectric layer **140** may be disposed above the amorphous oxide semiconductor layer **14** and the upper crystalline oxide semiconductor layer **16**. For example, along inner surfaces of one amorphous oxide semiconductor layer **14** and two upper crystalline oxide semiconductor layers **16** that form the U-shaped vertical cross-section, two gate dielectric layers **140** having an L-shaped vertical cross-section, facing each other, and spaced apart from each other may be disposed. In some embodiments, the uppermost end of the gate dielectric layer **140** may extend in the vertical direction (Z direction) along inner surfaces of one amorphous oxide semiconductor layer **14** and two upper crystalline oxide semiconductor layers **16** that form the U-shaped vertical cross-section, so as to be positioned at a higher vertical level than that of the uppermost end of the upper crystalline oxide semiconductor layer **16**. The gate dielectric layer **140** may include at least one of, for example, silicon oxide, silicon oxynitride, silicon nitride, or a high-k material having a dielectric constant that is greater than that of silicon oxide, but is not limited thereto.

(35) The gate electrode **150** may be formed on the gate dielectric layer **140** in the channel trench **115t**. The gate electrode **150** may cover the gate dielectric layer **140** in the channel trench **115t** and extend in the vertical direction (Z direction). The gate electrode **150** may extend long in the first horizontal direction (X direction). The gate electrode **150** may include doped polysilicon, metal, conductive metal nitride, conductive metal silicide, conductive metal oxide, or a combination thereof. For example, the gate electrode **150** may include doped polysilicon, Al, Cu, Ti, Ta, Ru, W, Mo, Pt, Ni, Co, TiN, TaN, WN, NON, TiAl, TiAlN, TiSi, TiSiN, TaSi, TaSiN, RuTiN, NiSi, CoSi, IrOx, RuOx, or a combination thereof, but is not limited thereto.

(36) In some embodiments, the gate electrode **150** may include a first gate electrode **150A** and a second gate electrode **150B** that face each other in one channel trench **115t**. The first gate electrode **150A** and the second gate electrode **150B** may be spaced apart from each other in the second horizontal direction (Y direction) and may each extend long in the first horizontal direction (X direction). In one channel trench **115t**, two gate dielectric layers **140** may be disposed respectively

between the channel structure **10** and the first gate electrode **150A** and between the channel structure **10** and the second gate electrode **150B**. The gate dielectric layer **140** disposed between the channel structure **10** and the first gate electrode **150A** and the gate dielectric layer **140** disposed between the channel structure **10** and the second gate electrode **150B** may have the L-shaped vertical cross-section and may be spaced apart from each other facing each other. In this case, two transistor structures per one channel structure **10** may be implemented. For example, the first gate electrode **150A** may function as a first word line of the semiconductor memory device **1**, and the second gate electrode **150B** may function as a second word line of the semiconductor memory device **1**.

(37) In some embodiments, a barrier insulating layer **162** and a gap-fill insulating layer **164** may be formed between the first gate electrode **150A** and the second gate electrode **150B**. The first gate electrode **150A** and the second gate electrode **150B** may be separated from each other by the barrier insulating layer **162** and the gap-fill insulating layer **164**. The barrier insulating layer **162** may extend along, for example, the inner surface of the first gate electrode **150A**, the upper surface of the amorphous oxide semiconductor layer **14**, and the inner surface of the second gate electrode **150B** to have the U-shaped vertical cross-section. The gap-fill insulating layer **164** may be formed on the barrier insulating layer **162** to fill the inside of the U-shaped vertical cross-section of the barrier insulating layer **162**, and filled in a region between the first gate electrode **150A** and the second gate electrode **150B**.

(38) The barrier insulating layer **162** and the gap-fill insulating layer **164** may separate the gate electrode **150** into the first gate electrode **150A** and the second gate electrode **150B**, which are opposed to each other in one channel trench **115t** but may not separate the amorphous oxide semiconductor layer **14**. The barrier insulating layer **162** may be in contact with the amorphous oxide semiconductor layer **14** but may be not in contact with the lower crystalline oxide semiconductor layer **12**. For example, the lowermost surface of the barrier insulating layer **162** may be formed to be higher than the lowermost surface of the amorphous oxide semiconductor layer **14**.

(39) Each of the barrier insulating layer **162** and the gap-fill insulating layer **164** may include at least one of silicon oxide, silicon oxynitride, silicon nitride, or a combination thereof, but is not limited thereto. For example, the barrier insulating layer **162** may include silicon nitride, and the gap-fill insulating layer **164** may include silicon oxide.

(40) A gate capping pattern **166** may be formed above the gate electrode **150**. The gate capping pattern **166** may cover, for example, the upper surface of the gate electrode **150**, the upper surface of the barrier insulating layer **162**, and the upper surface of the gap-fill insulating layer **164**. The gate capping pattern **166** may include silicon nitride, but is not limited to. In some embodiments, the gate dielectric layer **140** may extend further away from the substrate **100** in the vertical direction (Z direction) to cover the side surfaces of the gate electrode **150** and the side surfaces of the gate capping pattern **166**. In some embodiments, the upper surface of the gate dielectric layer **140** and the upper surface of the gate capping pattern **166** may be positioned at the same vertical level to be coplanar with each other.

(41) The contact structure **170** may be formed above the channel structure **10**. For example, the contact structure **170** may be connected to the upper surface of the upper crystalline oxide semiconductor layer **16**. The contact structure **170** may extend between the isolation insulating layer **115** and the gate dielectric layer **140** from upper surfaces of the isolation insulating layer **115** and the gate capping pattern **166**. In some embodiments, the lowermost end of the contact structure **170** may be positioned at a lower vertical level than that of the lower surface of the gate electrode **150**. The contact structure **170** may connect the channel structure **10** to the capacitor structure **190**. The contact structure **170** may include at least one of, for example, a conductive material, such as metal, conductive metal nitride, conductive metal carbonitride, conductive metal carbide, metal silicide, a doped semiconductor material, conductive metal oxynitride, conductive metal oxide, or a two-dimensional (2D) material, but is not limited thereto.

(42) The contact structure **170** may include a plurality of contact structures **170** separated by an insulating structure **175**. The insulating structure **175** may have a plurality of recesses covering above the isolation insulating layer **115** and the gate capping pattern **166**, and through which the channel structure **10** is exposed in the bottom surface, and the plurality of contact structures **170** may be respectively filled in the plurality of recesses. The insulating structure **175** may include nitride. In FIGS. **2A** and **2B**, the upper surface of the insulating structure **175** and upper surfaces of the plurality of contact structures **170** are positioned at the same vertical level, but the inventive concept is not limited thereto. For example, the upper surface of the insulating structure **175** may be positioned at a higher level than those of the upper surfaces of the plurality of contact structures **170**.

(43) In FIGS. **2A** and **2B**, a lower surface of the insulating structure **175** is at the same vertical level as that of the upper surface of the isolation insulating layer **115** and the upper surface of the gate capping pattern **166**, but is not limited thereto. In some embodiments, the insulating structure **175** may extend into the isolation insulating layer **115** and the gate capping pattern **166** so that the lower surface of the insulating structure **175** is positioned at a lower vertical level than that of the upper surface of the isolation insulating layer **115** and the upper surface of the gate capping pattern **166**.

(44) In some embodiments, two contact structures **170** may be formed per one amorphous oxide semiconductor layer **14** in the second horizontal direction (Y direction). For example, the upper surface of the channel structure **10** adjacent to the first gate electrode **150A** may be connected to one contact structure **170**, and the upper surface of the channel structure **10** adjacent to the second gate electrode **150B** may be connected to another contact structure **170**.

(45) The contact structure **170** may cover the upper surface of the isolation insulating layer **115** and the gate capping pattern **166**, and may extend between the isolation insulating layer **115** and the gate dielectric layer **140** toward the substrate **100**.

(46) A support insulating layer **180** may be disposed above the plurality of contact structures **170** and the insulating structure **175**. The support insulating layer **180** may cover the plurality of contact structures **170** and the insulating structure **175**, and may have a plurality of holes through which the plurality of contact structures **170** are exposed in bottom surfaces. The support insulating layer **180** may include, for example, a silicon nitride layer or silicon boron nitride (SiBN).

(47) The plurality of capacitor structures **190** may be formed above the plurality of contact structures **170**. The plurality of capacitor structures **190** may be connected to upper surfaces of the plurality of corresponding contact structures **170**. The capacitor structure **190** may be controlled by the conductive line **120** and the gate electrode **150** to store data.

(48) The plurality of capacitor structures **190** may include a plurality of lower electrodes **192**, a capacitor dielectric layer **194**, and an upper electrode **196**. Each of the plurality of capacitor structures **190** may store electric charges in the capacitor dielectric layer **194** by using a potential difference generated between the lower electrode **192** and the upper electrode **196**.

(49) The plurality of lower electrodes **192** may be respectively connected to the plurality of contact structures **170**. For example, the plurality of lower electrodes **192** may be connected to the upper surface of the contact structure **170** exposed in the bottom surfaces of the plurality of holes of the support insulating layer **180**. In FIG. **2A**, the lower electrode **192** has only a pillar shape extending in the vertical direction (Z direction) from the upper surface of the contact structure **170**, but this is an example. In some other embodiments, the lower electrode **192** may have a cylinder shape extending in the vertical direction (Z direction) from the upper surface of the contact structure **170**. In some embodiments, the plurality of lower electrodes **192** may be arranged in a matrix form. In some other embodiments, the plurality of lower electrodes **192** may be arranged in a honeycomb shape. The lower electrode **192** may include silicon doped with impurities, metal, such as tungsten or copper, or a conductive metal compound such as titanium nitride.

(50) The capacitor dielectric layer **194** may be formed on the plurality of lower electrodes **192**. In some embodiments, the capacitor dielectric layer **194** may conformally extend along profiles of the

side surfaces and upper surfaces of the plurality of lower electrodes **192** and the upper surface of the support insulating layer **180**. The capacitor dielectric layer **194** may include, for example, TaO, TaAlO, TaON, AlO, AlSiO, HfO, HfSiO, ZrO, ZrSiO, TiO, TiAlO, BST ((Ba,Sr)TiO), STO(SrTiO), BTO(BaTiO), PZT(Pb(Zr,Ti)O), (Pb,La)(Zr,Ti)O, Ba(Zr,Ti)O, Sr(Zr,Ti)O, or a combination thereof.

(51) The upper electrode **196** may be formed on the capacitor dielectric layer **194**. The upper electrode **196** may include a metal material. For example, the upper electrode **196** may include W, Ru, RuO, Pt, PtO, Ir, IrO, SRO (SrRuO), BSRO ((Ba,Sr) RuO), CRO (CaRuO), BaRuO, La (Sr,Co) O, or a combination thereof. In some embodiments, the upper electrode **196** may further include at least one of a doped semiconductor material layer and an interface layer, in addition to a metal material, to have a stack structure thereof. The doped semiconductor material layer may include, for example, at least one of doped polysilicon and doped polycrystalline silicon germanium (SiGe). The main electrode layer may include a metal material. The interface layer may include, for example, at least one of a metal oxide, a metal nitride, a metal carbide, or a metal silicide. In FIG. 2A, the upper electrode **196** only fills the region between the adjacent lower electrodes **192**, but this is only an example. As another example, the upper electrode **196** may conformally extend along the profile of the capacitor dielectric layer **194**.

(52) The semiconductor memory device **1** according to the inventive concept may include the channel structure **10** including the lower crystalline oxide semiconductor layer **12** and the upper crystalline oxide semiconductor layer **16**. The lower crystalline oxide semiconductor layer **12** may reduce the contact resistance between the conductive line **120** and the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** may reduce the contact resistance between the amorphous oxide semiconductor layer **14** and the contact structure **170**.

(53) Accordingly, an electrical characteristic of the semiconductor memory device **1** may be improved, and thus, the performance and reliability of the semiconductor memory device **1** may be improved.

(54) FIGS. 3A, 3B, 4A, 4B, 5A, 5B, 6A, 6B, 7A, 7B, 8A, 8B, 9A, 9B, 10A, 10B, 11A, 11B, 12A, 12B, 13A, 13B, 14A, 14B, 15A, 15B, 16, 17, 18A, 18B, 19A, 19B, 20A, and 20B are cross-sectional views illustrating a method of manufacturing the semiconductor memory device **1**, according to example embodiments. Specifically, FIGS. 3A, 3B, 4A, 4B, 5A, 5B, 6A, 6B, 7A, 7B, 8A, 8B, 9A, 9B, 10A, 10B, 11A, 11B, 12A, 12B, 13A, 13B, 14A, 14B, 15A, 15B, 16, 17, 18A, 18B, 19A, 19B, 20A, and 20B are cross-sectional views illustrating the method of manufacturing the semiconductor memory device **1** shown in FIGS. 1, 2A, and 2B, FIGS. 3A, 4A, 5A, 6A, 7A, 8A, 9A, 10A, 11A, 12A, 13A, 14A, 15A, 16, 17, 18A, 19A, and 20A are cross-sectional views taken along a part corresponding to A-A' in FIG. 1, and FIGS. 3B, 4B, 5B, 6B, 7B, 8B, 9B, 10B, 11B, 12B, 13B, 14B, 15B, 18B, 19B, and 20B are cross-sectional views taken along a part corresponding to B-B' in FIG. 1.

(55) Referring to FIGS. 3A and 3B together, a conductive material layer **120P** is formed above the substrate **100**. The conductive material layer **120P** may be formed to include doped polysilicon, metal, conductive metal nitride, conductive metal silicide, conductive metal oxide, or a combination thereof.

(56) Before forming the conductive material layer **120P**, a first interlayer insulating layer **110A** covering the upper surface of the substrate **100** may be formed. The conductive material layer **120P** may be formed to cover the upper surface of the first interlayer insulating layer **110A**.

(57) Referring to FIGS. 4A and 4B together, a preliminary lower crystalline oxide semiconductor layer **12P** covering the upper surface of the conductive material layer **120P** is formed. The preliminary lower crystalline oxide semiconductor layer **12P** may be formed to include a crystalline quaternary oxide semiconductor material.

(58) Referring to FIGS. 4A, 4B, 5A and 5B together, a plurality of conductive lines **120** and a

plurality of lower crystalline oxide semiconductor layer **12** are formed by patterning the conductive material layer **120P** and the preliminary lower crystalline oxide semiconductor layer **12P** together. The plurality of conductive lines **120** and the plurality of lower crystalline oxide semiconductor layers **12** may extend in the second horizontal direction (Y direction) and may be formed to be spaced apart from each other at equal intervals in the first horizontal direction (X direction).

(59) After forming the plurality of conductive lines **120** and the plurality of lower crystalline oxide semiconductor layers **12**, a second interlayer insulating layer **110B** surrounding side surfaces of the plurality of conductive lines **120** and the plurality of lower crystalline oxide semiconductor layers **12** is formed. A stack structure of the first interlayer insulating layer **110A** and the second interlayer insulating layer **110B** may be referred to as the interlayer insulating layer **110**. The second interlayer insulating layer **110B** may be formed to be positioned at the same vertical level as that of upper surfaces of the plurality of lower crystalline oxide semiconductor layers **12**.

(60) Referring to FIGS. **6A** and **6B** together, a preliminary isolation insulating layer **115P** is formed above the plurality of lower crystalline oxide semiconductor layers **12** and the interlayer insulating layer **110**. The preliminary isolation insulating layer **115P** may be formed to have a stack structure of a preliminary lower isolation insulating layer **115AP** and a preliminary upper isolation insulating layer **115BP**. In some embodiments, the preliminary lower isolation insulating layer **115AP** may be formed to include nitride, and the preliminary upper isolation insulating layer **115BP** may be formed to include oxide.

(61) Referring to FIGS. **6A**, **6B**, **7A**, and **7B** together, a plurality of isolation insulating layers **115** are formed by patterning the preliminary isolation insulating layer **115P**. Each of the plurality of isolation insulating layers **115** may have a stack structure of the lower isolation insulating layer **115A** and the upper isolation insulating layer **115B**. The plurality of separation layers **115** may extend in the first horizontal direction (X direction) and may be formed to be spaced apart from each other at equal intervals in the second horizontal direction (Y direction). The channel trench **115t** extending long in the first horizontal direction (X direction) may be formed between the plurality of isolation insulating layers **115**.

(62) Referring to FIGS. **8A** and **8B** together, a preliminary amorphous oxide semiconductor layer **14P** covering a surface of a resultant of FIGS. **7A** and **7B** is formed. The preliminary amorphous oxide semiconductor layer **14P** may be formed to conformally cover upper surfaces and side surfaces of the plurality of isolation insulating layers **115**, upper surfaces of the plurality of lower crystalline oxide semiconductor layers **12**, and the upper surface of the interlayer insulating layers **110** positioned on the bottom surface of the channel trench **115t**.

(63) Referring to FIGS. **9A** and **9B**, a plurality of first mold layers **MD1** are formed to cover the preliminary amorphous oxide semiconductor layer **14P** and to fill a part of the channel trench **115t**. The plurality of first mold layers **MD1** may extend long in the second horizontal direction (Y direction). The plurality of first mold layers **MD1** may be formed by forming a preliminary mold layer covering the preliminary amorphous oxide semiconductor layer **14P** and filling the channel trench **115t**, and then patterning the preliminary mold layer.

(64) Referring to FIGS. **9A**, **9B**, **10A**, and **10B** together, parts of the upper surface of the interlayer insulating layer **110** are exposed by removing a part of the preliminary amorphous oxide semiconductor layer **14P** by using the plurality of first mold layers **MD1** as an etch mask.

(65) Referring to FIGS. **11A** and **11B** together, a second mold layer **MD2** filling space between the plurality of first mold layers **MD1** and covering upper surfaces of the plurality of first mold layers **MD1** is formed. A stack structure of the plurality of first and second mold layers **MD1** and **MD2** may be referred to as a mold structure **MDS**.

(66) Referring to FIGS. **11A**, **11B**, **12A**, and **12B** together, a plurality of amorphous oxide semiconductor layers **14** are formed by removing a part of the upper side of the mold structure **MDS** and a part of the preliminary amorphous oxide semiconductor layer **14P** covering the upper surfaces of the plurality of isolation insulating layers **115**. Each of the plurality of amorphous oxide

semiconductor layers **14** may be formed to cover the inner surface and the bottom surface of the channel trench **115t** and to have a U-shaped vertical cross-section.

(67) Referring to FIGS. **12A**, **12B**, **13A**, and **13B** together, after removing the mold structure **MDS**, a preliminary gate dielectric layer **140P** conformally covering the upper surface of the plurality of isolation insulating layers **115** and the upper surface and side surfaces of the plurality of amorphous oxide semiconductor layers **14** and a preliminary gate electrode **150P** are sequentially formed. The preliminary gate dielectric layer **140P** and the preliminary gate electrode **150P** may be formed to fill only a part of the channel trench **115t**.

(68) Referring to FIGS. **13A**, **13B**, **14A** and **14B** together, after removing part of the preliminary gate dielectric layer **140P** and part of the preliminary gate electrode **150P** covering the upper surfaces of the plurality of isolation insulating layers **115** and the upper surfaces of the plurality of amorphous oxide semiconductor layers **14**, and, the gate dielectric layer **140** and the gate electrode **150** are formed by removing a part of the preliminary gate electrode **150P** covering a part of the upper side of the side surfaces of the plurality of isolation insulating layers **115** and a part of the preliminary gate electrode **150P** covering the bottom surface of the channel trench **115t**.

(69) For example, after forming a third mold layer filling the channel trench **115t** and covering the preliminary gate electrode **150P**, parts of the upper side of the third mold layer, part of the preliminary gate dielectric layer **140P**, and parts of the preliminary gate electrode **150P** covering the upper surfaces of the plurality of isolation insulating layers **115** and the upper surfaces of the plurality of amorphous oxide semiconductor layers **14** are removed. Thereafter, after removing the third mold layer, the gate dielectric layer **140** and the gate electrode **150** may be formed by performing anisotropic etching on the preliminary gate electrode **150P**, which remains.

(70) The gate dielectric layer **140** may be formed to cover side surfaces of the amorphous oxide semiconductor layer **14** and extend in the vertical direction (Z direction) in the channel trench **115t**, and the gate electrode **150** may be formed to cover the gate dielectric layer **140** and extend in the vertical direction (Z direction) in the channel trench **115t**.

(71) In some embodiments, the gate electrode **150** may be formed to include the first gate electrode **150A** and the second gate electrode **150B** that face each other in one channel trench **115t**. The first gate electrode **150A** and the second gate electrode **150B** may be spaced apart from each other in the second horizontal direction (Y direction) and extend long in the first horizontal direction (X direction).

(72) Referring to FIGS. **15A** and **15B** together, a barrier insulating layer **162** conformally covering above the gate electrode **150** and the amorphous oxide semiconductor layer **14** in the channel trench **115t**, a gap-fill insulating layer **164** covering the barrier insulating layer **162** to fill space defined by the barrier insulating layer **162** in the channel trench **115t**, and a gate capping pattern **166** covering the upper surface of the gate electrode **150**, the upper surface of the barrier insulating layer **162**, and the upper surface of the gap-fill insulating layer **164** are sequentially formed.

(73) Referring to FIGS. **15A**, **15B**, and **16** together, a part of the upper side of the amorphous oxide semiconductor layer **14** is removed. The uppermost end of the amorphous oxide semiconductor layer **14** may be positioned at a lower vertical level than that of the uppermost end of the gate electrode **150**, by removing the part of the upper side of the amorphous oxide semiconductor layer **14**.

(74) Referring to FIG. **17**, the upper crystalline oxide semiconductor layer **16** is formed above the upper surface of the amorphous oxide semiconductor layer **14**. The lower crystalline oxide semiconductor layer **12**, the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** may constitute the channel structure **10**. The upper crystalline oxide semiconductor layer **16** may be formed to fill a part of a lower side of space from which the part of the upper side of the amorphous oxide semiconductor layer **14** described with reference to FIG. **16** is removed, that is, space defined between the isolation insulating layer **115** and the gate dielectric layer **140**. An amorphous oxide semiconductor material may be transformed into a crystalline oxide

semiconductor material by adjusting temperature. Accordingly, each of the lower crystalline oxide semiconductor layer **12**, the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** may be formed by a simple process step. For example, each of the lower crystalline oxide semiconductor layer **12**, the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** may be formed only by a deposition process, and thus the process margin, process steps, or manufacturing cost may be enhanced.

(75) In some embodiments, the upper crystalline oxide semiconductor layer **16** may be formed to have an upper surface positioned at a lower vertical level than that of the upper surface of the isolation insulating layer **115**. In some embodiments, the upper crystalline oxide semiconductor layer **16** may be formed to have an upper surface at a lower vertical level than that of the upper surface of the gate electrode **150**.

(76) Referring to FIGS. **17**, **18A**, and **18B** together, a contact material layer **170P** covering the upper crystalline oxide semiconductor layer **16**, the isolation insulating layer **115**, and the gate capping pattern **166** is formed. The contact material layer **170P** may be formed to fill space defined between the isolation insulating layer **115** and the gate dielectric layer **140**, and to cover the upper surface of the isolation insulating layer **115** and the upper surface of the gate capping pattern **166**.

(77) Referring to FIGS. **18A**, **18B**, **19A**, and **19B** together, after forming the plurality of contact structures **170** by removing a part of the contact material layer **170P**, an insulating structure **175** filling space from which a part of the contact material layer **170P** is removed, i.e., space between the plurality of contact structures **170**, is formed. FIGS. **19A** and **19B** show that the lower surface of the insulating structure **175** is positioned at the same vertical level as that of the upper surface of the isolation insulating layer **115** and the upper surface of the gate capping pattern **166**, but is not limited thereto. In some embodiments, the insulating structure **175** may be formed to extend into the isolation insulating layer **115** and the gate capping pattern **166** so that the lower surface of the insulating structure **175** is positioned at a lower vertical level than those of the upper surface of the isolation insulating layer **115** and the upper surface of the gate capping pattern **166**.

(78) Referring to FIGS. **20A** and **20B** together, a support insulating layer **180** is formed above the plurality of contact structures **170** and the insulating structures **175**. The support insulating layer **180** may have a plurality of holes having a bottom surface through which the plurality of contact structures **170** are exposed.

(79) A plurality of lower electrodes **192** are respectively formed above the plurality of contact structures **170**. The plurality of lower electrodes **192** may be formed to extend in the vertical direction (Z direction) from the upper surface of the contact structure **170** exposed at the bottom surfaces of the plurality of holes of the support insulating layer **180**.

(80) In FIG. **20A**, the lower electrode **192** is illustrated to have a pillar shape extending from the upper surface of the contact structure **170** in the vertical direction (Z direction), but this is an example. In some other embodiments, the lower electrode **192** may be formed to have a cylindrical shape extending in the vertical direction (Z direction) from the upper surface of the contact structure **170**.

(81) Thereafter, as shown in FIGS. **2A** and **2B**, the capacitor dielectric layer **194** and the upper electrode **194** are sequentially formed above the plurality of lower electrodes **192**, and thus, the semiconductor memory device **1** including the plurality of capacitor structures **190** may be formed. The capacitor dielectric layer **194** may be formed to conformally extend along profiles of the side surfaces and upper surfaces of the plurality of lower electrodes **192** and the upper surface of the support insulating layer **180**. The upper electrode **196** may be formed to cover the capacitor dielectric layer **194**.

(82) FIG. **21** is a cross-sectional view illustrating a semiconductor memory device **2** according to example embodiments. Specifically, FIG. **21** is a cross-sectional view taken along a part corresponding to A-A' of FIG. **1**.

(83) Referring to FIG. **21**, the semiconductor memory device **2** may include the substrate **100**, the

interlayer insulating layer **110**, the conductive line **120**, an isolation insulating layer **115L**, the channel structure **10**, the gate dielectric layer **140**, the gate electrode **150**, a contact structure **170a**, and the capacitor structure **190**. The substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the channel structure **10**, the gate dielectric layer **140**, the gate electrode **150**, and the capacitor structure **190** included in the semiconductor memory device **2** are substantially the same as substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the channel structure **10**, the gate dielectric layer **140**, the gate electrode **150**, and the capacitor structure **190** described with reference to FIGS. **1**, **2A**, and **2B**, respectively, and thus, descriptions redundant with those given with reference to FIGS. **1**, **2A**, and **2B** may be omitted.

(84) The isolation insulating layer **115L** may have a stack structure of the lower isolation insulating layer **115A** and an upper isolation insulating layer **115Ba**. In some embodiments, the lower isolation insulating layer **115A** may include nitride, and the upper isolation insulating layer **115Ba** may include oxide.

(85) The upper surface of the isolation insulating layer **115L**, that is, the upper surface of the upper isolation insulating layer **115Ba**, may be positioned at a lower vertical level than that of the uppermost end of the gate electrode **150**. In some embodiments, the upper surface of the isolation insulating layer **115L**, that is, the upper surface of the upper isolation insulating layer **115Ba**, may be positioned at the same vertical level as that of the uppermost end of the amorphous oxide semiconductor layer **14**, but is not limited thereto. In some other embodiments, in some embodiments, the upper surface of the isolation insulating layer **115L**, that is, the upper surface of the upper isolation insulating layer **115Ba**, may be positioned at the same vertical level as that of the uppermost end of the upper crystalline oxide semiconductor layer **16**.

(86) The contact structure **170a** may be formed above the channel structure **10**. In some embodiments, the contact structure **170a** may be connected to the upper surface and side surfaces of the upper crystalline oxide semiconductor layer **16**. In some other embodiments, the contact structure **170a** may be connected to the upper surface of the upper crystalline oxide semiconductor layer **16**. The contact structure **170a** may connect the channel structure **10** to the capacitor structure **190**. The contact structure **170a** may include at least one conductive material, for example, metal, conductive metal nitride, conductive metal carbonitride, conductive metal carbide, metal silicide, a doped semiconductor material, conductive metal oxynitride, conductive metal oxide, or a 2D material, but is not limited thereto.

(87) The contact structure **170a** may include a plurality of contact structures **170a** separated by an insulating structure **175a**. The insulating structure **175a** may cover above the isolation insulating layer **115L** and the gate capping pattern **166**, and have a plurality of recesses through which the channel structure **10** is exposed in bottom surfaces, and the plurality of contact structures **170** may fill the plurality of recesses. The insulating structure **175a** may include nitride. In FIG. **21**, the upper surface of the insulating structure **175a** and upper surfaces of the plurality of contact structures **170a** are positioned at the same level, but are not limited thereto. For example, the upper surface of the insulating structure **175a** may be positioned at a higher level than that of the upper surfaces of the plurality of contact structures **170a**.

(88) FIG. **21** shows that the lower surface of the insulating structure **175a** is positioned at the same vertical level as that of the upper surface of the isolation insulating layer **115L**, but is not limited thereto. In some embodiments, the insulating structure **175a** may extend into the isolation insulating layer **115L** such that a lower surface of the insulating structure **175a** is positioned at a lower vertical level than that of the upper surface of the isolation insulating layer **115L**. In some embodiments, the insulating structure **175a** may pass through the gate capping pattern **166** and extend into the gap-fill insulating layer **164**. For example, the lower surface of the insulating structure **175a** may be positioned at a lower vertical level than that of the lower surface of the gate capping pattern **166**.

(89) FIGS. **22** to **26** are cross-sectional views illustrating a method of manufacturing the

semiconductor memory device **2**, according to example embodiments. Specifically, FIGS. **22** to **26** are cross-sectional views illustrating the method of manufacturing the semiconductor memory device **2** shown in FIG. **21**, taken along a part corresponding to A-A' of FIG. **1**.

(90) Referring to FIG. **22**, the isolation insulating layer **115L** is formed by removing a part of upper sides of the plurality of isolation insulating layers **115** shown in FIGS. **15A** and **15B**, that is, a part of upper sides of the upper isolation insulating layer **115B**, and then a part of upper sides of the plurality of amorphous oxide insulating layers **14** is removed. The isolation insulating layer **115L** may be formed to have an upper surface positioned at a lower vertical level than that of the uppermost end of the gate electrode **150**.

(91) In some embodiments, the uppermost end of the amorphous oxide semiconductor layer **14** may be positioned at the same vertical level as that of the upper surface of the isolation insulating layer **115L** by removing a part of the upper side of the of amorphous oxide insulating layer **14**, but is not limited thereto. In some other embodiments, the uppermost end of the amorphous oxide semiconductor layer **14** may be positioned at a lower vertical level than that of the upper surface of the isolation insulating layer **115L** by removing a part of the upper side of the of amorphous oxide insulating layer **14**.

(92) Referring to FIG. **23**, the upper crystalline oxide semiconductor layer **16** is formed above the upper surface of the amorphous oxide semiconductor layer **14**. The lower crystalline oxide semiconductor layer **12**, the amorphous oxide semiconductor layer **14**, and the upper crystalline oxide semiconductor layer **16** may constitute the channel structure **10**.

(93) Referring to FIG. **24**, a contact material layer **170Pa** covering the upper crystalline oxide semiconductor layer **16**, the isolation insulating layer **115**, and the gate capping pattern **166** is formed. The contact material layer **170Pa** may be formed to completely fill space defined between two adjacent gate dielectric layers **140** and to cover the upper surface of the gate capping pattern **166**.

(94) Referring to FIGS. **24** and **25** together, after forming a plurality of contact structures **170a** by removing a part of the contact material layer **170Pa**, the insulating structure **175a** filling space from which a part of the contact material layer **170Pa** is removed, that is, space between the plurality of contact structures **170a**, is formed.

(95) Referring to FIG. **26**, the support insulating layer **180** is formed above the plurality of contact structures **170a** and the insulating structure **175a**. The support insulating layer **180** may include a plurality of holes having bottom surfaces through which the plurality of contact structures **170a** are exposed.

(96) A plurality of lower electrodes **192** are respectively formed above the plurality of contact structures **170a**. The plurality of lower electrodes **192** may be formed to extend in the vertical direction (Z direction) from the upper surface of the contact structure **170a** exposed to the bottom surfaces of the plurality of holes of the support insulating layer **180**.

(97) Thereafter, as shown in FIG. **21**, the capacitor dielectric layer **194** and the upper electrode **196** are sequentially formed above the plurality of lower electrodes **192**, and thus, the semiconductor memory device **2** including the plurality of capacitor structures **190** may be formed

(98) FIGS. **27** to **30** are cross-sectional views respectively illustrating semiconductor memory devices **3**, **4**, **5**, and **6** according to example embodiments. Specifically, each of FIGS. **27** to **30** is a cross-sectional view taken along a part corresponding to A-A' of FIG. **1**.

(99) Referring to FIG. **27**, the semiconductor memory device **3** may include the substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the isolation insulating layer **115**, the channel structure **10**, the gate dielectric layer **140**, the gate electrode **150**, the contact structure **170**, and the capacitor structure **190**. The substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the isolation insulating layer **115**, the channel structure **10**, the gate dielectric layer **140**, the gate electrode **150**, the contact structure **170**, and the capacitor structure **190** included in the semiconductor memory device **3** are substantially similar to the substrate **100**, the interlayer

insulating layer **110**, the conductive line **120**, the isolation insulating layer **115**, the channel structure **10**, the gate dielectric layer **140**, the gate electrode **150**, the contact structure **170**, and the capacitor structure **190** described with reference to FIGS. **1**, **2A**, and **2B**, respectively, and thus, descriptions redundant with those given with reference to FIGS. **1**, **2A**, and **2B** may be omitted.

(100) Instead of the barrier insulating layer **162** and the gap-fill insulating layer **164** included in the semiconductor memory device **1** shown in FIGS. **2A** and **2B**, the semiconductor memory device **3** may include a barrier insulating layer **162a** and a gap-fill insulating layer **164a**. The barrier insulating layer **162a** and the gap-fill insulating layer **164a** may be between the first gate electrode **150A** and the second gate electrode **150B**. The first gate electrode **150A** and the second gate electrode **150B** may be separated from each other by the barrier insulating layer **162a** and the gap-fill insulating layer **164a**. In some embodiments, the barrier insulating layer **162a** may have a U-shaped vertical cross-section, and the gap-fill insulating layer **164a** may be formed on the barrier insulating layer **162a** to fill the inside of the U-shaped vertical cross-section of the barrier insulating layer **162a** and may be filled in a region between the first gate electrode **150A** and the second gate electrode **150B**. For example, the barrier insulating layer **162a** may include silicon nitride, and the gap-fill insulating layer **164a** may include silicon oxide.

(101) In the semiconductor memory device **3**, the amorphous oxide semiconductor layer **14** includes a first channel portion and a second channel portion separated from each other by the barrier insulating layer **162a** and the gap-fill insulating layer **164a** and opposite to each other. Each of the first channel portion and the second channel portion may have an L-shaped vertical cross-section. The amorphous oxide semiconductor layer **14** may be cut by the barrier insulating layer **162a** and the gap-fill insulating layer **164a** to form the first channel portion and the second channel portion. The barrier insulating layer **162a** may be in contact with the lower crystalline oxide semiconductor layer **12**. For example, the lowermost surface of the barrier insulating layer **162a** may be formed equal to or lower than the lowermost surface of the amorphous oxide semiconductor layer **14**.

(102) The gate capping pattern **166** may be formed above the gate electrode **150**. The gate capping pattern **166** may cover, for example, an upper surface of the gate electrode **150**, an upper surface of the barrier insulating layer **162a**, and an upper surface of the gap-fill insulating layer **164a**.

(103) Referring to FIG. **28**, the semiconductor memory device **4** may include the substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the isolation insulating layer **115**, a channel structure **10a**, the gate dielectric layer **140**, the gate electrode **150**, the contact structure **170**, and the capacitor structure **190**. The substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the isolation insulating layer **115**, the gate dielectric layer **140**, the gate electrode **150**, the contact structure **170**, and the capacitor structure **190** included in the semiconductor memory device **4** are substantially similar to the substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the gate dielectric layer **140**, the gate electrode **150**, and the capacitor structure **190** described with reference to FIGS. **1**, **2A** and **2B**, and thus descriptions redundant with those given with reference to FIGS. **1**, **2A** and **2B** may be omitted.

(104) The channel structure **10a** may include the amorphous oxide semiconductor layer **14** and the upper crystalline oxide semiconductor layer **16**. Unlike the channel structure **10** of the semiconductor memory device **1** shown in FIGS. **2A** and **2B** including the lower crystalline oxide semiconductor layer **12**, the amorphous oxide semiconductor layer **14** and the upper crystalline oxide semiconductor layer **16**, the channel structure **10a** of the semiconductor memory device **4** shown in FIG. **28** includes the amorphous oxide semiconductor layer **14** and the upper crystalline oxide semiconductor layer **16**, but may not include the lower crystalline oxide semiconductor layer **12** shown in FIG. **2A**.

(105) A lower surface of the amorphous oxide semiconductor layer **14** may be in contact with an upper surface of the conductive line **120**. A lower surface of the isolation insulating layer **115**, that is, a lower surface of the lower isolation insulating layer **115A**, may be in contact with the upper

surface of the conductive line **120**. In some embodiments, the lower surface of the isolation insulating layer **115**, that is, the lower surface of the lower isolation insulating layer **115A**, and the upper surface of the conductive line **120** may be positioned at the same vertical level. FIG. **28** shows that the lower surface of the amorphous oxide semiconductor layer **14** is positioned at the same vertical level as that of the upper surface of the conductive line **120**, but is not limited thereto. In some embodiments, the amorphous oxide semiconductor layer **14** may extend into the conductive line **120** so that the lower surface of the amorphous oxide semiconductor layer **14** is positioned at a lower vertical level than that of the upper surface of the conductive line **120**.

(106) The semiconductor memory device **4** according to the inventive concept may include the channel structure **10a** including the upper crystalline oxide semiconductor layer **16**. The upper crystalline oxide semiconductor layer **16** has a relatively small contact area and may reduce the contact resistance between the amorphous oxide semiconductor layer **14** and the contact structure **170**, so that an electrical characteristic of the semiconductor memory device **4** may be improved, and thus, the performance and reliability of the semiconductor memory device **4** may be improved.

(107) Referring to FIG. **29**, the semiconductor memory device **5** may include the substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the isolation insulating layer **115L**, the channel structure **10a**, the gate dielectric layer **140**, the gate electrode **150**, the contact structure **170a**, and the capacitor structure **190**. The substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the channel structure **10a**, the gate dielectric layer **140**, the gate electrode **150**, and the capacitor structure **190** included in the semiconductor memory device **5** are substantially the same as the substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the channel structure **10a**, the gate dielectric layer **140**, the gate electrode **150**, and the capacitor structure **190** described with reference to FIG. **28**, and thus descriptions redundant with those given with reference to FIGS. **1**, **2A**, **2B**, and **28** may be omitted.

(108) The isolation insulating layer **115L** may have a stack structure of the lower isolation insulating layer **115A** and the upper isolation insulating layer **115Ba**. The upper surface of the isolation insulating layer **115L**, that is, the upper surface of the upper isolation insulating layer **115Ba**, may be positioned at a lower vertical level than that of the uppermost end of the gate electrode **150**. In some embodiments, the upper surface of the isolation insulating layer **115L**, that is, the upper surface of the upper isolation insulating layer **115Ba**, may be positioned at the same vertical level as that of the uppermost end of the amorphous oxide semiconductor layer **14**, but is not limited thereto. In some other embodiments, the upper surface of the isolation insulating layer **115L**, that is, the upper surface of the upper isolation insulating layer **115Ba**, may be positioned at the same vertical level as that of the uppermost end of the upper crystalline oxide semiconductor layer **16**.

(109) The contact structure **170a** may be formed above the channel structure **10a**. In some embodiments, the contact structure **170a** may be connected to the upper surface and side surfaces of the upper crystalline oxide semiconductor layer **16**. In some other embodiments, the contact structure **170a** may be connected to the upper surface of the upper crystalline oxide semiconductor layer **16**. The contact structure **170a** may connect the channel structure **10a** and the capacitor structure **190** to each other.

(110) Referring to FIG. **30**, the semiconductor memory device **6** may include the substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the isolation insulating layer **115**, the channel structure **10a**, the gate dielectric layer **140**, the gate electrode **150**, the contact structure **170**, and the capacitor structure **190**. The substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the isolation insulating layer **115**, the gate dielectric layer **140**, the gate electrode **150**, the contact structure **170**, and the capacitor structure **190** included in the semiconductor memory device **6** are substantially similar to the substrate **100**, the interlayer insulating layer **110**, the conductive line **120**, the channel structure **10**, the gate dielectric layer **140**, the gate electrode **150**, and the capacitor structure **190** described with reference to FIGS. **1**, **2A**, and

2B and the channel structure **10a** described with reference to FIG. **28**, and thus descriptions redundant with those given with reference to FIGS. **1**, **2A** and **2B** and descriptions redundant with those given with reference to FIG. **28** may be omitted.

(111) Instead of the barrier insulating layer **162** and the gap-fill insulating layer **164** included in the semiconductor memory device **4** shown in FIG. **28**, the semiconductor memory device **6** may include the barrier insulating layer **162a** and the gap-fill insulating layer **164a**. The barrier insulating layer **162a** and the gap-fill insulating layer **164a** may be between the first gate electrode **150A** and the second gate electrode **150B**. The first gate electrode **150A** and the second gate electrode **150B** may be separated from each other by the barrier insulating layer **162a** and the gap-fill insulating layer **164a**. In some embodiments, the barrier insulating layer **162a** may have a U-shaped vertical cross-section, and the gap-fill insulating layer **164a** may be formed on the barrier insulating layer **162a** to fill the inside of the U-shaped vertical cross-section of the barrier insulating layer **162a** and may be filled in a region between the first gate electrode **150A** and the second gate electrode **150B**.

(112) In the semiconductor memory device **6**, the amorphous oxide semiconductor layer **14** includes a first channel portion and a second channel portion separated from each other by the barrier insulating layer **162a** and the gap-fill insulating layer **164a** and opposite to each other. Each of the first channel portion and the second channel portion may have an L-shaped vertical cross-section. The amorphous oxide semiconductor layer **14** may be cut by the barrier insulating layer **162a** and the gap-fill insulating layer **164a** to form the first channel portion and the second channel portion. The barrier insulating layer **162a** may be in contact with the conductive line **120**. For example, the lowermost surface of the barrier insulating layer **162a** may be formed equal to or lower than the lowermost surface of the amorphous oxide semiconductor layer **14**.

(113) A gate capping pattern **166** may be formed above the gate electrode **150**. The gate capping pattern **166** may cover, for example, an upper surface of the gate electrode **150**, an upper surface of the barrier insulating layer **162a**, and an upper surface of the gap-fill insulating layer **164a**.

(114) While the inventive concept has been particularly shown and described with reference to embodiments thereof, it will be understood that various changes in form and details may be made therein without departing from the spirit and scope of the following claims.

Claims

1. A semiconductor memory device comprising: a substrate; a conductive line extending in a first horizontal direction above the substrate; an isolation insulating layer comprising a channel trench extending in a second horizontal direction intersecting with the first horizontal direction and extending from an upper surface to a lower surface of the isolation insulating layer, above the conductive line; a channel structure disposed above the conductive line; a gate electrode extending in the second horizontal direction, in the channel trench; a capacitor structure above the isolation insulating layer; and a contact structure between the channel structure and the capacitor structure, wherein the channel structure comprises an amorphous oxide semiconductor layer disposed in the channel trench above the conductive line, and an upper crystalline oxide semiconductor layer between the amorphous oxide semiconductor layer and the contact structure.
2. The semiconductor memory device of claim 1, wherein the channel structure further comprises a lower crystalline oxide semiconductor layer interposed between the conductive line and the amorphous oxide semiconductor layer.
3. The semiconductor memory device of claim 2, wherein the isolation insulating layer is disposed above the lower crystalline oxide semiconductor layer.
4. The semiconductor memory device of claim 2, wherein the lower crystalline oxide semiconductor layer extends in the first horizontal direction above the conductive line.
5. The semiconductor memory device of claim 4, wherein both side surfaces of the lower

crystalline oxide semiconductor layer and both side surfaces of the conductive line are aligned in a vertical direction.

6. The semiconductor memory device of claim 1, wherein the amorphous oxide semiconductor layer has a U-shaped vertical cross-section in the first horizontal direction.

7. The semiconductor memory device of claim 6, wherein the upper crystalline oxide semiconductor layer comprises: a first upper crystalline oxide semiconductor layer disposed above a first upper surface of the amorphous oxide semiconductor layer; and a second upper crystalline oxide semiconductor layer disposed above a second upper surface of the amorphous oxide semiconductor layer and spaced apart from the first upper crystalline oxide semiconductor layer, and wherein the amorphous oxide semiconductor layer and the first and second upper crystalline oxide semiconductor layers have the U-shaped vertical cross-section in the first horizontal direction.

8. The semiconductor memory device of claim 6, further comprising: a gate dielectric layer interposed between the channel structure and the gate electrode.

9. The semiconductor memory device of claim 8, wherein the gate dielectric layer comprises: first and second gate dielectric layers each having an L-shaped vertical cross-section along an inner surface of the channel structure, facing each other, and spaced apart from each other.

10. The semiconductor memory device of claim 1, wherein the gate electrode comprises a first gate electrode and a second gate electrode spaced apart from each other in the first horizontal direction to face each other in the channel trench and extending in the second horizontal direction, further comprising: a barrier insulating layer disposed between the first gate electrode and the second gate electrode; and a gap-fill insulating layer disposed on the barrier insulating layer and filling a region between the first gate electrode and the second gate electrode.

11. A semiconductor memory device comprising: a substrate; a conductive line extending in a first horizontal direction above the substrate; an isolation insulating layer comprising a channel trench extending in a second horizontal direction intersecting with the first horizontal direction and extending from an upper surface to a lower surface of the isolation insulating layer, above the conductive line; a channel structure disposed above the conductive line; a gate electrode extending in the second horizontal direction, in the channel trench; a gate dielectric layer interposed between the channel structure and the gate electrode, in the channel trench; a capacitor structure above the isolation insulating layer; and a contact structure interposed between the channel structure and the capacitor structure, wherein the channel structure comprises: a lower crystalline oxide semiconductor layer extending in the first horizontal direction above the conductive line; an amorphous oxide semiconductor layer disposed in the channel trench above the lower crystalline oxide semiconductor layer; and an upper crystalline oxide semiconductor layer interposed between the amorphous oxide semiconductor layer and the contact structure.

12. The semiconductor memory device of claim 11, wherein the isolation insulating layer is disposed above the lower crystalline oxide semiconductor layer such that a lower surface of the isolation insulating layer and an upper surface of the lower crystalline oxide semiconductor layer are positioned at a same vertical level.

13. The semiconductor memory device of claim 11, wherein: an upper surface of the upper crystalline oxide semiconductor layer is positioned at a lower vertical level than a level of an upper surface of the gate electrode, and the contact structure is connected to the upper surface of the upper crystalline oxide semiconductor layer.

14. The semiconductor memory device of claim 11, wherein: the amorphous oxide semiconductor layer has a U-shaped vertical cross-section in the first horizontal direction, and the gate dielectric layer comprises first and second gate dielectric layers each having an L-shaped vertical cross-section along an inner surface of the channel structure, facing each other, and spaced apart from each other.

15. The semiconductor memory device of claim 14, wherein: the gate electrode comprises a first

gate electrode and a second gate electrode spaced apart from each other in the first horizontal direction to face each other in the channel trench and extending in the second horizontal direction, the first gate dielectric layer is interposed between the channel structure and the first gate electrode, and the second gate dielectric layer is interposed between the channel structure and the second gate electrode.

16. The semiconductor memory device of claim 14, wherein the upper crystalline oxide semiconductor layer comprises: a first upper crystalline oxide semiconductor layer disposed above a first upper surface of the amorphous oxide semiconductor layer; and a second upper crystalline oxide semiconductor layer disposed above a second upper surface of the amorphous oxide semiconductor layer and spaced apart from the first upper crystalline oxide semiconductor layer, and wherein the amorphous oxide semiconductor layer and the first and second upper crystalline oxide semiconductor layers have a U-shaped vertical cross-section in the first horizontal direction.

17. The semiconductor memory device of claim 11, wherein the lower crystalline oxide semiconductor layer and the conductive line overlap each other in a vertical direction.

18. A semiconductor memory device comprising: a substrate; a conductive line extending in a first horizontal direction above the substrate; an isolation insulating layer comprising a channel trench extending in a second horizontal direction intersecting with the first horizontal direction and extending from an upper surface to a lower surface of the isolation insulating layer, above the conductive line; a channel structure disposed above the conductive line; a gate electrode comprising a first gate electrode and a second gate electrode spaced apart from each other in the first horizontal direction to face each other in the channel trench and extending in the second horizontal direction; a gate dielectric layer interposed between the channel structure and the gate electrode, in the channel trench; a barrier insulating layer disposed between the first gate electrode and the second gate electrode; a gap-fill insulating layer disposed on the barrier insulating layer and filling a region between the first gate electrode and the second gate electrode; a gate capping pattern covering upper surfaces of the gate electrode, the barrier insulating layer, and the gap-fill insulating layer; a capacitor structure above the isolation insulating layer and the gate capping pattern; and a contact structure interposed between the channel structure and the capacitor structure, wherein the channel structure comprises: a lower crystalline oxide semiconductor layer having a lower surface covering an upper surface of the conductive line and extending in the first horizontal direction; an amorphous oxide semiconductor layer disposed in the channel trench above the lower crystalline oxide semiconductor layer and having a U-shaped vertical cross-section in the first horizontal direction; and first and second upper crystalline oxide semiconductor layers spaced apart from each other and interposed between the amorphous oxide semiconductor layer and the contact structure, and wherein the first upper crystalline oxide semiconductor is disposed above a first upper surface of the amorphous oxide semiconductor layer, and the second upper crystalline oxide semiconductor layer is disposed above a second upper surface of the amorphous oxide semiconductor layer.

19. The semiconductor memory device of claim 18, wherein: the amorphous oxide semiconductor layer comprises indium gallium zinc oxide (IGZO), and each of the lower crystalline oxide semiconductor layer and the first and second upper crystalline oxide semiconductor layers comprises c-axis aligned crystalline (CAAC) IGZO.

20. The semiconductor memory device of claim 18, wherein the contact structure extends between the isolation insulating layer and the gate dielectric layer from upper surfaces of the isolation insulating layer and the gate capping pattern, and is connected to the first and second upper crystalline oxide semiconductor layers.
