

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12406915
Kind Code	B2
Date of Patent	September 02, 2025
Inventor(s)	Noquil; Jonathan Almeria et al.

Plated metal layer in power packages

Abstract

In some examples, a semiconductor package comprises a multi-layer package substrate. The multi-layer package substrate includes first and second metal layers, the first metal layer positioned above the second metal layer and coupled to the second metal layer by way of a via. The substrate also includes a dielectric covering at least part of the first and second metal layers and the via. The package includes a plated metal layer plated on at least part of the first metal layer and positioned above the dielectric, a combination of the first metal layer and the plated metal layer being thicker than the second metal layer. The package includes a semiconductor die having a device side, the device side vertically aligned with and coupled to the plated metal layer.

Inventors: Noquil; Jonathan Almeria (Plano, TX), Kulkarni; Makarand Ramkrishna (Dallas, TX), Lopez; Osvaldo Jorge (Annandale, TX), Tang; Yiqi (Allen, TX), Murugan; Rajen Manicon (Dallas, TX), Wan; Liang (Chengdu, CN)

Applicant: TEXAS INSTRUMENTS INCORPORATED (Dallas, TX)

Family ID: 81848210

Assignee: Texas Instruments Incorporated (Dallas, TX)

Appl. No.: 18/484310

Filed: October 10, 2023

Prior Publication Data

Document Identifier	Publication Date
US 20240047330 A1	Feb. 08, 2024

Related U.S. Application Data

continuation parent-doc US 17334491 20210528 US 11784114 child-doc US 18484310
us-provisional-application US 63122903 20201208

Publication Classification

Int. Cl.: H01L23/498 (20060101); H01L23/00 (20060101)

U.S. Cl.:

CPC H01L23/49822 (20130101); H01L23/49844 (20130101); H01L24/13 (20130101); H01L24/16 (20130101); H01L2224/13147 (20130101); H01L2224/16238 (20130101)

Field of Classification Search

CPC: H01L (23/49822); H01L (23/49844); H01L (24/13); H01L (24/16); H01L (2224/13147); H01L (2224/16238); H01L (24/32); H01L (24/48); H01L (2224/0603); H01L (2224/16225); H01L (2224/48227); H01L (2224/48465); H01L (2224/49111); H01L (2224/49171); H01L (23/3107); H01L (2924/00014); H01L (2924/181)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
11784114	12/2022	Noquil	257/773	H01L 23/3107
2016/0218072	12/2015	Liao	N/A	H01L 23/66
2016/0276174	12/2015	Kim	N/A	H01L 23/5389
2020/0083135	12/2019	Swan	N/A	H01L 24/73
2021/0384153	12/2020	Lee	N/A	H01L 25/18
2022/0181237	12/2021	Yen	N/A	H01L 23/3677

Primary Examiner: Owens; Douglas W

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS (1) This application is a continuation of U.S. patent application Ser. No. 17/334,491, filed May 28, 2021, (now U.S. Pat. No. 11,784,114), which claims priority to U.S. Provisional Patent Application No. 63/122,903, which was filed Dec. 8, 2020, is titled “Flip Chip Routable Lead Frame With Elevated Trace,” and is hereby incorporated herein by reference in its entirety.

BACKGROUND

(1) Semiconductor chips are often housed inside packages that protect the chips from deleterious environmental influences, such as heat, moisture, and debris. A packaged chip generally communicates with electronic devices outside the package via conductive members (e.g., leads) that are exposed to surfaces of the package. Some packages include substrates on which the semiconductor die is positioned. The substrate may include multiple metal layers, or traces, that carry electrical signals or power.

SUMMARY

(2) In some examples, a semiconductor package comprises a multi-layer package substrate. The multi-layer package substrate includes first and second metal layers, the first metal layer positioned above the second metal layer and coupled to the second metal layer by way of a via. The substrate

also includes a dielectric covering at least part of the first and second metal layers and the via. The package includes a plated metal layer plated on at least part of the first metal layer and positioned above the dielectric, a combination of the first metal layer and the plated metal layer being thicker than the second metal layer. The package includes a semiconductor die having a device side, the device side vertically aligned with and coupled to the plated metal layer.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

- (1) For a detailed description of various examples, reference will now be made to the accompanying drawings in which:
- (2) FIGS. 1A and 1B are perspective views of a semiconductor package having a plated metal layer, in accordance with various examples.
- (3) FIG. 1C is a block diagram of an example electronic device in accordance with various examples.
- (4) FIGS. 2-4 are perspective views of contents of a semiconductor package having a plated metal layer, in accordance with various examples.
- (5) FIG. 5 is a profile cross-sectional view of a semiconductor package having a plated metal layer, in accordance with various examples.
- (6) FIG. 6A is a top-down view of contents of a semiconductor package having a plated metal layer, in accordance with various examples.
- (7) FIG. 6B is a profile cross-sectional view of a semiconductor package having a plated metal layer, in accordance with various examples.
- (8) FIG. 7A is a top-down view of contents of a semiconductor package having a plated metal layer, in accordance with various examples.
- (9) FIG. 7B is a profile cross-sectional view of a semiconductor package having a plated metal layer, in accordance with various examples.
- (10) FIG. 8 is a flow diagram of a method for manufacturing a semiconductor package having a plated metal layer, in accordance with various examples.

DETAILED DESCRIPTION

- (11) As described, some semiconductor packages include substrates having multiple metal layers, or traces. These metal layers carry electrical data signals and/or power between the semiconductor die and conductive terminals (e.g., leads) of the package. The thicknesses of these metal layers are generally limited by manufacturing processes and equipment, and in some cases, the metal layers are too thin to permit adequate current flow. This high resistance provided by the metal layers can result in unsatisfactory performance, particularly in power packages, as well as undesirable impacts on electro-migration.
- (12) This disclosure describes various examples of a semiconductor package that mitigates the challenges described above by including a plated metal layer that is plated on top of the highest metal layer of the package substrate. The plated metal layer is coupled to the highest metal layer of the package substrate, but it is separate and distinct from the highest metal layer. For example, the plated metal layer may be plated on only a portion of the highest metal layer. The plated metal layer, while distinct from the highest metal layer, abuts the highest metal layer and thus effectively increases the thickness of the highest metal layer. By effectively increasing the thickness of the highest metal layer, the total combined resistance of the metal layers in the substrate is substantially reduced, thereby permitting improved current flow and mitigating electro-migration. These features may be useful in any type of semiconductor package, and they may be particularly useful in power applications.
- (13) FIGS. 1A and 1B are perspective views of a semiconductor package **100** having a plated metal

layer, in accordance with various examples. FIG. 1A shows a top side of the semiconductor package **100**, and FIG. 1B shows a bottom side of the semiconductor package **100**. FIG. 1B shows a metal layer **102** exposed to an exterior of the semiconductor package **100**. The various portions of the metal layer **102** shown in FIG. 1B may be coupled to each other. In examples, a subset of the portions of the metal layer **102** are coupled to each other. In examples, none of the portions of the metal layer **102** are coupled to each other. Notwithstanding the particular manner in which the drawings depict the semiconductor package **100**, the semiconductor package **100** may be any suitable type of package, such as a dual inline package (DIP), a quad flat no-lead (QFN) package, a package having gullwing style leads, a flip-chip style package, a ball grid array (BGA) package, a combination of one or more such package types, etc. Any type of package in which the above-described challenges are present may benefit from the structures and techniques described herein.

(14) FIG. 1C is a block diagram of an electronic device **104** containing the semiconductor package **100**, in accordance with various examples. In particular, the electronic device **104** may include a personal electronic device (e.g., smartphones, laptop computers, desktop computers, tablets, notebooks, artificial intelligence assistants), an electronic appliance (e.g., refrigerators, microwave ovens, toaster ovens, dishwashers), a networking or enterprise-level electronic device or system (e.g., servers, routers, modems, mainframe computers, wireless access points), an automobile or aviation device or system (e.g., control panels, entertainment devices, navigation devices, power electronics), or any of a variety of other electronic devices or systems. The electronic device **104** may include a printed circuit board (PCB) **106** and a semiconductor package **100** coupled to the PCB **106**.

(15) FIGS. 2-4 are perspective views of contents of the semiconductor package **100**, in accordance with various examples. The semiconductor package **100** includes a semiconductor die **200**. The semiconductor die **200** has a flip-chip orientation, meaning that the device side of the semiconductor die **200** in which circuitry is formed is facing downward. The device side of the semiconductor die **200** is coupled to a top surface of a plated metal layer **210**. The plated metal layer **210** may be composed of a low resistivity metal, such as copper, aluminum, nickel, gold, or silver. The resistivity of the plated metal layer **210** is lower than 7×10^{-8} Ohm-meters at 20 degrees Celsius, with a resistivity greater than this range resulting in an unacceptably high total resistance in the semiconductor package **100**. A bottom surface of the plated metal layer **210** is coupled to a top surface of a metal layer **202**. As described below, the plated metal layer **210** may be plated on the metal layer **202**. Accordingly, while the plated metal layer **210** and the metal layer **202** are distinct and separate layers, they are coupled to each other. A bottom surface of the metal layer **202** is coupled to a top surface of a metal layer **204** by way of multiple vias (vias not expressly shown in FIG. 2). A bottom surface of the metal layer **204** is coupled to a top surface of the metal layer **102** (also shown in FIG. 1B and described above) by way of multiple vias (vias not expressly shown in FIG. 2). As described above, a bottom surface of the metal layer **102** is exposed to an exterior of the semiconductor package **100**. The semiconductor package **100** includes a dielectric **201** (e.g., such as AJINOMOTO® build-up film (ABF)). A mold compound is included in the semiconductor package **100** but is not expressly shown in FIG. 2. The metal layers **102**, **204**, and **202** are part of a substrate called a multi-layer package substrate, because the substrate is in a package and the substrate includes multiple metal layers. The multi-layer package substrate also includes the dielectric **201**. The multi-layer package substrate differs from a printed circuit board (PCB) because the multi-layer package substrate is within the semiconductor package **100**, whereas the PCB is outside the semiconductor package **100**. The multi-layer package substrate includes multiple metal layers that are separated by a solid, tangible dielectric **201**, whereas the PCB may contain multiple layers of printed circuit board that may not be separated by a dielectric material other than air.

(16) In examples, the metal layers **202**, **204**, and **102** abut the dielectric **201**. In examples, a top surface of the metal layer **202** is approximately flush with a top surface of the dielectric **201**. In

examples, the bottom surface of the metal layer **102** is approximately flush with a bottom surface of the dielectric **201**. In examples, each of the metal layers **202**, **204**, and **102** is co-planar with the dielectric **201**, meaning that a horizontal plane coincides with the metal layer **202** and the dielectric **201**, another horizontal plane coincides with the metal layer **204** and the dielectric **201**, and another horizontal plane coincides with the metal layer **102** and the dielectric **201**. In examples, the plated metal layer **210** is positioned above the top surface of the dielectric **201**.

(17) The patterns of the metal layers **202**, **204**, and **102** may be identical. In examples, the patterns of the metal layers **202**, **204**, and **102** are different. In examples, some, but not all, of the metal layers **202**, **204**, **102** have identical patterns.

(18) In examples, the pattern of the plated metal layer **210** is identical to that of the metal layer **202**. In such examples, the plated metal layer **210** abuts all or approximately all of the top surface of the metal layer **202**. In examples, the pattern of the plated metal layer **210** differs from that of the metal layer **202**. For instance, the plated metal layer **210** may abut some, but not all, of the metal layer **202**, with the coincident portions of the plated metal layer **210** and the metal layer **202** being identical in pattern, but with at least one portion of the metal layer **202** not being covered by the plated metal layer **210**. In examples, the plated metal layer **210** is strategically applied to power portions of the metal layer **202** that are connected to silicon nodes (e.g., voltage and ground terminals in the case of high power transistor drain and source terminals, or a switch node in a power converter) that use high current. In examples, the plated metal layer **210** is a continuous metal member, and in other examples, the plated metal layer **210** includes multiple distinct metal members.

(19) In examples, the metal layers **202**, **204**, and **102** are approximately flush with side surfaces of the dielectric **201**, as shown in FIG. 2. The plated metal layer **210** is not flush with the side surfaces of the dielectric **201** and, instead, it is recessed from the side surfaces of the dielectric **201** by a horizontal distance of at least 50 microns, with a distance lesser than this range being disadvantageous because of unacceptably increased difficulty during sawing operations (e.g., increased amount of metal to saw, thus slowing operations, reducing saw blade life, etc.). Distances lesser than the range described above are also disadvantageous because they increase overall package thickness, as the mold cap clamp used when injecting mold compound will contact the plated metal layer **210** instead of the metal layer **202**.

(20) The semiconductor die **200** may be coupled to the plated metal layer **210** using any suitable structures and techniques. For example, the semiconductor die **200** may be coupled to the plated metal layer **210** using copper pillars and solder bumps. For example, the semiconductor die **200** may be coupled to the plated metal layer **210** using solder bumps alone. Other structures and techniques are contemplated and included in the scope of this disclosure.

(21) In some examples, the plated metal layer **210** has a thickness ranging from 30 microns to microns. A thickness below this range does not acceptably improve overall resistance of the metal layers of the semiconductor package **100**. In addition, a thickness below this range does not acceptably improve electromigration and acceptably reduce current crowding in the metal layers of the semiconductor package **100**. Testing data demonstrate that parasitic resistance of semiconductor packages may be reduced by 33.9% in some designs implementing the plated metal layer described herein (e.g., a reduction from 1.74 milli Ohms to 1.15 milli Ohms). Conversely, a thickness above this range adds to semiconductor package **100** bulk and expense without providing a commensurate additional improvement in resistance, electromigration, and current crowding. Increasing the thickness of the metal layer **202** in lieu of or in addition to plating the plated metal layer **210** on the metal layer **202** is not feasible or acceptable, as doing so entails significant and expensive retooling of existing equipment and manufacturing processes. Accordingly, the thickness of the metal layer **202** may be in the range of 30 microns to 40 microns. The combined thickness of the plated metal layer **210** and the metal layer **202** is greater than the thickness of any of the remaining individual metal layers in the semiconductor package **100**.

(22) In operation, the plated metal layer **210**, although a distinct and separate layer from the metal layer **202**, effectively increases the thickness of the metal layer **202**, since the plated metal layer **210** is plated directly on the metal layer **202**. In this way, the current handling capability of the metal layer **202**, and thus the total current handling capability of the semiconductor package **100**, is increased. Total resistance of the semiconductor package **100** is decreased for the same reason, as is electromigration and current crowding. Because of these benefits, the semiconductor package **100** may find particular application and usefulness in power applications, and thus the semiconductor package **100** may be a power package of any suitable type. The scope of application, however, is not limited to power applications.

(23) FIG. **3** is a perspective view of the structure of FIG. **2**, with the semiconductor die **200** omitted to facilitate viewing of the remainder of the structure, and particularly of the plated metal layer **210**. FIG. **4** is a perspective view of the structure of FIG. **3**, with the plated metal layer **210** omitted to facilitate viewing of the remainder of the structure, and particularly of the metal layer **202**. As shown in FIGS. **3** and **4**, the plated metal layer **210** is plated on some, but not all, of the metal layer **202**. The portion of the metal layer **202** on which the plated metal layer **210** is plated has a common structure (e.g., pattern) as the plated metal layer **210**. The plated metal layer **210** is plated on at least 80% of the top surface of the metal layer **202** that is vertically aligned with the semiconductor die **200**, with a lesser coverage area being disadvantageous because of unacceptably increased combined resistance of the metal layers in the semiconductor package **100**, and with a coverage area greater than this range being disadvantageous because of substantially increased bulk and expense without a commensurate decrease in resistance, and further because of the possibility of the plated metal layer **210** extending to the side surfaces of the dielectric **201**, thereby causing the sawing challenges described above. The total thickness of the structure shown in FIG. **4** ranges from 120 microns to 500 microns, with a thickness less than this range being disadvantageous because of poor structural integrity, and with a thickness greater than this range being disadvantageous because of increased cost and decreased yield.

(24) FIG. **5** is a profile cross-sectional view of the semiconductor package **100**, in accordance with various examples. The semiconductor die **200** may be coupled to the plated metal layer **210** by way of copper pillars **500** and solder bumps **502**. Any suitable number of copper pillars **500** and solder bumps **502** may be used. In examples, the copper pillars **500** have a thickness ranging from microns to 65 microns, with thicknesses below this range being disadvantageous due to mold fill challenges (e.g., the formation of air gaps in the mold compound), and with thicknesses above this range being disadvantageous because of a lack of co-planarity between the copper pillars **500** and due to structural integrity and reliability challenges. The semiconductor die **200**, for example the device side of the semiconductor die **200**, is vertically aligned with the plated metal layer **210**, such that the semiconductor die **200** covers at least part of the plated metal layer **210**.

(25) The metal layer **202** is coupled to a portion of the metal layer **204** by way of a via **504**, and the metal layer **202** is coupled to another portion of the metal layer **204** by way of a via **508**. The portion of the metal layer **204** coupled to the via **504** may be coupled to a portion of the metal layer **102** by way of a via **506**, and the portion of the metal layer **204** coupled to the via **508** may be coupled to a portion of the metal layer **102** by way of a via **510**. The semiconductor package **100** includes a mold compound **512** that abuts the semiconductor die **200** (e.g., a top surface, a bottom surface, and/or one or more side surfaces of the semiconductor die **200**), the copper pillars **500**, the solder bumps **502**, the plated metal layer **210**, the metal layer **202**, and, in examples, the dielectric **201**. The thicknesses of the copper pillars **500** and the solder bumps **502** may be adjusted to provide increased clearance as described above, thus accommodating larger mold compound filler sizes (e.g., in the range of 60 to 80 microns) with few or no air gaps in the mold compound due to the increased clearance. The increased clearance is achieved between the bottom surface of the semiconductor die **200** and the top surface of the metal layer **202** in areas of the semiconductor package **100** where the plated metal layer **210** includes a horizontal gap or multiple horizontal gaps

between the bottom surface of the semiconductor die **200** and the top surface of the metal layer **202**.

(26) FIG. **6A** is a top-down view of contents of a semiconductor package **600** having a plated metal layer, in accordance with various examples. The semiconductor package **600** includes a semiconductor die **602** having a gate pad **604**. The gate pad **604** may be, for instance, the gate pad of a power transistor (e.g., metal oxide semiconductor field effect transistor (MOSFET)), or the base of a power bipolar junction transistor (BJT). The semiconductor package **600** includes a metal layer **606**. A plated metal layer **608** is plated on top of a portion of the top surface of the metal layer **606**. Plated areas may include the drain or source nodes of a power MOSFET, or the collector or emitter of a power BJT. A dielectric **612** abuts the metal layer **606**, and in examples, the top surface of the metal layer **606** is approximately flush with the top surface of the dielectric **612**. In examples, the plated metal layer **608** is positioned above the top surface of the dielectric **612**. The semiconductor package **600** may be a power transistor package (commonly used in power applications), in which current flows through the body of the semiconductor die **602**, toward and through a bottom surface of the semiconductor die **602** and into the plated metal layer **608**, which is positioned underneath the semiconductor die **602**. The current may then flow laterally (horizontally) within the various metal layers and vias that abut and are co-planar with the dielectric **612**. Wirebonds **610** couple the device side of the semiconductor die **602** and the gate pad **604** to the metal layer **606**, as shown.

(27) FIG. **6B** is an example profile cross-sectional view of the semiconductor package **600** along the line **614** shown in FIG. **6A**. As shown, the semiconductor package **600** includes a metal layer **616** coupled to the metal layer **606** by way of a via **622**; a metal layer **618** coupled to the metal layer **616** by way of a via **624**; and a metal layer **620** coupled to the metal layer **618** by way of a via **626**. The plated metal layer **608** is plated on the metal layer **606**, as shown and as described above. Further, via **628** couples a segment of the metal layer **606** to a segment of the metal layer **616**. A via **630** couples a segment of the metal layer **616** to a segment of the metal layer **618**. A via **632** couples a segment of the metal layer **618** to a segment of the metal layer **620**. The metal layer **620** is exposed to an exterior of the dielectric **612** and to an exterior of the semiconductor package **600**. In examples, the bottom surface of the metal layer **620** is approximately flush with the bottom surface of the semiconductor package **600**. A mold compound **636** covers the remaining structures of the semiconductor package **600**. The dimensions and physical properties of the plated metal layer **608** are similar to those of the plated metal layer **210**, and thus they are not described again here. The dimensions and physical properties of the remaining structures of the semiconductor package **600** are likewise similar to the corresponding structures of the semiconductor package **100**, and thus are not described again here. In operation, the plated metal layer **608**, while distinct and separate from the metal layer **606**, nonetheless increases the effective thickness of the metal layer **606** and thus reduces the overall resistance of the metal layers in the semiconductor package **600**. For similar reasons, electromigration and current crowding is reduced. Arrows **634** depict an example current flow path.

(28) FIG. **7A** is another example semiconductor package similar to that of FIGS. **6A** and **6B**. In particular, FIG. **7A** is a top-down view of contents of a semiconductor package **700** having a plated metal layer, in accordance with various examples. The semiconductor package **700** includes a metal layer **702**, a dielectric **704** having a top surface that is approximately flush with the top surface of the metal layer **702**, a plated metal layer **706** plated on the top surface of the metal layer **702**, a semiconductor die **708** having a gate pad **710**, a semiconductor die **712** having a gate pad **714**, and wirebonds **716** coupling the metal layer **702** to the semiconductor dies **708** and **712**, as shown. In examples, the semiconductor package **700** may be a dual die multi-chip module (MCM) power transistor type of package and may be suitable for use in power applications.

(29) FIG. **7B** is a profile cross-sectional view of the semiconductor package **700** along the line **718** shown in FIG. **7A**. As shown, the semiconductor package **700** includes a mold compound **720**

covering the structures of FIG. 7A. The dimensions and physical properties of the various structures of the semiconductor package **700** are similar to those of the corresponding structures of the semiconductor package **700**, and thus they are not repeated here. Further, the benefits attained by including the plated metal layer **706** are similar to those attained by including the plated metal layers described above, and thus they are not repeated here. Arrows **722** indicate lateral current flow, specifically, through the bodies of the semiconductor dies **708** and **712**, through the bottom surfaces of the semiconductor dies **708** and **712**, into the plated metal layer **706**, and then laterally through the plated metal layer **706** and the metal layer **702**. **60**

(30) FIG. **8** is a flow diagram of a method **800** for manufacturing a semiconductor package having a plated metal layer, in accordance with various examples. In examples, the method **800** includes forming a substrate having one or more metal layers (**802**). For example, referring to FIG. **5**, a substrate may include the dielectric **201**, the metal layers **102**, **204**, and **202**, and the vias coupling these metal layers. For example, referring to FIG. **6B**, the substrate may include the dielectric **612**, the metal layers **606**, **616**, **618**, and **620**, and the vias coupling these metal layers. For example, referring to FIG. **7B**, the substrate may include the dielectric **704** and the metal layer **702**.

(31) The method **800** includes plating a metal layer on the top surface of the top metal layer in the substrate (**804**). Examples of such plated metal layers include the plated metal layers **210**, **608**, and **706** described above. Any suitable plating technique(s) may be used, and any suitable metals and/or metal alloys may be used. In some examples, the plated metal layer is of the same composition as the top metal layer on which the plated metal layer is plated. The method **800** includes coupling the semiconductor die to the plated metal layer and/or to the top metal layer (**806**). In some examples, a die attach film (not expressly shown in the drawings above) may be used. Other techniques for coupling the semiconductor die to the plated metal layer are contemplated and included in the scope of this disclosure.

(32) The term “couple” is used throughout the specification. The term may cover connections, communications, or signal paths that enable a functional relationship consistent with this description. For example, if device A generates a signal to control device B to perform an action, in a first example device A is coupled to device B, or in a second example device A is coupled to device B through intervening component C if intervening component C does not substantially alter the functional relationship between device A and device B such that device B is controlled by device A via the control signal generated by device A.

(33) A device that is “configured to” perform a task or function may be configured (e.g., programmed and/or hardwired) at a time of manufacturing by a manufacturer to perform the function and/or may be configurable (or re-configurable) by a user after manufacturing to perform the function and/or other additional or alternative functions. The configuring may be through firmware and/or software programming of the device, through a construction and/or layout of hardware components and interconnections of the device, or a combination thereof.

(34) A circuit or device that is described herein as including certain components may instead be adapted to be coupled to those components to form the described circuitry or device. For example, a structure described as including one or more semiconductor elements (such as transistors), one or more passive elements (such as resistors, capacitors, and/or inductors), and/or one or more sources (such as voltage and/or current sources) may instead include only the semiconductor elements within a single physical device (e.g., a semiconductor die and/or integrated circuit (IC) package) and may be adapted to be coupled to at least some of the passive elements and/or the sources to form the described structure either at a time of manufacture or after a time of manufacture, for example, by an end-user and/or a third-party.

(35) While certain components may be described herein as being of a particular process technology, these components may be exchanged for components of other process technologies. Circuits described herein are reconfigurable to include the replaced components to provide functionality at least partially similar to functionality available prior to the component replacement. Components

shown as resistors, unless otherwise stated, are generally representative of any one or more elements coupled in series and/or parallel to provide an amount of impedance represented by the shown resistor. For example, a resistor or capacitor shown and described herein as a single component may instead be multiple resistors or capacitor, respectively, coupled in parallel between the same nodes. For example, a resistor or capacitor shown and described herein as a single component may instead be multiple resistors or capacitor, respectively, coupled in series between the same two nodes as the single resistor or capacitor.

(36) Uses of the phrase “ground voltage potential” in the foregoing description include a chassis ground, an Earth ground, a floating ground, a virtual ground, a digital ground, a common ground, and/or any other form of ground connection applicable to, or suitable for, the teachings of this description. Unless otherwise stated, “about,” “approximately,” or “substantially” preceding a value means ± 10 percent of the stated value. Modifications are possible in the described examples, and other examples are possible within the scope of the claims.

Claims

1. A semiconductor package including a power transistor, comprising: a semiconductor die including a gate pad, the semiconductor die attached to a package substrate, the package substrate including: a dielectric; a metal layer in the dielectric; a plated metal layer plated on top of the metal layer and having a thickness ranging from 30 microns to 60 microns.
2. The semiconductor package of claim 1, wherein the plated metal layer is positioned above and external to the dielectric.
3. The semiconductor package of claim 1, wherein a combination of the metal layer and the plated metal layer is thicker than a second metal layer that is below the metal layer.
4. The semiconductor package of claim 1, wherein the plated metal layer reduces a total combined resistance of the metal layer and the second metal layer.
5. The semiconductor package of claim 1, wherein a device side of the semiconductor die is coupled to the plated metal layer.
6. The semiconductor package of claim 1, wherein the semiconductor die is vertically aligned with the plated metal layer.
7. The semiconductor package of claim 1, further comprising a mold compound under the semiconductor die, wherein the mold compound includes a mold compound filler of 60 microns to 80 microns.
8. The semiconductor package of claim 1, wherein a top surface of the metal layer is approximately flush with a top surface of the dielectric.
9. The semiconductor package of claim 1, wherein the plated metal layer is plated on power portions of the metal layer.
10. The semiconductor package of claim 1, wherein a top surface of the metal layer along a perimeter of the metal layer is independent of the plated metal layer.
11. The semiconductor package of claim 1, wherein the dielectric includes a build-up film material.
12. A semiconductor package, comprising: a multi-layer package substrate including: first and second metal layers, the first metal layer positioned above the second metal layer and coupled to the second metal layer by way of a via, a side surface of the multi-layer package substrate approximately flush with side surfaces of the first and second metal layers; and a dielectric covering at least part of the first and second metal layers and the via; a plated metal layer plated on at least part of the first metal layer and positioned above the dielectric, a side surface of the plated metal layer parallel to the side surface of the multi-layer package substrate; and a semiconductor die having a device side, the device side vertically aligned with and coupled to the plated metal layer.
13. The semiconductor package of claim 12, wherein a thickness of the plated metal layer ranges

from 30 microns to 60 microns.

14. The semiconductor package of claim 12, further comprising a mold compound under the semiconductor die, wherein the mold compound includes a mold compound filler of size between 60 microns to 80 microns.

15. The semiconductor package of claim 12, wherein a top surface of the first metal layer is approximately flush with a top surface of the dielectric.

16. The semiconductor package of claim 12, wherein the plated metal layer is plated on power portions of the first metal layer.

17. The semiconductor package of claim 16, wherein the power portions include one of a voltage, a ground terminal, a drain terminal, a source, terminal, and a switch node terminal.

18. The semiconductor package of claim 12, wherein a top surface of the first metal layer along a perimeter of the first metal layer is independent of the plated metal layer.

19. The semiconductor package of claim 18, wherein a length of a segment of the first metal layer that is independent of the plated metal layer is at least 50 microns.

20. The semiconductor package of claim 12, wherein a combined thickness of the plated metal layer and the first metal layer greater than a thickness of the second metal layer.

21. A semiconductor package, comprising: a dielectric; a metal layer within the dielectric; a plated metal layer plated on top of the metal layer and having a thickness ranging from 30 microns to 60 microns; a semiconductor die coupled to the plated metal layer; and a mold compound under the semiconductor die.

22. The semiconductor package of claim 21, wherein a top surface of the metal layer along a perimeter of the metal layer is independent of the plated metal layer.

23. The semiconductor package of claim 21, wherein the mold compound includes a mold compound filler of size between 60 microns to 80 microns.
