

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250283332

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

BAUR; Joel et al.

STRUCTURE AND CONSTRUCTION METHOD

Abstract

A core wall structure is assembled by attaching together elements of lightweight thermal insulation material (16) and elements of mineral board (20), positioned between them to serve as webs (20) at spaced intervals. Opposing edges (22) of the webs (20) are exposed on outer surfaces (26,28) of the core wall structure, with recesses (24) around them. Skins (18) of cement-based plaster are applied to the outer surfaces (26,28) to cover the core wall structure at least in part and to embed the exposed edges (22) of the webs (20) at least in part in the cement-based plaster.

Inventors: BAUR; Joel (Cape Town, ZA), BÜELER; Benno (Winterthur, CH), GRAF; Andreas (Pieterlen, CH)

Applicant: Citra Group AG (Winterthur, CH)

Family ID: 1000008621058

Appl. No.: 19/215864

Filed: May 22, 2025

Foreign Application Priority Data

GB	2301325.3	Jan. 30, 2023
ZA	2023/08056	Aug. 21, 2023

Related U.S. Application Data

parent WO continuation PCT/IB2023/060338 20231013 PENDING child US 18951815
parent US division 18951815 20241119 parent-grant-document US 12331519 child US 19215864

Publication Classification

Int. Cl.: E04C2/288 (20060101); B32B13/02 (20060101); B32B13/04 (20060101)

U.S. Cl.:

CPC **E04C2/2885** (20130101); **B32B13/02** (20130101); **B32B13/04** (20130101);
B32B2250/03 (20130101); B32B2250/40 (20130101); B32B2307/304 (20130101);
B32B2607/00 (20130101)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS [0001] This application is a division of U.S. patent application Ser. No. 18/951,815, filed Nov. 19, 2024, which is a continuation of International Patent Application No. PCT/IB2023/060338, filed Oct. 13, 2023, which claims the benefit of GB Patent Application No. 2301325.3, filed Jan. 30, 2023, and ZA Application No. 2023/08056, filed Aug. 21, 2023, each of which content are incorporated herein in their entirety and by this reference thereto.

FIELD OF THE INVENTION

[0002] This invention relates to the construction of buildings, including buildings for human habitation and for other purposes, and including single or multiple storey buildings.

BACKGROUND

[0003] Conventional building technologies such as brick and mortar are often complemented with thermal insulation. Thermal insulation is applied in addition to other functional elements of the building, such as structural walls. This increases costs, time for construction, and requires additional space. Especially in buildings with space, cost, or weight constraints such as affordable housing or high-rise buildings, this approach of adding layers of different functions can cause problems and in some instances prevent buildings from being economically or technically feasible.

[0004] Attempts have been made to combine structural and thermal elements, e.g. by providing pre-manufactured building modules, but construction methods developed to date fall short in at least one of: material cost; labour cost; structural integrity; thermal performance; durability (e.g. being weather proof); practicality (e.g. mounting objects on walls with fasteners driven into walls or by drilling holes into walls); extendibility with conventional tools and skills; or design freedom (e.g. rooms beyond certain dimensions dictated by logistical constraints of pre-manufactured building modules).

[0005] Building elements that span horizontally are frequently constructed from steel reinforced concrete, with the steel reinforcement in a tension zone, lower in the building element. However, while steel is stronger than concrete under tension, it is also prone to corrosion and to protect reinforcing steel in horizontally spanning concrete structures against moisture and corrosion, the steel is typically spaced from the underside of the structure, so that the steel is covered with a minimum coverage of concrete on the underside of the structure. The concrete below the steel reinforcement is not strong under tension and add little to the strength of the structure, but adds significantly to its weight and cost. Also, the concrete below the steel reinforcement is prone to cracking under tension, which shortens the lifespan of these structures.

[0006] The present invention seeks to provide for the construction of buildings that addresses these shortfalls, at least in part.

SUMMARY

[0007] According to one aspect of the present invention there is provided a structure comprising: an core wall structure comprising elements of lightweight thermal insulation material and webs of mineral board, said core wall structure having two opposing outer surfaces and said webs being positioned between the elements of lightweight material at spaced intervals to extend across the core wall structure, with opposing edges of the webs being exposed on the opposing outer surfaces

of the core wall structure; and skins of cement-based plaster extending on the opposing outer surfaces of the core wall structure to cover the opposing sides of core wall structure at least in part; wherein the exposed edges of the webs are embedded at least in part in the skins of cement-based plaster on the opposing sides of the core wall structure.

[0008] The word “wall” is used herein to refer to a generally thin structure with generally parallel opposing surfaces, which could be upright (such as the inner and outer walls of a building), but it could also be horizontal (such as roofs and floors) or have any other orientations and it could be curved or straight in one or more dimensions.

[0009] The skins of cement-based plaster may be reinforced around the exposed edges of the webs, where those exposed edges are embedded in the skins of cement-based plaster. Preferably, edges of the elements of lightweight thermal insulation material are recessed (e.g. chamfered or rounded) adjacent the exposed edges of the webs, to provide space for the reinforcement of the skins of cement-based plaster.

[0010] According to another aspect of the present invention, there is provided a method of construction, said method comprising: assembling a core wall structure by positioning elements of lightweight thermal insulation material and webs of mineral board, said core wall structure having two opposing outer surfaces and said webs of mineral board being positioned between the elements of lightweight material to serve as connectors at spaced intervals, said webs extending across the core wall structure, with opposing edges of the webs being exposed on the opposing outer surfaces of the core wall structure; providing recesses around the exposed edges of the webs at the opposing outer surfaces of the core wall structure; applying skins of cement-based plaster to the opposing outer surfaces of the core wall structure to cover the core wall structure at least in part and to embed the exposed edges of the webs at least in part in the cement-based plaster.

[0011] The step of providing recesses around the exposed edges of the webs may comprise recessing edges of the elements of lightweight thermal insulation material adjacent the exposed edges of the webs, e.g. by chamfering or rounding the edges of the lightweight thermal insulation material.

[0012] The lightweight thermal insulation material may be expanded polystyrene, the mineral board may be magnesium oxide board, and the skins of cement-based plaster may include embedded reinforcement such as wire mesh or fibres.

[0013] The reinforcement embedded in the skins of cement-based plaster may include elongate tensile elements such as steel rods or basalt fibre reinforcement, embedded within one or both of the skins of cement-based plaster and the tensile elements may be aligned with the webs, e.g. the tensile elements may extend within one of the skins of cement-based plaster in close proximity to one of the embedded edges of one of the webs. The skin of cement-based plaster may be reinforced around the tensile element.

[0014] The method may include attaching a plurality of the core wall structures together before applying the skins of cement-based plaster to the opposing outer surfaces of the core wall structures and may include attaching the webs of adjacent core wall structures to each other.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0015] For a better understanding of the present invention, and to show how it may be carried into effect, the invention will now be described by way of non-limiting example, with reference to the accompanying drawings in which:

[0016] FIG. 1 shows a partly transparent three-dimensional view of a first embodiment of a structure in the form of a dwelling according to the present invention;

[0017] FIG. 2 shows a cross-sectional view of part of a second embodiment of a structure

according to the present invention;

[0018] FIG. **3** shows a cross-sectional view of part of a third embodiment of a structure according to the present invention; and

[0019] FIG. **4** shows a cross-sectional view of part of a fourth embodiment of a structure according to the present invention.

DETAILED DESCRIPTION OF THE DRAWINGS

[0020] Referring to FIGS. **1** and **2**, a first embodiment of a structure according to the present invention, in the form of a dwelling, is identified generally by reference sign **10** and a second embodiment of a structure according to the invention, in the form of a wall, is generally identified by reference sign **12**. The wall **12** can have any orientation or shape and can serve the purpose of an external or internal wall of structural or non-structural nature and can be part of a roof. The dwelling **10** is constructed from multiple walls such as the wall **12**, some of which are angled and curved to form a roof **14** of the dwelling.

[0021] Referring to FIG. **2**, in the present invention, thermal insulation material **16** is provided at the core of the wall **12** and the main structural elements of the wall are two structural skins **18** on the opposing sides of the wall—which could be exterior and interior sides of the wall, for example. The two skins **18** are structurally connected at regular intervals by webs **20** with exposed edges **22** that are embedded in the skins. The term “exposed” is used in this context to refer to the fact that the opposing edges of the webs **20** are exposed from the thermal insulation material **16** and it does not necessarily mean that the edges protrude beyond the outer surfaces of the thermal insulation material. In fact in some instances the edges of the webs **20** are exposed from the adjacent thermal insulation material **16** within recesses formed along edges of the thermal insulation, but the edges of the webs are set back from the outer surfaces of the thermal insulation material. (This is shown particularly clearly in FIG. **3**.)

[0022] The thermal insulation material **16** can be any suitable lightweight, thermally insulating material and one example that is highly suitable and cost-effective, is expanded polystyrene (EPS).

[0023] The structural skins **18** are made of a cement-based high strength plaster that is preferably reinforced with a mesh or fibres and the plaster can be applied in multiple layers.

[0024] The webs **20** are made of mineral boards with suitable mechanical properties that are preferably similar to the mechanical properties of the skins **18** and one example of mineral board that is highly suitable and cost-effective, is Magnesium Oxide board (MgO).

[0025] The connections between the exposed edges **22** of the webs **20** and the structural skins **18** are preferably strengthened with local thickening of the structural skins around the exposed edges. This is preferably achieved through a diagonal chamfer **24** along the edges of the EPS **16** adjacent the webs **20**. A diagonal chamfer **24** is easy and cost-effective to form or cut (in the process described below), but in other embodiments, the shape of thickening of the structural skins **18** around the exposed edges **22** could take different forms—e.g. it could be rounded or could take the form of rectangular recesses.

[0026] The wall **12** primarily obtains its structural strength from the skins **18** and the webs **20** that effect load transfer (including compressive, tension, bending, and/or shear loads) between the structural skins. In addition to transferring loads between the skins **18**, the webs **20** also increase the bending strength of the wall **12** by increasing the space between the skins, similar to the web of an I-beam increasing the second moment of area of the beam.

[0027] When the dwelling **10** or any other structure is constructed according to the present invention, core wall structures or panels are first assembled from elements in the form of blocks of the EPS **16** and elements in the form of strips of the MgO boards to form the webs **20**.

[0028] The EPS **16** is typically cut from a block with a hot-wire CNC cutter and the webs **20** are typically cut from MgO board with a router CNC cutter. The EPS elements **16** and MgO webs **20** are then assembled into core wall structures in the form of wall and roof panels of different sizes. The EPS elements **16** and webs **20** are preferably attached together using a suitable adhesive such

as polyurethane foam, although other attachment methods could be used instead. To serve their structural function best, each of the webs **20** extends continuously across the core panel. The cutting and assembly of the core panels can take place off site, e.g. in a factory or warehouse that need not be close to the construction site—or it can be done on site, if preferred.

[0029] Once assembled, each panel of the core wall structure has two opposing outer surfaces and for the purposes of illustration, these surfaces are identified as a top surface **26** and bottom surface **28** as shown in FIG. 2.

[0030] The webs **20** are spaced apart at intervals along the panel between the blocks of EPS **16** and each web extends across the panel so that the opposing edges **22** of each web are exposed from the EPS **16** on the opposing outer surfaces **26,28**. The spacing and orientation of the webs **20** may be varied in different panels and is dictated by the structural requirements and manufacturing constraints, to provide appropriate load transfer for the structural strength required of the particular wall **12**.

[0031] Recesses are provided around the exposed edges **22** of the webs **20** and in the illustrated embodiment, this is done by recessing edges of the blocks of EPS **16** adjacent the exposed edges with the diagonal chamfers **24**, but in other embodiments, the edges of the blocks of EPS could be rounded or could be rectangular recesses and/or the exposed edges **22** could protrude beyond the outer surfaces **26,28**.

[0032] Once the core wall panels have been assembled, they are transported to site and erected to form a thermal core of the wall **12** with the webs **20** preferably oriented to follow the direction of load transfer. The webs **20** of adjacent panels are preferably aligned and can be connected together to effect load-transfer between them, e.g. the webs of adjacent core panels can be connected by tongue-and-groove connections, but could also be attached by steel straps, or the like. In some embodiments of the invention, the webs **20** of adjacent core panels may be attached together, e.g. with clamps or rods. The erected structure is preferably temporarily supported (e.g. with braces, straps, and props) at this stage in order to hold the panels in their precise positions during application of the structural skins **18**. Panels can be connected with adhesive such as polyurethane foam, fasteners, interlocking connections (such as tongue and groove connections), or the like to provide additional stability in high stress areas such as panels of the roof **14**.

[0033] Once core wall panels are secured in position, the structural skins **18** are applied to the outer surfaces **26,28** of the panels in layers, generally working from the top of the structure downwards and from the outside of the structure inwards. The structural skins **18** can be applied by hand or spray application where the thermal core forms both the substrate and lost shutter.

[0034] The webs **20** provide structural strength to the core panels while the core panels are being erected and assembled, so that the support and bracing that is required is primarily to ensure precise positioning of the core panels. Furthermore, the webs **20** provide sufficient structural strength to the core panels so that the core panels can bear the weight of the structural skins **18** while they are being applied—even for non-vertical walls such as the roof, thus avoiding the need for extensive temporary load support such as scaffolds, props, etc.

[0035] As the structural skins **18** are applied, they cover the outer surfaces **26,28**, but also cover and embed the exposed edges **22** of the webs. The connection between the exposed edges **22** and the skins **18** are reinforced by local thickening of the skins adjacent the exposed edges and the chamfers **24** provide space for the cement-based plaster of the skins to fill and form the reinforcement of the skins around the exposed edges.

[0036] Referring to FIG. 3, a third embodiment of a structure according to the invention, in the form of a wall, is generally identified by reference sign **13**. The wall **13** has many similarities in common with the wall **12** shown in FIG. 2, including EPS thermal insulation elements **16**, structural skins **18** of cement-based high strength plaster, webs **20** of mineral boards such as Magnesium Oxide board (MgO), and exposed edges **22** of the webs are embedded in the structural skins.

[0037] The manner in which the webs **20** are embedded in the structural skin **18** applied to the top surface **26** in the wall **13** of FIG. **3** is identical to that in the wall **12** of FIG. **2**, but the manner in which the webs are embedded in the structural skin applied to the bottom surface **28** is different from that shown in FIG. **2**.

[0038] FIG. **3** shows two embodiments of recesses that are formed along bottom corners of the EPS elements **16**. These embodiments of recesses would not necessarily be used in combination in practice (although they might), but they are shown in a single drawing for conciseness.

[0039] The recess **30** shown on the left in FIG. **3** is triangular and is cut deeper into the EPS elements **16** than shown in FIG. **3**, whereas the recess **24** shown on the right in FIG. **3** is identical to the recess at the top of the web **20**. In both recesses **30,24** the exposed edge **22** of the web **20** protrudes beyond the EPS elements **16** on either side of it, but the exposed edge of the web **20** on the left in FIG. **3** is recessed from the core panel as a whole. The result is that the recess **30** is much larger than the recesses **24** shown in FIG. **2** and tensile elements such as reinforcing rods **34** are embedded in the bottom structural skin **18**. The reinforcing rods **34** can be made of steel, basalt fibres, high molecular weight polyethylene, carbon, or other alkaline resisting material with high tensile strength.

[0040] The reinforcing rods **34** are positioned before the structural skin **18** is applied and are each aligned with one of the webs **20**. In the example of the web **20** and reinforcing rod **34** shown on the left in FIG. **3**, the reinforcing rod is in close proximity to the exposed edge **22** of the web. However, in the example of the web **20** and reinforcing rod **34** shown on the right in FIG. **3**, the reinforcing rod is in contact with the exposed edge **22** of the web.

[0041] Once the structural skin **18** is applied, both the reinforcing rods **34** and the exposed edges **22** of the webs **20** are embedded in the thickened portion of the skin **18** formed in the recesses **30,24**, so that both the reinforcing rods and the webs can contribute to the strength of the structure **13** by transferring loads to/from the skins **18**. The structural function of the webs **20** has been described above and this is synergistically supplemented with the ability of the reinforcing rods **34** to bear tensile loads, so that the structure **13** has remarkable bending strength and light weight, so that it can be used for large structures such as floors or roofs, with far less supports such as columns, than are required in current building methods.

[0042] Referring to FIG. **4**, a fourth embodiment of a structure according to the invention, in the form of a wall, is generally identified by reference sign **15**. The wall **15** has many similarities in common with the wall **13** shown in FIG. **3**, including EPS thermal insulation elements **16**, structural skins **18** of cement-based high strength plaster, webs **20** of mineral boards, and exposed edges **22** of the webs and reinforcing rods **34** that are embedded in the structural skins.

[0043] The manner in which the webs **20** and reinforcing rods **34** are embedded in the structural skins **18** in the wall **15** of FIG. **4** are very similar to those in the wall **13** of FIG. **3**, but the reinforcing rods **34** are made of basalt rebar, but could instead be made of fibreglass rebar or other non-corrosive high-tensile material.

[0044] When the wall **15** is used with a horizontal orientation as shown in FIG. **4**, the basalt rebar rods **34** are below the lower edges **22** of the webs **20** and are in the tension zone, below a neutral axis **36** of the wall. The rebar rods **34** are covered on their underside with cementitious material of the structural skin **18** on the underside of the wall **15**, but since the rebar rods are made of basalt, they do not need to be embedded as deeply in the cementitious material as steel rebar would have required to protect it from moisture. In the illustrated, preferred embodiment, bottom edges of the rebar rods **34** are aligned with the bottom surfaces of the thermal insulation elements **16** on a common axis **38**.

[0045] The wall **15** can be used in any orientation, but it is particularly advantageous when used in horizontal or part-horizontal orientations, e.g. for roofs, internal floor slabs, foundations, or in connections between building elements where high tensile strength is required.

[0046] The wall **15** is constructed generally as described above, with reference to FIGS. **1** and **2**.

The basalt rebar reinforcing rods **34** are placed in the tension zone at the edges **22** of the webs **20** either in the factory or after erection of the panels on site. If the wall **15** is used horizontally, the rebar rods **34** need to be temporarily supported while applying the cementitious plaster to form the bottom skin **18**. The plaster is preferably applied in two coats: A first base coat of about 2 to 5 mm thickness of the cementitious plaster is applied on the side of the panel with the greatest tensile design strength—which is the underside as shown in the FIG. **4**. A second base coat of about 2 to 5 mm thickness is applied on the opposite side of the panel (the top, as illustrated in FIG. **4**). A first main coat of the cementitious material is applied on the side of the panel with the lower tensile design strength (the top, as illustrated in FIG. **4**). Thereafter, the cementitious material is allowed to cure sufficiently before removing the temporary supports and applying a second main coat on the side with the greater tensile design strength (the bottom, as illustrated in FIG. **4**).

[0047] The wall **15** can also be constructed using steel rebar, but then more cementitious material of the skin **18** will be required to cover the rebar and this would lead to greater weight and reduced span width.

Claims

1. A method of construction, comprising: assembling a core wall structure by attaching together elements of lightweight thermal insulation material and rigid mineral boards, said core wall structure having two opposing outer surfaces and at least some of said mineral boards being positioned between the elements of lightweight material at spaced intervals, each of said mineral boards extending transversely across the core wall structure, with opposing edges of the mineral boards being exposed on the opposing outer surfaces of the core wall structure; providing recesses around the exposed edges of the mineral boards at the opposing outer surfaces of the core wall structure; applying skins of cement-based plaster to the opposing outer surfaces of the core wall structure to cover the core wall structure at least in part and to embed the exposed edges of the mineral boards at least in part in the cement-based plaster.
2. A method according to claim 1, which includes reinforcing at least one of the skins of cement-based plaster.
3. A method according to claim **12** which includes providing elongate tensile elements adjacent one of the opposing outer surfaces of the core wall structure, said tensile elements being aligned with the mineral boards, and embedding the elongate tensile elements in the skin of cement-based plaster when applying said cement-based plaster to the outer surface of the core wall structure.
4. A method according to claim **12**, which includes positioning at least some of said tensile elements to extend in close proximity to one of the embedded edges of one of the mineral boards, before applying the cement-based plaster to the outer surface of the core wall structure.
5. A method according to claim **12**, wherein the tensile elements are made of basalt.
6. A method according to claim 1, wherein the step of providing recesses around the exposed edges of the mineral boards comprises recessing edges of the elements of lightweight thermal insulation material adjacent the exposed edges of the mineral boards.
7. A method according to claim 1, wherein the lightweight thermal insulation material is expanded polystyrene.
8. A method according to claim 1, wherein each of the mineral boards comprise magnesium oxide board.
9. A method according to claim 1, which includes attaching a plurality of the core wall structures together before applying the skins of cement-based plaster to the opposing outer surfaces of the core wall structures.
10. A method according to claim 9, which includes attaching the mineral boards of adjacent core

wall structures to each other before applying the skins of cement-based plaster to the opposing outer surfaces of the core wall structures.
