

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12412817
Kind Code	B2
Date of Patent	September 09, 2025
Inventor(s)	Lai; Chi-Hui et al.

Integrated circuit package and method

Abstract

In an embodiment, a device includes: a package component including: a first integrated circuit die; an encapsulant at least partially surrounding the first integrated circuit die; a redistribution structure on the encapsulant, the redistribution structure physically and electrically coupling the first integrated circuit die; a first module socket attached to the redistribution structure; an interposer attached to the redistribution structure adjacent the first module socket, the outermost extent of the interposer extending beyond the outermost extent of the redistribution structure; and an external connector attached to the interposer.

Inventors: Lai; Chi-Hui (Taichung, TW), Chun; Shu-Rong (Zhubei, TW), Pan; Kuo Lung (Hsinchu, TW), Kuo; Tin-Hao (Hsinchu, TW), Tsai; Hao-Yi (Hsinchu, TW), Liu; Chung-Shi (Hsinchu, TW), Yu; Chen-Hua (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Co., Ltd. (Hsinchu, TW)

Family ID: 71732611

Assignee: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Appl. No.: 17/977301

Filed: October 31, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20230053190 A1	Feb. 16, 2023

Related U.S. Application Data

continuation parent-doc US 17227608 20210412 US 11488897 child-doc US 17977301
division parent-doc US 16529119 20190801 US 10978382 20210413 child-doc US 17227608
us-provisional-application US 62798600 20190130

Publication Classification

Int. Cl.: H01L23/498 (20060101); H01L21/48 (20060101); H01L21/56 (20060101); H01L23/00 (20060101); H01L23/31 (20060101); H01L23/538 (20060101)

U.S. Cl.:

CPC H01L23/49811 (20130101); H01L21/4853 (20130101); H01L21/565 (20130101); H01L23/3107 (20130101); H01L23/49838 (20130101); H01L23/5386 (20130101); H01L24/09 (20130101); H01L2224/02371 (20130101); H01L2224/02379 (20130101)

Field of Classification Search

CPC: H01L (23/49811); H01L (24/19-20)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8361842	12/2012	Yu et al.	N/A	N/A
8680647	12/2013	Yu et al.	N/A	N/A
8703542	12/2013	Lin et al.	N/A	N/A
8759964	12/2013	Pu et al.	N/A	N/A
8778738	12/2013	Lin et al.	N/A	N/A
8785299	12/2013	Mao et al.	N/A	N/A
8803306	12/2013	Yu et al.	N/A	N/A
8809996	12/2013	Chen et al.	N/A	N/A
8829676	12/2013	Yu et al.	N/A	N/A
8877554	12/2013	Tsai et al.	N/A	N/A
2011/0291288	12/2010	Wu et al.	N/A	N/A
2013/0026468	12/2012	Yoshimuta et al.	N/A	N/A
2013/0062760	12/2012	Hung et al.	N/A	N/A
2013/0062761	12/2012	Lin et al.	N/A	N/A
2013/0168848	12/2012	Lin et al.	N/A	N/A
2013/0307140	12/2012	Huang et al.	N/A	N/A
2014/0029639	12/2013	Zarbock	372/50.1	G02B 6/4269
2014/0203429	12/2013	Yu et al.	N/A	N/A
2014/0225222	12/2013	Yu et al.	N/A	N/A
2014/0252646	12/2013	Hung et al.	N/A	N/A
2014/0264930	12/2013	Yu et al.	N/A	N/A
2017/0062383	12/2016	Yee et al.	N/A	N/A
2017/0199328	12/2016	Shubin	N/A	G02B 6/1228
2019/0317287	12/2018	Raghunathan	N/A	G02B 6/426
2019/0326273	12/2018	Bhagavat et al.	N/A	N/A
2023/0260983	12/2022	Lee	257/668	H01L 23/34

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
117594579	12/2023	CN	H01L 23/49816

Background/Summary

PRIORITY CLAIM AND CROSS-REFERENCE (1) This application is a continuation of U.S. patent application Ser. No. 17/227,608, filed on Apr. 12, 2021, entitled “Integrated Circuit Package and Method,” which is a divisional of U.S. patent application Ser. No. 16/529,119, filed on Aug. 1, 2019, entitled “Integrated Circuit Package and Method,” now U.S. Pat. No. 10,978,382, issued on Apr. 13, 2021, which claims the benefit of U.S. Provisional Application No. 62/798,600, filed on Jan. 30, 2019, which applications are hereby incorporated herein by reference.

BACKGROUND

(1) As semiconductor technologies continue to evolve, integrated circuit dies are becoming increasingly smaller. Further, more functions are being integrated into the dies. Accordingly, the numbers of input/output (I/O) pads needed by dies has increased while the area available for the I/O pads has decreased. The density of the I/O pads has risen quickly over time, increasing the difficulty of die packaging.

(2) In some packaging technologies, integrated circuit dies are singulated from wafers before they are packaged. An advantageous feature of this packaging technology is the possibility of forming fan-out packages, which allow the I/O pads on a die to be redistributed to a greater area. The number of I/O pads on the surfaces of the dies may thus be increased.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1 illustrates a cross-sectional view of an integrated circuit die, in accordance with some embodiments.

(3) FIGS. 2-11 illustrate cross-sectional views of intermediate steps during a process for forming a package component, in accordance with some embodiments.

(4) FIG. 12 is a top-down view of a package component, in accordance with some embodiments.

(5) FIG. 13 illustrates a cross-sectional view of a system-on-wafer assembly, in accordance with some embodiments.

(6) FIG. 14 illustrates a cross-sectional view of module installation in a system-on-wafer assembly, in accordance with some embodiments.

(7) FIGS. 15A, 15B, 15C, and 15D illustrate cross-sectional views of system-on-wafer assemblies, in accordance with other embodiments.

(8) FIGS. 16A-19B are various views of intermediate steps during a process for attaching an interposer to a package component, in accordance with some embodiments.

DETAILED DESCRIPTION

(9) The following disclosure provides many different embodiments, or examples, for implementing different features of the invention. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are

not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(10) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

(11) In accordance with some embodiments, fan-out interposer(s) are integrated on a system-on-wafer, such as a super-large fan-out wafer-level package (FOWLP), allowing the available I/O pin count for the system-on-wafer to be expanded. The fan-out interposer(s) are attached at the edges of the wafer, and extend beyond the edges of the wafer. External connectors are then attached to the interposer(s). The external connectors may thus extend beyond the outermost extent of the wafer, thereby increasing the surface area available for the external connectors. More external connectors may thus be included with the system-on-wafer.

(12) FIG. 1 illustrates a cross-sectional view of an integrated circuit die **50**, in accordance with some embodiments. The integrated circuit die **50** will be packaged in subsequent processing to form an integrated circuit package component. The integrated circuit die **50** may be a logic die (e.g., central processing unit (CPU), graphics processing unit (GPU), system-on-a-chip (SoC), application processor (AP), microcontroller, etc.), a memory die (e.g., dynamic random access memory (DRAM) die, static random access memory (SRAM) die, etc.), a power management die (e.g., power management integrated circuit (PMIC) die), a radio frequency (RF) die, a sensor die, a micro-electro-mechanical-system (MEMS) die, a signal processing die (e.g., digital signal processing (DSP) die), a front-end die (e.g., analog front-end (AFE) dies), an application-specific die (e.g., an application-specific integrated circuit (ASIC), a field-programmable gate array (FPGA), etc.), the like, or combinations thereof.

(13) The integrated circuit die **50** may be formed in a wafer, which may include different device regions that are singulated in subsequent steps to form a plurality of integrated circuit dies. The integrated circuit die **50** may be processed according to applicable manufacturing processes to form integrated circuits. For example, the integrated circuit die **50** includes a semiconductor substrate **52**, such as silicon, doped or undoped, or an active layer of a semiconductor-on-insulator (SOI) substrate. The semiconductor substrate **52** may include other semiconductor materials, such as germanium; a compound semiconductor including silicon carbide, gallium arsenic, gallium phosphide, indium phosphide, indium arsenide, and/or indium antimonide; an alloy semiconductor including SiGe, GaAsP, AlInAs, AlGaAs, GaInAs, GaInP, and/or GaInAsP; or combinations thereof. Other substrates, such as multi-layered or gradient substrates, may also be used. The semiconductor substrate **52** has an active surface (e.g., the surface facing upwards in FIG. 1), sometimes called a front side, and an inactive surface (e.g., the surface facing downwards in FIG. 1), sometimes called a back side. Devices may be formed at the front surface of the semiconductor substrate **52**. The devices may be active devices (e.g., transistors, diodes, etc.) or passive devices (e.g., capacitors, resistors, inductors, etc.).

(14) An interconnect structure **54** is over the semiconductor substrate **52**, and interconnects the devices to form an integrated circuit. The interconnect structure **54** may be formed by, for example, metallization patterns in dielectric layers on the semiconductor substrate **52**. The metallization

patterns include metal lines and vias formed in one or more low-k dielectric layers. The metallization patterns of the interconnect structure **54** are electrically coupled to the devices of the semiconductor substrate **52**. The integrated circuit die **50** further includes pads, such as aluminum pads, to which external connections are made. The pads are on the active side of the integrated circuit die **50**, such as in and/or on the interconnect structure **54**. One or more passivation films may be on the integrated circuit die **50**, such as on portions of the interconnect structure **54**. Die connectors **56**, such as conductive pillars (for example, formed of a metal such as copper), are physically and electrically coupled to the interconnect structure **54**. The die connectors **56** may be formed by, for example, plating, or the like. The die connectors **56** electrically couple the respective integrated circuits of the integrated circuit die **50**.

(15) Optionally, solder regions (e.g., solder balls or solder bumps) may be disposed on the pads of the interconnect structure **54**. The solder balls may be used to perform chip probe (CP) testing on the integrated circuit die **50**. CP testing may be performed on the integrated circuit die **50** to ascertain whether the integrated circuit die **50** is a known good die (KGD). Thus, only integrated circuit dies **50**, which are KGDs, undergo subsequent processing and packaging, and dies, which fail the CP testing, are not packaged. After testing, the solder regions may be removed in subsequent processing steps.

(16) A dielectric layer **58** may (or may not) be on the active side of the integrated circuit die **50**, such as on the passivation films and the die connectors **56**. The dielectric layer **58** laterally encapsulates the die connectors **56**, and the dielectric layer **58** is laterally coterminous with the integrated circuit die **50**. Initially, the dielectric layer **58** may bury the die connectors **56**, such that the topmost surface of the dielectric layer **58** is above the topmost surfaces of the die connectors **56**. In some embodiments where solder regions are disposed on the die connectors **56**, the dielectric layer **58** may also bury the solder regions. Alternatively, the solder regions may be removed prior to forming the dielectric layer **58**.

(17) The dielectric layer **58** may be a polymer such as polybenzoxazole (PBO), polyimide, benzocyclobutene (BCB), or the like; a nitride such as silicon nitride or the like; an oxide such as silicon oxide, phosphosilicate glass (PSG), borosilicate glass (BSG), boron-doped phosphosilicate glass (BPSG), or the like; the like, or a combination thereof. The dielectric layer **58** may be formed, for example, by spin coating, lamination, chemical vapor deposition (CVD), or the like. In some embodiments, the die connectors **56** are exposed through the dielectric layer **58** during formation of the integrated circuit die **50**. In some embodiments, the die connectors **56** remain buried and are exposed during a subsequent process for packaging the integrated circuit die **50**. Exposing the die connectors **56** may remove any solder regions that may be present on the die connectors **56**.

(18) In some embodiments, the integrated circuit die **50** is a stacked device that includes multiple semiconductor substrates **52**. For example, the integrated circuit die **50** may be a memory device such as a hybrid memory cube (HMC) device, a high bandwidth memory (HBM) device, or the like that includes multiple memory dies. In such embodiments, the integrated circuit die **50** includes multiple semiconductor substrates **52** interconnected by through-substrate vias (TSVs). Each of the semiconductor substrates **52** may (or may not) have an interconnect structure **54**.

(19) FIGS. 2-11 illustrate cross-sectional views of intermediate steps during a process for forming a package component **100**, in accordance with some embodiments. The package component **100** is a reconstructed wafer having multiple package regions, with one or more of the integrated circuit dies **50** being packaged in each of the package regions. The package regions include computing sites **102** and connecting sites **104**. Each of the computing sites **102** may have e.g., logic functions, memory functions, or the like, and the package component **100** may be a single computing device comprising the computing sites **102** and connecting sites **104**, such as a system-on-wafer assembly. For example, the package component **100** may be an artificial intelligence (AI), machine learning (ML), or deep learning (DL) accelerator, and each computing site **102** may be a neural network node for the accelerator. Each of the connecting sites **104** may have, e.g., external connectors

(discussed further below), and the computing sites **102** of the package component **100** may connect to external systems through the connecting sites **104**. Example systems for the package component **100** include AI servers, high-performance computing (HPC) systems, high power computing devices, cloud computing systems, edge computing systems, and the like.

(20) As noted above, the package component **100** will be part of a system-on-wafer assembly. As such, the package component **100** is large. For example, the package component **100** can have a surface area in excess of 10,000 mm². A large surface area allows for a large quantity of computing sites **102** and connecting sites **104**. Two computing sites **102**, e.g., computing sites **102A** and **102B**, and two connecting sites **104**, e.g., connecting sites **104A** and **104B**, are illustrated in FIGS. 2-11, but it should be appreciated that the package component **100** may include many computing sites **102** and connecting sites **104**, and the sites may be laid out in a variety of manners.

(21) In FIG. 2, a carrier substrate **106** is provided, and an adhesive layer **108** is formed on the carrier substrate **106**. The carrier substrate **106** may be a glass carrier substrate, a ceramic carrier substrate, or the like. The carrier substrate **106** may be a wafer, such that multiple packages can be formed on the carrier substrate **106** simultaneously. The adhesive layer **108** may be removed along with the carrier substrate **106** from the overlying structures that will be formed in subsequent steps. In some embodiments, the adhesive layer **108** is any suitable adhesive, epoxy, die attach film (DAF), or the like, and is applied over the surface of the carrier substrate **106**.

(22) In FIG. 3, integrated circuit dies **50** are attached to the adhesive layer **108**. A desired type and quantity of integrated circuit dies **50** are attached in each of the computing sites **102A** and **102B** and the connecting sites **104A** and **104B**. In some embodiments, a first type of integrated circuit die, such as a SoC die **50A**, is attached in the computing sites **102A** and **102B**, and a second type of integrated circuit die, such as an I/O interface die **50B**, is attached in the connecting sites **104A** and **104B**. Although a single integrated circuit die **50** is illustrated in some sites, it should be appreciated that multiple integrated circuit dies may be attached adjacent one another in some or all of the sites. When multiple integrated circuit dies are attached in each site, they may be of the same technology node, or of different technology nodes. For example, the integrated circuit dies **50** may include dies formed at a 10 nm technology node, dies formed at a 7 nm technology node, the like, or combinations thereof.

(23) In FIG. 4, an encapsulant **110** is formed on and around the various components. After formation, the encapsulant **110** encapsulates the integrated circuit dies **50**. The encapsulant **110** may be a molding compound, epoxy, or the like, and may be applied by compression molding, transfer molding, or the like. The encapsulant **110** may be applied in liquid or semi-liquid form and then subsequently cured. In some embodiments, the encapsulant **110** is formed over the carrier substrate **106** such that the integrated circuit dies **50** are buried or covered, and a planarization process is then performed on the encapsulant **110** to expose the die connectors **56** of the integrated circuit dies **50**. Topmost surfaces of the encapsulant **110**, die connectors **56**, and dielectric layers **58** are coplanar after the planarization process. The planarization process may be, for example, a chemical-mechanical polish (CMP).

(24) In FIGS. 5 through 7, a redistribution structure **112** (see FIG. 7) having a fine-featured portion **112A** and a coarse-featured portion **112B** is formed over the encapsulant **110** and integrated circuit dies **50**. The redistribution structure **112** includes metallization patterns, dielectric layers, and under-bump metallurgies (UBMs). The metallization patterns may also be referred to as redistribution layers or redistribution lines. The redistribution structure **112** is shown as an example having six layers of metallization patterns. More or fewer dielectric layers and metallization patterns may be formed in the redistribution structure **112**. If fewer dielectric layers and metallization patterns are to be formed, steps and process discussed below may be omitted. If more dielectric layers and metallization patterns are to be formed, steps and processes discussed below may be repeated. The fine-featured portion **112A** and coarse-featured portion **112B** of the redistribution structure **112** include metallization patterns and dielectric layers of differing sizes.

(25) In FIG. 5, the fine-featured portion **112A** of the redistribution structure **112** is formed. The fine-featured portion **112A** of the redistribution structure **112** includes dielectric layers **114**, **118**, **122**, and **126**; and metallization patterns **116**, **120**, and **124**. In some embodiments, the dielectric layers **118**, **122** and **126** are formed from a same dielectric material, and are formed to a same thickness. Likewise, in some embodiments, the conductive features of the metallization patterns **116**, **120** and **124** are formed from a same conductive material, and are formed to a same thickness. In particular, the dielectric layers **118**, **122** and **126** have a first thickness $T_{sub.1}$ that is small, such as in the range of about 7 μm to about 50 μm , and the conductive features of the metallization patterns **116**, **120** and **124** have a second thickness $T_{sub.2}$ that is small, such as in the range of about 2 μm to about 20 μm .

(26) As an example of forming the fine-featured portion **112A** of the redistribution structure **112**, the dielectric layer **114** is deposited on the encapsulant **110**, dielectric layers **58**, and die connectors **56**. In some embodiments, the dielectric layer **114** is formed of a photo-sensitive material such as PBO, polyimide, BCB, or the like, which may be patterned using a lithography mask. The dielectric layer **114** may be formed by spin coating, lamination, CVD, the like, or a combination thereof. The dielectric layer **114** is then patterned. The patterning forms openings exposing portions of the die connectors **56**. The patterning may be by an acceptable process, such as by exposing the dielectric layer **114** to light when the dielectric layer **114** is a photo-sensitive material or by etching using, for example, an anisotropic etch. If the dielectric layer **114** is a photo-sensitive material, the dielectric layer **114** can be developed after the exposure.

(27) The metallization pattern **116** is then formed. The metallization pattern **116** has line portions (also referred to as conductive lines or traces) on and extending along the major surface of the dielectric layer **114**, and has via portions (also referred to as conductive vias) extending through the dielectric layer **114** to physically and electrically couple the die connectors **56** of the integrated circuit dies **50**. As an example to form the metallization pattern **116**, a seed layer is formed over the dielectric layer **114** and in the openings extending through the dielectric layer **114**. In some embodiments, the seed layer is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In some embodiments, the seed layer comprises a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, physical vapor deposition (PVD) or the like. A photoresist is then formed and patterned on the seed layer. The photoresist may be formed by spin coating or the like and may be exposed to light for patterning. The pattern of the photoresist corresponds to the metallization pattern **116**. The patterning forms openings through the photoresist to expose the seed layer. A conductive material is then formed in the openings of the photoresist and on the exposed portions of the seed layer. The conductive material may be formed by plating, such as electroplating or electroless plating, or the like. The conductive material may comprise a metal, like copper, titanium, tungsten, aluminum, or the like. The combination of the conductive material and underlying portions of the seed layer form the metallization pattern **116**. The photoresist and portions of the seed layer on which the conductive material is not formed are removed. The photoresist may be removed by an acceptable ashing or stripping process, such as using an oxygen plasma or the like. Once the photoresist is removed, exposed portions of the seed layer are removed, such as by using an acceptable etching process, such as by wet or dry etching.

(28) The dielectric layer **118** is then deposited on the metallization pattern **116** and dielectric layer **114**. The dielectric layer **118** may be formed in a similar manner and of a similar material as the dielectric layer **114**. The metallization pattern **120** is then formed. The metallization pattern **120** has line portions on and extending along the major surface of the dielectric layer **118**, and has via portions extending through the dielectric layer **118** to physically and electrically couple the metallization pattern **116**. The metallization pattern **120** may be formed in a similar manner and of a similar material as the metallization pattern **116**.

(29) The dielectric layer **122** is then deposited on the metallization pattern **120** and dielectric layer

118. The dielectric layer **122** may be formed in a similar manner and of a similar material as the dielectric layer **114**. The metallization pattern **124** is then formed. The metallization pattern **124** has line portions on and extending along the major surface of the dielectric layer **122**, and has via portions extending through the dielectric layer **122** to physically and electrically couple the metallization pattern **120**. The metallization pattern **124** may be formed in a similar manner and of a similar material as the metallization pattern **116**.

(30) The dielectric layer **126** is deposited on the metallization pattern **124** and dielectric layer **122**. The dielectric layer **126** may be formed in a similar manner and of a similar material as the dielectric layer **114**.

(31) In FIG. **6**, the coarse-featured portion **112B** of the redistribution structure **112** is formed. The coarse-featured portion **112B** of the redistribution structure **112** includes dielectric layers **130**, **134**, and **138**; and metallization patterns **128**, **132**, and **136**. In some embodiments, the dielectric layers **130**, **134**, and **138** are formed from a same dielectric material, and are formed to a same thickness. Likewise, in some embodiments, the conductive features of the metallization patterns **128**, **132**, and **136** are formed from a same conductive material, and are formed to a same thickness. In particular, the dielectric layers **130**, **134**, and **138** have a third thickness $T_{sub.3}$ that is large, such as in the range of about 7 μm to about 50 μm , and the conductive features of the metallization patterns **128**, **132**, and **136** have a fourth thickness $T_{sub.4}$ that is large, such as in the range of about 2 μm to about 20 μm . The third thickness $T_{sub.3}$ is greater than the first thickness $T_{sub.1}$ (see FIG. **5**), and the fourth thickness $T_{sub.4}$ is greater than the second thickness $T_{sub.2}$ (see FIG. **5**).

(32) As an example of forming the coarse-featured portion **112B** of the redistribution structure **112**, the metallization pattern **128** is formed. The metallization pattern **128** has line portions on and extending along the major surface of the dielectric layer **126**, and has via portions extending through the dielectric layer **126** to physically and electrically couple the metallization pattern **124**. As an example to form the metallization pattern **128**, a seed layer is formed over the dielectric layer **126** and in the openings extending through the dielectric layer **126**. In some embodiments, the seed layer is a metal layer, which may be a single layer or a composite layer comprising a plurality of sub-layers formed of different materials. In some embodiments, the seed layer comprises a titanium layer and a copper layer over the titanium layer. The seed layer may be formed using, for example, PVD or the like. A photoresist is then formed and patterned on the seed layer. The photoresist may be formed by spin coating or the like and may be exposed to light for patterning. The pattern of the photoresist corresponds to the metallization pattern **128**. The patterning forms openings through the photoresist to expose the seed layer. A conductive material is then formed in the openings of the photoresist and on the exposed portions of the seed layer. The conductive material may be formed by plating, such as electroplating or electroless plating, or the like. The conductive material may comprise a metal, like copper, titanium, tungsten, aluminum, or the like. The combination of the conductive material and underlying portions of the seed layer form the metallization pattern **128**. The photoresist and portions of the seed layer on which the conductive material is not formed are removed. The photoresist may be removed by an acceptable ashing or stripping process, such as using an oxygen plasma or the like. Once the photoresist is removed, exposed portions of the seed layer are removed, such as by using an acceptable etching process, such as by wet or dry etching.

(33) The dielectric layer **130** is then deposited on the metallization pattern **128** and dielectric layer **126**. In some embodiments, the dielectric layer **130** is formed of a photo-sensitive material such as PBO, polyimide, BCB, or the like, which may be patterned using a lithography mask. The dielectric layer **130** may be formed by spin coating, lamination, CVD, the like, or a combination thereof. The metallization pattern **132** is then formed. The metallization pattern **132** has line portions on and extending along the major surface of the dielectric layer **130**, and has via portions extending through the dielectric layer **130** to physically and electrically couple the metallization pattern **128**. The metallization pattern **132** may be formed in a similar manner and of a similar material as the metallization pattern **128**.

(34) The dielectric layer **134** is then deposited on the metallization pattern **132** and dielectric layer **130**. The dielectric layer **134** may be formed in a similar manner and of a similar material as the dielectric layer **130**. The metallization pattern **136** is then formed. The metallization pattern **136** has line portions on and extending along the major surface of the dielectric layer **134**, and has via portions extending through the dielectric layer **134** to physically and electrically couple the metallization pattern **132**. The metallization pattern **136** may be formed in a similar manner and of a similar material as the metallization pattern **128**.

(35) The dielectric layer **138** is deposited on the metallization pattern **136** and dielectric layer **134**. The dielectric layer **138** may be formed in a similar manner and of a similar material as the dielectric layer **130**.

(36) In FIG. 7, UBMs **140** are formed for external connection to the redistribution structure **112**. The UBMs **140** have bump portions on and extending along the major surface of the dielectric layer **138**, and have via portions extending through the dielectric layer **138** to physically and electrically couple the metallization pattern **136**. As a result, the UBMs **140** are electrically coupled to the integrated circuit dies **50**. The UBMs **140** may be formed in a similar manner and of a similar material as the metallization pattern **136**. In some embodiments, the UBMs **140** have a different size than the metallization patterns **116**, **120**, **124**, **128**, **132**, and **136**.

(37) After formation, the outermost extent of the redistribution structure **112** extends a distance $D_{sub.1}$ from the center of the package component **100**. As noted above, the package component **100** is large. The distance $D_{sub.1}$ is thus also large. For example, the distance $D_{sub.1}$ can be in the range of about 50 mm to about 200 mm.

(38) In FIG. 8, a carrier substrate debonding is performed to detach (or “debond”) the carrier substrate **106** from the encapsulant **110** and integrated circuit dies **50**. In some embodiments, the debonding includes removing the carrier substrate **106** and adhesive layer **108** by, e.g., a grinding or planarization process, such as a CMP. After removal, back side surfaces of the integrated circuit dies **50** are exposed, and the back side surfaces of the encapsulant **110** and integrated circuit dies **50** are level. The structure is then placed on a tape **142**.

(39) In FIG. 9, bolt holes **144** are formed through the package component **100**. The bolt holes **144** may be formed by a drilling process such as laser drilling, mechanical drilling, or the like. The bolt holes **144** may be formed by drilling an outline for the bolt holes **144** with the drilling process, and then removing the material separated by the outline.

(40) In FIG. 10, conductive connectors **146** are formed on the UBMs **140**. The conductive connectors **146** may be ball grid array (BGA) connectors, solder balls, metal pillars, controlled collapse chip connection (C4) bumps, micro bumps, electroless nickel-electroless palladium-immersion gold technique (ENEPIG) formed bumps, or the like. The conductive connectors **146** may include a conductive material such as solder, copper, aluminum, gold, nickel, silver, palladium, tin, the like, or a combination thereof. In some embodiments, the conductive connectors **146** are formed by initially forming a layer of solder or solder paste through evaporation, electroplating, printing, solder transfer, ball placement, or the like. Once a layer of solder has been formed on the structure, a reflow may be performed in order to shape the material into the desired bump shapes.

(41) In FIG. 11, module sockets **148** and interposers **150** are attached to the redistribution structure **112**. The module sockets **148** and interposers **150** are interfaces for external connection to the package component **100** (discussed further below). The module sockets **148** and interposers **150** include pads **152**, such as aluminum pads, which are used for physical and electrical connection to the redistribution structure **112**. The pads **152** of the module sockets **148** and interposers **150** may (or may not) have the same pitch $P_{sub.1}$. For example, the pitch $P_{sub.1}$ can be small, such as in the range of about 0.1 mm to about 1 mm. Attaching the module sockets **148** and interposers **150** may include placing the module sockets **148** and interposers **150** on the redistribution structure **112** using, e.g., a pick-and-place technique, and then reflowing the conductive connectors **146** to

physically and electrically couple the pads **152** to the UBMs **140**. Reflow of the conductive connectors **146** may be performed such that the module sockets **148** and interposers **150** are simultaneously attached to the redistribution structure **112**. In the embodiment shown, the module sockets **148** are attached at the computing sites **102A** and **102B**, and the interposers **150** are attached at the connecting sites **104A** and **104B**. An underfill **154** may be formed to fill the gaps between the module sockets **148** and the redistribution structure **112**. The underfill **154** may be formed by a capillary flow process after the module sockets **148** and interposers **150** are attached, or may be formed by a suitable deposition method before the module sockets **148** and interposers **150** are attached.

(42) The module sockets **148** are electrical and physical interfaces for modules (discussed further below) that may be installed at the computing sites **102A** and **102B** subsequent to manufacture of the package component **100**. For example, a user of the package component **100** may install modules in the module sockets **148** to form completed functional systems at the computing sites **102A** and **102B**. The type of modules selected for installation depends on the type of functional systems desired at the computing sites **102A** and **102B**. Examples of modules that may be installed in the module sockets **148** include memory modules, voltage regulator modules, power supply modules, integrated passive device (IPD) modules, and the like. The module sockets **148** may include different components, such as a chassis, the pads **152**, and contact pins, which may comprise different materials.

(43) The interposers **150** are electrical and physical interfaces for additional external connectors (discussed further below) to the connecting sites **104A** and **104B**. The interposers **150** may include, e.g., a core and one or more metallization layers disposed on opposing sides of the core for fanning in and fanning out electrical connections. Any quantity of metallization layers may be formed in the interposers **150**. For example, the quantity of metallization layers in the interposers **150** can be in the range of 2 to 20. In addition to having the pads **152** at first sides facing the redistribution structure **112**, the interposers **150** also have pads **156** at second sides that are opposite the first sides. The pads **156** have a pitch $P_{sub.2}$, which is larger than the pitch $P_{sub.1}$ of the pads **152**. For example, the pitch $P_{sub.2}$ can be large, such as in the range of about 0.5 mm to about 3 mm, such as about 0.8 mm.

(44) The interposers **150** are placed along the periphery of the package component **100**, with the outermost extents of the interposers **150** extending beyond the outermost extent of the redistribution structure **112**. In particular, the interposers **150** are placed such that their inner edges are disposed a distance $D_{sub.2}$ from the center of the package component **100**, and their outer edges are disposed a distance $D_{sub.3}$ from the center of the package component **100**, where the distance $D_{sub.2}$ is smaller than the distance $D_{sub.1}$ (see FIG. 6), and the distance $D_{sub.3}$ is larger than the distance $D_{sub.1}$. For example, the distance $D_{sub.2}$ can be in the range of about 35 mm to about 140 mm, and the distance $D_{sub.3}$ can be in the range of about 65 mm to about 260 mm. In some embodiments, the distance $D_{sub.2}$ can be at least half of the distance $D_{sub.1}$. A majority of the area of the redistribution structure **112** may be unoccupied by the interposers **150**, thereby increasing the area available for the module sockets **148**.

(45) Further, external connectors **158** are attached to the interposers **150**. The external connectors **158** are electrical and physical interfaces for the package component **100** to external systems. For example, when the package component **100** is installed as part of a larger external system, such as a data center, the external connectors **158** may be used to couple the package component **100** to the external system. Examples of external connectors **158** include receptors for ribbon cables, flexible printed circuits, or the like. The external connectors **158** include pads **160**, which may be similar to (and have the same pitch $P_{sub.2}$ as) the pads **156**. The external connectors **158** may include different components, such as a chassis, the pads **160**, and external connection pins, which may comprise different materials. The external connectors **158** also include conductive connectors **162** on the pads **160**, which may be similar to the conductive connectors **146**. The pads **160** and

conductive connectors **162** are used for physical and electrical connection to the interposers **150**. Attaching the external connectors **158** may include placing the external connectors **158** on the interposers **150** using, e.g., a pick-and-place technique, and then reflowing the conductive connectors **162** to physically and electrically couple the pads **156** and pads **160**. Because they are stacked on the interposers **150**, the external connectors **158** are vertically offset from the module sockets **148** after being attached. The outermost extents of the external connectors **158** thus extend beyond the outermost extent of the redistribution structure **112**. In some embodiments, the external connectors **158** only partially laterally overlap with the redistribution structure **112**. In some embodiments, the external connectors **158** do not laterally overlap with the redistribution structure **112**.

(46) Some HPC systems may need a large quantity of external connections to external systems. For example, when the package component **100** is an AI accelerator, the connecting sites **104** may include thousands or tens of thousands of external connections. However, as noted above, the pads **160** of the external connectors **158** have a large pitch $P_{sub.2}$. Use of the interposers **150** allows the external connectors **158** to extend beyond the outermost extent of the package component **100**, thereby increasing the surface area available for the external connectors **158**. More external connectors **158** may thus be included with the package component **100**, thereby increasing the amount of available external connections.

(47) The module sockets **148** and external connectors **158** may be attached to the redistribution structure **112** in a variety of layouts. The cross-sectional views of FIGS. 2-11 show one example layout. FIG. 12 is a top-down view of the package component **100**, in accordance with some embodiments. In this embodiment, the computing sites **102** are arranged in a grid that includes twenty-five computing sites **102**, and four connecting sites **104** are disposed around the sides of the grid. Each one of the module sockets **148** directly overlies and is electrically coupled to the SoC dies **50A** of a corresponding computing site **102**. Each one of the interposers **150** directly overlies and is electrically coupled to the I/O interface dies **50B** of one or more connecting sites **104**. The interposers **150** and external connectors **158** extend beyond the outermost extent of the package component **100**.

(48) The interposers **150** have a width $W_{sub.1}$ and a length $L_{sub.1}$ in the top-down view. For example, the width $W_{sub.1}$ can be in the range of about 15 mm to about 45.5 mm, and the length $L_{sub.1}$ can be in the range of about 30 mm to about 250 mm. The external connectors **158** likewise have a width $W_{sub.2}$ and a length $L_{sub.2}$ in the top-down view, with the width $W_{sub.2}$ being less than the width $W_{sub.1}$, and the length $L_{sub.2}$ being less than the length $L_{sub.1}$. For example, the width $W_{sub.2}$ can be in the range of about 10 mm to about 32 mm, and the length $L_{sub.2}$ can be in the range of about 20 mm to about 245 mm. Further, the external connectors **158** are spaced apart from one another in the top-down view by a distance $D_{sub.4}$, and are spaced apart from edges of the interposers **150** in the top-down view by a distance $D_{sub.5}$. For example, the distance $D_{sub.4}$ can be in the range of about 0.2 mm to about 2 mm, and the distance $D_{sub.5}$ can be in the range of about 0.2 mm to about 2 mm. Further, the computing sites **102** can have a width $W_{sub.3}$ and a length $L_{sub.3}$ in the top-down view. For example, the width $W_{sub.3}$ can be in the range of about 15 mm to about 36.67 mm, and the length $L_{sub.3}$ can be in the range of about 15 mm to about 36.67 mm. Further, the computing sites **102** are spaced apart from one another in the top-down view by a distance $D_{sub.6}$, and are spaced apart from the connecting sites **104** in the top-down view by a distance $D_{sub.7}$. For example, the distance $D_{sub.6}$ can be in the range of about 0.1 mm to about 0.5 mm, and the distance $D_{sub.7}$ can be in the range of about 0.1 mm to about 0.5 mm.

(49) The module sockets **148**, interposers **150**, and external connectors **158** may be attached to the redistribution structure **112** with several techniques. As discussed further below, in some embodiments, the module sockets **148**, interposers **150**, and external connectors **158** are attached by the use of adjustable jig, which allows the interposers **150** to be supported before they are

physically coupled to the redistribution structure **112**. Other techniques may also be used to attach the module sockets **148**, interposers **150**, and external connectors **158**.

(50) FIG. **13** illustrates a cross-sectional view of a system-on-wafer assembly, in accordance with some embodiments. The system-on-wafer assembly is formed by securing the package component **100** between a thermal module **200** and a mechanical brace **300**. The thermal module **200** may be a heat sink, a heat spreader, a cold plate, or the like. The mechanical brace **300** is a rigid support that may be formed from a material with a high stiffness, such as a metal, e.g., steel, titanium, cobalt, or the like. The mechanical brace **300** physically engages portions of the redistribution structure **112**. Warpage of the package component **100**, such as that induced by carrier substrate debonding, may be reduced by clamping the package component **100** between the thermal module **200** and mechanical brace **300**. The mechanical brace **300** is a grid that has openings exposing portions of the module sockets **148**, for ease of module installation.

(51) The package component **100** is removed from the tape **142** and is fastened between the thermal module **200** and mechanical brace **300** with bolts **202**. The bolts **202** are threaded through the bolt holes **144** of the package component **100**, through corresponding bolt holes in the thermal module **200**, and through corresponding bolt holes in the mechanical brace **300**. Fasteners **204** are threaded onto the bolts **202** and tightened to clamp the package component **100** between the thermal module **200** and mechanical brace **300**. The fasteners **204** may be, e.g., nuts that thread to the bolts **202**. The fasteners **204** attach to the bolts **202** at both sides of the system-on-wafer assembly (e.g., at the side having the thermal module **200** (sometimes referred to as the back side) and at the side having the mechanical brace **300** (sometimes referred to as the front side)). After being attached, portions of the mechanical brace **300** are disposed between the module sockets **148**, and between the module sockets **148** and interposers **150**.

(52) Before fastening together the various components, a thermal interface material (TIM) **208** may be dispensed on the back side of the package component **100**, physically and thermally coupling the thermal module **200** to the integrated circuit dies **50**. In some embodiments, the TIM **206** is formed of a film comprising indium and a HM03 type material. During fastening, the fasteners **204** are tightened, thereby increasing the mechanical force applied to the package component **100** by the thermal module **200** and the mechanical brace **300**. The fasteners **204** are tightened until the thermal module **200** exerts a desired amount of pressure on the TIM **206**.

(53) FIG. **14** illustrates a cross-sectional view of a system-on-wafer assembly after modules **400** are installed in the module sockets **148**. As noted above, the modules **400** may be memory modules, voltage regulator modules, power supply modules, integrated passive device (IPD) modules, or the like. The modules **400** comprise conductive connectors **402**, which are inserted in corresponding receptors to physically and electrically couple the contact pins of the module sockets **148**. The modules **400** are thus secured in the module sockets **148**, forming completed functional systems at the computing sites **102A** and **102B**.

(54) FIGS. **15A**, **15B**, **15C**, and **15D** illustrate cross-sectional views of system-on-wafer assemblies, in accordance with other embodiments. In these embodiments, other features are attached to the interposers **150**, in addition to the external connectors **158**. In FIG. **15A**, device modules **164** are attached to the interposers **150**, adjacent the external connectors **158**. In FIG. **15B**, passive devices **166** are attached to the interposers **150**, adjacent the external connectors **158**. In FIG. **15C**, additional module sockets **148** for modules **400** (see FIG. **14**) are attached to the interposers **150**, adjacent the external connectors **158**. In FIG. **15D**, a combination of device modules **164**, passive devices **166**, and module sockets **148** are attached to the interposers **150**, adjacent the external connectors **158**. Any desired combination of connectors and modules may be attached to the interposers **150**.

(55) The device modules **164** may include several types of devices. The device modules **164** may include active devices. For example, the device modules **164** may be logic devices, memory devices, power management devices, radio frequency (RF) devices, signal processing devices,

front-end devices, application-specific devices, I/O devices, the like, or combinations thereof. The device modules **164** may be dies, multi-chip modules (MCMs), fan-out packages, chip-scale packages, or the like, and may be connected to the interposers **150** by flip-chip connections, wire bonds, or the like.

(56) The passive devices **166** may include several types of devices. For example, the passive devices **166** may be resistors such as film resistors, inductors such as coil inductors, capacitors such as metal electrode multilayered ceramic chip (MLCC) capacitors, or the like. The passive devices **166** may be discrete passive devices, or may be integrated passive devices (IPDs).

(57) FIGS. **16A-19B** are various views of intermediate steps during a process for attaching the module sockets **148**, interposers **150**, and external connectors **158** to the package component **100**, in accordance with some embodiments. The illustrated process may be performed, for example, during the intermediate step described above with respect to FIG. **11**. FIGS. **16A**, **17A**, **18A**, and **19A** are cross-sectional views illustrating a single computing site **102A** and a single connecting site **104A** at an edge of a package component **100**. FIGS. **16B**, **17B**, **18B**, and **19B** are top-down views corresponding to the respective cross-sectional views of the package component **100**.

(58) In FIGS. **16A** and **16B**, an adjustable jig is assembled around the package component **100**. The adjustable jig secures the package component **100** in place, and sandwiches it together to reduce wafer warpage during reflowing operations (discussed further below). The adjustable jig includes a bottom jig portion **502**, a middle jig portion **504**, and a top jig portion **506**. The bottom jig portion **502**, middle jig portion **504**, and top jig portion **506** may be formed of metal, such as steel, titanium, cobalt, or the like. The bottom jig portion **502** is placed below the tape **142**, and may be used to support the package component **100** in subsequent processing. The middle jig portion **504** is placed around the package component **100**, and laterally secures the package component **100** in subsequent processing. The top jig portion **506** is placed over the package component **100**, and clamps the package component **100** to reduce wafer warpage in subsequent processing. The bottom jig portion **502** and top jig portion **506** together include a pair of magnets **508**. The magnets **508** hold the bottom jig portion **502** and top jig portion **506** together, and are also used to adjust the middle jig portion **504** during the attaching of the interposers **150** (discussed further below). The magnets **508** may be electromagnets that are coupled to and controlled by a current source (not shown). The middle jig portion **504** is formed of a material that is magnetically attracted to the magnetic field produced by the magnets **508**. The position of the middle jig portion **504** may thus be changed by adjusting the amount of electric current that flows through the magnets **508** in the bottom jig portion **502** and/or the top jig portion **506**. The top jig portion **506** also includes an opening **510**. The opening **510** in the top jig portion **506** exposes the computing sites **102** and connecting site **104** of the package component **100** after the adjustable jig is assembled.

(59) In FIGS. **17A** and **17B**, the module sockets **148** and interposers **150** are attached to the redistribution structure **112**. As discussed above, attaching the module sockets **148** and interposers **150** may include placing the module sockets **148** and interposers **150** on the redistribution structure **112**, and then reflowing the conductive connectors **146**. The module sockets **148** and interposers **150** are placed in the opening **510** of the top jig portion **506**, on the portions of the redistribution structure **112** exposed by the opening **510**. Notably, the interposers **150** may be placed over the redistribution structure **112** and the middle jig portion **504**. After placement, some portions of the interposers **150** laterally extend beyond the outermost extent of the redistribution structure **112** and over the middle jig portion **504**, and other portions of the interposers **150** are laterally confined within the outermost extent of the redistribution structure **112**.

(60) During placement, the middle jig portion **504** may be adjusted to reduce the gap $G_{sub.1}$ between the middle jig portion **504** and the interposers **150**. In particular, the middle jig portion **504** may be adjusted to eliminate or at least reduce the gap $G_{sub.1}$, such that the interposers **150** are substantially level and contact all desired conductive connectors **146**. In some embodiments, the middle jig portion **504** has sufficient throw to allow the gap $G_{sub.1}$ to be adjusted by up to 10 μm

in each direction. Adjusting of the middle jig portion **504** may be accomplished with the magnets **508** by changing the amount of electric current supplied to the magnets **508**. The interposers **150** may thus be supported by the middle jig portion **504** after they are placed and before reflow occurs. After reflowing the conductive connectors **146**, the module sockets **148** and interposers **150** are simultaneously attached to the redistribution structure **112**. The underfill **154** may be formed before or after the module sockets **148** and interposers **150** attached.

(61) In FIGS. **18A** and **18B**, the external connectors **158** are attached to the interposers **150**. Further, module sockets **148**, device modules **164**, and/or passive devices **166** may also be attached to the interposers **150**. As discussed above, attaching the external connectors **158**, module sockets **148**, device modules **164**, and/or passive devices **166** may include placing them on the interposers **150**, and then reflowing the conductive connectors **162**.

(62) In FIGS. **19A** and **19B**, the adjustable jig is removed, including the bottom jig portion **502**, middle jig portion **504**, and top jig portion **506**. Because the components of the adjustable jig are held together by the magnets **508**, removal may be accomplished by pulling apart the bottom jig portion **502** and top jig portion **506** until the forces of the magnets **508** are overcome.

(63) When the module sockets **148**, device modules **164**, and/or passive devices **166** are attached to the interposers **150**, they can have a width $W_{sub.4}$ and a length $L_{sub.4}$ in the top-down view. For example, the width $W_{sub.4}$ can be in the range of about 3 mm to about 9.5 mm, and the length $L_{sub.4}$ can be in the range of about 10 mm to about 30.8 mm. The width $W_{sub.4}$ can be less than the width $W_{sub.2}$ (see FIG. **12**), and the length $L_{sub.4}$ can be less than the length $L_{sub.2}$ (see FIG. **12**). Further, the module sockets **148**, device modules **164**, and/or passive devices **166** on the interposers **150** are spaced apart from one another in the top-down view by a distance $D_{sub.8}$, and are spaced apart from edges of the interposers **150** in the top-down view by a distance $D_{sub.9}$. For example, the distance $D_{sub.8}$ can be in the range of about 0.1 mm to about 0.5 mm, and the distance $D_{sub.9}$ can be in the range of about 0.2 mm to about 2 mm.

(64) Embodiments may achieve advantages. As noted above, the connecting sites **104** may include thousands or tens of thousands of external connections, depending on the type of system implementing the package component **100**. Use of the interposers **150** allows the external connectors **158** to extend beyond the outermost extent of the package component **100**, thereby increasing the surface area available for the external connectors **158**. More external connectors **158** may thus be included, allowing more external connections to be included with the package component **100**.

(65) Other features and processes may also be included. For example, testing structures may be included to aid in the verification testing of the 3D packaging or 3DIC devices. The testing structures may include, for example, test pads formed in a redistribution layer or on a substrate that allows the testing of the 3D packaging or 3DIC, the use of probes and/or probe cards, and the like. The verification testing may be performed on intermediate structures as well as the final structure. Additionally, the structures and methods disclosed herein may be used in conjunction with testing methodologies that incorporate intermediate verification of known good dies to increase the yield and decrease costs.

(66) In an embodiment, a device includes: a package component including: a first integrated circuit die; an encapsulant at least partially surrounding the first integrated circuit die; a redistribution structure on the encapsulant, the redistribution structure physically and electrically coupling the first integrated circuit die; a first module socket attached to the redistribution structure; an interposer attached to the redistribution structure adjacent the first module socket, the outermost extent of the interposer extending beyond the outermost extent of the redistribution structure; and an external connector attached to the interposer.

(67) In some embodiments of the device, the interposer includes first pads on a first side of the interposer, and second pads on a second side of the interposer, the first pads physically and electrically coupling the redistribution structure, the second pads physically and electrically

coupling the external connector, the first pads having a first pitch, the second pads having a second pitch, the second pitch being greater than the first pitch. In some embodiments of the device, the first pitch is in a range of 0.1 mm to 1 mm, and the second pitch is in a range of 0.5 mm to 3 mm. In some embodiments of the device, the interposer includes metallization layers, a quantity of the metallization layers being in a range of 2 to 20. In some embodiments of the device, the outermost extent of the redistribution structure is disposed a first distance from a center of the package component, an inner edge of the interposer is disposed a second distance from the center of the package component, and an outer edge of the interposer is disposed a third distance from the center of the package component, the second distance being less than the first distance, the third distance being greater than the first distance. In some embodiments of the device, the second distance is at least half of the first distance. In some embodiments of the device, the package component further includes: a second integrated circuit die attached to the interposer adjacent the external connector. In some embodiments of the device, the package component further includes: a passive device attached to the interposer adjacent the external connector. In some embodiments of the device, the package component further includes: a second module socket attached to the interposer adjacent the external connector. In some embodiments of the device, the interposer is one of a plurality of interposers attached to the redistribution structure, each of the interposers having an outermost extent extending beyond the outermost extent of the redistribution structure. In some embodiments, the device further includes: a thermal interface material on a back-side surface of the first integrated circuit die; and a thermal module thermally and physically coupled to the back-side surface of the first integrated circuit die with the thermal interface material. In some embodiments, the device further includes: a mechanical brace, the package component being disposed between the thermal module and the mechanical brace; and a bolt extending through the mechanical brace, the package component, and the thermal module. In some embodiments of the device, the package component further includes: an underfill disposed between the interposer and the redistribution structure.

(68) In an embodiment, a method includes: forming a package component including a first integrated circuit die, a redistribution structure physically and electrically coupled to the first integrated circuit die, and conductive connectors physically and electrically coupled to the redistribution structure; assembling a jig around the package component; placing an interposer over the package component and the jig, the jig supporting a first portion of the interposer; adjusting the jig to reduce a gap between the jig and the first portion of the interposer; reflowing the conductive connectors to physically and electrically couple the interposer to the redistribution structure; and removing the jig.

(69) In some embodiments of the method, after removing the jig, the first portion of the interposer laterally extends beyond an outermost extent of the redistribution structure, and a second portion of the interposer is laterally confined within the outermost extent of the redistribution structure. In some embodiments of the method, the jig includes a bottom portion supporting the package component, a top portion having an opening exposing the package component, and a middle portion disposed between the top portion and the bottom portion. In some embodiments of the method, adjusting the jig includes moving the middle portion by adjusting a magnetic field. In some embodiments of the method, placing the interposer over the package component and the jig includes placing the interposer in the opening of the top portion of the jig.

(70) In an embodiment, a method includes: placing integrated circuit dies on a carrier substrate; encapsulating the integrated circuit dies with an encapsulant; forming a redistribution structure over the encapsulant and the integrated circuit dies, the outermost extent of the redistribution structure being disposed a first distance from a center of the redistribution structure; attaching a module socket to the redistribution structure; attaching an interposer to the redistribution structure adjacent the module socket, an inner edge of the interposer being disposed a second distance from the center of the redistribution structure, an outer edge of the interposer being disposed a third distance from

the center of the redistribution structure, the second distance being less than the first distance, the third distance being greater than the first distance; and attaching an external connector to the interposer.

(71) In some embodiments of the method, the second distance is at least half of the first distance.

(72) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A device comprising: a package component comprising: first integrated circuit dies; a redistribution structure on the first integrated circuit dies, an outer edge of the redistribution structure being disposed a first distance from a center of the redistribution structure in a cross-sectional view; first sockets attached to the redistribution structure, the first sockets arranged in a grid in a top-down view; and interposers attached to the redistribution structure, the interposers disposed around the grid of the first sockets in the top-down view, an inner edge of each of the interposers being disposed a second distance from the center of the redistribution structure in the cross-sectional view, an outer edge of each of the interposers being disposed a third distance from the center of the redistribution structure in the cross-sectional view, the second distance being less than the first distance, the third distance being greater than the first distance.
2. The device of claim 1, wherein the first sockets have different widths than the interposers in the top-down view, and the first sockets have different lengths than the interposers in the top-down view.
3. The device of claim 1, wherein the second distance is at least half of the first distance.
4. The device of claim 1, wherein the package component further comprises: external connectors attached to the interposers, the external connectors vertically offset from the first sockets.
5. The device of claim 4, wherein the interposers comprise first pads connected to the redistribution structure and further comprise second pads connected to the external connectors, the first pads and the second pads having different pitches.
6. The device of claim 1, wherein the first sockets comprise first pads connected to the redistribution structure, the interposers comprise second pads connected to the redistribution structure, and the first pads and the second pads have a same pitch.
7. The device of claim 1, wherein the first sockets comprise first pads connected to the redistribution structure, the interposers comprise second pads connected to the redistribution structure, and the first pads and the second pads have different pitches.
8. The device of claim 1 further comprising: a mechanical brace having openings exposing portions of the first sockets; and a thermal module, the package component being disposed between the thermal module and the mechanical brace.
9. The device of claim 8 further comprising: bolts extending through the thermal module, the package component, and the mechanical brace.
10. A device comprising: a package component comprising: an integrated circuit die; an encapsulant at least partially surrounding the integrated circuit die; a redistribution structure on the encapsulant, the redistribution structure connected to the integrated circuit die; a module socket comprising first pads connected to the redistribution structure; a plurality of interposers attached to the redistribution structure, the interposers disposed around the module socket in a top-down view;

and an external connector comprising second pads connected to an interposer of the interposers, the second pads having a greater pitch than the first pads.

11. The device of claim 10, wherein an outer edge of the interposer extends beyond an outer edge of the redistribution structure.

12. The device of claim 10, wherein an outer edge of the external connector extends beyond an outer edge of the redistribution structure.

13. The device of claim 10 further comprising: a mechanical brace; and a thermal module, the package component being disposed between the thermal module and the mechanical brace.

14. A device comprising: a package component comprising: integrated circuit dies; an encapsulant at least partially surrounding the integrated circuit dies; a redistribution structure on the encapsulant, the redistribution structure comprising redistribution lines connected to the integrated circuit dies; module sockets attached to a center of the redistribution structure; a first interposer attached to a first edge of the redistribution structure; and external connectors attached to the first interposer, the external connectors extending beyond the first edge of the redistribution structure.

15. The device of claim 14 further comprising: a second interposer attached to a second edge of the redistribution structure, the module sockets disposed between the first interposer and the second interposer in a top-down view.

16. The device of claim 14, wherein the external connectors partially vertically overlap the redistribution structure.

17. The device of claim 14, wherein the external connectors do not vertically overlap the redistribution structure.

18. The device of claim 14, wherein the external connectors are vertically offset from the module sockets.

19. The device of claim 14 further comprising: a mechanical brace having openings exposing the module sockets in a top-down view; and a thermal module, the package component being disposed between the thermal module and the mechanical brace.

20. The device of claim 19 further comprising: bolts extending through the thermal module, the package component, and the mechanical brace.
