

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250286015

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

Moon; Byung Hoon et al.

PIEZOELECTRIC MATERIALS FOR ON-DIE THERMAL ENHANCEMENT OF HYBRID BONDING AND ASSOCIATED SYSTEMS AND METHODS

Abstract

A semiconductor die is provided, comprising a semiconductor substrate; a dielectric layer over the semiconductor substrate; a bond pad in the dielectric layer, the bond pad including an exposed top surface that is recessed with respect to a surface of the dielectric layer opposite to the semiconductor substrate; and a region of piezoelectric material in the dielectric layer, wherein the region is located proximate to the bond pad to supply thermal energy to the bond pad in response to exposing the piezoelectric material to an externally-applied field.

Inventors: Moon; Byung Hoon (Taichung, TW), Kirby; Kyle K. (Eagle, ID)

Applicant: Micron Technology, Inc. (Boise, ID)

Family ID: 1000008626546

Appl. No.: 19/217479

Filed: May 23, 2025

Related U.S. Application Data

parent US continuation 17898330 20220829 parent-grant-document US 12334469 child US 19217479

Publication Classification

Int. Cl.: H01L23/00 (20060101)

U.S. Cl.:

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S)

[0001] The present application claims priority to U.S. patent application Ser. No. 17/898,330, filed Aug. 29, 2022, the disclosure of which is incorporated herein by reference in its entirety.

TECHNICAL FIELD

[0002] The present disclosure generally relates to semiconductor device assemblies, and more particularly relates to piezoelectric materials for on-die thermal enhancement of hybrid bonding and associated systems and methods.

BACKGROUND

[0003] Semiconductor packages typically include one or more semiconductor dies (e.g., memory chips, microprocessor chip, imager chip) mounted on a package substrate and encased in a protective covering. The semiconductor die may include functional features, such as memory cells, processor circuits, or imager devices, as well as bond pads electrically connected to the functional features. The bond pads can be electrically connected to corresponding conductive structures of the package substrate, which may be coupled to terminals outside the protective covering such that the semiconductor die can be connected to higher level circuitry.

[0004] In some semiconductor packages, two or more semiconductor dies are stacked on top of each other to reduce the footprint of the semiconductor packages. The semiconductor dies in the stack may be arranged in a pattern resembling stair-steps (which may be referred to as “shingle stacking”) such that a portion of the semiconductor dies may be freely accessible—e.g., to attach bond wires to one or more bond pads located in the portion. In some cases, the semiconductor dies may be stacked in a “zig-zag” pattern to increase a space above the bond pads with respect to a semiconductor die overlying above the bond pads so as to facilitate forming the bond wires. Such arrangements, however, tend to increase overall heights of the semiconductor packages. Further, the bond wires may add to the heights and/or introduce delays in signal propagation.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0005] Many aspects of the present technology can be better understood with reference to the following drawings. The components in the drawings are not necessarily to scale. Instead, emphasis is placed on illustrating clearly the overall features and the principles of the present technology.

[0006] FIG. 1 illustrates various stages of process steps for direct bonding schemes.

[0007] FIG. 2 illustrates example schematic diagrams depicting stages of forming semiconductor die assemblies in accordance with embodiments of the present technology.

[0008] FIG. 3 illustrates top-down views of conductive pads of semiconductor dies in accordance with embodiments of the present technology.

[0009] FIG. 4 is a flowchart of a method of forming semiconductor die assemblies in accordance with embodiments of the present technology.

[0010] FIG. 5 is a block diagram schematically illustrating a system including a semiconductor die assembly in accordance with embodiments of the present technology.

DETAILED DESCRIPTION

[0011] Specific details of several embodiments of on-die temperature control for semiconductor die assemblies, and associated systems and methods are described below. The term “semiconductor device or die” generally refers to a solid-state device that includes one or more semiconductor materials. Examples of semiconductor devices (or dies) include logic devices or dies, memory devices or dies, controllers, or microprocessors (e.g., central processing unit (CPU), graphics processing unit (GPU)), among others.

[0012] Such semiconductor devices may include integrated circuits or components, data storage elements, processing components, and/or other features manufactured on semiconductor substrates. Further, the term “semiconductor device or die” can refer to a finished device or to an assembly or other structure at various stages of processing before becoming a finished functional device. Depending upon the context in which it is used, the term “substrate” may include a semiconductor wafer, a package substrate, a semiconductor device or die, or the like. Suitable steps of the methods described herein can be performed with processing steps associated with fabricating semiconductor devices (wafer-level and/or die-level) and/or manufacturing semiconductor packages.

[0013] Various computing systems or environments, e.g., high-performance computing (HPC) systems, require high bandwidth and low power consumption. Certain schemes of forming interconnects between semiconductor dies (e.g., a direct bonding scheme) may facilitate satisfying the requirements, as well as providing form-factors suitable for scaling physical dimensions (e.g., heights) of semiconductor die assemblies of the HPC systems. The direct bonding scheme includes individual conductive components (e.g., copper pads, conductive pads, bond pads) of a first semiconductor die (or a first wafer including the first semiconductor die) aligned and directly bonded to corresponding one of conductive components of a second semiconductor die (or a second wafer including the second semiconductor die).

[0014] Further, a dielectric material surrounding each of the conductive components of the first semiconductor die can be directly bonded to another dielectric material surrounding each of the conductive components of the second semiconductor die. In other words, the bonding interface includes two or more dissimilar materials of the first semiconductor die directly bonded to corresponding materials of the second semiconductor die (e.g., between dielectric materials, between conductive materials) to form interconnects and surrounding dielectric layers. As such, the direct bonding scheme may also be referred to a combination bonding scheme, a hybrid bonding scheme, or the like.

[0015] In some embodiments, the conductive materials include copper (or other suitable conductive materials or metals, such as tungsten) as a primary constituent, and the dielectric materials include silicon oxides (e.g., SiO_2), silicon nitrides (e.g., Si_3N_4), silicon carbon nitrides (e.g., SiCN), silicon carbonates (e.g., SiCO), or the like. During the direct bonding process, the dielectric materials of the first and second semiconductor dies (or the first and second wafers including the first and second semiconductor dies) are brought together such that the dielectric materials adhere to each other and hermetically seal the conductive components aligned to each other.

[0016] Subsequently, the semiconductor dies are annealed at an elevated temperature (e.g., post bond annealing process) such that the conductive materials of the conductive components can expand—e.g., swell vertically toward the bonding interface—at least partially due to the differences in coefficients of thermal expansion (CTE) between the conductive materials and the dielectric materials (which may be referred to as CTE-based expansion). Eventually, the conductive materials are conjoined to form permanent bonding between them—e.g., metallurgical bonding. Additionally, the dielectric materials may enhance their bonding strength during the post bond annealing process.

[0017] In some embodiments, the post bond annealing temperature may reach approximately 400° C. or higher. As the semiconductor dies include fully processed semiconductor components (e.g., diodes, metal-oxide-semiconductor field-effect-transistors (MOSFETs)), the additional thermal

budget during the annealing process may degrade electrical characteristics of the semiconductor components and/or performance of the circuits including the semiconductor components (e.g., integrated circuitry). Accordingly, eliminating the post bond annealing process steps or reducing the post bond annealing process temperature may avoid risks to the semiconductor dies undergoing the direct bonding process steps.

[0018] The present technology provides localized thermal energy to facilitate CTE-based expansion of the conductive components (e.g., copper pads) such that the conductive components form metallurgical bonding at a lower post bond annealing temperature (or without the post bond annealing process, in some cases). The localized thermal energy may be sufficiently far from the integrated circuitry so as to avoid or reduce adverse effects stemming from the localized thermal energy. Accordingly, the present technology can mitigate risks associated with the thermal budget during the hybrid bonding process steps.

[0019] The localized thermal energy may be obtained by generating heat with one or more regions of piezoelectric material that are located proximate to the conductive components, where the piezoelectric material can generate the heat for the conductive components during the hybrid bonding process, for example, in response to an alternating (e.g., oscillating and/or rotating) electric field. In this manner, in some embodiments, the localized thermal energy supplements the thermal energy provided by the post bond annealing process—e.g., permitting the use of a lower environmental (e.g., oven) temperature during the post bond annealing process. In some embodiments, the localized thermal energy generated by the piezoelectric material may suffice to replace the thermal energy provided by the post bond annealing process, thereby eliminating the post bond annealing process.

[0020] As used herein, the terms “front,” “back,” “vertical,” “lateral,” “down,” “up,” “top,” “bottom,” “upper,” and “lower” can refer to relative directions or positions of features in the semiconductor device assemblies in view of the orientation shown in the Figures. For example, “upper” or “uppermost” can refer to a feature positioned closer to the top of a page than another feature. These terms, however, should be construed broadly to include semiconductor devices having other orientations. Unless stated otherwise, terms such as “first” and “second” are used to arbitrarily distinguish between the elements such terms describe. Thus, these terms are not necessarily intended to indicate temporal or other prioritization of such elements.

[0021] FIG. 1 illustrates various stages of process steps for direct bonding schemes. Diagram **100A** illustrates a portion of a semiconductor die **101** with a substrate **110** having integrated circuitry (not shown) and a through-substrate via (TSV) **115** coupled with the integrated circuitry. In some embodiments, the TSV **115** includes a first conductive material **117** (e.g., tungsten) and a conductive barrier layer **118** (e.g., TiN). The semiconductor die **101** also includes a conductive pad **125** (which may also be referred to as a bond pad) formed in a dielectric layer **120** (e.g., silicon oxides, silicon nitrides, silicon carbon nitrides, silicon carbonates, or a combination thereof). The conductive pad **125** is electrically connected to the TSV **115** (and to the integrated circuitry through the TSV **115**). In some embodiments, the conductive pad **125** includes a second conductive material **127** (e.g., copper) and another conductive barrier layer **128** (e.g., TaN).

[0022] The conductive pad **125** depicted in diagram **100A** includes a surface recessed by a depth **D** with respect to the surface of the dielectric layer **120** (i.e., the surface opposite to the substrate **110**). In some embodiments, CMP process steps are used to form the conductive pad **125**, and the recess may be a result of the CMP process. For example, the recess may be formed during over-polishing steps that remove excessive conductive material **127** on the surface of the dielectric layer **120**.

Moreover, the amount of recess (e.g., the recess depth **D**) may be targeted to ensure the surface of the conductive pad **125** not to protrude above the surface of the dielectric layer **120**—e.g., to avoid such protruded conductive pads **125** interfering with the bonding process described with reference to diagram **100B**. The amount of recess may be targeted to be within a certain range such that the conductive materials **127** can form an interconnect **140** as described with reference to diagram

100C without compromising the bonding integrity.

[0023] Diagram **100B** illustrates two semiconductor dies **101a** and **101b** (or two wafers including the semiconductor dies **101a** and **101b**) that are attached together such that dielectric materials of the top semiconductor die **101b** and bottom semiconductor die **101a** adhere to each other to form dielectric-to-dielectric bonding **130** at the bonding interface **105**. In some embodiments, the dielectric surfaces are activated (e.g., using a plasma treatment process) to facilitate the bonding of the dielectric surfaces. Also, conductive pads (e.g., the top conductive pad **125b** and the bottom conductive pad **125a**) of the top and bottom semiconductor dies **101a** and **101b** are aligned to face each other but are not connected to each other due to the recessed surfaces of the conductive pads **125a/b**.

[0024] Diagram **100C** illustrates that the bonded dies/wafers are annealed in an elevated temperature (e.g., around 400° C.) such that the conductive materials of the top and bottom conductive pads **125a/b** may expand toward each other in response to receiving thermal energy during the post bond annealing process (e.g., due to the mismatch in CTEs between the conductive materials and the dielectric materials) within the open space defined by the recess surfaces and the dielectric material surrounding the conductive pads **125a/b**.

[0025] When the surfaces of the top and bottom conductive materials are in contact as a result of the CTE-based expansion, the conductive materials are conjoined (e.g., via atomic migration (intermixing, diffusion) from one conductive material to another conductive material) to form metal-to-metal bonding **135**—e.g., metallurgical bonding, permanent bonding. Once the metallurgical bonding is formed between the conductive pads **125a/b** (thus, forming the interconnect **140**), the conductive materials do not separate (or sever) when the bonded dies/wafers are brought to the ambient temperature or operating temperatures of the semiconductor die assemblies. In this manner, the bonding interface **105** includes the dielectric-to-dielectric bonding **130** and the metal-to-metal bonding **135**.

[0026] FIG. 2 illustrates example schematic diagrams **200A** and **200B** depicting stages of forming semiconductor die assemblies in accordance with embodiments of the present technology. Diagram **200A** illustrates a portion of a semiconductor die **201**, which may be an example of or include aspects of the semiconductor die **101** described with reference to FIG. 1. For example, the semiconductor die **201** includes the substrate **110** having integrated circuitry (not shown) and the dielectric layer **120**.

[0027] The semiconductor die **201** also includes one or more conductive pads **225** (also identified individually as **225a-c**) formed in the dielectric layer **120**. The conductive pads **225** may be examples of or include aspects of the conductive pads **125** described with reference to FIG. 1. The TSVs **115** coupling the conductive pads **225** to the integrated circuitry are omitted in FIG. 2. The conductive pad **225** has a surface recessed with respect to the surface of the dielectric layer **120** (the amount of recess denoted as **D**)—e.g., as a result of the CMP process described with reference to FIG. 1. As shown in diagram **200A**, the surface of the conductive pad **225** is uncovered (i.e., exposed).

[0028] The semiconductor die **201** also includes one or more regions **210** of piezoelectric material in the dielectric layer **120**. The regions **210** may be laterally spaced apart from the conductive pads **225**, as illustrated, or may be immediately adjacent the conductive pads (e.g., when the piezoelectric material used is non-conductive). The regions **210** of piezoelectric material may be located proximate to the conductive pads **225** (e.g., with a lateral spacing from the conductive pads **225** less than a width of the conductive pads) such that the piezoelectric material, when energized by an externally-applied alternating electric field, can supply localized thermal energy (due to the mechanical deformation induced by the changes in the electric field) to the conductive pads **225** during the hybrid bonding process. In various embodiments, the piezoelectric material can include one or more ceramics such as barium titanate (BaTiO₃), lead titanate (PbTiO₃), lead zirconate titanate (PZT), potassium niobate (KNbO₃), lithium niobate (LiNbO₃), lithium

tantalate (LiTaO.sub.3), sodium tungstate (Na.sub.2WO.sub.4), sodium potassium niobate (NaKNb), bismuth ferrite (BiFeO.sub.3), or sodium niobate (NaNbO.sub.3), and/or one or more crystalline piezoelectrics such as quartz, gallium orthophosphate (GaPO.sub.4), or langasite (La.sub.3Ga.sub.5SiO.sub.14). The externally-applied electric field may have a frequency of between 500 and 5,000 kHz and a field strength of between 1000 V/m and 500 kV/m.

[0029] Diagram **200B** illustrates two semiconductor dies **201a** and **201b** (or two wafers including the semiconductor dies **201a** and **201b**) that are attached together to form the bonding interface **205** as described with reference to FIG. **1** (e.g., diagram **100B**). As shown in diagram **200B**, two semiconductor dies **201a** and **201b** are arranged such that the conductive pads **225** of the semiconductor dies **201a** and **201b** are aligned to each other—e.g., the conductive pad **225a** aligned to the conductive pad **225d**. The regions **210** of piezoelectric material are disposed below an outermost surface in the dielectric layer **120** such that the dielectric-to-dielectric bonding area and/or bonding strength is not reduced due to the presence of the piezoelectric material. In other embodiments, however, in which the piezoelectric material do not negatively impact the bonding strength of the dielectric material at the bonding interface **205**, the regions may extend all the way to the surface at the bonding interface **205**.

[0030] Subsequently, the piezoelectric material of the regions **210** material may be energized (e.g., by exposing them to an externally-applied alternating electric field) to provide heat energy (e.g., localized thermal energy) to the conductive pads **225**. As a result of energizing the piezoelectric material of the regions **210**, the CTE-based expansion of the conductive pads **225** may occur as indicated with arrows pointing toward the bond interface **205**. For example, the piezoelectric material of region **210a** provides localized thermal energy to the conductive pad **225a** (and to the conductive pad **225d**, in some cases). The semiconductor dies **201a** and **201b** (or the wafers including the semiconductor dies **201a** and **201b**) may also be brought to an elevated temperature to facilitate the CTE-based expansion of the conductive pads **225**. In this regard, the semiconductor dies **201a** and **201b** may be disposed in a chamber in which an alternating electric field may be generated, and which may optionally be heated (e.g., an oven).

[0031] The surface of the conductive pads **225** may expand toward the surface of the dielectric layer **120** (toward the bonding interface **205**) in response to receiving the localized thermal energy provided by the piezoelectric material of the regions **210**. In some embodiments, the surface of the conductive pad **225** expands to (or past) the surface of the dielectric layer **120** (or the bonding interface **205**) in response to receiving the localized thermal energy provided by the piezoelectric material. In such embodiments, the localized thermal energy provided by the piezoelectric material is sufficient to form metallic bonding interface between the conductive pads **225**—e.g., between the conductive pads **225a** and **225d**. Thus, a post bond annealing process may be omitted.

[0032] In some embodiments, the surface of the conductive pad **225** expands toward the surface of the dielectric layer **120** (toward the bonding interface **205**) in response to receiving the localized thermal energy provided by the piezoelectric material of the regions **210**, but may not reach the bonding interface **205**. In such embodiments, the localized thermal energy provided by the piezoelectric material is insufficient to form metallic bonding interface between the conductive pads **225**—e.g., between the conductive pads **225a** and **225d**.

[0033] As such, a post bond annealing process may be carried out to form the metallic bonding interface in addition to energizing (e.g., exposing to an externally-applied alternating electric field) the piezoelectric material **210**. The post bonding annealing process may bring the attached semiconductor dies **201a/b** to a temperature (e.g., 200° C., 250° C., 300° C., or the like) less than the temperature (e.g., 380° C., 400° C., 420° C., or the like) for the conductive pads **225** to directly bond to each other absent the localized thermal energy provided by the piezoelectric material. In other words, the localized thermal energy provided by the energized piezoelectric material may be a portion of the total thermal energy for the surface of the conductive pad **225** to expand to the surface of the dielectric layer **120** (or past the surface of the dielectric layer **120**) to form the metal-

to-metal bonding at the bonding interface **205**.

[0034] In some embodiments, the regions **210** of piezoelectric material can be surrounded (e.g., enclosed) by dielectric material. For example, in addition to being laterally surrounded by such dielectric material, region **210** may also be spaced vertically from other structures (e.g., through silicon vias, lower layers of BEOL metallization, semiconductor circuit elements) to avoid substantial heat transfer to underlying or overlying circuitry. In some embodiments, the dielectric material disposed over the regions **210** of piezoelectric material may be deposited separately from a bulk dielectric material (e.g., with an interface between the later-deposited layer and the bulk dielectric material). The thickness of the overlying dielectric material above the regions **210** of piezoelectric material may be different from spacing of the regions **210** from the conductive pads **225**.

[0035] Although the foregoing example schematic diagrams illustrate both semiconductor dies **201a/b** having regions **210/211** of piezoelectric material, the present technology is not limited thereto. For example, one of the semiconductor dies **201a** or **201b** may not include the regions **210/211** of piezoelectric material.

[0036] FIG. **3** illustrates top-down views of conductive pads **225** of semiconductor dies (e.g., the semiconductor die **201**) in accordance with embodiments of the present technology. Diagram **300A** depicts a conductive pad **225** (a copper pad, a bond pad, a conductive component) having a width (W) and a length (L). In some embodiments, the width and length are comparable as depicted in diagram **300A**. In other embodiments, the width and length are dissimilar (e.g., elongated rectangles). In some embodiments, the width (and/or length) can be less than 1 micrometer (μm). The shape and dimensions of the conductive pad **225** described with reference to FIG. **3** are examples only and the present technology is not limited thereto. For example, conductive pads **225** may have footprints (layout) resembling circles, ellipses, race-tracks, rectangles with dissimilar widths and lengths, or any polygon shapes. Further, the conductive pad **225** can have widths greater than 1, 5, 10 μm , or even greater.

[0037] Diagrams **300B** through **300D** illustrate various arrangements of regions **210/211** of piezoelectric material surrounding the conductive pads **225**. Diagrams **300B**, **300C**, and **300D** may correspond to a top-down view of one of the conductive pads **225** depicted in diagram **200A/B** (or **200B/D**), where the regions **210/211** of piezoelectric material are located proximate to the conductive pads **225**. For example, diagram **300B** illustrates the regions **210/211** of piezoelectric material surrounding (encircling) the conductive pad **225**. Diagram **300C** illustrates that the regions **210/211** of piezoelectric material surrounding the conductive pad **225** includes multiple strips. Diagram **300D** illustrates that the regions **210/211** of piezoelectric material surrounding the conductive pad **225** include multiple patterns of squares or rectangles (which may be referred to as a sea of squares/rectangles), where one or more square/rectangle patterns at least partially overlapping the conductive pad **225** are removed—e.g., during the layout of the conductive pads **225**.

[0038] In some embodiments, some regions **210/211** of piezoelectric material may be larger than other regions **210/211** to provide different amounts of localized thermal energy (e.g., to different size or more remotely-spaced conductive pads **225**). In this regard, the size (e.g., volume) of the regions **210/211** of piezoelectric material may correspond to the volume of the conductive pads **225** to which they are proximate (e.g., having an approximately equivalent volume, having a volume at least 50% of the volume of the conductive pad, having a volume at least 200% of the conductive pad, having a cumulative volume of piezoelectric material in multiple regions proximate to a conductive pad equal to at least some percentage of the volume of the conductive pad, such as 100%, 150%, 200%, 250%, 300%, etc.) In some embodiments, the regions **210/211** of piezoelectric material may be located in one or more regions of the semiconductor dies where the conductive pads **225** are located. For example, some semiconductor dies (e.g., the semiconductor die **201**) may include the conductive pads **225** located in certain regions (e.g., a central region, peripheral

regions, one or more regions near edges) of the semiconductor dies—e.g., for compact layouts of the semiconductor dies, for efficient signal routing schemes. FIG. 3 includes diagrams **300E** through **300G** depicting such regions of the semiconductor dies (e.g., regions including three (3) conductive pads **225**). Although diagrams **300E** through **300G** illustrate three (3) conductive pads **225** in such regions as examples, the present technology is not limited thereto. For example, the region where the conductive pads are located may include several tens of conductive pads, several hundreds of conductive pads, or even more.

[0039] FIG. 4 is a flowchart **400** of a method of forming semiconductor die assemblies in accordance with embodiments of the present technology. The flowchart **400** may include aspects of methods as described with reference to FIGS. 1 through 3. The method comprises providing a first semiconductor die including a first dielectric layer, wherein the first dielectric layer includes a first bond pad with a first top surface exposed and recessed with respect to a first surface of the first dielectric layer, and wherein the first dielectric layer includes a region of piezoelectric material located proximate to the first bond pad (box **410**). The method further comprises providing a second semiconductor die including a second dielectric layer, wherein the second dielectric layer includes a second bond pad with a second top surface exposed and recessed with respect to a second surface of the second dielectric layer (box **420**). The method further comprises attaching the first and second semiconductor dies such that the first surface is in contact with the second surface to form a bonding interface and the first bond pad is aligned to and facing the second bond pad (box **430**). The method further comprises exposing the piezoelectric material to an externally-applied electric field to supply thermal energy to at least the first bond pad such that at least the first top surface of the first bond pad expands toward the bonding interface (box **440**).

[0040] In some embodiments, the thermal energy is sufficient for the first and second top surfaces of the first and second bond pads to bond to each other as a result of supplying the thermal energy to the first and/or second bond pads. In some embodiments, both the first and second top surfaces of the first and second bond pads expand toward to the bonding interface in response to receiving the thermal energy. In some embodiments, the method further comprises heating, concurrently with applying the alternating electric field, the first and second semiconductor dies attached to each other to a first temperature such that the first and second top surfaces of the first and second bond pads expand toward the bonding interface to directly bond to each other, where the first temperature is less than a second temperature for the first and second bond pads to directly bond to each other absent the thermal energy.

[0041] In some embodiments, the region of piezoelectric material is a first region and the thermal energy is a first thermal energy, and the second semiconductor die includes a second region of piezoelectric material, and the method further comprises energizing (e.g., by exposing to an externally-applied alternating electric field) the piezoelectric material of the second region to supply second thermal energy to at least the second bond pad such that the second top surface of the second bond pad expands toward the bonding interface. In some embodiments, a sum of the first and second thermal energy is sufficient for the first and second top surfaces of the first and second bond pads to bond to each other as a result of supplying the first and second thermal energy to the first and/or second bond pads. In some embodiments, the method further comprises heating, concurrently with energizing the piezoelectric materials of the first and second regions, the first and second semiconductor dies attached to each other to a first temperature such that the first and second top surfaces of the first and second bond pads expand toward the bonding interface to directly bond to each other, where the first temperature is less than a second temperature for the first and second bond pads to directly bond to each other absent the first and second thermal energy.

[0042] It should be noted that the methods described above describe possible implementations, and that the operations and the steps may be rearranged or otherwise modified and that other implementations are possible. Furthermore, embodiments from two or more of the methods may be

combined. From the foregoing, it will be appreciated that specific embodiments of the technology have been described herein for purposes of illustration, but that various modifications may be made without deviating from the disclosure. In addition, while in the illustrated embodiments certain features or components have been shown as having certain arrangements or configurations, other arrangements and configurations are possible. Moreover, certain aspects of the present technology described in the context of particular embodiments may also be combined or eliminated in other embodiments.

[0043] FIG. 5 is a block diagram schematically illustrating a system **500** including a semiconductor die assembly in accordance with embodiments of the present technology. The system **500** can include a semiconductor device assembly **570**, a power source **572**, a driver **574**, a processor **576**, and/or other subsystems or components **578**. The semiconductor device assembly **570** can be incorporated into any of a myriad of larger and/or more complex systems, a representative example of which is the system **500** shown schematically in FIG. 5. The semiconductor die assembly described with reference to FIG. 2 may be included in the semiconductor device assembly **570** of the system **500**.

[0044] The semiconductor device assembly **570** can have features generally similar to the semiconductor die assembly described above with reference to FIG. 2. For example, the semiconductor device assembly **570** includes two semiconductor dies (e.g., a first semiconductor die **201a** and a second semiconductor die **201b**) that are directly bonded to each other. The semiconductor dies each includes conductive pads and regions of piezoelectric material in a dielectric layer, where the regions are located proximate to the conductive pads to supply localized thermal energy to the conductive pads in response to energizing the piezoelectric material (e.g., by exposing them to an externally-applied alternating electric field).

[0045] In some embodiments, the conductive pads of the first semiconductor die (e.g., conductive pads **225a-c**) are aligned and directly bonded to the corresponding conductive pads of the second semiconductor die (e.g., conductive pads **225d-f**) based, at least in part, on CTE-based thermal expansion of the conductive pads to conjoin at the bonding interface in response to the localized thermal energy generated by the piezoelectric material. In some embodiments, the conductive pads of the first semiconductor die are directly bonded to the conductive pads of the second semiconductor die at a first temperature less than a second temperature for the thermal expansion of the conductive pads absent the localized thermal energy generated by the piezoelectric material.

[0046] The resulting system **570** can perform any of a wide variety of functions, such as memory storage, data processing, and/or other suitable functions. Accordingly, representative systems **570** can include, without limitation, hand-held devices (e.g., mobile phones, tablets, digital readers, and digital audio players), computers, and appliances. Components of the system **570** may be housed in a single unit or distributed over multiple, interconnected units (e.g., through a communications network). The components of the system **570** can also include remote devices and any of a wide variety of computer readable media.

[0047] The devices discussed herein, including a semiconductor device, may be formed on a semiconductor substrate or die, such as silicon, germanium, silicon-germanium alloy, gallium arsenide, gallium nitride, etc. In some cases, the substrate is a semiconductor wafer. In other cases, the substrate may be a silicon-on-insulator (SOI) substrate, such as silicon-on-glass (SOG) or silicon-on-sapphire (SOS), or epitaxial layers of semiconductor materials on another substrate. The conductivity of the substrate, or sub-regions of the substrate, may be controlled through doping using various chemical species including, but not limited to, phosphorous, boron, or arsenic. Doping may be performed during the initial formation or growth of the substrate, by ion-implantation, or by any other doping means.

[0048] As used herein, including in the claims, “or” as used in a list of items (for example, a list of items prefaced by a phrase such as “at least one of” or “one or more of”) indicates an inclusive list such that, for example, a list of at least one of A, B, or C means A or B or C or AB or AC or BC or

ABC (i.e., A and B and C). Also, as used herein, the phrase “based on” shall not be construed as a reference to a closed set of conditions. For example, an exemplary step that is described as “based on condition A” may be based on both a condition A and a condition B without departing from the scope of the present disclosure. In other words, as used herein, the phrase “based on” shall be construed in the same manner as the phrase “based at least in part on.” The term “exemplary” used herein means “serving as an example, instance, or illustration,” and not “preferred” or “advantageous over other examples.”

[0049] From the foregoing, it will be appreciated that specific embodiments of the invention have been described herein for purposes of illustration, but that various modifications may be made without deviating from the scope of the invention. Rather, in the foregoing description, numerous specific details are discussed to provide a thorough and enabling description for embodiments of the present technology. One skilled in the relevant art, however, will recognize that the disclosure can be practiced without one or more of the specific details. In other instances, well-known structures or operations often associated with memory systems and devices are not shown, or are not described in detail, to avoid obscuring other aspects of the technology. In general, it should be understood that various other devices, systems, and methods in addition to those specific embodiments disclosed herein may be within the scope of the present technology.

Claims

1. A semiconductor die, comprising: a semiconductor substrate; a dielectric layer over the semiconductor substrate; a bond pad in the dielectric layer, the bond pad including an exposed top surface; and a region of piezoelectric material in the dielectric layer, wherein the region is located proximate to the bond pad to supply thermal energy to the bond pad in response to exposing the piezoelectric material to an externally-applied electric field.
2. The semiconductor die of claim 1, wherein: the bond pad is a first bond pad of a plurality of bond pads of the semiconductor die; and the region is a first region of a plurality of regions of the piezoelectric material of the semiconductor die, wherein individual regions of the plurality of regions are located proximate to corresponding bond pads of the plurality of bond pads.
3. The semiconductor die of claim 1, wherein the thermal energy is a portion of total thermal energy for the top surface of the bond pad to expand at least to the surface of the dielectric layer.
4. The semiconductor die of claim 1, wherein the piezoelectric material comprises barium titanate (BaTiO_3), lead titanate (PbTiO_3), lead zirconate titanate (PZT), potassium niobate (KNbO_3), lithium niobate (LiNbO_3), lithium tantalate (LiTaO_3), sodium tungstate (Na_2WO_4), sodium potassium niobate (NaKNb), bismuth ferrite (BiFeO_3), sodium niobate (NaNbO_3), quartz, gallium orthophosphate (GaPO_4), langasite ($\text{La}_3\text{Ga}_5\text{SiO}_{14}$), or a combination thereof.
5. The semiconductor die of claim 1, wherein a lateral spacing between the region of piezoelectric material and the bond pad is less than a width of the bond pad.
6. A method, comprising: providing a first semiconductor device including a first dielectric layer, wherein the first dielectric layer includes a first bond pad with a first top surface exposed, and wherein the first dielectric layer includes a region of piezoelectric material located proximate to the first bond pad; providing a second semiconductor device including a second dielectric layer, wherein the second dielectric layer includes a second bond pad with a second top surface exposed and recessed with respect to a second surface of the second dielectric layer; attaching the first and second semiconductor devices such that the first surface is in contact with the second surface to form a bonding interface and the first bond pad is aligned to and facing the second bond pad; and exposing the piezoelectric material to an externally-applied electric field to supply thermal energy to at least the first bond pad such that at least the first top surface of the first bond pad expands toward the bonding interface.
7. The method of claim 6, wherein the thermal energy is sufficient for the first and second top

surfaces of the first and second bond pads to bond to each other as a result of supplying the thermal energy to the first and/or second bond pads.

8. The method of claim 6, wherein both the first and second top surfaces of the first and second bond pads expand toward to the bonding interface in response to receiving the thermal energy.

9. The method of claim 6, further comprising: heating, concurrently with exposing the piezoelectric material to the externally-applied electric field, the first and second semiconductor devices attached to each other to a first temperature such that the first and second top surfaces of the first and second bond pads expand toward the bonding interface to directly bond to each other, wherein the first temperature is less than a second temperature for the first and second bond pads to directly bond to each other absent the thermal energy.

10. The method of claim 6, wherein the externally-applied electric field is an oscillating electric field or a rotating electric field.

11. The method of claim 6, wherein the externally-applied electric field has a frequency between 500 and 5,000 kHz and a field strength of between 1000 V/m and 500 kV/m.

12. The method of claim 6, wherein the piezoelectric material comprises barium titanate (BaTiO₃), lead titanate (PbTiO₃), lead zirconate titanate (PZT), potassium niobate (KNbO₃), lithium niobate (LiNbO₃), lithium tantalate (LiTaO₃), sodium tungstate (Na₂WO₄), sodium potassium niobate (NaKNb), bismuth ferrite (BiFeO₃), sodium niobate (NaNbO₃), quartz, gallium orthophosphate (GaPO₄), langasite (La₃Ga₅SiO₁₄), or a combination thereof.

13. A semiconductor device assembly, comprising: a first semiconductor device including a first dielectric layer, wherein the first dielectric layer includes a first bond pad and a region of piezoelectric material proximate to the first bond pad; and a second semiconductor device including a second dielectric layer, wherein the second dielectric layer includes a second bond pad; wherein the first dielectric layer and the second dielectric layer are directly bonded by a dielectric-dielectric bond, and wherein the first bond pad and the second bond pad are directly bonded by a metallurgical bond.

14. The semiconductor device assembly of claim 13, wherein: the first bond pad is comprised by a first plurality of bond pads of the first semiconductor device; and the region is a first region of a plurality of regions of piezoelectric material of the first semiconductor device, wherein individual regions of the plurality of regions are located proximate to corresponding bond pads of the first plurality of bond pads.

15. The semiconductor device assembly of claim 13, wherein a lateral spacing between the region of piezoelectric material and the first bond pad is less than a width of the first bond pad.

16. The semiconductor device assembly of claim 13, wherein the second dielectric layer includes a second region of piezoelectric material proximate to the second bond pad.

17. The semiconductor device assembly of claim 16, wherein the first region and the second region are vertically aligned.

18. The semiconductor device assembly of claim 16, wherein: the second bond pad is comprised by a second plurality of bond pads of the second semiconductor device; and the second region is comprised by a second plurality of regions of piezoelectric material of the second semiconductor device, wherein individual regions of the plurality of second regions are located proximate to corresponding bond pads of the second plurality of bond pads.

19. The semiconductor device assembly of claim 16, wherein the first and second pluralities of regions of piezoelectric material are vertically spaced apart from a bond line between the first and second semiconductor devices by portions of the first and second dielectric layer, respectively.

20. The semiconductor device assembly of claim 13, wherein the piezoelectric material comprises barium titanate (BaTiO₃), lead titanate (PbTiO₃), lead zirconate titanate (PZT), potassium niobate (KNbO₃), lithium niobate (LiNbO₃), lithium tantalate (LiTaO₃), sodium tungstate (Na₂WO₄), sodium potassium niobate (NaKNb), bismuth ferrite (BiFeO₃), sodium niobate (NaNbO₃), quartz, gallium orthophosphate (GaPO₄), langasite (La₃Ga₅SiO₁₄), or a combination thereof.

