

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12419040
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Kim; Seok Hyun et al.

Semiconductor device with bit-line structure over cell region isolation film

Abstract

A semiconductor device comprises a substrate comprising a cell region; a cell region isolation film in the substrate and extending along an outer edge of the cell region; a bit-line structure on the substrate and in the cell region, wherein the bit-line structure has a distal end positioned on the cell region isolation film; a cell spacer on a vertical side surface of the distal end of the bit-line structure; an etching stopper film extending along a side surface of the cell spacer and a top face of the cell region isolation film; and an interlayer insulating film on the etching stopper film, and on the side surface of the cell spacer, wherein the interlayer insulating film includes silicon nitride.

Inventors: Kim; Seok Hyun (Incheon, KR), Kim; Young Sin (Hwaseong-si, KR), Park; Dong Sik (Suwon-si, KR), Lee; Jong Min (Hwaseong-si, KR), Choe; Joon Yong (Hwaseong-si, KR)

Applicant: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Family ID: 1000008819137

Assignee: Samsung Electronics Co., Ltd. (Suwon-si, KR)

Appl. No.: 17/515888

Filed: November 01, 2021

Prior Publication Data

Document Identifier	Publication Date
US 20220271044 A1	Aug. 25, 2022

Foreign Application Priority Data

KR	10-2021-0022534	Feb. 19, 2021
----	-----------------	---------------

Publication Classification

Int. Cl.: H10B12/00 (20230101); H01L21/768 (20060101); H10D30/01 (20250101)

U.S. Cl.:

CPC H10B12/482 (20230201); H01L21/76831 (20130101); H10B12/50 (20230201); H10D30/0293 (20250101);

Field of Classification Search

CPC: H10B (12/482); H10B (12/50); H10B (12/485); H10B (12/09); H10B (12/34); H10B (12/053); H10B (12/315); H01L (21/76831); H01L (23/53295); H01L (23/5283); H01L (23/535); H01L (23/5386); H10D (30/0293); H10D (18/60); A23B (2/783); H10F (39/193); H10H (20/8314)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
7687342	12/2009	Haller et al.	N/A	N/A
8445350	12/2012	Han	N/A	N/A
8614509	12/2012	Kim	N/A	N/A
9082647	12/2014	Jang et al.	N/A	N/A
9768176	12/2016	Yoo	N/A	N/A
9947668	12/2017	Lee et al.	N/A	N/A
10504912	12/2018	Shu et al.	N/A	N/A
2011/0309435	12/2010	Hwang et al.	N/A	N/A
2012/0012911	12/2011	Jeong	257/330	H10B 12/482
2018/0350905	12/2017	Yoon	N/A	H10B 12/09
2020/0312845	12/2019	Yoon	N/A	H10D 84/85
2021/0098460	12/2020	Lee	N/A	H10B 12/053

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
20200115762	12/2019	KR	N/A

Primary Examiner: Dulka; John P.

Attorney, Agent or Firm: Wolf, Greenfield & Sacks, P.C.

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

(1) This application claims priority from Korean Patent Application No. 10-2021-0022534, filed on Feb. 19, 2021 in the Korean Intellectual Property Office, and all the benefits accruing therefrom under 35 U.S.C. § 119, the contents of which in its entirety are herein incorporated by reference.

FIELD

(2) The present disclosure relates to a semiconductor device.

BACKGROUND

(3) Semiconductor devices may have increasingly higher degrees or levels of integration. Thus, in order to implement more semiconductor elements in the same area, individual circuit patterns may be increasingly smaller. In other words, as the integration level of the semiconductor device increases, a design rule for components of the semiconductor device is decreasing.

(4) In a highly scaled semiconductor device, a process of forming a plurality of wire lines and a plurality of buried contacts (BC) interposed between the lines may become increasingly complex and difficult.

SUMMARY

(5) A technical purpose of the present disclosure is to provide a semiconductor device that may have improved reliability and performance.

(6) Purposes in accordance with the present disclosure are not limited to the above-mentioned purpose. Other purposes and advantages in accordance with the present disclosure as not mentioned above may be understood from following descriptions and more clearly understood from embodiments in accordance with the present disclosure. Further, it will be readily appreciated that the purposes and advantages in accordance with the present disclosure may be realized by features and combinations thereof as disclosed in the claims.

(7) According to an aspect of the present inventive concept, there is provided a semiconductor device including: a substrate comprising a cell region; a cell region isolation film in the substrate and extending along an outer edge of the cell region; a bit-line structure on the substrate and in the cell region, wherein the bit-line structure has a distal end positioned on the cell region isolation film; a cell spacer on a vertical side surface of the distal end of the bit-line structure; an etching stopper film extending along a side surface of the cell spacer and a top face of the cell region isolation film; and an interlayer insulating film on the etching stopper film, and on the side surface of the cell spacer, wherein the interlayer insulating film comprises silicon nitride.

(8) According to an aspect of the present inventive concept, there is provided a semiconductor device including: a substrate comprising a cell region and a peripheral area along a periphery of the cell region; a cell region isolation film in the substrate and extending along an outer edge of the cell region; a bit-line structure on the substrate and in the cell region, wherein the bit-line structure has a distal end positioned on the cell region isolation film; a peripheral gate structure on the substrate and in the peripheral area; an interlayer insulating film on the cell region isolation film and on the distal end of the bit-line structure; and an inserted insulating film disposed on the cell region isolation film, wherein the inserted insulating film is between the interlayer insulating film and the peripheral gate structure, wherein a side surface of the interlayer insulating film is in contact with the inserted insulating film and is convex toward the inserted insulating film.

(9) According to an aspect of the present inventive concept, there is provided a semiconductor device including: a substrate comprising a cell region and a peripheral area along a periphery of the cell region; a cell region isolation film in the substrate and extending along an outer edge of the cell region to define the cell region; a gate electrode comprising at least a portion in the substrate and in the cell region, wherein the gate electrode extends in a first direction; a bit-line structure on the substrate and in the cell region, wherein the bit-line structure extends in a second direction intersecting the first direction, wherein the bit-line structure has a distal end on the cell region isolation film; a cell spacer on a side surface of the bit-line structure; a peripheral gate structure in the peripheral area and on the substrate, wherein the peripheral gate structure is spaced apart from the bit-line structure in the second direction; an etching stopper film extending along a side surface of the cell spacer, a top face of the cell region isolation film, and an outer face of the peripheral gate structure; and an interlayer insulating film on the etching stopper film and on the side surface of the cell spacer, wherein the interlayer insulating film extends into at least a portion of a space

between the cell spacer and the peripheral gate structure, wherein the interlayer insulating film comprises silicon nitride.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) The above and other aspects and features of the present disclosure will become more apparent by describing in detail example embodiments thereof with reference to the attached drawings, in which:

(2) FIG. 1 is a schematic layout of a semiconductor device according to some implementations;

(3) FIG. 2 is an enlarged schematic layout diagram of a R1 portion of FIG. 1;

(4) FIG. 3 is an enlarged schematic layout diagram showing a R2 portion of FIG. 1;

(5) FIG. 4 is a cross-sectional view taken along a line A-A in FIG. 1;

(6) FIG. 5 is a cross-sectional view taken along a line B-B in FIG. 2;

(7) FIGS. 6, 7, and FIG. 8 are diagrams for illustration of a semiconductor device according to some implementations;

(8) FIGS. 9, 10, 11, 12, and FIG. 13 are diagrams of intermediate structures to illustrate a semiconductor device manufacturing method according to some implementations;

(9) FIG. 14 is a diagram for illustration of a semiconductor device according to some implementations;

(10) FIG. 15 is a diagram of an intermediate structure to illustrate a semiconductor device manufacturing method according to some implementations;

(11) FIG. 16 is a diagram for illustration of a semiconductor device according to some implementations;

(12) FIG. 17 and FIG. 18 are diagrams of intermediate structures for illustration of a semiconductor device manufacturing method according to some implementations;

(13) FIG. 19 is a diagram for illustration of a semiconductor device according to some implementations; and

(14) FIG. 20 is a diagram of an intermediate structure to illustrate a semiconductor device manufacturing method according to some implementations.

DETAILED DESCRIPTION

(15) For simplicity and clarity of illustration, elements in the figures are not necessarily drawn to scale. The same reference numbers in different figures represent the same or similar elements, and as such perform similar functionality. Further, descriptions and details of well-known steps and elements are omitted for simplicity of the description. Furthermore, in the following detailed description of the present disclosure, numerous specific details are set forth in order to provide a thorough understanding of the present disclosure. However, it will be understood that the present disclosure may be practiced without these specific details. In other instances, well-known methods, procedures, components, and circuits have not been described in detail so as not to unnecessarily obscure aspects of the present disclosure.

(16) Examples of various embodiments are illustrated and described further below. It will be understood that the description herein is not intended to limit the claims to the specific embodiments described. On the contrary, it is intended to cover alternatives, modifications, and equivalents as may be included within the spirit and scope of the present disclosure as defined by the appended claims.

(17) A shape, a size, a ratio, an angle, a number, etc. disclosed in the drawings for describing an embodiment of the present disclosure is provided by way of example only, and the present disclosure is not limited thereto.

(18) The terminology used herein is for the purpose of describing particular embodiments only and

is not intended to limit the present disclosure. As used herein, the singular forms “a” and “an” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprises”, “comprising”, “includes”, and “including” when used in this specification, specify the presence of the stated features, integers, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, operations, elements, components, and/or portions thereof. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

Expression such as “at least one of” when preceding a list of elements may modify the entirety of list of elements and may not modify the individual elements of the list. When referring to “C to D”, this means C inclusive to D inclusive unless otherwise specified.

(19) It will be understood that, although the terms “first”, “second”, “third”, and so on may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, a first element, component, region, layer or section described below could be termed a second element, component, region, layer or section, without departing from the spirit and scope of the present disclosure.

(20) In addition, it will also be understood that when a first element or layer is referred to as being present “on” or “beneath” a second element or layer, the first element may be disposed directly on or beneath the second element or may be disposed indirectly on or beneath the second element with a third element or layer being disposed between the first and second elements or layers.

(21) It will be understood that when an element or layer is referred to as being “connected to”, or “coupled to” another element or layer, it may be directly on, connected to, or coupled to the other element or layer, or one or more intervening elements or layers may be present. In addition, it will also be understood that when an element or layer is referred to as being “between” two elements or layers, it may be the only element or layer between the two elements or layers, or one or more intervening elements or layers may also be present.

(22) Further, as used herein, when a layer, film, region, plate, or the like is disposed “on” or “on a top” of another layer, film, region, plate, or the like, the former may directly contact the latter or still another layer, film, region, plate, or the like may be disposed between the former and the latter. As used herein, when a layer, film, region, plate, or the like is directly disposed “on” or “on a top” of another layer, film, region, plate, or the like, the former directly contacts the latter and still another layer, film, region, plate, or the like is not disposed between the former and the latter.

Further, as used herein, when a layer, film, region, plate, or the like is disposed “below” or “under” another layer, film, region, plate, or the like, the former may directly contact the latter or still another layer, film, region, plate, or the like may be disposed between the former and the latter. As used herein, when a layer, film, region, plate, or the like is directly disposed “below” or “under” another layer, film, region, plate, or the like, the former directly contacts the latter and still another layer, film, region, plate, or the like is not disposed between the former and the latter. That is, when elements are “directly” on or beneath or contacting or connected to or coupled to one another, no intervening elements are present.

(23) Unless otherwise defined, all terms including technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this inventive concept belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

(24) In descriptions of temporal relationships, for example, temporal precedent relationships between two events such as “after”, “subsequent to”, “before”, etc., another event may occur therebetween unless “directly after”, “directly subsequent” or “directly before” is indicated.

(25) The features of the various embodiments of the present disclosure may be partially or entirely combined with each other, and may be technically associated with each other or operate with each other. The embodiments may be implemented independently of each other and may be implemented together in an association relationship.

(26) Spatially relative terms, such as “beneath,” “below,” “lower,” “under,” “above,” “upper,” and the like, may be used herein for ease of explanation to describe one element or feature's relationship to another element or feature as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or in operation, in addition to the orientation depicted in the figures. For example, when the device in the figures is turned over, elements described as “below” or “beneath” or “under” other elements or features would then be oriented “above” the other elements or features. Thus, the example terms “below” and “under” can encompass both an orientation of above and below. The device may be otherwise oriented for example, rotated 90 degrees or at other orientations, and the spatially relative descriptors used herein should be interpreted accordingly.

(27) “D1 direction” and “D2 direction” should not be interpreted only to have a geometric relationship in which the D1 direction, and the D2 direction are perpendicular to each other. “D1 direction” and “D2 direction” may be interpreted to have a broader direction within a range in which components herein may work functionally.

(28) FIG. 1 is a schematic layout of a semiconductor device according to some implementations. FIG. 2 is an enlarged schematic layout of a R1 portion of FIG. 1. FIG. 3 is an enlarged schematic layout diagram showing a R2 portion of FIG. 1. FIG. 4 is a cross-sectional view taken along a line A-A in FIG. 1. FIG. 5 is a cross-sectional view taken along a line B-B in FIG. 2.

(29) For reference, FIG. 4 may be a cross-sectional view taken along a bit-line BL of FIGS. 2 and 3.

(30) In a diagram of a semiconductor device according to some implementations, DRAM (Dynamic Random Access Memory) is illustrated by way of example. However, the present disclosure is not limited thereto.

(31) Referring to FIG. 1 to FIG. 5, a semiconductor device according to some implementations may include a cell region 20, a cell region isolation film 22, and a peripheral area or region 24. The cell region isolation film 22 may be formed along an outer edge of the cell region 20. The cell region isolation film 22 may define the cell region 20 or a boundary of the cell region 20. The cell region isolation film 22 may separate the cell region 20 and the peripheral region 24 from each other. The peripheral region 24 may be formed along the periphery of the cell region 20. The peripheral region 24 may be defined as a periphery around the cell region 20.

(32) The cell region 20 may include a plurality of cell active areas ACT. The cell active area ACT may be defined by a cell element separation film 105 formed in the substrate 100. As the design rule of the semiconductor device decreases, the cell active area ACT may have a bar shape extending in a diagonal line or an oblique line as shown in FIG. 2. For example, the cell active area ACT may extend in a third direction D3.

(33) Each of a plurality of gate electrodes may extend in a first direction D1 and across the cell active area ACT. The plurality of gate electrodes may extend parallel to each other. Each of the plurality of gate electrodes may be embodied as, for example, each of a plurality of word-lines WL. The word-lines WL may be spaced from each other by an equal spacing. A width of the word-line WL or a spacing between word-lines WL may be determined according to the design rule.

(34) The two word-lines WL extending in the first direction D1 may allow each cell active area ACT to be divided into three portions. The cell active area ACT may include a storage connection area and a bit-line connection area. The bit-line connection area may be located at a middle portion of the cell active area ACT, while the storage connection area may be located at an end of the cell active area ACT.

(35) A plurality of bit-lines BL extending in a second direction D2 perpendicular to the extension

direction of the word-line WL may be disposed on the word-lines WL. The plurality of bit-lines BL may extend parallel to each other. The bit-lines BL may be arranged to be spaced from each other by the same spacing. A width of the bit-line BL or a spacing between bit-lines BL may be determined according to the design rule.

(36) A semiconductor device according to some implementations may include various contact arrangements formed on the cell active area ACT. The various contact arrangements may include, for example, a direct contact DC, a buried contact BC, and a landing pad LP, etc.

(37) In this connection, the direct contact DC may mean a contact that electrically connects the cell active area ACT to the bit-line BL. The buried contact BC may mean a contact connecting the cell active area ACT to a lower electrode **191** of a capacitor. In terms of an arrangement structure, a contact area between the buried contact BC and the cell active area ACT may be small.

Accordingly, a conductive landing pad LP may be introduced to expand the contact area between the cell active area ACT and the buried contact BC, and to expand the contact area between the buried contact BC and the lower electrode **191** of the capacitor.

(38) The landing pad LP may be disposed between the cell active area ACT and the buried contact BC and may be disposed between the buried contact BC and the lower electrode **191** of the capacitor. In the semiconductor device according to some implementations, the landing pad LP may be disposed between the buried contact BC and the lower electrode **191** of the capacitor. Expanding the contact area via the introduction of the landing pad LP may allow a contact resistance between the cell active area ACT and the lower electrode **191** of the capacitor to be reduced.

(39) The direct contact DC may be connected to the bit-line connection area. The buried contact BC may be connected to the storage connection area. As the buried contact BC is disposed in each of both opposing ends of the cell active area ACT, the landing pad LP may be disposed adjacent to each of both opposing ends of the cell active area ACT and partially overlap with the buried contact BC. In other words, the buried contact BC may be formed to overlap the cell active area ACT and the cell element separation film **105** between adjacent word-lines WL and between adjacent bit-lines BL.

(40) The word-line WL may be formed as a structure buried in the substrate **100**. The word-line WL may extend across the cell active area ACT between the direct contacts DC or between the buried contacts BC. As shown, two word-lines WL may extend through one cell active area ACT. As the cell active area ACT extends along the third direction D3, the extension direction of the word-line WL may have an angle smaller than 90 degrees with respect to the extension direction of the cell active area ACT.

(41) The direct contacts DC and the buried contacts BC may be arranged in a symmetrical manner. Accordingly, the direct contacts DC and the buried contacts BC may be arranged in a straight line or substantially linearly along the first direction D1 and the second direction D2. Unlike the direct contact DC and the buried contact BC, the landing pads LP may be arranged in a zigzag manner in the second direction D2 which the bit-line BL extends. Further, the landing pads LP may overlap with the same portion of a side surface of each bit-line BL in the first direction D1 in which the word-line WL extends. For example, each of the landing pads LP in a first line may overlap with a left side surface of a corresponding bit-line BL, while each of the landing pads LP in a second line may overlap with a right side surface of the corresponding bit-line BL.

(42) Referring to FIG. 3 to FIG. 5, the semiconductor device according to some implementations may include a plurality of cell gate structures **110**, a plurality of bit-line structures **140ST**, a plurality of storage contacts **120**, an information storage **190** and a peripheral gate structure **240ST**.

(43) A substrate **100** may include the cell region **20**, the cell region isolation film **22**, and the peripheral region **24**. The substrate **100** may be a silicon substrate or an SOI (silicon-on-insulator). Alternatively, the substrate **100** may include silicon germanium, SGOI (silicon germanium on insulator), indium antimonide, lead tellurium compound, indium arsenic, indium phosphide, gallium arsenide or gallium antimonide. However, the present disclosure is not limited thereto.

(44) The plurality of cell gate structures **110**, the plurality of bit-line structures **140ST**, the plurality of storage contacts **120**, and the information storage **190** may be disposed in the cell region **20**. The peripheral gate structure **240ST** may be disposed in the peripheral region **24**.

(45) A cell element separation film **105** may be formed in the substrate **100** and in the cell region **20**. The cell element separation film **105** may have an STI (shallow trench isolation) structure with excellent element separation ability. The cell element separation film **105** may define the cell active area ACT within the cell region **20**. The cell active area ACT defined by the cell element separation film **105** may have an elongated island shape including a minor axis and a major axis as shown in FIG. 2. The cell active area ACT may have a diagonally extension shape to have an angle of smaller than 90 degrees with respect to the extension direction of the word-line WL horizontally flush with the cell element separation film **105**. Further, the cell active area ACT may have a diagonally extension shape to have an angle of smaller than 90 degrees with respect to an extension direction of the bit-line BL formed on the cell element separation film **105**.

(46) The cell region isolation film **22** may have an STI structure. The cell region **20** may be defined by the cell region isolation film **22**.

(47) Each of the cell element separation film **105** and the cell region isolation film **22** may include, for example, at least one of a silicon oxide film, a silicon nitride film, and a silicon oxynitride film. However, the present disclosure is not limited thereto. In FIG. 4 and FIG. 5, each of the cell element separation film **105** and the cell region isolation film **22** is shown to be formed as a single insulating film. However, this is shown only for convenience of illustration, and the present disclosure is not limited thereto. Depending on a width of each of the cell element separation film **105** and the cell region isolation film **22**, each of the cell element separation film **105** and the cell region isolation film **22** may be formed as a single insulating film, or as a stack of a plurality of insulating films.

(48) In FIG. 4 and FIG. 5, a top face (e.g., an upper or top surface) of the cell element separation film **105**, a top face of the substrate **100**, and a top face of the cell region isolation film **22** are shown to be horizontally flush with each other. However, this is shown only for convenience of illustration, and the present disclosure is not limited thereto.

(49) The cell gate structure **110** may be formed in the substrate **100** and the cell element separation film **105**. The cell gate structure **110** may be formed along the cell element separation film **105** and the cell active area ACT defined by the cell element separation film **105**. The cell gate structure **110** may include a cell gate trench **115** formed in the substrate **100** and the cell element separation film **105**, a cell gate insulating film **111**, a cell gate electrode **112**, a cell gate capping pattern **113**, and a cell gate capping conductive film **114**. In this connection, the cell gate electrode **112** may act as the word-line WL. Unlike shown in FIGS. 4 and 5, the cell gate structure **110** may not include the cell gate capping conductive film **114**.

(50) The cell gate insulating film **111** may extend along a side wall and a bottom face (e.g., a lower or bottom surface) of the cell gate trench **115**. The cell gate insulating film **111** may extend along a profile of at least a portion of the cell gate trench **115**. The cell gate insulating film **111** may include, for example, at least one of silicon oxide, silicon nitride, silicon oxynitride, or high dielectric constant materials having a higher dielectric constant than that of silicon oxide. The high dielectric constant material may include, for example, hafnium oxide, hafnium silicon oxide, hafnium aluminum oxide, lanthanum oxide, lanthanum aluminum oxide, zirconium oxide, zirconium silicon oxide, tantalum oxide, titanium oxide, barium strontium titanium oxide, barium titanium oxide, strontium titanium oxide, yttrium oxide, aluminum oxide, lead scandium tantalum oxide, lead zinc niobate, and combinations thereof.

(51) The cell gate electrode **112** may be formed on the cell gate insulating film **111**. The cell gate electrode **112** may fill a portion of the cell gate trench **115**. The cell gate capping conductive film **114** may extend along a top face of the cell gate electrode **112**.

(52) The cell gate electrode **112** may include at least one of metal, metal alloy, conductive metal

carbonitride, conductive metal carbide, metal silicide, doped semiconductor material, conductive metal oxynitride, and conductive metal oxide. The cell gate electrode **112** may include at least one of for example, TiN, TaC, TaN, TiSiN, TaSiN, TaTiN, TiAlN, TaAlN, WN, Ru, TiAl, TiAlC—N, TiAlC, TiC, TaCN, W, Al, Cu, Co, Ti, Ta, Ni, Pt, Ni—Pt, Nb, NbN, NbC, Mo, MoN, MoC, WC, Rh, Pd, Ir, Ag, Au, Zn, V, RuTiN, TiSi, TaSi, NiSi, CoSi, IrOx, RuOx, and combinations thereof. However, the present disclosure is not limited thereto. The cell gate capping conductive film **114** may include, for example, polysilicon or polysilicon germanium. However, the present disclosure is not limited thereto.

(53) The cell gate capping pattern **113** may be disposed on the cell gate electrode **112** and the cell gate capping conductive film **114**. The cell gate capping pattern **113** may fill a remaining portion of the cell gate trench **115** except for the cell gate electrode **112** and the cell gate capping conductive film **114**. The cell gate insulating film **111** is shown to extend along a side wall of the cell gate capping pattern **113**. However, the present disclosure is not limited thereto. The cell gate capping pattern **113** may include, for example, at least one of silicon nitride SiN, silicon oxynitride SiON, silicon oxide SiO.sub.2, silicon carbonitride SiCN, silicon oxycarbonitride SiOCN, and combinations thereof.

(54) Although not shown, an impurity doped area may be formed on at least one side of the cell gate structure **110**. The impurity doped area may act as a source/drain area of the transistor.

(55) The bit-line structure **140ST** may include a cell conductive line **140** and a cell line capping film **144**. The cell conductive line **140** may be formed on the substrate **100** including the cell gate structure **110**, and on the cell element separation film **105** formed in the substrate **100**. The cell conductive line **140** may intersect a cell element separation film **105**, and the cell active area ACT defined by the cell element separation film **105**. The cell conductive line **140** may be formed to intersect with the cell gate structure **110**. In this connection, the cell conductive line **140** may act as the bit-line BL.

(56) The cell conductive line **140** may be embodied as a multi-film. The cell conductive line **140** may include, for example, a first cell conductive film **141**, a second cell conductive film **142**, and a third cell conductive film **143**. The first to third cell conductive films **141**, **142**, and **143** may be sequentially stacked on the substrate **100** and the cell element separation film **105**. Although the cell conductive line **140** is shown to be composed of three films, the present disclosure is not limited thereto.

(57) Each of the first to third cell conductive films **141**, **142**, and **143** may include, for example, at least one of a semiconductor material doped with impurities, a conductive silicide compound, a conductive metal nitride, a metal, and a metal alloy. For example, the first cell conductive film **141** may include a doped semiconductor material, the second cell conductive film **142** may include at least one of the conductive silicide compound and the conductive metal nitride, and the third cell conductive film **143** may include at least one of the metal and the metal alloy. However, the present disclosure is not limited thereto.

(58) A bit-line contact **146** may be formed between the cell conductive line **140** and the substrate **100**. That is, the cell conductive line **140** may be formed on the bit-line contact **146**. For example, the bit-line contact **146** may be formed at a point where the cell conductive line **140** intersects a center portion of the cell active area ACT having an elongated island shape. The bit-line contact **146** may be formed between the bit-line connection area and the cell conductive line **140**.

(59) The bit-line contact **146** may electrically connect the cell conductive line **140** and the substrate **100** to each other. In this connection, the bit-line contact **146** may act as the direct contact DC. The bit-line contact **146** may include, for example, at least one of a semiconductor material doped with impurities, a conductive silicide compound, a conductive metal nitride, and a metal.

(60) In an area in which the cell conductive line **140** overlaps a top face of the bit-line contact **146**, the cell conductive line **140** may include the second cell conductive film **142** and the third cell conductive film **143**. In an area in which the cell conductive line **140** does not overlap the top face

of the bit-line contact **146**, the cell conductive line **140** may include the first to third cell conductive films **141**, **142**, and **143**.

(61) In FIG. **4**, it is shown that the bit-line contact **146** is not disposed between the cell conductive line **140** closest to the cell region isolation film **22** and the substrate **100**. However, the present disclosure is not limited thereto. Alternatively, the bit-line contact **146** may be disposed between the cell conductive line **140** closest to the cell region isolation film **22** and the substrate **100**.

(62) The cell line capping film **144** may be disposed on the cell conductive line **140**. The cell line capping film **144** may extend in the second direction D2 and along a top face of the cell conductive line **140**. In this connection, the cell line capping film **144** may include, for example, at least one of silicon nitride, silicon oxynitride, silicon carbonitride, and silicon oxycarbonitride. In a semiconductor memory device according to some implementations, the cell line capping film **144** may include, for example, a silicon nitride film. The cell line capping film **144** is shown to be a single film, but is not limited thereto. The cell line capping film **144** may be a multi-film. However, when films constituting the multi-film are made of the same material, the cell line capping film **144** may act as a single film.

(63) A cell insulating film **130** may be formed on the substrate **100** and the cell element separation film **105**. More specifically, the cell insulating film **130** may be formed on a portion of the top face of the substrate **100** and the cell element separation film **105** on which the bit-line contact **146** is not formed. The cell insulating film **130** may be formed between the substrate **100** and the cell conductive line **140**, and between the cell element separation film **105** and the cell conductive line **140**.

(64) The cell insulating film **130** may be a single film. However, as illustrated, the cell insulating film **130** may be embodied as a multi-film including a first cell insulating film **131** and a second cell insulating film **132**. For example, the first cell insulating film **131** may include a silicon oxide film, while the second cell insulating film **132** may include a silicon nitride film. However, the present disclosure is not limited thereto. In another example, the cell insulating film **130** may be embodied as a triple film including a silicon oxide film, a silicon nitride film, and a silicon oxide film. However, the present disclosure is not limited thereto.

(65) Unlike shown, a cell buffer film including, for example, a silicon oxide film may be further disposed between the cell insulating film **130** and the cell region isolation film **22**.

(66) The bit-line structure **140ST** may extend in an elongated manner in the second direction D2. The bit-line structure **140ST** may include a distal end disposed on the cell region isolation film **22**. A cell spacer portion **281** to be described later may be disposed on a side surface of a distal end of the bit-line structure **140ST**. The cell spacer portion **281** may be disposed on a vertical side surface of a distal end of the bit-line structure **140ST**.

(67) In a semiconductor device according to some implementations, a side surface of the cell insulating film **130** may be substantially vertically flush with a side surface of the bit-line structure **140ST**.

(68) The bit-line structure **140ST** may include a first portion having a first vertical dimension $h1$ and a second portion having a second vertical dimension $h2$ from a top face of the cell insulating film **130**. The second portion may include a distal end of the bit-line structure **140ST**. For example, the second vertical dimension $h2$ may be smaller than the first vertical dimension $h1$. A top face **140ST_2_US** of the second portion may be lower than a top face **140ST_1_US** of the first portion. Accordingly, a top face of the bit-line structure **140ST** may have a step. In an area in which the bit-line structure **140ST** overlaps the cell region isolation film **22**, the top face of the bit-line structure **140ST** may have a step. Alternatively, unlike illustrated, in an area in which the bit-line structure **140ST** does not overlap with the cell region isolation film **22**, the top face of the bit-line structure **140ST** may have a step.

(69) Further, the bit-line structure **140ST** may further include a third portion having a third vertical dimension (e.g., $h3$; not shown) from the top face of the cell insulating film **130**. The first portion

may be disposed between the second portion and the third portion. The third portion may overlap with a pad separation insulating film **180** to be described later. For example, the third vertical dimension may be smaller than the first vertical dimension **h1**. However, the present disclosure is not limited thereto. Further, the third vertical dimension may be different from the second vertical dimension **h2**. Alternatively, the third vertical dimension may be substantially the same as the second vertical dimension **h2**, unlike shown in the drawings.

(70) A fence pattern **170** may be disposed on the substrate **100** and the cell element separation film **105**. The fence pattern **170** may be formed to overlap the cell gate structure **110** formed in the substrate **100** and the cell element separation film **105**. The fence pattern **170** may be disposed between the bit-line structures **140ST** extending in the second direction **D2**. The fence pattern **170** may include, for example, at least one of silicon oxide, silicon nitride, silicon oxynitride, and combinations thereof.

(71) The storage contact **120** may be disposed between the cell conductive lines **140** adjacent to each other in the first direction **D1**. The storage contact **120** may be disposed between fence patterns **170** adjacent to each other in the second direction **D2**. The storage contact **120** may overlap a portion of the substrate **100** and a portion of the cell element separation film **105** between adjacent cell conductive lines **140**. The storage contact **120** may be connected to the storage connection area of the cell active area **ACT**. In this connection, the storage contact **120** may act as the buried contact **BC**.

(72) The storage contact **120** may include, for example, at least one of a semiconductor material doped with impurities, a conductive silicide compound, a conductive metal nitride, and a metal.

(73) The storage pad **160** may be formed on the storage contact **120**. The storage pad **160** may be electrically connected to the storage contact **120**. In this connection, the storage pad **160** may act as the landing pad **LP**.

(74) The storage pad **160** may overlap with a portion of a top face of the bit-line structure **140ST**. The storage pad **160** may include, for example, at least one of a semiconductor material doped with impurities, a conductive silicide compound, a conductive metal nitride, a conductive metal carbide, a metal, and a metal alloy.

(75) The pad separation insulating film **180** may be formed on the storage pad **160** and the bit-line structure **140ST**. For example, the pad separation insulating film **180** may be disposed on the cell line capping film **144**. The pad separation insulating film **180** may define an area of the storage pad **160** forming a plurality of isolated areas. Further, the pad separation insulating film **180** may not cover a top face of the storage pad **160**.

(76) The pad separation insulating film **180** may include an insulating material and may electrically separate a plurality of storage pads **160** from each other. For example, the pad separation insulating film **180** may include at least one of a silicon oxide film, a silicon nitride film, a silicon oxynitride film, a silicon oxycarbonitride film, and a silicon carbonitride film.

(77) The peripheral gate structure **240ST** may be disposed on the substrate **100** and in the peripheral region **24**. The peripheral gate structure **240ST** may be disposed on a peripheral active area defined by a peripheral element separation film. Further, a portion of the peripheral gate structure **240ST** is shown to overlap with the cell region isolation film **22**. However, the present disclosure is not limited thereto.

(78) The peripheral gate structure **240ST** may include a peripheral gate insulating film **230**, a peripheral gate conductive film **240**, and a peripheral capping film **244** sequentially stacked on the substrate **100**. A peripheral spacer **245** may be disposed on a side wall or side surface of the peripheral gate structure **240ST**.

(79) The peripheral gate conductive film **240** may include first to third peripheral conductive films **241**, **242**, and **243** sequentially stacked on the peripheral gate insulating film **230**. In one example, no additional conductive film may be disposed between the peripheral gate conductive film **240** and the peripheral gate insulating film **230**. In another example, unlike shown, an additional

conductive film such as a work function conductive film may be disposed between the peripheral gate conductive film **240** and the peripheral gate insulating film **230**.

(80) The first to third peripheral conductive films **241**, **242**, and **243** may respectively include the same materials as those of the first to third cell conductive films **141**, **142**, and **143**. The peripheral gate insulating film **230** may include, for example, silicon oxide, silicon nitride, silicon oxynitride, or a high dielectric constant material having a higher dielectric constant than that of the silicon oxide. The peripheral capping film **244** may include, for example, at least one of silicon nitride, a silicon oxynitride, and a silicon oxide.

(81) The peripheral spacer **245** may include, for example, at least one of silicon nitride, silicon oxynitride, silicon oxide, silicon carbonitride, silicon oxycarbonitride, and combinations thereof. The peripheral spacer **245** is shown to be embodied as a single film; however, this is shown only for convenience of illustration, and the present disclosure is not limited thereto. In another example, the peripheral spacer **245** may be embodied as a multi-film. In a semiconductor device according to some implementations, the peripheral spacer **245** disposed on the side surface of the peripheral gate structure **240ST** may include a different material than that of the cell spacer portion **281** disposed on the side surface of the bit-line structure **140ST**. For example, the peripheral spacer **245** may include silicon oxide, while the cell spacer portion **281** may include silicon nitride.

(82) A first etching stopper film **251** may extend along the top face **140ST_1_US** of the first portion of the bit-line structure **140ST**. The first etching stopper film **251** may not extend along the top face **140ST_2_US** of the second portion of the bit-line structure **140ST**. The first etching stopper film **251** may extend along a side surface of the bit-line structure **140ST** and a side surface of the cell insulating film **130**. The first etching stopper film **251** may extend along a vertical side surface of a distal end of the bit-line structure **140ST** and a vertical side surface of the distal end of the cell insulating film **130**. The first etching stopper film **251** may extend along a side surface of the peripheral gate insulating film **230**, a side surface of the peripheral gate conductive film **240**, and a side surface and a top face of the peripheral capping film **244**.

(83) A second etching stopper film **252** may extend along the first etching stopper film **251** disposed on the top face **140ST_1_US** of the first portion of the bit-line structure **140ST**. The second etching stopper film **252** may not extend along the top face **140ST_2_US** of the second portion of the bit-line structure **140ST**. The second etching stopper film **252** may extend along a side surface **281_S** of the cell spacer portion **281**, and a top face **22_US** of the cell area defining film (e.g., the cell region isolation film **222**) to be described later. The second etching stopper film **252** may extend along a profile of the peripheral spacer **245** and the peripheral gate structure **240ST**.

(84) Each of the first etching stopper film **251** and the second etching stopper film **252** may include at least one of, for example, silicon nitride, silicon oxynitride, silicon carbonitride, and silicon oxycarbonitride.

(85) An inserted insulating film **290** may be disposed on the second etching stopper film **252** and between the bit-line structure **140ST** and the peripheral gate structure **240ST**. The inserted insulating film **290** may fill at least a portion of a space disposed on the cell region isolation film **22** and defined by the second etching stopper film **252**. The inserted insulating film **290** may fill a space disposed between the bit-line structure **140ST** and the peripheral gate structure **240ST** and defined by the second etching stopper film **252** and an interlayer insulating film **280** to be described later.

(86) The inserted insulating film **290** may include a material different from that of the interlayer insulating film **280**. The inserted insulating film **290** may include, for example, an oxide-based insulating material.

(87) The interlayer insulating film **280** may cover the second etching stopper film **252**, the bit-line structure **140ST**, the inserted insulating film **290**, and the peripheral gate structure **240ST**. Further, the interlayer insulating film **280** may fill a space between the first etching stopper film **251**

disposed on the distal end of the bit-line structure **140ST** and the second etching stopper film **252**.
(88) The interlayer insulating film **280** may include the cell spacer portion **281** and an interlayer insulating film portion **282**.

(89) The cell spacer portion **281** may be disposed on the cell region isolation film **22**. The cell spacer portion **281** may be disposed on a vertical side surface of the distal end of the bit-line structure **140ST**. The cell spacer portion **281** may fill a space defined by the first etching stopper film **251** disposed on the vertical side surface of the distal end of the bit-line structure **140ST** and the second etching stopper film **252**.

(90) The interlayer insulating film portion **282** may cover the second etching stopper film **252**, the bit-line structure **140ST**, the inserted insulating film **290**, and the peripheral gate structure **240ST**. The interlayer insulating film portion **282** may be disposed on the second etching stopper film **252** and between the bit-line structure **140ST** and the peripheral gate structure **240ST**.

(91) The interlayer insulating film portion **282** may fill at least a portion of a space defined by the second etching stopper film **252** and be disposed on the cell region isolation film **22**. The interlayer insulating film portion **282** may directly contact a side wall of the second etching stopper film **252**. The interlayer insulating film portion **282** may be disposed on the second etching stopper film **252** on the side surface **281_S** of the cell spacer portion **281**. The interlayer insulating film portion **282** may be disposed on the second etching stopper film **252** adjacent to the cell spacer portion **281**. That is, the inserted insulating film **290** and the interlayer insulating film portion **282** may be sequentially stacked on the second etching stopper film **252** and between the bit-line structure **140ST** and the peripheral gate structure **240ST**. The cell spacer portion **281** may be disposed between the first etching stopper film **251** and the second etching stopper film **252**. The interlayer insulating film portion **282** may be separated from the cell spacer portion **281** via the second etching stopper film **252**. The interlayer insulating film portion **282** may be disposed between the cell spacer portion **281** and the peripheral spacer **245**.

(92) The interlayer insulating film portion **282** may directly contact the inserted insulating film **290**. A side surface **282_S** of the interlayer insulating film portion **282** in contact with the inserted insulating film **290** may be curved along an interface between the interlayer insulating film portion **282** and the inserted insulating film **290**. The side surface **282_S** of the interlayer insulating film portion **282** in contact with the inserted insulating film **290** may be convex toward the inserted insulating film **290**, that is, the side surface **282_S** of the interlayer insulating film portion **282** may have a convex shape that protrudes toward the inserted insulating film **290**.

(93) As shown, the side surface **282_S** of the interlayer insulating film portion **282** may meet a bottom corner of the second etching stopper film **252** adjacent to the cell spacer portion **281**. Alternatively, unlike illustrated, the side surface **282_S** of the interlayer insulating film portion **282** may be formed along at least a portion of a bottom face of the second etching stopper film **252** adjacent to the cell spacer portion **281**.

(94) The interlayer insulating film **280** may include, for example, a nitride-based insulating material. The cell spacer portion **281** and the interlayer insulating film portion **282** may include the same material. For example, each of the cell spacer portion **281** and the interlayer insulating film portion **282** may include silicon nitride.

(95) Referring to FIGS. **1** and **3**, the interlayer insulating film portion **282** and the inserted insulating film **290** may be disposed on the distal end of the bit-line BL. The interlayer insulating film portion **282** and the inserted insulating film **290** may extend in the same direction as the extension direction of the bit-line BL. For example, the interlayer insulating film portion **282** and the inserted insulating film **290** may extend along the second direction D2. The buried contacts BC may be arranged in a straight line or substantially linearly along the first direction D1 and the second direction D2. The landing pads LP may be arranged in a zigzag manner in the second direction D2. The buried contact BC may be formed between adjacent interlayer insulating film portions **282** and between adjacent inserted insulating films **290**. The landing pads LP may be

arranged in a zigzag manner in a second direction D2 in which each of the interlayer insulating film portion **282** and the inserted insulating film **290** extends.

(96) When the interlayer insulating film **280** includes silicon oxide, the interlayer insulating film **280** may be less resistant to a dry etching process, and thus may be etched away together with contact formation. For example, when the interlayer insulating film **280** includes silicon oxide, at least a portion of the interlayer insulating film **280** may be etched together with formation of the buried contact BC shown in FIG. 3. Accordingly, contacts spaced apart from each other may be electrically connected to each other, such that reliability of the semiconductor device may be degraded.

(97) However, in a semiconductor device according to some implementations, the interlayer insulating film **280** including silicon nitride may be disposed on the second etching stopper film **252** disposed on the distal end of the bit-line structure **140ST**. Therefore, the interlayer insulating film **280** is resistant to the dry etching process, such that the interlayer insulating film **280** may not be etched during the formation of the buried contact BC shown in FIG. 3. Accordingly, the reliability of the semiconductor device may be improved.

(98) In FIGS. 4 and 5, a peripheral wire line **265** may be disposed on the interlayer insulating film portion **282**. The peripheral wire line **265** may pass through the cell line capping film **144** and may be connected to the cell conductive line **140**. Further, although not shown, the peripheral wire line **265** may be connected to the cell gate electrode **112**. A peripheral wire separation pattern **270** may divide the peripheral wire line **265** into two portions.

(99) The peripheral wire line **265** may include the same material as that of the storage pad **160**. The peripheral wire separation pattern **270** may include, for example, at least one of a silicon oxide film, a silicon nitride film, a silicon oxynitride film, a silicon oxycarbonitride film, and a silicon carbonitride film.

(100) A third etching stopper film **292** may be disposed on the pad separation insulating film **180** and the storage pad **160**. The third etching stopper film **292** may extend to the peripheral region **24** as well as the cell region **20**. The third etching stopper film **292** may be disposed on the peripheral wire line **265** and the peripheral wire separation pattern **270**. The third etching stopper film **292** may include at least one of a silicon nitride film, a silicon carbonitride film, a silicon boron nitride film (SiBN), a silicon oxynitride film, and a silicon oxycarbide film.

(101) The information storage **190** may be disposed on the storage pad **160**. The information storage **190** may be electrically connected to the storage pad **160**. A portion of the information storage **190** may be disposed in the third etching stopper film **292**. The information storage **190** may include, for example, a capacitor. However, the present disclosure is not limited thereto. The information storage **190** includes a lower electrode **191**, a capacitor dielectric film **192**, and an upper electrode **193**.

(102) The lower electrode **191** may be disposed on the storage pad **160**. The lower electrode **191** is shown to have a pillar shape. However, the present disclosure is not limited thereto. In another example, the lower electrode **191** may have a cylindrical shape. The capacitor dielectric film **192** is formed on the lower electrode **191**. The capacitor dielectric film **192** may be formed along a profile of the lower electrode **191**. The upper electrode **193** is formed on the capacitor dielectric film **192**. The upper electrode **193** may cover an outer wall of the lower electrode **191**.

(103) In one example, the capacitor dielectric film **192** may only have a portion vertically overlapping the upper electrode **193**. In another example, as illustrated, the capacitor dielectric film **192** may include a first portion vertically overlapping with the upper electrode **193** and a second portion not vertically overlapping with the upper electrode **193**.

(104) Each of the lower electrode **191** and the upper electrode **193** may include, for example, a doped semiconductor material, a conductive metal nitride such as titanium nitride, tantalum nitride, niobium nitride or tungsten nitride, etc., a metal such as ruthenium, iridium, titanium or tantalum, etc. or a conductive metal oxide such as iridium oxide or niobium oxide, etc. However, the present

disclosure is not limited thereto.

(105) The capacitor dielectric film **192** may include, for example, one of silicon oxide, silicon nitride, silicon oxynitride, and high dielectric constant material, and combinations thereof. However, the present disclosure is not limited thereto. In a semiconductor device according to some implementations, the capacitor dielectric film **192** may include a stack structure in which a zirconium oxide film, an aluminum oxide film, and a zirconium oxide film are sequentially stacked. In a semiconductor device according to some implementations, the capacitor dielectric film **192** may include a dielectric film including hafnium (Hf). In a semiconductor device according to some implementations, the capacitor dielectric film **192** may have a stack structure of a ferroelectric material film and a paraelectric material film.

(106) A peripheral interlayer insulating film **293** may be disposed on the third etching stopper film **292**. The peripheral interlayer insulating film **293** may cover a side wall of the upper electrode **193**. The peripheral interlayer insulating film **293** may include, for example, an insulating material.

(107) FIG. **6** to FIG. **8** are diagrams for illustration of a semiconductor device according to some implementations. For the convenience of illustration, following descriptions are based on differences from those described using FIG. **1** to FIG. **5**.

(108) For reference, FIG. **6** to FIG. **8** are cross-sectional views taken along a line A-A in FIG. **1**.

(109) Referring to FIG. **6**, in a semiconductor device according to some implementations, a distal end of the cell insulating film **130** may protrude from the distal end of the bit-line structure **140ST**. A side surface **130_S** of the cell insulating film **130** may protrude beyond a side surface **140ST_S** of the bit-line structure **140ST** and toward the peripheral gate structure **240ST**.

(110) The first etching stopper film **251** may extend along a top face of the cell insulating film **130** protruding from the distal end of the bit-line structure **140ST** and the side surface **130S** of the cell insulating film **130**. The cell spacer portion **281** may cover the cell insulating film **130** protruding from the distal end of the bit-line structure **140ST**.

(111) Referring to FIG. **7**, in a semiconductor device according to some implementations, the distal end of the bit-line structure may protrude from the distal end of the cell insulating film **130**. The side surface **140ST_S** of the bit-line structure may protrude from the side surface **130_S** of the cell insulating film **130**.

(112) The first etching stopper film **251** may extend along the side surface **140ST_S** of the bit-line structure **140ST**.

(113) Referring to FIG. **8**, in a semiconductor device according to some implementations, at least a portion of the second etching stopper film **252** may be recessed into the cell region isolation film **22**. A bottom face or lower surface **252_BS** of the second etching stopper film **252** may be disposed below a top face or upper surface **22_US** of the cell area defining film or cell region isolation film **22**.

(114) The bottom face **252_BS** of the second etching stopper film **252** may include at least one of a convex portion convex toward the cell region isolation film **22** and a concave portion concave toward the cell region isolation film **22**.

(115) As shown, the interlayer insulating film portion **282** may be formed along at least a portion of the bottom face **252_BS** of the second etching stopper film **252** adjacent to the cell spacer portion **281**. Alternatively, unlike shown, the interlayer insulating film portion **282** may meet the cell spacer portion **281** at a corner of the bottom face **252_BS** of the second etching stopper film **252** adjacent thereto.

(116) FIG. **9** to FIG. **13** are diagrams of intermediate structures to illustrate a semiconductor device manufacturing method according to some implementations. Descriptions duplicate with those described using FIG. **1** to FIG. **8** among the descriptions about the manufacturing method are briefly described or omitted.

(117) Referring to FIG. **9**, the substrate **100** including the cell region **20**, the peripheral region **24** and the cell region isolation film **22** may be provided.

(118) Subsequently, the cell insulating film **130** may be formed on the cell region **20**. The cell insulating film **130** may expose the peripheral region **24** of the substrate **100**.

(119) Subsequently, a cell conductive film structure **140p_ST** may be formed on the substrate **100** and in the cell region **20**. The cell conductive film structure **140p_ST** may be formed on the cell insulating film **130**. The cell conductive film structure **140p_ST** may include a pre-cell conductive film **140p** and a pre-cell capping film **144p** sequentially stacked on the cell insulating film **130**. Further, between the cell conductive film structure **140p_ST** and the substrate **100**, a pre-bit-line contact **146p** may be formed. The pre-bit-line contact **146p** may connect the cell conductive film structure **140p_ST** and the substrate **100** to each other.

(120) The peripheral gate insulating film **230**, the peripheral gate conductive film **240**, and the peripheral capping film **244** may be formed on the substrate **100** and in the peripheral region **24**. The peripheral gate insulating film **230**, the peripheral gate conductive film **240**, and the peripheral capping film **244** may be formed simultaneously with the formation of the cell conductive film structure **140p_ST**.

(121) Subsequently, the first etching stopper film **251** may be formed along the top face of the cell conductive film structure **140p_ST**, the side surface of the cell conductive film structure **140p_ST**, the side surface of each of the peripheral gate insulating film **230**, the peripheral gate conductive film **240**, and the peripheral capping film **244**, and the top face of the peripheral capping film **244**. The first etching stopper film **251** may expose at least a portion of the top face **22_US** of the cell area defining film or cell region isolation film **22**.

(122) Subsequently, a sacrificial spacer **281p** may be formed on the side surface of the cell conductive film structure **140p_ST**. The peripheral spacer **245** may be formed on the side surface of the peripheral gate structure **240ST**.

(123) Subsequently, the second etching stopper film **252** may be formed along the side wall of the first etching stopper film **251**, a side wall or side surface **281_S** of the sacrificial spacer **281p**, the top face **22_US** of the cell area defining film **22**, and a side wall of the peripheral spacer **245**. Each of the pre-cell capping film **144p**, the first etching stopper film **251**, and the second etching stopper film **252** may include, for example, silicon nitride. The sacrificial spacer **281p** may include, for example, silicon oxide.

(124) Subsequently, a pre-inserted insulating film **290p** may be formed on the second etching stopper film **252**. The pre-inserted insulating film **290p** may fill a space between the cell conductive film structure **140p_ST** and the peripheral gate structure **240ST** and be disposed on the second etching stopper film **252**. The pre-inserted insulating film **290p** may include, for example, silicon oxide.

(125) Referring to FIG. **10**, a mask pattern **300** including a first opening **OP1** may be formed on the second etching stopper film **252**. The first opening **OP1** may expose a portion of a top face of the second etching stopper film **252** on the cell conductive film structure **140p_ST** and the sacrificial spacer **281p**, and expose a portion of a top face of the pre-inserted insulating film **290p**.

(126) Referring to FIG. **11**, an etching process may be performed using the mask pattern **300** as an etching mask so that a top face of the sacrificial spacer **281p** is exposed. For example, a dry etching process may be performed. Accordingly, a first trench **t1** may be formed. The first trench **t1** may at least partially expose the pre-cell capping film **144p**, the first etching stopper film **251** on the side surface of the cell conductive film structure **140p_ST**, the top face of the sacrificial spacer **281p**, the second etching stopper film **252** on the side surface of the sacrificial spacer **281p**, and the pre-inserted insulating film **290p**. Further, a step may be formed on the top face of the cell conductive film structure **140p_ST** due to the first trench **t1**. That is, a first portion having a first vertical dimension **h1** from a top face of the cell insulating film **130** and a second portion having a second vertical dimension **h2** from the top face of the cell insulating film **130** may be formed.

(127) Referring to FIGS. **11** and **12**, an etching process may be performed using a mask pattern **300** as an etching mask. For example, a wet etching process may be performed. For example, a wet

etching process may be performed using a hydrofluoric acid (HF) aqueous solution. Accordingly, a portion of the pre-inserted insulating film **290p** is removed to form a second trench **t2** and the inserted insulating film **290** may be formed. Further, the sacrificial spacer **281p** may be removed to form a third trench **t3**.

(128) The second trench **t2** may expose a portion of the inserted insulating film **290**. The second trench **t2** may be recessed toward the inserted insulating film **290**. A bottom face of the second trench **t2** may be convex toward the inserted insulating film **290**. This may be due to the wet etching process.

(129) The third trench **t3** may expose at least a portion of a top face of the cell region isolation film **22** between the first etching stopper film **251** disposed on the distal end of the cell conductive film structure **140p_ST** and the second etching stopper film **252**.

(130) Referring to FIG. **12** and FIG. **13**, the mask pattern **300** may be removed. The interlayer insulating film **280** may be formed. The interlayer insulating film **280** may cover the second etching stopper film **252** and the first to third trenches **t1**, **t2**, and **t3**. The interlayer insulating film **280** may fill the first to third trenches **t1**, **t2** and **t3**. Accordingly, the cell spacer portion **281** filling the third trench **t3** and the interlayer insulating film portion **282** filling the first and second trenches **t1** and **t2** and covering the second etching stopper film **252** and the cell conductive film structure **140p_ST** may be formed.

(131) The top face **282_US** of the interlayer insulating film portion may be convex toward the substrate **100**. This may be due to the first to third trenches **t1**, **t2**, and **t3**. Alternatively, unlike shown, the top face **282_US** of the interlayer insulating film portion may be planarized using a planarization process.

(132) Subsequently, referring to FIG. **13**, FIG. **14**, and FIG. **15**, the cell conductive film structure **140p_ST**, the interlayer insulating film **280** and the second etching stopper film **252** in the cell region **20** may be patterned, such that the bit-line structure **140ST** extending in the second direction **D2** may be formed. While the bit-line structure **140ST** is formed, the bit-line contact **146** may be formed.

(133) Subsequently, the fence pattern **170** and the storage contact **120** may be formed on the cell gate structure **110**. Subsequently, the storage pad **160**, the peripheral wire line **265**, and the peripheral wire separation pattern **270** may be formed. Subsequently, the third etching stopper film **292** may be formed. Further, the information storage **190** may be formed.

(134) FIG. **14** is a diagram for illustration of a semiconductor device according to some implementations. For the convenience of illustration, following descriptions are based on differences from those described using FIG. **1** to FIG. **5**.

(135) Referring to FIG. **14**, in a semiconductor device according to some implementations, the cell spacer **283** may be formed at a location corresponding to the cell spacer portion **281** of FIGS. **1** to **5**. The cell spacer **283** may be separated from the interlayer insulating film **280**. The cell spacer **283** may be spaced from the interlayer insulating film **280** via the second etching stopper film **252**. The second etching stopper film **252** may be continuously formed along the top face of the bit-line structure **140ST** and the side surface **283_S** of the cell spacer **283**. The side surface **283_S** of the cell spacer **283** may directly and entirely contact the second etching stopper film **252**.

(136) The cell spacer **283** may include a material different from that of the interlayer insulating film **280**. For example, the cell spacer **283** may include an oxide-based insulating material.

(137) The interlayer insulating film **280** may include the interlayer insulating film portion **282**. A portion of the top face of the bit-line structure **140ST** overlapping the interlayer insulating film **280** may be free of a step.

(138) FIG. **15** is a diagram of an intermediate structure to illustrate a semiconductor device manufacturing method according to some implementations. Descriptions duplicate with those described using FIG. **9** to FIG. **13** are briefly described or omitted.

(139) For reference, FIG. **15** may be a drawing subsequent to a process of FIG. **10**. The cell spacer

283 in FIG. **15** may correspond to the sacrificial spacer **281p** in FIG. **9**.

(140) Referring to FIGS. **10** and **15**, an etching process may be performed using a mask pattern **300** as an etching mask. For example, a wet etching process may be performed. For example, a wet etching process may be performed using a hydrofluoric acid (HF) aqueous solution. Accordingly, a portion of the pre-inserted insulating film **290p** may be removed to form a fourth trench **t4** and the inserted insulating film **290** may be formed.

(141) The fourth trench **t4** may expose a portion of the inserted insulating film **290**. The fourth trench **t4** may be recessed toward the inserted insulating film **290**. A bottom face of the fourth trench **t4** may be convex toward the inserted insulating film **290**. This may be due to the wet etching process.

(142) Subsequently, referring to FIG. **14**, the mask pattern **300** may be removed. The interlayer insulating film **280** may be formed.

(143) FIG. **16** is a diagram for illustration of a semiconductor device according to some implementations. For the convenience of illustration, following descriptions are centered on differences from those described using FIG. **14**.

(144) Referring to FIG. **16**, in a semiconductor device according to some implementations, the inserted insulating film **290** and the interlayer insulating film **280** may be sequentially stacked on a portion of the second etching stopper film **252** between the bit-line structure **140ST** and the peripheral gate structure **240ST**. The inserted insulating film **290** and the interlayer insulating film **280** may fill a space defined on the second etching stopper film **252** and between the bit-line structure **140ST** and the peripheral gate structure **240ST**.

(145) A bottom face of the interlayer insulating film **280** at which the interlayer insulating film **280** and the inserted insulating film **290** contact each other may be convex toward the substrate **100**.

(146) FIG. **17** and FIG. **18** are diagrams of intermediate structures for illustration of a semiconductor device manufacturing method according to some implementations. Descriptions duplicate with those described using FIG. **9** to FIG. **13** are briefly described or omitted.

(147) For reference, FIG. **17** may be a drawing subsequent to the process of FIG. **9**. The cell spacer **283** in FIG. **17** may correspond to the sacrificial spacer **281p** in FIG. **10**.

(148) Referring to FIG. **17**, a mask pattern **300** including a second opening **OP2** may be formed on the second etching stopper film **252**. The second opening **OP2** may expose a portion of a top face of the second etching stopper film **252** on the cell conductive film structure **140p_ST** and the cell spacer **283**, and an entirety of a top face of the pre-inserted insulating film **290p**. The second opening **OP2** may expose at least a portion of the second etching stopper film **252** on the peripheral gate structure **240ST**. However, the present disclosure is not limited thereto. The second opening **OP2** may not expose the second etching stopper film **252** on the peripheral gate structure **240ST**.

(149) Referring to FIG. **18**, an etching process may be performed using the mask pattern **300** as an etching mask. For example, a wet etching process may be performed. For example, a wet etching process may be performed using a hydrofluoric acid (HF) aqueous solution. Accordingly, the top face of the pre-inserted insulating film **290p** may be recessed to form a fifth trench **t5** and the inserted insulating film **290** may be formed.

(150) The fifth trench **t5** may expose an entirety of a top face of the inserted insulating film **290**. The fifth trench **t5** may be recessed toward the inserted insulating film **290**. A bottom face of the fifth trench **t5** may be convex toward the inserted insulating film **290**. This may be due to the wet etching process.

(151) Subsequently, referring to FIG. **16**, the mask pattern **300** may be removed, and the interlayer insulating film **280** may be formed.

(152) FIG. **19** is a diagram for illustration of a semiconductor device according to some implementations. For convenience of illustration, following descriptions are based on differences from the description using FIG. **16**.

(153) Referring to FIG. **19**, a semiconductor device according to some implementations may not

include the inserted insulating film (290 in FIG. 16). The interlayer insulating film 280 may cover an entirety of the second etching stopper film 252. Accordingly, the interlayer insulating film 280 may fill a space defined on the second etching stopper film 252 and between the bit-line structure 140ST and the peripheral gate structure 240ST.

(154) FIG. 20 is a diagram of an intermediate structure to illustrate a semiconductor device manufacturing method according to some implementations. Descriptions duplicate with those described using FIG. 9 to FIG. 13 are briefly described or omitted.

(155) For reference, FIG. 20 may be a drawing subsequent to the process of FIG. 17.

(156) Referring to FIG. 17 and FIG. 20, an etching process may be performed using a mask pattern 300 as an etching mask. For example, a dry etching process may be performed. Accordingly, the pre-inserted insulating film 290p may be removed to form a sixth trench t6. The sixth trench t6 may be defined by the second etching stopper film 252 and on the cell region isolation film 22.

(157) Although embodiments of the present disclosure have been described in more detail with reference to the accompanying drawings, the present disclosure is not necessarily limited to these embodiments. The present disclosure may be implemented in various modified manners within the scope not departing from the technical idea of the present disclosure. Accordingly, embodiments disclosed in the present disclosure are not intended to limit the technical idea of the present disclosure, but to describe the present disclosure. The scope of the technical idea of the present disclosure is not limited by embodiments. Therefore, it should be understood that embodiments as described above are illustrative and non-limiting in all respects. The scope of protection of the present disclosure should be interpreted by the claims, and all technical ideas within the scope of the present disclosure should be interpreted as being included in the scope of the present disclosure.

Claims

1. A semiconductor device comprising: a substrate comprising a cell region; a cell region isolation film in the substrate and extending along an outer edge of the cell region; a bit-line structure on the substrate and in the cell region, wherein the bit-line structure has a distal end positioned on the cell region isolation film; a cell spacer on a vertical side surface of the distal end of the bit-line structure; an etching stopper film extending along a side surface of the cell spacer and a top face of the cell region isolation film; and an interlayer insulating film on the etching stopper film, and on the side surface of the cell spacer, wherein the interlayer insulating film comprises silicon nitride.
2. The semiconductor device of claim 1, further comprising: an inserted insulating film on the cell region isolation film, and on a side surface of the interlayer insulating film, wherein the inserted insulating film comprises a material different from a material of the interlayer insulating film.
3. The semiconductor device of claim 2, wherein the inserted insulating film comprises silicon oxide.
4. The semiconductor device of claim 2, wherein the substrate further comprises a peripheral area along a periphery of the cell region and the semiconductor device further comprises a peripheral gate structure on the substrate and in the peripheral area, wherein the interlayer insulating film extends along a top face of the inserted insulating film and a top face of the peripheral gate structure, wherein the inserted insulating film is between the peripheral gate structure and the interlayer insulating film.
5. The semiconductor device of claim 1, wherein the bit-line structure comprises a first portion and a second portion including the distal end, wherein a top face of the second portion is lower than a top face of the first portion relative to the substrate.
6. The semiconductor device of claim 1, wherein the cell spacer comprises silicon nitride.
7. The semiconductor device of claim 1, wherein the cell spacer comprises a material different from a material of the interlayer insulating film.
8. The semiconductor device of claim 1, further comprising: a cell insulating film between the

substrate and the bit-line structure and disposed in the cell region, wherein a distal end of the cell insulating film protrudes from the distal end of the bit-line structure.

9. The semiconductor device of claim 1, further comprising: a cell insulating film between the substrate and the bit-line structure and disposed in the cell region, wherein the distal end of the bit-line structure protrudes from a distal end of the cell insulating film.

10. The semiconductor device of claim 1, wherein the substrate further comprises a peripheral area along a periphery of the cell region and separated therefrom by the cell region isolation film, and the semiconductor device further comprises: a peripheral gate structure on the substrate and in the peripheral area; and a peripheral spacer on the cell region isolation film, wherein the peripheral spacer is between the cell spacer and the peripheral gate structure.

11. The semiconductor device of claim 10, further comprising: an inserted insulating film between the cell region isolation film and the interlayer insulating film, wherein the inserted insulating film comprises a material different from silicon nitride, and wherein a bottom face of the interlayer insulating film is in contact with the inserted insulating film and is convex toward the inserted insulating film.

12. A semiconductor device comprising: a substrate comprising a cell region and a peripheral area along a periphery of the cell region; a cell region isolation film in the substrate and extending along an outer edge of the cell region; a bit-line structure on the substrate and in the cell region, wherein the bit-line structure has a distal end positioned on the cell region isolation film; a peripheral gate structure on the substrate and in the peripheral area; an interlayer insulating film on the cell region isolation film and on the distal end of the bit-line structure; and an inserted insulating film on the cell region isolation film, wherein the inserted insulating film is between the interlayer insulating film and the peripheral gate structure, wherein a side surface of the interlayer insulating film in contact with the inserted insulating film is convex toward the inserted insulating film.

13. The semiconductor device of claim 12, wherein the interlayer insulating film comprises a material different from a material of the inserted insulating film.

14. The semiconductor device of claim 12, further comprising: a cell spacer on a vertical side surface of the distal end of the bit-line structure; and an etching stopper film extending along a side surface of the cell spacer, a top face of the cell region isolation film, and at least a portion of the peripheral gate structure, wherein the inserted insulating film is between the etching stopper film and the interlayer insulating film.

15. The semiconductor device of claim 14, wherein each of the interlayer insulating film and the cell spacer comprises silicon nitride.

16. The semiconductor device of claim 14, wherein the cell spacer comprises an insulating material that is different from an insulating material of the interlayer insulating film.

17. A semiconductor device comprising: a substrate comprising a cell region and a peripheral area along a periphery of the cell region; a cell region isolation film in the substrate and extending along an outer edge of the cell region; a gate electrode comprising at least a portion in the substrate and in the cell region, wherein the gate electrode extends in a first direction; a bit-line structure on the substrate and in the cell region, wherein the bit-line structure extends in a second direction intersecting the first direction, wherein the bit-line structure has a distal end on the cell region isolation film; a cell spacer on a side surface of the bit-line structure; a peripheral gate structure in the peripheral area and on the substrate, wherein the peripheral gate structure is spaced apart from the bit-line structure in the second direction; an etching stopper film extending along a side surface of the cell spacer, a top face of the cell region isolation film, and an outer face of the peripheral gate structure; and an interlayer insulating film on the etching stopper film and on the side surface of the cell spacer, wherein the interlayer insulating film extends into at least a portion of a space between the cell spacer and the peripheral gate structure, wherein the interlayer insulating film comprises silicon nitride.

18. The semiconductor device of claim 17, further comprising: an inserted insulating film separated

from the cell spacer by the interlayer insulating film, wherein the inserted insulating film is between the interlayer insulating film and the peripheral gate structure, wherein the interlayer insulating film extends along a top face of the inserted insulating film and a top face of the peripheral gate structure.

19. The semiconductor device of claim 17, wherein the interlayer insulating film fills the space between the cell spacer and the peripheral gate structure on the cell region isolation film.

20. The semiconductor device of claim 17, wherein a bottom face of the etching stopper film is lower than a top face of the cell region isolation film relative to the substrate.
