

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250280739

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

DUREL; Aurore et al.

ELECTRONIC DEVICE

Abstract

The present description concerns a method of manufacturing an electronic device comprising: the forming, on an upper surface of a support, of first elements; the forming, on the side walls of each first element, of a first layer of titanium silicon nitride; the forming of a protective layer covering the upper surface of the support and the first elements; and the planarization of the second layer so as to reach at least the level of an upper surface of the first elements.

Inventors: DUREL; Aurore (Fontaine, FR), MERMOZ; Sebastien (Bernin, FR)

Applicant: STMicroelectronics International N.V. (Geneva, CH)

Family ID: 92042868

Assignee: STMicroelectronics International N.V. (Geneva, CH)

Appl. No.: 19/057639

Filed: February 19, 2025

Foreign Application Priority Data

FR 2401994

Feb. 29, 2024

Publication Classification

Int. Cl.: H10N70/00 (20230101); H10B63/10 (20230101); H10N70/20 (20230101)

U.S. Cl.:

CPC H10N70/021 (20230201); H10B63/10 (20230201); H10N70/231 (20230201);
H10N70/883 (20230201);

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION(S)

[0001] The present disclosure is based on French patent application number FR2401994, filed on Feb. 29, 2024, entitled “Dispositif électronique” (electronic device), the content of which is hereby incorporated by reference to the maximum extent permitted by Law.

BACKGROUND

Technical Field

[0002] The present disclosure generally concerns electronic devices and their manufacturing methods.

Description of the Related Art

[0003] Many manufacturing methods comprise the forming of a protective layer covering elements to be protected. Said protective layer is generally planarized in order to obtain a planar surface.

BRIEF SUMMARY

[0004] An embodiment is directed to overcomes all or part of the disadvantages of known electronic device manufacturing methods.

[0005] An embodiment provides a method of manufacturing an electronic device comprising:

[0006] the forming, on an upper surface of a support, of first elements; [0007] the forming, on the side walls of each first element, of a first layer of titanium silicon nitride; and [0008] the forming of a protective layer covering the upper surface of the support and the first elements; and [0009] the planarization of the second layer so as to reach at least the level of an upper surface of the first elements.

[0010] Another embodiment provides a device, comprising first elements bonded to an upper surface of a support, the side walls of the first element being covered with a first titanium silicon nitride layer, the device further comprising a protective layer covering the upper surface of the support and extending all the way to the upper surface of the first elements.

[0011] According to an embodiment, the forming of the first layers comprises the conformal forming of a second titanium silicon nitride layer and the anisotropic etching of the second titanium silicon nitride layer.

[0012] According to an embodiment, each first element comprises a phase-change memory cell and the support comprises a semiconductor substrate inside and on top of which selection transistors associated with the phase-change memory cells are formed.

[0013] According to an embodiment, each memory cell comprises a stack of a resistive element, of a layer of phase-change material, and of a conductive layer, each memory cell comprising an insulating layer covering the stack, the portions of the insulating layer covering the side walls of the stack of each cell being covered with the first layer.

[0014] According to an embodiment, the thickness of the second titanium silicon nitride layer is in the range from 5 nm to 20 nm.

[0015] According to an embodiment, each first element is an electronic chip.

[0016] According to an embodiment, the thickness of the second titanium silicon nitride layer is greater than 200 nm.

[0017] According to an embodiment, the first titanium silicon nitride layers extend only over the side walls of the first elements.

[0018] According to an embodiment, the planarization step is a chemical-mechanical polishing step.

[0019] According to an embodiment, the protective layer is made of an insulating material.

[0020] According to an embodiment, the planarization step is maintained until the upper surface of the first elements has been reached.

[0021] According to an embodiment, the planarization step comprises the thinning of the first elements.

Description

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0022] The foregoing features and advantages, as well as others, will be described in detail in the rest of the disclosure of specific embodiments given as an illustration and not limitation with reference to the accompanying drawings, in which:

[0023] FIG. 1A, FIG. 1B, FIG. 1C, FIG. 1D, and FIG. 1E show an embodiment of a method of manufacturing an electronic device;

[0024] FIG. 2A, FIG. 2B, FIG. 2C, FIG. 2D, and FIG. 2E show another embodiment of an electronic device manufacturing method; and

[0025] FIG. 3A, FIG. 3B, FIG. 3C, FIG. 3D, and FIG. 3E show another embodiment of an electronic device manufacturing method.

DETAILED DESCRIPTION

[0026] Like features have been designated by like references in the various figures. In particular, the structural and/or functional features that are common among the various embodiments may have the same references and may dispose identical structural, dimensional and material properties.

[0027] For clarity, only those steps and elements which are useful to the understanding of the described embodiments have been shown and are described in detail.

[0028] Unless indicated otherwise, when reference is made to two elements connected together, this signifies a direct connection without any intermediate elements other than conductors, and when reference is made to two elements coupled together, this signifies that these two elements can be connected or they can be coupled via one or more other elements.

[0029] In the following description, where reference is made to absolute position qualifiers, such as “front,” “back,” “top,” “bottom,” “left,” “right,” etc., or relative position qualifiers, such as “top,” “bottom,” “upper,” “lower,” etc., or orientation qualifiers, such as “horizontal,” “vertical,” etc., reference is made unless otherwise specified to the orientation of the drawings.

[0030] Unless specified otherwise, the expressions “about,” “approximately,” “substantially,” and “in the order of” signify plus or minus 10% or 10°, preferably of plus or minus 5% or 5°.

[0031] FIG. 1A, FIG. 1B, FIG. 1C, FIG. 1D, and FIG. 1E show an embodiment of a method of manufacturing an electronic device **10**. More specifically, FIGS. 1A to 1E show steps, preferably successive, of a method of manufacturing device **10**.

[0032] Device **10** is, for example, an electronic device intended to be integrated in electrical, electromechanical, or optoelectronic equipment. Device **10** is, for example, intended to be integrated in industrial equipment, household appliances, equipment connected via the Internet of Things (IOT), or automotive equipment.

[0033] FIG. 1A shows, schematically, a structure resulting from a step of manufacturing electronic device **10**.

[0034] Device **10** comprises a support **12**. Support **12** is, for example, an electronic chip. The support for example comprises a semiconductor substrate and an interconnection network, that is, a stack of insulating layers as well as conductive tracks and conductive vias. Support **12** is, for example, an electronic chip wafer. Support **12** is, for example, only a semiconductor substrate. The support is, for example, a layer made of an insulating material.

[0035] Device **10** further comprises elements **14**. Elements **14** are bonded to an upper surface of support **12**. Elements **14** correspond, for example, to portions of layers having been formed on support **12** and etched. Elements **14** correspond, for example, to chips or stacks of layers formed independently from support **12** and bonded to the support, more specifically to the upper surface of

the support. Elements **14** are for example bonded by a bonding layer, for example an adhesive layer, by molecular bonding or by soldering.

[0036] According to an embodiment, at least two of elements **14** are identical to one another. For example, all elements **14** are identical to one another. Further, at least some of elements **14** may, for example, be different from one another. Elements **14** preferably have a substantially identical height. As an example, device **10** may comprise elements, not shown, bonded to support **12**, having a height lower than the height of elements **14**.

[0037] The different elements **14** are, for example, laterally surrounded by air or by another gas. Elements **14** are preferably not in contact with one another.

[0038] Elements **14** are for example not placed regularly or periodically on support **12**. Device **10** thus comprises, for example, regions comprising a higher density of elements **14** than other regions of device **10**.

[0039] FIG. **1B** shows, schematically, a structure resulting from a step of manufacturing electronic device **10**.

[0040] During this step, a layer **16** made of an alloy of titanium, silicon, and nitrogen is formed on the structure resulting from the step of FIG. **1A**. Layer **16** is preferably made of titanium silicon nitride (TiSiN). Layer **16** is preferably made of a homogeneous material. Layer **16** is preferably entirely made of TiSiN.

[0041] Layer **16** is conformally formed. Layer **16** is for example formed by atomic layer deposition (ALD) or chemical vapor deposition (CVD). Layer **16** covers all the exposed walls of the structure resulting from the step shown in FIG. **1A**. More specifically, layer **16** covers the side walls and the upper surface of elements **14** and the portions of support **12** not being covered by elements **14**.

[0042] Layer **14**, for example, has a thickness in the range from 5 nm to 750 μm . Preferably, the thickness of layer **16** is substantially constant. Preferably, the thickness of layer **16** and the distance between elements **14** are such that portions of layer **16** extending over the side walls of adjacent elements **14** are not in contact.

[0043] FIG. **1C** shows, schematically, a structure resulting from a step of manufacturing electronic device **10**.

[0044] The step of FIG. **1C** comprises a step of anisotropic etching of layer **14**. The etching is a selective etching. More precisely, the etching is a selective etching of TiSiN over the materials of support **12** and of elements **14** having layer **16** resting thereon. In other words, the etching for example etches the TiSiN at least twice, for example at least five times, for example at least ten times, faster than the materials of the support or of the elements **14** having layer **16** resting thereon.

[0045] The etching of layer **16** being anisotropic, the portions of layer **16** located on the upper surface of support **12** and on the upper surfaces of elements **14** are removed. Portions **18** of layer **16**, located on the side walls of elements **14**, are kept at the end of the etching.

[0046] Portions **18** preferably extend all over the side walls of elements **14**. Thus, portions **18** preferably extend from the upper surface of support **12** and up to the upper surface of elements **14**.

[0047] FIG. **1D** shows, schematically, a structure resulting from a step of manufacturing electronic device **10**.

[0048] During this step, a layer **20** is formed on the structure resulting from the step of FIG. **1C**. Layer **20** is, for example, a protective layer. Layer **20** is, for example, made of a dielectric material, for example of silicon oxide.

[0049] Layer **20** is configured to entirely cover elements **14**. Thus, the thickness of layer **20** is greater than the height of elements **14**, that is, the distance between the upper surface of support **12** and the upper surface of elements **14**.

[0050] The upper surface of layer **20** is not planar. In particular, the portions of layer **20** covering elements **14** are located further away from the support than the portions of layer **20** directly covering substrate **12**.

[0051] FIG. **1E** shows, schematically, a structure resulting from a step of manufacturing electronic

device **10**.

[0052] The step of FIG. **1E** corresponds to a step of planarization of layer **20**. For example, the planarization is performed by chemical mechanical polishing (CMP). The planarization is preferably maintained to reach the upper surface of elements **14**.

[0053] FIG. **2A**, FIG. **2B**, FIG. **2C**, FIG. **2D**, and FIG. **2E** show an embodiment of a method of manufacturing an electronic device **22**. The embodiment of FIGS. **2A** to **2E** corresponds, for example, to a more detailed example of implementation of the embodiment of the method of FIGS. **1A** to **1E**. More precisely, FIGS. **2A** to **2E** show steps, preferably successive, of a method of manufacturing device **22**.

[0054] FIG. **2A** schematically shows a structure resulting from a step of manufacturing electronic device **22**.

[0055] The step of FIG. **2A** comprises the forming of a support **24**. Support **24** comprises a semiconductor substrate **26** having its upper surface covered by an insulating layer **28**, for example made of silicon oxide.

[0056] Electronic components are for example formed inside and on top of substrate **26**. For example, in the example of FIG. **2A**, transistors **30** are formed inside and on top of substrate **26**. Transistors **30** are schematically shown by their gate **30a** resting on the upper surface of substrate **26** and their conduction nodes **30b** located in substrate **26**. Transistors **30** are, for example, selection transistors for memory cells.

[0057] Conductive vias **32** run through insulating layer **28**. Vias **32** enable to form connections between substrate **26** and the upper surface of layer **28**. In particular, vias **32** run through layer **28** to reach the conductive nodes **30b** of transistors **30**. For example, the device comprises, for each transistor **30**, a via **32** running through layer **28** in such a way as to reach a source region of said transistor **30** and a via **32** running through layer **28** in such a way as to reach a drain region of said transistor **30**.

[0058] Device **22** further comprises elements **34**. Each element **34** corresponds to a memory cell, for example a PCM (Phase Change Memory) cell. Each element **34** comprises a stack of a resistive element **36**, of a layer **38** made of a phase-change material, of a conductive layer **40** forming an upper electrode, and of a protective layer **42**.

[0059] The resistive element **36** of each element **34** is in contact with a via **32**. For example, the lower surface of each resistive element **36** is in contact with the upper surface of a via **32**. Each resistive element **36** for example has an L shape in a cross-section plane orthogonal to the plane of FIG. **2A**. Element **36** is for example made of metal, for example of tungsten or of copper.

[0060] Layer **38** is in contact with element **36**. For example, the upper surface of element **36** covers and is in contact with the lower surface of layer **38**. Layer **38** is for example made of a chalcogen material or of an alloy comprising a chalcogen material. For example, layer **38** is made of an alloy of germanium, antimony, and tellurium.

[0061] Layer **40** is in contact with layer **38**. Preferably, the lower surface of layer **40** covers and is in contact with the upper surface of layer **38**. Layer **40** is made of a metal, for example of copper.

[0062] Layer **42** is in contact with layer **40**. Preferably the lower surface of layer **42** covers and is in contact with the upper surface of layer **40**. Layer **42** is for example made of titanium nitride (TiN).

[0063] Elements **34** are for example arranged in an array, that is, in rows and in columns. Preferably, each element **34** comprises a resistive element **36**. The elements **36** of the different elements **34** of a same row are for example separated from one another by an insulating layer. The elements **34** of a same row for example comprise common layers **38**, **40**, **42**.

[0064] Each element **34** further comprises a passivation layer **44** covering the stack of element **36** and of layers **38**, **40**, **42**. Layer **44** is for example made of an insulating material, for example of silicon nitride. Layer **44** covers the upper surface of layer **42** and the side walls of the stack comprising element **36** and layers **38**, **40**, **42**. Layer **44** is for example common to all elements **34**.

Thus, layer **44** covers the portions of the upper surface of support **24** located between the stacks. Preferably, layer **44** conformably covers the entire structure comprising support **24** and the stacks.

[0065] Device **22** for example comprises at least one memory region, comprising a high density of elements **34**, and at least another region, for example a logic region, comprising a lower density of elements **34** or comprising no element **34**.

[0066] FIG. **2B** shows, schematically, a structure resulting from a step of manufacturing electronic device **22**. More particularly, FIG. **2B** corresponds to the manufacturing portions **46**.

[0067] Portions **46**, like the portions **18** of the embodiment of FIGS. **1A** to **1E**, are made of TiSiN. Portions **46** extend over the side walls of elements **34**, just as the portions **18** of the embodiment of FIGS. **1A** to **1E** extend over the walls of elements **14**.

[0068] Portions **46** are formed, like the portions **18** of the embodiment of FIGS. **1A** to **1E**, by conformally forming a TiSiN layer over the entire structure resulting from the step of FIG. **1A** and the anisotropic etching of said layer so as to remove the portions of said layer other than portions **46**. Thus, the portions of said layer located on the portions of layer **44** covering, preferably entirely, the upper surfaces of layers **42** and the portions of said layer located on the portions of layer **44** covering the upper surface of support **24** are removed by the anisotropic etch step. Preferably, each portion **46** extends from the upper surface of layer **44** extending over support **24** and up to at least the upper surface of layer **42**, preferably up to the upper surface of the portion of layer **44** extending over layer **42**. Said layer for example has a thickness in the range from 1 nm to 50 nm, for example substantially equal to 10 nm.

[0069] FIG. **2C** shows, schematically, a structure resulting from a step of manufacturing electronic device **22**.

[0070] During this step, a layer **48** is formed on the structure resulting from the step of FIG. **2B**. Layer **48** is for example a protective layer. Layer **48** is for example made of a dielectric material, for example of silicon nitride or of silicon oxide. Preferably, layer **48** is made of a material different from the material of layer **44**.

[0071] Layer **48** is configured to entirely cover elements **34**. Thus, the thickness of layer **48** is greater than the height of elements **34**, that is, the distance between the upper surface of support **24** and the upper surface of the portion of layer **44** covering layer **42**. Preferably, layer **44** is entirely covered by layer **48**.

[0072] The upper surface of layer **48** is not planar. In particular, the portions of layer **48** covering elements **34** are located further away from the support than the portions of layer **48** directly covering support **24**.

[0073] FIG. **2D** shows, schematically, a structure resulting from a step of manufacturing electronic device **22**.

[0074] The step of FIG. **2D** corresponds to a step of planarization of layer **48**. For example, the planarization is performed by chemical mechanical polishing (CMP). The planarization is preferably maintained until the upper surface of the portions of layer **44** covering layer **42** has been reached, that is, the surface of elements **34** most distant from support **24**.

[0075] For example, the upper end of portions **46** and the upper surface of the portions of layer **44** covering layers **42** are exposed by the planarization step.

[0076] FIG. **2E** shows, schematically, a structure resulting from a step of manufacturing electronic device **22**.

[0077] During this step, an insulating layer **50** is formed on the structure resulting from the step of FIG. **2D**. Layer **50** thus covers layer **48** and elements **34**. In other words, layer **50** covers layer **48**, the upper ends of portions **46** and the upper surfaces of portions of layer **44** covering layers **42**.

[0078] Conductive vias **52** and **54** are then formed in such a way as to form connections with the support. Vias **52** run through layers **44**, **48**, **50** in such a way as to reach the ends of vias **32** not being covered by elements **34**. Vias **54** run through layer **50** and layer **44** in such a way as to reach layer **42**.

[0079] It could have been chosen not to form portions **46**. However, the nitride density in the regions comprising elements **34**, and more specifically the silicon nitride rate with respect to the silicon oxide rate, is too low to enable the planarization method to form a planar upper surface. Thus, in the absence of portions **46**, the upper surface of layer **48** is not planar after the planarization method.

[0080] FIG. **3A**, FIG. **3B**, FIG. **3C**, FIG. **3D**, and FIG. **3E** show another embodiment of a method of manufacturing an electronic device **56**. The embodiment of FIGS. **3A** to **3E** corresponds, for example, to a more detailed example of implementation of the embodiment of the method of FIGS. **1A** to **1E**. More precisely, FIGS. **3A** to **3E** show steps, preferably successive, of a method of manufacturing device **56**.

[0081] FIG. **3A** shows, schematically, a structure resulting from a step of manufacturing electronic device **56**.

[0082] The step of FIG. **3A** comprises the forming of a support **58**. Support **58** is, for example, an electronic chip. Support **58** for example comprises a semiconductor substrate and an interconnection network, that is, a stack of insulating layers as well as conductive tracks and conductive vias. Support **58** is, for example, a wafer. Support **58** is, for example, only a semiconductor substrate. Support **58** is, for example, a layer made of an insulating material.

[0083] The step of FIG. **3A** further comprises the forming of elements **60**. Elements **60** are bonded to an upper surface of support **58**. Elements **60** correspond, for example, to portions of layers having been formed on support **58** and etched. Elements **60** correspond, for example, to chips or stacks of layers formed independently from support **58** and bonded to the support **58**, more precisely to the upper surface of the support **58**. Elements **60** are for example bonded by a bonding layer, for example an adhesive layer, by molecular bonding or by soldering.

[0084] For example, support **58** corresponds to a handle, for example a temporary handle, having elements **60** bonded thereto.

[0085] Each element **60** comprises, for example, a main portion **60a**, corresponding to the portion closest to support **58**, and a secondary portion **60b**, corresponding to the portion most distant from support **58**. Secondary portion **60b** is intended to be thinned. Thus, secondary portion **60b** preferably comprises no electronic components.

[0086] Elements **60** for example have a surface area, in top view, in the range from 1 mm.² to 100 mm.². Elements **60** are separated from one another by a distance in the range from 100 μ m to 50 mm. The height of the elements **60** is for example greater than 500 μ m, for example greater than 1 mm.

[0087] FIG. **3B** shows, schematically, a structure resulting from a step of manufacturing electronic device **56**.

[0088] During this step, a layer **62** of TiSiN is formed on the structure resulting from the step of FIG. **3A**. Layer **62** is preferably made of a homogeneous material. Layer **62** is preferably entirely made of TiSiN.

[0089] Layer **62** is conformally formed. Layer **62** covers all the exposed walls of the structure resulting from the step of FIG. **3A**. More precisely, layer **62** covers the side walls and the upper surface of elements **60** and the portions of support **58** not being covered by elements **60**. Layer **62** for example has a thickness greater than 200 nm, for example greater than 500 nm.

[0090] FIG. **3C** shows, schematically, a structure resulting from a step of manufacturing electronic device **56**.

[0091] The step of FIG. **3C** comprises a step of anisotropic etching of layer **62**. The etching is a selective etching. More precisely, the etching is a selective etching of TiSiN over to the materials of support **58** and the elements **60** having layer **62** resting thereon.

[0092] The etching of layer **62** being anisotropic, the portions of layer **62** located on the upper surface of support **58** and on the upper surfaces of elements **60** are removed. Portions **64** of layer **62**, located on the side walls of elements **60**, are kept at the end of the etching.

[0093] Portions **64** preferably extend all over the side walls of elements **60**. Thus, portions **64** preferably extend from the upper surface of support **58** and up to the upper surface of elements **60**, more precisely of the portion **60b** of elements **60**.

[0094] FIG. **3D** shows, schematically, a structure resulting from a step of manufacturing electronic device **56**.

[0095] During this step, a layer **66** is formed on the structure resulting from the step of FIG. **3C**. Layer **66** is, for example, a protective layer. Layer **66** is for example made of a dielectric material, for example of silicon nitride or silicon oxide.

[0096] Layer **66** is configured to entirely cover elements **60**. Thus, the thickness of layer **66** is greater than the height of elements **60**, that is, the distance between the upper surface of support **58** and the upper surface of the portions **60b** of elements **60**.

[0097] The upper surface of layer **66** is not planar. In particular, the portions of layer **66** covering elements **60** are located further away from the support than the portions of layer **66** directly covering support **58**.

[0098] FIG. **3E** shows, schematically, a structure resulting from a step of manufacturing electronic device **56**.

[0099] The step of FIG. **3E** corresponds to a step of thinning of elements **60**, more precisely of the portion **60b** of elements **60**.

[0100] The step of FIG. **3E** for example comprises a planarization step. For example, the planarization is performed by a chemical mechanical polishing (CMP). The planarization is maintained so as to thin elements **60**. More precisely, the planarization is maintained until portions **64** and portions **60b** are partially etched. For example, the height of each element **60** after thinning is in the range from 5 μm to 100 μm .

[0101] It could have been chosen not to form portions **64** on the side walls of elements **60**.

However, the thinning step, and more precisely the CMP step, would then cause a faster etching at the corners of elements **60** and would not allow a correct planarization.

[0102] Various embodiments and variants have been described. Those skilled in the art will understand that certain features of these various embodiments and variants may be combined, and other variants will occur to those skilled in the art.

[0103] Finally, the practical implementation of the described embodiments and variants is within the abilities of those skilled in the art based on the functional indications given hereabove.

[0104] Method of manufacturing an electronic device (**10**, **22**, **56**) is summarized as including: the forming, on an upper surface of a support (**12**, **24**, **58**), of first elements (**14**, **34**, **60**); the forming, on the side walls of each first element (**14**, **34**, **60**), of a first layer (**18**, **46**, **64**) of titanium silicon nitride; the forming of a protective layer (**20**, **48**, **66**) covering the upper surface of the support and the first elements; and the planarization of the second layer so as to reach at least the level of an upper surface of the first elements.

[0105] Device (**10**, **22**, **56**), is summarized as including first elements (**14**, **34**, **60**) bonded to an upper surface of a support (**12**, **24**, **58**), the side walls of the first element being covered by a first titanium silicon nitride layer (**18**, **46**, **64**), the device further including a protective layer (**20**, **48**, **66**) covering the upper surface of the support and extending all the way to the upper surface of the first elements.

[0106] The forming of the first layers (**18**, **46**, **64**) includes the conformal forming of a second titanium silicon nitride layer (**16**, **62**) and the anisotropic etching of the second titanium silicon nitride layer.

[0107] Each first element (**34**) includes a phase-change memory cell, and the support (**24**) includes a semiconductor substrate inside and on top of which selection transistors (**30**) associated with the phase-change memory cells are formed.

[0108] Each memory cell includes a stack of a resistive element (**36**), of a layer of phase-change material (**38**), and of a conductive layer (**40**), each memory cell includes an insulating layer (**44**)

covering the stack, the portions of the insulating layer covering the side walls of the stack of each cell being covered by the first layer (46).

[0109] The thickness of the second titanium silicon nitride layer (44) is in the range from 5 nm to 20 nm.

[0110] Each first element (60) is an electronic chip.

[0111] The thickness of the second titanium silicon nitride layer (62) is greater than 200 nm.

[0112] The first titanium silicon nitride layers (18, 46, 64) extend only on the side walls of the first elements (14, 34, 60).

[0113] The planarization step is a chemical mechanical polishing step.

[0114] The protective layer is made of an insulating material (20, 48, 66).

[0115] The planarization step is maintained until the upper surface of the first elements has been reached.

[0116] The planarization step includes the thinning of the first elements.

[0117] The various embodiments described above can be combined to provide further embodiments. Aspects of the embodiments can be modified, if necessary to employ concepts of the various patents, applications and publications to provide yet further embodiments.

[0118] These and other changes can be made to the embodiments in light of the above-detailed description. In general, in the following claims, the terms used should not be construed to limit the claims to the specific embodiments disclosed in the specification and the claims, but should be construed to include all possible embodiments along with the full scope of equivalents to which such claims are entitled. Accordingly, the claims are not limited by the disclosure.

Claims

1. A method of manufacturing an electronic device comprising in sequence: providing a support, forming, on an upper surface of the support, a plurality of memory elements each comprising a stack of layers, one of which is made of a phase-change material, the memory element having a first height; forming, on each side wall of each memory element, an etching stop element made of titanium silicon nitride, the etching stop elements having a second height substantially equal to the first height; forming a protective layer covering the upper surface of the support and an upper surface of the memory elements and of the etching stop elements; and planarizing the protective layer to expose the upper surface of the memory elements and the upper surface of the etching stop elements.
2. The method according to claim 1, wherein the forming of the etching stop elements includes conformally depositing a titanium silicon nitride layer on the upper surface of the support and on the side wall and the upper surface of the memory elements and anisotropic etching the titanium silicon nitride layer from the upper surface of the support and from the upper surface of the memory elements.
3. The method according to claim 2, wherein a thickness of the titanium silicon nitride layer is in the range from 5 nm to 20 nm.
4. The method according to claim 1, wherein the support comprises a semiconductor substrate comprising selection transistors formed inside and on top of substrate, an insulating layer covering the semiconductor substrate, conductive vias running through the insulating layer to form connections between substrate and the memory elements.
5. The method according to claim 1, wherein the planarizing includes chemical mechanical polishing.
6. The method according to claim 1, wherein the planarizing is continued until the upper surface of the etching stop elements is reached.
7. The method according to claim 1, wherein the planarizing includes thinning the etching stop elements.

- 8.** The method according to claim 1, wherein each stack comprises a resistive element, the layer of phase-change material, and a conductive layer.
- 9.** The method according to claim 1, wherein the forming of the memory elements comprises conformally depositing an insulating layer directly covering the upper surface of the support and each stack, the etch stop elements being in direct contact with sidewall portions of the insulating layer covering side walls of the stack.
- 10.** The method according to claim 9, wherein the protective layer is made of a first dielectric material and the insulating layer is made of a second dielectric material different from the first dielectric material.
- 11.** The method according to claim 9, wherein the planarizing of the protective layer comprises exposing the insulating layer on top of each stack and the upper surface of the etching stop elements.
- 12.** A method of manufacturing an electronic device comprising in sequence: providing a support, bonding, on an upper surface of the support, a plurality of electronic elements each comprising a main portion proximal to support, and a secondary portion distal from the support, the electronic elements having a first height; forming, on each side wall of each electronic elements, an etching stop element made of titanium silicon nitride, the etching stop elements having a second height substantially equal to the first height; forming a protective layer covering the upper surface of the support and an upper surface of the electronic elements and of the etching stop elements; and planarizing the protective layer to thin the electronic elements and the etching stop elements.
- 13.** The method according to claim 12, wherein a height of the electronic elements and the etching stop elements after planarizing is in the range from 5 μm to 100 μm .
- 14.** The method according to claim 12, wherein the first and second height is greater than 500 μm .
- 15.** The method according to claim 12, wherein the secondary portion of each electronic elements comprises no electronic components.
- 16.** The method according to claim 12, wherein the forming of the etching stop elements includes conformally depositing a titanium silicon nitride layer on the upper surface of the support and on the side wall and the upper surface of the first elements and anisotropic etching the titanium silicon nitride layer from the upper surface of the support and from the upper surface of the first elements.
- 17.** The method according to claim 16, wherein the titanium silicon nitride layer has a thickness greater than 200 nm.
- 18.** The method according to claim 12, wherein bonding the electronic elements to the support is made by an adhesive layer, by molecular bonding or by soldering.
- 19.** The method according to claim 12, wherein the support comprises a semiconductor substrate and an interconnection network comprising a stack of insulating layers, conductive tracks and conductive vias.
-