

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250287619

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

JEON; Intak et al.

INTEGRATED CIRCUIT DEVICE

Abstract

An integrated circuit device includes: a lower electrode disposed on a substrate; an insulating support pattern supporting the lower electrode; a dielectric film surrounding the lower electrode and the insulating support pattern; a high-k interface layer arranged between the lower electrode and the dielectric film and between the insulating support pattern and the dielectric film, wherein the high-k interface layer contacts the insulating support pattern and includes a zirconium oxide layer; and an upper electrode disposed adjacent the lower electrode, wherein the high-k interface layer and the dielectric film are disposed between the upper electrode and the lower electrode.

Inventors: JEON; Intak (Seoul, KR), LIM; Hanjin (Seoul, KR), JUNG; Hyungsuk (Suwon-si, KR), CHOI; Jaehyoung (Hwaseong-si, KR)

Applicant: SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)

Family ID: 85774434

Assignee: SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)

Appl. No.: 19/213912

Filed: May 20, 2025

Foreign Application Priority Data

KR 10-2021-0132680

Oct. 06, 2021

Related U.S. Application Data

parent US continuation 17805702 20220607 parent-grant-document US 12336202 child US 19213912

Publication Classification

Int. Cl.: H10D1/68 (20250101); **H01G4/10** (20060101); **H10B12/00** (20230101); **H10D1/00** (20250101)

U.S. Cl.:

CPC H10D1/696 (20250101); **H01G4/10** (20130101); **H10B12/03** (20230201); **H10D1/042** (20250101); **H10D1/694** (20250101); **H10D1/716** (20250101);

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION [0001] This application is a Continuation of U.S. patent application Ser. No. 17/805,702, filed on Jun. 7, 2022, which claims priority under 35 U.S.C. § 119 to Korean Patent Application Nos. 10-2021-0132680, filed on Oct. 6, 2021 in the Korean Intellectual Property Office, the disclosures of which are incorporated by reference herein in their entireties.

TECHNICAL FIELD

[0002] Embodiments of the inventive concept relate to an integrated circuit device, and more particularly, to an integrated circuit device including a capacitor.

DISCUSSION OF THE RELATED ART

[0003] User electronic devices have become ubiquitous in recent times. Semiconductor devices are used in several user electronic devices that process digital information. For example, mobile phones, watches, personal computers, and the like all utilize semiconductor devices. For example, semiconductor devices are used for implementing displays, processors, memory, etc.

[0004] As these electronics continue to be developed, semiconductor devices have been rapidly down-scaled, and thus, patterns within the devices have become smaller. Patterns such as finer pitch wiring, thinner insulating and connecting layers, etc. have all been developed to increase utilization of space. However, the reduction in size of the patterns and the connections may also cause undesired electrical characteristics, such as loss of charge, and changes to charges and data in adjacent components. Accordingly, there is a need to develop structures allowing fine-sized capacitors to have reduced leakage currents and maintain desired electrical characteristics.

SUMMARY

[0005] The inventive concept provides an integrated circuit device having a structure which allows a capacitor to have a reduced leakage current by preventing a bridge between lower electrodes that are storage nodes and to maintain desired electrical characteristics.

[0006] An integrated circuit device according to an aspect of the inventive concept includes: a lower electrode disposed on a substrate; an insulating support pattern supporting the lower electrode; a dielectric film surrounding the lower electrode and the insulating support pattern; a high-k interface layer, wherein the high-k interface layer is arranged between the lower electrode and the dielectric film and between the insulating support pattern and the dielectric film, and wherein the high-k interface layer contacts the insulating support pattern and includes a zirconium oxide layer; and an upper electrode disposed adjacent to the lower electrode, wherein the high-k interface layer and the dielectric film are disposed between the upper electrode and the lower electrode.

[0007] An integrated circuit device according to another aspect of the inventive concept includes: a substrate including an active region; a conductive region disposed on the active region; a capacitor disposed on the conductive region; and an insulating support pattern supporting a portion of the capacitor, wherein the capacitor includes: a lower electrode including a portion contacting the insulating support pattern; a dielectric film at least partially surrounding the lower electrode and the

insulating support pattern; a high-k interface layer arranged between the lower electrode and the dielectric film and between the insulating support pattern and the dielectric film, and wherein the high-k interface layer contacts the insulating support pattern, and includes a zirconium oxide layer; and an upper electrode disposed adjacent the lower electrode, wherein the high-k interface layer and the dielectric film are disposed between the upper electrode and the lower electrode.

[0008] An integrated circuit device according to another aspect of the inventive concept includes: a substrate including an active region; a plurality of conductive regions disposed on the active region; an insulating pattern disposed on the plurality of conductive regions and extending in a horizontal direction parallel to the substrate, the insulating pattern including a plurality of openings that vertically overlap the plurality of conductive regions; a plurality of lower electrodes penetrating the insulating pattern through the plurality of openings and connected to the plurality of conductive regions, wherein each of the plurality of lower electrodes includes a first metal; an insulating support pattern disposed apart from the insulating pattern in a vertical direction to extend in the horizontal direction, the insulating support pattern contacting a portion of each of the plurality of lower electrodes to support the plurality of lower electrodes; a dielectric film covering the plurality of lower electrodes, the insulating pattern, and the insulating support pattern; a high-k interface layer arranged between the plurality of lower electrodes and the dielectric film, between the insulating support pattern and the dielectric film, and between the insulating pattern and the dielectric film, wherein the high-k interface layer contacts the insulating support pattern, and includes a zirconium oxide layer; and an upper electrode disposed adjacent to each of the plurality of lower electrodes, wherein the high-k interface layer and the dielectric film are disposed between the upper electrode and each of the plurality of lower electrodes, and wherein the upper electrode includes a second metal.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] Embodiments of the inventive concept will be more clearly understood from the following detailed description taken in conjunction with the accompanying drawings, in which:

[0010] FIG. 1 is a schematic planar layout that illustrates some components in a memory cell array area of an integrated circuit device, according to embodiments of the inventive concept;

[0011] FIG. 2A is a plan view that illustrates some components of the integrated circuit device shown in FIG. 1;

[0012] FIG. 2B is a cross-sectional view that schematically illustrates some components, taken along a line X1-X1' of FIG. 2A;

[0013] FIG. 3 is an enlarged cross-sectional view of a region EX1A in FIG. 2B;

[0014] FIG. 4 is an enlarged cross-sectional view of a region EX1B in FIG. 2B;

[0015] FIG. 5A is a plan view that illustrates a planar shape of a high-k interface layer included in an integrated circuit device, according to embodiments of the inventive concept;

[0016] FIG. 5B is an enlarged partially-cutaway perspective view of a portion of a region EXP in FIG. 5A;

[0017] FIG. 6 is a cross-sectional view that illustrates main components of an integrated circuit device, according to embodiments of the inventive concept;

[0018] FIG. 7 is an enlarged cross-sectional view of a region EX2A in FIG. 6;

[0019] FIG. 8 is an enlarged cross-sectional view of a region EX2B in FIG. 6;

[0020] FIGS. 9A to 9I are cross-sectional views that illustrate sequential processes of a method of manufacturing an integrated circuit device, according to embodiments of the inventive concept; and

[0021] FIG. 10 is a cross-sectional view that illustrates a method of manufacturing an integrated circuit device, according to other embodiments of the inventive concept.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0022] Hereinafter, embodiments of the inventive concept will be described in detail with reference to the accompanying drawings. Like components are denoted by like reference numerals throughout the specification, and to the extent any description is omitted, it will be appreciated that description of similar components may be found throughout in the specification.

[0023] FIG. 1 is a schematic planar layout that illustrates some components in a memory cell array area of an integrated circuit device, according to embodiments of the inventive concept.

[0024] Referring to FIG. 1, an integrated circuit device **100** may include a plurality of active regions AC which extend in an oblique direction on a horizontal plane with respect to a first horizontal direction (e.g., an X direction) and a second horizontal direction (e.g., a Y direction), which are perpendicular to each other on the horizontal plane. A plurality of word lines WL may extend parallel to each other in the first horizontal direction (e.g., the X direction) across the plurality of active regions AC. A plurality of bit lines BL may be arranged over the plurality of word lines WL and extend parallel to each other in the second horizontal direction (e.g., the Y direction). Each of the plurality of bit lines BL may be connected to an active region AC via a direct contact DC.

[0025] A plurality of buried contacts BC may be formed between two adjacent bit lines BL from among the plurality of bit lines BL. A plurality of conductive landing pads LP may be respectively formed on the plurality of buried contacts BC. Each of the plurality of conductive landing pads LP may at least partially overlap a buried contact BC. A plurality of lower electrodes LE may be respectively formed on the plurality of conductive landing pads LP. The plurality of lower electrodes LE may be spaced apart from each other. The plurality of lower electrodes LE may be respectively connected to the plurality of active regions AC via the plurality of buried contacts BC and the plurality of conductive landing pads LP.

[0026] FIG. 2A is a plan view that illustrates some components of the integrated circuit device **100** shown in FIG. 1. FIG. 2B is a schematic cross-sectional view that illustrates some components of the integrated circuit device **100**, taken along a line X1-X1' of FIG. 2A. FIG. 3 is an enlarged cross-sectional view of a region EX1A in FIG. 2B. FIG. 4 is an enlarged cross-sectional view of a region EX1B in FIG. 2B.

[0027] Referring to FIGS. 2A, 2B, 3, and 4, the integrated circuit device **100** may include a substrate **110** including the plurality of active regions AC, and a lower structure **120** disposed on the substrate **110**. A plurality of conductive regions **124** may be respectively connected to the plurality of active regions AC through the lower structure **120** in a vertical direction (Z direction).

[0028] The substrate **110** may include an elemental semiconductor such as Si or Ge, or a compound semiconductor such as SiC, GaAs, InAs, or InP. The substrate **110** may include a semiconductor substrate, and structures including at least one insulating film and/or at least one conductive region, which is formed on the semiconductor substrate. The conductive region may include, for example, an impurity-doped well or an impurity-doped structure. A device isolation film **112**, which defines the plurality of active regions AC, may be formed in the substrate **110**. The device isolation film **112** may include an oxide film, a nitride film, or a combination thereof.

[0029] In some embodiments, the lower structure **120** may include an insulating film including a silicon oxide film, a silicon nitride film, or a combination thereof. In some embodiments, the lower structure **120** may include various conductive regions, such as a wiring layer, a contact plug, a transistor, and the like, and insulating films that insulate the conductive regions from each other. The plurality of conductive regions **124** may each include polysilicon, a metal, a conductive metal nitride, a metal silicide, or a combination thereof. The lower structure **120** may include the plurality of bit lines BL described with reference to FIG. 1. Each of the plurality of conductive regions **124** may include the buried contact BC and the conductive landing pad LP, which are described with reference to FIG. 1.

[0030] An insulating pattern **126P** having a plurality of openings **126H** may be arranged on the

lower structure **120** and the plurality of conductive regions **124**. The plurality of openings **126H** may respectively overlap the plurality of conductive regions **124** in the vertical direction (Z direction). The insulating pattern **126P** may include a silicon nitride (SiN) film, a silicon carbonitride (SiCN) film, a silicon boron nitride (SiBN) film, or a combination thereof. As used herein, each of the terms “SiN”, “SiCN”, and “SiBN” refer to a material that is composed of elements included in each of the terms, and is not a chemical formula representing a stoichiometric relationship.

[0031] A plurality of capacitors **CP1** may be respectively arranged on the plurality of conductive regions **124**. Each of the plurality of capacitors **CP1** may include a lower electrode **LE**, a high-k interface layer **150** and a dielectric film **160** which are both sequentially stacked on the lower electrode **LE** in the stated order, and an upper electrode **UE** which covers the dielectric film **160**. The plurality of lower electrodes **LE** may face the upper electrode **UE** with the high-k interface layer **150** and the dielectric film **160** therebetween. For example, there may be two lower electrodes **LE** adjacent to an upper electrode **UE** disposed between them. As used herein, the term “high-k interface layer” may refer to a layer having a dielectric constant that is greater than a dielectric constant of the dielectric film **160**. The dielectric constant of the high-k interface layer **150** may be greater than the dielectric constant of the dielectric film **160**.

[0032] The insulating pattern **126P** may be arranged adjacent to a lower end of each of the plurality of lower electrodes **LE**. For example, the lower end of each of the plurality of lower electrodes **LE** may be the end of the lower electrode **LE** that is proximal to the lower structure **120**. Each of the plurality of lower electrodes **LE** may have a pillar shape extending lengthwise in a direction, which is orthogonal to the substrate **110** in the vertical direction (Z direction), through an opening **126H** of the insulating pattern **126P** from a top surface of a conductive region **124**. Although FIG. 2B illustrates an example in which each of the plurality of lower electrodes **LE** has a pillar shape, the inventive concept is not limited thereto. For example, each of the plurality of lower electrodes **LE** may have a cross-sectional structure having a cup shape or a closed-bottom cylinder shape.

[0033] The integrated circuit device **100** may include a lower insulating support pattern **142P** and an upper insulating support pattern **144P**, which support the plurality of lower electrodes **LE**.

[0034] FIG. 2A illustrates a planar structure of each of the upper insulating support pattern **144P** and the plurality of lower electrodes **LE**. As shown in FIGS. 2A and 2B, the upper insulating support pattern **144P** may extend in a direction parallel to the substrate **110** and may at least partially surround an upper end of each of the plurality of lower electrodes **LE** while being spaced apart from the insulating pattern **126P** in the vertical direction (Z direction). A plurality of holes **144H**, through which the plurality of lower electrodes **LE** are disposed, may be formed in the upper insulating support pattern **144P**. An inner sidewall of each of the plurality of holes **144H** formed in the upper insulating support pattern **144P** may contact an outer sidewall of the lower electrode **LE**. A top surface of each of the plurality of lower electrodes **LE** may be coplanar with a top surface of the upper insulating support pattern **144P**.

[0035] As shown in FIG. 2B, the lower insulating support pattern **142P** may be arranged between the substrate **110** and the upper insulating support pattern **144P** and may extend horizontally and parallel to the substrate **110**, and may contact sidewalls of the plurality of lower electrode **LE**. A plurality of holes **142H**, through which the plurality of lower electrodes **LE** are disposed, may be formed in the lower insulating support pattern **142P**. The plurality of lower electrodes **LE** may extend lengthwise in the vertical direction (Z direction) through the plurality of holes **144H**, which are formed in the upper insulating support pattern **144P**, and the plurality of holes **142H**, which are formed in the lower insulating support pattern **142P**.

[0036] As shown in FIG. 2A, a plurality of upper holes **UH** may be formed in the upper insulating support pattern **144P**. FIG. 2A illustrates a configuration in which a planar shape of each of the plurality of upper holes **UH** is approximately a rhombic shape where four adjacent lower electrodes **LE** correspond to vertices of the shape. However, the planar shape of each of the plurality of upper

holes UH is not limited to the example of FIG. 2A, and various changes and modifications may be made therein without departing from the spirit and scope of the inventive concept. A plurality of lower holes LH (see FIG. 9E), each having a planar shape corresponding to the planar shape of each of the plurality of upper holes UH, may be formed in the lower insulating support pattern **142P**.

[0037] Each of the lower insulating support pattern **142P** and the upper insulating support pattern **144P** may include a silicon nitride (SiN) film, a silicon carbonitride (SiCN) film, a silicon boron nitride (SiBN) film, or a combination thereof. In example embodiments, the lower insulating support pattern **142P** and the upper insulating support pattern **144P** may include the same materials as each other. In other example embodiments, the lower insulating support pattern **142P** and the upper insulating support pattern **144P** may include different materials from each other. In one example, each of the lower insulating support pattern **142P** and the upper insulating support pattern **144P** may include SiCN. In another example, the lower insulating support pattern **142P** may include SiCN, and the upper insulating support pattern **144P** may include SiBN. However, the inventive concept is not limited to the materials set forth above, which are examples.

[0038] The high-k interface layer **150**, the dielectric film **160**, and the upper electrode UE may be sequentially stacked on each of the plurality of lower electrodes LE, the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**. For example, high-k interface layer **150**, the dielectric film **160**, and the upper electrode UE may be sequentially stacked in the above stated order, as illustrated in FIG. 2B.

[0039] The high-k interface layer **150** may include a first interface portion **150A** arranged between the lower insulating support pattern **142P** and the dielectric film **160** and between the upper insulating support pattern **144P** and the dielectric film **160**, a second interface portion **150B** arranged between the lower electrode LE and the dielectric film **160**, and a third interface portion **150C** arranged between the insulating pattern **126P** and the dielectric film **160**.

[0040] The first interface portion **150A** of the high-k interface layer **150** may contact each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the dielectric film **160**. The second interface portion **150B** of the high-k interface layer **150** may contact the lower electrode LE and the dielectric film **160**. The third interface portion **150C** of the high-k interface layer **150** may contact the insulating pattern **126P** and the dielectric film **160**.

[0041] Each of the first interface portion **150A**, the second interface portion **150B**, and the third interface portion **150C** of the high-k interface layer **150** may include a plurality of interface clusters having a plurality of island shapes which are spaced apart from each other.

[0042] FIG. 5A is a plan view that illustrates a planar shape of the high-k interface layer **150**. FIG. 5A illustrates a plan view of some regions of the first interface portion **150A** of the high-k interface layer **150**, including regions covering the upper insulating support pattern **144P**.

[0043] As shown in FIG. 5A, the first interface portion **150A** of the high-k interface layer **150** may have a planar structure having a plurality of island shapes. Similar to the first interface portion **150A** shown in FIG. 5A, the second interface portion **150B** and the third interface portion **150C** of the high-k interface layer **150** may each also have a planar structure having a plurality of island shapes.

[0044] FIG. 5B is an enlarged partially-cutaway perspective view of some area included in a region EXP in FIG. 5A.

[0045] As shown in FIG. 5B, the upper insulating support pattern **144P** may be formed by a chemical vapor deposition (CVD) process. The upper insulating support pattern **144P** formed by the CVD process may include a plurality of insulating grains **144G**. The upper insulating support pattern **144P** formed by the CVD process may have a relatively less dense structure than a film formed by an atomic layer deposition (ALD) process.

[0046] The first interface portion **150A** covering the upper insulating support pattern **144P** may include a portion that at least partially covers a top surface of the upper insulating support pattern

144P, and a portion that permeates into the upper insulating support pattern **144P** through grain boundaries between each of the plurality of insulating grains **144G** included in the upper insulating support pattern **144P**. Accordingly, as shown in FIG. 3, a portion of the first interface portion **150A** covering the upper insulating support pattern **144P** may protrude toward the dielectric film **160** from an interface between the upper insulating support pattern **144P** and the dielectric film **160**, and another portion of the first interface portion **150A** covering the upper insulating support pattern **144P** may protrude into the upper insulating support pattern **144P** from the interface between the upper insulating support pattern **144P** and the dielectric film **160**. Although FIG. 3 illustrates an example case in which the portion of the first interface portion **150A**, which protrudes into the upper insulating support pattern **144P**, has a flat bottom surface, this is merely for the convenience of illustration, and a cross-sectional shape of the first interface portion **150A** is not limited to the example shown in FIG. 3.

[0047] For example, as shown in FIG. 5B, the portion of the first interface portion **150A**, which protrudes into the upper insulating support pattern **144P**, may have an irregular shape and an irregular size, and thus, the roughness of a surface of the first interface portion **150A**, which faces the upper insulating support pattern **144P**, may be greater than the roughness of a surface of the first interface portion **150A**, which faces the dielectric film **160**. For example, there may be a greater variation in heights and protrusions on the side of the first interface portion **150A** that faces the upper insulating support pattern than the side that faces the dielectric film **160**.

[0048] Each of the lower insulating support pattern **142P** and the insulating pattern **126P** may be obtained by a CVD process. Similar to the descriptions made regarding the upper insulating support pattern **144P** with reference to FIG. 5B, each of the lower insulating support pattern **142P** and the insulating pattern **126P** may include a plurality of insulating grains. Accordingly, the first interface portion **150A** of the high-k interface layer **150**, which at least partially covers the lower insulating support pattern **142P**, and the third interface portion **150C** of the high-k interface layer **150**, which at least partially covers the insulating pattern **126P**, may each have a shape that is the same as or similar to that of the first interface portion **150A** of the high-k interface layer **150**, which at least partially covers the upper insulating support pattern **144P**, as described with reference to FIGS. 5A and 5B.

[0049] The plurality of lower electrodes LE may be formed by an ALD process. Accordingly, each of the plurality of lower electrodes LE may have a more dense structure than the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**, and the roughness of surfaces of the plurality of lower electrodes LE, which face the dielectric film **160**, may be less than the roughness of respective surfaces of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**, which face the dielectric film **160**. Therefore, the second interface portion **150B** covering a surface of each of the plurality of lower electrodes LE may not include a portion protruding into the lower electrode LE.

[0050] As described above, the shape of the first interface portion **150A** of the high-k interface layer **150**, which at least partially covers the lower insulating support pattern **142P** and the upper insulating support pattern **144P**, and the shape of the third interface portion **150C** of the high-k interface layer **150**, which at least partially covers the insulating pattern **126P**, may be different from the shape of the second interface portion **150B** of the high-k interface layer **150**, which at least partially covers the plurality of lower electrodes LE, and a thickness of each of the first interface portion **150A** and the third interface portion **150C** may be different from a thickness of the second interface portion **150B**.

[0051] The high-k interface layer **150** may have a thickness between about 0 nm and about 2 nm. For example, the high-k interface layer **150** may have a thickness between about 0 nm and about 1 nm. In example embodiments, the thicknesses of each of the first interface portion **150A** and the third interface portion **150C** may be greater than the thickness of the second interface portion **150B**. For example, as shown in FIGS. 3 and 4, a thickness TH1A of the first interface portion **150A** may

be greater than a thickness TH1B of the second interface portion **150B**. The thickness TH1A of the first interface portion **150A** and the thickness TH1B of the second interface portion **150B** may be less than a thickness THD of the dielectric film **160**.

[0052] As shown in FIG. 2B, the dielectric film **160** may contact the lower insulating support pattern **142P** and the upper insulating support pattern **144P** through spaces between each of the plurality of interface clusters constituting the first interface portion **150A**, may contact the lower electrode LE through spaces between each of the plurality of interface clusters constituting the second interface portion **150B**, and may contact the insulating pattern **126P** through spaces between each of the plurality of interface clusters constituting the third interface portion **150C**.

[0053] The high-k interface layer **150** might not be disposed between the lower electrode LE and the insulating pattern **126P**, between the lower electrode LE and the lower insulating support pattern **142P**, and between the lower electrode LE and the upper insulating support pattern **144P**.

[0054] The high-k interface layer **150** may include a material having a relatively broad band gap energy of about 5 eV or more. In example embodiments, the high-k interface layer **150** may include a zirconium oxide layer. For example, the high-k interface layer **150** may include a portion including ZrO.sub.2.

[0055] In some example embodiments, the high-k interface layer **150** may include a zirconium oxide layer including at least one dopant element. The at least one dopant element may include a metallic element that is different from zirconium (Zr). The at least one dopant element may include a typical metal, a transition metal, or a post-transition metal.

[0056] In example embodiments, the high-k interface layer **150** may include a zirconium oxide layer including at least one dopant element selected from among aluminum (Al), niobium (Nb), molybdenum (Mo), ruthenium (Ru), indium (In), tin (Sn), antimony (Sb), scandium (Sc), titanium (Ti), vanadium (V), manganese (Mn), iron (Fe), cobalt (Co), nickel (Ni), arsenic (As), tantalum (Ta), tungsten (W), iridium (Ir), yttrium (Y), and bismuth (Bi). For example, the high-k interface layer **150** may include a zirconium oxide layer doped with Ti, a zirconium oxide layer doped with Nb, a zirconium oxide layer doped with Ti and Nb, or a combination thereof.

[0057] The high-k interface layer **150** may include a stoichiometric metallic oxide layer or a non-stoichiometric metallic oxide layer. For example, the high-k interface layer **150** may include a ZrO.sub.2 layer, an oxygen-deficient zirconium oxide layer having a lower oxygen atom content proportion than the ZrO.sub.2 layer, or an oxygen-rich zirconium oxide layer having a greater oxygen atom content proportion than the ZrO.sub.2 layer. Each of the ZrO.sub.2 layer, the oxygen-deficient zirconium oxide layer, and the oxygen-rich zirconium oxide layer may further include at least one dopant element including a metallic element that is different from zirconium (Zr), or may not include the dopant element set forth above.

[0058] The dielectric film **160** may include a high-k film. As used herein, the term “high-k film” refers to a dielectric film having a higher dielectric constant than a silicon oxide film. In example embodiments, the dielectric film **160** may include a metal oxide including at least one metal selected from among hafnium (Hf), zirconium (Zr), aluminum (Al), niobium (Nb), cerium (Ce), lanthanum (La), tantalum (Ta), and titanium (Ti). In example embodiments, the dielectric film **160** may have a single-layer structure including one type of high-k film. In some example embodiments, the dielectric film **160** may have a multi-layer structure including a plurality of types of high-k films. The high-k film may include, but is not limited to, HfO.sub.2, ZrO.sub.2, Al.sub.2O.sub.3, La.sub.2O.sub.3, Ta.sub.2O.sub.5, Nb.sub.2O.sub.5, CeO.sub.2, TiO.sub.2, GeO.sub.2, or a combination thereof. In example embodiments, the thickness THD (see FIGS. 3 and 4) of the dielectric film **160** may be, but is not limited to, about 2 nm to about 8 nm.

[0059] The lower electrode LE may include a first metal. The upper electrode UE may include a second metal. In example embodiments, the second metal may be the same as the first metal. In other example embodiments, the second metal may be different from the first metal.

[0060] The lower electrode LE and the upper electrode UE may each include a metal film, a

conductive metal oxide film, a conductive metal nitride film, a conductive metal oxynitride film, or a combination thereof. In example embodiments, the lower electrode LE and the upper electrode UE may each include Nb, Nb oxide, Nb nitride, Nb oxynitride, Ti, Ti oxide, Ti nitride, Ti oxynitride, Co, Co oxide, Co nitride, Co oxynitride, Sn, Sn oxide, Sn nitride, Sn oxynitride, or a combination thereof. For example, the lower electrode LE and the upper electrode UE may each include NbN, TiN, CON, SnO.sub.2, or a combination thereof. In other example embodiments, the lower electrode LE and the upper electrode UE may each include TaN, TiAlN, TaAlN, V, VN, Mo, MoN, W, WN, Ru, RuO.sub.2, SrRuO.sub.3, Ir, IrO.sub.2, Pt, PtO, SRO (SrRuO.sub.3), BSRO ((Ba,Sr)RuO.sub.3), CRO (CaRuO.sub.3), LSCO ((La,Sr)CoO.sub.3), or a combination thereof. However, the material of each of the lower electrode LE and the upper electrode UE is not limited to the examples set forth above.

[0061] In example embodiments, the lower electrode LE may include a first metallic element, the dielectric film **160** may include a second metallic element that is different from the first metallic element, and the high-k interface layer **150** may include a dopant element including the same metallic element as the first metallic element and/or the second metallic element. In one example, the lower electrode LE may include Ti, Ti oxide, Ti nitride, Ti oxynitride, or a combination thereof, and the high-k interface layer **150** may include a zirconium oxide layer doped with Ti or a zirconium oxide layer doped with Ti and Nb. In another example, the lower electrode LE may include Nb, Nb oxide, Nb nitride, Nb oxynitride, or a combination thereof, and the high-k interface layer **150** may include a zirconium oxide layer doped with Nb or a zirconium oxide layer doped with Ti and Nb.

[0062] In some example embodiments, the lower electrode LE may include a first metallic element, the dielectric film **160** may include a second metallic element that is different from the first metallic element, and the high-k interface layer **150** may include at least one dopant element including a metallic element that is different from the first metallic element and the second metallic element. In one example, the lower electrode LE may include Co, Co oxide, Co nitride, Co oxynitride, Sn, Sn oxide, Sn nitride, Sn oxynitride, or a combination thereof, and the high-k interface layer **150** may include a zirconium oxide layer doped with Ti or a zirconium oxide layer doped with Ti and Nb.

[0063] In other example embodiments, the integrated circuit device **100** may further include an upper conductive interface layer arranged between the dielectric film **160** and the upper electrode UE. The upper conductive interface layer may include, but is not limited to, a TiO.sub.2 layer.

[0064] FIG. **6** is a cross-sectional view that illustrates main components of an integrated circuit device **200**, according to embodiments of the inventive concept. FIG. **6** schematically illustrates some components corresponding to a cross-section taken along the line X1-X1' of FIG. **2A**. FIG. **7** is an enlarged cross-sectional view of a region EX2A in FIG. **6**. FIG. **8** is an enlarged cross-sectional view of a region EX2B in FIG. **6**. In FIGS. **6** to **8**, the same reference numerals as in FIGS. **1** to **4** denote the same members, and here, repeated detailed descriptions thereof may be omitted for brevity.

[0065] Referring to FIGS. **6** to **8**, the integrated circuit device **200** may have a substantially the same configuration as the integrated circuit device **100** described with reference to FIGS. **1** to **5B**. However, the integrated circuit device **200** may include a high-k interface layer **250** instead of the high-k interface layer **150**. For example, the high-k interface layer **250** may be implemented without the irregular portions of the high-k interface layer **150**.

[0066] The high-k interface layer **250** may have substantially the same configuration as the high-k interface layer **150** described with reference to FIGS. **2B**, **3**, **4**, **5A**, and **5B**. The high-k interface layer **250** may include a first interface portion **250A** arranged between the lower insulating support pattern **142P** and the dielectric film **160**, and arranged between the upper insulating support pattern **144P** and the dielectric film **160**, a second interface portion **250B** arranged between the lower electrode LE and the dielectric film **160**, and a third interface portion **250C** arranged between the

insulating pattern **126P** and the dielectric film **160**.

[0067] The high-k interface layer **250** may conformally cover (e.g., at least partially cover) a surface of each of the lower electrode LE, the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**. The high-k interface layer **250** may contact each of the lower electrode LE, the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**. The first interface portion **250A** of the high-k interface layer **250** may contact each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the dielectric film **160**. The second interface portion **250B** of the high-k interface layer **250** may contact each of the lower electrode LE and the dielectric film **160**. The third interface portion **250C** of the high-k interface layer **250** may contact each of the insulating pattern **126P** and the dielectric film **160**.

[0068] The first interface portion **250A** of the high-k interface layer **250** may extend (e.g., continuously extend) between the lower insulating support pattern **142P** and the dielectric film **160** and between the upper insulating support pattern **144P** and the dielectric film **160** such that the lower insulating support pattern **142P** and the upper insulating support pattern **144P** do not contact the dielectric film **160**. The second interface portion **250B** of the high-k interface layer **250** may extend (e.g., continuously extend) between the lower electrode LE and the dielectric film **160** such that the lower electrode LE and the dielectric film **160** do not contact each other. The third interface portion **250C** of the high-k interface layer **250** may extend (e.g., continuously extend) between the insulating pattern **126P** and the dielectric film **160** such that the insulating pattern **126P** and the dielectric film **160** do not contact each other. The first interface portion **250A**, the second interface portion **250B**, and the third interface portion **250C** of the high-k interface layer **250** may be integrally connected to each other.

[0069] The high-k interface layer **250** may have a thickness between about 0 nm and about 2 nm. For example, the high-k interface layer **250** may have a thickness that is between about 0 nm and about 1 nm. In the high-k interface layer **250**, a thickness of each of the first interface portion **250A** and the third interface portion **250C** may be different from a thickness of the second interface portion **250B**. In example embodiments, the thickness of the first interface portion **250A** may be equal or similar to the thickness of the third interface portion **250C**. In example embodiments, as shown in FIGS. 7 and 8, a thickness TH2A of the first interface portion **250A** may be greater than a thickness TH2B of the second interface portion **250B**. The thickness TH2A of the first interface portion **250A** and the thickness TH2B of the second interface portion **250B** may be less than a thickness THE of the dielectric film **160**.

[0070] A constituting material (e.g., a main material) of the high-k interface layer **250** is the same as described regarding the constituting material of the high-k interface layer **150** with reference to FIGS. 2B, 3, 4, 5A, and 5B.

[0071] In some embodiments, the integrated circuit device **200** may further include an upper conductive interface layer disposed between the dielectric film **160** and the upper electrode UE. The upper conductive interface layer may include, but is not limited to, a TiO.sub.2 layer.

[0072] In an integrated circuit device according to the present disclosure, such as the integrated circuit devices **100** and **200** described with reference to FIGS. 1 to 8, the high-k interface layer **150** or **250** is arranged between each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, the insulating pattern **126P**, and the lower electrode LE and the dielectric film **160** covering these components. Thus, an undesired depletion layer may be prevented from being generated in a portion of the lower electrode LE, which is adjacent to the dielectric film **160**. In addition, the high-k interface layers **150** and **250** may each include a zirconium oxide layer having a relatively high value of band gap energy, and the zirconium oxide layer may contact the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**, thereby suppressing the occurrence of leakage current through a portion of the high-k interface layer **150** or **250**, which at least partially covers the lower insulating support pattern **142P**,

the upper insulating support pattern **144P**, and/or the insulating pattern **126P**. Therefore, the generation of a leakage current in each of the capacitors **CP1** and **CP2** may be suppressed, and a minimum value of capacitance (C_{min}) of each of the capacitors **CP1** and **CP2** and the total capacitance thereof may be increased, thereby increasing the reliability of each of the integrated circuit devices **100** and **200**.

[0073] FIGS. **9A** to **9I** are cross-sectional views that illustrate sequential processes of a method of manufacturing an integrated circuit device, according to embodiments of the inventive concept. In FIGS. **9A** to **9I**, the same reference numerals as in FIGS. **1** to **4** denote the same members, and here, repeated detailed descriptions thereof may be omitted for brevity.

[0074] Referring to FIG. **9A**, the lower structure **120** and the conductive region **124** connected to the active region **AC** through the lower structure **120** may be formed on the substrate **110**, in which the active region **AC** is defined by the device isolation film **212**. Next, the insulating film **126** may be formed to cover the lower structure **120** and the conductive region **124**.

[0075] The insulating film **126** may be used as an etch stop layer in a subsequent process. The insulating film **126** may include an insulating material having etch selectivity with respect to the lower structure **120**. In example embodiments, the insulating film **126** may include a silicon nitride (SiN) film, a silicon carbonitride (SiCN) film, a silicon boron nitride (SiBN) film, or a combination thereof.

[0076] Referring to FIG. **9B**, a mold structure **MST** may be formed on the insulating film **126**.

[0077] The mold structure **MST** may include a plurality of mold films and a plurality of support films. For example, the mold structure **MST** may include a first mold film **132**, a lower insulating support film **142**, a second mold film **134**, and an upper insulating support film **144**, which are sequentially stacked on the insulating film **126** (e.g., in the stated order). Each of the first mold film **132** and the second mold film **134** may include a material which has a relatively high etch rate in an etchant including ammonium fluoride (NH_4F), hydrofluoric acid (HF), and water and thus is removable by a lift-off process using the etchant. In example embodiments, the first mold film **132** and the second mold film **134** may each include an oxide film, a nitride film, or a combination thereof.

[0078] For example, the first mold film **132** may include a borophosphosilicate glass (BPSG) film. The BPSG film may include a first portion, in which a concentration of a boron (B) dopant may vary in a thickness direction of the BPSG film, and/or a second portion, in which a concentration of a phosphorus (P) dopant may vary in the thickness direction of the BPSG film. The second mold film **134** may include a multi-insulating film, in which a relatively thin silicon oxide film and a relatively thin silicon nitride film are alternately stacked one by one a plurality of times, and/or a silicon nitride film. However, a constituting material of each of the first mold film **132** and the second mold film **134** is not limited to the examples set forth above, and various modifications and changes may be made therein without departing from the spirit and scope of the inventive concept. In addition, a stacking order in the mold structure **MST** is not limited to the example shown in FIG. **9B**, and various modifications and changes may be made therein without departing from the spirit and scope of the inventive concept.

[0079] The lower insulating support film **142** and the upper insulating support film **144** may each include a silicon nitride (SiN) film, a silicon carbonitride (SiCN) film, a silicon boron nitride (SiBN) film, or a combination thereof. In example embodiments, the lower insulating support film **142** and the upper insulating support film **144** may include the same materials as each other. In some embodiments, the lower insulating support film **142** and the upper insulating support film **144** may include different materials from each other. In one example, the lower insulating support film **142** and the upper insulating support film **144** may each include a silicon carbonitride film. In another example, the lower insulating support film **142** may include a silicon carbonitride film, and the upper insulating support film **144** may include a boron-containing silicon nitride film. However, a constituting material of each of the lower insulating support film **142** and the upper insulating

support film **144** is not limited to the examples set forth above, and various modifications and changes may be made therein without departing from the spirit and scope of the inventive concept. [0080] Referring to FIG. **9C**, in a resulting product of FIG. **9B**, a mask pattern MP may be formed on the mold structure MST, followed by anisotropically etching the mold structure MST by using the mask pattern MP as an etch mask and using the insulating film **126** as an etch stop layer, thereby forming a mold structure pattern MSP, which defines a plurality of holes BH.

[0081] The mold structure pattern MSP may include a first mold pattern **132P**, the lower insulating support pattern **142P**, a second mold pattern **134P**, and the upper insulating support pattern **144P**. The mask pattern MP may include a nitride film, an oxide film, a polysilicon film, a photoresist film, or a combination thereof.

[0082] A process of forming the plurality of holes BH may further include wet-treating a resulting product obtained by anisotropically etching the mold structure MST shown in FIG. **9B**. During the processes of anisotropically etching the mold structure MST and wet-treating the resulting product thereof, the insulating film **126** may also be partially etched, thereby obtaining the insulating pattern **126P** having the plurality of openings **126H**, which expose the plurality of conductive regions **124**. In an example process of wet-treating the resulting product obtained by anisotropically etching the mold structure MST, an etchant including a diluted sulfuric acid peroxide (DSP) solution may be used, but the inventive concept is not limited thereto.

[0083] In the mold structure pattern MSP, the plurality of holes **142H**, which are portions of the plurality of holes BH, may be formed in the lower insulating support pattern **142P**, and the plurality of holes **144H**, which are portions of the plurality of holes BH, may be formed in the upper insulating support pattern **144P**.

[0084] Referring to FIG. **9D**, the mask pattern MP may be removed from a resulting product of FIG. **9C**, and the plurality of lower electrodes LE may be formed to respectively fill the plurality of holes BH.

[0085] In example embodiments, to form the plurality of lower electrodes LE, a conductive layer may be formed in the resulting product of FIG. **9C** to cover the top surface of the upper insulating support pattern **144P** and to fill the plurality of holes BH. To form the conductive layer, an ALD process may be used. Next, the conductive layer may be partially removed by using an etchback process or a chemical mechanical polishing (CMP) process, thereby exposing the top surface of the upper insulating support pattern **144P**.

[0086] The surface roughness of exposed surfaces of the plurality of lower electrodes LE formed by an ALD process may be less than the surface roughness of respective exposed surfaces of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**, which are formed by CVD processes.

[0087] Referring to FIG. **9E**, the plurality of upper holes UH may be formed by partially removing the upper insulating support pattern **144P** from a resulting product of FIG. **9D**. Then, the second mold pattern **134P** may be removed in a wet manner through the plurality of upper holes UH. Next, the plurality of lower holes LH may be formed by partially removing the lower insulating support pattern **142P** exposed by the plurality of upper holes UH. Then, the top surface of the insulating pattern **126P** may be exposed by removing the first mold pattern **132P** in a wet manner through the plurality of lower holes LH. After the first mold pattern **132P** and the second mold pattern **134P** are removed, sidewalls of the plurality of lower electrodes LE may be exposed.

[0088] A planar shape of each of the plurality of upper holes UH and the plurality of lower holes LH may vary across embodiments. For example, the planar shape of each of the plurality of upper holes UH may be the same as the example shown in FIG. **2A**, but the inventive concept is not limited thereto. For example, the planar shape of each of the plurality of upper holes UH may be a polygonal shape, a curved shape, an irregular shape, or the like.

[0089] In example embodiments, to remove the second mold pattern **134P** and the first mold pattern **132P** in a wet manner, an etchant including ammonium fluoride (NH₄F), hydrofluoric

acid (HF), and water may be used, but the inventive concept is not limited thereto.

[0090] Referring to FIG. 9F, a first interface layer **150P1** may be formed to cover exposed surfaces of a resulting product of FIG. 9E.

[0091] The first interface layer **150P1** may include a material having a relatively broad band gap energy of about 5 eV or more. In example embodiments, the first interface layer **150P1** may include a zirconium oxide layer. For example, the high-k interface layer **150** may include ZrO₂.

[0092] The first interface layer **150P1** may conformally cover respective surfaces of the plurality of lower electrodes LE, the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**. The first interface layer **150P1** may contact the lower electrode LE, the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**.

[0093] The surface roughness of an exposed surface of each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**, which are formed by CVD processes, may be greater than the surface roughness of exposed surfaces of the plurality of lower electrodes LE formed by an ALD process. Further, a density of each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**, which are formed by the CVD processes, may be lower than a density of the plurality of lower electrodes LE formed by the ALD process. Accordingly, portions of the first interface layer **150P1**, which are formed on the exposed surfaces of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**, may include portions which permeate into the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P** through spaces between grain boundaries of insulating grains of the first interface layer **150P1**. The permeating portions of the first interface layer **150P1** form a relatively less dense structure in each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**. As a result, the thickness of the portions of the first interface layer **150P1**, which are formed on the insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P**, may be greater than the thickness of portions of the first interface layer **150P1**, which are formed on the plurality of lower electrodes LE.

[0094] To form the first interface layer **150P1**, an ALD process may be used. In example embodiments, an ALD process for forming the first interface layer **150P1** includes an ALD cycle that may be repeated a plurality of times. The ALD cycle includes a process of supplying a Zr precursor, which includes a central atom including zirconium (Zr) and at least one ligand bonded to the central atom, onto the substrate **110**, a process of removing unnecessary by-products on the substrate **110** and a physisorbed layer of the Zr precursor remaining on the substrate **110** by supplying a purge gas onto the substrate **110**, a process of supplying an oxidizing gas onto the substrate **110**, and a process of removing unnecessary by-products on the substrate **110** and the residue of the oxidizing gas by supplying the purge gas onto the substrate **110**.

[0095] The ligand included in the Zr precursor may include, but is not limited to, a C5 to C12 cyclopentadienyl group, a C1 to C10 saturated or unsaturated hydrocarbon group, a C1 to C10 organic amine group, a C5 to C20 B-diketonato group, a C5 to C20 β-ketoiminato group, a C5 to C20 β-diiminato group, or a halogen element. For example, the Zr precursor may include, but is not limited to, tetrakis(ethylmethylamino)zirconium (TEMAZ), tris(dimethylamino)cyclopentadienyl zirconium, (C₅H₅)₃Zr [N(CH₃)₂]₃, Zr(i-OPr)₄, Zr(TMHD)(i-OPr)₃, Zr(TMHD)₂(i-OPr)₂, Zr(TMHD)₄, Zr(DMAE)₄, Zr(METHD)₄, or a derivative thereof. (Here, i-OPr=isopropoxide; TMHD=2,2,6,6-tetramethyl-3,5-heptanedionate; DMAE=dimethylaminoethoxide; and METHD=methoxyethoxytetramethylheptanedionate).

[0096] An inert gas such as Ar, He, or Ne, N₂ gas, or the like may be used as the purge gas.

The oxidizing gas may be selected from among O.sub.2, O.sub.3, H.sub.2O, NO.sub.2, NO, N.sub.2O (nitrous oxide), CO, CO.sub.2, H.sub.2O.sub.2, HCOOH, CH.sub.3COOH, (CH.sub.3CO).sub.2O, alcohol, peroxide, sulfur oxide, plasma O.sub.2, remote plasma O.sub.2, plasma N.sub.2O, plasma H.sub.2O, and/or a combination thereof.

[0097] When the ALD process for forming the first interface layer **150P1** is performed, a process temperature may be maintained at about 100° C. to about 600° C., and a process pressure may be maintained at about 10 Pa to atmospheric pressure. In example embodiments, to form the first interface layer **150P1**, one Zr precursor or a combination of at least two Zr precursors may be supplied onto the substrate **110**. In some embodiments, to form the first interface layer **150P1**, a precursor including a metallic element other than Zr, for example, a Ti precursor, may be supplied onto the substrate **110** along with a Zr precursor.

[0098] In some embodiments, to obtain a structure in which the thicknesses of the portions of the first interface layer **150P1** formed on the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P** are greater than the thicknesses of the portions of the first interface layer **150P1** respectively formed on the plurality of lower electrodes LE, an area selective deposition (ASD) process may be used. The ASD process may be a process in which an ALD process is performed under a process condition where a deposition rate is higher on the exposed surface of each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, and the insulating pattern **126P** than on the exposed surfaces of the plurality of lower electrodes LE from among the exposed surfaces of a resulting product of FIG. **9E**, may be used.

[0099] In example embodiments, the first interface layer **150P1** may have, but is not limited to, a thickness that is between about 0 nm and about 2 nm, for example, a thickness that is between about 0 nm and about 1 nm.

[0100] Referring to FIG. **9G**, in a resulting product of FIG. **9F**, a second interface layer **150P2** may be formed to cover exposed surfaces of the first interface layer **150P1**. While the second interface layer **150P2** is formed, the first interface layer **150P1** of FIG. **9F** may be changed into a doped interface layer **150P**.

[0101] The second interface layer **150P2** may include a metal oxide film including at least one metallic element. The at least one metallic element may be a metallic element that is different from Zr. In example embodiments, the second interface layer **150P2** may include a single TiO.sub.2 layer, a single Nb.sub.2O.sub.5 layer, or a multilayer including a combination thereof.

[0102] To form the second interface layer **150P2**, an ALD process may be used. When the ALD process for forming the second interface layer **150P2** is performed, a process temperature may be maintained at about 100° C. to about 600° C., and a process pressure may be maintained at about 10 Pa to atmospheric pressure.

[0103] When the second interface layer **150P2** includes a TiO.sub.2 layer, an ALD process using a Ti precursor may be performed to form the TiO.sub.2 layer. The Ti precursor may include, but is not limited to, titanium tetrachloride (TiCl.sub.4), titanium tetrafluoride (TiF.sub.4), titanium tetrakis(isopropoxide), cyclopentadienyl titanium, titanium bis(isopropoxide)bis(2,2,6,6-tetramethyl-3,5-heptanedionate), tetrakisdimethylaminotitanium, tetrakis(diethylamino)titanium, trimethoxy(pentamethylcyclopentadienyl)titanium, or a derivative thereof.

[0104] When the second interface layer **150P2** includes an Nb.sub.2O.sub.5 layer, an ALD process using an Nb precursor may be performed to form the Nb.sub.2O.sub.5 layer. The Nb precursor may include, but is not limited to, niobium pentachloride (NbCl.sub.5), niobium pentafluoride (NbF.sub.5), pentakisdimethylaminoniobium (PDMAN, Nb(N(CH.sub.3).sub.2).sub.5), pentakisdialkylaminoniobium (PDEAN), pentakis(methylethylamido) niobium (PMEAN), tert-butyliminotris (dimethylamino) niobium (TBTDMN), tert-butyliminotris(diethylamino)niobium (TBTDEN), tert-butyliminotris(methylethylamino)niobium (TBTMEN), ethylimido-tris tris(dimethylamido)niobium, ethylimido-tris (diethylamido) niobium, ethylimido-

tris(ethylmethyramid)niobium, tert-amylimido-tris(dimethylamido)niobium (NBIMANB), tert-amylimido-tris(diethylamido)niobium (NBIEANB), tert-amylimido-tris(ethylmethyramid)niobium (NBIMANB), or a derivative thereof.

[0105] While the second interface layer **150P2** is formed, metallic elements constituting the second interface layer **150P2** may diffuse into the first interface layer **150P1**, or Zr constituting the first interface layer **150P1** may be intermixed with the metallic elements constituting the second interface layer **150P2**. As a result, the first interface layer **150P1** shown in FIG. **9F** may be changed into the doped interface layer **150P** while the second interface layer **150P2** is formed. In example embodiments, the doped interface layer **150P** may include, but is not limited to, a zirconium oxide layer doped with Ti, a zirconium oxide layer doped with Nb, a zirconium oxide layer doped with Ti and Nb, or a combination thereof.

[0106] In some embodiments, after the second interface layer **150P2** is formed in the process of FIG. **9G**, the first interface layer **150P1** of FIG. **9F** may remain as the first interface layer **150P1** including an undoped zirconium oxide layer instead of being changed into the doped interface layer **150P**.

[0107] Referring to FIG. **9H**, the second interface layer **150P2** may be removed from a resulting product of FIG. **9G**, and a portion of the doped interface layer **150P** may be removed, thereby forming the high-k interface layer **150**, which includes the remaining portion of the doped interface layer **150P**.

[0108] In example embodiments, a process of removing the second interface layer **150P2** and a process of removing the portion of the doped interface layer **150P** may be performed by a wet process using a hydrofluoric acid (HF) solution. In this case, the high-k interface layer **150**, which includes a plurality of interface clusters having a plurality of island shapes apart from each other as shown in FIG. **9H**, may be obtained along with a reduction in the thickness of the doped interface layer **150P**, which remains on a resulting product obtained after the portion of the doped interface layer **150P** is removed.

[0109] In some embodiments, the process of forming the second interface layer **150P2**, which is described with reference to FIG. **9G**, may be omitted. In this case, in the process described with reference to FIG. **9H**, the high-k interface layer **150** may be formed by performing a process of removing a portion of the first interface layer **150P1** formed in the process of FIG. **9F**, without the need to perform a process of removing the second interface layer **150P2**.

[0110] Referring to FIG. **9I**, the dielectric film **160** may be formed on a resulting product of FIG. **9H**, in which the high-k interface layer **150** is formed.

[0111] To form the dielectric film **160**, an ALD process may be used. The dielectric film **160** may include, but is not limited to, HfO_2 , ZrO_2 , Al_2O_3 , La_2O_3 , Ta_2O_5 , Nb_2O_5 , CeO_2 , TiO_2 , GeO_2 , or a combination thereof.

[0112] Next, in a resulting product of FIG. **9I**, the upper electrode UE may be formed to cover the dielectric film **160**, thereby manufacturing the integrated circuit device **100**, which includes the capacitor CP1 shown in FIG. **2B**. In example embodiments, to form the upper electrode UE, a CVD, metal organic CVD (MOCVD), physical vapor deposition (PVD), or ALD process may be used.

[0113] FIG. **10** is a cross-sectional view that illustrates a method of manufacturing an integrated circuit device, according to other embodiments of the inventive concept. In FIG. **10**, the same reference numerals as in FIGS. **1** to **9I** denote the same members, and here, repeated detailed descriptions thereof are omitted for brevity.

[0114] Referring to FIG. **10**, the method described with reference to FIGS. **9A** to **9G**, up to the process of forming the second interface layer **150P2**, which at least partially covers the exposed surfaces of the first interface layer **150P1**, may be performed. The first interface layer **150P1** formed in the process of FIG. **9F** may be changed into the doped interface layer **150P** while the second interface layer **150P2** is formed.

[0115] Next, the second interface layer **150P2** may be removed from the resulting product of FIG. **9G** by a method similar to that described with reference to FIG. **9H**, thereby forming the high-k interface layer **250**, which includes at least a portion of the doped interface layer **150P**.

[0116] To form the high-k interface layer **250**, the second interface layer **150P2** may be removed as described with reference to FIG. **9H** to expose the doped interface layer **150P**. Then, the doped interface layer **150P** may be scarcely removed, or may be removed only by as much as a relatively small thickness. As a result, the remaining doped interface layer **150P** may constitute the high-k interface layer **250**.

[0117] The first interface portion **250A** of the high-k interface layer **250** may continuously extend on the surface of each of the lower insulating support pattern **142P** and the upper insulating support pattern **144P**. The second interface portion **250B** of the high-k interface layer **250** may continuously extend on the surface of the lower electrode LE without interruption. The third interface portion **250C** of the high-k interface layer **250** may continuously extend on the surface of the insulating pattern **126P** without interruption. The first interface portion **250A**, the second interface portion **250B**, and the third interface portion **250C** of the high-k interface layer **250** may be integrally connected to each other.

[0118] Next, the dielectric film **160** may be formed by the method described with reference to FIG. **9I**, and the upper electrode UE may be formed to cover the dielectric film **160**, thereby manufacturing the integrated circuit device **200**, which includes the capacitor CP2 shown in FIG. **6**.

[0119] To form the high-k interface layer **150** or **250** between each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, the insulating pattern **126P**, and the lower electrode LE and the dielectric film **160** covering these components, the first interface layer **150P1** including a zirconium oxide layer, which contacts the exposed surface of each of the lower insulating support pattern **142P**, the upper insulating support pattern **144P**, the insulating pattern **126P**, and the lower electrode LE, is formed according to the methods of manufacturing the integrated circuit devices **100** and **200** as described with reference to FIGS. **9A** to **9I** and **10**. Next, the second interface layer **150P2** may be formed to cover the exposed surfaces of the first interface layer **150P1** as described with reference to FIG. **9G**, and the high-k interface layer **150** or **250** may be formed from the first interface layer **150P1** or the doped interface layer **150P** obtained from the first interface layer **150P1**. The first interface layer **150P1** may include a zirconium oxide layer having a relatively high band gap energy.

[0120] Accordingly, the generation of a leakage current through a portion of the high-k interface layer **150** or **250**, which covers the lower insulating support pattern **142P** and/or the upper insulating support pattern **144P**, may be suppressed. For example, the high-k interface layer **150** or **250** may be obtained from the first interface layer **150P1** as described in the above processes with reference to FIGS. **9A-9I** and FIG. **10**. In addition, the high-k interface layer **150** or **250** may be arranged between the lower electrode LE and the dielectric film **160**, thereby preventing an undesired depletion layer from being generated in a portion of the lower electrode LE, which is adjacent to the dielectric film **160**. Therefore, the generation of a leakage current in the capacitor CP1 or CP2 may be suppressed, the minimum value of capacitance (Cmin) of the capacitor CP1 or CP2 and the total capacitance thereof may be increased, and the mass-productivity and reliability of the integrated circuit device **100** or **200** may be increased.

[0121] While the inventive concept has been particularly shown and described with reference to embodiments thereof, it will be understood that various changes in form and details may be made therein without departing from the spirit and scope of the following claims.

Claims

1. An integrated circuit device comprising: a substrate comprising an active region; a word line on the active region, the word line extending in a first horizontal direction across the active region; a

bit line over the word line, the bit line extending in a second horizontal direction perpendicular to the first horizontal direction; a buried contact on the active region; a conductive landing pad on the buried contact; a lower electrode on the conductive landing pad; an insulating support pattern supporting the lower electrode; a dielectric film surrounding the lower electrode and the insulating support pattern; a high-k interface layer, wherein the high-k interface layer is arranged between the lower electrode and the dielectric film and between the insulating support pattern and the dielectric film, and wherein the high-k interface layer comprises a zirconium oxide layer contacting the insulating support pattern; and an upper electrode disposed adjacent to the lower electrode, wherein the high-k interface layer and the dielectric film are disposed between the upper electrode and the lower electrode.

2. The integrated circuit device of claim 1, wherein the high-k interface layer contacts both the lower electrode and the insulating support pattern.

3. The integrated circuit device of claim 1, wherein the high-k interface layer comprises a first interface portion disposed between the insulating support pattern and the dielectric film, and further comprises a second interface portion disposed between the lower electrode and the dielectric film, wherein both the first interface portion and the second interface portion each comprise a plurality of interface clusters having a plurality of island shapes spaced apart from each other, and wherein the dielectric film contacts the insulating support pattern through spaces between each of the plurality of interface clusters of the first interface portion, and further contacts the lower electrode through spaces between each of the plurality of interface clusters of the second interface portion.

4. The integrated circuit device of claim 1, wherein the high-k interface layer comprises: a first interface portion continuously extending between the insulating support pattern and the dielectric film such that the insulating support pattern and the dielectric film do not contact each other; and a second interface portion continuously extending between the lower electrode and the dielectric film such that the lower electrode and the dielectric film do not contact each other, and wherein a thickness of the first interface portion is different from a thickness of the second interface portion.

5. The integrated circuit device of claim 1, wherein the high-k interface layer comprises a first interface portion disposed between the insulating support pattern and the dielectric film and a second interface portion disposed between the lower electrode and the dielectric film, and wherein a thickness of the first interface portion is greater than a thickness of the second interface portion.

6. The integrated circuit device of claim 1, wherein the high-k interface layer further comprises at least one dopant element comprising a metallic element that is different from zirconium, and wherein the at least one dopant element comprises a typical metal, a transition metal, or a post-transition metal.

7. The integrated circuit device of claim 1, wherein the high-k interface layer further comprises a dopant element, wherein the dopant element is one of aluminum (Al), niobium (Nb), molybdenum (Mo), ruthenium (Ru), indium (In), tin (Sn), antimony (Sb), scandium (Sc), titanium (Ti), vanadium (V), manganese (Mn), iron (Fe), cobalt (Co), nickel (Ni), arsenic (As), tantalum (Ta), tungsten (W), iridium (Ir), yttrium (Y), or bismuth (Bi).

8. The integrated circuit device of claim 1, further comprising: an insulating pattern on the conductive landing pad, the insulating pattern being adjacent to a lower end of the lower electrode, wherein the high-k interface layer comprises a first interface portion disposed between the insulating support pattern and the dielectric film, a second interface portion disposed between the lower electrode and the dielectric film, and a third interface portion disposed between the insulating pattern and the dielectric film, and wherein a thickness of each of the first interface portion and the third interface portion is greater than a thickness of the second interface portion.

9. An integrated circuit device comprising: a substrate comprising an active region; a word line on the active region, the word line extending in a first horizontal direction across the active region; a bit line over the word line, the bit line extending in a second horizontal direction perpendicular to the first horizontal direction; a conductive region disposed on the active region and connected to

the active region, the conductive region including a buried contact the active region and a conductive landing pad on the buried contact; a capacitor disposed on the conductive region; and an insulating support pattern supporting a portion of the capacitor, wherein the capacitor comprises: a lower electrode comprising a first portion contacting the insulating support pattern and a second portion contacting the conductive landing pad of the conductive region; a dielectric film at least partially surrounding each of the lower electrode and the insulating support pattern; a high-k interface layer arranged between the lower electrode and the dielectric film and between the insulating support pattern and the dielectric film, the high-k interface layer comprising a zirconium oxide layer contacting the insulating support pattern; and an upper electrode disposed adjacent to the lower electrode, wherein the high-k interface layer and the dielectric film are disposed between the upper electrode and the lower electrode.

10. The integrated circuit device of claim 9, wherein the high-k interface layer further comprises at least one dopant element comprising a typical metal, a transition metal, or a post-transition metal.

11. The integrated circuit device of claim 9, wherein the high-k interface layer comprises a first interface portion and a second interface portion, wherein the first interface portion is arranged between the insulating support pattern and the dielectric film and contacts the insulating support pattern, and wherein the second interface portion is arranged between the lower electrode and the dielectric film and contacts the lower electrode, wherein each of the first interface portion and the second interface portion comprises a plurality of interface clusters having a plurality of island shapes apart from each other, and wherein the dielectric film contacts the insulating support pattern through spaces between each of the plurality of interface clusters of the first interface portion, and further contacts the lower electrode through spaces between each of the plurality of interface clusters of the second interface portion.

12. The integrated circuit device of claim 9, wherein the high-k interface layer comprises: a first interface portion continuously extending between the insulating support pattern and the dielectric film such that the insulating support pattern and the dielectric film do not contact each other; and a second interface portion continuously extending between the lower electrode and the dielectric film such that the lower electrode and the dielectric film do not contact each other, and wherein a thickness of the first interface portion is greater than a thickness of the second interface portion.

13. The integrated circuit device of claim 9, wherein the insulating support pattern comprises a silicon nitride (SiN) film, a silicon carbonitride (SiCN) film, a silicon boron nitride (SiBN) film, or a combination thereof.

14. The integrated circuit device of claim 9, wherein the lower electrode comprises a first metallic element, wherein the dielectric film comprises a second metallic element that is different from the first metallic element, and wherein the high-k interface layer further comprises a dopant element comprising a metallic element that is the same as the first metallic element or the second metallic element.

15. The integrated circuit device of claim 9, wherein the lower electrode comprises a first metallic element, wherein the dielectric film comprises a second metallic element that is different from the first metallic element, and wherein the high-k interface layer further comprises at least one dopant element comprising a metallic element that is different from the first metallic element and the second metallic element.

16. The integrated circuit device of claim 9, wherein the high-k interface layer further comprises a dopant element, wherein the dopant element is aluminum (Al), niobium (Nb), molybdenum (Mo), ruthenium (Ru), indium (In), tin (Sn), antimony (Sb), scandium (Sc), titanium (Ti), vanadium (V), manganese (Mn), iron (Fe), cobalt (Co), nickel (Ni), arsenic (As), tantalum (Ta), tungsten (W), iridium (Ir), yttrium (Y), or bismuth (Bi).

17. An integrated circuit device comprising: a substrate comprising a plurality of active regions; a plurality of word lines on the plurality of active regions, the plurality of word lines extending parallel to each other in a first horizontal direction across the plurality of active regions; a plurality

of direct contacts; a plurality of bit lines arranged over the plurality of word lines, the plurality of bit lines extending in a second horizontal direction perpendicular to the first horizontal direction, each of the plurality of bit lines being connected to at least one active region from among the plurality of active regions via one of the plurality of direct contacts; a plurality of conductive regions disposed on the plurality of active regions, wherein each of the plurality of conductive regions includes a buried contact between two adjacent bit lines from among the plurality of bit lines, and a conductive landing pad on the buried contact, and wherein the conductive landing pad at least partially overlap the buried contact; an insulating pattern disposed on the plurality of conductive regions, the insulating pattern comprising a plurality of openings that vertically overlap the plurality of conductive regions; a plurality of lower electrodes penetrating the insulating pattern through the plurality of openings and respectively connected to the plurality of conductive regions, wherein each of the plurality of lower electrodes comprises a first metal; an insulating support pattern disposed apart from the insulating pattern in a vertical direction, the insulating support pattern contacting a portion of each of the plurality of lower electrodes to support the plurality of lower electrodes; a dielectric film surrounding the plurality of lower electrodes, the insulating pattern, and the insulating support pattern; a high-k interface layer arranged between the plurality of lower electrodes and the dielectric film, between the insulating support pattern and the dielectric film, and between the insulating pattern and the dielectric film, wherein the high-k interface layer comprises a zirconium oxide layer contacting the insulating support pattern; and an upper electrode disposed adjacent to each of the plurality of lower electrodes, wherein the high-k interface layer and the dielectric film are disposed between the upper electrode and each of the plurality of lower electrodes, and wherein the upper electrode comprises a second metal.

18. The integrated circuit device of claim 17, wherein the high-k interface layer comprises a plurality of interface clusters having a plurality of island shapes spaced apart from each other, and wherein the dielectric film contacts the insulating support pattern, the plurality of lower electrodes, and the insulating pattern through spaces between each of the plurality of interface clusters.

19. The integrated circuit device of claim 17, wherein the high-k interface layer comprises a first interface portion disposed between the insulating support pattern and the dielectric film, a second interface portion disposed between the plurality of lower electrodes and the dielectric film, and a third interface portion contacting the insulating pattern, and wherein a thickness of each of the first interface portion and the third interface portion is greater than a thickness of the second interface portion.

20. The integrated circuit device of claim 17, wherein each of the plurality of lower electrodes and the upper electrode comprises at least one of TiN, NbN, CON, SnO.sub.2, or a combination thereof, wherein the dielectric film comprises a metal oxide comprising at least one metal selected from among hafnium (Hf), zirconium (Zr), aluminum (Al), niobium (Nb), cerium (Ce), lanthanum (La), tantalum (Ta), or titanium (Ti), and wherein the high-k interface layer comprises a zirconium oxide layer further comprising a dopant element, wherein the dopant element is at least one of aluminum (Al), niobium (Nb), molybdenum (Mo), ruthenium (Ru), indium (In), tin (Sn), antimony (Sb), scandium (Sc), titanium (Ti), vanadium (V), manganese (Mn), iron (Fe), cobalt (Co), nickel (Ni), arsenic (As), tantalum (Ta), tungsten (W), iridium (Ir), yttrium (Y), or bismuth (Bi).
