

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250287737

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

KAGEYAMA; Hiroaki

LIGHT-EMITTING ELEMENT AND LIGHT-EMITTING DEVICE

Abstract

A light-emitting element includes: a semiconductor layered body including first and second semiconductor layers, the first semiconductor layer having a plurality of exposed portions exposed from the second semiconductor layer at locations inward of an outer periphery of the second semiconductor layer; an insulating film covering the semiconductor layered body and defining a first opening above the exposed portions and second openings above a part of the second semiconductor layer; first and second electrodes electrically connected to the first and second semiconductor layer through the first and second openings, respectively; first bumps and second bumps disposed on the first and second electrodes, respectively. The first electrode and the second electrode have a first surface and a second surface, respectively, that are located at the same height from the second semiconductor layer. The first and second bumps are respectively connected to the first and second surfaces.

Inventors: KAGEYAMA; Hiroaki (Tokushima-shi, JP)

Applicant: NICHIA CORPORATION (Anan-shi, JP)

Family ID: 80823584

Appl. No.: 19/213999

Filed: May 20, 2025

Foreign Application Priority Data

JP 2020-165837

Sep. 30, 2020

Related U.S. Application Data

parent US continuation 17489392 20210929 parent-grant-document US 12336337 child US 19213999

Publication Classification

Int. Cl.: **H10H20/831** (20250101); **H10H20/825** (20250101); **H10H20/832** (20250101);
H10H20/84 (20250101); **H10H20/857** (20250101)

U.S. Cl.:

CPC **H10H20/8312** (20250101); **H10H20/84** (20250101); **H10H20/857** (20250101);
H10H20/825 (20250101); H10H20/835 (20250101)

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS [0001] This application is a continuation application of U.S. patent application Ser. No. 17/489,392, filed on Sep. 29, 2021. This application claims priority to Japanese Patent Application No. 2020-165837, filed on Sep. 30, 2020. The entire disclosures of U.S. patent application Ser. No. 17/489,392 and Japanese Patent Application No. 2020-165837 are hereby incorporated herein by reference.

BACKGROUND

[0002] The present disclosure relates to a light-emitting element and a light-emitting device.

[0003] A light-emitting device is known in which light-emitting elements are flip-chip mounted with adjustment in heights of bumps (for example, Japanese Unexamined Patent Application Publication No. 2012-49296, Japanese Unexamined Patent Application Publication No. 2015-60964, and Japanese Unexamined Patent Application Publication No. 2014-36080).

SUMMARY

[0004] An object of certain embodiments of the present disclosure is to provide a light-emitting element with good mountability when flip-chip mounted and a light-emitting device employing the light-emitting element.

[0005] An embodiment of the present disclosure includes: [0006] (1) A light-emitting element includes a semiconductor layered body, an insulating film, a first electrode, a second electrode, a plurality of first bumps, and a plurality of second bumps. The semiconductor layered body includes a first semiconductor layer, a second semiconductor layer, and an active layer between the first semiconductor layer and the second semiconductor layer. The first semiconductor layer has a plurality of exposed portions exposed from the second semiconductor layer and the active layer at locations inward of an outer periphery of the second semiconductor layer in a plan view from a side of the second semiconductor layer. The insulating film covers the semiconductor layered body and defines at least one first opening above one of the exposed portions and a plurality of second openings above a part of the second semiconductor layer. The first electrode is electrically connected to the first semiconductor layer through the first opening and partially located above the second semiconductor layer via the insulating film. The second electrode is electrically connected to the second semiconductor layer through the second openings and partially located above the second semiconductor layer via the insulating film. The first bumps are arranged above the first electrode. The second bumps are arranged above the second electrode. The second bumps are aligned along a first direction. The first electrode has a first surface and the second electrode has a second surface above the insulating film disposed above the second semiconductor layer. The first surface and the second surface are located at a same height from the second semiconductor layer. The first bumps are electrically connected to the first surface, and the second bumps are electrically connected to the second surface. In the plan view, the second electrode has an elongated shape that is longer in the first direction than in a second direction perpendicular to the first direction. In the

plan view, the second openings are arranged along outer edges of the second electrode extending in the first direction, with at least two of the second openings being aligned in the second direction and at least one of the second bumps being arranged between the at least two of the second openings. [0007] (2) A light-emitting device includes a substrate and a light-emitting element. The substrate has an upper surface and includes a first wiring and a second wiring that are disposed on the upper surface. The light-emitting element includes a semiconductor layered body, an insulating film, a first electrode, and a second electrode. The semiconductor layered body includes a first semiconductor layer, a second semiconductor layer, and an active layer between the first semiconductor layer and the second semiconductor layer. The first semiconductor layer has a plurality of exposed portions exposed from the second semiconductor layer and the active layer at locations inward of an outer periphery of the second semiconductor layer in a plan view from a side of the second semiconductor layer. The insulating film covers the semiconductor layered body and defines a plurality of first openings respectively over the exposed portions and a plurality of second openings over a part of the second semiconductor layer. The first electrode is electrically connected to the first semiconductor layer through the first openings and partially disposed above the second semiconductor layer via the insulating film. The second electrode is electrically connected to the second semiconductor layer through the second openings and partially disposed above the second semiconductor layer via the insulating film. The first electrode has a first surface and the second electrode has a second surface above the insulating film disposed above the second semiconductor layer. The first surface and the second surface are located at a same height from the second semiconductor layer. The light-emitting element is flip-chip mounted on the substrate via a plurality of first bumps electrically connecting the first surface of the first electrode and the first wiring of the substrate, and a plurality of second bumps electrically connecting the second surface of the second electrode and the second wiring of the substrate, the second bumps being aligned along a first direction. In the plan view, the second electrode has an elongated shape that is longer in the first direction than in a second direction perpendicular to the first direction. In the plan view, the second openings are arranged along outer edges of the second electrode extending in the first direction, with at least two of the second openings being aligned in the second direction and at least one of the second bumps being arranged between the at least two of the second openings. [0008] According to certain embodiments of the present disclosure, a light-emitting element with good mountability for flip-chip mounting and a light-emitting device can be obtained.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] FIG. 1A is a schematic plan view of an embodiment of a light-emitting element of the present disclosure.

[0010] FIG. 1B is a schematic cross-sectional view taken along line I-I' of FIG. 1A.

[0011] FIG. 1C is a schematic plan view for illustrating the shape of an insulating film of the light-emitting element in FIG. 1A.

[0012] FIG. 1D is a schematic plan view for illustrating the shapes of a first electrode and a second electrode of the light-emitting element in FIG. 1A.

[0013] FIG. 1E is a schematic plan view for illustrating the shape of a light-reflective electrode of the light-emitting element in FIG. 1A.

[0014] FIG. 1F is an enlarged schematic plan view of a main part for illustrating positional relationships between a first opening, an exposed portion, and a hole defined by the light-reflective electrode of the light-emitting element in FIG. 1A.

[0015] FIG. 2A is a schematic plan view of another embodiment of the light-emitting element of the present disclosure.

[0016] FIG. 2B is a schematic plan view for illustrating the shape of an insulating film of the light-emitting element in FIG. 2A.

[0017] FIG. 2C is a schematic plan view for illustrating the shape of a light-reflective electrode of the light-emitting element in FIG. 2A.

[0018] FIG. 3A is a schematic plan view of still another embodiment of the light-emitting element of the present disclosure.

[0019] FIG. 3B is a schematic plan view for illustrating the shape of an insulating film of the light-emitting element in FIG. 3A.

[0020] FIG. 3C is a schematic plan view for illustrating the shapes of a first electrode and a second electrode of the light-emitting element in FIG. 3A.

[0021] FIG. 3D is a schematic plan view for illustrating the shape of a light-reflective electrode of the light-emitting element in FIG. 3A.

[0022] FIG. 4A is a schematic plan view of still another embodiment of the light-emitting element of the present disclosure.

[0023] FIG. 4B is a schematic plan view for illustrating the shape of an insulating film of the light-emitting element in FIG. 4A.

[0024] FIG. 4C is a schematic plan view for illustrating the shapes of a first electrode and a second electrode of the light-emitting element in FIG. 4A.

[0025] FIG. 4D is a schematic plan view for illustrating the shape of a light-reflective electrode of the light-emitting element in FIG. 4A.

[0026] FIG. 5A is a schematic plan view of still another embodiment of the light-emitting element of the present disclosure.

[0027] FIG. 5B is a schematic plan view for illustrating the shape of an insulating film of the light-emitting element in FIG. 5A.

[0028] FIG. 5C is a schematic plan view for illustrating the shapes of a first electrode and a second electrode of the light-emitting element in FIG. 5A.

[0029] FIG. 5D is a schematic plan view for illustrating the shape of a light-reflective electrode of the light-emitting element in FIG. 5A.

[0030] FIG. 6A is a schematic plan view of still another embodiment of the light-emitting element of the present disclosure.

[0031] FIG. 6B is a schematic plan view for illustrating the shape of an insulating film of the light-emitting element in FIG. 6A.

[0032] FIG. 6C is a schematic plan view for illustrating the shapes of a first electrode and a second electrode of the light-emitting element in FIG. 6A.

[0033] FIG. 7A is a schematic perspective view of an embodiment of a light-emitting device of the present disclosure.

[0034] FIG. 7B is a schematic end view taken along line II-II' of FIG. 7A.

DETAILED DESCRIPTION OF EMBODIMENTS

[0035] Certain embodiments of the present disclosure will be described with reference to the accompanying drawings. The embodiments described below are intended to describe examples to give a concrete form to the technical idea of the present invention and are not intended to limit the present invention to the description below. Sizes or positional relationships of members illustrated in each drawing may be exaggerated in order to clarify the descriptions. The cross-sectional views may be cross-sectional end views showing only cross sections of members. Further, the same term or the same reference numeral generally represents the same member or members made of the same material, and its repetitive descriptions will be omitted as appropriate. A member in an embodiment designated as the same name as in another embodiment indicates the same or corresponding member. A material, size, and the like of such a member may be the same as such another embodiment unless otherwise described. The terms “part” in the present specification may refer to a portion of a single member or one or more members among a plurality of members, and

the terms “all” and “whole” may refer to the whole of a single member or all of a plurality of members. Terms such as “up/upper” and “down/lower” in the present specification are not intended to represent absolute positions unless otherwise specified but represent relative positions between components in drawings referred to for the purpose of illustration. The term “cover” in the embodiments includes not only covering in direct contact but also includes indirect covering, such as covering via another member therebetween.

Light-Emitting Element

[0036] A light-emitting element **10** in the present embodiment includes a supporting substrate **27**, a semiconductor layered body **23**, an insulating film **14**, a first electrode **11**, a second electrode **12**, first bumps **31**, and second bumps **32** as shown in FIGS. **1A** and **1B**.

[0037] The semiconductor layered body **23** includes a first semiconductor layer **21**, a second semiconductor layer **22**, and an active layer **24** between the first semiconductor layer **21** and the second semiconductor layer **22**, the first semiconductor layer **21** having a plurality of exposed portions **21a** exposed from the second semiconductor layer **22** and the active layer **24** (i.e., the exposed portions are not covered by the active layer **24** or the second semiconductor layer **22**), the plurality of exposed portions **21a** located inward of an outer periphery of the second semiconductor layer **22**.

[0038] The insulating film **14** covers an upper surface (that is, a surface on the second semiconductor layer **22** side) of the semiconductor layered body **23** and defines first openings **14a** above the exposed portions **21a** and second openings **14b** above a portion of the second semiconductor layer **22**.

[0039] The first electrode **11** is electrically connected to the first semiconductor layer **21** through the first openings **14a** and partially located on the second semiconductor layer **22** via the insulating film **14**. The second electrode **12** is electrically connected to the second semiconductor layer **22** through the second openings **14b** and partially located on the second semiconductor layer **22** via the insulating film **14**. The first electrode **11** and the second electrode **12** have a first surface **11a** and a second surface **12a**, respectively, above the insulating film **14** above the second semiconductor layer **22**, the first surface **11a** and the second surface **12a** located at the same height from the second semiconductor layer **22**.

[0040] A plurality of first bumps **31** are disposed on the first electrode **11**. A plurality of second bumps **32** are disposed on the second electrode **12**. The first bumps **31** and the second bumps **32** are respectively connected to the first surface **11a** and the second surface **12a**.

[0041] That is, in the light-emitting element **10**, the first electrode **11** extends between insides of the first openings **14a** used for electrical connections to the first semiconductor layer and the insulating film **14** above the second semiconductor layer **22**, and the second electrode **12** extends between insides of the second openings **14b** used for electrical connections to the second semiconductor layer and the insulating film **14** above the second semiconductor layer **22**, such that the first surface **11a** and the second surface **12a** located at the same height are located above the insulating film **14** above the second semiconductor layer **22**. The first bumps **31** are connected to the first surface **11a**, and the second bumps **32** are connected to the second surface **12a**.

[0042] In the light-emitting element having such a structure, of the surfaces of the first bumps **31** and the second bumps **32** respectively connected to the first surface **11a** and the second surface **12a** can be located at substantially the same height (that is, the heights from the lower surface of the light-emitting element to upper surfaces **31a** and **32a** of the bumps). This structure allows for reducing inclination due to the difference in height between the first electrode and the second electrode on the mounting surface of the light-emitting element at the time of flip-chip mounting. Accordingly, substantially the same amount of load is experienced on the first bumps and the second bumps when the light-emitting element is flip-chip mounted, which allows for reducing imbalances in loads experienced on the first electrode and the second electrode and also loads experienced on the first semiconductor layer and the second semiconductor layer at the time of

mounting. Stable flip-chip mounting can thus be performed.

[0043] Also, the first bumps **31** and the second bumps **32** with no difference in height can be formed under the same conditions at once in the manufacturing. This can simplify manufacturing. For example, when forming bumps under the same conditions on electrodes with a difference in height, the obtained bumps have a difference in height of respective upper surfaces, which necessitates a step of adjusting the bump heights, such as polishing, in order to reduce the inclination described above. Such a step can be omitted in the present embodiment.

[0044] Examples of the planar shape of the light-emitting element **10** and/or the semiconductor layered body include rectangular shapes. The planar shape may be a polygonal shape such as a triangular shape or a hexagonal shape, a shape with rounded corners, a circular shape, or an elliptic shape. The term “rectangular shape” as used in the present specification includes variations in the angles of the four corners of $90^\circ \pm 5^\circ$ are acceptable and includes an approximate rectangle such as rectangles with chamfered or rounded corners. The term “rectangular shape” includes a “square shape.”

Semiconductor Layered Body **23**

[0045] The semiconductor layered body **23** includes the first semiconductor layer **21** (such as an n-type semiconductor layer), the active layer **24**, and the second semiconductor layer **22** (such as a p-type semiconductor layer) layered on the supporting substrate **27**. The supporting substrate **27** may have been removed when in the form of the light-emitting element **10**. The second semiconductor layer **22** is preferably disposed inward of the outer periphery of the first semiconductor layer **21** in a plan view from the second semiconductor layer **22** side. That is, it is preferable that, in a plan view from the second semiconductor layer side, neither the second semiconductor layer **22** nor the active layer **24** is located in the outer peripheral portion of the semiconductor layered body **23** and the first semiconductor layer **21** exposed in the outer peripheral portion of the semiconductor layered body **23**. Further, it is preferable that the outer edges of the second semiconductor layer **22** substantially coincide with the outer edges of the active layer **24** and that the outer edges of the first semiconductor layer substantially coincide with the outer edges of the semiconductor layered body **23** in a plan view from the second semiconductor layer **22** side.

[0046] Examples of the first semiconductor layer, the active layer, and the second semiconductor layer include various semiconductors such as Groups III-V compound semiconductors and Group II-VI compound semiconductors. The specific examples include nitride semiconductor materials represented by $\text{In.sub.XAl.sub.YGa.sub.1-X-YN}$ ($0 \leq X$, $0 \leq Y$, and $X+Y \leq 1$), such as InN , AlN , GaN , InGaN , AlGaN , and InGaAlN . Each layer can have a thickness and layer structure known in the art. cl Supporting Substrate **27**

[0047] Examples of the supporting substrate **27** include a growth substrate for semiconductor layers, such as a substrate on which semiconductor layers can be epitaxially grown. Examples of the material for such a growth substrate include insulating substrates such as sapphire (Al.sub.2O.sub.3) and spinel (MgAl.sub.2O.sub.4) substrates.

Exposed Portion **21a**

[0048] The semiconductor layered body **23** includes, at locations inward of the outer periphery of the second semiconductor layer **22**, a plurality of exposed portions **21a** in which the second semiconductor layer **22** and the active layer **24** have been removed entirely in the thickness direction such that the first semiconductor layer **21** is exposed from the second semiconductor layer **22** and the active layer **24**. In other words, the upper surface of the second semiconductor layer **22** of the semiconductor layered body **23** defines recesses passing through the second semiconductor layer **22** and the active layer **24** to reach the first semiconductor layer **21**. The recesses are each defined by a base surface and a lateral surface surrounding the base surface. The first semiconductor layer **21** is exposed in the base surface defining the recess as the exposed portion **21a**. The second semiconductor layer **22**, the active layer **24**, and the first semiconductor layer **21** are located in the lateral surface of the recess in the order from the opening toward the base surface

defining the recess.

[0049] The shape, size, positions, and number of the exposed portions can be appropriately determined according to the size, shape, electrode pattern, and other factors of the light-emitting element to be obtained. For example, all the exposed portions **21a** may have the same shape and size, or all or part of the exposed portions **21a** may have different shapes and sizes. It is preferable that all the exposed portions **21a** have substantially the same size and shape. Because the exposed portions **21a** do not have the active layer **24**, regularly arraying the exposed portions **21a** of substantially the same size allows for reducing reduction in the emission area and unevenness in emission regions.

[0050] It is preferable that the exposed portions are regularly arranged inward of the outer periphery of the second semiconductor layer in a plan view from the second semiconductor layer side. In particular, when the semiconductor layered body **23** has a rectangular shape in a top view (that is, in a plan view from the second semiconductor layer side), the exposed portions are preferably arranged regularly along a first direction parallel to a side of the rectangle. It is more preferable that a plurality of rows of the exposed portions along the first direction be arranged parallel to one another. With the exposed portions **21a** regularly arranged spaced apart from one another, unevenness in the current density distribution can be reduced.

[0051] Examples of the shape of the exposed portions **21a** in a plan view include circular shapes, elliptic shapes, and polygonal shapes such as triangular shapes, quadrangular shapes, and hexagonal shapes. Among these shapes, circular shapes or near-circular shapes (such as elliptic shapes and polygonal shapes with six or more vertices) are preferable. The size of the exposed portions can be appropriately adjusted according to the size of the semiconductor layered body, the desired light output of the light-emitting element, and the like. For example, the exposed portions preferably have a diameter of about several tens of micrometers to several hundred micrometers. The exposed portions preferably have a diameter of about 1/20 to 1/5 of a side of the semiconductor layered body.

[0052] The total planar area of the exposed portions located inward of the outer periphery of the second semiconductor layer is preferably 30% or less, 25% or less, 20% or less, 18% or less, or 15% or less of the planar area of the inside of the outer periphery of the second semiconductor layer. With such ranges and regular arrangement of the exposed portions, unevenness in the current density distribution can be reduced while reducing a decrease in the light output due to a decrease in the emission area.

Insulating Film **14**

[0053] The insulating film **14** covers a surface of the semiconductor layered body **23** at the second semiconductor layer **22** side. The insulating film **14** defines the first openings **14a** and the second openings **14b**. The first semiconductor layer **21** is exposed from the insulating film in the first openings **14a**, and the second semiconductor layer is exposed from the insulating film in the second openings **14b**.

[0054] That is, the insulating film **14** covers the surface of the semiconductor layered body **23** at the second semiconductor layer side and defines the first openings **14a** over the exposed portions **21a** and the second openings **14b** over partial regions of the second semiconductor layer **22** as shown in FIG. **1C**. Part of the first openings **14a** may be located over the first semiconductor layer **21** exposed on the outer peripheral portion of the semiconductor layered body **23**.

[0055] The insulating film **14** covers the semiconductor layered body **23** and defines the first openings **14a** with the exposed portions **21a**. This structure allows the first electrode **11** to be disposed over a wide region of the upper surface of the insulating film **14**. The first openings **14a** preferably has a size smaller than that of the exposed portions **21a**, and it is more preferable that the first openings **14a** and the exposed portions **21a** be arranged in the same number and in a similar shape. That is, the insulating film **14** preferably covers the lateral surfaces defining the recesses defining the exposed portions **21a**, more preferably also covers outer peripheral portions

of the exposed portions **21a** near the lateral surfaces, and defines the first openings **14a** directly above central portions of the exposed portions **21a**. That is, the insulating film **14** preferably covers the lateral surfaces of the second semiconductor layer **22** and the lateral surfaces of the active layers **24** surrounding the exposed portions **21a**. This structure allows the first electrode **11** to be electrically connected only to the first semiconductor layer **21** in the first openings **14a**, so that a short circuit between the second semiconductor layer **22** and the active layer **24** can be prevented. [0056] It is not necessary that all the first openings **14a** has the same size and/or shape. When the semiconductor layered body **23** has a rectangular shape in a top view, the first openings **14a** are preferably arranged along the first direction parallel to a side of the rectangle. The opening areas of the first openings **14a** can be appropriately determined according to the size of the semiconductor layered body, the desired light output of the light-emitting element, and the like. For example, the total opening area of the first openings **14a** is preferably 0.1% to 1.5%, more preferably 0.3% to 0.5%, of the planar area of the semiconductor layered body.

[0057] As long as the second openings **14b** do not overlap (that is, not overlap in a plan view) with the exposed portions **21a**, the second openings **14b** may be defined in any appropriate number, shape, and size. When defining a plurality of second openings **14b**, part or all of the second openings **14b** may have the same shape and size or may have different shapes and sizes. The second openings **14b** can have, for example, a circular shape, an elliptic shape, a polygonal shape such as a triangular shape, a quadrangular shape, or a hexagonal shape, or a combination of two or more of these shapes.

[0058] For example, when the semiconductor layered body **23** has a rectangular shape in a top view and the second electrode has a shape that is longer in the first direction parallel to a side of the rectangular shape than in the second direction perpendicular to the first direction, the second openings **14b** are preferably longer in the first direction. Further, part or all of the second openings **14b** are preferably arranged along the outer edge of the second electrode **12**, the outer edge being close to the first electrode **11** to be described below. With the second bumps that are not disposed in the second openings **14b**, defining the second openings **14b** on the first electrode **11** side allows for securing the distances between the second bumps disposed on the second electrode and the first bumps disposed on the first electrode. The term “part” as used herein may refer to a portion of a single second opening **14b** or some of the second openings **14b**. The term “all” may refer to the whole of a single second opening **14b** or all the second openings **14b**.

[0059] The opening areas of the second openings **14b** can be appropriately determined according to the size of the semiconductor layered body, the desired light output of the light-emitting element, and the like. For example, the total opening area of the second openings **14b** is preferably 3% to 10%, more preferably 4% to 6%, of the planar area of the semiconductor layered body.

[0060] The total opening area of the first openings **14a** is preferably smaller than the total opening area of the second openings **14b**. For example, the total opening area of the first openings **14a** is preferably 5% to 25%, more preferably 8% to 15%, of the total opening area of the second openings **14b**.

[0061] In the case in which the second semiconductor layer is disposed inward of the outer periphery of the first semiconductor layer in a plan view from the second semiconductor layer side as described above, part or the whole of the first semiconductor layer exposed on the outer peripheral portion of the semiconductor layered body may be covered with the insulating film **14**.

[0062] The insulating film **14** is formed of a material known in the art and has a thickness that allows for having electrical insulation. More specifically, for the insulating film **14**, a metal oxide or a metal nitride can be used, and, for example, at least one of oxides and nitrides of substances selected from the group consisting of Si, Ti, Zr, Nb, Ta, or Al can be preferably used. The insulating film **14** can be formed by sputtering, vapor deposition, or the like.

First Electrode 11 and Second Electrode 12

[0063] The first electrode **11** and the second electrode **12** are located on the upper surface side (that

is, the second semiconductor layer **22** side opposite to the supporting substrate) of the semiconductor layered body **23** as shown in FIG. **1D**. The first electrode **11** and the second electrode **12** are electrically connected respectively to the first semiconductor layer **21** and the second semiconductor layer **22** through the first openings **14a** and the second openings **14b**. The first semiconductor layer **21** and the first electrode **11**, and the second semiconductor layer **22** and the second electrode **12** may be in direct contact with each other or may be electrically connected via an electroconductive layer such as a light-reflective electrode **28** described below. The first electrode **11** preferably covers all or part of the first openings **14a** integrally, more preferably covers all the first openings **14a** integrally. The second electrode **12** preferably covers all or part of the second openings **14b** integrally, more preferably covers all the second openings **14b** integrally. [0064] In the case in which the second semiconductor layer **22** is disposed inward of the outer periphery of the first semiconductor layer **21** in a plan view from the second semiconductor layer side as described above, it is preferable that the first electrode **11** be electrically connected to the first semiconductor layer **21** exposed from the insulating film **14** at locations outward of the outer periphery of the second semiconductor layer **22** in the plan view.

[0065] The first electrode **11** and the second electrode **12** can be formed by sputtering, vapor deposition, or the like.

[0066] For example, each of the first electrode **11** and the second electrode **12** can be formed of a single-layer film or a layered film made of metals such as Au, Pt, Pd, Rh, Ni, W, Mo, Cr, Ti, Al, and Cu or alloys of these metals. More specifically, each of the first electrode **11** and the second electrode **12** can be formed of a layered film of Ti/Rh/Au, Ti/Pt/Au, W/Pt/Au, Rh/Pt/Au, Ni/Pt/Au, Al-Cu alloy/Ti/Pt/Au, Al-Si-Cu alloy/Ti/Pt/Au, or Ti/Rh layered in this order from the semiconductor layer side. The first electrode **11** and the second electrode **12** may not be formed of the same material but are preferably formed of the same material in view of simplification of the manufacturing. The thicknesses of the first electrode **11** and the second electrode **12** can be appropriately set to a thickness of a film used in the art. In this case, the first electrode **11** and the second electrode **12** may not have the same thickness but preferably have the same thickness. In particular, the first electrode **11** and the second electrode **12** both have regions located above the second semiconductor layer **22** via the insulating film **14**. It is preferable that the thicknesses of the first electrode **11** and the second electrode **12** be determined such that the first surface **11a** and the second surface **12a** at least in such regions are located at the same height from the second semiconductor layer **22**. Alternatively, when the light-reflective electrode **28** and a protective layer **29** are disposed over the second semiconductor layer **22** as will be described below, the first electrode **11** and the second electrode **12** are preferably disposed such that the first surface **11a** and the second surface **12a** are located at the same height from the second semiconductor layer **22** in consideration of the thicknesses of the light-reflective electrode **28** and the protective layer **29** and the regions occupied by the light-reflective electrode **28** and the protective layer **29**. The first surface **11a** and the second surface **12a** are both regions in which the first bumps and the second bumps that will be described below are to be formed, and it is preferable to appropriately determine the sizes, shapes, arrangement, and the like in consideration of a voltage applied to the light-emitting element and the like. For example, the first surface **11a** and the second surface **12a** are preferably disposed in regions without the exposed portions **21a**.

[0067] The shapes of the first electrode **11** and the second electrode **12** can be appropriately determined. For example, the overall planar shape of the first electrode **11** and the second electrode **12** is preferably substantially the same as the planar shape of the semiconductor layered body **23**. For example, the first electrode **11** and the second electrode **12** may be arranged in parallel in the first direction parallel to a side of the rectangular semiconductor layered body **23** in a plan view, or the second electrode **12** may be disposed between the first electrodes **11** or vice versa.

[0068] The first electrode **11** is electrically connected to the exposed portions **21a** located on the second semiconductor layer **22** side of the semiconductor layered body **23**, described above,

through the first openings **14a**. In this case, the first electrode **11** is preferably connected to a plurality of exposed portions **21a** to collectively cover the exposed portions **21a**, more preferably integrally connected to all the exposed portions **21a**. The first electrode **11** is disposed not only over the exposed portions **21a** (that is, the first semiconductor layer **21**) but also above the second semiconductor layer **22**. The first electrode **11** covers the lateral surfaces of the second semiconductor layer **22** and the active layer **24**, which define the exposed portions **21a**, in the first openings **14a** via the insulating film **14**.

[0069] The second electrode **12** is disposed in a region without the exposed portions **21a**, that is, over the second semiconductor layer **22**, and is electrically connected to the second semiconductor layer **22** through the second openings **14b**. The second electrode **12** may be in direct contact with the second semiconductor layer **22** but is preferably disposed on the second semiconductor layer **22** with an electroconductive layer such as the light-reflective electrode described below therebetween.

First Bump 31 and Second Bump 32

[0070] A plurality of first bumps **31** are disposed on the first electrode **11**. A plurality of second bumps **32** are disposed on the second electrode **12**. The first bumps **31** and the second bumps **32** are disposed on the first surface **11a** and the second surface **12a** described above, respectively, and are respectively connected to the first electrode **11** and the second electrode **12**.

[0071] The first bumps **31** and the second bumps **32** preferably have the same thickness. With this structure, when the light-emitting element is flip-mounted on wirings on the substrate, which will be described below, the bumps can have approximately the same bonding strength. Further, the inclination of the light-emitting element can be avoided, which allows for facilitating adjustment of the optical axis with respect to the substrate.

[0072] The shapes, sizes, and numbers of the first bumps **31** and the second bumps **32** can all be appropriately determined as long as the first bumps **31** and the second bumps **32** can be disposed on the first surface **11a** and the second surface **12a**. For example, the first bumps **31** and the second bumps **32** can have a circular shape, an elliptic shape, or a polygonal shape such as a triangular shape, a quadrilateral shape, or a hexagonal shape in a plan view. Among these shapes, a circular shape or a near-circular shape (such as elliptic shapes or polygonal shapes with six or more vertices) is preferable. The size of the first bumps **31** and the second bumps **32** can be appropriately adjusted according to the size of the semiconductor layered body, the desired light output of the light-emitting element, and the like. For example, the first bumps **31** and the second bumps **32** can have a diameter in a range of about several tens of micrometers to several hundred micrometers. The diameter can be, for example, in a range of about 1/20 to 1/5 of a side of the semiconductor layered body. All or part of the first bumps **31** and the second bumps **32** may have the same shape and/or size or may have different shapes and/or sizes. All or part of the first bumps **31** may have the same shape and/or size as or may have different shapes and/or sizes from the second bumps **32**. The number of the first bumps **31** may be equal to or different from the number of the second bumps **32**.

[0073] The first bumps **31** and the second bumps **32** are used for flip-mounting the light-emitting element on the wiring on the substrate described below. The first bumps **31** and the second bumps **32** can be disposed at any appropriate positions on the first surface **11a** of the first electrode **11** and the second surface **12a** of the second electrode **12**. For example, the first bumps **31** and the second bumps **32** are preferably disposed evenly with respect to a surface of the semiconductor layered body as a whole. It is preferable that the first bumps **31** and the second bumps **32** are connected to the first surface and the second surface, respectively, with respective regularities at substantially uniform intervals. Such an arrangement allows the first bumps **31** and the second bumps **32** to be densely arranged without overlapping with the exposed portions in a plan view. This allows for supplying a sufficient current to the light-emitting element and dispersing the density of the supplied current, so that unevenness in the current density distribution can be reduced. Further, unevenness in the heat dissipation performance in a plane of the light-emitting element can be

reduced. Furthermore, the load experienced at the time of bonding to the substrate can be reduced, which can reduce variations in the degree of flattening of the bumps after the bonding. The inclination of the light-emitting element can also be avoided, which allows for facilitating adjustment in the optical axis with respect to the substrate.

[0074] For example, the first bumps **31** and the second bumps **32** can be formed of Au, Ag, Cu, Al, Sn, Pt, Zn, Ni, or an alloy of these metals and, for example, can be stud bumps known in the art. Stud bumps can be formed using a stud bump bonder or a wire bonder. The first bumps **31** and the second bumps **32** can be formed using a method known in the art, such as electroplating, electroless plating, vapor deposition, and sputtering.

Light-Reflective Electrode **28**

[0075] The light-emitting element **10** may include the light-reflective electrode **28** between the second electrode **12** and the second semiconductor layer **22**. The light-reflective electrode **28** covers the upper surface of the second semiconductor layer **22** as shown in FIG. **1A** and FIG. **1B**.

[0076] For example, the light-reflective electrode **28** defines holes **28a** above respective exposed portions **21a** as shown in FIG. **1A** and FIG. **1E**. The holes **28a** are through holes formed at positions corresponding to the exposed portions **21a** such that the light-reflective electrode **28** does not cover the exposed portions **21a**. The holes **28a** preferably have the same size and shape as the exposed portions **21a** or slightly larger than the exposed portions **21a** to surrounding the exposed portions **21a** in a plan view. The light-reflective electrode **28** is electrically connected to the second electrode **12** and the second semiconductor layer **22** and is therefore not in contact with the first semiconductor layer **21** including the exposed portions **21a**.

[0077] An electroconductive and light-reflective metal material can be used for the light-reflective electrode **28**. For example, Ag, Al, Ti, Pt, or an alloy mainly composed of any of these metals can be used. Among these materials, Ag or an Ag alloy that is reflective to light emitted from the active layer is more preferable. The light-reflective electrode **28** preferably has a thickness large enough to effectively reflect light emitted from the active layer, and the thickness can be in a range of about 20 nm to 1 μm . The greater the contact area between the light-reflective electrode and the second semiconductor layer, the more preferable, and accordingly the light-reflective electrode **28** is preferably disposed also at positions on the second semiconductor layer **22** above which the first electrode **11** is disposed. More specifically, for example, the total planar area of the light-reflective electrode **28** is 50% or more, 60% or more, or 70% or more of the planar area of the semiconductor layered body.

[0078] When the light-reflective electrode **28** contains Ag, the protective layer **29** is preferably disposed over the second semiconductor layer **22** to prevent Ag migration, such that the protective layer **29** covers the upper surface, preferably the entire upper and lateral surfaces, of the light-reflective electrode **28**.

[0079] More specifically, the light-reflective electrode **28** covers the second semiconductor layer **22** with spacing apart from the outer peripheral end of the second semiconductor layer **22** and opening ends of recesses defining the exposed portions **21a**. The protective layer **29** covers the whole upper surface of the second semiconductor layer **22** including the outer peripheral end of the second semiconductor layer **22** and the opening ends of the recesses defining the exposed portions **21a**. The protective layer **29** can thus cover the whole surfaces of the light-reflective electrode **28** including the lateral surfaces of the light-reflective electrode **28**.

[0080] For the protective layer **29**, an electroconductive member such as metals, alloys, or the like generally used as electrode materials may be used, or an insulating member may be used. Examples of the electroconductive member include single-layer films and layered films containing metals such as Al, Cu, and Ni. Examples of the insulating member include materials of the insulating film **14** described above, and SiN is preferable among the materials. SiN forms a dense film, and thus greatly prevents entry of water. For example, the thickness of the protective layer **29** is in a range of about several hundred nanometers to several micrometers to effectively reduce silver migration.

[0081] In the case in which the protective layer **29** is formed of an insulating member, the protective layer **29** preferably defines openings passing through the protective layer **29** at positions on or above the light-reflective electrode **28** that correspond to the second openings **14b** of the insulating film **14**. The second semiconductor layer **22** can thus be electrically connected to the second electrode **12** through the second openings via the light-reflective electrode **28**. In this case, the entire exposed surfaces of the light-reflective electrode **28** exposed from the protective layer **29** are preferably covered with the second electrode **12**.

[0082] The light-reflective electrode and the protective layer can be formed by sputtering, vapor deposition, or the like.

Light-Emitting Device

[0083] A light-emitting device **30** according to the present embodiment includes a substrate **33**, a light-emitting element **44**, and a plurality of bumps **45** as shown in FIGS. 7A and 7B. The bumps **45** include first bumps and second bumps. The light-emitting element **44** is flip-chip mounted on the substrate **33** via the first bumps and the second bumps.

[0084] Light-emitting elements **10** and **10A** to **10E** and the like described above or below may be employed for the light-emitting element **44** and the bumps **45** in the example herein. The bumps **45** may be bumps disposed on the substrate **33** separately from the light-emitting element. In this case, the light-emitting element preferably has substantially the same structure as that of the light-emitting elements **10** and **10A** to **10E** and the like described above or below except that the first bumps and the second bumps are not included. The bumps **45** may have substantially the same structure as the first bumps and the second bumps, described above, disposed on the light-emitting element. That is, the bumps **45** disposed on the substrate **33** are connected to the first surface of the first electrode and the second surface of the second electrode above the insulating film over the second semiconductor layer of the light-emitting element as described above, the first surface and the second surface being located at the same height from the second semiconductor layer.

[0085] The light-emitting device **30** may further include a covering member **34**. A light-transmissive member **35** is preferably disposed on the light-emitting element **44**.

Substrate **33**

[0086] The substrate **33** includes first wiring **41** and second wiring **42** on the upper surface.

[0087] Examples of a material of the substrate **33** include insulating members such as glass epoxy, resins, and ceramics, and metal members provided with insulating members on surfaces of the metal members. Among these materials, a material containing a ceramic, which is resistant to heat and weathering, is preferable for the substrate. Examples of a ceramic material include aluminum oxide and aluminum nitride.

[0088] Any appropriate wiring that can supply current to the light-emitting element can be used for the first wiring **41** and the second wiring **42** with materials, thickness, and shapes that are generally employed in the art. More specifically, for example, the first wiring **41** and the second wiring **42** can be formed of a metal such as Cu, Al, Au, Ag, Pt, Ti, W, Pd, Fe, and Ni or an alloy containing two or more of these metals. In order to efficiently extract light from the light-emitting element **10**, respective outermost surfaces of the first wiring **41** and the second wiring **42** disposed on the upper surface of the substrate **33** are preferably covered with a material having a high reflectance such as silver or gold. The first wiring **41** and the second wiring **42** can be formed by electroplating, electroless plating, vapor deposition, sputtering, or the like. For example, in the case in which Au bumps are used as the bumps **45**, employing Au for the outermost surfaces of the first wiring **41** and the second wiring **42** can improve bondability between the light-emitting element and the substrate.

[0089] The first wiring **41** and the second wiring **42** are preferably disposed on the upper surface of the substrate **33** to serve as positive and negative patterns. With the first wiring **41** and the second wiring **42** having such a structure, the first electrode electrically connected to the first semiconductor layer and the second electrode electrically connected to the second semiconductor

layer in the light-emitting element described below can be connected to the first wiring **41** and the second wiring **42**, respectively, via the bumps **45** by flip-chip mounting. The first wiring **41** and the second wiring **42** may be disposed not only over the upper surface of the substrate **33** but also over the lower surface through the inside and/or the lateral surfaces of the substrate **33**. The first wiring and the second wiring disposed over the lower surface can be used as external connecting terminals for supplying a current from the outside. The substrate **33** may include, in addition to the first wiring **41** and the second wiring **42** connected to the light-emitting element, wiring for securing heat dissipation performance and/or wiring for driving another electronic component such as a protective element.

Covering Member **34**

[0090] The covering member **34** is an insulating member covering part or all of the light-emitting element **44**, the bumps **45** including the first bumps and the second bumps, and the upper surface of the substrate **33** as shown in FIG. 7B. The covering member **34** preferably covers all of the lateral surfaces of the light-emitting element **44**, a region between the light-emitting element **44** and the substrate **33**, and the lateral surfaces of the bumps **45** on the upper surface of the substrate **33**.

[0091] For example, the covering member **34** can be formed of a light-reflective, light-transmissive, or light-shielding material. For example, a resin containing a light-reflective substance, a phosphor, a diffusing material, a colorant, etc., can be used. Among these properties, the covering member preferably has light-reflective and/or light-shielding properties. Any appropriate materials generally used in the art can be used for the resin, the light-reflective substance, and the like constituting the covering member.

[0092] Examples of the resin include a resin or hybrid resin containing at least one of a silicone resin, a modified silicone resin, an epoxy resin, a modified epoxy resin, an acrylic resin, a phenolic resin, or a fluorocarbon resin. Examples of the light-reflective substance include titanium oxide, silicon oxide, zirconium oxide, potassium titanate, aluminum oxide, aluminum nitride, boron nitride, and mullite.

[0093] The material constituting the covering member **34** preferably contains a resin, which is highly fluid and is cured by application of heat or light, in view of ease of entering the gap between the light-emitting element and the substrate and prevention of formation of voids. Examples of such a material include a material that has a fluidity at a viscosity of 0.5 Pa·s to 30 Pa·s. The amounts of reflection and transmission of light can be adjusted by adjusting the content of the light-reflective substance or the like in the material constituting the covering member **34**. For example, the covering member preferably contains 20 wt % or more of the light-reflective substance.

[0094] The covering member **34** can be formed by, for example, injection molding, potting, printing, transfer molding, or compression molding.

Light-Transmissive Member **35**

[0095] The light-emitting device **30** includes the light-transmissive member **35** on the light-emitting element **10**. The light-emitting element **10** is flip-chip mounted on the first wiring **41** and the second wiring **42** such that a surface of light-emitting element **10** provided with the first electrode and the second electrode serves as a lower surface of the light-emitting element **10**. The upper surface of the light-emitting element **10** opposite to the lower surface serves as a main light extracting surface and is bonded to the lower surface of the light-transmissive member **35**.

[0096] The light-transmissive member **35** covers the light extracting surface of the light-emitting element and is adapted to transmit, to the outside, 60% or more, preferably 70% or more, of light emitted from the light-emitting element and/or light emitted from the light-emitting element and subjected to wavelength conversion (for example, wavelengths of 320 nm to 850 nm). The light-transmissive member **35** may contain a phosphor or the like adapted to perform wavelength conversion of at least part of light emitted from the light-diffusing material or the light-emitting element **44**.

[0097] The lower surface of the light-transmissive member **35** preferably has an area dimension of about 80% to 150% of the area dimension of the upper surface of the light-emitting element **44**. It is preferable that the outer edges of the lower surface of the light-transmissive member **35** coincide with the outer edges of the upper surface of the light-emitting element or be located either inward or outward of the outer edge of the upper surface. That is, in a plan view, one of the upper surface of the light-emitting element and the lower surface of the light-transmissive member is preferably located inward of the other of the upper surface of the light-emitting element and the lower surface of the light-transmissive member. The light-transmissive member has a thickness in a range of, for example, 50 μm to 300 μm .

[0098] For example, the light-transmissive member **35** can be formed of resin, glass, or an inorganic substance. Examples of the light-transmissive member containing a phosphor include a sintered body of a phosphor and a mixture of a phosphor and a substance such as resin, glass, and other inorganic substances. Alternatively, a flat-plate shaped molded body of a resin, glass, or an inorganic substance provided with a resin layer containing a phosphor and/or a diffusing material on a surface of the molded body can be used. The higher the transparency of the light-transmissive member is, the more light is likely to be reflected at the interface with the covering member, so that the luminance of the light-emitting device can be improved.

[0099] Examples of the phosphor contained in the light-transmissive member **35** when using a blue or ultraviolet light-emitting element for the light-emitting element include cerium-activated yttrium-aluminum-garnet based phosphors (YAG:Ce), cerium-activated lutetium-aluminum-garnet based phosphors (LAG:Ce), europium- and/or chromium-activated nitrogen-containing calcium aluminosilicate based phosphors ($\text{CaO—Al}_2\text{O}_3\text{—SiO}_2\text{:Eu}$ and/or Cr), europium-activated silicate based phosphors (such as $(\text{Sr,Ba})_2\text{SiO}_4\text{:Eu}$), nitride phosphors such as $\beta\text{-SiAlON}$ based phosphors (such as $\text{Si}_6\text{—ZAl}_2\text{O}_7\text{:Z:Eu}$ ($0 < Z < 4.2$)), CASN based phosphors, and SCASN based phosphors, KSF based phosphors ($\text{K}_2\text{SiF}_6\text{:Mn}$), sulfide based phosphors, and quantum-dot phosphors. A combination of such a phosphor and a blue or ultraviolet light-emitting element allows for obtaining a light-emitting device configured to emit light having a desired color (such as a light-emitting device configured to emit a white light). In the case in which the light-transmissive member contains such a phosphor, the concentration of the phosphor is preferably, for example, in a range of about 5% to 50%.

[0100] The light-transmissive member **35** is bonded to cover the light extracting surface of the light-emitting element. The light-transmissive member can be directly bonded to the light-emitting element by press-bonding, sintering, surface-activated bonding, atomic diffusion bonding, or hydroxy group bonding or may be bonded with an adhesive. Examples of the adhesive include known resins such as epoxy resins and silicone resins.

[0101] When the light-emitting device **30** includes the light-transmissive member **35**, the covering member **34** preferably covers part or all of the lateral surfaces of the light-transmissive member **35**.

[0102] The light-emitting device may include other elements or electronic components such as a protective element **36**. These elements and components are preferably mounted on the substrate **33** and embedded in the covering member **34**.

First Embodiment

[0103] As shown in FIGS. **1A** and **1B**, the light-emitting element **10** according to a first embodiment has a substantially square shape in a plan view. For example, the light-emitting element **10** with each side of 1.0 mm can be employed.

[0104] The light-emitting element **10** includes the semiconductor layered body **23**, the insulating film **14**, the first electrode **11**, the second electrode **12**, the first bumps **31**, and the second bumps **32**.

[0105] The semiconductor layered body **23** includes the first semiconductor layer **21**, the second semiconductor layer **22**, and the active layer **24** between the first semiconductor layer **21** and the second semiconductor layer **22**. The first semiconductor layer **21** has the exposed portions **21a**

exposed from the second semiconductor layer **22** at a location inward of the outer periphery of the second semiconductor layer **22**. The first semiconductor layer **21** is exposed on the outer periphery of the second semiconductor layer **22**.

[0106] For example, the exposed portions **21a** have a substantially circular shape, and a plurality of exposed portions **21a** are disposed at substantially regular intervals in a plan view of the light-emitting element **10** on both sides of the second electrode **12** that is longer in the first direction.

[0107] The insulating film **14** defines the first openings **14a** and the second openings **14b** that extend through the insulating film **14** as shown in FIG. **1A** to FIG. **1C**. The insulating film **14** covers substantially the entire surface of the semiconductor layered body **23** except for the first openings **14a** defined over the exposed portions **21a** and the second openings **14b** defined over the partial regions of the second semiconductor layer **22**. The second openings **14b** are arranged along the outer edge of the second electrode **12** facing the first electrode **11**. For example, the total opening area of the first openings **14a** is $4,800\ \mu\text{m}^2$, and the total opening area of the second openings **14b** is $50,900\ \mu\text{m}^2$. The total opening area of the first openings is therefore smaller than the total opening area of the second openings.

[0108] In the light-emitting element **10**, the light-reflective electrode **28** mainly composed of Ag is disposed over substantially the entire surface of the second semiconductor layer **22**. The light-reflective electrode **28** defines the holes **28a** as

[0109] The first openings **14a** are arranged to overlap with the holes **28a** and the exposed portions **21a**. That is, the exposed portions (that is, the first semiconductor layer) are exposed from the light-reflective electrode **28** in the holes **28a**. The protective layer **29** composed of SiN is disposed over the second semiconductor layer **22** to cover all of surfaces of the light-reflective electrode **28**, the surfaces including the upper surface, the outer peripheral lateral surfaces, and the inner lateral surfaces defining the holes **28a**.

[0110] As shown in FIG. **1F**, in the light-emitting element **10**, each of the substantially circular holes **28a** (that is, the inner peripheries of the light-reflective electrode **28** defining the holes **28a**) is defined to surround a corresponding one of the substantially circular exposed portions **21a** in a plan view. Each of the exposed portions **21a** surrounds a corresponding one of the substantially circular first openings **14a** (that is, the inner periphery of the insulating film **14** defining the first opening **14a**) in a plan view.

[0111] The second openings **14b** are defined over portions of the light-reflective electrode **28** that cover the second semiconductor layer **22**, the portions being regions above the partial regions of the second semiconductor layer **22**.

[0112] The first electrode **11** and the second electrode **12** are made of Au. The first electrode **11** is disposed on both sides with respect to the second electrode **12** in a plan view from the second semiconductor layer side as shown in FIG. **1A** and FIG. **1D**. More specifically, the first electrode **11** surrounds the second electrode **12** that is long in the first direction. In other words, portions of the first electrode **11** on both sides with respect to the second electrode **12** are continuous with each other through portions of the first electrode **11** at both ends of the second electrode **12** in the first direction. The first electrode **11** is electrically connected to the first semiconductor layer through each first opening **14a** and is partially disposed above the second semiconductor layer **22** via the insulating film **14**. The first electrode **11** collectively covers a plurality of exposed portions. The second electrode **12** is electrically connected to the second semiconductor layer **22** through the second openings **14b** and partially disposed above the second semiconductor layer **22** via the insulating film **14**. The second electrode collectively covers the two second openings **14b**. The first electrode **11** and the second electrode **12** have a thickness of about $1\ \mu\text{m}$ at a portion above the insulating film **14** above the second semiconductor layer **22**. The first electrode **11** and the second electrode **12** have the first surface **11a** and the second surface **12a**, respectively, at the same distance (**H1** and **H2** in FIG. **1B**) from a surface of the second semiconductor layer **22**.

[0113] The first bumps **31** and the second bumps **32** are formed of Au with a thickness of $15\ \mu\text{m}$.

Each first bump **31** and each second bump **32** have a circular shape with a diameter of 110 μm in a plan view and are respectively bonded to the first surface **11a** and the second surface **12a**. On the first electrode **11** at both sides of the second electrode **12**, six-by-two first bumps **31** are disposed at uniform intervals between the exposed portions so as not to overlap with the exposed portions **21a** in a plan view. Six second bumps **32** are disposed at uniform intervals on the narrow second electrode **12** along the longitudinal direction of the second electrode so as not to overlap with the second openings **14b** in a plan view.

[0114] The two second openings **14b** are defined on both sides of the second bumps along the longitudinal direction of the narrow second electrode. The outer edges of the second openings **14b** at the second bump side are partially recessed to form substantially circular arcs corresponding to the substantially circular second bumps **32**. This structure allows for facilitating disposing the second bumps on the second surface.

[0115] With such a structure, corresponding surfaces of the first bumps and the second bumps are in the same plane on the surface of the light-emitting element, and when the light-emitting element is flip-chip mounted on the substrate using the bumps, the heights of the bumps connected to electrodes with different polarities can be substantially equal to each other, so that stable flip-chip mounting can be performed. Further, with regular arrangement of the first bumps and the second bumps, imbalances in loads at the time of mounting can be reduced, so that more stable flip-chip mounting can be performed.

Second Embodiment

[0116] The light-emitting element **10A** of a second embodiment differs from the light-emitting element **10** described above in that an insulating film **114** defines first openings **114a** also outward of the outer periphery of the second semiconductor layer as shown in FIG. 2A. In the light-emitting element **10A**, the first openings **114a** located outward of the outer periphery of the second semiconductor layer **22** are regularly arranged along the outer periphery of the second semiconductor layer **22** at certain intervals. For example, the intervals between adjacent first openings **114a** are preferably 100 μm to 300 μm .

[0117] In the light-emitting element **10A** of the second embodiment, the first openings **114a** located inward of and outward of the outer periphery of the second semiconductor layer **22** have substantially the same circular shapes in a plan view. In order to define the substantially circular first openings outward of the outer periphery, the second semiconductor layer **22** defines outer peripheral recesses of arc-shaped recessed shape on part of the outer periphery thereof in a plan view. First openings having a substantially circular shape **114a** are defined at positions corresponding to the outer peripheral recesses. With this structure, electrical connections between the first electrode **11** and the first semiconductor layer **21** can be secured also at locations outward of the outer periphery of the second semiconductor layer **22**, and a decrease in the area of the second semiconductor layer **22** can be reduced.

[0118] Corresponding to the arrangement of the first openings **114a**, for example, a light-reflective electrode **128** defines holes **128a** above the exposed portions **21a**. Further, the light-reflective electrode **128** also defines outer peripheral recesses **128b** in its outer periphery at positions corresponding to the arrangement of the outer peripheral recesses of the second semiconductor layer **22** as shown in FIG. 2C.

[0119] Also, in the light-emitting element **10A**, the first electrode **11** and the second electrode **12** respectively have the first surface **11a** and the second surface **12a** above the insulating film **14** over the second semiconductor layer **22**, the first surface **11a** and the second surface **12a** located at the same distance from the surface of the second semiconductor layer **22**.

[0120] On the first surface **11a** of the first electrode **11** at both sides of the second electrode **12**, six-by-two first bumps **31** are disposed at uniform intervals between the exposed portions **21a** so as not to overlap with the exposed portions **21a** in a plan view. Six second bumps **32** are disposed at uniform intervals at positions on the second surface **12a** of the second electrode **12** that do not

overlap with second openings **214b** in a plan view. The first bumps **31** and the second bumps **32** are made of the same material and have the same thickness.

[0121] Structures other than those described above are substantially the same as those of the light-emitting element **10** of the first embodiment. Accordingly, similar effects can be obtained.

[0122] With such an arrangement of the first semiconductor layer **21** and the first openings **114a**, unevenness in the current density distribution at the time of emission of light can be reduced while securing the areas of the second semiconductor layer **22** and the active layer **24**.

Third Embodiment

[0123] As shown in FIGS. **3A** and **3C**, in a light-emitting element **10B** of a third embodiment, a first electrode **311** and a second electrode **312** are predominantly disposed on one side and the other side, respectively, of two opposite sides of the semiconductor layered body **23** having a rectangular shape in a plan view. In a plan view, in a central portion of the light-emitting element **10B**, an outer edge of the first electrode **311** facing the second electrode **312** defines a projecting region protruding toward the second electrode **312**. An outer edge of the second electrode **312** facing the projecting region of the first electrode **311** is recessed to correspond to the projecting region of the first electrode **311**.

[0124] On the central portion, three-by-three exposed portions **321a** are arranged to overlap with the first electrode **311** and at least partially overlap with the projecting region of the first electrode **311**. Each of the exposed portions **321a** has a substantially circular planar shape.

[0125] As shown in FIG. **3B**, first openings **314a** of an insulating film **314** are arranged at the central region of the light-emitting element **10B** to correspond to the arrangement of the exposed portions **321a**. Two slightly larger rectangular second openings **314b** are arranged on both sides of the first openings **314a** at the central region. Further, five second openings **314bb**, each having a substantially circular planar shape and each being slightly larger than the first opening **314a**, are arranged in a row along an outer edge on the other side at which the second electrode **312** is disposed. For example, the total opening area of the first openings **314a** is $9,200\ \mu\text{m}^2$, and the total opening area of the second openings **314b** and **314bb** is $68,400\ \mu\text{m}^2$. The total opening area of the first openings is therefore smaller than the total opening area of the second openings.

[0126] A light-reflective electrode **328** is disposed over substantially the entire surface of the second semiconductor layer **22** to be spaced apart from the end portion (including opening ends of the recesses defining the exposed portions **321a**) of the second semiconductor layer **22**. The light-reflective electrode **328** defines holes **328a** above the exposed portions **321a**. Accordingly, the second openings **314b** and **314bb** are defined above partial regions of the second semiconductor layer **22**, that is, above partial regions of the light-reflective electrode **328**. In the second openings **314b**, the second electrode **312** is electrically connected to the second semiconductor layer **22** via the light-reflective electrode **328**.

[0127] Also in the light-emitting element **10B**, the first electrode **311** and the second electrode **312** respectively have the first surface and the second surface above the insulating film **314** above the second semiconductor layer **22**, the first surface and the second surface located at the same distance from the surface of the second semiconductor layer **22**.

[0128] Six-by-three first bumps **31** are disposed at uniform intervals at positions on the first surface of the first electrode **311** that do not overlap with the exposed portions **321a** or the first openings **314a** in a plan view. Six-by-two second bumps **32** are disposed at regular intervals at positions on the second surface of the second electrode **312** that do not overlap with the second openings **314b** in a plan view. The first bumps **31** and the second bumps **32** are made of the same material and have the same thickness.

[0129] Structures other than those described above are substantially the same as those of the light-emitting element **10** of the first embodiment. Accordingly, similar effects can be obtained.

[0130] Such an arrangement of the first electrode and the second electrode causes the first bumps and the second bumps to be predominantly disposed on the one and the other sides, respectively of

the light-emitting element. Even with such an arrangement, the heights of the surfaces of the first bumps **31** and the second bumps **32** respectively connected to the first surface **11a** and the second surface **12a** can be substantially equal to each other, so that inclination at the time of mounting can be reduced.

Fourth Embodiment

[0131] In a light-emitting element **10C** according to a fourth embodiment, as shown in FIGS. **4A** and **4C**, a first electrode **411** and a second electrode **412** are predominantly disposed on one and the other sides, respectively, of two opposite sides of the semiconductor layered body **23** having a rectangular shape in a plan view. In a central portion of the light-emitting element **10C**, an outer edge of the first electrode **411** facing the second electrode **412** defines a projecting region protruding toward the second electrode **412**. An outer edge of the second electrode **412** facing the projecting region of the first electrode **411** is recessed to correspond to the projecting region of the first electrode **411**.

[0132] Five exposed portions **421a** are arranged on the central portion to overlap with the first electrode **411** and at least partially overlap with the projecting region of the first electrode **411**. Each of the exposed portions **421a** has a substantially circular planar shape.

[0133] First openings **414a** of an insulating film **414** are defined at a central region of the light-emitting element **10C** to correspond to the arrangement of the exposed portions **421a** as shown in FIG. **4B**. Two slightly larger rectangular second openings **414b** are defined on both sides of the first openings **414a** at the center region. Further, six-by-two second openings **414bb** are defined on the other side at which the second electrode **412** are disposed, each of the second openings **414bb** having a substantially circular planar shape and being slightly smaller than the first opening **414a**. Part of the second openings **414b** are arranged along the outer edge of the second electrode **412** facing the first electrode **411**. For example, the total opening area of the first openings **414a** is $13,200\ \mu\text{m}^2$, and the total opening area of the second openings **414b** and **414bb** is $54,100\ \mu\text{m}^2$. The total opening area of the first openings is therefore smaller than the total opening area of the second openings. The first electrode **411** is electrically connected to the first semiconductor layer **21** through the first openings **414a**. The second electrode **412** is electrically connected to the second semiconductor layer **22** through the second openings **414b**.

[0134] Also in the present embodiment, a light-reflective electrode **428** is disposed over substantially the entire surface except for the edges of the second semiconductor layer **22**. The light-reflective electrode **428** defines holes **428a** above the exposed portions **421a**.

[0135] Also, in the light-emitting element **10C**, the first electrode **411** and the second electrode **412** respectively have the first surface and the second surface **22** above the insulating film **414** over the second semiconductor layer **22**, the first surface and the second surface **22** located at the same distance from the surface of the second semiconductor layer.

[0136] Six-by-one and seven-by-two first bumps **31** are disposed at substantially uniform intervals at positions on the first surface of the first electrode **411** that do not overlap with the exposed portions **421a** or the first openings **414a** in a plan view. Seven-by-two and six-by-one second bumps **32** are disposed at substantially uniform intervals at positions on the second surface of the second electrode **412** that do not overlap with the second openings **414b** in a plan view. The first bumps **31** and the second bumps **32** are made of the same material and have the same thickness.

[0137] Structures other than those described above are substantially the same as those of the light-emitting elements **10** and **10B**. Accordingly, similar effects can be obtained.

Fifth Embodiment

[0138] A light-emitting element **10D** according to a fifth embodiment includes, as shown in FIGS. **5A** and **5C**, second electrodes **512** of a narrow shape longer in the first direction on two opposing end portions of the semiconductor layered body **23** and a first electrode **511** disposed between the second electrodes **512** in a plan view. In other words, the second electrodes **512** are disposed on both sides with respect to the first electrode **511** in a plan view from the second semiconductor

layer **22** side. The first electrode **511** surrounds the second electrodes **512** located at the two opposing end portions.

[0139] At a central region in a direction perpendicular to the first direction, five-by-four exposed portions **521a** are arranged to overlap with the first electrode **511** in a plan view. Each of the exposed portions **521a** has a substantially circular planar shape. Intervals between the exposed portions **521a** are substantially equal to each other.

[0140] Corresponding to the arrangement of the exposed portions **521a**, first openings **514a** of an insulating film **514** are arranged to overlap with the exposed portions **521a** in a plan view as shown in FIG. **5B**. Two narrow second openings **514b** are arranged on both sides of the first openings **514a** along corresponding outer edges of the second electrodes. The second openings **514b** are arranged along outer edges of the second electrodes **512** facing the first electrode **511**. For example, the total opening area of the first openings **514a** is $2,700\ \mu\text{m}^2$, and the total opening area of the second openings **514b** is $36,600\ \mu\text{m}^2$. The total opening area of the first openings is therefore smaller than the total opening area of the second openings. The first electrode **511** collectively covers a plurality of exposed portions **521a** and first openings **514a**. The second electrodes **512** on two opposing end portions respectively cover the two second openings **514b**.

[0141] A light-reflective electrode **528** is disposed over substantially the entire surface of the second semiconductor layer **22** except for the exposed portions **521a**, and holes **528a** are defined over the first openings **514a**.

[0142] Also, in the light-emitting element **10D**, the first electrode **511** and the second electrodes **512** respectively have the first surface and the second surfaces above the insulating film **514** over the second semiconductor layer **22**, the first surface and the second surfaces located at the same distance from the surface of the second semiconductor layer **22**.

[0143] Six-by-three first bumps **31** are disposed at positions on the first surface of the first electrode **511** at uniform intervals between the exposed portions **521a**, the positions not overlapping with the exposed portions **521a** or the first openings **514a** in a plan view. Six second bumps **32** are disposed at positions on each second surface of the second electrodes **512** at uniform intervals in a row on both sides of the first bumps **31**, the positions not overlapping with the second openings **514b** in a plan view. The first bumps **31** and the second bumps **32** are made of the same material and have the same thickness.

[0144] Structures other than those described above are substantially the same as those of the light-emitting element **10** of the first embodiment. Accordingly, similar effects can be obtained.

Sixth Embodiment

[0145] A light-emitting element **10E** of a sixth embodiment includes the second electrode only on one side of the semiconductor layered body **23** as shown in FIGS. **6A** and **6C** while the light-emitting element **10D** described above includes the second electrodes disposed on both sides of the semiconductor layered body **23**. In other words, substantially the same structure as that of the light-emitting element **10D** is employed except that a first electrode **611** and a second electrode **612** are respectively disposed on one side and the other side in a plan view from the second semiconductor layer side.

[0146] Also, in the light-emitting element **10E**, the first electrode **611** and the second electrode **612** respectively have the first surface and the second surface above an insulating film **614** above the second semiconductor layer **22**, the first surface and the second surface located at the same distance from the surface of the second semiconductor layer **22**.

[0147] On the first surface of the first electrode **611**, six-by-three first bumps **31** are disposed at uniform intervals without overlapping with the exposed portions **621a** or first openings **614a** in a plan view, such that each of the six-by-three first bumps **31** is located between adjacent ones of exposed portions **621a**, and six first bumps **31** are disposed at uniform intervals in a row at an end portion at which the second electrode **612** is not disposed. Six second bumps **32** are arranged in a row at positions on the second surface of the second electrode **612** at uniform intervals, the

positions not overlapping with second openings **614b** in a plan view. The first bumps **31** and the second bumps **32** are made of the same material and have the same thickness.

[0148] Structures other than those described above are substantially the same as that of the light-emitting element **10** of the first embodiment. Accordingly, similar effects can be obtained.

[0149] The light-emitting elements of the present disclosure can be used for various light sources such as light sources for lighting, light sources for various indicators, light sources for vehicles, light sources for displays, light sources for backlights of liquid crystal screens, light sources for sensors, signals, vehicle components, and channel letters for signage.

[0150] In the description above, certain embodiments of a light-emitting element and a light-emitting device are described. However, the present invention is not limited to the description above, and should be broadly construed on the basis of the claims. The present invention also encompasses variations and modifications that are made on the basis of the description above.

Claims

1. A light-emitting element comprising: a semiconductor layered body including a first semiconductor layer, a second semiconductor layer, and an active layer between the first semiconductor layer and the second semiconductor layer, the first semiconductor layer having a plurality of exposed portions exposed from the second semiconductor layer and the active layer at locations inward of an outer periphery of the second semiconductor layer in a plan view from a side of the second semiconductor layer; an insulating film covering the semiconductor layered body and defining at least one first opening above one of the exposed portions and a plurality of second openings above a part of the second semiconductor layer; a first electrode electrically connected to the first semiconductor layer through the first opening and partially located above the second semiconductor layer via the insulating film; a second electrode electrically connected to the second semiconductor layer through the second openings and partially located above the second semiconductor layer via the insulating film; a plurality of first bumps above the first electrode; and a plurality of second bumps above the second electrode, the second bumps being aligned along a first direction, wherein the first electrode has a first surface and the second electrode has a second surface above the insulating film disposed above the second semiconductor layer, the first surface and the second surface being located at a same height from the second semiconductor layer, the first bumps are electrically connected to the first surface, and the second bumps are electrically connected to the second surface, in the plan view, the second electrode has an elongated shape that is longer in the first direction than in a second direction perpendicular to the first direction, and in the plan view, the second openings are arranged along outer edges of the second electrode extending in the first direction, with at least two of the second openings being aligned in the second direction and at least one of the second bumps being arranged between the at least two of the second openings.

2. The light-emitting element according to claim 1, wherein the first bumps and the second bumps have a same thickness.

3. The light-emitting element according to claim 1, wherein the second semiconductor layer is disposed inward of an outer periphery of the first semiconductor layer in the plan view, and the first electrode is electrically connected to the first semiconductor layer exposed from the insulating film at a location outward of the outer periphery of the second semiconductor layer in the plan view.

4. The light-emitting element according to claim 1, wherein the first electrode is disposed on two opposing sides with respect to the second electrode in the plan view.

5. The light-emitting element according to claim 1, wherein the first electrode is disposed on one side, and the second electrode is disposed on another side in the plan view.

6. The light-emitting element according to claim 1, wherein the second electrode is disposed on two opposing sides with respect to the first electrode in the plan view.

7. The light-emitting element according to claim 1, wherein an opening area of the at least one first opening is smaller than an opening area of each of the second openings.
 8. The light-emitting element according to claim 1, wherein the semiconductor layered body has a rectangular shape in the plan view, the second electrode is longer in a first direction parallel to a side of the rectangular shape than in a second direction perpendicular to the first direction, and at least one of the second openings is longer in the first direction along an outer edge of the second electrode.
 9. The light-emitting element according to claim 1, wherein the first electrode collectively covers the plurality of exposed portions.
 10. The light-emitting element according to claim 1, wherein the second electrode collectively covers the second openings arranged over the second semiconductor layer.
 11. The light-emitting element according to claim 1, wherein the second electrode is connected to the second semiconductor layer via a light-reflective electrode.
 12. The light-emitting element according to claim 11, wherein the light-reflective electrode defines holes respectively above the exposed portions.
 13. A light-emitting device comprising: a substrate having an upper surface and including a first wiring and a second wiring that are disposed on the upper surface; and a light-emitting element including a semiconductor layered body including a first semiconductor layer, a second semiconductor layer, and an active layer between the first semiconductor layer and the second semiconductor layer, the first semiconductor layer having a plurality of exposed portions exposed from the second semiconductor layer and the active layer at locations inward of an outer periphery of the second semiconductor layer in a plan view from a side of the second semiconductor layer, an insulating film covering the semiconductor layered body and defining a plurality of first openings respectively over the exposed portions and a plurality of second openings over a part of the second semiconductor layer, a first electrode electrically connected to the first semiconductor layer through the first openings and partially disposed above the second semiconductor layer via the insulating film, and a second electrode electrically connected to the second semiconductor layer through the second openings and partially disposed above the second semiconductor layer via the insulating film, wherein the first electrode has a first surface and the second electrode has a second surface above the insulating film disposed above the second semiconductor layer, the first surface and the second surface being located at a same height from the second semiconductor layer, wherein the light-emitting element is flip-chip mounted on the substrate via a plurality of first bumps electrically connecting the first surface of the first electrode and the first wiring of the substrate, and a plurality of second bumps electrically connecting the second surface of the second electrode and the second wiring of the substrate, the second bumps being aligned along a first direction, in the plan view, the second electrode has an elongated shape that is longer in the first direction than in a second direction perpendicular to the first direction, and in the plan view, the second openings are arranged along outer edges of the second electrode extending in the first direction, with at least two of the second openings being aligned in the second direction and at least one of the second bumps being arranged between the at least two of the second openings.
-