

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250287807

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

LEE; Jaeho et al.

ORGANIC LIGHT EMITTING DISPLAY APPARATUS HAVING PIXELS OF DIFFERENT STRUCTURES

Abstract

An organic light emitting display apparatus can include a first subpixel configured to emit a first color of light, the first subpixel including a first-first electrode, a first light emitting portion, and a first-second electrode, a second subpixel configured to emit a second color of light different than the first color of light, the second subpixel including a second-first electrode, a second light emitting portion, and a second-second electrode, and a third subpixel configured to emit a third color of light different than the first color of light and the second color of light, the third subpixel including a third-first electrode, a third light emitting portion, and a third-second electrode. Also, at least one of the first light emitting portion, the second light emitting portion and the third light emitting portion includes at least a first stack light emitting portion and a second stack light emitting portion.

Inventors: LEE; Jaeho (Seoul, KR), KOO; Wonhoe (Goyang-si, KR), SIM; Dongmin (Paju-si, KR), KIM; Taemin (Paju-si, KR), CHOI; Hyekyung (Seoul, KR), HAN; Kyunghoon (Seoul, KR)

Applicant: LG Display Co., Ltd. (Seoul, KR)

Family ID: 1000008618296

Assignee: LG Display Co., Ltd. (Seoul, KR)

Appl. No.: 19/213635

Filed: May 20, 2025

Foreign Application Priority Data

KR

10-2019-0179655

Dec. 31, 2019

Related U.S. Application Data

parent US continuation 18603852 20240313 parent-grant-document US 12336410 child US 19213635
parent US continuation 17117702 20201210 parent-grant-document US 11974480 child US 18603852

Publication Classification

Int. Cl.: **H10K59/35** (20230101); **H10K50/15** (20230101); **H10K50/81** (20230101); **H10K59/80** (20230101); **H10K101/20** (20230101); **H10K102/00** (20230101)

U.S. Cl.:

CPC **H10K59/351** (20230201); **H10K50/15** (20230201); **H10K50/81** (20230201); **H10K59/353** (20230201); **H10K59/8051** (20230201); **H10K59/876** (20230201); H10K2101/20 (20230201); H10K2102/351 (20230201)

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATIONS [0001] This application is a Continuation of U.S. application Ser. No. 18/603,852, filed on Mar. 13, 2024, which is a Continuation of U.S. application Ser. No. 17/117,702, filed on Dec. 10, 2020 (now U.S. Pat. No. 11,974,480 issued on Apr. 30, 2024), which claims priority to Korean Patent Application No. 10-2019-0179655 filed on Dec. 31, 2019, in the Republic of Korea, the entire contents of all these applications are hereby incorporated herein by reference into the present application.

BACKGROUND

Technical Field

[0002] The present disclosure relates to an organic light emitting display apparatus, and more particularly, to an organic light emitting display apparatus which minimizes a color change and a luminance change according to a viewing angle.

Description of the Related Art

[0003] Organic light emitting display apparatuses do not need a separate light source, which is different from a liquid crystal display apparatus, e.g., OLED displays include self-emitting sub-pixels (e.g., no backlight). Therefore, the organic light emitting display apparatus can be manufactured to have a light weight and a small thickness. Further, since the organic light emitting display apparatus is driven at a low voltage, it is advantageous not only in terms of power consumption, but also in terms of a color implementation, a response speed, a viewing angle, and a contrast ratio (CR). Therefore, the light emitting display apparatus is being studied as the next generation displays.

[0004] The organic light emitting display apparatus is a self-emitting display apparatus and uses an organic light emitting diode in which electrons and holes from a cathode for injecting electrons and an anode for injecting holes are injected into a light emitting layer and excitons formed by coupling the injected electrons and holes are dropped from an excited state to a ground state to emit light.

[0005] The organic light emitting display apparatus can be classified into a top emission type, a bottom emission type, and a dual emission type depending on a direction in which light is emitted and can also be classified into a passive matrix type and an active matrix type depending on a driving method. Further, a need exists for an organic light emitting display apparatus that has a multi-stack structure for sub-pixels that can allow for individual fine tuning on a per-sub-pixel basis for provided improved viewing angle, enhanced current efficiency, higher luminance,

improved color and luminance uniformity, enhanced lifespan, and robust encapsulation to better protect against moisture penetration.

SUMMARY OF THE DISCLOSURE

[0006] Inventors of the present disclosure developed an organic light emitting diode having a multi-stack structure which uses a stack of a plurality of light emitting portions to implement an improved efficiency and lifespan characteristic of an organic light emitting display apparatus.

[0007] In the organic light emitting diode having a multi-stack structure, an emission area in which light is emitted by recombination of electrons and holes is located in each of the plurality of light emitting portions. Therefore, the organic light emitting diode including a multi-stack structure has a high efficiency and is driven at a low current so that the lifespan of the organic light emitting diode could be improved.

[0008] However, the inventors of the present disclosure recognized that when the organic light emitting diodes including the same structure are applied to all of the plurality of pixels which emit different color light, colors are changed or luminance is changed depending on a viewing angle in a specific pixel. For example, different colored sub-pixel can have different needs and may face different constraints. For example, there was a problem in that an optimized structure could not be applied to the pixels which emit different color light so that a display quality was degraded.

[0009] Accordingly, the inventors of the present disclosure invented an improved organic light emitting display apparatus in which different structures are applied to individual pixels which emit different color light, which can address specific needs for the different colored sub-pixels, on an individual, per-sub-pixel basis.

[0010] An aspect of the present disclosure is to provide an organic light emitting display apparatus which configures a thickness of a first electrode of a first pixel and a thickness of a first electrode of a second pixel to be different from each other to improve a color viewing angle characteristic.

[0011] Another aspect of the present disclosure is to provide an organic light emitting display apparatus which configures a thickness of a first electrode of a second pixel and a thickness of a first electrode of a third pixel to be different from each other to improve a luminance viewing angle characteristic.

[0012] Another aspect of the present disclosure is to provide an organic light emitting display apparatus which improves a display quality while minimizing a photo process.

[0013] Additional features and aspects will be set forth in the description that follows, and in part will be apparent from the description, or can be learned by practice of the inventive concepts provided herein. Other features and aspects of the inventive concepts can be realized and attained by the structure particularly pointed out in the written description, or derivable therefrom, and the claims hereof as well as the appended drawings.

[0014] According to an embodiment of the present disclosure, there is provided an organic light emitting display apparatus. The organic light emitting display apparatus includes a substrate including a plurality of pixels. The organic light emitting display apparatus further includes a plurality of organic light emitting diodes disposed on the substrate to correspond to the plurality of pixels. The plurality of pixels includes a first pixel, a second pixel, a third pixel, and a fourth pixel which emit different color light. Each of the plurality of organic light emitting diodes includes a first electrode, a light emitting portion on the first electrode and a second electrode on the light emitting portion. A thickness of the first electrode of the first pixel is different from a thickness of the first electrode of the second pixel, and the thickness of the first electrode of the second pixel is different from a thickness of the first electrode of the third pixel.

[0015] According to another embodiment of the present disclosure, there is provided an organic light emitting display apparatus. The organic light emitting display apparatus includes a substrate including a plurality of pixels. The organic light emitting display apparatus further includes a plurality of organic light emitting diodes disposed on the substrate to correspond to the plurality of pixels. The plurality of pixels includes a white pixel, a red pixel, a green pixel, and a blue pixel.

Each of the plurality of organic light emitting diodes includes a first electrode, a first light emitting portion which is disposed on the first electrode and includes a blue light emitting layer, a second light emitting portion which is disposed on the first light emitting portion and includes a red light emitting layer and two yellow-green light emitting layers, a third light emitting portion which is disposed on the second light emitting portion and includes a blue light emitting layer and a second electrode on the third light emitting portion. A thickness of the first electrode of the white pixel is different from a thickness of the first electrode of the red pixel, and the thickness of the first electrode of the red pixel is different from a thickness of the first electrode of the green pixel.

[0016] According to another embodiment of the present disclosure, an organic light emitting display apparatus includes a substrate including a plurality of pixels; and a plurality of organic light emitting diodes disposed on the substrate to correspond to the plurality of pixels respectively, in which the plurality of pixels includes a first pixel, a second pixel, a third pixel, and a fourth pixel, and emits different color lights, and each pixel of the plurality of pixels includes a micro cavity structure corresponding to the light emitted from the pixel, each of the plurality of organic light emitting diodes includes a first electrode; a light emitting portion on the first electrode; and a second electrode on the light emitting portion, the micro cavity structure of the first pixel is different from the micro cavity structure of the second pixel, and the micro cavity structure of the second pixel is different from the micro cavity structure of the third pixel.

[0017] Other devices, systems, methods, features and advantages will be, or will become, apparent to one with skill in the art upon examination of the following figures and detailed description. It is intended that all such additional systems, methods, features and advantages be included within this description, be within the scope of the present disclosure, and be protected by the following claims. Nothing in this section should be taken as a limitation on those claims. Further aspects and advantages are discussed below in conjunction with embodiments of the disclosure. It is to be understood that both the foregoing general description and the following detailed description of the present disclosure are examples and explanatory, and are intended to provide further explanation of the disclosure as claimed.

[0018] According to some embodiments of the present disclosure, a thickness of an anode of a white pixel and a thickness of an anode of a red pixel are configured to be different from each other to minimize a color change according to a viewing angle.

[0019] According to some embodiments of the present disclosure, a thickness of an anode of a red pixel and a thickness of an anode of a green pixel are configured to be different from each other to minimize a luminance change according to a viewing angle.

[0020] According to some embodiments of the present disclosure, thicknesses of anodes of pixels which emit different color light are configured to be different from each other with a minimum process to improve a display quality.

[0021] It is to be understood that both the foregoing general description and the following detailed description are examples and explanatory and are intended to provide further explanation of the inventive concepts as claimed.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0022] The accompanying drawings can provide a further understanding of the disclosure and are incorporated in and constitute a part of this specification, and illustrate embodiments of the disclosure and together with the description serve to explain various principles of the disclosure.

[0023] FIG. 1 is a plan view of an organic light emitting display apparatus according to an embodiment of the present disclosure.

[0024] FIG. 2 is a cross-sectional view taken along the line II-II' of FIG. 1 according to an

embodiment of the present disclosure.

[0025] FIG. 3 is a view illustrating a structure of an organic light emitting diode of FIG. 2 according to an embodiment of the present disclosure.

[0026] FIG. 4 is a cross-sectional view of an organic light emitting display apparatus according to an embodiment of the present disclosure.

[0027] FIG. 5 is a graph illustrating a cavity enhancement factor according to a wavelength for every viewing angle according to an embodiment of the present disclosure.

[0028] FIG. 6 is a graph illustrating a luminance according to a viewing angle according to an embodiment of the present disclosure.

[0029] FIG. 7 illustrates a color viewing angle characteristic according to thicknesses of a first electrode of a first pixel and a first hole transport layer according to an embodiment of the present disclosure.

[0030] FIGS. 8A to 8D illustrate a luminance characteristic according to thicknesses of first electrodes and first hole transport layers of a first pixel, a second pixel, a third pixel, and a fourth pixel according to embodiments of the present disclosure.

[0031] FIGS. 9 to 14 are schematic cross-sectional views of an organic light emitting display apparatus according to various example embodiments of the present disclosure.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0032] Advantages and characteristics of the present disclosure and a method of achieving the advantages and characteristics will be clear by referring to example embodiments described below in detail together with the accompanying drawings. However, the present disclosure is not limited to the example embodiments disclosed herein but will be implemented in various forms. The example embodiments are provided by way of example only so that those skilled in the art can fully understand the disclosures of the present disclosure and the scope of the present disclosure. Therefore, the present disclosure will be defined only by the scope of the appended claims.

[0033] The shapes, sizes, ratios, angles, numbers, and the like illustrated in the accompanying drawings for describing the example embodiments of the present disclosure are merely examples, and the present disclosure is not limited thereto. Like reference numerals generally denote like elements throughout the specification. Further, in the following description of the present disclosure, a detailed explanation of known related technologies can be omitted to avoid unnecessarily obscuring the subject matter of the present disclosure. The terms such as “including,” “having,” and “comprising” used herein are generally intended to allow other components to be added unless the terms are used with the term “only.” Any references to singular can include plural unless expressly stated otherwise.

[0034] Components are interpreted to include an ordinary error range even if not expressly stated.

[0035] When the position relation between two parts is described using the terms such as “on,” “above,” “below,” and “next,” one or more parts can be positioned between the two parts unless the terms are used with the term “immediately” or “directly.”

[0036] When an element or layer is disposed “on” another element or layer, another layer (or multiple layers) or another element (or multiple elements) can be interposed directly on the other element or therebetween.

[0037] Although the terms “first,” “second,” and the like are used for describing various components, these components are not confined by these terms. These terms are merely used for distinguishing one component from the other components and may not define any order. Therefore, a first component to be mentioned below can be a second component in a technical concept of the present disclosure.

[0038] Like reference numerals generally denote like elements throughout the specification.

[0039] A size and a thickness of each component illustrated in the drawing are illustrated for convenience of description, and the present disclosure is not limited to the size and the thickness of the component illustrated.

[0040] The features of various embodiments of the present disclosure can be partially or entirely adhered to or combined with each other and can be interlocked and operated in technically various ways, and the embodiments can be carried out independently of or in association with each other. Also, the term “can” used herein includes all meanings and definitions of the term “may.”

[0041] Hereinafter, the present disclosure will be described in detail with reference to accompanying drawings.

[0042] FIG. 1 is a plan view of an organic light emitting display apparatus according to an example embodiment of the present disclosure. FIG. 2 is a cross-sectional view taken along the line II-II' of FIG. 1. All the components of the organic light emitting display apparatus according to all embodiments of the present disclosure are operatively coupled and configured.

[0043] With reference to FIGS. 1 and 2, an organic light emitting display apparatus **100** includes a substrate **110**, a transistor **120**, a color filter **130**, an organic light emitting diode **140**, and an encapsulation substrate **150**.

[0044] The organic light emitting display apparatus **100** can be configured as a bottom emission type. For example, in the organic light emitting display apparatus **100** according to the example embodiment of the present disclosure, light can be emitted to a rear surface of the substrate **110**. According to the bottom emission type, light emitted from the organic light emitting diode **140** is emitted to a lower portion of the substrate **110** on which the organic light emitting diode **140** is formed. According to the bottom emission type, in order to allow light emitted from the organic light emitting diode **140** to travel to a lower portion of the substrate **110**, a first electrode **141** can be formed of a transparent conductive material and a second electrode **143** can be formed of a metal material having a high reflectivity, which will be described below.

[0045] With reference to FIG. 1, the substrate **110** is a substrate which supports and protects several components of the organic light emitting display apparatus **100**. The substrate **110** can be formed of a plastic material having flexibility. Further, since the organic light emitting display apparatus **100** is a bottom emission type, in order to allow the light to travel to a lower portion of the substrate **110**, the substrate **110** can be formed of an insulating material having a transparency. For example, the substrate **110** can be formed of transparent polyimide (PI).

[0046] The substrate **110** includes a display area AA and a non-display area NA.

[0047] The display area AA is disposed at a center portion of the substrate **110** and images are displayed in the display area of the organic light emitting display apparatus **100**. In the display area AA, a display element and various driving elements for driving the display element can be disposed. For example, the display element can be configured by an organic light emitting diode **140** including a first electrode **141**, a light emitting portion **142**, and a second electrode **143**. Further, various driving elements for driving the display element, such as transistors, capacitors, or wiring lines can be disposed in the display area AA.

[0048] A plurality of pixels PX can be included in the display area AA. The plurality of pixels PX can be intersections of a plurality of gate lines disposed in a first direction and a plurality of data lines disposed in a second direction which is different from the first direction. Here, the first direction can be a horizontal direction of FIG. 1 and the second direction can be a vertical direction of FIG. 1, but are not limited thereto. The plurality of pixels PX can include a plurality of first pixels PX1, a plurality of second pixels PX2, a plurality of third pixels PX3, and a plurality of fourth pixels PX4 which emit light having different wavelengths. For example, the plurality of first pixels PX1 can be white pixels, the plurality of second pixels PX2 can be red pixels, the plurality of third pixels PX3 can be green pixels, and the plurality of fourth pixels PX4 can be blue pixels.

[0049] The pixel PX is a minimum unit which configures a screen and each of the plurality of pixels PX can include an organic light emitting diode **140** and a driving element. For example, one pixel PX can include four sub-pixels (e.g., sub-pixels PX1, PX2, PX3, PX4). However, embodiments are not limited thereto and one pixel PX can include fewer than four sub-pixels (e.g., 2 or 3), or more than four sub-pixels. The driving element can include a switching transistor and a

driving transistor. The driving element can be electrically connected to signal lines such as a gate line and a data line which are connected to a gate driver and a data driver disposed in the non-display area NA.

[0050] The non-display area NA is disposed in a peripheral area of the substrate **110** and the non-display area, images are not displayed. The non-display area NA is disposed to enclose the display area AA. Various components for driving a plurality of pixels PX disposed in the display area AA can be disposed in the non-display area NA. For example, a driving integrated circuit (IC), a driving circuit, a signal line, and a flexible film which supply a signal for driving the plurality of pixels PX can be disposed. The driving IC can include a gate driver and a data driver, etc. The driving IC and the driving circuit can be disposed in a gate in panel (GIP) manner, a chip on film (COF) manner, a tape automated bonding (TAB) manner, a tape carrier package (TCP) manner, or a chip on glass (COG) manner, etc.

[0051] Hereinafter, one pixel PX disposed in the display area AA of the organic light emitting display apparatus **100** will be described in more detail with reference to FIG. 2. A cross-sectional view illustrated in FIG. 2 can be a cross-sectional view of a second pixel PX2. However, the structure of FIG. 2 can be applied not only to the second pixel PX2, but also to a third pixel PX3 and a fourth pixel PX4 in the same manner. Further, the same structure as in FIG. 2 can also be applied to the first pixel PX1 except that a color filter **130** is not disposed, but embodiments are not limited thereto (e.g., according to another embodiment the first pixel PX1 may also include a color filter).

[0052] With reference to FIG. 2, a buffer layer **111** is disposed on the substrate **110**. The buffer layer **111** can enhance adhesiveness between layers on the buffer layer **111** and the substrate **110**. Further, the buffer layer **111** can block alkali components discharged from the substrate **110** and suppress diffusion of moisture and/or oxygen which penetrates from the outside of the substrate **110**. The buffer layer **111** can be configured by a single layer or a multi-layer of silicon nitride (SiNx) or silicon oxide (SiOx) but is not limited thereto. Further, the buffer layer **111** can be omitted based on a type and a material of the substrate **110**, and a structure and a type of the transistor **120**.

[0053] The transistor **120** is disposed on the buffer layer **111** to drive the organic light emitting diode **140**. The transistor **120** can be disposed in each of the plurality of pixels of the display area AA. The transistor **120** disposed in each of the plurality of pixels can be used as a driving element of the organic light emitting display apparatus **100**. For example, the transistor **120** can be a thin film transistor (TFT), an N-channel metal oxide semiconductor (NMOS) transistor, a P-channel metal oxide semiconductor (PMOS) transistor, a complementary metal oxide semiconductor (CMOS) transistor, or a field effect transistor FET, but is not limited thereto. Hereinafter, the transistor **120** is assumed as a thin film transistor, but is not limited thereto.

[0054] The transistor **120** includes an active layer **121**, a gate electrode **122**, a source electrode **123**, and a drain electrode **124**. The transistor **120** illustrated in FIG. 2 is a top gate type thin film transistor in which the gate electrode **122** is disposed on the active layer **121**. However, it is not limited thereto and the transistor **120** can be implemented as a bottom gate type thin film transistor.

[0055] The active layer **121** of the transistor **120** is disposed on the buffer layer **111**. When the transistor **120** is driven, a channel is formed in the active layer **121**. The active layer **121** can be formed of an oxide semiconductor or amorphous silicon (a-Si), polycrystalline silicon (poly-Si), or an organic semiconductor, but is not limited thereto.

[0056] A gate insulating layer **112** is disposed on the active layer **121**. The gate insulating layer **112** can be formed as a single layer or a multi-layer of silicon nitride SiNx or silicon oxide SiOx, which is an inorganic material. In the gate insulating layer **112**, a contact hole through which the source electrode **123** and the drain electrode **124** are in contact with a source area and a drain area of the active layer **121**, respectively, is formed. The gate insulating layer **112** can be formed on the entire surface of the substrate **110** as illustrated in FIG. 2, or patterned to have the same width as the gate

electrode **122**, but is not limited thereto.

[0057] The gate electrode **122** is disposed on the gate insulating layer **112**. The gate electrode **122** is disposed on the gate insulating layer **112** to overlap with a channel area of the active layer **121**. The gate electrode **122** can be formed of various metal materials, for example, any one of molybdenum (Mo), aluminum (Al), chrome (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd), and copper (Cu) or an alloy of two or more of them, or a multi-layer thereof, but it is not limited thereto.

[0058] An interlayer insulating layer **113** is disposed on the gate electrode **122**. The interlayer insulating layer **113** can be formed as a single layer or a multi-layer of silicon nitride SiN_x or silicon oxide SiO_x which is an inorganic material. In the interlayer insulating layer **113**, a contact hole through which the source electrode **123** and the drain electrode **124** are in contact with the source area and the drain area of the active layer **121**, respectively, is formed.

[0059] The source electrode **123** and the drain electrode **124** are disposed on the interlayer insulating layer **113**. The source electrode **123** and the drain electrode **124** are electrically connected to the active layer **121** through the contact holes formed in the gate insulating layer **112** and the interlayer insulating layer **113**. The source electrode **123** and the drain electrode **124** can be formed of various metal materials, for example, any one of molybdenum (Mo), aluminum (Al), chrome (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd), and copper (Cu) or an alloy of two or more of them, or a multi-layer thereof. However, the present disclosure is not limited thereto.

[0060] For the convenience of description, in FIG. 2, only a driving transistor among various transistors **120** included in the display apparatus **100** is illustrated, but other transistors such as a switching transistor can also be disposed.

[0061] With reference to FIG. 2, a passivation layer **114** for protecting the transistor **120** is disposed on the transistor **120**. A contact hole which exposes the drain electrode **124** of the transistor **120** is formed on the passivation layer **114**. Even though in FIG. 2, the contact hole which exposes the drain electrode **124** is formed in the passivation layer **114**, a contact hole which exposes the source electrode **123** can also be formed. The passivation layer **114** can be configured as a single layer or a multi-layer of silicon nitride SiN_x or silicon oxide SiO_x. However, the passivation layer **114** can be omitted depending on the example embodiment of the present disclosure.

[0062] The color filter **130** is disposed on the passivation layer **114**. The color filter **130** can be disposed to correspond to an emission area defined by a bank **116**. The color filter **130** converts light emitted from the light emitting portion **142** of the organic light emitting diode **140** into light having a specific color. Since the second pixel PX2 illustrated in FIG. 2 is a red pixel, the color filter **130** can be a red color filter. Further, the third pixel PX3 which is a green pixel includes a green color filter and the fourth pixel PX4 which is a blue pixel includes a blue color filter. White light emitted from the light emitting portion **142** is converted into red light, green light, and blue light by the color filter **130** of the corresponding pixel PX. In the meantime, the color filter **130** may not be disposed in the first pixel PX1 which is a white pixel.

[0063] An over coating layer **115** is disposed on the passivation layer **114** and the color filter **130** to planarize an upper portion of the transistor **120**. A contact hole which exposes the drain electrode **124** of the transistor **120** is formed on the over coating layer **115**. Even though in FIG. 2, the contact hole which exposes the drain electrode **124** is formed in the over coating layer **115**, a contact hole which exposes the source electrode **123** can also be formed. The over coating layer **115** can be formed of any one of acrylic resin, epoxy resin, phenol resin, polyamide resin, polyimide resin, unsaturated polyester resin, polyphenylene resin, polyphenylene sulfide resin, benzocyclobutene, and photoresist, but is not limited thereto.

[0064] With reference to FIG. 2, the organic light emitting diode **140** is disposed on the over coating layer **115**. The organic light emitting diode **140** includes a first electrode **141** which is

formed on the over coating layer **115** to be electrically connected to the drain electrode **124** of the transistor **120**, a light emitting portion **142** disposed on the first electrode **141**, and a second electrode **143** formed on the light emitting portion **142**. Here, the first electrode **141** can be an anode electrode and the second electrode **143** can be a cathode electrode.

[0065] The first electrode **141** is disposed on the over coating layer **115** to be electrically connected to the drain electrode **124** through contact holes formed in the passivation layer **114** and the over coating layer **115**. The first electrode **141** can be formed of a transparent conductive material having a high work function to supply holes to the light emitting portion **142**. For example, the first electrode **141** can be formed of transparent conductive oxide such as indium tin oxide (ITO), indium zinc oxide (IZO), indium tin zinc oxide (ITZO), zinc oxide (ZnO), and tin oxide (TO), but is not limited thereto.

[0066] Even though in FIG. 2, it is illustrated that the first electrode **141** is electrically connected to the drain electrode **124** of the transistor **120** through a contact hole, the first electrode **141** can also be configured to be electrically connected to the source electrode **123** of the transistor **120** through a contact hole by the type of the transistor **120** and a design method of the driving circuit.

[0067] The bank **116** is disposed on the first electrode **141** and the over coating layer **115**. The bank **116** can cover an edge or periphery of the first electrode **141** of the organic light emitting diode **140** to define an emission area. The bank **116** is disposed at the boundary between the adjacent pixels to reduce the color mixture of light emitted from the organic light emitting diode **140** of each of the plurality of pixels. The bank **116** can be formed of an organic material. For example, the bank **116** can be formed of polyimide resin, acrylic resin, or benzocyclobutene resin, but is not limited thereto.

[0068] The light emitting portion **142** is disposed on the first electrode **141**. The light emitting portion **142** can be a white light emitting layer which emits white light, but embodiments are not limited thereto. The white light emitted from the light emitting portion **142** can be converted into any one of red, green, and blue by the color filter **130**. Further, the light emitting portion **142** can further include various layers such as a hole transport layer, a hole injection layer, a hole blocking layer, an electron injection layer, an electron blocking layer, or an electron transport layer, etc. This will be described below with reference to FIG. 3.

[0069] The second electrode **143** is disposed on the light emitting portion **142**. The second electrode **143** supplies electrons to the light emitting portion **142**. The second electrode **143** can be formed of a conductive material having a low work function. For example, the second electrode **143** can be formed of any one or more among opaque conductive metals such as magnesium (Mg), silver (Ag), aluminum (Al), or calcium (Ca) or an alloy thereof, but is not limited thereto.

[0070] With reference to FIG. 2, an encapsulation layer **117** is disposed on the organic light emitting diode **140**. The encapsulation layer **117** can cover the organic light emitting diode **140**. The encapsulation layer **117** can protect the organic light emitting diode **140** from moisture, oxygen, and impacts of the outside. The encapsulation layer **117** can be formed by alternately laminating a plurality of inorganic layers and a plurality of organic layers. For example, the inorganic layer can be formed of an inorganic material such as silicon nitride SiN_x, silicon oxide SiO_x, and aluminum oxide AlO_x and the organic layer can be formed of epoxy or acrylic polymer, but they are not limited thereto.

[0071] The encapsulation substrate **150** is disposed on the encapsulation layer **117**. The encapsulation substrate **150** can protect the organic light emitting diode **140** from moisture, oxygen, and impacts of the outside, together with the encapsulation layer **117**. The encapsulation substrate **150** can be formed of a metal material such as aluminum (Al), nickel (Ni), chrome (Cr), or an alloy material of iron (Fe) and nickel, but is not limited thereto.

[0072] With reference to FIG. 2, an adhesive member **118** is disposed between the encapsulation layer **117** and the encapsulation substrate **150**. The adhesive member **118** can bond the encapsulation layer **117** and the encapsulation substrate **150** to each other. The adhesive member

118 is formed of a material having adhesiveness and can be a thermosetting or natural curable type adhesive. For example, the adhesive member **118** can be formed of an optical clear adhesive (OCA) or a pressure sensitive adhesive (PSA), but is not limited thereto.

[0073] Hereinafter, a structure of the organic light emitting diode **140** according to the example embodiment of the present disclosure will be described in detail with reference to FIG. 3.

[0074] FIG. 3 is a view illustrating a structure of an organic light emitting diode of FIG. 2. A structure of the organic light emitting diode **140** of FIG. 3 can be applied to some or all of the plurality of pixels PX of the organic light emitting display apparatus **100**.

[0075] With reference to FIG. 3, the organic light emitting diode **140** includes a first electrode **141**, a light emitting portion **142**, and a second electrode **143**.

[0076] The light emitting portion **142** is disposed between the first electrode **141** and the second electrode **143**. The light emitting portion **142** is an area where light is emitted by the coupling of electrons and holes supplied from the first electrode **141** and the second electrode **143**. The light emitting portion **142** includes a first light emitting portion **142-1**, a second light emitting portion **142-2**, and a third light emitting portion **142-3**.

[0077] The first light emitting portion **142-1** is disposed on the first electrode **141**. The first light emitting portion **142-1** includes a first hole transport layer **211**, a second hole transport layer **212**, a first light emitting layer **221**, a first electron transport layer **231**, and a first N-type charge generating layer **241**. Since the first light emitting layer **221** is a fluorescent emitting layer, the first light emitting portion **142-1** can be a fluorescent emitting portion. As another example, the first light emitting portion **142-1** may not include the first N-type charge generating layer **241**.

[0078] The first hole transport layer **211** and the second hole transport layer **212** are sequentially disposed on the first electrode **141**. For example, the first hole transport layer **211** and the second hole transport layer **212** are disposed on the first electrode **141**. The first hole transport layer **211** and the second hole transport layer **212** are organic layers which smoothly transmit holes from the first electrode **141** to the first light emitting layer **221**.

[0079] The first hole transport layer **211** can be configured by applying one or more layers or one or more materials. For example, the first hole transport layer **211** and the second hole transport layer **212** can be formed of a material including any one or more of NPD(N,N'-bis(naphthalen-1-yl)-N,N'-bis(phenyl)-2,2'-dimethylbenzidine), NPB(N,N'-bis(naphthalen-1-yl)-N,N'-bis(phenyl)-benzidine), TPD(N,N'-bis-(3-methylphenyl)-N,N'-bis(phenyl)-benzidine), Spiro-TAD(2,2',7,7'-tetrakis(N,N-diphenylamino)-9,9'-spirofluorene), and MTDATA(4,4',4''-Tris(N-3-methylphenyl-N-phenyl-amino)-triphenylamine), but is not limited thereto.

[0080] A thickness of the first hole transport layer **211** can be 100 Å to 2200 Å (e.g., 1150 Å). When the thickness of the first hole transport layer **211** is smaller than 100 Å, the first hole transport layer **211** may not smoothly transmit the holes to the first light emitting layer **221**. When the thickness of the first hole transport layer **211** exceeds 2200 Å, the thickness of the organic light emitting display apparatus **100** can be excessively thick due to the thickness of the first hole transport layer **211**. In this way, the first hole transport layer **211** can be configured to have a thickness of 100 Å to 2200 Å (e.g., 1150 Å), which can optimally balance an ability to provide smooth transmission of holes to the first light emitting layer **221** while being as thin and compact as possible. For example, according to an embodiment, this specific range of thickness can be pivotal for optimally balancing these two conflicting needs for providing good, smooth transmission of holes and being as thin as possible.

[0081] The second hole transport layer **212** can serve as an electron blocking layer EBL. The electron blocking layer is an organic layer which blocks the electrons injected onto the first light emitting layer **221** from passing over the first hole transport layer **211** and the second hole transport layer **212**. The electron blocking layer blocks the movement of the electrons to improve the coupling of the holes and electrons in the first light emitting layer **221** and improve an emission efficiency of the first light emitting layer **221**. The electron blocking layer can be disposed on a

different layer from the second hole transport layer **212**. As another example, the second hole transport layer **212** can be omitted.

[0082] In the first light emitting layer **221**, the holes supplied through the first electrode **141** and the electrons supplied through the second electrode **143** are recombined to generate excitons. Here, an area where the excitons are generated is referred to as an emission area (or emission zone) or a recombination zone.

[0083] The first light emitting layer **221** is disposed between the second hole transport layer **212** and the first electron transport layer **231**. The first light emitting layer **221** which is a fluorescent emitting layer is disposed in the first light emitting portion **142-1** where excitons are formed and includes a material which emits specific color light. The first light emitting layer **221** can include a material which emits blue light.

[0084] The first light emitting layer **221** can have a host-dopant system. For example, the first light emitting layer **221** can have a system in which an emission dopant material having a smaller weight ratio is doped on a host material which occupies a larger weight ratio. The host of the first light emitting layer **221** can be configured by a single material or a mixed host formed of mixed materials. A blue fluorescent dopant material is doped on the first light emitting layer **221** including a single host material or a mixed host material. For example, the first light emitting layer **221** is a blue light emitting layer and a range of a wavelength of light emitted from the first light emitting layer **221** can be 440 nm to 480 nm (e.g., 460 nm).

[0085] The blue fluorescent dopant material is a material which is capable of emitting blue light. An EL spectrum of light emitted from the first light emitting layer **221** on which the blue fluorescent dopant material is doped can have a peak in a blue wavelength region, a peak in a dark blue wavelength region, or a peak in a sky blue wavelength region.

[0086] The host material of the first light emitting layer **221** can be formed by mixing one or more of Alq.sub.3(tris(8-hydroxy-quinolino)aluminum), ADN(9,10-di(naphth-2-yl)anthracene), and BSBF(2-(9,9-spirofluoren-2-yl)-9,9-spirofluorene), but is not limited thereto.

[0087] The blue fluorescent dopant material of the first light emitting layer **221** can be formed of a material having any one or more of a pyrene series material in which an aryl amine-based compound is substituted, an iridium (Ir) ligand complex including FIrPic(bis(3,5-difluoro-2-(2-pyridyl)phenyl-(2-carboxypyridyl)iridium) or Ir(ppy).sub.3(factris(2-phenylpyridine)iridium) (tris(2-phenylpyridine)iridium), spiro-DPVBi, spiro-6P, spiro-BDAVB(2,7-bis[4-(diphenylamino)styryl]-9,9'-spirofluorene), distyryl benzene (DSB), distyryl arylene (DSA), PFO-based polymer, and PPV-based polymer, but is not limited thereto.

[0088] The first electron transport layer **231** is disposed on the first light emitting layer **221**. The first electron transport layer **231** is supplied with electrons from the first N-type charge generating layer **241**. The first electron transport layer **231** can transmit the supplied electrons to the first light emitting layer **221**.

[0089] The first electron transport layer **231** can serve as a hole blocking layer HBL. The hole blocking layer can suppress the holes which do not participate in the recombination from being leaked from the first light emitting layer **221**.

[0090] The first electron transport layer **231** can be formed of any one or more of PBD(2-(4-biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole), TAZ(3-(4-biphenyl)-4-phenyl-5-tert-butylphenyl-1,2,4-triazole), BAlq(Bis(2-methyl-8-quinolinolate)-4-(phenylphenolato)aluminium), Liq(8-hydroxyquinolinolato-lithium), TPBi(2,2',2''-(1,3,5-benzinetriyl)-tris(1-phenyl-1-H-benzimidazole), Liq(8-hydroxyquinolinolato-lithium), and BCP(2,9-Dimethyl-4,7-diphenyl-1,10-phenanthroline), but is not limited thereto.

[0091] The first N-type charge generating layer **241** is disposed on the first electron transport layer **231**. The first N-type charge generating layer **241** injects electrons into the first light emitting portion **142-1**. The first N-type charge generating layer **241** is disposed between the first light emitting portion **142-1** and the second light emitting portion **142-2** adjacent to the first light

emitting portion **142-1** to supply charges to the first light emitting portion **142-1**.

[0092] The first N-type charge generating layer **241** can include an N-type dopant material and an N-type host material. The N-type dopant material can be a metal of Group 1 and Group 2 on the periodic table, an organic material which can inject the electrons, or a mixture thereof. For example, the N-type dopant material can be any one of an alkali metal and an alkaline earth metal. For example, the first N-type charge generating layer **241** can be formed of an organic layer doped with an alkali metal such as lithium (Li), sodium (Na), potassium (K), or cesium (Cs) or an alkali earth metal such as magnesium (Mg), strontium (Sr), barium (Ba), or radium (Ra), but is not limited thereto. The N-type host material can be formed of a material which is capable of transmitting electrons, for example, can be formed of any one or more of Alq.sub.3(tris(8-hydroxyquinolino)aluminum), Liq(8-hydroxyquinolinolato-lithium), PBD(2-(4-biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole), TAZ(3-(4-biphenyl)-4-phenyl-5-tert-butylphenyl-1,2,4-triazole), spiro-PBD, and BAlq(bis(2-methyl-8-quinolinolato)-4-(phenylphenolato)aluminum), SAlq, TPBi(2,2',2''-(1,3,5-benzinetriyl)-tris(1-phenyl-1-H-benzimidazole), oxadiazole, triazole, phenanthroline, benzoxazole, and benzothiazole, but is not limited thereto.

[0093] A thickness of the first light emitting portion **142-1** from which the first hole transport layer **211** is excluded can be 300 Å to 900 Å (e.g., 600 Å). For example, a total thickness the first light emitting portion **142-1** (e.g., 400 Å to 3100 Å, such as 1750 Å) minus a thickness of the first hole transport layer **211** (e.g., 100 Å to 2200 Å, such as 1150 Å) can be 300 Å to 900 Å (e.g., 600 Å). For example, 1750 Å minus 1150 Å equals 600 Å, as a non-limiting example. In this way, an optimal ratio of thickness due to the first hole transport layer **211** to a total thickness first light emitting portion **142-1** can be provided (e.g., a ratio of 1:3 or approximately 1:3, or according to embodiments 12:35 or 17:50), in order to optimally balance the needs of providing proper, smooth transmission of holes while also being as thin as possible. For example, the thickness due to the first hole transport layer **211** can make up about 1/3 of the total thickness of the first light emitting portion **142-1**. Since the thickness of the first hole transport layer **211** is 100 Å to 2200 Å (e.g., 1150 Å), a total thickness of the first light emitting portion **142-1** can be 400 Å to 3100 Å (e.g., 1750 Å). Further, a distance between a center of the first light emitting layer **221** and a first surface of the second electrode **143** can be 2500 Å to 3100 Å (e.g., 2800 Å).

[0094] The second light emitting portion **142-2** is disposed on the first light emitting portion **142-1**. The second light emitting portion **142-2** includes a first P-type charge generating layer **242**, a third hole transport layer **213**, a second light emitting layer **222**, a third light emitting layer **223**, a fourth light emitting layer **224**, a second electron transport layer **232**, and a second N-type charge generating layer **243**. Since the second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** are phosphorescent emitting layers, the second light emitting portion **142-2** can be a phosphorescent emitting portion. As another example, the second light emitting portion **142-2** may not include the first P-type charge generating layer **242** and the second N-type charge generating layer **243**.

[0095] The first P-type charge generating layer **242** is disposed on the first N-type charge generating layer **241**. The first P-type charge generating layer **242** injects holes into the second light emitting portion **142-2**. The first P-type charge generating layer **242** is disposed between the first light emitting portion **142-1** and the second light emitting portion **142-2** which are adjacent to each other to supply charges to the second light emitting portion **142-2**.

[0096] The first P-type charge generating layer **242** can include a P-type dopant material and a P-type host material. The P-type dopant material can be formed of metal oxide, an organic material such as tetrafluoro-tetracyanoquinodimethane (F4-TCNQ), HAT-CN (Hexaazatriphenylene-hexacarbonitrile), or hexaazatriphenylene, or a metal material such as V.sub.2O.sub.5, MoOx, and WO.sub.3, but is not limited thereto. The P-type host material can be formed of a material which is capable of transmitting holes, for example, can be formed of a material including any one or more of NPD(N,N-dinaphthyl-N,N'-diphenyl benzidine)(N,N'-bis(naphthalene-1-yl)-N,N'-

bis(phenyl)-2,2'-dimethylbenzidine), TPD(N,N'-bis-(3-methylphenyl)-N,N'-bis-(phenyl)-benzidine), and MTDATA(4,4',4''-Tris(N-3-methylphenyl-N-phenyl-amino)-triphenylamine), but is not limited thereto.

[0097] The third hole transport layer **213** is disposed on the first P-type charge generating layer **242**. The third hole transport layer **213** is an organic layer which smoothly transmits holes from the first P-type charge generating layer **242** to the second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224**. The third hole transport layer **213** is substantially the same as the first hole transport layer **211** and the second hole transport layer **212** of the first light emitting portion **142-1**, so that a redundant description will be omitted.

[0098] The second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** are sequentially disposed between the third hole transport layer **213** and the second electron transport layer **232**. For example, the second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** are disposed between the third hole transport layer **213** and the second electron transport layer **232**. The second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** which are phosphorescent emitting layers are disposed in the second light emitting portion **142-2** where excitons are formed and include a material which emits specific color light. The second light emitting layer **222** includes a material which emits red light and the third light emitting layer **223** and the fourth light emitting layer **224** include a material which emits yellow-green light. The fourth light emitting layer **224** can be omitted. For example, the fourth light emitting layer **224** can include a material which emits green light. For example, the second light emitting portion **142-2** can be configured by the second light emitting layer **222** and the third light emitting layer **223**.

[0099] The second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** can have a host-dopant system, similar to the first light emitting layer **221**. Each of the second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** can include a single host or a mixed host and at least one dopant. When the second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** include a mixed host, the mixed host can include a hole-type host and an electron-type host. When the second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** are configured by the mixed host or pre-mixed host, the host can be uniformly deposited in the light emitting layer so that the efficiency of the light emitting layer can be improved.

[0100] The second light emitting layer **222** which is a phosphorescent emitting layer can include a first hole-type host and a first electron-type host and the second light emitting layer **222** is doped with a red phosphorescent dopant material. For example, the second light emitting layer **222** is a red light emitting layer and a range of a wavelength of light emitted from the second light emitting layer **222** can be 600 nm to 650 nm (e.g., 625 nm).

[0101] The red phosphorescent dopant material is a material which is capable of emitting red light. An EL spectrum of light emitted from the second light emitting layer **222** doped with the red phosphorescent dopant material can have a peak in a red wavelength range. The host material of the second light emitting layer **222** can be formed by mixing one or more of CBP(4,4'-bis(carbazol-9-yl)biphenyl) and MCP(1,3-bis(carbazol-9-yl)benzene) but is not limited thereto.

[0102] The red phosphorescent dopant material of the second light emitting layer **222** can be formed of a material including any one or more of an iridium (Ir) ligand complex including Ir(ppy).sub.3(tris(2-phenylpyridine)iridium(III)), Ir(ppy).sub.2(acac)(Bis(2-phenylpyridine)(acetylacetonato)iridium(III)), PIQIr(acac)(bis(1-phenylisoquinoline) acetylacetonate iridium), PQIr(acac)(bis(1-phenylquinoline) acetylacetonate iridium), PQIr(tris(1-phenylquinoline) iridium), Ir(piq).sub.3(tris(1-phenylisoquinoline)iridium), Ir(piq).sub.2(acac)(bis(1-phenylisoquinoline)(acetylacetonate)iridium), PtOEP(octaethylporphyrinporphine platinum) PBD:Eu(DBM).sub.3(Phen), and perylene, but is not limited thereto.

[0103] Each of the third light emitting layer **223** and the fourth light emitting layer **224** includes the same second hole-type host and second electron-type host. However, a ratio of the second hole-type host and the second electron-type host can be different in each light emitting layer.

[0104] For example, the third light emitting layer **223** is disposed to be closer to the first electrode **141** which supplies holes, than the fourth light emitting layer **224** and the fourth light emitting layer **224** is disposed to be closer to the second electrode **143** which supplies electrons, than the third light emitting layer **223**. In the third light emitting layer **223**, a ratio of the second electron-type host can be higher to be smoothly supplied with the electrons and in the fourth light emitting layer **224**, a ratio of the second hole-type host can be higher to be smoothly supplied with the holes.

Accordingly, the ratio of the second-hole type host and the second electron-type host can vary depending on a type of carrier which is relatively hard to reach each light emitting layer.

[0105] The third light emitting layer **223** and the fourth light emitting layer **224** are phosphorescent emitting layers and are doped with a yellow-green phosphorescent dopant material. For example, the third light emitting layer **223** and the fourth light emitting layer **224** can be yellow-green light emitting layers and a range of the wavelength of light emitted from the third light emitting layer **223** and the fourth light emitting layer **224** can be 510 nm to 590 nm.

[0106] The yellow-green phosphorescent dopant material is a material which is capable of emitting light having a wavelength of a yellow-green region. The EL spectrum of light emitted from the third light emitting layer **223** and the fourth light emitting layer **224** doped with the yellow-green dopant material has a peak in the yellow-green wavelength region or has a first peak in a yellow-green wavelength region and a second peak which is lower than the first peak in the red wavelength region. Alternatively, the EL spectrum can have a first peak in the yellow-green wavelength region and a point of inflection between the yellow-green wavelength region and the red wavelength region.

[0107] The host material of the third light emitting layer **223** and the fourth light emitting layer **224** can be formed by mixing one or more of CBP(4,4'-bis(carbazol-9-yl)biphenyl) and MCP(1,3-bis(carbazol-9-yl)benzene) but is not limited thereto.

[0108] A yellow-green dopant material of the third light emitting layer **223** and the fourth light emitting layer **224** can be formed of a material including any one or more selected from a group consisting of an iridium (Ir) ligand complex including Ir(ppy).sub.3(tris(2-phenylpyridine)iridium(III)) or Ir(ppy).sub.2(acac)(Bis(2-phenylpyridine)(acetylacetonato)iridium(III)) or Alq.sub.3(tris(8-hydroxyquinolino)aluminum), but is not limited thereto.

[0109] A range of the wavelength of the second light emitting portion **142-2** including the second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224** can be 510 nm to 650 nm (e.g., 580 nm). For example, a range of the wavelength of the second light emitting layer **222** which is a red light emitting layer is 600 nm to 650 nm (e.g., 625 nm). Further, when the yellow-green dopant material has a peak in the yellow-green wavelength region, the range of the wavelength of the third light emitting layer **223** and the fourth light emitting layer **224**, which are the yellow-green light emitting layers, can be 510 nm to 590 nm (e.g., 550 nm). Therefore, the range of the wavelength of the second light emitting portion **142-2** can be a minimum of 510 nm to a maximum of 650 nm (e.g., 580 nm).

[0110] The second electron transport layer **232** is disposed on the fourth light emitting layer **224**. The second electron transport layer **232** is supplied with electrons from the second N-type charge generating layer **243**. The second electron transport layer **232** transmits the supplied electrons to the second light emitting layer **222**, the third light emitting layer **223**, and the fourth light emitting layer **224**. The second electron transport layer **232** is substantially the same as the first electron transport layer **231** of the first light emitting portion **142-1**, so that a redundant description will be omitted.

[0111] The second N-type charge generating layer **243** is disposed on the second electron transport

layer **232**. The second N-type charge generating layer **243** injects electrons into the second light emitting portion **142-2**. The second N-type charge generating layer **243** is disposed between the second light emitting portion **142-2** and the third light emitting portion **142-3** which are adjacent to each other to supply charges to the second light emitting portion **142-2**. The second N-type charge generating layer **243** is substantially the same as the first N-type charge generating layer **241** of the first light emitting portion **142-1**, so that a redundant description will be omitted.

[0112] A total thickness of the second light emitting portion **142-2** can be 750 Å to 1350 Å (e.g., 1050 Å). Further, a distance between a center of the second light emitting layer **222** and the first surface of the second electrode **143** can be 2000 Å to 2600 Å (e.g., 2300 Å). A distance between a boundary of the third light emitting layer **223** and the fourth light emitting layer **224** which is the center of the third light emitting layer **223** and the fourth light emitting layer **224** and the first surface of the second electrode **143** can be 1700 Å to 2300 Å (e.g., 2000 Å).

[0113] The third light emitting portion **142-3** is disposed on the second light emitting portion **142-2**. The third light emitting portion **142-3** includes a second P-type charge generating layer **244**, a fourth hole transport layer **214**, a fifth hole transport layer **215**, a fifth light emitting layer **225**, a third electron transport layer **233**, and an electron injection layer **251**. Since the fifth light emitting layer **225** is a fluorescent emitting layer, the third light emitting portion **142-3** can be as a fluorescent emitting portion. As another example, the third light emitting portion **142-3** may not include the second P-type charge generating layer **244**.

[0114] The second P-type charge generating layer **244** is disposed on the second N-type charge generating layer **243**. The second P-type charge generating layer **244** injects holes into the third light emitting portion **142-3**. The second P-type charge generating layer **244** is disposed between the second light emitting portion **142-2** and the third light emitting portion **142-3** which are adjacent to each other to supply charges to the third light emitting portion **142-3**. The second P-type charge generating layer **244** is substantially the same as the first P-type charge generating layer **242** of the second light emitting portion **142-2**, so that a redundant description will be omitted.

[0115] The fourth hole transport layer **214** and the fifth hole transport layer **215** are sequentially disposed on the second P-type charge generating layer **244**. The fourth hole transport layer **214** and the fifth hole transport layer **215** are organic layers which smoothly transmit holes from the second P-type charge generating layer **244** to the fifth light emitting layer **225**. The fourth hole transport layer **214** and the fifth hole transport layer **215** are substantially the same as the first hole transport layer **211** and the second hole transport layer **212** of the first light emitting portion **142-1**, so that a redundant description will be omitted.

[0116] The fifth light emitting layer **225** is disposed between the fifth hole transport layer **215** and the third electron transport layer **233**. The fifth light emitting layer **225** is disposed in the third light emitting portion **142-3** where excitons are formed and includes a material which emits specific color light. For example, the fifth light emitting layer **225** can include a material which emits blue light. The fifth light emitting layer **225** is substantially the same as the first light emitting layer **221** of the first light emitting portion **142-1**, so that a redundant description will be omitted.

[0117] The third electron transport layer **233** is disposed on the fifth light emitting layer **225**. The third electron transport layer **233** is supplied with electrons from the second electrode **143**. The third electron transport layer **233** transmits the supplied electrons to the fifth light emitting layer **225**. The third electron transport layer **233** is substantially the same as the first electron transport layer **231** of the first light emitting portion **142-1**, so that a redundant description will be omitted.

[0118] The electron injection layer **251** is disposed on the third electron transport layer **233**. The electron injection layer **251** is an organic layer which smoothly injects the electrons from the second electrode **143** to the fifth light emitting layer **225**. The electron injection layer **251** can be formed of a material including any one or more of LIF, Al, MoO₃, LiQ(lithium quinolate), Alq₃(tris(8-hydroxyquinolino)aluminum), PBD, TAZ, spiro-PBD, BAq, or SAq, but is not limited thereto. The electron injection layer **251** can be omitted.

[0119] A total thickness of the third light emitting portion **142-3** can be 1200 Å to 1800 Å (e.g., 1500 Å). Further, a distance between a center of the fifth light emitting layer **225** and the first surface of the second electrode **143** can be 100 Å to 700 Å (e.g., 400 Å).

[0120] The organic light emitting diode **140** is an organic light emitting diode **140** having a three stack structure in which the first light emitting portion **142-1**, the second light emitting portion **142-2**, and the third light emitting portion **142-3** are laminated. Light which is finally emitted from the light emitting portion **142** can be implemented by mixing light emitted from the first light emitting portion **142-1**, the second light emitting portion **142-2**, and the third light emitting portion **142-3**. Accordingly, a design in the light emitting portion **142** can vary depending on a color of light to be implemented. For example, the first light emitting portion **142-1** and the third light emitting portion **142-3** which are fluorescent emitting portions emit blue light and the second light emitting portion **142-2** which is a phosphorescent emitting portion emits red light and yellow-green light. Therefore, the organic light emitting diode **140** according to the example embodiment of the present disclosure can be an organic light emitting diode **140** which emits white light.

[0121] FIG. **4** is a schematic cross-sectional view of an organic light emitting display apparatus according to an example embodiment of the present disclosure. In FIG. **4**, for the convenience of description, only the substrate **110** and organic light emitting diodes **140A**, **140B**, **140C**, and **140D** disposed on the substrate **110** of the organic light emitting display apparatus **100** of FIG. **2** are illustrated. The configuration of the organic light emitting diodes **140A**, **140B**, **140C**, and **140D** can be the same as the organic light emitting diode **140** illustrated in FIG. **3**.

[0122] With reference to FIG. **4**, the organic light emitting display apparatus **100** according to the example embodiment of the present disclosure includes a first organic light emitting diode **140A** corresponding to the first pixel PX**1**, a second organic light emitting diode **140B** corresponding to the second pixel PX**2**, a third organic light emitting diode **140C** corresponding to the third pixel PX**3**, and a fourth organic light emitting diode **140D** corresponding to the fourth pixel PX**4**. For example, the first pixel PX**1** can be a white pixel, the second pixel PX**2** can be a red pixel, the third pixel PX**3** can be a green pixel, and the fourth pixel PX**4** can be a blue pixel. Light emitted from the first organic light emitting diode **140A** is white light, white light emitted from the second organic light emitting diode **140B** can be converted into red light by the color filter **130**. The white light emitted from the third organic light emitting diode **140C** can be converted into green light by the color filter **130** and the white light emitted from the fourth organic light emitting diode **140D** can be converted into blue light by the color filter **130**.

[0123] The first organic light emitting diode **140A** includes a first electrode **141A**, a light emitting portion **142A**, and a second electrode **143A**. The second organic light emitting diode **140B** includes a first electrode **141B**, a light emitting portion **142B**, and a second electrode **143B**. The third organic light emitting diode **140C** includes a first electrode **141C**, a light emitting portion **142C**, and a second electrode **143C**. The fourth organic light emitting diode **140D** includes a first electrode **141D**, a light emitting portion **142D**, and a second electrode **143D**. The light emitting portions **142A**, **142B**, **142C**, and **142D** of the first organic light emitting diode **140A**, the second organic light emitting diode **140B**, the third organic light emitting diode **140C**, and the fourth organic light emitting diode **140D** can have the same configuration. Further, the second electrodes **143A**, **143B**, **143C**, and **143D** of the first organic light emitting diode **140A**, the second organic light emitting diode **140B**, the third organic light emitting diode **140C**, and the fourth organic light emitting diode **140D** can have the same configuration. For example, only the thicknesses of the first electrodes **141A**, **141B**, **141C**, and **141D** of the first organic light emitting diode **140A**, the second organic light emitting diode **140B**, the third organic light emitting diode **140C**, and the fourth organic light emitting diode **140D** can be different.

[0124] The first pixel PX**1**, the second pixel PX**2**, the third pixel PX**3**, and the fourth pixel PX**4** can have a micro cavity structure corresponding to light emitted from the corresponding pixel PX. According to the micro cavity structure, light is repeatedly reflected between the first electrode **141**

and the second electrode **143** which are spaced apart from each other with an optical length therebetween so that light of a specific wavelength is amplified by the constructive interference. For example, this microcavity effect in each subpixel utilize the space between a reflective rear electrode and a semi-transparent front electrode to form an optical resonant cavity. By precisely and independently adjusting this distance (e.g., cavity length) for each white, red, green, and blue subpixel, the display device can be fine-tuned to selectively enhance the emission of each color's wavelength through constructive interference, while suppressing other wavelengths. In this way, the targeted resonance can amplify the intensity of the specific color, leading to improved brightness and efficiency, and also narrows its emission spectrum to provide higher color purity and a wider overall color gamut. Therefore, the second pixel **PX2** can have a micro cavity structure in which light of a wavelength corresponding to red can be amplified. The third pixel **PX3** can have a micro cavity structure in which light of a wavelength corresponding to green can be amplified. The fourth pixel **PX4** can have a micro cavity structure in which light of a wavelength corresponding to blue can be amplified.

[0125] The micro cavity can be implemented by the thickness of the first electrode **141** which is a transparent conductive material and a refractive index difference between the first electrode **141** and the first hole transport layer **211**. For example, when the first electrode **141** is formed of indium zinc oxide, the first electrode **141** has a larger refractive index so that a refractive index difference between the first electrode **141** and the first hole transport layer **211** can be increased. Therefore, more light can be reflected by the first electrode **141** so that the light can be more efficiently amplified. Further, in order to implement optimized micro cavity effect for each of the first pixel **PX1**, the second pixel **PX2**, the third pixel **PX3**, and the fourth pixel **PX4**, the thickness of the first electrode **141** for every pixel can be formed to be different from each other.

[0126] To improve the color viewing angle characteristic, the thickness of the first electrode **141A** of the first organic light emitting diode **140A** can be configured to be different from the thickness of the first electrode **141B** of the second organic light emitting diode **140B**. For example, the same micro cavity structure may not be applied to the first pixel **PX1** and the second pixel **PX2**. That is to say, different micro cavity structures can be applied to the first pixel **PX1** and the second pixel **PX2**. For example, when the thickness of the first electrode **141A** and the thickness of the first electrode **141B** are equal to each other, the color of the first pixel **PX1** can be changed according to a viewing angle. Therefore, the thickness of the first electrode **141A** and the thickness of the first electrode **141B** are set to be different from each other to minimize the color change according to the viewing angle of the organic light emitting display apparatus **100**.

[0127] Here, the color viewing angle refers to a changing degree of white in accordance with the change of the viewing angle as compared with white on a front surface in a state in which a screen of the display apparatus is set to be white having a color temperature of 10,000 K. When the changing degree of white in accordance with the change of the viewing angle is small, the color viewing angle characteristic is good and when the changing degree of white in accordance with the change of the viewing angle is large, the color viewing angle characteristic is not good.

[0128] To improve the luminance viewing angle characteristic, the thickness of the first electrode **141B** of the second organic light emitting diode **140B** can be formed to be different from the thickness of the first electrode **141C** of the third organic light emitting diode **140C**. For example, the same micro cavity structure may not be applied to the second pixel **PX2** and the third pixel **PX3**. That is to say, different micro cavity structures can be applied to the second pixel **PX2** and the third pixel **PX3**. For example, when the thickness of the first electrode **141B** and the thickness of the first electrode **141C** are equal to each other, the luminance of the second pixel **PX2** can be changed according to the viewing angle. Therefore, the thickness of the first electrode **141B** and the thickness of the first electrode **141C** are set to be different from each other to minimize the luminance change according to the viewing angle of the organic light emitting display apparatus **100**.

[0129] Here, the luminance viewing angle refers to a reducing degree of the luminance according to the viewing angle. When the changing degree of luminance in accordance with the change of the viewing angle is small, the luminance viewing angle characteristic is good and when the changing degree of luminance in accordance with the change of the viewing angle is large, the luminance viewing angle characteristic is not good.

[0130] Hereinafter, a color change characteristic and a luminance change characteristic according to the viewing angle will be described with reference to FIGS. 5 and 6.

[0131] FIG. 5 is a graph illustrating a cavity enhancement factor according to a wavelength for every viewing angle. In FIG. 5, a micro cavity structure of the second pixel PX2 is applied to the first pixel PX1. For example, FIG. 5 is a graph measured by applying a thickness of the first electrode **141A** of the first pixel PX1 to be 400 Å and a thickness of the first hole transport layer **211** to be 500 Å. The graph of FIG. 5 was measured at viewing angles of 0°, 15°, 30°, 45°, and 60°.

[0132] A cavity enhancement factor represents a ratio of a power when exciton is in the organic light emitting diode **140** to a power (assumed to be 1) when exciton is in the air. The power when the exciton is in the air refers to a power when the micro cavity is not applied. For example, the cavity enhancement factor can refer to an amplification ratio of light by the micro cavity.

[0133] With reference to FIG. 5, it is confirmed that a peak of the cavity enhancement factor varies according to the viewing angle. For example, since the distance of the micro cavity varies in accordance with the viewing angle, the peak to be amplified can vary. It is confirmed that a peak at approximately 650 nm which is a red R region and a peak at approximately 470 nm which is a blue B region are sharply reduced as the viewing angle is increased. For example, the peak in the red R region can be shifted to the blue B region. However, it is confirmed that the cavity enhancement factor at approximately 550 nm which is a green G region is maintained at a constant level even though the viewing angle is increased. For example, the larger the viewing angle, the smaller the cavity enhancement factor of the red R region and the blue B region, but the cavity enhancement factor in the green G region is maintained. Accordingly, the amplification degree of light in the green G region is relatively increased so that the white light emitted from the first pixel PX1 can be greenish. In other words, the color of the white light of the first pixel PX1 varies according to the viewing angle, so that the color viewing angle characteristic can be degraded. As a result, when the thickness of the first electrode **141A** of the first pixel PX1 and the thickness of the first electrode **141B** of the second pixel PX2 are configured to be different, the color viewing angle characteristic can be improved.

[0134] FIG. 6 is a graph illustrating a luminance according to a viewing angle. FIG. 6 was measured under the same condition as FIG. 5. A normalized intensity of FIG. 6 can refer to a luminance.

[0135] With reference to FIG. 6, it is confirmed that as the viewing angle Angle is increased, the luminance of the red R light is reduced, but the luminance of the green G light is maintained at a constant level. For example, the larger the viewing angle, the larger the luminance of the green G light, relatively, so that the luminance deviation of the red R light and the green G light can be increased. Accordingly, as the viewing angle is increased, the white light can be green color. In other words, the luminance of the white light is changed in accordance with the viewing angle, so that the luminance viewing angle characteristic can be degraded. For example, the luminance deviation of the red R light and the green G light is increased according to the viewing angle, so that the thickness of the first electrode **141B** of the second pixel PX2 and the thickness of the first electrode **141C** of the third pixel PX3 can be configured to be different.

[0136] Hereinafter, a thickness of the first electrode will be described with reference to FIGS. 7 to 8D.

[0137] FIG. 7 illustrates a color viewing angle characteristic according to thicknesses of a first electrode and a first hole transport layer of a first pixel. FIGS. 8A to 8D illustrate a luminance characteristic according to thicknesses of first electrodes and first hole transport layers of a first

pixel, a second pixel, a third pixel, and a fourth pixel. An X-axis of FIGS. 7 to 8D refers to a thickness of the first electrode and a Y-axis refers to a thickness of the first hole transport layer. The larger the value of $\Delta u'v'$ of FIG. 7, the worse the color viewing angle characteristic. The larger the value of cdm.sup.-2 of FIGS. 8A to 8D, the worse the luminance viewing angle characteristic. [0138] With reference to FIGS. 7 and 8A, it is confirmed that when the thickness range of the first hole transport layer **211** of the first pixel **PX1** is 100 Å to 1000 Å, the first electrode **141A** has excellent color viewing angle characteristic and luminance viewing angle characteristic in a thickness range of 200 Å to 1600 Å or 2000 Å to 2400 Å. Further, when the thickness range of the first hole transport layer **211** of the first pixel **PX1** is 1000 Å to 2200 Å, the first electrode **141A** can have excellent color viewing angle characteristic and luminance viewing angle characteristic in a thickness range of 100 Å to 600 Å or 1000 Å to 1800 Å.

[0139] With reference to FIG. 8B, when a thickness range of the first hole transport layer **211** of the second pixel **PX2** is 100 Å to 1000 Å, a thickness range of the first electrode **141B** can be 200 Å to 1000 Å or 1700 Å to 2400 Å (e.g., 2050 Å). When a thickness range of the first hole transport layer **211** of the second pixel **PX2** is 1000 Å to 2200 Å, a thickness range of the first electrode **141B** can be 200 Å to 1200 Å or 1600 Å to 2400 Å. The second pixel **PX2** can have excellent luminance characteristic in the above-described range.

[0140] With reference to FIG. 8C, when a thickness range of the first hole transport layer **211** of the third pixel **PX3** is 100 Å to 1000 Å, a thickness range of the first electrode **141C** can be 800 Å to 1600 Å. When a thickness range of the first hole transport layer **211** of the third pixel **PX3** is 1000 Å to 2200 Å, a thickness range of the first electrode **141C** can be 100 Å to 600 Å or 1200 Å to 2200 Å. The third pixel **PX3** can have excellent luminance characteristic in the above-described range.

[0141] With reference to FIG. 8D, when a thickness range of the first hole transport layer **211** of the fourth pixel **PX4** is 100 Å to 1000 Å, a thickness range of the first electrode **141D** can be 200 Å to 1000 Å, or 1200 Å to 2000 Å, or 2200 Å to 2400 Å. When a thickness range of the first hole transport layer **211** of the fourth pixel **PX4** is 1000 Å to 2200 Å, a thickness range of the first electrode **141D** can be 100 Å to 600 Å or 1200 Å to 2000 Å. The fourth pixel **PX4** can have excellent luminance characteristic in the above-described range.

[0142] The thicknesses of the first electrode **141A** of the first pixel **PX1**, the first electrode **141B** of the second pixel **PX2**, the first electrode **141C** of the third pixel **PX3**, and the first electrode **141D** of the fourth pixel **PX4** can be set in the above-described range. The thickness of the first electrode **141A** of the first organic light emitting diode **140A** can be set to be different from the thickness of the first electrode **141B** of the second organic light emitting diode **140B**. The thickness of the first electrode **141B** of the second organic light emitting diode **140B** can be set to be different from the thickness of the first electrode **141C** of the third organic light emitting diode **140C**.

[0143] With reference to FIG. 4 again, the thickness of the first electrode **141A** of the first pixel **PX1** can be equal to the thickness of the first electrode **141C** of the third pixel **PX3** (e.g., thickness of **141A** equal to or approximately equal to thickness of **141C**). The thickness of the first electrode **141B** of the second pixel **PX2** can be equal to the thickness of the first electrode **141D** of the fourth pixel **PX4** (e.g., thickness of **141B** equal to or approximately equal to thickness of **141D**). For example, the first electrodes **141A**, **141B**, **141C**, and **141D** of the organic light emitting display apparatus **100** can be formed by performing a photo process two times. Therefore, the photo process for forming the first electrodes **141A**, **141B**, **141C**, and **141D** is minimized and the color change and the luminance change according to the viewing angle are also minimized.

[0144] In the meantime, even though in FIG. 4, it is illustrated that the thicknesses of the first electrode **141A** of the first pixel **PX1** and the first electrode **141C** of the third pixel **PX3** are larger than the thicknesses of the first electrode **141B** of the second pixel **PX2** and the first electrode **141D** of the fourth pixel **PX4**, the present disclosure is not limited thereto. For example, the thicknesses of the first electrode **141A** of the first pixel **PX1** and the first electrode **141C** of the

third pixel PX3 can be smaller than the thicknesses of the first electrode **141B** of the second pixel PX2 and the first electrode **141D** of the fourth pixel PX4.

[0145] In the organic light emitting display apparatus, anodes of a white pixel, a red pixel, a green pixel, and a blue pixel which emit different color light are formed to have the same thickness. For example, the same micro cavity structure is applied to each pixel. In this situation, color of light emitted from the white pixel is changed according to the viewing angle so that there is a problem in that the color viewing angle characteristic is degraded. Further, luminance of light emitted from the red pixel, the green pixel, or the blue pixel is changed according to the viewing angle so that there is a problem in that the luminance viewing angle characteristic is degraded.

[0146] The organic light emitting display apparatus **100** according to an example embodiment of the present disclosure adjusts the thickness of the first electrode **141** of each of the first pixel PX1, the second pixel PX2, the third pixel PX3, and the fourth pixel PX4 which emit different color light. Therefore, the color viewing angle characteristic and the luminance viewing angle characteristic can be improved. For example, the thickness of the first electrode **141A** of the first pixel PX1 which is a white pixel and the thickness of the first electrode **141B** of the second pixel PX2 which is a red pixel are configured to be different from each other, so that the color viewing angle characteristic can be improved. Further, the thickness of the first electrode **141B** of the second pixel PX2 which is a red pixel and the thickness of the first electrode **141C** of the third pixel PX3 which is a green pixel are configured to be different from each other, so that the luminance viewing angle characteristic can be improved.

[0147] Further, the thicknesses of the first electrode **141A** of the first pixel PX1 and the first electrode **141C** of the third pixel PX3 can be configured to be equal to each other and the thicknesses of the first electrode **141B** of the second pixel PX2 and the first electrode **141D** of the fourth pixel PX4 can be configured to be equal to each other. Accordingly, the first electrode **141A** of the first pixel PX1 and the first electrode **141C** of the third pixel PX3 can be simultaneously formed and the first electrode **141B** of the second pixel PX2 and the first electrode **141D** of the fourth pixel PX4 can be simultaneously formed. For example, the first electrodes **141** of the organic light emitting display apparatus **100** can be formed by performing the photo process two times. In other words, the first electrode **141A** of the first pixel PX1 and the first electrode **141C** of the third pixel PX3 can be formed during the same processing step, and the first electrode **141B** of the second pixel PX2 and the first electrode **141D** of the fourth pixel PX4 can be formed during the same processing step. Accordingly, the photo process can be minimized and a micro cavity structure optimized for every pixel PX1, PX2, PX3, PX4 can also be applied. For example, the manufacturing steps can be reduced, which improves manufacturing efficiency and reduces the risk of introducing defects since each additional processing step adds an additional variable or risk to consider. Thus, a higher yield of defect-free displays can be produced in less time.

[0148] FIG. **9** is a schematic cross-sectional view of an organic light emitting display apparatus according to another example embodiment of the present disclosure. An organic light emitting display apparatus **900** of FIG. **9** is substantially the same as the organic light emitting display apparatus **100** of FIG. **4** except for a thickness relationship of a first electrode **941A** of a first pixel PX1, a first electrode **941B** of a second pixel PX2, a first electrode **941C** of a third pixel PX3, and a first electrode **941D** of a fourth pixel PX4 so that a redundant description will be omitted.

[0149] With reference to FIG. **9**, the organic light emitting display apparatus **900** includes a first organic light emitting diode **940A** corresponding to the first pixel PX1, a second organic light emitting diode **940B** corresponding to the second pixel PX2, a third organic light emitting diode **940C** corresponding to the third pixel PX3, and a fourth organic light emitting diode **940D** corresponding to the fourth pixel PX4. For example, the first pixel PX1 can be a white pixel, the second pixel PX2 can be a red pixel, the third pixel PX3 can be a green pixel, and the fourth pixel PX4 can be a blue pixel. For example, light emitted from the first organic light emitting diode

940A is white light, white light emitted from the second organic light emitting diode **940B** can be converted into red light by the color filter **130**. The white light emitted from the third organic light emitting diode **940C** can be converted into green light by the color filter **130** and the white light emitted from the fourth organic light emitting diode **940D** can be converted into blue light by the color filter **130**.

[0150] A thickness of the first electrode **941A** of the first pixel **PX1** can be different from a thickness of the first electrode **941B** of the second pixel **PX2**. The thickness of the first electrode **941A** of the first pixel **PX1**, a thickness of the first electrode **941C** of the third pixel **PX3**, and a thickness of the first electrode **941D** of the fourth pixel **PX4** can be equal to one another. For example, the thickness of the first electrode **941A** of the first pixel **PX1** and the thickness of the first electrode **941B** of the second pixel **PX2** are configured to be different, so that the color viewing angle characteristic of the organic light emitting display apparatus **900** can be improved. Further, the thickness of the first electrode **941B** of the second pixel **PX2** and the thickness of the first electrode **941C** of the third pixel **PX3** are configured to be different, so that the luminance viewing angle characteristic of the organic light emitting display apparatus **900** can be improved.

[0151] Here, when the thickness of the first hole transport layer **211** is 100 Å to 1000 Å (e.g., 550 Å), the thickness of the first electrode **941A** is 200 Å to 1600 Å (e.g., 900 Å) or 2000 Å to 2400 Å (e.g., 2200 Å). Further, the thickness of the first electrode **941B** is 200 Å to 1000 Å (e.g., 600 Å) or 1700 Å to 2400 Å (e.g., 2050 Å), the thickness of the first electrode **941C** is 800 Å to 1600 Å (e.g., 1200 Å), and the thickness of the first electrode **941D** is 200 Å to 1000 Å (e.g., 600 Å) or 1200 Å to 2000 Å (e.g., 1600 Å), or 2200 Å to 2400 Å (e.g., 2300 Å). When the thickness of the first hole transport layer **211** is 1000 Å to 2200 Å (e.g., 1600 Å), the thickness of the first electrode **941A** is 100 Å to 600 Å (e.g., 350 Å) or 1000 Å to 1800 Å (e.g., 1400 Å). Further, the thickness of the first electrode **941B** is 200 Å to 1200 Å (e.g., 700 Å) or 1600 Å to 2400 Å (e.g., 2000 Å), the thickness of the first electrode **941C** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2200 Å (e.g., 1600 Å), and the thickness of the first electrode **941D** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2000 Å (e.g., 1600 Å).

[0152] Even though in FIG. 9, it is illustrated that the thickness of the first electrodes **941A** of the first pixel **PX1**, the thickness of the first electrode **941C** of the third pixel **PX3**, and the thickness of the first electrode **941D** of the fourth pixel **PX4** are larger than the thickness of the first electrode **941B** of the second pixel **PX2**, but embodiments of the present disclosure area not limited thereto. For example, the thickness of the first electrodes **941A** of the first pixel **PX1**, the thickness of the first electrode **941C** of the third pixel **PX3**, and the thickness of the first electrode **941D** of the fourth pixel **PX4** can be smaller than the thickness of the first electrode **941B** of the second pixel **PX2**. According to an embodiment, the thickness of the first electrodes **941A** of the first pixel **PX1**, the thickness of the first electrode **941C** of the third pixel **PX3**, and the thickness of the first electrode **941D** of the fourth pixel **PX4** can be equal to each other, but embodiments are not limited thereto.

[0153] The organic light emitting display apparatus **900** according to another example embodiment of the present disclosure configures the thickness of the first electrode **941A** of the first pixel **PX1** to be different from the thickness of the first electrode **941B** of the second pixel **PX2**, so that the color viewing angle characteristic can be improved. Further, the thickness of the first electrode **941B** of the second pixel **PX2** and the thickness of the first electrode **941C** of the third pixel **PX3** are configured to be different so that the luminance viewing angle characteristic can be improved.

[0154] Further, the thickness of the first electrode **941A** of the first pixel **PX1**, the thickness of the first electrode **941C** of the third pixel **PX3**, and the thickness of the first electrode **941D** of the fourth pixel **PX4** can be configured to be equal to one another. For example, the first electrodes **941A**, **941B**, **941C**, and **941D** of the organic light emitting display apparatus **900** can be formed by performing the photo process two times. Accordingly, the photo process can be minimized and a micro cavity structure optimized for every pixel **PX1**, **PX2**, **PX3**, **PX4** can also be applied.

[0155] FIG. 10 is a schematic cross-sectional view of an organic light emitting display apparatus according to another example embodiment of the present disclosure. An organic light emitting display apparatus 1000 of FIG. 10 is substantially the same as the organic light emitting display apparatus 100 of FIG. 4 except for a thickness relationship of a first electrode 1041A of a first pixel PX1, a first electrode 1041B of a second pixel PX2, a first electrode 1041C of a third pixel PX3, and a first electrode 1041D of a fourth pixel PX4 so that a redundant description will be omitted. [0156] With reference to FIG. 10, the organic light emitting display apparatus 1000 includes a first organic light emitting diode 1040A corresponding to the first pixel PX1, a second organic light emitting diode 1040B corresponding to the second pixel PX2, a third organic light emitting diode 1040C corresponding to the third pixel PX3, and a fourth organic light emitting diode 1040D corresponding to the fourth pixel PX4. For example, the first pixel PX1 can be a white pixel, the second pixel PX2 can be a red pixel, the third pixel PX3 can be a green pixel, and the fourth pixel PX4 can be a blue pixel. For example, light emitted from the first organic light emitting diode 1040A is white light, white light emitted from the second organic light emitting diode 1040B can be converted into red light by the color filter 130. The white light emitted from the third organic light emitting diode 1040C can be converted into green light by the color filter 130 and the white light emitted from the fourth organic light emitting diode 1040D can be converted into blue light by the color filter 130.

[0157] A thickness of the first electrode 1041A of the first pixel PX1, a thickness of the first electrode 1041B of the second pixel PX2, and a thickness of the first electrode 1041C of the third pixel PX3 can be different from one another. The thickness of the first electrode 1041B of the second pixel PX2 can be equal to the thickness of the first electrode 1041D of the fourth pixel PX4. For example, the thickness of the first electrode 1041A of the first pixel PX1 and the thickness of the first electrode 1041B of the second pixel PX2 are configured to be different, so that the color viewing angle characteristic of the organic light emitting display apparatus 1000 can be improved. Further, the thickness of the first electrode 1041B of the second pixel PX2 and the thickness of the first electrode 1041C of the third pixel PX3 are configured to be different, so that the luminance viewing angle characteristic of the organic light emitting display apparatus 1000 can be improved. [0158] Here, when the thickness of the first hole transport layer 211 is 100 Å to 1000 Å (e.g., 550 Å), the thickness of the first electrode 1041A is 200 Å to 1600 Å (e.g., 900 Å) or 2000 Å to 2400 Å (e.g., 2200 Å). Further, the thickness of the first electrode 1041B is 200 Å to 1000 Å (e.g., 600 Å) or 1700 Å to 2400 Å (e.g., 2050 Å), the thickness of the first electrode 1041C is 800 Å to 1600 Å (e.g., 1200 Å), and the thickness of the first electrode 1041D is 200 Å to 1000 Å (e.g., 600 Å) or 1200 Å to 2000 Å (e.g., 1600 Å), or 2200 Å to 2400 Å (e.g., 2300 Å). When the thickness of the first hole transport layer 211 is 1000 Å to 2200 Å (e.g., 1600 Å), the thickness of the first electrode 1041A is 100 Å to 600 Å (e.g., 350 Å) or 1000 Å to 1800 Å (e.g., 1400 Å). Further, the thickness of the first electrode 1041B is 200 Å to 1200 Å (e.g., 700 Å) or 1600 Å to 2400 Å (e.g.,), the thickness of the first electrode 1041C is 100 Å to 600 Å (e.g.,) or 1200 Å to 2200 Å (e.g., 2000 Å), and the thickness of the first electrode 1041D is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2000 Å (e.g., 1600 Å).

[0159] In the meantime, even though in FIG. 10, it is illustrated that the thickness of the first electrodes 1041A of the first pixel PX1, the thickness of the first electrode 1041C of the third pixel PX3, and the thicknesses of the first electrodes 1041B and 1041D of the second pixel PX2 and the fourth pixel PX4 are reduced in this order (e.g., 1041A>1041C>1041B and 1041D), embodiments of the present disclosure are not limited thereto.

[0160] The organic light emitting display apparatus 1000 according to another example embodiment of the present disclosure configures the thickness of the first electrode 1041A of the first pixel PX1 to be different from the thickness of the first electrode 1041B of the second pixel PX2, so that the color viewing angle characteristic can be improved. Further, the thickness of the first electrode 1041B of the second pixel PX2 and the thickness of the first electrode 1041C of the

third pixel PX3 are configured to be different so that the luminance viewing angle characteristic can be improved.

[0161] Further, the thicknesses of the first electrode **1041A** of the first pixel PX1 and the first electrode **1041C** of the third pixel PX3 can be configured to be different from each other and the thicknesses of the first electrode **1041B** of the second pixel PX2 and the first electrode **1041D** of the fourth pixel PX4 can be configured to be equal to each other. For example, the first electrodes **1041A**, **1041B**, **1041C**, and **1041D** of the organic light emitting display apparatus **1000** can be formed to have three types of thicknesses for each of pixels PX1, PX2, PX3, and PX4 by performing a photo process three times. Accordingly, the photo process can be minimized and various thicknesses are also applied for each of the pixels PX1, PX2, PX3, and PX4 so that a more optimized micro cavity structure can be implemented.

[0162] FIG. **11** is a schematic cross-sectional view of an organic light emitting display apparatus according to another example embodiment of the present disclosure. An organic light emitting display apparatus **1100** of FIG. **11** is substantially the same as the organic light emitting display apparatus **100** of FIG. **4** except for a thickness relationship of a first electrode **1141A** of a first pixel PX1, a first electrode **1141B** of a second pixel PX2, a first electrode **1141C** of a third pixel PX3, and a first electrode **1141D** of a fourth pixel PX4 so that a redundant description will be omitted.

[0163] With reference to FIG. **11**, the organic light emitting display apparatus **1100** includes a first organic light emitting diode **1140A** corresponding to the first pixel PX1, a second organic light emitting diode **1140B** corresponding to the second pixel PX2, a third organic light emitting diode **1140C** corresponding to the third pixel PX3, and a fourth organic light emitting diode **1140D** corresponding to the fourth pixel PX4. For example, the first pixel PX1 can be a white pixel, the second pixel PX2 can be a red pixel, the third pixel PX3 can be a green pixel, and the fourth pixel PX4 can be a blue pixel. For example, light emitted from the first organic light emitting diode **1140A** is white light, white light emitted from the second organic light emitting diode **1140B** can be converted into red light by the color filter **130**. The white light emitted from the third organic light emitting diode **1140C** can be converted into green light by the color filter **130** and the white light emitted from the fourth organic light emitting diode **1140D** can be converted into blue light by the color filter **130**.

[0164] A thickness of the first electrode **1141A** of the first pixel PX1, a thickness of the first electrode **1141B** of the second pixel PX2, and a thickness of the first electrode **1141C** of the third pixel PX3 can be different from one another. The thickness of the first electrode **1141C** of the third pixel PX3 can be equal to the thickness of the first electrode **1141D** of the fourth pixel PX4. For example, the thickness of the first electrode **1141A** of the first pixel PX1 and the thickness of the first electrode **1141B** of the second pixel PX2 are configured to be different, so that the color viewing angle characteristic of the organic light emitting display apparatus **1100** can be improved. Further, the thickness of the first electrode **1141B** of the second pixel PX2 and the thickness of the first electrode **1141C** of the third pixel PX3 are configured to be different, so that the luminance viewing angle characteristic of the organic light emitting display apparatus **1100** can be improved.

[0165] Here, when the thickness of the first hole transport layer **211** is 100 Å to 1000 Å (e.g., 550 Å), the thickness of the first electrode **1141A** is 200 Å to 1600 Å (e.g., 900 Å) or 2000 Å to 2400 Å (e.g., 2200 Å). Further, the thickness of the first electrode **1141B** is 200 Å to 1000 Å (e.g., 600 Å) or 1700 Å to 2400 Å (e.g., 2050 Å), the thickness of the first electrode **1141C** is 800 Å to 1600 Å (e.g., 1200 Å), and the thickness of the first electrode **1141D** is 200 Å to 1000 Å (e.g., 600 Å) or 1200 Å to 2000 Å (e.g., 1600 Å), or 2200 Å to 2400 Å (e.g., 2300 Å). When the thickness of the first hole transport layer **211** is 1000 Å to 2200 Å (e.g., 1600 Å), the thickness of the first electrode **1141A** is 100 Å to 600 Å (e.g., 350 Å) or 1000 Å to 1800 Å (e.g., 1400 Å). Further, the thickness of the first electrode **1141B** is 200 Å to 1200 Å (e.g., 700 Å) or 1600 Å to 2400 Å (e.g., 2000 Å), the thickness of the first electrode **1141C** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2200 Å (e.g., 1600 Å), and the thickness of the first electrode **1141D** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å

to 2000 Å (e.g., 1600 Å).

[0166] In the meantime, even though in FIG. 11, it is illustrated that the thickness of the first electrodes **1141A** of the first pixel PX1, the thicknesses of the first electrodes **1141C** and **1141D** of the third pixel PX3 and the fourth pixel PX4, and the thickness of the first electrode **1141B** of the second pixel PX2 are reduced in this order (e.g., **1141A**>**1141C** and **1141D**>**1141B**), embodiments of the present disclosure are not limited thereto.

[0167] The organic light emitting display apparatus **1100** according to another example embodiment of the present disclosure is configured to have the thickness of the first electrode **1141A** of the first pixel PX1 to be different from the thickness of the first electrode **1141B** of the second pixel PX2, so that the color viewing angle characteristic can be improved. Further, the thickness of the first electrode **1141B** of the second pixel PX2 and the thickness of the first electrode **1141C** of the third pixel PX3 are configured to be different so that the luminance viewing angle characteristic can be improved.

[0168] Further, the thicknesses of the first electrode **1141A** of the first pixel PX1 and the first electrode **1141C** of the third pixel PX3 can be configured to be different from each other and the thicknesses of the first electrode **1141C** of the third pixel PX3 and the first electrode **1141D** of the fourth pixel PX4 can be configured to be equal to each other. For example, the first electrodes **1141A**, **1141B**, **1141C**, and **1141D** of the organic light emitting display apparatus **1100** can be formed to have three types of thicknesses for each of pixels PX1, PX2, PX3, and PX4 by performing a photo process three times. Accordingly, the photo process can be minimized and various thicknesses are also applied for each of the pixels PX1, PX2, PX3, and PX4 so that a more optimized micro cavity structure can be implemented.

[0169] FIG. 12 is a schematic cross-sectional view of an organic light emitting display apparatus according to another example embodiment of the present disclosure. An organic light emitting display apparatus **1200** of FIG. 12 is substantially the same as the organic light emitting display apparatus **100** of FIG. 4 except for a thickness relationship of a first electrode **1241A** of a first pixel PX1, a first electrode **1241B** of a second pixel PX2, a first electrode **1241C** of a third pixel PX3, and a first electrode **1241D** of a fourth pixel PX4 so that a redundant description will be omitted.

[0170] With reference to FIG. 12, the organic light emitting display apparatus **1200** includes a first organic light emitting diode **1240A** corresponding to the first pixel PX1, a second organic light emitting diode **1240B** corresponding to the second pixel PX2, a third organic light emitting diode **1240C** corresponding to the third pixel PX3, and a fourth organic light emitting diode **1240D** corresponding to the fourth pixel PX4. For example, the first pixel PX1 can be a white pixel, the second pixel PX2 can be a red pixel, the third pixel PX3 can be a green pixel, and the fourth pixel PX4 can be a blue pixel. For example, light emitted from the first organic light emitting diode **1240A** is white light, white light emitted from the second organic light emitting diode **1240B** can be converted into red light by the color filter **130**. The white light emitted from the third organic light emitting diode **1240C** can be converted into green light by the color filter **130** and the white light emitted from the fourth organic light emitting diode **1240D** can be converted into blue light by the color filter **130**.

[0171] A thickness of the first electrode **1241A** of the first pixel PX1, a thickness of the first electrode **1241B** of the second pixel PX2, and a thickness of the first electrode **1241C** of the third pixel PX3 can be different from one another. The thickness of the first electrode **1241A** of the first pixel PX1 can be equal to a thickness of the first electrode **1241D** of the fourth pixel PX4. For example, the thickness of the first electrode **1241A** of the first pixel PX1 and the thickness of the first electrode **1241B** of the second pixel PX2 are configured to be different, so that the color viewing angle characteristic of the organic light emitting display apparatus **1200** can be improved. Further, the thickness of the first electrode **1241B** of the second pixel PX2 and the thickness of the first electrode **1241C** of the third pixel PX3 are configured to be different, so that the luminance viewing angle characteristic of the organic light emitting display apparatus **1200** can be improved.

[0172] Here, when the thickness of the first hole transport layer **211** is 100 Å to 1000 Å (e.g., 550 Å), the thickness of the first electrode **1241A** is 200 Å to 1600 Å (e.g., 900 Å) or 2000 Å to 2400 Å (e.g., 2200 Å). Further, the thickness of the first electrode **1241B** is 200 Å to 1000 Å (e.g., 600 Å) or 1700 Å to 2400 Å (e.g., 2050 Å), the thickness of the first electrode **1241C** is 800 Å to 1600 Å (e.g., 1200 Å), and the thickness of the first electrode **1241D** is 200 Å to 1000 Å (e.g., 600 Å) or 1200 Å to 2000 Å (e.g., 1600 Å), or 2200 Å to 2400 Å (e.g., 2300 Å). When the thickness of the first hole transport layer **211** is 1000 Å to 2200 Å (e.g., 1600 Å), the thickness of the first electrode **1241A** is 100 Å to 600 Å (e.g., 350 Å) or 1000 Å to 1800 Å (e.g., 1400 Å). Further, the thickness of the first electrode **1241B** is 200 Å to 1200 Å (e.g., 700 Å) or 1600 Å to 2400 Å (e.g., 2000 Å), the thickness of the first electrode **1241C** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2200 Å (e.g., 1600 Å), and the thickness of the first electrode **1241D** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2000 Å (e.g., 1600 Å).

[0173] In the meantime, even though in FIG. **12**, it is illustrated that the thicknesses of the first electrodes **1241A** and **1241D** of the first pixel **PX1** and the fourth pixel **PX4**, the thickness of the first electrodes **1241C** of the third pixel **PX3**, and the thickness of the first electrode **1241B** of the second pixel **PX2** are reduced in this order, embodiments of the present disclosure area not limited thereto.

[0174] The organic light emitting display apparatus **1200** according to another example embodiment of the present disclosure is configured to have the thickness of the first electrode **1241A** of the first pixel **PX1** to be different from the thickness of the first electrode **1241B** of the second pixel **PX2**, so that the color viewing angle characteristic can be improved. Further, the thickness of the first electrode **1241B** of the second pixel **PX2** and the thickness of the first electrode **1241C** of the third pixel **PX3** are configured to be different so that the luminance viewing angle characteristic can be improved.

[0175] Further, the thicknesses of the first electrode **1241A** of the first pixel **PX1** and the first electrode **1241C** of the third pixel **PX3** can be configured to be different from each other and the thicknesses of the first electrode **1241A** of the first pixel **PX1** and the first electrode **1241D** of the fourth pixel **PX4** can be configured to be equal to each other. For example, the first electrodes **1241A**, **1241B**, **1241C**, and **1241D** of the organic light emitting display apparatus **1200** can be formed to have three types of thicknesses for each of pixels **PX1**, **PX2**, **PX3**, and **PX4** by performing a photo process three times. Accordingly, the photo process can be minimized and various thicknesses are also applied for each of the pixels **PX1**, **PX2**, **PX3**, and **PX4** so that a more optimized micro cavity structure can be implemented.

[0176] FIG. **13** is a schematic cross-sectional view of an organic light emitting display apparatus according to another example embodiment of the present disclosure. An organic light emitting display apparatus **1300** of FIG. **13** is substantially the same as the organic light emitting display apparatus **100** of FIG. **4** except for a thickness relationship of a first electrode **1341A** of a first pixel **PX1**, a first electrode **1341B** of a second pixel **PX2**, a first electrode **1341C** of a third pixel **PX3**, and a first electrode **1341D** of a fourth pixel **PX4** so that a redundant description will be omitted.

[0177] With reference to FIG. **13**, the organic light emitting display apparatus **1300** includes a first organic light emitting diode **1340A** corresponding to the first pixel **PX1**, a second organic light emitting diode **1340B** corresponding to the second pixel **PX2**, a third organic light emitting diode **1340C** corresponding to the third pixel **PX3**, and a fourth organic light emitting diode **1340D** corresponding to the fourth pixel **PX4**. For example, the first pixel **PX1** can be a white pixel, the second pixel **PX2** can be a red pixel, the third pixel **PX3** can be a green pixel, and the fourth pixel **PX4** can be a blue pixel. For example, light emitted from the first organic light emitting diode **1340A** is white light, white light emitted from the second organic light emitting diode **1340B** can be converted into red light by the color filter **130**. The white light emitted from the third organic light emitting diode **1340C** can be converted into green light by the color filter **130** and the white light emitted from the fourth organic light emitting diode **1340D** can be converted into blue light by

the color filter **130**.

[0178] A thickness of the first electrode **1341A** of the first pixel **PX1**, a thickness of the first electrode **1341B** of the second pixel **PX2**, and a thickness of the first electrode **1341D** of the fourth pixel **PX4** can be different from one another. The thickness of the first electrode **1341A** of the first pixel **PX1** can be equal to a thickness of the first electrode **1341C** of the third pixel **PX3**. For example, the thickness of the first electrode **1341A** of the first pixel **PX1** and the thickness of the first electrode **1341B** of the second pixel **PX2** are configured to be different, so that the color viewing angle characteristic of the organic light emitting display apparatus **1300** can be improved. Further, the thickness of the first electrode **1341B** of the second pixel **PX2** and the thickness of the first electrode **1341C** of the third pixel **PX3** are configured to be different, so that the luminance viewing angle characteristic of the organic light emitting display apparatus **1300** can be improved.

[0179] Here, when the thickness of the first hole transport layer **211** is 100 Å to 1000 Å (e.g., 550 Å), the thickness of the first electrode **1341A** is 200 Å to 1600 Å (e.g., 900 Å) or 2000 Å to 2400 Å (e.g., 2200 Å). Further, the thickness of the first electrode **1341B** is 200 Å to 1000 Å (e.g., 600 Å) or 1700 Å to 2400 Å (e.g., 2050 Å), the thickness of the first electrode **1341C** is 800 Å to 1600 Å (e.g., 1200 Å), and the thickness of the first electrode **1341D** is 200 Å to 1000 Å (e.g., 600 Å) or 1200 Å to 2000 Å (e.g., 1600 Å), or 2200 Å to 2400 Å (e.g., 2300 Å). When the thickness of the first hole transport layer **211** is 1000 Å to 2200 Å (e.g., 1600 Å), the thickness of the first electrode **1341A** is 100 Å to 600 Å (e.g., 350 Å) or 1000 Å to 1800 Å (e.g., 1400 Å). Further, the thickness of the first electrode **1341B** is 200 Å to 1200 Å (e.g., 700 Å) or 1600 Å to 2400 Å (e.g., 2000 Å), the thickness of the first electrode **1341C** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2200 Å (e.g., 1600 Å), and the thickness of the first electrode **1341D** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2000 Å (e.g., 1600 Å).

[0180] In the meantime, even though in FIG. **13**, it is illustrated that the thicknesses of the first electrodes **1341A** and **1341C** of the first pixel **PX1** and the third pixel **PX3**, the thickness of the first electrodes **1341D** of the fourth pixel **PX4**, and the thickness of the first electrode **1341B** of the second pixel **PX2** are reduced in this order (e.g., **1341A** and **1341C** > **1341D** > **1341B**), embodiments of the present disclosure are not limited thereto.

[0181] The organic light emitting display apparatus **1300** according to another example embodiment of the present disclosure is configured to have the thickness of the first electrode **1341A** of the first pixel **PX1** to be different from the thickness of the first electrode **1341B** of the second pixel **PX2**, so that the color viewing angle characteristic can be improved. Further, the thickness of the first electrode **1341B** of the second pixel **PX2** and the thickness of the first electrode **1341C** of the third pixel **PX3** are configured to be different so that the luminance viewing angle characteristic can be improved.

[0182] Further, the thicknesses of the first electrode **1341A** of the first pixel **PX1** and the first electrode **1341C** of the third pixel **PX3** can be configured to be equal to each other. Further, the thickness of the first electrodes **1341A** of the first pixel **PX1**, the thickness of the first electrode **1341B** of the second pixel **PX2**, and the thickness of the first electrode **1341D** of the fourth pixel **PX4** can be configured to be different from one another. For example, the first electrodes **1341A**, **1341B**, **1341C**, and **1341D** of the organic light emitting display apparatus **1300** can be formed to have three types of thicknesses for each of pixels **PX1**, **PX2**, **PX3**, and **PX4** by performing a photo process three times. Accordingly, the photo process can be minimized and various thicknesses are also applied for each of the pixels **PX1**, **PX2**, **PX3**, and **PX4** so that a more optimized micro cavity structure can be implemented.

[0183] FIG. **14** is a schematic cross-sectional view of an organic light emitting display apparatus according to another example embodiment of the present disclosure. An organic light emitting display apparatus **1400** of FIG. **14** is substantially the same as the organic light emitting display apparatus **100** of FIG. **4** except for a thickness relationship of a first electrode **1441A** of a first pixel **PX1**, a first electrode **1441B** of a second pixel **PX2**, a first electrode **1441C** of a third pixel **PX3**,

and a first electrode **1441D** of a fourth pixel **PX4** so that a redundant description will be omitted. [0184] With reference to FIG. **14**, the organic light emitting display apparatus **1400** includes a first organic light emitting diode **1440A** corresponding to the first pixel **PX1**, a second organic light emitting diode **1440B** corresponding to the second pixel **PX2**, a third organic light emitting diode **1440C** corresponding to the third pixel **PX3**, and a fourth organic light emitting diode **1440D** corresponding to the fourth pixel **PX4**. For example, the first pixel **PX1** can be a white pixel, the second pixel **PX2** can be a red pixel, the third pixel **PX3** can be a green pixel, and the fourth pixel **PX4** can be a blue pixel. For example, light emitted from the first organic light emitting diode **1440A** is white light, white light emitted from the second organic light emitting diode **1440B** can be converted into red light by the color filter **130**. The white light emitted from the third organic light emitting diode **1440C** can be converted into green light by the color filter **130** and the white light emitted from the fourth organic light emitting diode **1440D** can be converted into blue light by the color filter **130**.

[0185] A thickness of the first electrode **1441A** of the first pixel **PX1**, a thickness of the first electrode **1441B** of the second pixel **PX2**, a thickness of the first electrode **1441C** of the third pixel **PX3**, and a thickness of the first electrode **1441D** of the fourth pixel **PX4** can be different from one another. For example, the thickness of the first electrode **1441A** of the first pixel **PX1** and the thickness of the first electrode **1441B** of the second pixel **PX2** are configured to be different, so that the color viewing angle characteristic of the organic light emitting display apparatus **1400** can be improved. Further, the thickness of the first electrode **1441B** of the second pixel **PX2** and the thickness of the first electrode **1441C** of the third pixel **PX3** are configured to be different, so that the luminance viewing angle characteristic of the organic light emitting display apparatus **1400** can be improved.

[0186] Here, when the thickness of the first hole transport layer **211** is 100 Å to 1000 Å (e.g., 550 Å), the thickness of the first electrode **1441A** is 200 Å to 1600 Å (e.g., 900 Å) or 2000 Å to 2400 Å (e.g., 2200 Å). Further, the thickness of the first electrode **1441B** is 200 Å to 1000 Å (e.g., 600 Å) or 1700 Å to 2400 Å (e.g., 2050 Å), the thickness of the first electrode **1441C** is 800 Å to 1600 Å (e.g., 1200 Å), and the thickness of the first electrode **1441D** is 200 Å to 1000 Å (e.g., 600 Å) or 1200 Å to 2000 Å (e.g., 1600 Å), or 2200 Å to 2400 Å (e.g., 2300 Å). When the thickness of the first hole transport layer **211** is 1000 Å to 2200 Å (e.g., 1600 Å), the thickness of the first electrode **1441A** is 100 Å to 600 Å (e.g., 350 Å) or 1000 Å to 1800 Å (e.g., 1400 Å). Further, the thickness of the first electrode **1441B** is 200 Å to 1200 Å (e.g., 700 Å) or 1600 Å to 2400 Å (e.g., 2000 Å), the thickness of the first electrode **1441C** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2200 Å (e.g., 1600 Å), and the thickness of the first electrode **1441D** is 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2000 Å (e.g., 1600 Å).

[0187] In the meantime, even though in FIG. **14**, it is illustrated that the thickness of the first electrodes **1441A** of the first pixel **PX1**, the thickness of the first electrode **1441C** of the third pixel **PX3**, the thickness of the first electrode **1441B** of the second pixel **PX2**, and the thickness of the first electrode **1441D** of the fourth pixel **PX4** are reduced in this order, embodiments of the present disclosure are not limited thereto.

[0188] The organic light emitting display apparatus **1400** according to another example embodiment of the present disclosure configures the thickness of the first electrode **1441A** of the first pixel **PX1** to be different from the thickness of the first electrode **1441B** of the second pixel **PX2**, so that the color viewing angle characteristic can be improved. Further, the thickness of the first electrode **1441B** of the second pixel **PX2** and the thickness of the first electrode **1441C** of the third pixel **PX3** are configured to be different so that the luminance viewing angle characteristic can be improved.

[0189] Further, the thicknesses of the first electrodes **1441A**, **1441B**, **1441C**, and **1441D** of the first pixel **PX1**, the second pixel **PX2**, the third pixel **PX3**, and the fourth pixel **PX4** can be configured to be different from one another. For example, the thicknesses of the first electrodes **1441A**, **1441B**,

1441C, and **1441D** more optimized for each of the first pixel **PX1**, the second pixel **PX2**, the third pixel **PX3**, and the fourth pixel **PX4** of the organic light emitting display apparatus **1400** can be set. Accordingly, an effect by the micro cavity of the organic light emitting display apparatus **1400** can be improved.

[0190] The example embodiments of the present disclosure can also be described as follows:

[0191] An organic light emitting display apparatus according to an embodiment of the present disclosure includes a substrate including a plurality of pixels. The organic light emitting display apparatus further includes a plurality of organic light emitting diodes disposed on the substrate to correspond to the plurality of pixels. The plurality of pixels includes a first pixel, a second pixel, a third pixel, and a fourth pixel which emit different color light. Each of the plurality of organic light emitting diodes includes a first electrode, a light emitting portion on the first electrode and a second electrode on the light emitting portion. A thickness of the first electrode of the first pixel is different from a thickness of the first electrode of the second pixel, and the thickness of the first electrode of the second pixel is different from a thickness of the first electrode of the third pixel.

[0192] According to some embodiments of the present disclosure, the first pixel can be a white pixel, the second pixel can be a red pixel, the third pixel can be a green pixel, and the fourth pixel can be a blue pixel.

[0193] According to some embodiments of the present disclosure, the thickness of the first electrode of the first pixel can be equal to the thickness of the first electrode of the third pixel, and the thickness of the first electrode of the second pixel can be equal to a thickness of the first electrode of the fourth pixel.

[0194] According to some embodiments of the present disclosure, the thickness of the first electrode of the first pixel, the thickness of the first electrode of the third pixel, and a thickness of the first electrode of the fourth pixel can be equal to one another.

[0195] According to some embodiments of the present disclosure, the thickness of the first electrode of the first pixel can be different from the thickness of the first electrode of the third pixel, and the thickness of the first electrode of the second pixel can be equal to a thickness of the first electrode of the fourth pixel.

[0196] According to some embodiments of the present disclosure, the thickness of the first electrode of the first pixel can be different from the thickness of the first electrode of the third pixel, and the thickness of the first electrode of the third pixel can be equal to a thickness of the first electrode of the fourth pixel.

[0197] According to some embodiments of the present disclosure, the thickness of the first electrode of the first pixel can be different from the thickness of the first electrode of the third pixel, and the thickness of the first electrode of the first pixel can be equal to a thickness of the first electrode of the fourth pixel.

[0198] According to some embodiments of the present disclosure, the thickness of the first electrode of the first pixel can be equal to the thickness of the first electrode of the third pixel, and the thickness of the first electrode of the first pixel, the thickness of the first electrode of the second pixel, and a thickness of the first electrode of the fourth pixel can be different from one another.

[0199] According to some embodiments of the present disclosure, the thicknesses of the first electrodes of the first pixel, the second pixel, the third pixel, and the fourth pixel can be different from one another.

[0200] According to some embodiments of the present disclosure, the light emitting portion can include a hole transport layer disposed on the first electrode and a thickness of the hole transport layer can be 100 Å to 2200 Å (e.g., 1600 Å).

[0201] According to some embodiments of the present disclosure, when the thickness of the hole transport layer can be 100 Å to 1000 Å (e.g., 550 Å), the thickness of the first electrode of the first pixel can be 200 Å to 1600 Å (e.g., 900 Å) or 2000 Å to 2400 Å (e.g., 2200 Å), the thickness of the first electrode of the second pixel can be 200 Å to 1000 Å (e.g., 600 Å) or 1700 Å to 2400 Å (e.g.,

2050 Å), the thickness of the first electrode of the third pixel can be 800 Å to 1600 Å (e.g., 1200 Å), and a thickness of the first electrode of the fourth pixel can be 200 Å to 1000 Å (e.g., 600 Å) or 1200 Å to 2000 Å (e.g., 1600 Å), or 2200 Å to 2400 Å (e.g., 2300 Å).

[0202] According to some embodiments of the present disclosure, when the thickness of the hole transport layer can be 1000 Å to 2200 Å (e.g., 1600 Å), the thickness of the first electrode of the first pixel can be 100 Å to 600 Å (e.g., 350 Å) or 1000 Å to 1800 Å (e.g., 1400 Å), the thickness of the first electrode of the second pixel can be 200 Å to 1200 Å (e.g., 600 Å) or 1600 Å to 2400 Å (e.g., 2000 Å), the thickness of the first electrode of the third pixel can be 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2200 Å (e.g., 1600 Å), and a thickness of the first electrode of the fourth pixel can be 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2000 Å (e.g., 1600 Å).

[0203] According to some embodiments of the present disclosure, the light emitting portion can include a first light emitting portion on the first electrode and including a blue light emitting layer, a second light emitting portion on the first light emitting portion and including a red light emitting layer and two yellow-green light emitting layers, and a third light emitting portion on the second light emitting portion and including a blue light emitting layer.

[0204] According to some embodiments of the present disclosure, a thickness of the first light emitting portion can be 400 Å to 3100 Å (e.g., 1750 Å), a thickness of the second light emitting portion can be 750 Å to 1350 Å (e.g., 1050 Å), a thickness of the third light emitting portion can be 1200 Å to 1800 Å (e.g., 1500 Å), a distance between a center of the blue light emitting layer of the first light emitting portion and the second electrode can be 2500 Å to 3100 Å (e.g., 2800 Å), a distance between a center of the red light emitting layer of the second light emitting portion and the second electrode can be 2000 Å to 2600 Å (e.g., 2300 Å), a distance between a boundary of the two yellow-green light emitting layers of the second light emitting portion and the second electrode can be 1700 Å to 2300 Å (e.g., 2000 Å), and a distance between a center of the blue light emitting layer of the third light emitting portion and the second electrode can be 100 Å to 700 Å (e.g., 400 Å).

[0205] According to some embodiments of the present disclosure, the first electrode can include a transparent conductive material, and the second electrode can include a metal material.

[0206] An organic light emitting display apparatus according to another embodiment of the present disclosure includes a substrate including a plurality of pixels. The organic light emitting display apparatus further includes a plurality of organic light emitting diodes disposed on the substrate to correspond to the plurality of pixels. The plurality of pixels includes a white pixel, a red pixel, a green pixel, and a blue pixel. Each of the plurality of organic light emitting diodes includes a first electrode, a first light emitting portion on the first electrode and including a blue light emitting layer, a second light emitting portion on the first light emitting portion and including a red light emitting layer and two yellow-green light emitting layers, a third light emitting portion on the second light emitting portion and including a blue light emitting layer and a second electrode on the third light emitting portion. A thickness of the first electrode of the white pixel is different from a thickness of the first electrode of the red pixel, and the thickness of the first electrode of the red pixel is different from a thickness of the first electrode of the green pixel.

[0207] According to some embodiments of the present disclosure, the first light emitting portion can include a hole transport layer on the first electrode and a thickness of the hole transport layer is 100 Å to 2200 Å (e.g., 1150 Å).

[0208] According to some embodiments of the present disclosure, when the thickness of the hole transport layer can be 100 Å to 1000 Å (e.g., 550 Å), the thickness of the first electrode of the white pixel can be 200 Å to 1600 Å (e.g., 900 Å) or 2000 Å to 2400 Å (e.g., 2200 Å), the thickness of the first electrode of the red pixel can be 200 Å to 1000 Å (e.g., 600 Å) or 1700 Å to 2400 Å (e.g., 2050 Å), the thickness of the first electrode of the green pixel can be 800 Å to 1600 Å (e.g., 1200 Å), and a thickness of the first electrode of the blue pixel can be 200 Å to 1000 Å (e.g., 600 Å) or 1200 Å to 2000 Å (e.g., 1600 Å), or 2200 Å to 2400 Å (e.g., 2300 Å).

[0209] According to some embodiments of the present disclosure, when the thickness of the hole

transport layer can be 1000 Å to 2200 Å (e.g., 1600 Å), the thickness of the first electrode of the white pixel can be 100 Å to 600 Å (e.g., 350 Å) or 1000 Å to 1800 Å (e.g., 1400 Å), the thickness of the first electrode of the red pixel can be 200 Å to 1200 Å (e.g., 700 Å) or 1600 Å to 2400 Å (e.g., 2000 Å), the thickness of the first electrode of the green pixel can be 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2200 Å (e.g., 1700 Å), and a thickness of the first electrode of the blue pixel can be 100 Å to 600 Å (e.g., 350 Å) or 1200 Å to 2000 Å (e.g., 1600 Å).

[0210] According to another embodiment of the present disclosure, an organic light emitting display apparatus includes a substrate including a plurality of pixels; and a plurality of organic light emitting diodes disposed on the substrate to correspond to the plurality of pixels respectively, in which the plurality of pixels includes a first pixel, a second pixel, a third pixel, and a fourth pixel, and emits different color lights, and each pixel of the plurality of pixels includes a micro cavity structure corresponding to the light emitted from the pixel, each of the plurality of organic light emitting diodes includes a first electrode; a light emitting portion on the first electrode; and a second electrode on the light emitting portion, the micro cavity structure of the first pixel is different from the micro cavity structure of the second pixel, and the micro cavity structure of the second pixel is different from the micro cavity structure of the third pixel.

[0211] It will be apparent to those skilled in the art that various modifications and variations can be made in the present disclosure without departing from the technical idea or scope of the disclosure. Thus, it can be intended that embodiments of the present disclosure cover the modifications and variations of the disclosure provided they come within the scope of the appended claims and their equivalents.

Claims

1. An organic light emitting display apparatus, comprising: a first substrate including a plurality of pixels including at least a first pixel, a second pixel and a third pixel, the first, second, and third pixels being configured to emit different colors of light from each other; a transistor disposed on the first substrate and including a gate electrode, a source electrode, a drain electrode and an active layer; an over coating layer disposed on the transistor; a plurality of organic light emitting diodes disposed on the over coating layer to correspond to the plurality of pixels, each of the first, second, and third pixels including: a first electrode disposed on the over coating layer, a light emitting portion disposed on the first electrode, the light emitting portion having a three stack structure including: a first light emitting portion including at least a first-first hole transport layer, a first-second hole transport layer disposed on the first-first hole transport layer, and a first charge generation layer, the first light emitting portion having a total thickness of approximately 400 Å to 3100 Å, the first-first hole transport layer having a thickness of approximately 100 Å to 2200 Å, and the total thickness of the first light emitting portion minus the thickness of the first hole transport layer is 300 Å to 900 Å, a second light emitting portion disposed on the first light emitting portion, the second light emitting portion including at least a second-first hole transport layer and second charge generation layer, the second light emitting portion having a total thickness of approximately 750 Å to 1350 Å, and a third light emitting portion disposed on the second light emitting portion, at least one of the first light emitting portion, the second light emitting portion, and the third light emitting portion being configured to emit blue color light; a second electrode disposed on the light emitting portion; an encapsulation layer disposed on the plurality of organic light emitting diodes and including at least an inorganic layer and at least an organic layer; an adhesive member disposed on the encapsulation layer; and a second substrate disposed on the adhesive member.

2. The organic light emitting display apparatus according to claim 1, wherein a thickness of the first electrode of the first pixel is different from a thickness of the first electrode of the second pixel, and wherein the thickness of the first electrode of the second pixel is different from a thickness of the

first electrode of the third pixel.

3. The organic light emitting display apparatus according to claim 1, wherein the first light emitting portion further includes a first light emitting layer which is a fluorescent emitting layer.

4. The organic light emitting display apparatus according to claim 1, wherein the light emitting portion includes a phosphorescent emitting layer.

5. The organic light emitting display apparatus according to claim 1, wherein the second light emitting portion further includes a second light emitting layer configured to emit a different color of light from a color of a first light emitting layer of the first light emitting portion.

6. The organic light emitting display apparatus according to claim 1, wherein the second light emitting portion further includes a second light emitting layer configured to emit a color light including at least one of red, yellow or green.

7. The organic light emitting display apparatus according to claim 1, further comprising: a bank disposed on the first electrode and the over coating layer, the bank covering an edge of the first electrode or a periphery of the first electrode.

8. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, wherein a thickness of the first electrode of the first pixel is equal to a thickness of the first electrode of the third pixel, and wherein a thickness of the first electrode of the second pixel is equal to a thickness of a first electrode of the fourth pixel.

9. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, and wherein a thickness of the first electrode of the first pixel, a thickness of the first electrode of the third pixel, and a thickness of a first electrode of the fourth pixel are equal to one another.

10. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, wherein a thickness of the first electrode of the first pixel is different from a thickness of the first electrode of the third pixel, and wherein a thickness of the first electrode of the second pixel is equal to a thickness of a first electrode of the fourth pixel.

11. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, wherein a thickness of the first electrode of the first pixel is different from a thickness of the first electrode of the third pixel, and wherein a thickness of the first electrode of the third pixel is equal to a thickness of a first electrode of the fourth pixel.

12. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, wherein a thickness of the first electrode of the first pixel is different from a thickness of the first electrode of the third pixel, and wherein a thickness of the first electrode of the first pixel is equal to a thickness of a first electrode of the fourth pixel.

13. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, wherein a thickness of the first electrode of the first pixel is equal to a thickness of the first electrode of the third pixel, and wherein the thickness of the first electrode of the first pixel, a thickness of the first electrode of the second pixel, and a thickness of a first electrode of the fourth pixel are different from each other.

14. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, and wherein thicknesses of the first electrodes of the first pixel, the second pixel, the third pixel, and the fourth pixel are different from each other.

15. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, wherein the thickness of the first-first hole transport layer is approximately 100 Å to 1000 Å, wherein a thickness of the first electrode of the first pixel is approximately 200 Å to 1600 Å or approximately 2000 Å to 2400 Å, wherein a thickness of the first electrode of the second pixel is approximately 200 Å to 1000 Å or approximately 1700 Å to 2400 Å, wherein a thickness of the first electrode of the third pixel is approximately 800 Å to 1600 Å, and wherein a thickness of the first electrode of the fourth pixel is approximately 200 Å to 1000 Å or approximately 1200 Å to 2000 Å, or approximately 2200 Å to 2400 Å.

16. The organic light emitting display apparatus according to claim 1, wherein the plurality of pixels further include a fourth pixel, wherein the thickness of the first hole transport layer is approximately 1000 Å to 2200 Å, wherein a thickness of the first electrode of the first pixel is approximately 100 Å to 600 Å or approximately 1000 Å to 1800 Å, wherein a thickness of the first electrode of the second pixel is approximately 200 Å to 1200 Å or approximately 1600 Å to 2400 Å, wherein a thickness of the first electrode of the third pixel is approximately 100 Å to 600 Å or approximately 1200 Å to 2200 Å, and wherein a thickness of a first electrode of the fourth pixel is approximately 100 Å to 600 Å or approximately 1200 Å to 2000 Å.

17. The organic light emitting display apparatus according to claim 1, wherein the first light emitting portion includes a blue light emitting layer, wherein the second light emitting portion includes a red light emitting layer and two yellow-green light emitting layers, and wherein the third light emitting portion includes a blue light emitting layer.

18. The organic light emitting display apparatus according to claim 17, wherein a thickness of the first light emitting portion is approximately 400 Å to 3100 Å, wherein a thickness of the second light emitting portion is approximately 750 Å to 1350 Å, wherein a thickness of the third light emitting portion is approximately 1200 Å to 1800 Å, wherein a distance between a center of the blue light emitting layer of the first light emitting portion and the second electrode is approximately 2500 Å to 3100 Å, wherein a distance between a center of the red light emitting layer of the second light emitting portion and the second electrode is approximately 2000 Å to 2600 Å, wherein a distance between a boundary of the two yellow-green light emitting layers of the second light emitting portion and the second electrode is approximately 1700 Å to 2300 Å, and wherein a distance between a center of the blue light emitting layer of the third light emitting portion and the second electrode is approximately 100 Å to 700 Å.

19. The organic light emitting display apparatus according to claim 1, wherein the first electrode includes a transparent conductive material, and the second electrode includes a metal material.

20. The organic light emitting display apparatus according to claim 1, wherein the first light emitting portion further includes an electron transport layer, and wherein the second light emitting portion further includes an electron transport layer.
