

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12419199
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Shibata; Tatsuo et al.

Domain wall motion type magnetic recording element

Abstract

A magnetic domain wall movement type magnetic recording element according to an embodiment includes: a first ferromagnetic layer which includes a ferromagnetic body; a non-magnetic layer which faces the first ferromagnetic layer; and a magnetic recording layer which faces a surface of the non-magnetic layer on a side opposite to the first ferromagnetic layer and extends in a first direction. A first surface of the magnetic recording layer which faces the non-magnetic layer has a smaller arithmetic mean roughness than a second surface opposite to the first surface.

Inventors:	Shibata; Tatsuo (Tokyo, JP), Ito; Kuniyasu (Tokyo, JP)
Applicant:	TDK CORPORATION (Tokyo, JP)
Family ID:	1000008819678
Assignee:	TDK CORPORATION (Tokyo, JP)
Appl. No.:	17/900312
Filed:	August 31, 2022

Prior Publication Data

Document Identifier	Publication Date
US 20220416155 A1	Dec. 29, 2022

Foreign Application Priority Data

JP	2018-002469	Jan. 11, 2018
----	-------------	---------------

Related U.S. Application Data

continuation-in-part parent-doc US 16760169 US 11469370 WO PCT/JP2019/000323 20190109
child-doc US 17900312

Publication Classification

Int. Cl.: H10N52/80 (20230101); H10B61/00 (20230101); H10N52/01 (20230101)

U.S. Cl.:

CPC H10N52/80 (20230201); H10B61/00 (20230201); H10N52/01 (20230201);

Field of Classification Search

CPC: H01L (43/02); H01L (27/222); H01L (43/12); H01F (10/3254); H01F (10/3286); H01F (10/329); H01F (41/32); G11C (11/161)

USPC: 257/421

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
11244781	12/2021	Shibata	N/A	H10D 48/40
11653573	12/2022	Ashida	257/421	H10B 61/22
11696512	12/2022	Ota	257/427	H01F 10/3254
2002/0094457	12/2001	Krusin-Elbaum	N/A	B82Y 25/00
2005/0069732	12/2004	Kamata	N/A	G11B 5/74
2007/0218318	12/2006	Watanabe	428/836	G11B 5/7368
2008/0130355	12/2007	Saitoh	257/E27.005	G11C 11/1659
2011/0129691	12/2010	Ishiwata et al.	N/A	N/A
2012/0222940	12/2011	Ehresmann	137/13	B03C 3/28
2017/0241803	12/2016	Ausserlechner	N/A	G01D 5/145
2018/0130511	12/2017	Belashchenko	N/A	G11C 11/161
2019/0283127	12/2018	Kinouchi	N/A	B22F 3/02
2022/0007556	12/2021	Miyano	N/A	H01F 1/14708
2022/0376168	12/2021	Yamada	N/A	H10B 61/22

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
5441005	12/2013	JP	N/A
2006/046591	12/2005	WO	N/A
2009/101827	12/2008	WO	N/A

OTHER PUBLICATIONS

Feb. 17, 2022 Office Action issued in U.S. Appl. No. 16/760,169. cited by applicant
Mar. 19, 2019 International Search Report issued in International Patent Application No. PCT/JP2019/000323. cited by applicant

Background/Summary

TECHNICAL FIELD

(1) The present invention relates to a magnetic domain wall movement type magnetic recording element. Priority is claimed on Japanese Patent Application No. 2018-002469 and U.S. application Ser. No. 16/760,169, the content of which is incorporated herein by reference.

BACKGROUND ART

(2) As a next-generation non-volatile memory which replaces a flash memory or the like of which miniaturization has come to a limit, attention has been focused on a resistance change type magnetic recording device which stores data using a resistance change type element. Examples of the magnetic recording device include a magnetoresistive random access memory (MRAM), a resistance random access memory (ReRAM), a phase change random access memory (PCRAM), and the like.

(3) As a method of increasing a density (enlarging a capacity) of a memory, there is a method of multi-valuing recording bits per element constituting the memory, in addition to a method of reducing a size of the element itself constituting the memory.

(4) Patent Literature 1 describes a magnetic domain wall movement type magnetic recording element which can record multi-valued data by moving a magnetic domain wall in a magnetic recording layer. Patent Literature 1 describes that multi-valued data recording is stabilized by providing a trap site in a magnetic recording layer.

CITATION LIST

Patent Literature

(5) [Patent Literature 1] Japanese Patent No. 5441005

SUMMARY

Technical Problem

(6) The magnetic domain wall movement type magnetic recording element described in Patent Literature 1 has concavity and convexity on a side surface of the magnetic recording layer. The concavity and convexity serve as a trap site of the magnetic domain wall and control a position of the magnetic domain wall. However, in order to form the concavity and convexity on the side surface, it is necessary to perform post-processing after layers are laminated. In the case of the post-processing, damage or the like occurs on a lamination surface on which a ferromagnetic layer is laminated. The magnetic domain wall movement type magnetic recording element reads and writes data using a change in magnetoresistance. The change in magnetoresistance is caused by a change in the magnetization state between the magnetic recording layer and the ferromagnetic layer which sandwich a non-magnetic layer. Damage to the lamination surface causes a decrease in a magnetoresistance change rate (MR ratio). Further, Patent Literature 1 also describes that the trap site is provided on the lamination surface of the magnetic recording layer. Also in this case, the trap site reduces magnetization stability of a ferromagnetic body and causes noise.

(7) The present invention has been made in view of the above circumstances, and an object thereof is to provide a magnetic domain wall movement type magnetic recording element which controls movement of a magnetic domain wall, curbs a decrease in a magnetoresistance change rate (MR ratio), and has little noise.

Solution to Problem

(8) The present invention provides the following means to solve the above problems. (1) A magnetic domain wall movement type magnetic recording element according to a first aspect includes a first ferromagnetic layer which includes a ferromagnetic body, a non-magnetic layer

which faces the first ferromagnetic layer, and a magnetic recording layer which faces a surface of the non-magnetic layer on a side opposite to the first ferromagnetic layer and extends in a first direction, wherein a first surface of the magnetic recording layer which faces the non-magnetic layer has a smaller arithmetic average roughness than a second surface opposite to the first surface. (2) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the second surface may have a concave-convex structure, and in the concave-convex structure, apex positions of convex portions constituting the concave-convex structure may be irregular in a plan view in the lamination direction. (3) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the magnetic domain wall movement type magnetic recording element may further include: a coating layer in contact with the second surface of the magnetic recording layer. A third surface in contact with the second surface of the coating layer may have a larger arithmetic mean roughness than a fourth surface opposite to the third surface. (4) The magnetic domain wall movement type magnetic recording element according to the above-described aspect may further include a base body which faces the second surface of the magnetic recording layer, and an intermediate body which is located between the base body and the magnetic recording layer. (5) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the intermediate body may be a non-magnetic trap-reinforcing member, and the trap-reinforcing member may be layers which are scattered on one surface of the base body or a layer which has concavity and convexity on the second surface side of the magnetic recording layer. (6) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the intermediate body may have a trap-reinforcing member, and an insulating layer which covers the trap-reinforcing member from a position near the base body, and the trap-reinforcing member may be layers which are scattered on one surface of the base body or a layer which has concavity and convexity on the second surface side of the magnetic recording layer. (7) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, one end of the trap-reinforcing member may be in contact with the base body, and when a surface energy of a material constituting a surface of the base body is $\gamma_{\text{sub.A}}$, and a surface energy of a material of the trap-reinforcing member is $\gamma_{\text{sub.B}}$, $\gamma_{\text{sub.B}} < \gamma_{\text{sub.A}}$, and a surface energy mismatch $\Gamma_{\text{sub.AB}}$ defined by the following Equation (1) may be larger than 0.5.

[Math1]

$$(9) \quad \Gamma_{AB} = 2 \cdot \text{Math.} \frac{\gamma_{\text{sub.A}} - \gamma_{\text{sub.B}}}{\gamma_{\text{sub.A}} + \gamma_{\text{sub.B}}} \cdot \text{Math.} \quad (1) \quad (8) \text{ In the magnetic domain wall movement type}$$

magnetic recording element according to the above-described aspect, a plurality of recording parts which includes the first ferromagnetic layer, the nonmagnetic layer and the magnetic recording layer may be provided, the plurality of recording parts may be arranged in a second direction which intersects the first direction, and the trap-reinforcing member may spread in a same plane over the plurality of recording parts. (9) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, a plurality of recording parts which includes the first ferromagnetic layer, the nonmagnetic layer and the magnetic recording layer may be provided, and the trap-reinforcing member or a convex portion of the trap-reinforcing member may extend in a second direction which intersects the first direction over the plurality of recording parts. (10) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the second surface may have a concave-convex structure and the concave-convex structure may have periodicity in the first direction. (11) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the second surface may have a concave-convex structure and the concave-convex structure may have a concave portion or a convex portion having a first shape, and a concave portion or a convex portion having a second shape having a larger volume than that of the first shape. (12) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the concave

portion or the convex portion having the second shape may be located at a position at which the concave portion or the convex portion having the second shape overlaps an end surface of the first ferromagnetic layer in a plan view in the lamination direction. (13) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the concave or convex portion having the second shape may be larger than the concave or convex portion having the first shape in the first direction. (14) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the concave or convex portion having the second shape may be larger than the concave or convex portion having the first shape in the lamination direction. (15) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, a second ferromagnetic layer which reflects a magnetization state of the magnetic recording layer may be provided between the magnetic recording layer and the non-magnetic layer. (16) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the first ferromagnetic layer may be closer to a base body configured to support the first ferromagnetic layer, the non-magnetic layer, and the magnetic recording layer than the magnetic recording layer. (17) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the second surface may have a concave-convex structure, and in the concave-convex structure, apex positions of convex portions constituting the concave-convex structure may be irregular in a plan view in the lamination direction. (18) In the magnetic domain wall movement type magnetic recording element according to the above-described aspect, the magnetic recording layer may have a magnetic domain wall therein and the second surface may have a concave-convex structure within a movement range in which the magnetic domain wall is able to move. (19) A magnetic domain wall movement type magnetic recording element according to a second aspect includes a recording part which includes a magnetic recording layer which extends in a first direction which intersects a lamination direction, has a magnetic domain wall therein, and has a concave-convex structure which traps the magnetic domain wall, a first ferromagnetic layer which is laminated on the magnetic recording layer and includes a ferromagnetic body, a non-magnetic layer sandwiched between the first ferromagnetic layer and the magnetic recording layer, and a control part which has a planarization layer laminated on a side of the magnetic recording layer opposite to the first ferromagnetic layer and planarizes the concave-convex structure of the magnetic recording layer. The concave-convex structure is on a side opposite to the first ferromagnetic layer.

Advantageous Effects of Invention

(10) According to the magnetic domain wall movement type magnetic recording element of the above-described aspect, it is possible to control movement of a magnetic domain wall, to curb a decrease in a magnetoresistance change rate (MR ratio) and to have little noise.

Description

BRIEF DESCRIPTION OF DRAWINGS

(1) FIG. 1 is a cross-sectional view schematically showing a magnetic domain wall movement type magnetic recording element according to a first embodiment.

(2) FIG. 2 is an xz sectional view schematically showing a modified example of the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(3) FIG. 3 is a yz sectional view schematically showing a modified example of the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(4) FIG. 4 is an xz sectional view schematically showing a modified example of the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(5) FIG. 5 is a plan view schematically showing the magnetic domain wall movement type

magnetic recording element according to the first embodiment.

(6) FIG. 6A is an explanatory diagram of one example of a method for manufacturing the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(7) FIG. 6B is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(8) FIG. 6C is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(9) FIG. 6D is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(10) FIG. 6E is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(11) FIG. 6F is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(12) FIG. 7 is a cross-sectional view schematically showing a modified example of the magnetic domain wall movement type magnetic recording element according to the first embodiment.

(13) FIG. 8 is a cross-sectional view schematically showing a magnetic domain wall movement type magnetic recording element according to a second embodiment.

(14) FIG. 9A is an explanatory diagram of one example of a method for manufacturing the magnetic domain wall movement type magnetic recording element according to the second embodiment.

(15) FIG. 9B is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the second embodiment.

(16) FIG. 9C is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the second embodiment.

(17) FIG. 9D is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the second embodiment.

(18) FIG. 9E is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the second embodiment.

(19) FIG. 9F is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the second embodiment.

(20) FIG. 9G is an explanatory diagram of one example of the method for manufacturing the magnetic domain wall movement type magnetic recording element according to the second embodiment.

(21) FIG. 10 is a cross-sectional view schematically showing a modified example of the magnetic domain wall movement type magnetic recording element according to the second embodiment.

(22) FIG. 11 is a cross-sectional view schematically showing a magnetic domain wall movement type magnetic recording element according to a third embodiment.

(23) FIG. 12 is a cross-sectional view schematically showing the magnetic domain wall movement type magnetic recording element according to the third embodiment.

(24) FIG. 13 is a cross-sectional view schematically showing a magnetic domain wall movement

type magnetic recording element according to a fourth embodiment.

(25) FIG. **14** is a plan view schematically showing a magnetic domain wall movement type magnetic recording element according to a fifth embodiment.

(26) FIG. **15** is a plan view schematically showing a modified example of the magnetic domain wall movement type magnetic recording element according to the fifth embodiment.

(27) FIG. **16** is a schematic diagram of a magnetic recording array according to a sixth embodiment.

(28) FIG. **17** is an xz sectional view schematically showing a magnetic domain wall movement type magnetic recording element according to a seventh embodiment.

BEST MODE FOR CARRYING OUT THE INVENTION

(29) Hereinafter, embodiments will be described in detail with reference to the drawings as appropriate. In the drawings used in the following description, in order to make the characteristics of this invention easy to understand, parts which become features may be enlarged for convenience, and dimensional ratios and the like of the respective components may be different from actual ones. The materials, dimensions, and the like exemplified in the following description are merely examples, and the present invention is not limited thereto and can be implemented with appropriate modifications within a range in which effects of the present invention are exhibited.

Magnetic Domain Wall Movement Type Magnetic Recording Element

First Embodiment

(30) FIG. **1** is a cross-sectional view schematically showing a magnetic domain wall movement type magnetic recording element **100** according to a first embodiment. The magnetic domain wall movement type magnetic recording element **100** includes a recording part **60** and a control part **75**. The recording part **60** includes a first ferromagnetic layer **10**, a magnetic recording layer **20**, and a non-magnetic layer **30**. The recording part **60** is a part for writing and reading data. The control part **75** has a base body **80** and an intermediate body (a planarization layer) **70**. The control part **75** is a part provided for forming a concave-convex structure which controls movement of a magnetic domain wall **21** of the recording part **60**. The control part **75** indirectly controls the magnetic domain wall **21** of the recording part **60**, but the control part **75** does not actively control the movement of the magnetic domain wall **21**. The magnetic domain wall movement type magnetic recording element **100** shown in FIG. **1** includes a first electrode **41** and a second electrode **42** at positions which sandwich the first ferromagnetic layer **10** when seen in a lamination direction of the first ferromagnetic layer **10**.

(31) Hereinafter, a first direction in which the magnetic recording layer **20** extends is defined as an x direction, a second direction orthogonal to the x direction in a plane in which the magnetic recording layer **20** extends is defined as a y direction, and a third direction orthogonal to the x direction and the y direction is defined as a z direction. The lamination direction of the magnetic domain wall movement type magnetic recording element **100** shown in FIG. **1** coincides with the z direction. Further, in the specification, the expression “extending in the x direction” means, for example, that a dimension in the x direction is larger than a minimum dimension among dimensions in the x, y, and z directions. The same applies to the case of extending in other directions.

(32) “Recording Part”

(33) <First Ferromagnetic Layer>

(34) The first ferromagnetic layer **10** includes a ferromagnetic body. For example, the first ferromagnetic layer **10** includes a plurality of layers. Examples of a ferromagnetic material constituting the first ferromagnetic layer **10** include a metal selected from the group consisting of Cr, Mn, Co, Fe and Ni, an alloy containing at least one of these metals, an alloy containing these metals and at least one element of B, C, and N, and the like. Specifically, Co—Fe, Co—Fe—B, Ni—Fe, CoHo.sub.2, SmFe.sub.12 and the like can be used.

(35) The material forming the first ferromagnetic layer **10** may be a Heusler alloy. The Heusler

alloy is a half-metal and has a high spin polarization. The Heusler alloy is an intermetallic compound having a chemical composition of XYZ or X₂YZ, X is a Co-, Fe-, Ni-, or Cu-group transition metal element on the periodic table or a noble metal element, Y is a Mn-, V-, Cr- or Ti-group transition metal or an element represented by X, and Z is a typical element of group III to group V. Examples of the Heusler alloy include Co₂FeSi, Co₂FeGe, Co₂FeGa, Co₂MnSi, Co₂Mn_{1-a}Fe_aAl_bSi_{1-b}, and Co₂FeGe_{1-c}Ga_c, and the like.

(36) The first ferromagnetic layer **10** may be an in-plane magnetization film having an easy magnetization axis in an in-xy plane direction or may be a perpendicular magnetization film having an easy magnetization axis in the z direction. In FIG. 1, the first ferromagnetic layer **10** is assumed to be an in-plane magnetization film.

(37) When the easy magnetization axis of the first ferromagnetic layer **10** is set in the z direction (a perpendicular magnetization film), a thickness of the first ferromagnetic layer **10** is preferably 1.0 nm or more and 2.5 nm or less and more preferably 1.0 nm or more and 2.0 nm or less. When the first ferromagnetic layer **10** is formed to be thin, the first ferromagnetic layer **10** has perpendicular magnetic anisotropy (interface perpendicular magnetic anisotropy) due to an influence of an interface between the first ferromagnetic layer **10** and another layer (the non-magnetic layer **30**).

(38) <Magnetic Recording Layer>

(39) The magnetic recording layer **20** faces the first ferromagnetic layer **10**. Here, the term “facing” means opposing another layer and includes a case in which another layer is interposed therebetween. The non-magnetic layer **30** is sandwiched between the magnetic recording layer **20** and the first ferromagnetic layer **10**. The magnetic recording layer **20** is on one side (the lower side in FIG. 1) of the first ferromagnetic layer **10**. The magnetic recording layer **20** extends in a first direction (the x direction in FIG. 1) which intersects a lamination direction (the z direction in FIG. 1). The magnetic recording layer **20** has, for example, a rectangular shape which has a major axis in the x direction and a minor axis in the y direction in a plan view in the z direction.

(40) The magnetic recording layer **20** has a first surface **20A** which faces the non-magnetic layer **30**, and a second surface **20B** which is opposite to the first surface **20A**. The magnetic recording layer **20** has a concave-convex structure **24** which traps the magnetic domain wall **21** on the second surface **20B**. The first surface **20A** has a smaller arithmetic average roughness (Ra) or arithmetic surface roughness than the second surface **20B** and is flat. The arithmetic average roughness (Ra) is a value obtained by extracting a reference length in a direction of an average line from a roughness curve obtained by measuring the first surface **20A** or the second surface **20B** and summing and averaging absolute values of deviations from the average line of the extracted portion to the measure curve. The roughness curves of the first surface **20A** and the second surface **20B** are measured along the x direction. The average line is an average position of a height in the z direction and extends in the x direction. The arithmetic surface roughness is a parameter obtained by extending the arithmetic average roughness (Ra) in a surface direction and is an average of absolute values of height differences of respective points with respect to an average surface of the surface. A magnetic potential energy at a convex portion **24a** is lower than that at a concave portion **24b**. The magnetic domain wall **21** is easily trapped by the convex portion **24a**.

(41) The convex portions **24a** and the concave portions **24b** are periodically (equally spaced) or irregularly disposed in the x direction when seen in the z direction. When the convex portions **24a** and the concave portions **24b** are periodically disposed in the x direction (refer to FIG. 1), the magnetic domain walls **21** are trapped at predetermined intervals. As a result, the magnetic domain wall movement type magnetic recording element **100** can easily perform multi-valued data recording.

(42) FIG. 2 is a diagram schematically showing an xz cross section of another example of the magnetic domain wall movement type magnetic recording element according to the first embodiment. In a magnetic domain wall movement type magnetic recording element **100A** shown

in FIG. 2, a distance in the x direction between the adjacent convex portions **24a** is not constant, and widths of the convex portions **24a** in the x direction are also different from each other. The convex portions **24a** and the concave portions **24b** are disposed irregularly in the x direction. When the convex portions **24a** and the concave portions **24b** are disposed irregularly in the x direction, the magnetic domain wall **21** is trapped irregularly, and the movement of the magnetic domain wall **21** becomes smooth. As a result, the magnetic domain wall movement type magnetic recording element **100** can easily record data in an analog manner.

(43) Further, FIG. 3 is a diagram schematically showing a yz cross section of another example of the magnetic domain wall movement type magnetic recording element according to the first embodiment. In a magnetic domain wall movement type magnetic recording element **100B** shown in FIG. 3, a distance in the y direction between adjacent convex portions **24a** is not constant, and widths of the convex portions **24a** in the y direction are different from each other. The convex portions **24a** and the concave portions **24b** are disposed irregularly in the y direction. As shown in FIG. 3, the convex portions **24a** and the concave portions **24b** may be disposed irregularly in the y direction, there being no limitation to the x direction.

(44) Also, FIG. 4 is a diagram schematically showing an xz cross section of another example of the magnetic domain wall movement type magnetic recording element according to the first embodiment. In a magnetic domain wall movement type magnetic recording element **100C** shown in FIG. 4, a height of each of the convex portions **24a** in the z direction is not constant. As shown in FIG. 4, the height or depth of each of the convex portions **24a** and the concave portions **24b** may be irregular in the z direction, there being no limitation to the x direction.

(45) The magnetic recording layer **20** can have the magnetic domain wall **21** inside. The magnetic domain wall **21** is a boundary between a first magnetic domain **22** and a second magnetic domain **23** having magnetizations in directions opposite to each other. When two magnetic domains are formed inside, the magnetic recording layer **20** has the magnetic domain wall **21** inside. In the magnetic domain wall movement type magnetic recording element **100** shown in FIG. 1, the first magnetic domain **22** has a magnetization oriented in the +x direction, and the second magnetic domain **23** has a magnetization oriented in the -x direction.

(46) The magnetic domain wall movement type magnetic recording element **100** records data in a multi-valued or analog manner according to a position of the magnetic domain wall **21** of the magnetic recording layer **20**. Data recorded on the magnetic recording layer **20** is read as a change in resistance values of the first ferromagnetic layer **10** and the magnetic recording layer **20** in the lamination direction. When the magnetic domain wall **21** moves, the ratio between the first magnetic domain **22** and the second magnetic domain **23** in the magnetic recording layer **20** changes. The magnetization of the first ferromagnetic layer **10** is in the same direction as (parallel to) the magnetization of the first magnetic domain **22** and is in a direction opposite (anti-parallel) to the magnetization of the second magnetic domain **23**. When the magnetic domain wall **21** moves in the x direction and an area of the first magnetic domain **22** in a portion which overlaps the first ferromagnetic layer **10** when seen in the z direction increases, the resistance value of the magnetic domain wall movement type magnetic recording element **100** decreases. Conversely, when the magnetic domain wall **21** moves in the -x direction and an area of the second magnetic domain **23** in a portion which overlaps the first ferromagnetic layer **10** when seen in the z direction increases, the resistance value of the magnetic domain wall movement type magnetic recording element **100** increases.

(47) The magnetic domain wall **21** moves by causing a current to flow in a direction in which the magnetic recording layer **20** extends or by applying an external magnetic field. For example, when a current pulse is applied from the first electrode **41** to the second electrode **42**, the first magnetic domain **22** spreads in a direction of the second magnetic domain **23**, and the magnetic domain wall **21** moves in the direction of the second magnetic domain **23**. That is, the position of the magnetic domain wall **21** is controlled by setting a direction and intensity of the current flowing through the

first electrode **41** and the second electrode **42**, and data is written to the magnetic domain wall movement type magnetic recording element **100**.

(48) The magnetic recording layer **20** is configured of a magnetic body. The same magnetic body as that of the first ferromagnetic layer **10** can be used for the magnetic body constituting the magnetic recording layer **20**. Further, the magnetic recording layer **20** preferably contains at least one element selected from the group consisting of Co, Ni, Pt, Pd, Gd, Tb, Mn, Ge, and Ga. For example, a laminated film of Co and Ni, a laminated film of Co and Pt, a laminated film of Co and Pd, a MnGa-based material, a GdCo-based material, and a TbCo-based material can be used. Ferrimagnetic bodies such as MnGa-based materials, GdCo-based materials, and TbCo-based materials have a small saturation magnetization and can reduce a threshold current required for moving a magnetic domain wall. Furthermore, the laminated film of Co and Ni, the laminated film of Co and Pt, and the laminated film of Co and Pd have a large coercivity and can curb a movement speed of the magnetic domain wall.

(49) <Non-Magnetic Layer>

(50) The non-magnetic layer **30** is sandwiched between the first ferromagnetic layer **10** and the magnetic recording layer **20**. A known material can be used for the non-magnetic layer **30**. For example, when the non-magnetic layer **30** is made of an insulator (when it is a tunnel barrier layer), a material thereof may be Al.sub.2O.sub.3, SiO.sub.2, MgO, MgAl.sub.2O.sub.4, or the like. In addition, materials in which Al, Si, and Mg are partially replaced by Zn, Be, or the like can be used as the non-magnetic layer **30**. Among them, MgO and MgAl.sub.2O.sub.4 are materials capable of realizing coherent tunneling, and spin can be implanted efficiently. When the non-magnetic layer **30** is made of a metal, Cu, Au, Ag, or the like can be used as the material thereof. Furthermore, when the non-magnetic layer **30** is made of a semiconductor, the material thereof may be Si, Ge, CuInSe.sub.2, CuGaSe.sub.2, Cu(In, Ga)Se.sub.2, or the like.

(51) <First Electrode, Second Electrode>

(52) The first electrode **41** and the second electrode **42** are disposed at positions which sandwich the first ferromagnetic layer **10** in the x direction when seen in the z direction. The first electrode **41** and the second electrode **42** may be made of a conductive material such as Cu, Al, and Au. Further, the first electrode **41** may be a ferromagnetic body in which the magnetization is oriented in the x direction, and the second electrode **42** may be a ferromagnetic body in which the magnetization is oriented in the -x direction. When a current passes through the first electrode **41** or the second electrode **42**, the current is spin-polarized. When the spin-polarized current is applied to the magnetic recording layer **20**, the ratio between the first magnetic domain **22** and the second magnetic domain **23** of the magnetic recording layer **20** changes.

(53) The first electrode **41** and the second electrode **42** may be replaced with spin-orbit torque wiring. For example, spin-orbit torque wiring which extends in the y direction is arranged at the positions of the first electrode **41** and the second electrode **42**. When a current flows through the spin-orbit torque wiring, a spin Hall effect occurs in the spin-orbit torque wiring. When the spin polarized by the spin Hall effect flows into the magnetic recording layer **20**, the ratio between the first magnetic domain **22** and the second magnetic domain **23** of the magnetic recording layer **20** changes. Both the first electrode **41** and the second electrode **42** may be replaced with the spin-orbit torque wiring, or only one thereof may be replaced. When both are replaced with the spin-orbit torque wiring, the direction of current flowing is reversed.

(54) The first electrode **41** and the second electrode **42** may not be provided. In this case, the magnetic domain wall of the magnetic recording layer **20** is moved by an external magnetic field.

(55) "Control Part"

(56) <Intermediate Body (Planarization Layer)>

(57) The intermediate body **70** is located between the base body **80** and the magnetic recording layer **20**. For example, the intermediate body **70** is in contact with the second surface **20B** of the magnetic recording layer **20**. The intermediate body **70** fills the concave-convex structure **24** on the

second surface **20B** of the magnetic recording layer **20** and makes it flat. When seen from the magnetic recording layer **20**, the intermediate body **70** can be regarded as a planarization layer. Furthermore, the intermediate **70** is also a covering layer which covers the second surface **20B** of the magnetic recording layer **20**.

(58) The intermediate body **70** shown in FIG. **1** is a layer having concavity and convexity on a first surface **70A** on a second surface **20B** side of the magnetic recording layer **20**. The first surface **70A** has a larger arithmetic average roughness than the second surface **70B**. The first surface **70A** is an example of a third surface of the claims and the second surface **70B** is an example of a fourth surface of the claims. The first surface **70A** of the intermediate body **70** has a concave-convex structure **74** including a convex portion **74a** and a concave portion **74b**. The magnetic recording layer **20B** is laminated on the first surface **70A** of the intermediate body **70**. The concave-convex structure **24** of the magnetic recording layer **20B** is formed by the concave-convex structure **74** on the first surface **70A** of the intermediate body **70**. The convex portion **74a** of the intermediate body **70** corresponds to the concave portion **24b** of the magnetic recording layer **20**, and the concave portion **74b** of the intermediate body **70** corresponds to the convex portion **24a** of the magnetic recording layer **20**.

(59) The intermediate body **70** shown in FIG. **1** is a non-magnetic body. The intermediate body **70** shown in FIG. **1** is an example of a trap-reinforcing member which will be described later. When a surface of the base body **80** is formed of an insulator, the intermediate body **70** may be a conductor or an insulator. When the surface of the base body **80** is a conductor, the intermediate body **70** is preferably an insulator. When the intermediate body **70** has an insulating property, a current flowing between the first electrode **41** and the second electrode **42** can be prevented from flowing through a portion other than the magnetic recording layer **20**. When resistance of the intermediate body **70** is sufficiently higher than that of the magnetic recording layer **20**, a conductor, a semiconductor, or the like may be used for the intermediate body **70**.

(60) A thickness of the intermediate body **70** is preferably 20 nm or less, more preferably 10 nm or less, and even more preferably 5 nm or less. The thickness of the intermediate body **70** is preferably 2 nm or more. Here, the thickness of the intermediate body **70** is a distance between an average height position of the first surface **70A** and the second surface **70B** of the intermediate body **70**. The average height position is a position obtained by averaging the height positions of concavity and convexity on the first surface **70A** and can be confirmed by a transmission electron microscope. When the thickness of the intermediate body **70** is within the above-described range, the concave-convex structure **74** having a sufficient concave-convex difference on the first surface **70A** of the intermediate body **70** can be formed.

(61) FIG. **5** is a plan view schematically showing the magnetic domain wall movement type magnetic recording element **100** according to the first embodiment. In FIG. **5**, the convex portions **74a** of the intermediate body **70** are irregularly disposed in a xy plane. Here, the term “irregular” in this specification means that a distance between vertices of the adjacent convex portions **74a** is not constant. The fact that the distance between the vertices of the adjacent convex portions **74a** is not constant is obtained as follows. First, the distances **L1**, **L2**, **L3**, . . . between the vertices of the convex portions **74a** located at positions which overlaps the magnetic recording layer **20** are determined. Then, a most frequent value of the distances between the vertices of the convex portions **74a** is obtained. When each of the distances **L1**, **L2**, **L3**, . . . between the vertices of the convex portions **74a** is within a range of $\pm 5\%$ of the most frequent value, the distances between the vertices of the adjacent convex portion **74a** are considered to be constant. Conversely, when the condition is not satisfied, it can be determined that the distances between the vertices of the adjacent convex portions **74a** are not constant and the convex portions **74a** are irregularly disposed in the xy plane. The magnetic recording layer **20**, the non-magnetic layer **30**, and the first ferromagnetic layer **10** are sequentially laminated on the intermediate body **70**. The convex portion **24a** and the concave portion **24b** of the magnetic recording layer **20** are formed irregularly. FIG. **5**

shows an example in which the convex portions **74a** of the intermediate body **70** are irregular, but the convex portions **74a** of the intermediate body **70** may be disposed regularly.

(62) <Base Body>

(63) The base body **80** has, for example, a substrate and an underlayer laminated on one surface of the substrate on the intermediate body **70** side. The substrate is, for example, a semiconductor substrate such as silicon. The base body **80** may have only the substrate without the underlayer.

(64) <Underlayer>

(65) The underlayer is, for example, Fe, Cu, Ni, Co, Si, SiO.sub.2, Al.sub.2O.sub.3, MgO, or the like. The concavity and convexity on the first surface **70A** of the intermediate body **70** are formed in relation to the underlayer. For example, crystal growth of the intermediate body **70** becomes granular due to the underlayer, and the concavity and convexity are formed on the first surface **70A** of the intermediate body **70**. In addition, for example, the concavity and convexity are formed on the first surface **70A** of the intermediate body **70** using the difference in surface energy between the underlayer and the intermediate body **70**.

(66) Next, an example of a method for manufacturing the magnetic domain wall movement type magnetic recording element **100** according to the first embodiment will be described with reference to FIGS. **6A** to **6F**.

(67) First, the base body **80** is prepared. The base body **80** has a substrate **81** and an underlayer **82**. Then, as shown in FIG. **6A**, the intermediate body **70** is formed on one surface of the underlayer **82**. The intermediate body **70** is laminated by, for example, a sputtering method, a chemical vapor deposition (CVD) method, or the like. The first surface **70A** of the intermediate body **70** has concavity and convexity in relation to the underlayer **82**. For example, when a crystal of the intermediate body **70** and a crystal of the underlayer **82** have different lattice constants, a crystal structure is disturbed to reduce the difference in the lattice constant, and the concavity and convexity are formed on the first surface **70A**. Also, for example, when there is a difference in surface energy between the underlayer **82** and the intermediate body **70**, the concavity and convexity are formed on the first surface **70A**. For example, atoms constituting the intermediate body **70** sputtered on one surface of the underlayer **82** aggregate with each other due to the difference in the surface energy. The atoms which are aggregated together are scattered in an island shape. When film formation of the intermediate body **70** is continued, the islands are combined with each other, and the intermediate body **70** having the concavity and convexity on the first surface **70A** is formed. The positions in the x direction and the positions in the y direction of the convex portions of the concavity and convexity formed on the first surface **70A** may be regular or irregular, and the heights of the convex portions in the z direction may be constant or different.

(68) Next, as shown in FIG. **6B**, a magnetic body **28** is laminated on one surface of the intermediate body **70**. A first surface **28A** of the magnetic body **28** has concavity and convexity which reflect a shape of the first surface **70A** of the intermediate body **70**.

(69) Further, as shown in FIG. **6C**, anisotropic sputtering may be performed when the magnetic body **28** is laminated. The anisotropic sputtering is a method in which ions are sputtered to a film-forming object (the intermediate body **70**) in an oblique direction. When ions are supplied in an oblique direction, a film forming speed changes in a plane of the film-forming body (the intermediate body **70**), and the first surface **28A** of the magnetic body **28** is planarized with respect to the first surface **70A** of the intermediate body **70**.

(70) Next, as shown in FIG. **6D**, the first surface **28A** of the magnetic body **28** is planarized. The planarization is performed by, for example, chemical mechanical polishing, dry etching, wet etching, or the like. As shown in FIG. **6C**, when the anisotropic sputtering is performed, a process in which the first surface **28A** is planarized may not be performed.

(71) Next, as shown in FIG. **6E**, a magnetic body **29** is laminated on the first surface **28A** of the magnetic body **28**. The magnetic body **28** and the magnetic body **29** are the same. The magnetic body **28** and the magnetic body **29** are combined to form the magnetic recording layer **20**.

(72) Next, as shown in FIG. 6F, the non-magnetic layer **30** and the first ferromagnetic layer **10** are sequentially laminated on one surface of the magnetic recording layer **20**. Then, unnecessary portions of the non-magnetic layer **30** and the first ferromagnetic layer **10** are removed by photolithography or the like. With such a procedure, the magnetic domain wall movement type magnetic recording element **100** according to the first embodiment can be manufactured.

(73) As described above, since the magnetic domain wall movement type magnetic recording element **100** according to the first embodiment has the concave-convex structure **24** on a surface of the magnetic recording layer **20** on the back surface side (the side opposite to the first ferromagnetic layer **10**), and the concave-convex structure **24** serves as a trap site for the magnetic domain wall **21**, controllability of the movement of the magnetic domain wall **21** can be improved. Further, the second surface **20B** on which the concave-convex structure **24** is formed corresponds to a back surface of the first surface **20A** on which the first ferromagnetic layer **10** is laminated, and has little effect on the MR ratio of the magnetic domain wall movement type magnetic recording element **100**. That is, noise of the magnetic domain wall movement type magnetic recording element **100** can be curbed.

(74) Further, when a trap site is separately provided around the magnetic recording layer **20**, it is necessary to maintain a predetermined distance between the magnetic recording layer **20** and the trap site due to a process restriction. On the other hand, in the embodiment, the back surface of the magnetic recording layer **20** is the trap site, the magnetic domain wall **21** can be trapped at a closer position than a case in which the trap site is provided around the magnetic recording layer **20**, and thus the controllability of the movement of the magnetic domain wall **21** can be further improved. Further, when the trap site is provided on a side surface of the magnetic recording layer **20**, the concavity and convexity in which a difference between the concavity and convexity is about a few tens of nm are formed on the side surface due to a problem of processing accuracy of photolithography or the like. In other words, an extra space of about a few tens of nm is required outside the first ferromagnetic layer **10**. On the other hand, the magnetic domain wall movement type magnetic recording element **100** according to the embodiment has the trap site in the z direction and does not require an extra space in the xy directions.

(75) Further, since the magnetic domain wall movement type magnetic recording element **100** according to the embodiment does not have the concave-convex structure **24** on the surface side (the first ferromagnetic layer **10** side), a problem that noise is generated when a density of a current flowing on the surface side becomes discontinuous in the concave-convex structure can be avoided.

(76) Further, the magnetic domain wall movement type magnetic recording element **100** according to the embodiment does not require physical processing of the first ferromagnetic layer in the manufacturing process and can also avoid a problem that noise is generated at the time of operation due to an effect of processing damage.

(77) Although an example of the first embodiment has been described in detail, the first embodiment is not limited to this example, and various modifications and changes may be made within the scope of the present invention described in the appended claims.

(78) FIG. 7 is a cross-sectional view schematically showing Modified Example 1 of the magnetic domain wall movement type magnetic recording element according to the first embodiment. A magnetic domain wall movement type magnetic recording element **100D** according to Modified Example 1 is different from the magnetic domain wall movement type magnetic recording element **100** shown in FIG. 1 in that the intermediate body **70** has no layer formed and is scattered on one surface of the base body **80**. Also in this case, the second surface **20B** of the magnetic recording layer **20** has the concave-convex structure **24**, and the same effect as in the magnetic domain wall movement type magnetic recording element **100** can be obtained.

(79) The magnetic domain wall movement type magnetic recording element **100D** according to Modified Example 1 is manufactured by stopping the film formation of the intermediate body **70** before the islands are combined when the intermediate body **70** is laminated.

Second Embodiment

(80) FIG. 8 is a schematic cross-sectional view of a magnetic domain wall movement type magnetic recording element according to a second embodiment. The magnetic domain wall movement type magnetic recording element **101** shown in FIG. 8 is different from the magnetic domain wall movement type magnetic recording element **100** shown in FIG. 1 in that the intermediate body **70** includes a trap-reinforcing member **90** and an insulating layer **91** which covers the trap-reinforcing member **90** from a position near the base body **80**. The same parts as those of the magnetic domain wall movement type magnetic recording element **100** are designated by the same reference numerals, and description thereof will be omitted.

(81) In FIG. 8, the trap-reinforcing member **90** is scattered on one surface of the base body **80**. The trap-reinforcing member **90** may be made of a non-magnetic material such as Ta, Al, or Cu, or may be made of a magnetic material such as Ni, Fe, or Co. When the trap-reinforcing member **90** is made of a non-magnetic material, the difference in magnetic potential energy can be clarified between the convex portion **24a** and the concave portion **24b** in the concave-convex structure **24** of the magnetic recording layer, and a magnetic domain wall trapping function can be enhanced. Further, when the trap-reinforcing member **90** is made of a magnetic material, the magnetic domain wall **21** can be trapped more strongly by magnetically coupling with the magnetization of the magnetic recording layer **20**, as compared with the case in which the trap-reinforcing member **90** is made of a non-magnetic material.

(82) When a film is formed by sputtering a material to form the insulating layer **91** after the trap-reinforcing member **90** is formed, according to film forming conditions, the ratio of the thickness of a planarization material to be formed can be adjusted at an upper surface and a side surface of the trap-reinforcing member **90**. At this time, the ratio between the width of the trap-reinforcing member **90** and the thickness of the planarization material is 1:1 to 2:1. Therefore, in an extending direction (the x direction) of the magnetic recording element **20**, the width of the trap-reinforcing member **90** is about 0.3 to 0.5 times the width of the concave portion **24b**.

(83) The insulating layer **91** covers the surface of the trap-reinforcing member **90** scattered in an island shape. The insulating layer **91** is formed by reflecting surface shapes of the base body **80** and the trap-reinforcing member **90**. Therefore, the concave-convex structure **74** including the convex portion **74a** and the concave portion **74b** is formed on the first surface **70A** of the intermediate body **70**. Since the magnetic recording layer **20** is formed on the first surface **70A** of the intermediate body **70**, the second surface **20B** has the concave-convex structure **24**.

(84) In the insulating layer **91**, at least a portion between an inner wall of the concave portion **24b** and the trap-reinforcing member **90** has insulating properties. The insulating layer **91** preferably has insulating properties as a whole. The insulating layer **91** electrically separates the magnetic recording layer **20** from the base body **80**. The base body **80** is formed on the side of the intermediate body **70** opposite to the magnetic recording layer **20**. The base body **80** is in contact with one end of the trap-reinforcing member **90**.

(85) When a surface energy of a material constituting the surface of the base body **80** is $\gamma_{\text{sub.A}}$, and a surface energy of a material of the trap-reinforcing member **90** is $\gamma_{\text{sub.B}}$, $\gamma_{\text{sub.B}} < \gamma_{\text{sub.A}}$, and a surface energy mismatch $\Gamma_{\text{sub.AB}}$ defined by the following Equation (1) is preferably larger than 0.5. Here, the material constituting the surface of the base body **80** is a material which constitutes the underlayer when the base body **80** is formed of the substrate and the base layer, and the material is a material which constitutes the substrate when the base body **80** is formed of the substrate. In the first embodiment, the material constituting the intermediate body **70** and the material constituting the surface of the base body **80** also preferably satisfy the same relationship.

[Math2]

(86)
$$\Gamma_{AB} = 2 \cdot \frac{\gamma_{\text{sub.A}} - \gamma_{\text{sub.B}}}{\gamma_{\text{sub.A}} + \gamma_{\text{sub.B}}} \quad (1)$$

(87) When the surface energy of the surface of the base body **80** and the surface energy of the trap-

reinforcing member **90** satisfy the above relationship, the trap-reinforcing member **90** grows in an island shape only by performing a film forming process. In this case, since patterning for forming the trap-reinforcing member **90** is not required, the manufacturing process can be simplified.

(88) Table 1 shows an example of a combination of materials of the surface of the base body **80** and the trap-reinforcing member **90** which satisfies the above relationship.

(89) TABLE-US-00001 TABLE 1 Base body Trap-reinforcing member Material γ .sub.A(mNm.sup.-1) Material γ .sub.B(mNm.sup.-1) Γ .sub.AB Al 1085 SiO.sub.2 290 1.16 1085 Al.sub.2O.sub.3 580 0.61 1085 MgO 520 0.70 Si 1107 SiO.sub.2 290 1.17 1107 Al.sub.2O.sub.3 580 0.62 1107 MgO 520 0.72 Au 1616 SiO.sub.2 290 1.39 1616 Al.sub.2O.sub.3 580 0.94 1616 MgO 520 1.03 1616 Al 1085 0.39 Cu 1934 SiO.sub.2 290 1.48 1934 Al.sub.2O.sub.3 580 1.08 1934 MgO 520 1.15 1934 Al 1085 0.56 Pd 2043 SiO.sub.2 290 1.50 2043 Al.sub.2O.sub.3 580 1.12 2043 MgO 520 1.19 2043 Al 1085 0.61 Cr 2056 SiO.sub.2 290 1.51 2056 Al.sub.2O.sub.3 580 1.12 2056 MgO 520 1.19 2056 Al 1085 0.62 Ti 2570 SiO.sub.2 290 1.59 2570 Al.sub.2O.sub.3 580 1.26 2570 MgO 520 1.33 2570 Al 1085 0.81 Pt 2691 SiO.sub.2 290 1.61 2691 Al.sub.2O.sub.3 580 1.29 2691 MgO 520 1.35 2691 Al 1085 0.85 Ta 3018 SiO.sub.2 290 1.65 3018 Al.sub.2O.sub.3 580 1.36 3018 MgO 520 1.41 3018 Al 1085 0.94 Ru 3409 SiO.sub.2 290 1.69 3409 Al.sub.2O.sub.3 580 1.42 3409 MgO 520 1.47 3409 Al 1085 1.03 Al.sub.2O.sub.3 580 SiO.sub.2 290 0.67 MgO 520 SiO.sub.2 290 0.57

(90) Next, an example of a method for manufacturing the magnetic domain wall movement type magnetic recording element **101** according to the second embodiment will be described with reference to FIGS. **9A** to **9F**.

(91) First, the base body **80** is prepared. The base body **80** includes the substrate **81** and the underlayer **82**. Next, as shown in FIG. **9A**, the trap-reinforcing member **90** is formed on one surface of the underlayer **82**. The trap-reinforcing member **90** is laminated by, for example, a sputtering method, a chemical vapor deposition (CVD) method, or the like. The trap-reinforcing member **90** grows in an island shape. When a film is formed under a condition that the thickness of the trap-reinforcing member **90** is equal to or less than the thickness at which the trap-reinforcing member **90** becomes a layer, the trap-reinforcing member **90** grows into a nucleus and has an island shape. The condition that the thickness of the trap-reinforcing member **90** is equal to or less than the thickness at which the trap-reinforcing member **90** becomes a layer is a condition that is equal to or less than a condition that the trap-reinforcing member **90** theoretically has a thickness corresponding to several atomic layers. Even under the condition of a film having a thickness corresponding to several atomic layers being formed theoretically, the islands which are grown into a nucleus are not actually combined, and thus the trap-reinforcing member **90** is scattered in an island shape. Also, for example, when the trap-reinforcing member **90** is selected in consideration of the difference in the surface energy with respect to the underlayer **82**, the trap-reinforcing member **90** is formed in an island shape.

(92) Next, as shown in FIG. **9B**, the insulating layer **91** is laminated on one surface of the trap-reinforcing member **90**. The insulating layer **91** covers the surfaces of the base body **80** and the trap-reinforcing member **90**. As a result, the first surface **70A** of the intermediate body **70** has the concavity and convexity.

(93) Next, as shown in FIG. **9C**, the magnetic body **28** is laminated on one surface of the intermediate body **70**. The first surface **28A** of the magnetic body **28** has the concavity and convexity which reflect the shape of the first surface **70A** of the intermediate body **70**.

(94) Further, as shown in FIG. **9D**, the anisotropic sputtering may be performed when the magnetic body **28** is laminated. The first surface **28A** of the magnetic body **28** is planarized with respect to the first surface **70A** of the intermediate body **70**.

(95) Next, as shown in FIG. **9E**, the first surface **28A** of the magnetic body **28** is planarized. The planarization is performed by, for example, chemical mechanical polishing, dry etching, wet etching, or the like. As shown in FIG. **9D**, when the first surface **28A** is planarized by another

method, the planarizing process may not be performed.

(96) Next, as shown in FIG. 9F, the magnetic body **29** is laminated on the first surface **28A** of the magnetic body **28**. The magnetic body **28** and the magnetic body **29** are the same. The magnetic body **28** and the magnetic body **29** are combined to form the magnetic recording layer **20**.

(97) Next, as shown in FIG. 9E, the non-magnetic layer **30** and the first ferromagnetic layer **10** are sequentially laminated on one surface of the magnetic recording layer **20**. Then, the unnecessary portions of the non-magnetic layer **30** and the first ferromagnetic layer **10** are removed by photolithography or the like. With such a procedure, the magnetic domain wall movement type magnetic recording element **101** according to the second embodiment can be manufactured.

(98) In the magnetic domain wall movement type magnetic recording element **101** according to the embodiment, the trap-reinforcing member **90** is covered with the insulating layer **91**. The insulating layer **91** electrically separates the magnetic recording layer **20** from the base body **80**. Therefore, the degree of freedom in selecting the trap-reinforcing member **90** is increased. Thus, the controllability of the movement of the magnetic domain wall **21** can be further enhanced as compared with the magnetic domain wall movement type magnetic recording element **100** of the first embodiment.

(99) Although an example of the second embodiment has been described in detail, the second embodiment is not limited to this example, and various modifications and changes may be made within the scope of the present invention described in the appended claims. For example, the second embodiment can employ the same modified example as the first embodiment.

(100) FIG. **10** is a cross-sectional view schematically showing Modified Example 2 of the magnetic domain wall movement type magnetic recording element according to the second embodiment. A magnetic domain wall movement type magnetic recording element **101A** according to Modified Example 2 is different from the magnetic domain wall movement type magnetic recording element **100** shown in FIG. **1** in that the adjacent trap-reinforcing members **90** are combined with each other and a layer is formed. The trap-reinforcing member **90** is a layer having concavity and convexity. The insulating layer **91** reflects the surface shape of the trap-reinforcing member **90**. Therefore, the first surface **70A** of the intermediate body **70** has the concave-convex structure **74**. Also in this case, the second surface **20B** of the magnetic recording layer **20** has the concave-convex structure **24**, and the same effect as in the magnetic domain wall movement type magnetic recording element **101** can be obtained.

(101) The magnetic domain wall movement type magnetic recording element **101A** according to Modified Example 2 is manufactured by continuing the film formation until islands are combined with each other when the trap-reinforcing member **90** is laminated.

Third Embodiment

(102) FIGS. **11** and **12** are schematic cross-sectional views of magnetic domain wall movement type magnetic recording elements according to a third embodiment. The magnetic domain wall movement type magnetic recording elements **102** and **103** shown in FIGS. **11** and **12** are different from the magnetic domain wall movement type magnetic recording element **101** shown in FIG. **1** in that, in the concave-convex structure **24** of the magnetic recording layer, some of the concave portions or the convex portions (the convex portions or the concave portions having a second shape) have different shapes from other concave portions or convex portions (the convex portions or the concave portions having a first shape). When the first shape is a convex portion, the second shape is a convex portion, and when the first shape is a concave portion, the second shape is a concave portion. The same parts as those of the magnetic domain wall movement type magnetic recording element according to the first embodiment are designated by the same reference numerals, and description thereof will be omitted. Hereinafter, a case in which the first shape is the convex portion **25** and the second shape is the convex portion **24a** will be described as an example.

(103) In the magnetic domain wall movement type magnetic recording element **102** shown in FIG. **11**, the convex portion **25** having the second shape (hereinafter, referred to as a first convex portion

25) in the concave-convex structure **24** of the magnetic recording layer **20** is larger than the convex portion **24a** having the first shape in the xz cross section in the extending direction (the x direction, a first direction) of the magnetic recording layer. Therefore, since the first convex portion **25** has a larger volume than the other convex portions **24a**, the intensity of a generated magnetic field is large, and the movement of the magnetic domain wall **21** can be more strongly restricted than by the other convex portion **24a**. In a plan view from the z direction, at least a part of the first convex portion **25** is located inward from the first ferromagnetic layer **10** and overlaps an end surface of the first ferromagnetic layer **10**. When the end surface of the first ferromagnetic layer **10** is inclined, the end surface may overlap any part of the end surface. In a plan view, when the entire first convex portion **25** is located inward from the first ferromagnetic layer **10** and overlaps the end surface of the first ferromagnetic layer **10**, the movement range of the magnetic domain wall **21** is controlled to be within a range which overlaps the first ferromagnetic layer **10**. The resistance value of the magnetic domain wall movement type magnetic recording element **102** changes due to the difference in the magnetization state between the first ferromagnetic layer **10** and the magnetic recording layer **20**. Even when the magnetic domain wall **21** moves to a position at which it does not overlap the first ferromagnetic layer **10**, a change in the resistance value does not occur. That is, it is possible to suppress the magnetic domain wall **21** from reaching a portion that does not affect the change in the resistance value by controlling the movement range of the magnetic domain wall **21**. Further, the range of the change in the resistance value of the magnetic domain wall movement type magnetic recording element **102** can be specified by defining the movement range of the magnetic domain wall **21**.

(104) In the magnetic domain wall movement type magnetic recording element **103** shown in FIG. **12**, a convex portion **26** having the second shape (hereinafter, referred to as a second convex portion **26**) in the concave-convex structure **24** of the magnetic recording layer **20** is larger than the convex portion **24a** having the first shape in the xz cross section in the thickness direction (the z direction) of the magnetic recording layer. Therefore, since the second convex portion **26** has a larger volume than the other convex portion **24a**, the intensity of a generated magnetic field is large, and the movement of the magnetic domain wall **21** can be more strongly restricted than by the other convex portion **24a**. In a plan view from the z direction, at least a part of the second convex portion **26** is located inward from the first ferromagnetic layer **10** and overlaps an end surface of the first ferromagnetic layer **10**. Thus, the movement range of the magnetic domain wall **21** can be controlled, and it is possible to suppress the magnetic domain wall **21** from reaching a portion that does not affect the change in the resistance value. Further, the range of the change in the resistance value of the magnetic domain wall movement type magnetic recording element **103** can be specified by defining the movement range of the magnetic domain wall **21**.

(105) Here, although the volumes of the convex portions **25** and **26** having the second shape and the convex portion **24a** having the first shape are compared, the comparison may be made based on areas of the convex portions **25** and **26** having the second shape and the convex portion **24a** having the first shape in the xz cross section. The difference in the intensity of the magnetic field in the x direction controls the movement of the magnetic domain wall **21** in the x direction. Therefore, even when the volume is constant, the movement range of the magnetic domain wall **21** can be restricted when there is a difference between the convex portions **25** and **26** having the second shape and the convex portion **24a** having the first shape in the xz cross section.

(106) In the magnetic domain wall movement type magnetic recording elements **102** and **103** according to the third embodiment, the trapping function can be locally strengthened at positions of the convex portions larger than other convex portions, such as the first convex portion **25** and the second convex portion **26**, and thus the movement speed of the magnetic domain wall **21** in the vicinity thereof can be largely changed. Therefore, when electric resistance and the like are continuously measured while the magnetic domain wall **21** is moved, a change point occurs in measurement data, and a position of the magnetic domain wall **21** below the first ferromagnetic

layer **10** can be detected from this change point.

(107) The change in the resistance value of the magnetic domain wall movement magnetic recording elements **102** and **103** occurs when the magnetic domain wall **21** is present at a position at which it overlaps the first ferromagnetic layer **10** in a plan view. The concave portion or the convex portion of the second shape having a strong trapping function is preferably located at a position at which it overlaps the first ferromagnetic layer **10** in a plan view in the lamination direction L of the recording part **60**. Further, the concave or convex portion having the second shape is preferably disposed inward from an end portion of the first ferromagnetic layer **10** in the x direction and more preferably overlaps the end portion of the first ferromagnetic layer **10**. When there is the concave or convex portion of the second shape having the strong trapping function at a position at which it overlaps both ends of the first ferromagnetic layer **10** in the x direction, an upper limit and a lower limit of the change in the resistance value are easily determined. That is, a start point and an end point of the multi-valued recording can be clarified, and reliability of data of the magnetic domain wall movement type magnetic recording elements **102** and **103** can be improved.

(108) Although changing of the shape of the convex portion in the cross sections of the magnetic domain wall movement type magnetic recording elements **102** and **103** has been described, for example, the shape of the convex portion may be changed in a plan view shape in the lamination direction L. Further, as a method other than changing the shape, for example, even when the trap-reinforcing member **90** shown in the second embodiment is provided only in some of the concave portions, the same effect as when the shape of the convex portion is changed can be obtained. Furthermore, even when the trap-reinforcing members **90** are provided in all the concave portions and only the trap-reinforcing members **90** provided in some of the concave portions are made of a material having a relatively strong trapping function, the same effect can be obtained.

Fourth Embodiment

(109) FIG. **13** is a schematic cross-sectional view of a magnetic domain wall movement type magnetic recording element according to a fourth embodiment. The magnetic domain wall movement type magnetic recording element **104** shown in FIG. **13** is different from the magnetic domain wall movement type magnetic recording element **100** shown in FIG. **1** in that a second ferromagnetic layer **50** which reflects the magnetization state of the magnetic recording layer **20** is provided between the magnetic recording layer **20** and the non-magnetic layer **30**. The same parts as those of the magnetic domain wall movement type magnetic recording element **100** according to the first embodiment are designated by the same reference numerals, and description thereof will be omitted. The constitution of the magnetic domain wall movement type magnetic recording element according to the fourth embodiment can be applied to any of the elements according to the first to third embodiments.

(110) The second ferromagnetic layer **50** includes a magnetic body. The same magnetic body as that of the first ferromagnetic layer **10** can be used for a magnetic body constituting the second ferromagnetic layer **50**.

(111) The second ferromagnetic layer **50** is adjacent to the magnetic recording layer **20**. The magnetization of the second ferromagnetic layer **50** is magnetically coupled to the magnetization of the magnetic recording layer **20**. Therefore, the second ferromagnetic layer **50** reflects a magnetic state of the magnetic recording layer **20**. When the second ferromagnetic layer **50** and the magnetic recording layer **20** are ferromagnetically coupled, the magnetic state of the second ferromagnetic layer **50** becomes the same as the magnetization state of the magnetic recording layer **20**, and when the second ferromagnetic layer **50** and the magnetic recording layer **20** are antiferromagnetically coupled, the magnetic state of the second ferromagnetic layer **50** is opposite to the magnetization state of the magnetic recording layer **20**.

(112) When the second ferromagnetic layer **50** is inserted between the magnetic recording layer **20** and the non-magnetic layer **30**, functions of the second ferromagnetic layer **50** and the magnetic

recording layer **20** in the magnetic domain wall movement type magnetic recording element **104** can be separated. The MR ratio of the magnetic domain wall movement type magnetic recording element **104** is caused by a change in the magnetization state of two magnetic bodies (the first ferromagnetic layer **10** and the second ferromagnetic layer **50**) which sandwich the non-magnetic layer **30**. Therefore, the second ferromagnetic layer **50** can mainly have a function of improving the MR ratio, and the magnetic recording layer **20** can mainly have a function of moving the magnetic domain wall **21**.

(113) When the functions of the second ferromagnetic layer **50** and the magnetic recording layer **20** are separated, the degree of freedom of the magnetic body constituting each increases. The second ferromagnetic layer **50** can be made of a material which provides a coherent tunnel effect with the first ferromagnetic layer **10**, and the magnetic recording layer **20** can be made of a material which reduces the movement speed of the magnetic domain wall.

(114) As described above, also in the magnetic domain wall movement type magnetic recording element **104** according to the fourth embodiment, the same effect as that in the first embodiment can be obtained. Further, the degree of freedom in selecting materials used for the layers can be increased by inserting the second ferromagnetic layer **50**. In addition, the MR ratio of the magnetic domain wall movement type magnetic recording element **104** can be further increased by increasing the degree of freedom in selecting materials.

Fifth Embodiment

(115) FIG. **14** is a schematic plan view of a magnetic domain wall movement type magnetic recording element **105** according to a fifth embodiment in which “a configuration having a plurality of recording parts **60**” is added to the second embodiment. The magnetic domain wall movement type magnetic recording element **105** shown in FIG. **14** is different from the magnetic domain wall movement type magnetic recording element **101** shown in FIG. **8** in that a plurality of recording parts **60** are provided. The same parts as those of the magnetic domain wall movement type magnetic recording element **101** according to the second embodiment are designated by the same reference numerals, and description thereof will be omitted. The configuration of the magnetic domain wall movement type magnetic recording element **105** according to the fifth embodiment can be applied to any of the elements of the other embodiments.

(116) The magnetic domain wall movement type magnetic recording element **105** shown in FIG. **14** has a plurality of recording parts **60** which extend substantially parallel to each other in the x direction (the first direction). The plurality of recording parts **60** are arranged at predetermined intervals in a second direction (the y direction in FIG. **14**) which intersects the x direction. The plurality of recording parts **60** are formed on the control unit **75** which spreads in the xy plane. Further, the trap-reinforcing member **90** extends over the plurality of recording parts **60**. For example, the trap-reinforcing member **90** extends to be in communication with the inside of the concave portion **24b** constituting each of the recording parts and to cross the magnetic recording layer **20** in a direction intersecting the x direction.

(117) The respective recording parts **60** are preferably disposed so that the concave-convex structures **24** (the positions of the convex portions **24a** and the concave portions **24b**) of the respective magnetic recording layers **20** overlap each other in a plan view in the y direction. The trap-reinforcing member **90** can be formed linearly in the y direction. Further, in this case, a distance between the trap sites of the adjacent magnetic recording layers (between the convex portions **24a**) can be made uniform, and an amount of movement of the magnetic domain wall with respect to a pulse input can be made uniform. That is, it becomes easy to simultaneously control the movement of the magnetic domain wall **21** in each of the plurality of recording parts **60**.

(118) Since the trap-reinforcing member **90** is present over the plurality of recording parts **60**, the multi-valued recording can be performed in each of the recording parts **60** in the same manner. That is, a multi-valued signal generated for each of the recording parts **60** can be changed evenly. The difference in signal strength between the recording parts **60** is reduced by making a threshold

for recording data in each of the recording parts **60** constant. As a result, noise of the magnetic domain wall movement type magnetic recording element **105** as a whole is reduced, and multi-valued recording of data can be stably performed.

(119) As described above, although the magnetic domain wall movement type magnetic recording element according to the embodiment has been described in detail with reference to the drawings, each of the constitutions and the combination thereof in each of the embodiments is an example, and addition, omission, substitution, and other changes of the constitution are possible without departing from the gist of the present invention.

(120) FIG. **15** is a cross-sectional view schematically showing Modified Example 3 of the magnetic domain wall movement type magnetic recording element according to the fifth embodiment. A magnetic domain wall movement type magnetic recording element **105A** according to Modified Example 3 is different from the magnetic domain wall movement type magnetic recording element **105** in that the trap-reinforcing members **90** are not linear but are scattered in the xy plane.

(121) The trap-reinforcing member **90** is scattered irregularly in the xy plane. The plurality of recording parts **60** are formed on the trap-reinforcing member **90** which spreads in the xy plane. The trap-reinforcing member **90** spreads over the plurality of recording parts **60** in the xy plane.

(122) The movement of the magnetic domain wall **21** in each of the recording parts **60** is controlled by the trap-reinforcing member **90** which spreads in the xy plane. When the trap-reinforcing member **90** is scattered irregularly, the movement of the magnetic domain wall **21** becomes irregular. Further, the magnetic domain wall **21** is inclined in the y direction. Since a data change in each of the recording parts **60** becomes irregular, the magnetic domain wall movement type magnetic recording element **105A** is excellent in analog recording of data. Further, when the trap-reinforcing member **90** forms a layer, the “trap-reinforcing member **90**” can be replaced with the “convex portion of the trap-reinforcing member **90**”.

Sixth Embodiment

(123) FIG. **16** is a plan view of a magnetic recording array **200** according to a sixth embodiment. In the magnetic recording array **200** shown in FIG. **16**, the recording parts **60** of the magnetic domain wall movement type magnetic recording element have a 3×3 matrix arrangement. FIG. **16** is an example of a magnetic recording array, and the type, number, and arrangement of the recording parts **60** are arbitrary. Further, the control part may be provided to be present over all the recording parts **60**, or may be provided for each of the recording parts **60**.

(124) The magnetic domain wall movement type magnetic recording element **100** is connected to one word line WL**1** to WL**3**, one bit line BL**1** to **3**, and one read line RL**1** to RL**3**.

(125) A pulse current is applied to the magnetic recording layer **20** of an arbitrary recording part **60** by selecting the word lines WL**1** to WL**3** and the bit lines BL**1** to BL**3** to which a current is applied, and a write operation is performed. In addition, a current flows in the lamination direction of the arbitrary recording part **60** by selecting the read lines RL**1** to RL**3** and the bit lines BL**1** to BL**3** to which a current is applied, and a reading operation is performed. The word lines WL**1** to WL**3**, the bit lines BL**1** to BL**3**, and the read lines RL**1** to RL**3** to which a current is applied can be selected by a transistor or the like. Since each of the recording parts **60** records information in multi-values, a high-capacity magnetic recording array can be realized.

Seventh Embodiment

(126) FIG. **17** is a schematic cross-sectional view of a magnetic domain wall movement element **107** according to a seventh embodiment. The magnetic domain movement type magnetic recording element **107** shown in FIG. **17** is different from the magnetic domain wall movement type magnetic recording element **100** shown in FIG. **1** in that a first ferromagnetic layer **10** is closer to a substrate **80** than a magnetic recording layer **20**. The constituent elements in the seventh embodiment that are the same as those of the magnetic domain wall movement type magnetic recording element **100** according to the first embodiment will be denoted by the same reference numerals and description thereof will be omitted.

(127) The magnetic recording layer **20** has a concave-convex structure **24** on an upper surface side using a base body **80** as a reference. The upper surface is a surface opposite to a first surface **20A** of the magnetic recording layer **20** on a non-magnetic layer **30** side and is a second surface **20B**.
(128) The concave-convex structure **24** is at a position in which a first electrode **41** and a second electrode **42** do not overlap when viewed in the z direction. A movable region of a magnetic domain wall **21** is between the first electrode **41** and the second electrode **42** and the concave-convex structure **24** is formed within a magnetic domain wall movement range of the magnetic recording layer **20**.

(129) Although FIG. **17** shows an example in which convex portions **24a** and concave portions **24b** of the concave-convex structure **24** are arranged periodically, as in the example of FIG. **2**, the convex portions **24a** and the concave portions **24b** may be arranged irregularly. Furthermore, distances between adjacent convex portions **24a** in the x direction or in the y direction may or may not be constant. In addition, heights of the convex portions **24a** may be the same as in the example of FIG. **4** or may be different from each other. Moreover, as in the example of FIGS. **11** and **12**, the concave-convex structure **24** may have convex portions or concave portions of a first shape and convex portions or concave portions of a second shape.

(130) The second surface **20B** of the magnetic recording layer **20** is in contact with a covering layer **71**. A third surface **71A** of the covering layer **71** has a larger arithmetic average roughness than the fourth surface **71B** of the covering layer **71**. The third surface **71A** is a surface in contact with the second surface **20B** of the covering layer **71** and the fourth surface **71B** is a surface which faces the third surface **71A**. The covering layer **71** covers an upper surface of the magnetic recording layer **20** within a magnetic domain wall movement range thereof.

(131) The same material as that of the intermediate body **70** can be used for the covering layer **71**. The covering layer **71** fills the concave-convex structure **24** of the second surface **20B** of the magnetic recording layer **20** and planarizes it. The covering layer **71** can be regarded as a planarizing layer when viewed the covering layer **71** from the magnetic recording layer **20**.

(132) The covering layer **71** may be the trap-reinforcing member **90** described above. Furthermore, the covering layer **71** may have an insulating layer **91** and the trap-reinforcing member **90** from a side close to the magnetic recording layer **20**.

(133) As described above, the magnetic domain wall type magnetic recording element **107** according to the seventh embodiment can also obtain the same effect as the first embodiment.

(134) Although the embodiments have been described in detail, the present invention is not limited to a specific embodiment, and various modifications and changes may be made within the scope of the present invention described in the appended claims.

REFERENCE SIGNS LIST

(135) **10** First ferromagnetic layer **20** Magnetic recording layer **20A**, **70A**, **28A** First surface **20B**, **70B** Second surface **21** Magnetic domain wall **22** First magnetic domain **23** Second magnetic domain **24**, **74** Concave-convex structure **24a**, **74a** Convex portion **24b**, **74b** Concave portion **25** First convex portion **26** Second convex portion **28**, **29** Magnetic body **30** Non-magnetic layer **41** First electrode **42** Second electrode **50** Second ferromagnetic layer **60** Recording part **70** Intermediate body (planarization layer) **71** Covering layer **71A** Third surface **71B** Fourth surface **75** Control part **80** Base body **81** Substrate **82** Underlayer **90** Trap-reinforcing member **91** Insulating layer **100** to **105**, **100A**, **101A**, **105A** Magnetic domain wall movement type magnetic recording element **200** Magnetic recording array

Claims

1. A magnetic domain wall movement type magnetic recording element, comprising: a first ferromagnetic layer which includes a ferromagnetic body; a non-magnetic layer which faces the first ferromagnetic layer; and a magnetic recording layer which faces a surface of the non-magnetic

layer on a side opposite to the first ferromagnetic layer and extends in a first direction, wherein a first surface of the magnetic recording layer which faces the non-magnetic layer has a smaller arithmetic average roughness than a second surface opposite to the first surface.

2. The magnetic domain wall movement type magnetic recording element according to claim 1, wherein the second surface has a concave-convex structure, and in the concave-convex structure, apex positions of convex portions constituting the concave-convex structure is irregular in a plan view in the lamination direction.

3. The magnetic domain wall movement type magnetic recording element according to claim 1, further comprising: a coating layer in contact with the second surface of the magnetic recording layer, wherein a third surface in contact with the second surface of the coating layer has a larger arithmetic mean roughness than a fourth surface opposite to the third surface.

4. The magnetic domain wall movement type magnetic recording element according to claim 1, further comprising: a base body which faces the second surface of the magnetic recording layer; and an intermediate body which is located between the base body and the magnetic recording layer.

5. The magnetic domain wall movement type magnetic recording element according to claim 4, wherein: the intermediate body is a non-magnetic trap-reinforcing member, and the trap-reinforcing member is layers which are scattered on one surface of the base body or a layer which has concavity and convexity on the second surface side of the magnetic recording layer.

6. The magnetic domain wall movement type magnetic recording element according to claim 4, wherein: the intermediate body has a trap-reinforcing member, and an insulating layer which covers the trap-reinforcing member from a position near the base body, and the trap-reinforcing member is layers which are scattered on one surface of the base body or a layer which has concavity and convexity on the second surface side of the magnetic recording layer.

7. The magnetic domain wall movement type magnetic recording element according to claim 5, wherein: one end of the trap-reinforcing member is in contact with the base body, and when a surface energy of a material constituting a surface of the base body is $\gamma_{\text{sub.A}}$, and a surface energy of a material of the trap-reinforcing member is $\gamma_{\text{sub.B}}$, $\gamma_{\text{sub.B}} < \gamma_{\text{sub.A}}$, and a surface energy mismatch $\Gamma_{\text{sub.AB}}$ defined by the following Equation (1) is larger than 0.5

[Math1]

$$\Gamma_{AB} = 2 \cdot \text{Math.} \frac{\gamma_{\text{sub.A}} - \gamma_{\text{sub.B}}}{\gamma_{\text{sub.A}} + \gamma_{\text{sub.B}}} \cdot \text{Math.} \quad (1)$$

8. The magnetic domain wall movement type magnetic recording element according to claim 5, wherein: a plurality of recording parts which includes the first ferromagnetic layer, the nonmagnetic layer and the magnetic recording layer are provided, the plurality of recording parts are arranged in a second direction which intersects the first direction, and the trap-reinforcing member spreads in a same plane over the plurality of recording parts.

9. The magnetic domain wall movement type magnetic recording element according to claim 5, wherein: a plurality of recording parts which includes the first ferromagnetic layer, the nonmagnetic layer and the magnetic recording layer are provided, and the trap-reinforcing member or a convex portion of the trap-reinforcing member extends in a second direction which intersects the first direction over the plurality of recording parts.

10. The magnetic domain wall movement type magnetic recording element according to claim 1 wherein the second surface has a concave-convex structure and the concave-convex structure has periodicity in the first direction.

11. The magnetic domain wall movement type magnetic recording element according to claim 1, wherein the second surface has a concave-convex structure and the concave-convex structure has a concave portion or a convex portion having a first shape, and a concave portion or a convex portion having a second shape having a larger volume than that of the first shape.

12. The magnetic domain wall movement type magnetic recording element according to claim 11, wherein the concave portion or the convex portion having the second shape is located at a position

at which the concave portion or the convex portion having the second shape overlaps an end surface of the first ferromagnetic layer in a plan view in the lamination direction.

13. The magnetic domain wall movement type magnetic recording element according to claim 11, wherein the concave or convex portion having the second shape is larger than the concave or convex portion having the first shape in the first direction.

14. The magnetic domain wall movement type magnetic recording element according to claim 11, wherein the concave or convex portion having the second shape is larger than the concave or convex portion having the first shape in the lamination direction.

15. The magnetic domain wall movement type magnetic recording element according to claim 1, wherein a second ferromagnetic layer which reflects a magnetization state of the magnetic recording layer is provided between the magnetic recording layer and the non-magnetic layer.

16. The magnetic domain wall movement type magnetic recording element according to claim 1, wherein the first ferromagnetic layer is closer to a base body configured to support the first ferromagnetic layer, the non-magnetic layer, and the magnetic recording layer than the magnetic recording layer.

17. The magnetic domain wall movement type magnetic recording element according to claim 16, wherein the second surface has a concave-convex structure, and in the concave-convex structure, apex positions of convex portions constituting the concave-convex structure are irregular in a plan view in the lamination direction.

18. The magnetic domain wall movement type magnetic recording element according to claim 1, wherein the magnetic recording layer has a magnetic domain wall therein and the second surface has a concave-convex structure within a movement range in which the magnetic domain wall is able to move.

19. A magnetic domain wall movement type magnetic recording element comprising: a recording part which includes: a magnetic recording layer which extends in a first direction which intersects a lamination direction, has a magnetic domain wall therein, and has a concave-convex structure which traps the magnetic domain wall; a first ferromagnetic layer which is laminated on the magnetic recording layer and includes a ferromagnetic body; a non-magnetic layer sandwiched between the first ferromagnetic layer and the magnetic recording layer; and a control part which has a planarization layer laminated on a side of the magnetic recording layer opposite to the first ferromagnetic layer and planarizes the concave-convex structure of the magnetic recording layer wherein the concave-convex structure is on a side opposite to the first ferromagnetic layer.
