

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250279308

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

AMANO; Shingo et al.

MEMBER FOR SEMICONDUCTOR MANUFACTURING EQUIPMENT

Abstract

A member for a semiconductor manufacturing equipment includes a ceramic substrate including: a terminal dense portion, a plurality of heater electrodes which are zoned, and a plurality of jumper electrode layers; wherein each of the jumper electrode layers is composed of a plurality of planar jumper electrodes that are electrically isolated by an insulator, and wherein in at least one of the terminal dense portion, each of 70% or more of all the terminals arranged in the terminal dense portion is electrically connected to a predetermined planar jumper electrode through a first via extending in the vertical direction, on a condition that it is not electrically connected to a planar jumper electrode located in a layer above any other planar jumper electrode to which other terminals that have a longer distance from an outer periphery of the terminal dense portion than itself are electrically connected.

Inventors: AMANO; Shingo (Chita-Gun, JP), TSUZUKI; Naoki (Toyoake-Shi, JP), KAJIURA; Yohei (Nagoya-Shi, JP)

Applicant: NGK INSULATORS, LTD. (Nagoya-Shi, JP)

Family ID: 95978948

Assignee: NGK INSULATORS, LTD. (Nagoya-Shi, JP)

Appl. No.: 18/815928

Filed: August 27, 2024

Related U.S. Application Data

parent WO continuation PCT/JP2024/007630 20240229 PENDING child US 18815928

Publication Classification

Int. Cl.: H01L21/683 (20060101); H01L21/67 (20060101)

U.S. Cl.:

CPC H01L21/6833 (20130101); H01L21/67103 (20130101);

Background/Summary

CROSS REFERENCE TO RELATED APPLICATIONS [0001] The present invention claims the benefit of priority to International Patent Application PCT/JP2024/007630 filed on Feb. 29, 2024 with the Japanese Patent Office, the entire contents of which are incorporated herein by reference in its entirety.

FIELD OF THE INVENTION

[0002] The present invention relates to a member for a semiconductor manufacturing equipment.

BACKGROUND OF THE INVENTION

[0003] Conventionally, members for semiconductor manufacturing equipment used for holding, temperature control, transporting, or the like of wafers have been known. These types of members for semiconductor manufacturing equipment are also called a wafer placement table, an electrostatic chuck, a susceptor, or the like. Generally, they have the function of applying electrical power for electrostatic adsorption to an internal electrode and adsorbing a wafer using electrostatic force.

[0004] There are many different types of processing for wafers, such as etching and CVD, and the optimum wafer temperature distribution differs depending on the type of processing. For this reason, a member for a semiconductor manufacturing equipment are required to have the ability to control the temperature distribution of the wafer. In order to meet such demands, a member for a semiconductor manufacturing equipment with a multi-zone heater that includes a ceramic substrate incorporating a plurality of heater electrodes is known.

[0005] Japanese Patent Application Publication No. 2021-015933 discloses that a heater electrode layer having a plurality of heater electrodes formed of a conductive material, a driver electrode layer having a plurality of driver electrodes for supplying power to the heater electrode layer, and various vias are disposed inside a ceramic plate-shaped member. The literature also discloses that a plurality of power supply pads are arranged in a direction substantially perpendicular to the vertical direction in a positioning recess on the lower surface of the plate-like member, and each power supply pad is electrically connected to a driver electrode of the driver electrode layer through a via. The drawings in this literature show a number of driver electrodes arranged at different heights.

PRIOR ART

Patent Literature

[0006] [Patent Literature 1] Japanese Patent Application Publication No. 2021-015933

SUMMARY OF THE INVENTION

[0007] In such a member for a semiconductor manufacturing equipment with multi-zone heaters, there is a demand for improved performance in controlling the temperature distribution of the wafer in order to accommodate more precise wafer processing. To improve the ability to control the temperature distribution on the wafer, it is necessary to increase the number of zones by increasing the number of heater electrodes. However, as the number of heater electrodes increases, the number of driver electrodes (hereinafter referred to as “jumper electrodes” in this specification) for supplying power to the heater electrodes also increases. As the number of jumper electrodes increases, it becomes necessary to make the jumper electrodes multi-layered, and the number of layers also increases, which increases the number of manufacturing steps for the ceramic substrate,

resulting in a problem that the manufacturing costs of a member for a semiconductor manufacturing equipment tend to rise.

[0008] In view of the above circumstances, in one embodiment of the present invention, an object is to reduce the number of jumper electrode layers in a member for a semiconductor manufacturing equipment having a plurality of zoned heater electrodes.

[0009] As a result of intensive research conducted by the present inventors to solve the above problems, the present invention, which is illustrated as below, has been created.

Aspect 1

[0010] A member for a semiconductor manufacturing equipment comprising a ceramic substrate, the ceramic substrate comprising: [0011] an upper surface on which a wafer is to be placed, [0012] a terminal dense portion in which 10 or more terminals are arranged within a single section, [0013] a plurality of heater electrodes which are zoned, and [0014] a plurality of jumper electrode layers that electrically connect the plurality of heater electrodes to each terminal of the terminal dense portion and are stacked in a vertical direction via an insulator; [0015] wherein each of the jumper electrode layers is composed of a plurality of planar jumper electrodes that are electrically isolated by an insulator, [0016] wherein in at least one of the terminal dense portion, each of 70% or more of all the terminals arranged in the terminal dense portion is electrically connected to a predetermined planar jumper electrode through a first via extending in the vertical direction, on a condition that it is not electrically connected to a planar jumper electrode located in a layer above any other planar jumper electrode to which other terminals that have a longer distance from an outer periphery of the terminal dense portion than itself are electrically connected, and [0017] wherein each of the plurality of planar jumper electrodes is electrically connected to a first connection portion of a predetermined heater electrode selected from the plurality of heater electrodes through a second via extending in the vertical direction.

Aspect 2

[0018] A member for a semiconductor manufacturing equipment according to aspect 1, wherein in at least one of the terminal dense portion, at least one terminal T.sub.1 is electrically connected to a planar jumper electrode located in a layer above a planar jumper electrode to which at least one other terminal T.sub.2, which has a longer distance from the outer periphery of the terminal dense portion than the at least one terminal T.sub.1, is electrically connected; and wherein assuming a distance between the at least one terminal T.sub.1 and the outer periphery is M.sub.1 (mm), and a distance between the at least one other terminal T.sub.2 and the outer periphery is M.sub.2 (mm), a formula 1: $M_{sub.1} < M_{sub.2} \leq M_{sub.1} + 2$ is satisfied for all of the at least one terminal T.sub.1.

Aspect 3

[0019] A member for a semiconductor manufacturing equipment according to aspect 1, wherein in at least one of the terminal dense portion, each of all the terminals arranged in the terminal dense portion is electrically connected to the predetermined planar jumper electrode through the first via extending in the vertical direction, on the condition that it is not electrically connected to the planar jumper electrode located in the layer above any other planar jumper electrode to which other terminals that have a longer distance from the outer periphery of the terminal dense portion than itself are electrically connected.

Aspect 4

[0020] A member for a semiconductor manufacturing equipment according to any one of aspects 1 to 3, wherein at least one jumper electrode layer among the plurality of jumper electrode layers electrically connected to the 10 or more terminals constituting the terminal dense portion in each single section is composed of 8 to 12 planar jumper electrodes.

Aspect 5

[0021] A member for a semiconductor manufacturing equipment according to any one of aspects 1 to 4, wherein assuming a total number of the plurality of jumper electrode layers electrically connected to the 10 or more terminals constituting the terminal dense portion in each single section

is A, a number of planar jumper electrodes constituting a Nth jumper electrode layer (N is a natural number from 1 to A) from a lowermost layer is equal to or less than a number of planar jumper electrodes constituting the (N-1)th jumper electrode layer from the lowermost layer, and a number of the planar jumper electrodes constituting the uppermost jumper electrode layer is less than a number of the planar jumper electrodes constituting the lowermost jumper electrode layer.

Aspect 6

[0022] A member for a semiconductor manufacturing equipment according to any one of aspects 1 to 5, wherein each of the plurality of planar jumper electrodes constituting at least one jumper electrode layer among the plurality of jumper electrode layers electrically connected to the 10 or more terminals constituting the terminal dense portion in each single section has a planar shape having two adjacent line segments at the same angle with a position of the first via as a vertex.

Aspect 7

[0023] A member for a semiconductor manufacturing equipment according to any one of aspects 1 to 6, wherein each of the plurality of the heater electrodes has a second connection portion, and the second connection portion is connected to a common terminal for grounding via a common jumper.

Aspect 8

[0024] A member for a semiconductor manufacturing equipment according to aspect 7, wherein the common jumper is electrically connected to the common terminal through a third via extending in the vertical direction, and a diameter of the third via is larger than a diameter of the first via.

Aspect 9

[0025] A member for a semiconductor manufacturing equipment according to any one of aspects 1 to 8, wherein in each of the plurality of jumper electrode layers connected to the 10 or more terminals constituting the terminal dense portion in each single section, adjacent planar jumper electrodes are electrically isolated from each other by a linear insulator, and the linear insulator does not linearly overlap any other linear insulator in a different jumper electrode layer in the vertical direction.

Aspect 10

[0026] A member for a semiconductor manufacturing equipment according to any one of aspects 1 to 9, wherein for any of the plurality of planar jumper electrodes constituting at least one jumper electrode layer among the plurality of jumper electrode layers connected to the 10 or more terminals constituting the terminal dense portion in each single section, a distance between adjacent planar jumper electrodes in the same layer is 0.3 mm or more.

[0027] According to the member for a semiconductor manufacturing equipment in one embodiment of the present invention, it is possible to reduce the number of layers of the jumper electrodes when the jumper electrodes are multi-layered by increasing the number of heater electrodes. This makes it possible to manufacture at low cost a member for a semiconductor manufacturing equipment with multi-zone heaters to improve wafer temperature distribution control performance.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0028] FIG. 1 is a schematic vertical cross-sectional view (cross-sectional view taken along a plane including the central axis of the member for a semiconductor manufacturing equipment) of a member for a semiconductor manufacturing equipment according to one embodiment of the present invention.

[0029] FIG. 2 is a schematic partial enlarged view of the area enclosed by a frame in FIG. 1.

[0030] FIG. 3-1 is an arrangement example 1 of a terminal dense portion in a single section as observed from the bottom surface side of a ceramic substrate in a member for a semiconductor

manufacturing equipment according to an embodiment of the present invention.

[0031] FIG. **3-2** is a diagram illustrating an example of jumper electrode layers to which each terminal in the terminal dense portion according to arrangement example 1 is connected, from the lowermost layer (the 1.sup.st layer) to the uppermost layer (the 5.sup.th layer).

[0032] FIG. **4-1** is a diagram showing an arrangement example 2 of a terminal dense portion in a single section as observed from the bottom surface side of a ceramic substrate in a member for a semiconductor manufacturing equipment according to an embodiment of the present invention.

[0033] FIG. **4-2** is a diagram illustrating an example of jumper electrode layers to which each terminal in the terminal dense portion according to arrangement example 2 is connected, from the lowermost layer (the 1.sup.st layer) to the uppermost layer (the 5.sup.th layer).

[0034] FIG. **5** shows schematic examples of the shapes of a plurality of planar jumper electrodes constituting each of the jumper electrode layers from the 1.sup.st to the 5.sup.th layers and an example of the shape of a common jumper, when the upper surface, which is the wafer placement surface of the ceramic substrate, is circular, the number of terminal dense portions is three, and the number of jumper electrode layers is five.

[0035] FIG. **6** is a schematic plan view of each of the 1.sup.st to the 3.sup.rd jumper electrode layers.

[0036] FIG. **7** is a schematic view of the five jumper electrode layers illustrated in FIG. **5** as viewed virtually from above.

DETAILED DESCRIPTION OF THE INVENTION

[0037] Hereinafter, embodiments of the present invention will now be described in detail with reference to the drawings. It should be understood that the present invention is not intended to be limited to the following embodiments, and any change, improvement or the like of the design may be appropriately added based on ordinary knowledge of those skilled in the art without departing from the spirit of the present invention. In addition, as used herein, “upper” and “lower” are used to conveniently express the relative positional relationship when a member for a semiconductor manufacturing equipment is placed on a horizontal surface with the upper surface for placing a wafer of the ceramic substrate facing up, and they do not represent any absolute positional relationships. Therefore, depending on the orientation of the member for a semiconductor manufacturing equipment, “upper” and “lower” may become “lower” and “upper”, or “left” and “right”, or “front” and “rear”.

1. Configuration of Member for Semiconductor Manufacturing Equipment

[0038] Referring to FIG. **1** and FIG. **2**, a member **10** for a semiconductor manufacturing equipment according to an embodiment of the present invention can be used when performing processes such as CVD and etching on a wafer **W** using plasma, and can be fixed to a mounting plate (not shown) provided inside a semiconductor processing chamber. The member **10** for a semiconductor manufacturing equipment comprises a ceramic substrate **20** and a base plate **30** that is located on the side of the lower surface **23** of the ceramic substrate **20** and has a refrigerant passage **32** provided therein. The ceramic substrate **20** and the base plate **30** can be bonded together by, for example, a bonding layer **40**.

1-1. Ceramic Substrate

[0039] According to an embodiment of the present invention, the ceramic substrate **20** comprises: [0040] an upper surface **21a** on which a wafer is to be placed, [0041] a terminal dense portion **52** in which 10 or more terminals **52a** are arranged within a single section, [0042] a plurality of heater electrodes **27** which are zoned, and [0043] a plurality of jumper electrode layers **29** that electrically connect the plurality of heater electrodes **27** to each terminal **52a** of the terminal dense portion **52** and are stacked in a vertical direction via an insulator **28**.

[0044] More specifically, the ceramic substrate **20** according to one embodiment of the present invention comprises a central portion **20a** having a circular upper surface **21a** in a planar view, and an outer peripheral portion **20b** having an annular upper surface **21b** in a planar view on the outer

periphery of the central portion **20a**. A wafer W can be placed on the upper surface **21a**, and a focus ring **78** can be placed on the upper surface **21b**. The ceramic substrate **20** is made of a ceramic material such as alumina or aluminum nitride. The upper surface **21b** of the outer periphery **20b** is one step lower than the upper surface **21a** of the central portion **20a**. The lower surface **23** of the central portion **20a** and that of the outer peripheral portion **20b** may be one the same plane. The ceramic substrate **20** may have the central portion **20a** but no outer peripheral portion **20b**, that is, may not have the upper surface **21b** which is one step lower.

[0045] In the embodiment shown in FIG. **1**, the upper surface of the focus ring **78** and that of the wafer W are flush with each other, but the upper surface of the focus ring **78** may be located higher than the wafer. In the embodiment shown in FIG. **1**, the outer diameter of the focus ring **78** and the outer diameter of the outer peripheral portion **20b** of the ceramic substrate **20** are the same, but the two outer diameters do not have to be the same.

[0046] The upper surface **21a** on which the wafer W is to be placed may be provided with a plurality of small protrusions (not shown). Also, a seal band (not shown) may be formed along the outer edge of the upper surface **21a**. In this case, the wafer W may be supported by the top surface of the seal band and the top surfaces of the small protrusions.

[0047] The central portion **20a** of the ceramic substrate **20** may have a diameter of, for example, 190 to 450 mm and a thickness of 1 to 20 mm. In addition, the central portion **20a** of the ceramic substrate **20** may incorporate an electrostatic adsorption electrode **26** on the side closer to the upper surface **21a**. The electrostatic adsorption electrode **26** can be made of a material containing, for example, W, Mo, WC, MoC, or the like. The electrostatic adsorption electrode **26** may be, for example, a planar electrode. The ceramic substrate **20** may have one layer of the electrostatic adsorption electrode **26** therein, or two or more layers of the electrostatic adsorption electrode **26** therein with a gap therebetween.

[0048] The electrostatic adsorption electrode **26** is connected to an external DC power source via a power supply member (not shown). A low-pass filter may be disposed on the power supply member. The power supply member is electrically insulated from the bonding layer **40** and the base plate **30**. When a DC voltage is applied to the electrostatic adsorption electrode **26**, the wafer W is adsorbed and fixed to the upper surface **21a** by electrostatic adsorption force, and when the application of the DC voltage is stopped, the wafer W is released from the adsorption and fixation to the upper surface **21a**. The ceramic substrate **20** may incorporate an RF electrode for generating plasma in place of or in addition to the electrostatic adsorption electrode **26**.

[0049] The ceramic substrate **20** also has a plurality of heater electrodes **27** which are zoned. The heater electrodes **27** are arranged, for example, such that a plurality of zones are formed in a planar direction parallel to the upper surface **21a** of the ceramic substrate **20**. The output of each of the zoned heater electrodes **27** can be controlled. As a result, the upper surface **21a** of the ceramic substrate **20** is divided into a plurality of zones, and the temperature can be controlled for each zone, so that the performance of controlling the temperature distribution of the wafer can be improved.

[0050] The heater electrode **27** may be provided only in the central portion **20a** of the ceramic substrate **20**, but the heater electrode **27** may also be provided in the outer peripheral portion **20b** of the ceramic substrate **20** (that is, under the focus ring **78**).

[0051] In order to improve the performance of controlling the temperature distribution of the wafer, the ceramic substrate **20** preferably has 10 or more, more preferably 50 or more, and even more preferably 100 or more heater electrodes **27** in total. Each heater electrode **27** may be, for example, a linear electrode in a single stroke extending in a direction parallel to the upper surface **21a** of the ceramic substrate **20**. Each heater electrode **27** has a first connection portion **27a** which is a connection portion with a second via **62** and a second connection portion **27b** which is a connection portion with a fourth via **64**.

[0052] The heater electrode **27** can be made of, for example, a mixed material of metal and

ceramics. Examples of metals include Ru, W, and Mo. One or a combination of two or more of these metals may be used, but those having a thermal expansion coefficient close to that of the ceramic material constituting the ceramic substrate **20** are preferable. As the ceramic, it is preferable to use the same material as that of the ceramic substrate **20** (for example, alumina, and aluminum nitride). By forming the heater electrode **27** from such a mixed material, the risk of cracks occurring between the heater electrode **27** and the ceramic substrate **20** due to the difference in thermal expansion between them can be reduced.

[0053] Each jumper electrode layer **29** is composed of a plurality of planar jumper electrodes **29a** electrically separated via an insulator **29b** (see FIG. 6). As the jumper electrode **29a** is planar, there is an advantage that heat generation in the jumper electrode is suppressed compared to when the jumper electrode is linear. The fact that the jumper electrode **29a** is planar means that the jumper electrode **29a** extends in a plane direction parallel to the upper surface **21a** of the ceramic substrate **20**. Typically, the shape may be flat (for example, foil-like), but it may also have an uneven shape such as a mesh-like shape. The thickness of each planar jumper electrode **29a** may be, for example, 10 to 100 μm , and typically 20 to 50 μm .

[0054] For any of the plurality of planar jumper electrodes **29a** constituting at least one jumper electrode layer **29**, preferably half or more of the jumper electrode layers **29**, and more preferably all of the jumper electrode layers **29** among the plurality of jumper electrode layers **29** connected to the 10 or more terminals constituting the terminal dense portion in each single section, a distance D between adjacent planar jumper electrodes **29a** in the same layer is preferably 0.1 mm or more, more preferably 0.2 mm or more, and even more preferably 0.3 mm or more (see FIG. 4-2). This reduces the risk of adjacent planar jumper electrodes **29a** being electrically connected to each other, resulting in malfunction. On the other hand, from the viewpoint of reducing the risk of the jumper electrode width becoming narrower and generating more heat, the distance D is preferably 2 mm or less, more preferably 1.5 mm or less, and even more preferably 1 mm or less. Therefore, for any of the plurality of planar jumper electrodes **29a** constituting at least one jumper electrode layer **29**, preferably half or more of the jumper electrode layers **29**, and more preferably all of the jumper electrode layers **29** among the plurality of jumper electrode layers **29** connected to the 10 or more terminals constituting the terminal dense portion in each single section, a distance D between adjacent planar jumper electrodes **29a** in the same layer is preferably 0.1 to 2 mm, more preferably 0.2 to 1.5 mm, and even more preferably 0.3 to 1 mm.

[0055] The area of one planar jumper electrode **29a** (excluding the opening) in a planar view is preferably 450 mm^2 or more, more preferably 700 mm^2 or more, and even more preferably 1400 mm^2 or more, for the reason of suppressing heat generation. In addition, the area of one planar jumper electrode **29a** (excluding the opening) in a planar view is preferably 15,000 mm^2 or less, more preferably 7,000 mm^2 or less, and even more preferably 4,000 mm^2 or less, for the reason of simplifying electrode zoning. Therefore, the area of one planar jumper electrode **29a** (excluding the opening) in a planar view is, for example, preferably 450 to 15,000 mm^2 , more preferably 700 to 7,000 mm^2 , and even more preferably 1,400 to 4,000 mm^2 .

[0056] Each terminal **52a** of the terminal dense portion **52** is electrically connected to a predetermined planar jumper electrode **29a** through a first via **61** extending in the vertical direction. Each terminal **52a** can be fixed to the ceramic substrate **20** by, for example, brazing. Further, each terminal **52a** of the terminal dense portion **52** can be connected to a power supply member (not shown) that is connected to a heater power source. There are no particular limitations on the shape of each terminal **52a**, but it may be, for example, a rigid rod extending in the vertical direction, or a flexible wire.

[0057] Each of the plurality of planar jumper electrodes **29a** is electrically connected to a first connection portion **27a** of a predetermined heater electrode **27** selected from the plurality of heater electrodes **27** via a second via **62** extending in the vertical direction. The second connection portion

27b of each of the plurality of heater electrodes 27 can be electrically connected to a common terminal 72 via a common jumper 71. The common terminal 72 can be connected to, for example, a ground (earth) wire. In addition, the common terminal 72 may be connected to a heater power supply. The common jumper 71 can be electrically connected to the common terminal 72 through a third via 63 extending in the vertical direction. In addition, the second connection portion 27b can be electrically connected to a common jumper 71 through a fourth via 64 extending in the vertical direction. In the illustrated embodiment, the common terminal 72 is inserted inside the ceramic substrate 20 and can be fixed by brazing. This configuration can increase the bonding strength of the common terminal 72. However, it is sufficient that the common terminal 72 is electrically connected to the common jumper 71, and it is not necessary for the common terminal 72 to be inserted inside the ceramic substrate 20. For example, the common terminal 72 may be fixed to the lower surface 23 of the ceramic substrate 20 or to the bottom surface of a recess 35 provided in the lower surface 23 by brazing.

[0058] The common jumper 71 can be formed at a different height from the jumper electrode layer 29 and the heater electrode 27 via the insulator 28. In the embodiment shown in FIG. 1, a common jumper 71 is formed between the jumper electrode layer 29 and the heater electrode 27. The position of the common jumper 71 is not limited to this, and it is also possible to provide it at a position of a layer above the heater electrode 27, for example.

[0059] One common jumper 71 can be electrically connected to all or some of the plurality of terminals of one or a plurality of terminal dense portions 52. In one embodiment, all of the plurality of terminals in one terminal dense portion 52 may be electrically connected to one common jumper 71. In another embodiment, among the plurality of terminals in one terminal dense portion 52, some terminals may be electrically connected to one common jumper 71, and the remaining terminals may be electrically connected to another common jumper 71. While there is an advantage in that the more common jumpers 71 there are, the more the current is dispersed and heat generation is suppressed, there is a disadvantage in that the number of common terminals 72 increases, resulting in increased costs and more complicated wiring. Therefore, the member 10 for a semiconductor manufacturing equipment preferably has 1 to 5 common jumpers 71 in total, and more preferably has 1 to 3 common jumpers 71 in total.

[0060] In a preferred embodiment, the common jumper 71 is planar, which has the advantage that heat generation is suppressed compared to when the common jumper 71 is linear. The fact that the common jumper 71 is planar means that the common jumper 71 extends in a plane direction parallel to the upper surface 21a of the ceramic substrate 20. Typically, the shape may be flat (for example, foil-like), but it may also have an uneven shape such as a mesh-like shape. The thickness of the common jumper 71 can be, for example, 10 to 100 μm , and typically 30 to 80 μm .

Furthermore, the area of one common jumper 71 (excluding the opening) in a planar view is preferably 3,500 mm^2 or more, more preferably 7,000 mm^2 or more, and even more preferably 14,000 mm^2 or more, for the reason of suppressing heat generation. Furthermore, the area of one common jumper 71 (excluding the opening) in a planar view is preferably 70,000 mm^2 or less, and more preferably 40,000 mm^2 or less, for the reason of simplifying electrode zoning. Therefore, the area of one common jumper 71 (excluding the opening) in a plan view is, for example, preferably 3,500 to 70,000 mm^2 , more preferably 7,000 to 40,000 mm^2 , and even more preferably 14,000 to 40,000 mm^2 .

[0061] One or more common terminals 72 may be provided for one terminal dense portion 52. However, from the viewpoint of suppressing heat generation caused by current concentration in the common terminal, it is preferable to provide more than one common terminal 72 for one terminal dense portion 52.

[0062] In the illustrated embodiment, the common terminal 72 is provided in a recess 35 provided in the lower surface 23 of the ceramic substrate 20. The recess 35 may be omitted. The common terminal 72 can be joined to the ceramic substrate 20 by, for example, brazing or soldering. There

are no particular limitations on the common terminal **72**, but it may be, for example, a rigid rod extending in the vertical direction, or a flexible cable.

[0063] The planar jumper electrode **29a** and the common jumper **71** can be formed from, for example, a mixed material of ceramics and one or more selected from W, Mo, and Ru.

[0064] The first via **61**, the second via **62**, the third via **63**, and the fourth via **64** can be formed from, for example, a mixed material of ceramics and one or more selected from W, Mo, and Ru.

[0065] The terminal **52a** and the common terminal **72** can be made of a material such as Mo or Kovar (Fe—Ni—Co alloy).

[0066] The third via **63** is prone to generate heat because current supplied through each terminal **52a** is concentrated in the third via **63**.

[0067] Therefore, in order to suppress excessive heat generation in the third via **63**, it is preferable that the diameter of the third via **63** be larger than the diameter of the first via. The ratio of the diameter $X_{sub.3}$ of the third via to the diameter $X_{sub.1}$ of the first via may be set appropriately taking into consideration the current flowing through the third via, and may be, for example, $2 \leq X_{sub.3}/X_{sub.1} \leq 25$, and typically, $4 \leq X_{sub.3}/X_{sub.1} \leq 10$.

[0068] The diameter $X_{sub.1}$ of the first via can be, for example, 50 to 1000 μm , and typically 100 to 400 μm .

[0069] The diameter $X_{sub.2}$ of the second via can be, for example, 50 to 1000 μm , and typically 100 to 400 μm .

[0070] The diameter $X_{sub.3}$ of the third via can be, for example, 300 to 5000 μm , and typically 500 to 2000 μm .

[0071] The diameter $X_{sub.4}$ of the fourth via can be, for example, 50 to 1000 μm , and typically 100 to 400 μm .

[0072] As used herein, the diameters of the first, second, third and fourth vias refer to the equivalent circle diameters in a cross section perpendicular to the extension direction of each via.

[0073] The terminal dense portion **52** is a portion in which 10 or more terminals **52a** are arranged within a single section **55** (see FIG. 3-1). In the embodiment shown in FIG. 1, only one terminal dense portion **52** is shown. Depending on the wiring that supplies power to the terminals, the ceramic substrate **20** may be provided with a plurality of terminal dense portions **52**, that is, a plurality of single sections **55**. There is no particular limit to the number of terminals **52a** arranged in the terminal dense portion **52** within a single section **55**, but it may be, for example, 10 to 100, and typically 20 to 70. In the embodiment shown in FIG. 1, the terminal dense portion **52** is provided in a recess **34** provided in the lower surface **23** of the ceramic substrate **20**, and a single section **55** is partitioned by the recess **34**. The recess **34** may not be provided. In addition, from the viewpoints of saving space and ensuring insulation between the terminals, the number density of the terminals **52a** arranged in the terminal dense portion **52** is preferably 10 to 100 pieces/ cm^2 , more preferably 30 to 90 pieces/ cm^2 , and even more preferably 50 to 80 pieces/ cm^2 . The number density of the terminals **52a** arranged in the terminal dense portion **52** is obtained by dividing the number of terminals arranged in the terminal dense portion **52** by the area of the region surrounded by the outer periphery **54** of the terminal dense portion **52**. The outer periphery **54** will be defined later.

[0074] From the viewpoint of saving space and ensuring insulation among the terminals, for each of the 10 or more terminals **52a** arranged in a single section **55**, it is preferable that the shortest distance X (insulated distance) from the nearest terminal **52a** among the adjacent terminals **52a** is 0.3 to 2 mm, more preferably 0.5 to 1.5 mm, and even more preferably 0.7 to 1.3 mm (see FIG. 3-1 and FIG. 4-1).

[0075] The plurality of jumper electrode layers **29** electrically connect the plurality of heater electrodes **27** to each terminal **52a** of the terminal dense portion **52**, and are stacked in the vertical direction via the insulator **28**. The distance between vertically adjacent jumper electrode layers **29** (equal to the thickness T of the insulator **28** between the layers) is preferably 0.02 to 1 mm, more

preferably 0.02 to 0.5 mm, and even more preferably 0.02 to 0.2 mm, in order to strike a balance between ensuring insulation between the vertically adjacent jumper electrode layers **29** and reducing the manufacturing cost by thinning the ceramic substrate **20**.

[0076] Since an increase in the number of jumper electrode layers **29** increases the number of laminations, which increases the manufacturing cost, it is desirable to keep the number of jumper electrode layers **29** as small as possible. In order to reduce the number of jumper electrode layers **29**, it is preferable that each jumper electrode layer **29** have a plurality of planar jumper electrodes **29a**.

[0077] Thus, in one embodiment, each jumper electrode layer **29** may be comprised of a plurality of planar jumper electrodes **29a** electrically separated by insulators **29b** (see FIG. 6). While a larger number of jumper electrodes **29a** in the same jumper electrode layer **29** helps to reduce the number of jumper electrode layers **29**, it is not desirable to have an excessively large number of jumper electrodes **29a** since a narrower width of each jumper electrode **29a** will result in greater heat generation. Therefore, it is desirable that at least one jumper electrode layer **29**, preferably half or more jumper electrode layers **29**, and more preferably all of the jumper electrode layers **29** among the plurality of jumper electrode layers **29** electrically connected to the 10 or more terminals **52a** constituting the terminal dense portion **52** in each single section **55** be composed of 5 to 15 planar jumper electrodes **29a**, and more preferably composed of 8 to 12 planar jumper electrodes **29a**.

[0078] As the insulator **29b** for electrically isolating the plurality of planar jumper electrodes **29a**, for example, the ceramics (alumina and/or aluminum nitride, or the like) constituting the ceramic substrate **20** can be used. Further, without being limited thereto, a type of ceramic different from the ceramic constituting the ceramic substrate **20** may be used as the insulator **29b**.

[0079] Each terminal **52a** of the terminal dense portion **52** is electrically connected to a predetermined planar jumper electrode **29a** through a first via **61** extending in the vertical direction. One terminal **52a** may be electrically connected to a plurality of planar jumper electrodes **29a**, or a plurality of terminals **52a** may be electrically connected to one planar jumper electrode **29a**. In a preferred embodiment, each of the terminals **52a** is connected to one predetermined planar jumper electrode **29a**.

[0080] In order to reduce the number of jumper electrode layers **29**, it is necessary to electrically connect the numerous terminals **52a** arranged in the terminal dense portion **52** to each jumper electrode **29a** through the first vias **61** with high spatial efficiency. Specifically, it is desirable to connect the first via **61** connected to the terminal **52a** on the outer periphery of the terminal dense portion **52** to the jumper electrode layer **29** on the lower layer side, and to connect the first via **61** connected to the terminal **52a** on the inner periphery to the jumper electrode layer **29** on the upper layer side. Therefore, in one embodiment, in at least one terminal dense portion **52**, each of 70% or more of all the terminals **52a**, preferably each of 80% or more of all the terminals **52a**, and more preferably each of all the terminals **52a** arranged in the terminal dense portion **52** is electrically connected to a predetermined planar jumper electrode **29a** through the first via **61** extending in the vertical direction, on a condition that it is not electrically connected to a planar jumper electrode **29a** located in a layer above any other planar jumper electrodes **29a** to which other terminals that have a longer distance from the outer periphery **54** of the terminal dense portion **52** than itself are electrically connected. That is, when a terminal A, which is closer to the outer periphery **54** of the terminal dense portion **52**, is compared with a terminal B, which is more distant from the outer periphery **54** of the terminal dense portion **52** than the terminal A, it is preferable that the planar jumper electrode **29a** to which the terminal A is connected belongs to the same jumper electrode layer **29** as the planar jumper electrode **29a** to which the terminal B is connected, or alternatively, it is preferable that the planar jumper electrode **29a** to which the terminal A is connected belongs to a jumper electrode layer **29** located in a lower layer than the planar jumper electrode **29a** to which the terminal B is connected.

[0081] Of all the terminals **52a** arranged in the terminal dense portion **52**, some of the terminals

52a do not need to satisfy the above condition. Therefore, in at least one of the terminal dense portions **52**, at least one terminal **52a** (T.sub.1) may be electrically connected to a planar jumper electrode **29a** located in a layer above a planar jumper electrode **29a** to which at least one other terminal **52a** (T.sub.2), which has a longer distance from the outer periphery **54** of the terminal dense portion **52** than the at least one terminal T.sub.1, is electrically connected. However, assuming the distance between the at least one terminal **52a** (T.sub.1) and the outer periphery **54** is M.sub.1 (mm), and the distance between the at least one other terminal **52a** (T.sub.2) and the outer periphery **54** is M.sub.2 (mm), it is preferable that a formula 1: $M_{sub.1} < M_{sub.2} \leq M_{sub.1} + 2$ is satisfied for all of the terminals **52a** (T.sub.1).

[0082] When the ceramic substrate **20** has a plurality of terminal dense portions **52**, it is preferable that a half or more than half of the terminal dense portions **52** satisfy the above condition, and it is more preferable that all of the terminal dense portions **52** satisfy the above condition. There is no particular limit to the number of the terminal dense portions **52**, and it may be set appropriately depending on the area of the upper surface **21a**, which is the wafer placement surface of the ceramic substrate **20**, the number of heater electrodes **27**, the number of jumper electrode layers **29**, and the like. Exemplarily, it may be 1 to 10, typically 1 to 5.

[0083] FIGS. **3-1** and **4-1** show an arrangement example 1 and an arrangement example 2 when the terminal dense portion **52** in a single section **55** is observed from the lower surface **23** side of the ceramic substrate **20**. The outer periphery **54** of the terminal dense portion **52** is defined as a convex hull (the smallest convex set) that contains all the terminals **52a** in a single section **55** to which the terminal dense portion **52** belongs. In addition, the distance between each terminal **52a** and the outer periphery **54** refers to the shortest distance M from the center of gravity of the terminal **52a** to the outer periphery **54** when the terminal **52a** is observed in a direction perpendicular to the surface to which the terminal **52a** is connected.

[0084] FIG. **3-2** shows an example diagram explaining the allocation when each terminal **52a** of the terminal dense portion **52** in the arrangement example 1 is electrically connected to the planar jumper electrode **29a** of the jumper electrode layer **29** consisting of five layers via the first via **61**. In other words, FIG. **3-2** illustrates, by way of example, jumper electrode layers **29** to which each terminal **52a** of the terminal dense portion **52** is electrically connected, from the lowermost layer (1.sup.st layer) to the uppermost layer (5.sup.th layer). In the 1.sup.st layer, 11 terminals **52a** located on the outermost periphery are allocated. In the 2.sup.nd layer, 9 terminals **52a** located on the outermost periphery and 2 terminals **52a** located one step inward from the outermost periphery are allocated. In the 3.sup.rd layer, 10 terminals **52a** located one step inward from the outermost periphery are allocated. In the 4.sup.th layer, 6 terminals **52a** located one step inward from the outermost periphery and 3 terminals **52a** located two steps inward from the outermost periphery are allocated. In the 5.sup.th layer, 9 terminals **52a** located two steps inward from the outermost periphery are allocated.

[0085] In the arrangement example 1, for all the terminals **52a**, the condition is satisfied that the terminal **52a** is not electrically connected to a planar jumper electrode located in a layer above any other planar jumper electrode to which other terminals that have a longer distance from the outer periphery **54** of the terminal dense portion **52** than itself are electrically connected.

[0086] FIG. **4-2** shows an example diagram explaining the allocation when each terminal **52a** of the terminal dense portion **52** in the arrangement example 2 is electrically connected to the planar jumper electrode **29a** of the jumper electrode layer **29** consisting of five layers via the first via **61**. In other words, FIG. **4-2** illustrates, by way of example, jumper electrode layers **29** to which each terminal **52a** of the terminal dense portion **52** is electrically connected, from the lowermost layer (1.sup.st layer) to the uppermost layer (5.sup.th layer). In the 1.sup.st layer, 11 terminals **52a** are allocated. In the 2.sup.nd layer, 11 terminals **52a** are allocated. In the 3.sup.rd layer, 10 terminals **52a** are allocated. In the 4.sup.th layer, 10 terminals **52a** are allocated. In the 5.sup.th layer, 8 terminals **52a** are allocated.

[0087] In the arrangement example 2, a total of 50 terminals 52a are arranged in the terminal dense portion 52. In FIG. 4-2, 13 terminals 52a (9 on the 2.sup.nd layer and 4 on the 4.sup.th layer) surrounded by thick circles do not satisfy the condition that the terminal 52a is not electrically connected to a planar jumper electrode located in a layer above any other planar jumper electrode to which other terminals 52a that have a longer distance from the outer periphery 54 of the terminal dense portion 52 than itself are electrically connected. The remaining 37 terminals 52a (74%) satisfy this condition.

[0088] In a preferred embodiment, assuming the total number of the plurality of jumper electrode layers 29 electrically connected to the 10 or more terminals 52a constituting the terminal dense portion 52 in each single section 55 is A, the number of planar jumper electrodes 29a constituting the N.sup.th jumper electrode layer (N is a natural number from 1 to A) from the lowermost layer is equal to or less than the number of planar jumper electrodes 29a constituting the (N-1).sup.th jumper electrode layer 29 from the lowermost layer, and the number of the planar jumper electrodes 29a constituting the uppermost jumper electrode layer 29 is less than the number of the planar jumper electrodes 29a constituting the lowermost jumper electrode layer 29. A wider distance between electrodes of the jumper electrodes 29a is preferable from the viewpoint of insulation between the electrodes, and a wider width of the electrodes is preferable from the viewpoint of suppressing heat generation. Therefore, by adopting this configuration in which jumper electrodes connected to terminals on the outer periphery, where it is easier to ensure the distance between electrodes and the width of electrodes, are arranged on the lower layer side, it is possible to obtain the advantage of being able to arrange jumper electrodes efficiently using a minimum number of layers.

[0089] FIG. 5 shows schematic examples of the shapes of the plurality of planar jumper electrodes 29a constituting each of the jumper electrode layers 29 from the 1.sup.st to the 5.sup.th layers and an example of the shape of a common jumper, when the upper surface 21a, which is the wafer placement surface of the ceramic substrate 20, is circular, the number of terminal dense portions 52 is three, and the number of jumper electrode layers 29 is five. In the embodiment shown in FIG. 5, the planar shape of one jumper electrode layer 29 electrically connected to the plurality of terminals 52a in one terminal dense area 52 is substantially a sector with the center of the circle formed by the upper surface 21a as the reference for the central angle. In the embodiment shown in FIG. 5, three jumper electrode layers 29 are arranged at the same height in each of the 1.sup.st to 5.sup.th layers. The three jumper electrode layers 29 are electrically connected to the corresponding terminal dense portions 52. The three jumper electrode layers 29 at the same height (same layer number) are arranged so as to correspond as a whole to the planar shape (circular in FIG. 5) of the upper surface 21a which is the wafer placement surface.

[0090] In the embodiment shown in FIG. 5, the three jumper electrode layers 29 at the same height (the same layer number) all have a substantially sector shape with substantially the same central angle (specifically, 120°), and are electrically isolated from each other by linear insulators 29c (for example, ceramics) extending along the radius. It is preferable that the linear insulators 29c electrically isolating the adjacent jumper electrode layers 29 from each other do not linearly overlap in the vertical direction with any linear insulators 29c in different jumper electrode layers 29. FIG. 7 shows a schematic sight-through view of a plurality of planar jumper electrodes constituting the five jumper electrode layers shown in FIG. 5 as viewed virtually from above. This can reduce the risk of cracks occurring in the ceramic substrate 20. The line width of the linear insulator 29c (equal to the distance between adjacent jumper electrode layers 29) is not limited to, but may be, for example, 0.3 to 2 mm, and typically 0.3 to 1 mm.

[0091] FIG. 6 shows a schematic plan view of each of the 1.sup.st to 3.sup.rd jumper electrode layers 29 as an example. It is preferable that each of the plurality of planar jumper electrodes 29a constituting at least one jumper electrode layer 29, preferably half or more of the jumper electrode layers 29, and more preferably all of the jumper electrode layers among the plurality of jumper

electrode layers **29** electrically connected to the 10 or more terminals **52a** constituting the terminal dense portion **52** in each single section **55** have a planar shape having two adjacent line segments at the same angle with the position of the first via **61** as a vertex. Current tends to concentrate and generate heat near the first via **61** extending in the vertical direction from the terminal dense portion **52**. Therefore, by spreading the planar jumper electrodes **29a** at equal intervals, it is possible to obtain an advantage that the heat can be easily dispersed.

[0092] Referring to FIG. **6**, in the 1.sup.st and 2.sup.nd jumper electrode layers **29**, each of the 11 pieces of jumper electrodes **29a** has a planar shape having two line segments as a component adjacent at an angle of $32.7^\circ (=360^\circ/11)$. In the 3.sup.rd jumper electrode layer **29**, each of the 10 pieces of jumper electrodes **29a** has a planar shape having two line segments as a component adjacent at an angle of $36^\circ (=360^\circ/10)$.

[0093] In each of the multiple jumper electrode layers **29** connected to the 10 or more terminals **52a** constituting the terminal dense portion **52** in each single section **55**, adjacent planar jumper electrodes **29a** can be electrically isolated from each other by the linear insulators **29b** (for example, ceramics). The linear insulator **29b** may be formed, for example, with a straight line, a curved line, or a combination of both. In this case, it is preferable that the linear insulators **29b** do not linearly overlap with any linear insulators **29b** in different jumper electrode layers **29** in the vertical direction. FIG. **7** shows a schematic sight-through view of a plurality of planar jumper electrodes constituting the 5 jumper electrode layers shown in FIG. **5** as viewed virtually from above. This reduces the risk of cracks occurring in the ceramic substrate. The line width of the linear insulator **29b** (equal to the distance between adjacent jumper electrodes **29a**) is not limited, but may be, for example, 0.3 to 2 mm, and typically 0.5 to 1 mm.

[0094] From the viewpoint of reducing manufacturing costs, the total layer number A of the jumper electrode layers **29** is preferably 20 or less, more preferably 10 or less, and even more preferably 5 or less. On the other hand, from the viewpoint of increasing the number of heater electrodes to increase the number of zones and thereby improving the performance of controlling the temperature distribution of the wafer, the total layer number A of jumper electrode layers **29** is preferably 2 or more, more preferably 3 or more, and even more preferably 4 or more. Therefore, the total layer number A of the jumper electrode layers **29** is, for example, preferably 2 to 20, more preferably 3 to 10, and even more preferably 4 to 5.

1-2. Base Plate

[0095] The base plate **30** may be, for example, circular plate-shaped. In one embodiment, the base plate **30** comprises a central portion **30a** having a circular upper surface **31a** in a plan view, and a flange portion **30b** having an annular upper surface **31b** in a plan view on the outer periphery of the central portion **30a**. The thickness of the central portion **30a** may be, for example, 5 to 30 mm. The flange portion **30b** can be used to clamp or bolt the member **10** for a semiconductor manufacturing equipment to a mounting plate disposed on the side of the lower surface **33**. Also, a ring heater (not shown) can be placed on the flange portion **30b**. In this case, the ring heater can be bolted to the mounting plate.

[0096] The base plate **30** can be made of, for example, a metal material or a composite material of metal and ceramics. Examples of metal materials include Al, Ti, Mo, and alloys thereof. Examples of composite materials of metal and ceramics include metal matrix composites (MMCs) and ceramic matrix composites (CMCs). Specific examples of such composite materials include materials containing Si, SiC, and Ti (also called SiSiCTi), materials in which a porous SiC body is impregnated with Al and/or Si, and composite materials of Al.sub.2O.sub.3 and TiC. A material in which a porous SiC body is impregnated with Al is called AlSiC, and a material in which a porous SiC body is impregnated with Si is called SiSiC. It is preferable to select a material for the base plate **30** that has a thermal expansion coefficient close to that of the ceramics that constitutes the ceramic substrate **20**. For example, when the ceramic substrate **20** is made of alumina, the base plate **30** is preferably made of SiSiCTi or AlSiC, which have a thermal expansion coefficient close

to that of alumina.

[0097] The base plate **30** can be used as an RF electrode by connecting it to an RF power source via a power supply terminal (not shown). A high pass filter (HPF) can be disposed between the base plate **30** and the RF power source.

[0098] Inside the base plate **30**, a refrigerant passage **32** through which refrigerant circulates may be formed. The refrigerant flowing through the refrigerant passage **32** is preferably liquid and preferably electrically insulating. An example of the electrically insulating liquid includes fluorine-based inert liquid. The refrigerant passage **32** can be formed, for example, in a single stroke across the entire base plate **30** from one end (inlet) to the other end (outlet) in a plan view. A supply port and a recovery port of an external refrigerant device (not shown) are connected to one end and the other end of the refrigerant passage **32**, respectively. The refrigerant supplied from the supply port of the external refrigerant device to one end of the refrigerant passage **32** passes through the refrigerant passage **32** and then returns from the other end of the refrigerant passage **32** to a recovery port of the external refrigerant device, and after the temperature has been adjusted, the refrigerant is again supplied to the one end of the refrigerant passage **32** from the supply port.

1-3. Bonding Layer

[0099] The bonding layer **40** bonds the lower surface **23** of the ceramic substrate **20** to the upper surface **31a** of the base plate **30**. The bonding layer **40** may be composed of a metal layer made of, for example, solder or a metal brazing material. The bonding layer **40** is formed, for example, by TCB (Thermal Compression Bonding). TCB refers to a known method in which a metal bonding material is sandwiched between two members to be bonded, and the two members are pressure-bonded while being heated to a temperature equal to or lower than the solidus temperature of the metal bonding material. The bonding layer **40** is not limited to a metal layer. For example, a resin bonding layer may be used instead of the metal layer. The resin bonding layer may be made of, for example, a silicone resin-based adhesive, an epoxy resin-based adhesive, an acrylic resin-based adhesive, or a urethane resin-based adhesive.

[0100] The bonding layer **40** and the base plate **30** may have a through hole at a location corresponding to the terminal dense portion **52** in order to facilitate connection of power supply member to the respective terminals **52a** of the terminal dense portion **52**. In addition, the bonding layer **40** and the base plate **30** may have a through hole at a location corresponding to the common terminal **72** such that the common terminal **72** can be easily connected to the ground wire **73**.

1-4. Others

[0101] The side surface of the outer peripheral portion **20b** of the ceramic substrate **20**, the outer periphery of the bonding layer **40**, the side surface of the base plate **30**, and the upper surface **31b** of the flange portion **30b** can be covered with an insulating film **42**. An example of the insulating film **42** includes a thermally sprayed film of alumina, yttria, or the like.

[0102] In the above-described embodiment, the member **10** for a semiconductor manufacturing equipment may have a plurality of holes that pass through the member **10** for a semiconductor manufacturing equipment in the vertical direction. Such holes include a plurality of gas holes opening in the upper surface **21a** and a lift pin hole for inserting a lift pin that moves the wafer

[0103] W up and down relative to the upper surface **21a**. A plurality of gas holes can be provided at appropriate positions in a planar view of the upper surface **21a**. A thermally conductive gas such as He gas is supplied to the gas holes. Normally, the gas holes can be provided so as to have an opening on the upper surface **21a** on which the above-mentioned seal band or small protrusions are provided, but at positions where the seal band or small protrusions are not provided. When the thermally conductive gas is supplied to the gas holes, the thermally conductive gas fills the space on the rear side of the wafer W placed on the upper surface **21a**. Gas passage may be embedded in the gas holes. A plurality of lift pin holes may be provided at equal intervals along a concentric circle on the upper surface **21a** in a planar view of the upper surface **21a**.

2. Method of Using a Member for Semiconductor Manufacturing Equipment

[0104] Next, an example of how to use the member **10** for a semiconductor manufacturing equipment will be described. The common terminal **72** of the member **10** for a semiconductor manufacturing equipment is connected to earth via the earth wire **73**. Further, each terminal **52a** of the terminal dense portion **52** is connected to a heater power supply via a power supply member (not shown). In this state, when a voltage is applied from the heater power supply, a current flows in the order of each terminal **52a** in the terminal dense portion **52**.
the first via **61**.
the jumper electrode layer **29**.
the second via **62**.
each heater electrode **27**.
the fourth via **64**.
the common jumper **71**.
the third via **63**.
the common terminal **72**, so that each heater electrode **27** generates heat. By changing the voltage applied to each terminal **52a**, it is possible to change the amount of heat generated by the zoned multiple heater electrodes **27**. This makes it possible to realize a desired heat distribution on the ceramic substrate **20**, and therefore, for example, it is possible to control the temperature distribution of the wafer W fixed by adsorption to the upper surface **21a** of the ceramic substrate **20**.

[0105] A method for adsorbing and fixing a wafer W will be described below. First, the wafer W is placed on the upper surface **21a** of the ceramic substrate **20** with the member **10** for a semiconductor manufacturing equipment placed in a chamber (not shown). Then, the pressure inside the chamber is reduced using a vacuum pump to adjust it to a predetermined degree of vacuum, and a voltage is applied to the electrostatic adsorption electrode **26** to generate an electrostatic adsorption force, thereby adsorbing and fixing the wafer W to the upper surface **21a** of the ceramic substrate **20**. A method for processing the wafer W will now be described. The

[0106] inside of the chamber is set to a reaction gas atmosphere at a predetermined pressure (for example, several tens to several hundreds of Pa). The zoned multiple heater electrodes **27** are controlled such that the temperature distribution of the wafer W fixed by adsorption to the upper surface **21a** of the ceramic substrate **20** becomes a desired state. Plasma is then generated by applying a high-frequency voltage such as an RF voltage between an upper electrode (not shown) provided on the ceiling of the chamber and the base plate **30** of the member **10** for a semiconductor manufacturing equipment. The surface of the wafer W is processed by the generated plasma.

3. Method for Manufacturing a Member for Semiconductor Manufacturing Equipment

[0107] Next, a method for manufacturing the member **10** for a semiconductor manufacturing equipment will be exemplarily described.

[0108] First, a method for producing the ceramic substrate **20** will be described. A plurality of circular plate-shaped green sheets that are the precursor of the ceramic substrate **20** are produced. The green sheets can be produced by, for example, a tape forming process. Grooves are formed in the lower surface of the first green sheet from the bottom layer at positions where the recesses **34** and **35** are to be provided. Further, a through hole is formed in the green sheet at a position corresponding to the first via **61**, and the through hole is filled with a conductive paste to form a paste-filled portion. Furthermore, if necessary, a through hole is also formed at a position where the common terminal **72** is to be inserted. Next, a conductive paste is printed on the upper surface of the green sheet so as to obtain the same pattern as the 1.sup.st jumper electrode layer **29**, thereby forming a jumper precursor for the 1.sup.st layer.

[0109] For the second green sheet from the lowermost layer onwards (N.sup.th layer), through holes are formed at positions corresponding to the first via **61**, the second via **62**, the third via **63**, and the fourth via **64** as necessary, and the through holes are filled with conductive paste to form paste-filled portions. Furthermore, if necessary, a through hole is formed at the position where the common terminal **72** is to be inserted. Next, a conductive paste is printed on the upper surface of the green sheet in the same pattern as the jumper electrode layer **29**, the common jumper **71** or the heater electrode **27** required in the order from the lowermost layer, thereby forming a jumper precursor. The uppermost green sheet can be used without any processing.

[0110] The green sheets, which have been subjected to the predetermined processing, are stacked in

order from the lowermost layer to the uppermost layer to form a laminate. This laminate is fired to obtain the ceramic substrate **20**. The electrostatic adsorption electrode **26** and vias (not shown) connected to the electrostatic adsorption electrode **26** can be formed inside the ceramic substrate **20** by a standard method.

[0111] A base plate **30** and a metal bonding material are prepared in addition to the ceramic substrate **20**. The base plate **30** has a refrigerant passage **32**. Additionally, the base plate **30** and the metal bonding material may have through holes for accessing the recesses **34** and **35** of the ceramic substrate **20**. The base plate **30** having the refrigerant passage **32** can be manufactured, for example, by joining multiple aluminum or MMC plate members in which grooves or holes corresponding to the refrigerant passage **32** have been formed by machining using a method such as electron beam, welding, diffusion bonding, or TCB. The through holes can be formed by machining.

[0112] Next, a resin or metal bonding material is sandwiched between the lower surface **23** of the ceramic substrate **20** and the upper surface **31a** of the base plate **30** to form a laminate. Then, the laminate is pressurized and bonded at a temperature no higher than the solidus temperature of the metal bonding material **90** (for example, the temperature 20° C. lower than the solidus temperature or more and no higher than the solidus temperature), and then returned to room temperature (TCB). As a result, the metal bonding material becomes the bonding layer **40**, and a bonded body is obtained in which the ceramic substrate **20** and the base plate **30** are bonded together by the bonding layer **40**. It is preferable to use a metal bonding material having a thickness of about 100 μm (for example, 80 to 240 μm).

[0113] Thereafter, the plurality of terminals **52a** constituting the terminal dense portion **52** are connected to the corresponding first vias **61** by a method such as brazing. Further, the common terminal **72** is connected to the third via **63** by a method such as brazing. Thereafter, the member **10** for a semiconductor manufacturing equipment is completed by appropriately going through processes such as adjusting the overall shape.

DESCRIPTION OF REFERENCE NUMERALS

[0114] **10**: Member for semiconductor manufacturing equipment [0115] **20**: Ceramic substrate [0116] **20a**: Center portion [0117] **20b**: Outer peripheral portion [0118] **21a**: Upper surface [0119] **21b**: Upper surface [0120] **23**: Lower surface [0121] **26**: Electrostatic adsorption electrode [0122] **27**: Heater electrode [0123] **27a**: First connection portion [0124] **27b**: Second connection portion [0125] **28**: Insulator [0126] **29**: Jumper electrode layer [0127] **29a**: (Planar) jumper electrode [0128] **29b**: Insulator [0129] **29c**: Insulator [0130] **30**: Base plate [0131] **30a**: Central portion [0132] **30b**: Flange portion [0133] **31a**: Upper surface [0134] **31b**: Upper surface [0135] **32**: Refrigerant passage [0136] **33**: Lower surface [0137] **34**: Recess [0138] **35**: Recess [0139] **40**: Bonding layer [0140] **42**: Insulating film [0141] **52**: Terminal dense portion [0142] **52a**: Terminal [0143] **54**: Outer periphery [0144] **55**: Single section [0145] **61**: First via [0146] **62**: Second via [0147] **63**: Third via [0148] **64**: Fourth via [0149] **71**: Common jumper [0150] **72**: Common terminal [0151] **73**: Earth wire [0152] **78**: Focus ring [0153] **W**: Wafer

Claims

1. A member for a semiconductor manufacturing equipment comprising a ceramic substrate, the ceramic substrate comprising: an upper surface on which a wafer is to be placed, a terminal dense portion in which 10 or more terminals are arranged within a single section, a plurality of heater electrodes which are zoned, and a plurality of jumper electrode layers that electrically connect the plurality of heater electrodes to each terminal of the terminal dense portion and are stacked in a vertical direction via an insulator; wherein each of the jumper electrode layers is composed of a plurality of planar jumper electrodes that are electrically isolated by an insulator, wherein in at least one of the terminal dense portion, each of 70% or more of all the terminals arranged in the terminal

dense portion is electrically connected to a predetermined planar jumper electrode through a first via extending in the vertical direction, on a condition that it is not electrically connected to a planar jumper electrode located in a layer above any other planar jumper electrode to which other terminals that have a longer distance from an outer periphery of the terminal dense portion than itself are electrically connected, and wherein each of the plurality of planar jumper electrodes is electrically connected to a first connection portion of a predetermined heater electrode selected from the plurality of heater electrodes through a second via extending in the vertical direction.

2. A member for a semiconductor manufacturing equipment according to claim 1, wherein in at least one of the terminal dense portion, at least one terminal T.sub.1 is electrically connected to a planar jumper electrode located in a layer above a planar jumper electrode to which at least one other terminal T.sub.2, which has a longer distance from the outer periphery of the terminal dense portion than the at least one terminal T.sub.1, is electrically connected; and wherein assuming a distance between the at least one terminal T.sub.1 and the outer periphery is M.sub.1 (mm), and a distance between the at least one other terminal T.sub.2 and the outer periphery is M.sub.2 (mm), a formula 1: $M_{sub.1} < M_{sub.2} \leq M_{sub.1} + 2$ is satisfied for all of the at least one terminal T.sub.1.

3. A member for a semiconductor manufacturing equipment according to claim 1, wherein in at least one of the terminal dense portion, each of all the terminals arranged in the terminal dense portion is electrically connected to the predetermined planar jumper electrode through the first via extending in the vertical direction, on the condition that it is not electrically connected to the planar jumper electrode located in the layer above any other planar jumper electrode to which other terminals that have a longer distance from the outer periphery of the terminal dense portion than itself are electrically connected.

4. A member for a semiconductor manufacturing equipment according to claim 1, wherein at least one jumper electrode layer among the plurality of jumper electrode layers electrically connected to the 10 or more terminals constituting the terminal dense portion in each single section is composed of 8 to 12 planar jumper electrodes.

5. A member for a semiconductor manufacturing equipment according to claim 1, wherein assuming a total number of the plurality of jumper electrode layers electrically connected to the 10 or more terminals constituting the terminal dense portion in each single section is A, a number of planar jumper electrodes constituting a N.sup.th jumper electrode layer (N is a natural number from 1 to A) from a lowermost layer is equal to or less than a number of planar jumper electrodes constituting the (N-1).sup.th jumper electrode layer from the lowermost layer, and a number of the planar jumper electrodes constituting the uppermost jumper electrode layer is less than a number of the planar jumper electrodes constituting the lowermost jumper electrode layer.

6. A member for a semiconductor manufacturing equipment according to claim 1, wherein each of the plurality of planar jumper electrodes constituting at least one jumper electrode layer among the plurality of jumper electrode layers electrically connected to the 10 or more terminals constituting the terminal dense portion in each single section has a planar shape having two adjacent line segments at the same angle with a position of the first via as a vertex.

7. A member for a semiconductor manufacturing equipment according to claim 1, wherein each of the plurality of the heater electrodes has a second connection portion, and the second connection portion is connected to a common terminal for grounding via a common jumper.

8. A member for a semiconductor manufacturing equipment according to claim 7, wherein the common jumper is electrically connected to the common terminal through a third via extending in the vertical direction, and a diameter of the third via is larger than a diameter of the first via.

9. A member for a semiconductor manufacturing equipment according to claim 1, wherein in each of the plurality of jumper electrode layers connected to the 10 or more terminals constituting the terminal dense portion in each single section, adjacent planar jumper electrodes are electrically isolated from each other by a linear insulator, and the linear insulator does not linearly overlap any other linear insulator in a different jumper electrode layer in the vertical direction.

10. A member for a semiconductor manufacturing equipment according to claim 1, wherein for any of the plurality of planar jumper electrodes constituting at least one jumper electrode layer among the plurality of jumper electrode layers connected to the 10 or more terminals constituting the terminal dense portion in each single section, a distance between adjacent planar jumper electrodes in the same layer is 0.3 mm or more.
