

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250279353

Kind Code

A1

Publication Date

September 04, 2025

Inventor(s)

Chang; Cheng-Wei et al.

MIDDLE-OF-LINE INTERCONNECT STRUCTURE AND MANUFACTURING METHOD

Abstract

In some embodiments, the present disclosure relates to an integrated circuit device. A transistor structure includes a gate electrode separated from a substrate by a gate dielectric and a pair of source/drain regions disposed within the substrate on opposite sides of the gate electrode. A lower conductive plug is disposed through a lower inter-layer dielectric (ILD) layer and contacting a first source/drain region. A capping layer is disposed directly on the lower conductive plug. An upper inter-layer dielectric (ILD) layer is disposed over the capping layer and the lower ILD layer. An upper conductive plug is disposed through the upper ILD layer and directly on the capping layer.

Inventors: Chang; Cheng-Wei (Taipei City, TW), Wang; Sung-Li (Zhubei City, TW), Liu; Yi-Ying (Hsinchu City, TW), Chu; Chia-Hung (Taipei City, TW), Lee; Fang-Wei (Hsinchu City, TW)

Applicant: Taiwan Semiconductor Manufacturing Company, Ltd. (Hsinchu, TW)

Family ID: 74873021

Appl. No.: 19/211450

Filed: May 19, 2025

Related U.S. Application Data

parent US continuation 18650166 20240430 parent-grant-document US 12334435 child US 19211450

parent US continuation 17875533 20220728 parent-grant-document US 12009294 child US 18650166

parent US division 16844133 20200409 parent-grant-document US 11462471 child US 17875533
us-provisional-application US 62908029 20190930

Publication Classification

Int. Cl.: **H01L23/522** (20060101); **H01L21/285** (20060101); **H01L21/768** (20060101);
H01L23/528 (20060101); **H01L23/532** (20060101)

U.S. Cl.:

CPC **H01L23/5226** (20130101); **H01L21/28568** (20130101); **H01L21/76802** (20130101);
H01L21/76843 (20130101); **H01L21/76864** (20130101); **H01L21/76877** (20130101);
H01L23/528 (20130101); **H01L23/53266** (20130101);

Background/Summary

REFERENCE TO RELATED APPLICATIONS [0001] This Application is a Continuation of U.S. application Ser. No. 18/650,166, filed on Apr. 30, 2024, which is a Continuation of U.S. application Ser. No. 17/875,533, filed on Jul. 28, 2022 (now U.S. Pat. No. 12,009,294, issued on Jun. 11, 2024), which is a Divisional of U.S. application Ser. No. 16/844,133, filed on Apr. 9, 2020 (now U.S. Pat. No. 11,462,471, issued on Oct. 4, 2022), which claims the benefit of U.S. Provisional Application No. 62/908,029, filed on Sep. 30, 2019. The contents of the above-referenced Patent Applications are hereby incorporated by reference in their entirety.

BACKGROUND

[0002] In the manufacturing of integrated circuits (ICs), devices are formed on a wafer and connected by conductive interconnect layers. These conductive interconnect layers can be formed during so-called middle-of-the-line (MOL) processes or back-end-of-line (BEOL) processes. MOL and BEOL processes are similar in that they both form openings in a dielectric layer (e.g. contact holes, trenches, or via holes in a dielectric layer), and then fill these openings with a conductive material. MOL differs from BEOL in that the MOL typically occurs earlier in the fabrication process, and may refer to the process of forming contacts to conductive regions such as source/drain regions in the substrate; whereas BEOL typically occurs later in the fabrication process, and may refer to the process of forming successive metallization layers and vias above the contacts formed by MOL.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

[0003] Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

[0004] FIG. 1 illustrates a cross-sectional view of some embodiments of an integrated circuit having a ruthenium contact structure.

[0005] FIG. 2 illustrates a cross-sectional view of some additional embodiments of an integrated circuit having a ruthenium contact structure.

[0006] FIG. 3 illustrates some embodiments of an integrated circuit having an interconnect structure with an intermixing barrier layer.

[0007] FIGS. 4-17 illustrate cross-sectional views of some embodiments of a method of forming an integrated circuit having a ruthenium contact structure.

[0008] FIG. 18 illustrates a flow diagram of some embodiments of a method of forming an integrated circuit having a ruthenium contact structure.

DETAILED DESCRIPTION

[0009] The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

[0010] Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

[0011] In a middle-of-the-line (MOL) interconnect structure, both contacts and interconnect vias and metal lines play a significant role in transistor and circuit performance. As scaling continues, contact and interconnect resistance is becoming the key limiting factor for device performance. Some solutions are beginning to emerge. For example, the MOL contacts may migrate from traditional tungsten materials to cobalt, which reduces the line resistance in chips. As an example, a first glue layer, e.g. made of titanium nitride (TiN) or tantalum nitride (TaN) and also functioned as a barrier liner, is firstly formed lining a lower plug opening. Then, a lower plug made of cobalt is formed to fill the remainder of the lower plug opening. Above the cobalt plug, a second glue layer (e.g. made of titanium, titanium nitride, or tantalum nitride) may be deposited lining an upper plug opening and reaching on a top surface of the lower plug. The upper plug opening is then filled with an upper plug made of tungsten. The glue layers were carried out for the growth of lower and upper plugs to increase the conformal adhesive between the sidewall interlayer dielectrics and the metal plugs and prevent metal diffusion to the sidewall interlayer dielectric. The tungsten plug may have a relative high resistance due to the phase transition introduced by the high temperature deposition.

[0012] Several ion implantation processes may be required for this cobalt/tungsten plug fabrication process. For example, a first germanium ion implantation process is applied between the filling of the lower cobalt plug and the upper tungsten plug, in order to prevent corrosion effect of the lower plug. It has been appreciated that removing the work piece from the vacuum chamber after forming the metal liner and the barrier liner (i.e., before the subsequent annealing process) has drawbacks. The ambient environment can cause oxidation of the metal liner and/or barrier liner, which can increase the resistance of the resultant interconnect structures. Although this oxidation can be removed by an oxidation reduction process, removal of the oxidation material can lead to the formation of voids. These voids can result in poor electrical connections and can decrease reliability. A second germanium ion implantation process needs to be applied after the filling of the upper tungsten plug to strength the sidewall interface of the tungsten and the sidewall interlayer dielectrics.

[0013] Accordingly, the present disclosure relates to an improved MOL interconnect structure and associated manufacturing methods to reduce contact resistance, reduce voids, improve reliability and simplify manufacturing processes. In some embodiments, a metal core material is filled in a

contact or via opening of an interlayer dielectric without forming a glue layer or barrier layer first. The metal core material is sophisticatedly selected that a thin metal-dielectric intermixing barrier layer can be formed at the interface of the metal core and the interlayer dielectric by a proper annealing process. The metal-dielectric intermixing barrier layer acts as a glue and barrier layer to bond the metal core and prevent it from diffusing to the interlayer dielectric. In a more detailed embodiment, an integrated circuit comprises a contact structure having a lower conductive plug contacting a source/drain region and disposed through a lower inter-layer dielectric (ILD) layer. An upper conductive plug is disposed over the lower conductive plug and through an upper ILD layer. The upper conductive plug may be made of ruthenium (Ru). An intermixing barrier layer of ruthenium oxide may be disposed between the upper conductive plug and the upper ILD layer and acts as a homogeneous glue layer therebetween. The intermixing barrier layer may be formed by an annealing process following a filling process of the ruthenium conductive plug. Ruthenium is a better material to form contacts because of the less resistivity incensement of ruthenium film than tungsten and cobalt. In addition, ruthenium has higher melting point than cobalt and thus provides higher tolerance for subsequent manufacturing processes. As a result, contact resistance is reduced. Also, by forming the ruthenium oxide intermixing barrier layer by an annealing process, deposition processes for forming barrier layers are saved. The intermixing barrier layer ties the upper conductive plug to the upper ILD layer strongly to prevent the formation of voids. The ion implantation processes are also no longer needed because of the good adhesive performance of the intermixing barrier layer. Thus, the manufacturing is simplified and device liability is improved. [0014] In some further embodiments, a capping layer is disposed between the lower conductive plug and the upper conductive plug. A lower barrier layer is disposed covering sidewalls of the capping layer and the lower conductive plug. The capping layer is made of a conductive material such as tungsten. By arranging the capping layer on the lower conductive plug, the upper conductive plug can be electrically coupled to the lower conductive plug, and the formation process of the upper conductive plug can be integrated together with forming a gate electrode plug coupling to a gate electrode.

[0015] FIG. 1 shows a cross-sectional view of an integrated circuit **100** in accordance with some embodiments. As shown in FIG. 1, a transistor structure **101** is disposed over a substrate **102**. The transistor structure **101** can be a logic device that includes a gate electrode **104** separated from the substrate **102** by a gate dielectric layer **105**. A pair of source/drain regions **103a**, **103b** is disposed within the substrate **102** on opposite sides of the gate electrode **104**. In some embodiments, the transistor structure **101** can be a single-gate planar device as well as on a multi-gate device, such as the FinFET device. The transistor structure **101** can also be other devices such as gate-all-around (GAA) devices, Omega-gate devices, or Pi-gate devices, as well as strained-semiconductor devices, silicon-on-insulator (SOI) devices, partially-depleted SOI (PD-SOI) devices, fully-depleted SOI (FD-SOI) devices, or other applicable devices as known in the art.

[0016] Contacts are respectively coupled to the gate electrode **104**, the source/drain regions **103a**, **103b**, body contact regions (not shown), or other active regions of the transistor structure **101**. In some embodiments, a contact may comprise a lower contact structure **142** surrounded by a lower inter-layer dielectric (ILD) layer **110** and electrically connected to an upper contact structure **144** surrounded by an upper inter-layer dielectric (ILD) layer **128** and disposed over the lower ILD layer **110**. In some embodiments, the lower contact structure **142** comprises a lower conductive plug **120** disposed through the lower ILD layer **110** and contacting a first source/drain region **103a**. In some embodiments, the lower conductive plug **120** comprises or is made of cobalt. In some embodiments, a capping layer **124** is disposed directly on the lower conductive plug **120**. In some embodiments, the capping layer **124** comprises or is made of tungsten. In some embodiments, a lower barrier layer **119** is disposed along sidewalls of the lower conductive plug **120**. The lower barrier layer **119** may cover sidewalls of the capping layer **124** and the lower conductive plug **120**. In some embodiments, the capping layer **124** may have a thickness in a range of 8 nm to 15 nm.

[0017] In some embodiments, the upper contact structure **144** comprises an upper conductive plug **137** disposed through the upper ILD layer **128** and directly reaching on the capping layer **124**. In some embodiments, the capping layer **124** isolates the upper conductive plug **137** and the lower conductive plug **120** and may have a top surface directly contacting the upper conductive plug **137** and a bottom surface directly contacting the lower conductive plug **120**. In some embodiments, the upper conductive plug **137** comprises a metal core **138** and an intermixing barrier layer **140** lining an interface of the metal core **138** and the upper ILD layer **128**. The intermixing barrier layer **140** may be a material mixed of materials of the metal core **138** and the upper ILD layer **128**. In some embodiments, the metal core **138** comprises or is made of ruthenium. In some embodiments, the intermixing barrier layer **140** contains ruthenium and oxygen. In some embodiments, the intermixing barrier layer **140** comprises or is made of ruthenium oxide. In some embodiments, the intermixing barrier layer **140** contains ruthenium, silicon, and oxygen. In some embodiments, the intermixing barrier layer **140** contains ruthenium, aluminum, and oxygen. Ruthenium is a better material to form contacts because of the less resistivity incensement of ruthenium film than tungsten and cobalt. Ruthenium metal core may have only hcp (hexagonal close packing) lattice structure comparing to tungsten may have a phase transition to β -W when deposited at a temperature range of 100° C. to 200° C. A bulk resistance of ruthenium plug can be 40% less than that of a tungsten plug. In addition, ruthenium has higher melting point than cobalt and thus provides higher tolerance for subsequent manufacturing processes. As a result, contact resistance is reduced. The intermixing barrier layer **140** acts as a glue and barrier layer to bond the metal core **138** to prevent the formation of voids and to prevent the metal core **138** from diffusing to the upper ILD layer **128**. Thereby, the device liability is improved.

[0018] In some embodiments, the intermixing barrier layer **140** has a thickness in a range of from about 10 nm to about 15 nm. In some embodiments, the upper contact structure **144** further comprises a gate electrode plug **139** disposed next to the upper conductive plug **137** and through the upper ILD layer **128**. The gate electrode plug **139** may be electrically coupled to the gate electrode **104** through a gate barrier layer **114**. The gate electrode **104** may comprise a stack of metal layers including work function metals disposed on a core gate metal. The gate barrier layer **114** may comprise or be made of fluorine-free tungsten (FFW). In some embodiments, the gate electrode plug **139** comprises or is made of the same material of the upper conductive plug **137**, i.e., the metal core **138** and the intermixing barrier layer **140** disposed along the sidewall of the metal core **138**.

[0019] In some embodiments, a first contact etch stop layer (CESL) **116** is disposed between the upper ILD layer **128** and the lower ILD layer **110**. The first contact etch stop layer **116** may have a top surface coplanar with that of the capping layer **124**. As an example, the first contact etch stop layer **116** may comprise or be made of silicon nitride. In some embodiments, the intermixing barrier layer **140** is disposed at an interface of the metal core **138** and the upper ILD layer **128**, but absent from an interface of the metal core **138** and the first contact etch stop layer **116** and an interface of the metal core **138** and the gate barrier layer **114**.

[0020] FIG. 2 shows a cross-sectional view of an integrated circuit **200** in accordance with some additional embodiments. Besides the upper conductive plug **137** and the gate electrode plug **139** described above in FIG. 1, the upper contact structure **144** may also comprise a power rail (VDR) conductive plug **141** comprising the metal core **138** and the intermixing barrier layer **140** lining the interface of the metal core **138** and the upper ILD layer **128**. The VDR conductive plug **141** comprises a first portion **141a** electrically coupled to a source/drain region **103** through the lower conductive plug **120** and a second portion **141b** disposed through the first contact etch stop layer **116** and electrically coupled to the gate electrode **104**. The first portion **141a** has a bottom surface **141s** disposed on the capping layer **124**. In some embodiments, the VDR conductive plug **141** comprises or is made of the same material of the upper conductive plug **137** and the gate electrode plug **139**, i.e., the metal core **138** and the intermixing barrier layer **140** disposed along the sidewall

of the metal core **138**. The intermixing barrier layer **140** of the VDR conductive plug **141** may be absent from the bottom surface **141s** and an interface of the metal core **138** and the first contact etch stop layer **116**. In some embodiments, the VDR conductive plug **141** may have a depth in a range of 18 nm to 33 nm and a width in a range of 20 nm to 35 nm, the upper conductive plug **137** may have a depth in a range of 18 nm to 22 nm and a width in a range of 9 nm to 17 nm, and the gate electrode plug **139** may have a depth in a range of 28 nm to 35 nm and a width in a range of 7 nm to 15 nm.

[0021] In some embodiments, a second contact etch stop layer **126** is formed over the first contact etch stop layer **116**, and the upper ILD layer **128** is formed over the second contact etch stop layer **126**. As an example, the second contact etch stop layer **126** may comprise or be made of aluminum oxide. The second contact etch stop layer **126** may also comprise or be made of nitride dielectric material such as silicon nitride. In some embodiments, the upper ILD layer **128** may include or be made of materials such as tetraethylorthosilicate (TEOS) oxide, un-doped silicate glass, or doped silicon oxide such as borophosphosilicate glass (BPSG), fused silica glass (FSG), phosphosilicate glass (PSG), boron doped silicon glass (BSG), and/or other suitable dielectric materials. Thus, in some cases, the upper ILD layer **128** may be substantially the same as the lower ILD layer **110**. In some embodiments, the intermixing barrier layer **140** may comprise an upper portion and a lower portion. The upper portion covers an interface of the metal core **138** and the upper ILD layer **128**. The lower portion covers an interface of the metal core **138** and the second contact etch stop layer **126**. In some embodiments, the upper ILD layer **128** and the second contact etch stop layer **126** may comprise or be made of materials with different ratios of oxygen atoms, such that ratios of oxygen atoms in the lower portion and the upper portion of the intermixing barrier layer **140** may differ. In some alternative embodiments, the intermixing barrier layer **140** may be disposed at an interface of the metal core **138** and the upper ILD layer **128**, but be absent from an interface of the metal core **138** and the second contact etch stop layer **126**. In this instance, the second contact etch stop layer **126** may comprise non-oxide dielectric materials such as silicon nitride. In some embodiments, the intermixing barrier layer **140** may not cover an interface of the metal core **138** and the first contact etch stop layer **116**, and the metal core **138** directly contacts the first contact etch stop layer **116**. In this instance, the first contact etch stop layer **116** may comprise silicon nitride. In some examples, the second contact etch stop layer **126** has a thickness of about 5-20 nm, and the upper ILD layer **128** has a thickness of about 5-40 nm.

[0022] FIG. 3 illustrates some embodiments of an integrated circuit **300** having an interconnect structure with a metal core separated from an ILD layer by an intermixing barrier layer. Though the intermixing barrier layer structure is described above associated with the upper contact structure **144** as shown in FIG. 1 and FIG. 2, it is appreciated that similar structures and manufacturing processes can also be used to form other conductive vias or even metal lines for MOL interconnect structure or even other interconnect structures in order to achieve improved connecting performance. In some embodiments, the integrated circuit **300** comprises a dielectric layer **306** disposed over the substrate **102**. A conductive interconnect structure **320** is disposed within an opening **322** vertically extending through the dielectric layer **306**. The conductive interconnect structure **320** can be a contact plug, a via, or a metal line connecting two conductive features **304**, **318**. In some embodiments, the conductive features **304**, **318** can respectively be metal lines or metal vias of an interconnect structure. In some alternative embodiments, the conductive feature **304** is a middle-of-the-line (MOL) structure, an active region of a semiconductor device comprising a doped semiconductor structure, such as a source/drain region or polysilicon gate or metal gate of a transistor.

[0023] The conductive interconnect structure **320** comprises a metal core **138** and an intermixing barrier layer **140** lining an interface of the metal core **138** and the dielectric layer **306**. Similar as illustrated above, the intermixing barrier layer **140** may be a material mixed of materials of the metal core **138** and the dielectric layer **306**. The metal core **138** may be a continuous conductive

body of uniform material with a thickness of from about 200 nm to about 600 nm. The intermixing barrier layer **140** may be formed by performing an annealing process to mix and form a very thin liner between the metal core **138** and the dielectric layer **306**. A thickness of the intermixing barrier layer **140** may be in wherein the intermixing barrier layer has a thickness in a range of from about 10 nm to about 15 nm. In some embodiments, the metal core **138** is ruthenium, and the intermixing barrier layer **140** comprises or is made of a compound of oxygen atoms and ruthenium atoms, providing adhesion and isolation between the conductive interconnect structure **320** and the dielectric layer **306**.

[0024] FIGS. **4-17** illustrate cross-sectional views **400-1700** of some embodiments of a method of forming an integrated circuit having a ruthenium contact structure. Although FIGS. **4-17** are described in relation to a method, it will be appreciated that the structures disclosed in FIGS. **4-17** are not limited to such a method, but instead may stand alone as structures independent of the method.

[0025] As shown in FIG. **4** and FIG. **5**, a transistor structures **101** is formed over a substrate **102** and surrounded by a lower ILD layer **110**. In some embodiments, the transistor structure **101** has a gate dielectric layer **105** over the substrate **102**, a gate electrode **104** over the gate dielectric layer **105**, and a pair of source/drain regions **103** within the substrate **102** disposed on opposite sides of the gate electrode **104** (see FIG. **5**). The gate electrode **104** may be a polysilicon gate or a metal gate. The gate dielectric layer **105** may comprise or be made of a silicon dioxide layer or a high-k dielectric material such as hafnium dioxide. The gate electrode **104** and the gate dielectric layer **105** may be formed by a replacement gate process where a dummy gate **404** is firstly formed and patterned over the substrate **102**. Sidewall spacers **106**, **108** may be formed alongside the dummy gate **404** lining or covering sidewalls of the dummy gate **404** (see FIG. **4**). Then, source/drain regions **103** may be formed on opposite sides of the sidewall spacers **106**, **108** within the substrate **102**. In some cases, each of the sidewall spacer **106**, **108** include materials having different dielectric constant values (e.g., k values). In various embodiments, the sidewall spacer **106**, **108** include silicon oxide, silicon nitride, silicon carbide, aluminum oxide, aluminum nitride or the combinations thereof, or other suitable dielectric materials. In some embodiments, the sidewall spacer **106**, **108** include multiple layers, such as main spacer walls, liner layers, and the like. As an example, the sidewall spacer **106**, **108** may be formed by depositing a dielectric material over the dummy gate **404** and vertically etching back the dielectric material to have a top surface substantially coplanar with that of the dummy gate **404**.

[0026] As shown in FIG. **5**, a dielectric layer is deposited over the transistor structures **101** followed by a planarization process to form the lower ILD layer **110**. As an example, the dielectric layer may include materials such as tetraethyl-orthosilicate (TEOS) oxide, un-doped silicate glass, or doped silicon oxide such as borophosphosilicate glass (BPSG), fused silica glass (FSG), phosphosilicate glass (PSG), boron doped silicon glass (BSG), and/or other suitable dielectric materials. The lower ILD layer **110** may be deposited by a subatmospheric CVD (SACVD) process, a flowable CVD process, or other suitable deposition technique. The dielectric layer may be planarized by a chemical mechanical planarization (CMP) process to have a top surface substantially coplanar with that of the sidewall spacer **106**, **108**. As an example, the lower ILD layer **110** has a thickness of about 5-40 nm. For the replacement gate process, the dummy gate **404** in FIG. **4** is then removed and replaced by the gate electrode **104**. The gate dielectric layer **105** may also be formed after removing the dummy gate **404**. To form the gate electrode **104**, stacks of metal materials may be filled in gate openings followed by a planarization process to remove excessive portions above the lower ILD layer **110**. Varied for different devices, the stacks of metal materials may comprise or be made of titanium nitride, tantalum nitride, titanium aluminum, and aluminum, etc. Other materials can also be used for the gate electrode **104**.

[0027] As shown in FIG. **6**, the gate electrode **104** is recessed. In some embodiments, a patterning process is firstly performed to form a masking layer **112** over the lower ILD layer **110**, leaving the

gate electrode exposed. Then, an etching process is performed to the gate electrode **104** to lower a top surface of the gate electrode to a position lower than a top surface of the sidewall spacers **106**, **108**. The etching process controls a thickness of the gate electrode and thus tunes an effective work function of the gate electrode **104** to a desired value.

[0028] As shown in FIG. 7, a gate barrier layer **114** is formed on the recessed upper surface of the gate electrode **104** and may function as a diffusion barrier. In some embodiments, the gate barrier layer **114** comprises or is made of fluorine-free tungsten (FFW). The gate barrier layer **114** prevent material intermixing of the gate electrode **104** and a gate electrode plug to be formed such that a threshold voltage degradation can be reduced or prevented. In some embodiments, the gate barrier layer **114** may be deposited using a metal organic tungsten source not containing fluorine (F). Since fluorine (F) is not included in the layer, a surface of the underlying gate electrode **104** is not deteriorated. The gate barrier layer **114** may be etched back to have the top surface lowered to a position lower than a top surface of the sidewall spacers **106**, **108**. In some embodiments, the masking layer **112** comprises or is made of photoresist material. In some alternative embodiments, the masking layer **112** may comprise or is made of hard masking material such as silicon oxide, silicon nitride, or other applicable metal or dielectric material.

[0029] As shown in FIG. 8, a first contact etch stop layer **116** is formed over the gate barrier layer **114** filling a remaining upper portion of the sidewall spacer **106**. The first contact etch stop layer **116** may comprise or be made of silicon nitride and may be deposited and then planarized to cover top surfaces of the lower ILD layer **110** and the sidewall spacers **106**, **108**.

[0030] As shown in FIG. 9, a first pattern, that includes an opening **118**, is formed through the first contact etch stop layer **116** and the lower ILD layer **110**. In some cases, the opening **118** provides access to source, drain, or body contact regions. As an example, the opening **118** may be formed by a suitable combination of lithographic patterning and etching (e.g., wet or dry etching) processes. A metallization process may be performed to form a semiconductor-metal compound (such as silicide, germanides, germanosilicide) layer on exposed portions of the substrate **102** (e.g., exposed by the opening **118**), thus providing a low resistance contact.

[0031] As shown in FIG. 10, in some examples, a lower glue or barrier layer **119** may be formed within the opening **118**. In some cases, the lower glue or barrier layer **119** may include Ti, TiN, Ta, TaN, W, or other appropriate material. Then, a lower conductive plug **120** may be formed on the lower glue or barrier layer **119** within the opening **118**. In some examples, the lower conductive plug **120** may include cobalt, or other appropriate material such as W, Cu, Ru, Al, Rh, Mo, Ta, Ti. After the deposition of the lower conductive plug **120**, a chemical mechanical planarization (CMP) process may be performed to remove excess material of the lower glue or barrier layer **119** and the lower conductive plug **120** and planarize the top surface of the workpiece. In some embodiments, an annealing process may be performed after filling the lower barrier layer **119** and the lower conductive plug **120** to form a semiconductor-metal compound film at an interface of the lower barrier layer **119** and the exposed portion of the upper surface of the source/drain region **103**.

[0032] As shown in FIG. 11, the lower conductive plug **120** is recessed and thus an opening **122** is formed within an upper portion of the lower barrier layer **119**. An etching process is performed to the lower conductive plug **120** to lower a top surface of the lower conductive plug **120** to a position lower than a top surface of the barrier layer **119**.

[0033] As shown in FIG. 12, a capping layer **124** is formed to fill the opening **122** within the upper portion of the lower barrier layer **119**. In some embodiments, the capping layer **124** may be formed by depositing selective tungsten followed by a CMP process. The capping layer **124** may have a top surface substantially coplanar with that of the first etch stop layer **116** and/or the lower barrier layer **119**. The lower barrier layer **119** may cover the whole surfaces of the lower conductive plug **120** and the capping layer **124**. The capping layer **124** provides a protection and isolation to the lower conductive plug **120**.

[0034] As shown in FIG. 13, a second contact etch stop layer **126** is formed over the first contact

etch stop layer **116**, and an upper ILD layer **128** is formed over the second contact etch stop layer **126**. As an example, the second contact etch stop layer **126** may comprise or be made of aluminum oxide. The second contact etch stop layer **126** may also comprise or be made of silicon nitride (SiN) or Zirconia (ZrO₂). Other applicable dielectric materials may also be used for the second contact etch stop layer **126**. In some embodiments, the upper ILD layer **128** may include materials such as tetraethylorthosilicate (TEOS) oxide, un-doped silicate glass, or doped silicon oxide such as borophosphosilicate glass (BPSG), fused silica glass (FSG), phosphosilicate glass (PSG), boron doped silicon glass (BSG), and/or other suitable dielectric materials. Thus, in some cases, the upper ILD layer **128** may be substantially the same as the lower ILD layer **110**. In various embodiments, the second contact etch stop layer **126** and the upper ILD layer **128** may be deposited by a subatmospheric CVD (SACVD) process, a flowable CVD process, an ALD process, a PVD process, or other suitable deposition technique. In some examples, the second contact etch stop layer **126** has a thickness of about 5-20 nm, and the upper ILD layer **128** has a thickness of about 5-40 nm.

[0035] As shown in FIGS. **14-16**, a plurality of openings **130, 132, 134, 136** is formed to reach on the gate barrier layer **114** or the capping layer **124** and then filled with a core metal material. In some embodiments, the core metal material is ruthenium. The plurality of openings **130, 132, 134, 136** can be formed one by one in any order or in some combination manner, but the plurality of openings **130, 132, 134, 136** may be all formed prior to filling the core metal material concurrently. The openings **130, 132, 134, 136** may respectively be formed by a multiple-step etching process separately to improve etch selectivity and provide over-etch control. For example, referring to FIG. **15**, the opening **134** may be formed by performing a first etch having a high etching rate to the upper ILD layer **128** and stopping on the second etch stop layer **126**. Then, a second etch is performed to etch the second etch stop layer **126** slowly and thus expose the capping layer **124** without too much over etching. Similarly, referring to FIG. **14**, the opening **130** may be formed by performing a first etch having a high etching rate to the upper ILD layer **128** and stopping on the second etch stop layer **126**. Then, a second etch is performed to etch the second etch stop layer **126** and the first etch stop layer **116** slowly and thus expose the gate barrier layer **114** without too much over etching. Alternatively, the opening **130** may be formed by performing a first etch having a high etching rate to the upper ILD layer **128** and the second etch stop layer **126** and stopping on the first etch stop layer **116**. Then, a second etch is performed to etch the first etch stop layer **116** slowly and thus expose the gate barrier layer **114** without too much over etching. As an example, in FIG. **14**, a second pattern, including an opening **130**, is formed through the upper ILD layer **128**, the second contact etch stop layer **126**, and the first contact etch stop layer **116**. In some embodiments, the patterning process (e.g., for the formation of the plurality of openings) may include a multiple-step etching process to etch the upper ILD layer **128**, the second contact etch stop layer **126**, and the first contact etch stop layer **116** separately to improve etch selectivity and provide over-etch control. The opening **130** may also be formed by a suitable combination of lithographic patterning and etching (e.g., wet or dry etching) processes. In some cases, the opening **130** provides access to the gate electrode **104** through the gate barrier layer **114**.

[0036] In FIG. **15**, a third pattern, including a first opening **134** and a second opening **136**, is formed through the upper ILD layer **128** and the second contact etch stop layer **126**. In some embodiments, the patterning process (e.g., for the formation of the plurality of openings) may include a multiple-step etching process to etch the upper ILD layer **128** and the second contact etch stop layer **126** separately to improve etch selectivity and provide over-etch control. The openings **134, 136** may also be formed by a suitable combination of lithographic patterning and etching (e.g., wet or dry etching) processes. In some embodiments, an additional opening **132** may be formed in FIG. **14** and may be merged with the opening formed in FIG. **15** to form the opening **136**.

[0037] As shown in FIG. **16**, one or more metal layers are deposited to form metal cores **138** in the openings **130, 134, 136**. In some cases, the VDR conductive plug **141** provides for a direct contact

between the gate electrode **104** and an adjacent source, drain, and/or body region. The upper conductive plug **137** provides an access to the source/drain regions within the substrate **102** through the lower conductive plug **120**, and the gate electrode plug **139** provides access to the gate electrode **104**. As discussed above, the capping layer **124** isolates and protects the lower conductive plug **120**. The gate barrier layer **114** isolates and protects the gate electrode **104**. By arranging the the first etch stop layer **116**, the second etch stop layer **126**, the capping layer **124** on the lower conductive plug **120**, and the gate barrier layer **114** on the gate electrode **104** as disclosed, the formation process of the upper conductive plug **137** can be integrated together with forming the gate electrode plug **139** and the VDR conductive plug **141**. In some embodiments, the metal core **138** is formed by a chemical vapor deposition (CVD) process of ruthenium at a temperature range of 120° C. to 220° C. The ruthenium precursor may be in solid state. The ingredient of ruthenium precursor is comprised or is made of Ru, C, and O. The precursor may vaporize at a temperature range of 120° C. to 260° C. Ruthenium may be deposited on SiO₂, AlO_x, W, SiN, or Co substances.

[0038] As shown in FIG. **17**, an annealing process is performed such that a metal-dielectric intermixing barrier layer **140** is formed at an interface of the metal core **138** and the upper ILD layer **128**. The intermixing barrier layer **140** may be formed at interfaces where the metal cores **138** contact dielectric materials having certain atoms. For example, ruthenium and oxygen atoms can form a self-limiting intermixing layer. The metal core **138** made of ruthenium forms the intermixing barrier layer **140** with dielectric materials containing oxygen atoms. As such, the intermixing barrier layer **140** may comprise an upper portion and a lower portion. The upper portion covers an interface of the metal core **138** and the upper ILD layer **128**. The lower portion covers an interface of the metal core **138** and the second contact etch stop layer **126**. In some embodiments, the upper ILD layer **128** and the second contact etch stop layer **126** may comprise or be made of materials with different ratios of oxygen atoms, such that ratios of oxygen atoms in the lower portion and the upper portion of the intermixing barrier layer **140** may differ. In some embodiments, the intermixing barrier layer **140** may not cover an interface of the metal core **138** and the first contact etch stop layer **116**. Thus, the metal core **138** may directly contact the first contact etch stop layer **116**. The metal-dielectric intermixing barrier layer **140** acts as a barrier and adhesive layer between the metal material of the metal cores **138** and the dielectric material of the upper ILD layer **128**. Growth and reflow of the metal core **138** can be tuned by tailoring the working temperature. The needed annealing conditions depend on materials and device structure. The annealing process for a ruthenium metal core and oxide dielectric material should be performed at a temperature greater than 450° C. For example, an annealing at 530° C. for three hours can form a ruthenium-oxide intermixing barrier layer with a thickness in a range of from 14 Å to 34 Å. In some embodiments, the annealing process is performed at a temperature range of 490° C. to 550° C. The intermixing barrier layer **140** may have a thickness in a range of from 10 nm to 15 nm.

[0039] FIG. **18** illustrates a flow diagram of some embodiments of a method **1800** of forming an integrated chip having an interconnect structure with an intermixing barrier layer.

[0040] While method **1800** is illustrated and described below as a series of acts or events, it will be appreciated that the illustrated ordering of such acts or events are not to be interpreted in a limiting sense. For example, some acts may occur in different orders and/or concurrently with other acts or events apart from those illustrated and/or described herein. In addition, not all illustrated acts may be required to implement one or more aspects or embodiments of the description herein. Further, one or more of the acts depicted herein may be carried out in one or more separate acts and/or phases.

[0041] At **1802**, a transistor structure is formed and surrounded by a lower ILD layer. The transistor structure comprises a gate electrode formed over a substrate and a pair of source/drain regions disposed on opposite sides of the gate electrode. A sidewall spacer is formed alongside the gate

electrode lining or covering sidewalls of the gate electrode. FIGS. **4-5** illustrate cross-sectional views **400-500** of some embodiments corresponding to act **1802**.

[0042] At **1804**, the gate electrode is recessed and a gate barrier layer is formed on the recessed upper surface of the gate electrode. In some embodiments, the gate barrier layer comprises or is made of fluorine-free tungsten (FFW). In some embodiments, a first contact etch stop layer is formed over the gate barrier layer filling a remaining upper portion of the sidewall spacer. FIGS. **6-8** illustrate cross-sectional views **600-800** of some embodiments corresponding to act **1804**.

[0043] At **1806**, a lower barrier layer and a lower conductive plug are formed through the lower ILD layer reaching on a source/drain region of the transistor structure within the substrate. FIGS. **9-10** illustrate cross-sectional views **900-1000** of some embodiments corresponding to act **1806**.

[0044] At **1808**, the lower conductive plug is recessed and a capping layer is formed to fill an upper portion of the lower barrier layer. In some embodiments, the capping layer may be formed by depositing selective tungsten followed by a CMP process. FIGS. **11-12** illustrate cross-sectional views **1100-1200** of some embodiments corresponding to act **1808**.

[0045] At **1810**, an upper ILD layer over the lower ILD layer and the capping layer. FIG. **13** illustrates a cross-sectional view **1300** of some embodiments corresponding to act **1810**.

[0046] At **1812**, a plurality of openings is formed through the upper ILD layer and/or the first contact etch stop layer reaching on the gate barrier layer or the capping layer. FIGS. **14-15** illustrate cross-sectional views **1400-1500** of some embodiments corresponding to act **1812**.

[0047] At **1814**, the plurality of openings is filled with a metal material to form a plurality of conductive plugs. In some embodiments, the metal material is ruthenium. FIG. **16** illustrates a cross-sectional view **1600** of some embodiments corresponding to act **1814**.

[0048] At **1816**, an annealing process is performed such that a metal-dielectric intermixing barrier layer is formed at an interface of the plurality of conductive plugs and the upper ILD layer. The metal-dielectric intermixing barrier layer acts as a barrier and adhesive layer between the metal material of the plurality of conductive plugs and the dielectric material of the upper ILD layer. In some embodiments, the metal material is ruthenium. FIG. **17** illustrates a cross-sectional view **1700** of some embodiments corresponding to act **1816**.

[0049] Therefore, the present disclosure relates to a new integrated circuit device that eliminates a glue or barrier layer between an interconnect feature and a surrounding ILD layer and a method of manufacturing such a device by using an annealing process to form a metal-dielectric intermixing barrier layer.

[0050] Accordingly, in some embodiments, the present disclosure relates to an integrated circuit device. A transistor structure includes a gate electrode separated from a substrate by a gate dielectric and a pair of source/drain regions disposed within the substrate on opposite sides of the gate electrode. A lower conductive plug is disposed through a lower inter-layer dielectric (ILD) layer and contacting a first source/drain region. A capping layer is disposed directly on the lower conductive plug. An upper inter-layer dielectric (ILD) layer is disposed over the capping layer and the lower ILD layer. An upper conductive plug is disposed through the upper ILD layer and directly on the capping layer.

[0051] In other embodiments, the present disclosure relates to an integrated circuit device. A lower inter-layer dielectric (ILD) layer is disposed over a substrate and has a lower plug opening vertically extending through the lower ILD layer. A lower barrier layer is disposed along sidewall surfaces of the lower plug opening and a lower conductive plug fills a lower portion of the lower plug opening. An upper ILD layer is disposed over the lower ILD layer and has an upper plug opening vertically extending through the upper ILD layer. An upper conductive plug fills the upper plug opening and comprises an intermixing barrier layer disposed along sidewall surfaces of the upper plug opening and a metal core filling remaining space of the upper plug opening.

[0052] In yet other embodiments, the present disclosure relates to a method of forming an integrated circuit device. The method comprises forming a lower inter-layer dielectric (ILD) layer

over a substrate and forming a lower conductive plug through the lower ILD layer reaching on a source/drain region of a transistor structure within the substrate. The method further comprises forming a capping layer on the lower conductive plug and forming an upper ILD layer over the lower ILD layer and the capping layer. The method further comprises forming an upper conductive plug through the upper ILD layer reaching the capping layer. The upper conductive plug is formed by forming a core metal followed by a self-protecting annealing process to form an intermixing barrier layer lining an interface of the metal core and the upper ILD layer.

[0053] The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. An integrated circuit device, comprising: a lower inter-layer dielectric (ILD) layer disposed over a substrate; a lower conductive plug disposed in the lower ILD layer; an upper ILD layer disposed over the lower ILD layer; and an upper conductive plug disposed in the upper ILD layer and comprising a first lower surface overlying the lower conductive plug and a second lower surface laterally spaced from the lower conductive plug and extending beneath an uppermost surface of the lower conductive plug.
2. The integrated circuit device of claim 1, wherein the lower conductive plug further comprises a lower barrier layer having the uppermost surface and a lower metal core having an upper surface beneath the uppermost surface.
3. The integrated circuit device of claim 2, wherein the second lower surface of the upper conductive plug extends beneath the upper surface of the lower metal core.
4. The integrated circuit device of claim 1, further comprising a first etch stop layer separating the lower ILD layer and the upper ILD layer and extending from the first lower surface to the second lower surface.
5. The integrated circuit device of claim 1, further comprising a gate, the gate comprising: a gate electrode over the substrate; a gate dielectric extending between the gate electrode and the substrate; and a gate barrier layer covering an upper surface of the gate electrode, wherein the second lower surface of the upper conductive plug contacts the gate barrier layer.
6. The integrated circuit device of claim 1, further comprising: a first etch stop layer separating the lower ILD layer and the upper ILD layer; and a lower barrier layer surrounding the lower conductive plug, wherein an upper surface of the lower barrier layer is level with an upper surface of the first etch stop layer.
7. The integrated circuit device of claim 6, further comprising a capping layer covering an upper surface of the lower conductive plug, the capping layer confined between inner sidewalls of the lower barrier layer and having an upper surface substantially coplanar with the upper surface of the lower barrier layer and the upper surface of the first etch stop layer.
8. An integrated device, comprising: a lower inter-layer dielectric (ILD) layer disposed over a substrate; a lower conductive plug disposed in the lower ILD layer and comprising a lower conductive core and a lower barrier layer; a capping layer comprising a different material from the lower conductive core, covering a first upper surface of the lower conductive core, and confined between inner sidewalls of the lower barrier layer; an upper ILD layer disposed over the lower ILD layer; and an upper conductive plug disposed in the upper ILD layer and comprising an upper

conductive core and an intermixing barrier layer disposed along sidewall surfaces of the upper conductive core, wherein the upper conductive core has a first lower surface that is substantially level with a second upper surface of the capping layer, and wherein the first lower surface extends from a point directly overlying the capping layer to a point spaced from the capping layer in a first direction substantially parallel to the second upper surface of the capping layer.

9. The integrated device of claim 8, wherein the upper conductive core has a second lower surface extending beneath the first lower surface and a lowermost surface of the intermixing barrier layer.

10. The integrated device of claim 9, wherein the intermixing barrier layer extends from an uppermost surface of the upper conductive core to the first lower surface of the upper conductive core.

11. The integrated device of claim 9, further comprising a gate on the substrate, wherein the second lower surface of the upper conductive core contacts the gate, and wherein the first lower surface of the upper conductive core contacts the second upper surface of the capping layer.

12. The integrated device of claim 9, wherein a third upper surface of the lower conductive core is above the second lower surface of the upper conductive core.

13. The integrated device of claim 8, wherein the upper conductive core comprises ruthenium.

14. The integrated device of claim 8, wherein the intermixing barrier layer comprises both atoms of a material of the upper conductive core and atoms of a material of the upper ILD layer.

15. An integrated circuit device, comprising: a lower inter-layer dielectric (ILD) layer disposed over a substrate; a lower conductive plug comprising a lower metal core and a lower barrier layer disposed in the lower ILD layer; an upper ILD layer disposed over the lower ILD layer; an upper conductive plug disposed in the upper ILD layer; and a first etch stop layer disposed between the upper ILD layer and the lower ILD layer, the first etch stop layer comprising a portion that is beneath an uppermost surface of the lower metal core and above a lowermost surface of the upper conductive plug.

16. The integrated circuit device of claim 15, wherein upper conductive plug comprises a lower surface above the lowermost surface that faces the uppermost surface of the lower conductive plug.

17. The integrated circuit device of claim 16, wherein the upper conductive plug comprises an upper metal core having the lower surface and the lowermost surface and an intermixing barrier layer having a second lowermost surface level with the lower surface of the upper metal core.

18. The integrated circuit device of claim 15, wherein the upper conductive plug extends from an uppermost surface of the first etch stop layer to a lowermost surface of the first etch stop layer.

19. The integrated circuit device of claim 15, wherein the lower metal core is spaced from the upper conductive plug by a capping layer, and wherein the lower barrier layer extends from the lower metal core to the upper conductive plug.

20. The integrated circuit device of claim 15, wherein the upper conductive plug further comprises a lower surface level with an uppermost surface of the first etch stop layer.
