

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent Application Publication

20250286095

Kind Code

A1

Publication Date

September 11, 2025

Inventor(s)

KIM; Jung Ho et al.

MEMBRANE-ELECTRODE ASSEMBLY AND METHOD FOR MANUFACTURING SAME

Abstract

Disclosed are: a membrane-electrode assembly having enhanced adhesion and interfacial durability between a polymer electrolyte membrane and electrodes; and a method for manufacturing a membrane-electrode assembly, in which, in forming electrodes by directly coating a catalyst slurry on a polymer electrolyte membrane, adhesion and interfacial durability between the polymer electrolyte membrane and the electrodes can be enhanced without a separate additional step, thus improving both the durability and the productivity of the membrane-electrode assembly. The method comprises the steps of: dispersing a catalyst and an ion conductor in a dispersion medium to obtain a catalyst slurry; applying the catalyst slurry onto a polymer electrolyte membrane; and drying the catalyst slurry applied onto the polymer electrolyte membrane to form an electrode. The dispersion medium is a solvent capable of forming a plurality of grooves on a surface of the polymer electrolyte membrane, and, when the electrode is formed through the drying step, at least some of the grooves are filled with the catalyst, the ion conductor, or a mixture thereof.

Inventors: KIM; Jung Ho (Seoul, KR), KIM; Jun Young (Seoul, KR), SONG; Kah-Young (Seoul, KR), KONG; Nakwon (Seoul, KR), LEE; Jusung (Seoul, KR), NAM; Kyoungsik (Seoul, KR), PARK; Chanmi (Seoul, KR)

Applicant: KOLON INDUSTRIES, INC. (Seoul, KR)

Family ID: 1000008628953

Appl. No.: 19/218223

Filed: May 24, 2025

Foreign Application Priority Data

KR

10-2020-0176531

Dec. 16, 2020

Related U.S. Application Data

Publication Classification

Int. Cl.: **H01M8/1004** (20160101); **H01M4/88** (20060101)

U.S. Cl.:

CPC **H01M8/1004** (20130101); **H01M4/881** (20130101); **H01M4/8828** (20130101);
H01M4/8882 (20130101);

Background/Summary

CROSS REFERENCE TO RELATED APPLICATION(S) [0001] This is a divisional application of U.S. application Ser. No. 17/758,572 filed on Jul. 9, 2022 which is a National Stage of International Application No. PCT/KR2021/017999 filed on Dec. 1, 2021, claiming priority based on Korean Patent Application No. 10-2020-0176531 filed on Dec. 16, 2020, the disclosure of which are incorporated herein by reference in their entireties.

TECHNICAL FIELD

[0002] The present disclosure relates to a membrane-electrode assembly manufacturing method, and more particularly to a membrane-electrode assembly with increased adhesive strength between a polymer electrolyte membrane and an electrode and improved durability of the interface therebetween and a membrane-electrode assembly manufacturing method capable of, in directly coating a catalyst slurry on a polymer electrolyte membrane to form an electrode, increasing the adhesive strength between the polymer electrolyte membrane and the electrode and durability of the interface therebetween without a separate additional process, whereby it is possible to improve both durability and productivity of a membrane-electrode assembly.

BACKGROUND ART

[0003] A polymer electrolyte membrane fuel cell (PEMFC), which is configured to generate electricity using a structure in which unit cells, each of which includes a membrane-electrode assembly (MEA) and a separator (also referred to as a bipolar plate), are stacked, has attracted attention as a next-generation energy source capable of replacing fossil fuels due to high energy efficiency and environmentally friendly characteristics thereof.

[0004] The membrane-electrode assembly generally includes an anode (also referred to as a fuel electrode), a cathode (also referred to as an air electrode), and a polymer electrolyte membrane disposed therebetween.

[0005] When fuel such as hydrogen gas is supplied to the anode, hydrogen ions (H^{sup.+}) and electrons (e^{sup.-}) are generated at the anode as the result of hydrogen oxidation reaction. The generated hydrogen ions are transferred to the cathode via the polymer electrolyte membrane, and the generated electrons are transferred to the cathode via an external circuit. Oxygen supplied to the cathode is bonded with the hydrogen ions and the electrons, and water is generated as the result of reduction.

[0006] Low durability of the interface between a polymer electrolyte membrane and an electrode causes deterioration in performance of a membrane-electrode assembly due to long-term operation of a fuel cell. Low durability of the interface between the polymer electrolyte membrane and the electrode results from insufficient adhesive strength therebetween.

[0007] In order to increase the adhesive strength between the polymer electrolyte membrane and

the electrode, forming irregularities on the surface of the polymer electrolyte membrane to increase surface roughness thereof using (i) a physical method, such as stamp pressing, sandpapering, sandblasting, or rubbing, or (ii) a physical and chemical method, such as plasma treatment or corona discharge treatment, has been proposed.

[0008] Since a separate additional process of providing surface roughness to the polymer electrolyte membrane is needed, however, the above methods are not preferable in terms of simplicity in process and limit improvement in productivity of a membrane-electrode assembly. In addition, the adhesive strength between a polymer electrolyte membrane and an electrode of a membrane-electrode assembly manufactured using the above methods is not sufficiently high, whereby satisfactory durability of the interface therebetween cannot be secured.

DISCLOSURE

Technical Problem

[0009] Therefore, the present disclosure relates to a membrane-electrode assembly capable of solving problems due to limitations and shortcomings of the related technology described above and a method of manufacturing the same.

[0010] It is an object of the present disclosure to provide a membrane-electrode assembly with increased adhesive strength between a polymer electrolyte membrane and an electrode and improved durability of the interface therebetween.

[0011] It is another object of the present disclosure to provide a membrane-electrode assembly manufacturing method capable of, in directly coating a catalyst slurry on a polymer electrolyte membrane to form an electrode, increasing the adhesive strength between the polymer electrolyte membrane and the electrode and durability of the interface therebetween without a separate additional process, whereby it is possible to improve both durability and productivity of a membrane-electrode assembly.

[0012] In addition to the above objects, other features and advantages of the present disclosure will be described hereinafter, or will be clearly understood by those skilled in the art to which the present disclosure pertains from the following description thereof.

Technical Solution

[0013] In accordance with an aspect of the present disclosure, there is provided a membrane-electrode assembly including a polymer electrolyte membrane and a first electrode on a first surface of the polymer electrolyte membrane, wherein the first electrode includes a first catalyst and a first ion conductor, a plurality of grooves are randomly formed on the first surface, each of the grooves has a depth of 5 μm or less and a width of 10 μm or less, each of the grooves is filled with a portion of the first electrode, and the content of the first ion conductor in the portion of the first electrode with which the grooves are filled is higher than the content of the first ion conductor in the remaining portion of the first electrode.

[0014] The difference between the content of the first ion conductor in the portion of the first electrode with which the grooves are filled and the content of the first ion conductor in the remaining portion of the first electrode may be 2 to 12% of the content of the first ion conductor in the remaining portion of the first electrode.

[0015] In accordance with another aspect of the present disclosure, there is provided a membrane-electrode assembly manufacturing method including dispersing a first catalyst and a first ion conductor in a first dispersion medium in order to obtain a first catalyst slurry, coating the first catalyst slurry on a first surface of a polymer electrolyte membrane, and drying the first catalyst slurry coated on the first surface in order to form a first electrode, wherein the first dispersion medium includes (i) a first ingredient capable of partially melting the polymer electrolyte membrane at the first surface thereof or causing deformation of the first surface to form a plurality of grooves on the first surface and (ii) a second ingredient different from the first ingredient, the first ingredient is alcohol, acetic acid, propionic acid, dimethylacetamide, or a mixture of two or more thereof, the alcohol is methanol, ethanol, propanol, ethoxyethanol, butanol, or a mixture of

two or more thereof, the second ingredient is water, N-methyl pyrrolidone (NMP), dimethyl sulfoxide (DMSO), tetrahydrofuran (THF), or a mixture of two or more thereof, the content of the first dispersion medium in the first catalyst slurry is 83 to 98 wt. %, the content of the first ingredient in the first dispersion medium is 55 to 80 wt. %, and when the first electrode is formed through the drying step, at least some of the grooves are filled with the first catalyst, the first ion conductor, or a mixture thereof.

[0016] The first catalyst slurry may be coated on the first surface to a coating thickness of 10 to 200 μm .

[0017] The drying step may be performed at a temperature of 50 to 150° C. for 10 to 300 seconds.

[0018] (i) The content of the first dispersion medium in the first catalyst slurry, (ii) the content of the first ingredient in the first dispersion medium, (iii) the coating thickness of the first catalyst slurry, (iv) the temperature of the drying step, and (v) the time of the drying step may be set such that each of the grooves has a depth of 5 μm or less and a width of 10 μm or less.

[0019] The dispersion step may be performed using at least one selected from the group consisting of an ultrasonic homogenizer, a ball mill, a roll mill, a resonant acoustic mixer, a high-pressure homogenizer, a planetary mixer, and a homogeneous mixer.

[0020] The polymer electrolyte membrane may include a fluorine-based ion conductor.

[0021] The drying step may be performed by hot-air drying, infrared drying, or hot-plate drying.

[0022] The method may further include coating a second catalyst slurry on a second surface of the polymer electrolyte membrane opposite the first surface after forming the first electrode and drying the second catalyst slurry coated on the second surface in order to form a second electrode.

[0023] The step of coating the first catalyst slurry on the first surface may be performed while a protective film is attached to the second surface of the polymer electrolyte membrane.

[0024] The method may further include removing the protective film from the second surface before coating the second catalyst slurry on the second surface.

[0025] The method may further include attaching a first protective sheet to the first surface having the first electrode formed thereon before removing the protective film from the second surface.

[0026] The method may further include attaching a second protective sheet to the second surface having the second electrode formed thereon.

[0027] The method may further include attaching a first masking film having a first window to the first surface before coating the first catalyst slurry on the first surface, removing the first masking film after forming the first electrode, attaching a second masking film having a second window to the second surface before coating the second catalyst slurry on the second surface, and removing the second masking film after forming the second electrode, wherein the step of coating the first catalyst slurry on the first surface may be performed by coating the first catalyst slurry on the portion of the first surface exposed through the first window, and the step of coating the second catalyst slurry on the second surface may be performed by coating the second catalyst slurry on the portion of the second surface exposed through the second window.

[0028] The general description of the present disclosure given above is provided merely to illustrate or describe the present disclosure, and does not limit the scope of rights of the present disclosure.

Advantageous Effects

[0029] According to the present disclosure, grooves each having a predetermined size randomly arranged on the surface of a polymer electrolyte membrane are filled with a portion of an electrode formed on the surface, whereby the adhesive strength between the polymer electrolyte membrane and the electrode may be higher than in a conventional art, and therefore it is possible to provide a membrane-electrode assembly having higher durability of the interface between the polymer electrolyte membrane and the electrode than in the conventional art.

[0030] Conventional physical or physicochemical methods of increasing the adhesive strength between a polymer electrolyte membrane and an electrode in order to improve durability of the

interface therebetween deteriorate simplicity in process and productivity of a membrane-electrode assembly, whereas a membrane-electrode assembly manufacturing method according to the present disclosure is capable of, in directly coating a catalyst slurry on a polymer electrolyte membrane to form an electrode, increasing the adhesive strength between the polymer electrolyte membrane and the electrode and durability of the interface therebetween without a separate additional process. In the method according to the present disclosure, therefore, it is possible to manufacture a membrane-electrode assembly having excellent durability in a relatively simple way with high productivity.

Description

DESCRIPTION OF DRAWINGS

[0031] The accompanying drawings, which are included to assist in understanding of the present disclosure and are incorporated in and constitute a part of the present specification, illustrate embodiments of the present disclosure and serve to explain the principle of the present disclosure together with the detailed description of the present disclosure.

[0032] FIGS. **1(a)** to **1(c)** schematically illustrate a process in which an electrode is formed on a polymer electrolyte membrane according to a method of the present disclosure;

[0033] FIG. **2** schematically shows a membrane-electrode assembly manufacturing method according to an embodiment of the present disclosure;

[0034] FIGS. **3(a)** and **3(b)** schematically illustrate a membrane-electrode assembly manufacturing method according to another embodiment of the present disclosure;

[0035] FIG. **4** schematically shows a membrane-electrode assembly manufacturing method according to a further embodiment of the present disclosure;

[0036] FIG. **5** is an optical micrograph showing the surface of a membrane-electrode assembly obtained in Example 1;

[0037] FIGS. **6(a)** and **6(b)** are scanning electron micrographs respectively showing the surface and the section of the membrane-electrode assembly obtained in Example 1;

[0038] FIG. **7** is a graph showing H.sub.2 crossover measured while 20,000 wet/dry cycles were performed on the membrane-electrode assembly obtained in Example 1; and

[0039] FIGS. **8(a)** and **8(b)** are graphs respectively showing voltage retention and H.sub.2 crossover measured while an OCV hold method was performed for 500 hours on the membrane-electrode assembly obtained in Example 1.

BEST MODE

[0040] Hereinafter, embodiments of the present disclosure will be described in detail with reference to the accompanying drawings. However, the following embodiments are illustratively provided merely for clear understanding of the present disclosure and do not limit the scope of the present disclosure.

[0041] FIGS. **1a** to **1c** schematically illustrate a process in which an electrode is formed on a polymer electrolyte membrane according to a method of the present disclosure.

[0042] As shown in FIG. **1a**, a membrane-electrode assembly manufacturing method according to the present disclosure includes a step of coating a first catalyst slurry **210a** on a first surface of a polymer electrolyte membrane **100**.

[0043] According to the present disclosure, a first catalyst **211** and a first ion conductor **212** are dispersed in a first dispersion medium **213** in order to obtain the first catalyst slurry **210a**. A portion **212a** of the first ion conductor **212** is coated on at least a portion of the first catalyst **211**, and the remainder **212b** thereof exists in the form of a free ion conductor that is not coated on the first catalyst **211**.

[0044] The first catalyst **211** may include a support **211a** and a plurality of catalyst metal particles

211b dispersed on the support **211a**.

[0045] The support **211a** may be (i) a carbon-based support, (ii) a porous inorganic oxide support, such as zirconia, alumina, titania, silica, or ceria, or (iii) a zeolite support.

[0046] For example, the carbon-based support may be graphite, super P, carbon fiber, carbon sheet, carbon black, Ketjen black, Denka black, acetylene black, carbon nanotube (CNT), carbon sphere, carbon ribbon, fullerene, active carbon, carbon nanofiber, carbon nanowire, carbon nanoball, carbon nanohorn, carbon nanocage, carbon nanoring, ordered nano-/meso-porous carbon, carbon aerogel, mesoporous carbon, graphene, stabilized carbon, activated carbon, or a combination of two or more thereof.

[0047] The catalyst metal particles **211b** may include platinum or a platinum-based alloy. The platinum-based alloy may be (i) a binary alloy, such as Pt—Co, Pt—Pd, Pt—Mn, Pt—Sn, Pt—Mo, Pt—Cr, Pt—W, Pt—Ir, Pt—Ru, Pt—Ni, or Pt—Fe, (ii) a ternary alloy, such as Pt—Ru—W, Pt—Ru—Ni, Pt—Ru—Mo, Pt—Ru—Ir, Pt—Co—Mn, Pt—Co—Ni, Pt—Co—Fe, Pt—Co—Ir, Pt—Co—S, Pt—Co—P, Pt—Fe—Ir, Pt—Fe—S, Pt—Fe—P, Pt—Au—Co, Pt—Au—Fe, Pt—Au—Ni, Pt—Ni—Ir, or Pt—Cr—Ir, or (iii) a quaternary alloy, such as Pt—Ru—Rh—Ni, Pt—Ru—Sn—W, or Pt—Ru—Ir—Ni. However, the present disclosure is not limited thereto.

[0048] The first ion conductor **212** dispersed in the first dispersion medium **213** together with the first catalyst **211** performs not only a hydrogen ion transfer function in a first electrode **210b** but also the function of a binder that increases the adhesive strength between the polymer electrolyte membrane **100** and the first electrode **210b**.

[0049] The first ion conductor **212** may be a fluorine-based or hydrocarbon-based ion conductor having an ion exchange group. The ion exchange group may be at least one proton exchange group selected from the group consisting of a sulfonic acid group, a carboxyl group, a boronic acid group, a phosphate group, an imide group, a sulfonimide group, a sulfonamide group, and a sulfonic acid fluoride group.

[0050] There are poly (perfluorosulfonic acid) and poly (perfluorocarboxylic acid) as examples of the fluorine-based ion conductor. However, the present disclosure is not limited thereto.

[0051] There are sulfonated polyimide (S-PI), sulfonated polyarylethersulfone (S-PAES), sulfonated polyetheretherketone (SPEEK), sulfonated polybenzimidazole (SPBI), sulfonated polysulfone (S-PSU), sulfonated polystyrene (S-PS), sulfonated polyphosphazene, sulfonated polyquinoxaline, sulfonated polyketone, sulfonated polyphenylene oxide, sulfonated polyether sulfone, sulfonated polyether ketone, sulfonated polyphenylene sulfone, sulfonated polyphenylene sulfide, sulfonated polyphenylene sulfide sulfone, sulfonated polyphenylene sulfide sulfone nitrile, sulfonated polyarylene ether, sulfonated polyarylene ether nitrile, sulfonated polyarylene ether ether nitrile, and sulfonated polyarylene ether sulfone ketone as examples of the hydrocarbon-based ion conductor. However, the present disclosure is not limited thereto.

[0052] The first dispersion medium **213** according to the present disclosure is a solvent that partially and slightly removes the polymer electrolyte membrane **100** from the first surface or causes the first surface to be deformed, e.g. wrinkled, whereby a plurality of grooves may be formed on the first surface. The term “groove” used herein is a concept that encompasses angular-shaped grooves, curved-shaped grooves, or hybrid-shaped grooves caused due to partial removal or surface deformation, such as wrinkles, of the polymer electrolyte membrane **100**.

[0053] For example, the first dispersion medium **213** may include (i) a first ingredient, such as alcohol, acetic acid, propionic acid, dimethylacetamide, or a mixture of two or more thereof, and (ii) a second ingredient different from the first ingredient, such as water, N-methyl pyrrolidone (NMP), dimethyl sulfoxide (DMSO), tetrahydrofuran (THF), or a mixture of two or more thereof. The alcohol may be methanol, ethanol, propanol, ethoxyethanol, butanol, or a mixture of two or more thereof.

[0054] The content of the first dispersion medium **213** in the first catalyst slurry **210a** may be 83 to 98 wt. %. If the content of the first dispersion medium **213** deviates from the above-specified

range, it is difficult for grooves to be formed on the surface of the polymer electrolyte membrane **100**.

[0055] The content of the first ingredient in the first dispersion medium **213** may be 55 to 80 wt. %.

[0056] The first catalyst **211** and the first ion conductor **212** may be dispersed in the first dispersion medium **213** using at least one selected from the group consisting of an ultrasonic homogenizer, a ball mill, a roll mill, a resonant acoustic mixer, a high-pressure homogenizer, a planetary mixer, and a homogeneous mixer.

[0057] The polymer electrolyte membrane **100** includes an ion conductor. Since the above-specified ion conductors that may be used to form the first catalyst slurry **210a** may be used for the polymer electrolyte membrane **100**, a detailed description of the ion conductor for the polymer electrolyte membrane **100** will be omitted. The ion conductor included in the polymer electrolyte membrane **100** may be identical to or different from the first ion conductor **212** of the first catalyst slurry **210a**.

[0058] In order to well form a plurality of grooves G on the first surface of the polymer electrolyte membrane **100** using the first dispersion medium **213** according to the present disclosure (i.e. in order to sufficiently increase roughness of the first surface), it may be preferable for the polymer electrolyte membrane **100** to include a fluorine-based ion conductor, rather than a hydrocarbon-based ion conductor. However, some (e.g. dimethylacetamide) of the above-specified examples of the first ingredient of the first dispersion medium **213** may increase surface roughness of a hydrocarbon-based polymer electrolyte membrane just as sufficiently as a fluorine-based polymer electrolyte membrane.

[0059] The polymer electrolyte membrane **100** may be (i) a single membrane substantially made of only an ion conductor or (ii) a reinforced composite membrane configured such that pores of a porous support are filled with the ion conductor.

[0060] The reinforced composite membrane may include two pure layers substantially made of only an ion conductor and a coexistence layer of the porous support and the ion conductor existing therebetween. In a reinforced composite membrane type polymer electrolyte membrane **100**, a ratio of the apparent volume of the porous support (i.e. the volume of the coexistence layer) to the entire volume of the polymer electrolyte membrane **100** may be 5 to 90%.

[0061] The first dispersion medium **213** according to the present disclosure includes 55 to 80 wt. % of the first ingredient that may partially and slightly remove the ion conductor of the polymer electrolyte membrane **100** or may cause surface deformation, such as wrinkles, of the polymer electrolyte membrane (i.e. alcohol, acetic acid, propionic acid, dimethylacetamide, or a mixture of two or more thereof). As illustrated in FIG. **1b**, therefore, a plurality of grooves G may be irregularly formed on the first surface of the polymer electrolyte membrane **100**, whereby surface roughness of the polymer electrolyte membrane may be increased.

[0062] As previously described, alcohol may be methanol, ethanol, propanol, ethoxyethanol, butanol, or a mixture of two or more thereof.

[0063] The content of the first ingredient in the first dispersion medium **213** may be 55 to 80 wt. %.

[0064] If the content of the first ingredient in the first dispersion medium **213** is less than 55 wt. %, it is difficult for grooves to be formed on the surface of the polymer electrolyte membrane **100**.

Consequently, surface roughness of the polymer electrolyte membrane **100** may not be sufficiently increased. As a result, the adhesive strength between the polymer electrolyte membrane **100** and the first electrode **210b** and durability of the interface therebetween may not be sufficiently increased.

[0065] If the content of the first ingredient in the first dispersion medium **213** is greater than 80 wt. %, on the other hand, the ion conductor of the polymer electrolyte membrane **100** is excessively removed or surface deformation, such as wrinkles, of the polymer electrolyte membrane is excessively caused, whereby excessively large grooves (i.e. grooves each having a depth of greater than 5 μm and a width of greater than 10 μm) are formed on the surface of the polymer electrolyte membrane **100**. As a result, durability of the polymer electrolyte membrane **100** may be

unintentionally lowered or interfacial bonding defects may occur.

[0066] The second ingredient, which is the other ingredient of the first dispersion medium **213** according to the present disclosure, may be an arbitrary ingredient commonly used to manufacture a catalyst slurry for membrane-electrode assemblies, e.g. (i) a hydrophilic solvent including water (H.sub.2O) and/or (ii) an organic solvent selected from the group consisting of N-methyl pyrrolidone (NMP), dimethyl sulfoxide (DMSO), tetrahydrofuran (THF), and a mixture of two or more thereof.

[0067] In an embodiment of the present disclosure, the first catalyst slurry **210a** may be coated on the first surface of the polymer electrolyte membrane **100** to a coating thickness of 10 to 200 μm , more specifically 20 to 200 μm .

[0068] If the coating thickness of the first catalyst slurry **210a** is less than 10 μm , surface roughness of the polymer electrolyte membrane **100** and the electrode loading amount are not sufficiently increased. As a result, the adhesive strength between the polymer electrolyte membrane **100** and the first electrode **210b** and durability of the interface therebetween are not sufficiently increased. If the coating thickness of the first catalyst slurry **210a** is greater than 200 μm , on the other hand, the first dispersion medium **213** of the first catalyst slurry **210a** is not completely removed in a subsequent drying process, whereby not only electrode formation defects are caused but also a subsequent process is adversely affected. In addition, the ion conductor of the polymer electrolyte membrane **100** is excessively removed by the first dispersion medium **213** or surface deformation, such as wrinkles, of the polymer electrolyte membrane is excessively caused (or excessively large grooves are formed), whereby durability of the polymer electrolyte membrane **100** may be unintentionally lowered or electrode formation defects may be caused.

[0069] In the present disclosure, a method of coating the first catalyst slurry **210a** on the first surface of the polymer electrolyte membrane **100** is not particularly restricted as long as it is possible to control the coating thickness of the first catalyst slurry **210a** within the above-specified range. For example, a coating method, such as slot-die coating, comma coating, or spray coating, may be used.

[0070] Subsequently, the first catalyst slurry **210a** according to the present disclosure coated on the first surface of the polymer electrolyte membrane **100** is dried to form a first electrode **210b**. The drying step may be performed by hot-air drying, infrared drying, or hot-plate drying.

[0071] When the first electrode **210b** is formed through the drying step, as illustrated in FIG. **1c**, at least some of the grooves **G** are filled with the first catalyst **211**, the first ion conductor **212**, or a mixture thereof.

[0072] As a result, according to the present disclosure, the contact area between the first electrode **210b** and the polymer electrolyte membrane **100** is increased. That is, the first catalyst slurry **210a** is directly coated on the polymer electrolyte membrane **100** to form the first electrode **210b**, and it is possible to increase the adhesive strength between the polymer electrolyte membrane **100** and the first electrode **210b** and durability of the interface therebetween without performing a separate additional process. According to the present disclosure, therefore, both durability and productivity of the membrane-electrode assembly may be improved.

[0073] In addition, according to the present disclosure, since a plurality of grooves **G** is formed on the first surface of the polymer electrolyte membrane **100** when the first electrode **210b** is formed using the first catalyst slurry **210a**, the portions of the first electrode **210b** with which the grooves **G** are filled and the remaining portion thereof are different from each other in terms of the content of the first ion conductor **212**. Specifically, the content of the first ion conductor **212** in the portions of the first electrode **210b** with which the grooves **G** are filled is higher than the content of the first ion conductor **212** in the remaining portion of the first electrode **210b** (e.g. 2 to 12% higher than the content of the first ion conductor **212** in the remaining portion).

[0074] In an embodiment of the present disclosure, the drying step of removing the first dispersion medium **213** from the first catalyst slurry **210a** may be performed at a temperature of 50 to 150° C.,

more specifically 50 to 130° C., for 10 to 300 seconds, more specifically 10 to 200 seconds. [0075] If the drying step is performed at a temperature lower than 50° C., the first dispersion medium **213** is not completely removed, whereby electrode formation defects are caused and a subsequent process is adversely affected. In addition, the residual first dispersion medium **213** excessively deeply penetrates into the polymer electrolyte membrane **100**, thus excessively removing the ion conductor of the polymer electrolyte membrane **100** or causing excessive surface deformation, such as wrinkles, of the polymer electrolyte membrane (or forming excessively large grooves), whereby durability of the polymer electrolyte membrane **100** may be lowered or electrode formation defects may be caused. If the drying step is performed at a temperature higher than 150° C., on the other hand, the first dispersion medium **213** is rapidly evaporated, whereby partial removal of the ion conductor from the polymer electrolyte membrane **100** or surface deformation, such as wrinkles, of the polymer electrolyte membrane due to the first dispersion medium **213** is not sufficiently achieved. Consequently, surface roughness of the polymer electrolyte membrane **100** may not be sufficiently increased. As a result, the adhesive strength between the polymer electrolyte membrane **100** and the first electrode **210b** and durability of the interface therebetween may not be sufficiently increased. Furthermore, a drying temperature higher than 100° C. may cause deformation and/or denaturation of the polymer electrolyte membrane **100**, and may cause deterioration in performance and durability of a membrane-electrode assembly and a fuel cell, which are final products.

[0076] If the drying step is performed only for a time less than 10 seconds, some of the first dispersion medium **213** may not be evaporated but may remain, whereby electrode formation defects may be caused and a subsequent process may be adversely affected. In addition, the ion conductor of the polymer electrolyte membrane **100** may be excessively removed or surface deformation, such as wrinkles, of the polymer electrolyte membrane may be excessively caused due to the residual first dispersion medium **213**, whereby durability of the polymer electrolyte membrane **100** may be greatly lowered or electrode formation defects may be caused. If the drying step is performed for a time greater than 300 seconds, on the other hand, not only may ionic conductivity of the polymer electrolyte membrane **100** be lowered but also productivity of the membrane-electrode assembly may be lowered due to deformation and/or denaturation of the polymer electrolyte membrane.

[0077] According to the present disclosure, in order to increase surface roughness of the polymer electrolyte membrane **100** without deterioration in durability and performance thereof, it is preferable for only the first surface of the polymer electrolyte membrane **100** or only the vicinity thereof to be affected by the first dispersion medium **213**. For this reason, in an embodiment of the present disclosure, (i) the content of the first dispersion medium **213** in the first catalyst slurry **210a**, (ii) the content of the first ingredient in the first dispersion medium **213**, (iii) the coating thickness of the first catalyst slurry **210a**, (iv) the temperature of the drying step, and (v) the time of the drying step may be set such that the first dispersion medium **213** cannot deform 70% or more of the thickness of the polymer electrolyte membrane **100** through the first surface thereof.

[0078] Alternatively or additionally, in order to increase surface roughness of the polymer electrolyte membrane **100** without deterioration in durability and performance thereof, a plurality of grooves G irregularly formed on the first surface of the polymer electrolyte membrane **100** may each have a depth D of 5 μm or less, preferably 0.05 to 5 μm, more preferably 0.1 to 4.5 μm, and a width W of 10 μm or less, preferably 0.5 to 10 μm, more preferably 1 to 9 μm. (i) The content of the first dispersion medium **213** in the first catalyst slurry **210a**, (ii) the content of the first ingredient in the first dispersion medium **213**, (iii) the coating thickness of the first catalyst slurry **210a**, (iv) the temperature of the drying step, and (v) the time of the drying step may be set such that each of the grooves G has a depth D and a width within the above-specified ranges.

[0079] A membrane-electrode assembly according to the present disclosure manufactured as described above includes a polymer electrolyte membrane **100** and a first electrode **210b** on a first

surface of the polymer electrolyte membrane **100**, wherein the first electrode **210b** includes a first catalyst **211** and a first ion conductor **212**, a plurality of grooves G is randomly formed on the first surface, and each of the grooves G has a depth D of 5 μm or less and a width W of 10 μm or less. [0080] The depth D/width W of the grooves G may be obtained by measuring the depth D/width W of each groove G through observation of a sectional SEM photograph of a sample (2 cm $\times$ 2 cm) and calculating the arithmetic mean of the measured values.

[0081] In addition, according to the present disclosure, the content of the first ion conductor **212** in the portions of the first electrode **210b** with which the grooves G are filled is higher than the content of the first ion conductor **212** in the remaining portion of the first electrode **210b** (e.g. 2 to 12% higher than the content of the first ion conductor **212** in the remaining portion).

[0082] Since the first ion conductor **212** naturally moves downwards during the process of drying the first catalyst slurry **210a** coated on the polymer electrolyte membrane **100**, a relatively high content of the first ion conductor **212** exists in the grooves G located lower than the normal surface of the polymer electrolyte membrane **100** (i.e. the surface having no grooves formed thereon). As a result, the adhesive strength between the polymer electrolyte membrane **100** and the first electrode **210b** and durability of the interface therebetween may be increased.

[0083] The portion-specific content of the ion conductor in the first electrode **210b** may be calculated as follows.

[0084] First, the content of the ion conductor in each of arbitrary five points of a sample electrode (2 cm $\times$ 2 cm) is measured using a thermogravimetric analysis (TGA) method, and the arithmetic mean of the measured values is calculated to obtain the content of the first ion conductor **212** in the remaining portion of the first electrode **210b** (i.e. the portion outside the grooves).

[0085] Subsequently, the remaining portion of the first electrode **210b** is completely removed using a surface and interfacial cutting analysis system (SAICAS), whereby the portions of the first electrode **210b** with which the grooves G are filled remain. The content of the ion conductor in each of the portions of the first electrode **210b** with which the grooves G are filled is measured using the TGA method, and the arithmetic mean of the measured values is calculated to obtain the content of the first ion conductor **212** in the portions of the first electrode **210b** with which the grooves G are filled. According to the present disclosure, the grooves G each having a predetermined size randomly arranged on the first surface of the polymer electrolyte membrane **100** are filled with a portion of the first electrode **210b** formed on the first surface, whereby the adhesive strength between the polymer electrolyte membrane **100** and the first electrode **210b** may be higher than in a conventional art, and therefore it is possible to provide a membrane-electrode assembly having higher durability of the interface between the polymer electrolyte membrane **100** and the first electrode **210b** than in the conventional art.

[0086] A second electrode **220b** may be formed on a second surface of the polymer electrolyte membrane **100** using substantially the same method as the method of forming the first electrode **210b**.

[0087] For example, the membrane-electrode assembly manufacturing method according to the present disclosure may further include a step of coating a second catalyst slurry **220a** on a second surface of the polymer electrolyte membrane **100** opposite the first surface after forming the first electrode **210b** and a step of drying the second catalyst slurry **220a** coated on the second surface in order to form a second electrode **220b**.

[0088] The second catalyst slurry **220a** may be obtained by dispersing a second catalyst and a second ion conductor in a second dispersion medium. The above-specified materials for the first catalyst **211** may be used for the second catalyst, the above-specified materials for the first ion conductor **212** may be used for the second ion conductor, and the above-specified compositions for the first dispersion medium **213** may be used for the second dispersion medium.

[0089] Hereinafter, a membrane-electrode assembly manufacturing method according to an embodiment of the present disclosure will be described with reference to FIG. 2.

[0090] As illustrated in FIG. 2, a membrane-electrode assembly according to the present disclosure may be manufactured through batch processes.

[0091] Specifically, a polymer electrolyte membrane **100** having a protective film **10** attached to a second surface thereof is prepared. The protective film **10** is configured to prevent folding or bending of the polymer electrolyte membrane **100** and to perform easy handling of the polymer electrolyte membrane **100** during a process. The material for the protective film **10** is not restricted as long as the material has mechanical properties capable of achieving the above object.

[0092] Subsequently, a first catalyst slurry **210a** according to the present disclosure is coated on a first surface of the polymer electrolyte membrane **100** so as to have a predetermined shape and size and is then dried to form a first electrode **210b**. For example, the first catalyst slurry **210a** may be coated using a slot die. Optionally, the first catalyst slurry **210a** may be coated while a first masking film (not shown) having a first window of a predetermined shape and size is attached to the first surface such that only the portion of the polymer electrolyte membrane exposed through the first window is coated with the first catalyst slurry **210a**.

[0093] Subsequently, the protective film **10** is removed from the second surface of the polymer electrolyte membrane **100**, and a second catalyst slurry **220a** is coated on the second surface so as to have a predetermined shape and size and is then dried to form a second electrode (not shown in FIG. 2). In an embodiment of the present disclosure, the second catalyst slurry **220a** is identical to the first catalyst slurry **210a**. However, the first and second catalyst slurries **210a** and **220a** may be different from each other. The second catalyst slurry **220a** may also be coated on the second surface so as to have a predetermined shape and size using a slot die or may also be coated on the second surface so as to have a predetermined shape and size using a second masking film (not shown) having a second window.

[0094] The first and second masking films are finally removed after the electrodes are formed.

[0095] Hereinafter, a membrane-electrode assembly manufacturing method according to another embodiment of the present disclosure will be described with reference to FIG. 3.

[0096] As illustrated in FIG. 3, first and second electrodes **210b** and **220b** may be separately manufactured through a roll-to-roll process.

[0097] As shown in FIG. 3(a), a polymer electrolyte membrane **100** having a protective film **10** attached to a second surface thereof is supplied from a PEM unwinder **1100**.

[0098] A first coater **1210** coats a first catalyst slurry **210a** according to the present disclosure on a first surface of the polymer electrolyte membrane **100** supplied from the PEM unwinder **1100** so as to have a predetermined shape and size. As previously described, the first dispersion medium **213** according to the present disclosure irregularly (i.e. randomly) forms a plurality of grooves **G** on the first surface of the polymer electrolyte membrane **100** to increase surface roughness thereof.

[0099] As the polymer electrolyte membrane **100** having the first catalyst slurry **210a** coated thereon passes through a first drying means **1310**, a first dispersion medium **213** in the first catalyst slurry **210a** is removed, and a first electrode **210b** is formed. As previously described, when the first electrode **210b** is formed through the drying step, at least some of the grooves **G** are filled with the first catalyst **211**, the first ion conductor **212**, or a mixture thereof, whereby the contact area between the first electrode **210b** and the polymer electrolyte membrane **100** is increased.

Consequently, the adhesive strength between the polymer electrolyte membrane **100** and the first electrode **210b** and durability of the interface therebetween are increased.

[0100] The polymer electrolyte membrane **100** is wound around a first winder **1510** together with first electrodes **210b** formed on the first surface thereof at predetermined intervals and the protective film **10** attached to the second surface thereof. Optionally, as shown in FIG. 3(a), a first protective sheet **21** supplied from a first unwinder **1410** may be wound around the first winder **1510** together with the polymer electrolyte membrane **100** so as to be attached to the first surface having the first electrodes **210b** formed thereon. The first protective sheet **21**, which is a sheet configured to protect the first electrodes **210b**, may be paper or a polymer film.

[0101] Subsequently, as shown in FIG. 3(b), the polymer electrolyte membrane **100** wound around the first winder **1510**, the first electrodes **210b** formed on the first surface thereof at predetermined intervals, and the first protective sheet **21** configured to protect the first electrodes **210b** are unwound. At this time, the protective film **10** attached to the second surface of the polymer electrolyte membrane **100** is removed from the second surface thereof by a protective film winder **1600**.

[0102] A second coater **1220** coats a second catalyst slurry **220a** according to the present disclosure on the second surface of the polymer electrolyte membrane **100** supplied from the first winder **1510** so as to have a predetermined shape and size. A dispersion medium in the second catalyst slurry **220a** also irregularly forms a plurality of grooves G on the second surface of the polymer electrolyte membrane **100** to increase surface roughness thereof.

[0103] As the polymer electrolyte membrane **100** having the second catalyst slurry **220a** coated thereon passes through a second drying means **1320**, the dispersion medium in the second catalyst slurry **220a** is removed, and a second electrode **220b** is formed. As previously described, when the second electrode **220b** is formed through the drying step, at least some of the grooves are filled with a catalyst, an ion conductor, or a mixture thereof, whereby contact area between the second electrode **220b** and the polymer electrolyte membrane **100** is increased. Consequently, the adhesive strength between the polymer electrolyte membrane **100** and the second electrode **220b** and durability of the interface therebetween are increased.

[0104] The polymer electrolyte membrane **100** is wound around an MEA winder **1700** together with first electrodes **210b** formed on the first surface thereof at predetermined intervals, second electrodes **220b** formed on the second surface thereof at predetermined intervals, and the first protective sheet **21** configured to protect the first electrodes **210b**. At this time, as shown in FIG. 3(b), a second protective sheet **22** supplied from a second unwinder **1420** may be wound around the MEA winder **1700** together with the polymer electrolyte membrane **100** so as to be attached to the second surface having the second electrodes **220b** formed thereon. The second protective sheet **22**, which is a sheet configured to protect the second electrodes **220b**, may be paper or a polymer film.

[0105] In an alternative embodiment of the present disclosure, the first protective sheet **21** may be temporarily provided between the first electrodes **210b** and equipment only during formation of the second electrodes **220b** in order to protect the first electrodes **210b** and the equipment (i.e. the first protective sheet may not be wound around the MEA winder **1700**).

[0106] A membrane-electrode assembly manufacturing method according to a further embodiment of the present disclosure will be described with reference to FIG. 4.

[0107] In the method illustrated in FIG. 3, first and second electrodes **210b** and **220b** are manufactured through separate roll-to-roll processes, whereas first and second electrodes **210b** and **220b** are manufactured through a single roll-to-roll process in the method illustrated in FIG. 4.

[0108] As shown in FIG. 4, a polymer electrolyte membrane **100** having a protective film **10** attached to a second surface thereof is supplied from a PEM unwinder **1100**.

[0109] A first coater **1210** coats a first catalyst slurry **210a** according to the present disclosure on a first surface of the polymer electrolyte membrane **100** supplied from the PEM unwinder **1100** so as to have a predetermined shape and size. As previously described, the first dispersion medium **213** according to the present disclosure irregularly forms a plurality of grooves G on the first surface of the polymer electrolyte membrane **100** to increase surface roughness thereof.

[0110] As the polymer electrolyte membrane **100** having the first catalyst slurry **210a** coated thereon passes through a first drying means **1310**, a first dispersion medium **213** in the first catalyst slurry **210a** is removed, and a first electrode **210b** is formed. As previously described, when the first electrode **210b** is formed through the drying step, at least some of the grooves G are filled with the first catalyst **211**, the first ion conductor **212**, or a mixture thereof, whereby the contact area between the first electrode **210b** and the polymer electrolyte membrane **100** is increased.

Consequently, the adhesive strength between the polymer electrolyte membrane **100** and the first

electrode **210b** and durability of the interface therebetween are increased.

[0111] Subsequently, the polymer electrolyte membrane **100** passes between first and second press rolls **1810** and **1820** together with first electrodes **210b** formed on the first surface thereof at predetermined intervals and the protective film **10** attached to the second surface thereof. At this time, as shown in FIG. 4, a first protective sheet **21** supplied from a first unwinder **1410** also passes between first and second press rolls **1810** and **1820**, whereby the first protective sheet is attached to the first surface of the polymer electrolyte membrane **100** having the first electrodes **210b** formed thereon. As previously described, the first protective sheet **21**, which is a sheet configured to protect the first electrodes **210b**, may be paper or a polymer film.

[0112] Subsequently, as shown in FIG. 4, the protective film **10** attached to the second surface of the polymer electrolyte membrane **100** is removed from the second surface thereof by a protective film winder **1600**.

[0113] A second coater **1220** coats a second catalyst slurry **220a** according to the present disclosure on the second surface of the polymer electrolyte membrane **100** supplied from the first winder **1510** so as to have a predetermined shape and size. A dispersion medium in the second catalyst slurry **220a** also irregularly forms a plurality of grooves **G** on the second surface of the polymer electrolyte membrane **100** to increase surface roughness thereof.

[0114] As the polymer electrolyte membrane **100** having the second catalyst slurry **220a** coated thereon passes through a second drying means **1320**, the dispersion medium in the second catalyst slurry **220a** is removed, and a second electrode **220b** is formed. As previously described, when the second electrode **220b** is formed through the drying step, at least some of the grooves are filled with a catalyst, an ion conductor, or a mixture thereof, whereby contact area between the second electrode **220b** and the polymer electrolyte membrane **100** is increased. Consequently, the adhesive strength between the polymer electrolyte membrane **100** and the second electrode **220b** and durability of the interface therebetween are increased.

[0115] The polymer electrolyte membrane **100** is wound around an MEA winder **1700** together with first electrodes **210b** formed on the first surface thereof at predetermined intervals, second electrodes **220b** formed on the second surface thereof at predetermined intervals, and the first protective sheet **21** configured to protect the first electrodes **210b**. At this time, as shown in FIG. 4, a second protective sheet **22** supplied from a second unwinder **1420** may be wound around the MEA winder **1700** together with the polymer electrolyte membrane **100** so as to be attached to the second surface having the second electrodes **220b** formed thereon. The second protective sheet **22**, which is a sheet configured to protect the second electrodes **220b**, may be paper or a polymer film.

[0116] As previously described, alternatively, the first protective sheet **21** may be temporarily provided between the first electrodes **210b** and equipment only during formation of the second electrodes **220b** in order to protect the first electrodes **210b** and the equipment (i.e. the first protective sheet may not be wound around the MEA winder **1700**).

[0117] Optionally, masking films may be used to form the first and second electrodes **210b** and **220b** at predetermined intervals so as to consistently have a predetermined shape and size.

Specifically, a method according to an embodiment of the present disclosure may further include a step of attaching a first masking film (not shown) having a first window to the first surface before coating the first catalyst slurry **210a** on the first surface, a step of removing the first masking film after forming the first electrode **210b**, a step of attaching a second masking film having a second window to the second surface before coating the second catalyst slurry **220a** on the second surface, and a step of removing the second masking film after forming the second electrode **220b**.

Consequently, the first catalyst slurry **210a** supplied from the first coater **1210** may be coated only on the portion of the first surface exposed through the first window. In the same manner, the second catalyst slurry **220a** supplied from the second coater **1220** may be coated only on the portion of the second surface exposed through the second window.

[0118] Hereinafter, the present disclosure will be described in detail with reference to concrete

examples. However, the following examples are given merely to assist in understanding of the present disclosure, and do not limit the scope of rights of the present disclosure.

Example 1

[0119] 1 g of a commercial catalyst was put in a reaction vessel and was wetted by water.

Subsequently, 0.4 g of ion conductor powder was put in the reaction vessel. Subsequently, 40 g of a dispersion medium containing 60 wt. % of ethanol and 40 wt. % of water was put in the reaction vessel. Subsequently, the catalyst and the ion conductor were dispersed in the dispersion medium using a homogeneous mixer to obtain a catalyst slurry. The content of the dispersion medium in the catalyst slurry was 96.6 wt. %.

[0120] The catalyst slurry was coated on a first surface of a fluorine-based polymer electrolyte membrane having a protective film attached to a second surface thereof to a thickness of 130 μm using a slot die while a masking film was attached thereto, and was then dried at a temperature of 80° C. for 180 seconds to form a first electrode. The polymer electrolyte membrane was a reinforced composite membrane type polymer electrolyte membrane including a porous support. After the masking film was removed, a protective sheet was attached to the first surface having the first electrode formed thereon. Subsequently, the protective film was removed from the second surface, and then a masking film was attached to the second surface. The catalyst slurry was coated on the portion of the second surface exposed through a window of the masking film to a thickness of 100 μm using a slot die, and was then dried at a temperature of 80° C. for 100 seconds to form a second electrode. Subsequently, the protective sheet was removed from the first surface, whereby a membrane-electrode assembly was manufactured.

Example 2

[0121] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the content of the dispersion medium in the catalyst slurry was 83.0 wt. %.

Example 3

[0122] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the content of the dispersion medium in the catalyst slurry was 98.0 wt. %.

Example 4

[0123] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained 55 wt. % of ethanol and 45 wt. % of water.

Example 5

[0124] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained 80 wt. % of ethanol and 20 wt. % of water.

Example 6

[0125] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained methanol instead of ethanol.

Example 7

[0126] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained propanol instead of ethanol.

Example 8

[0127] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained ethoxyethanol instead of ethanol.

Example 9

[0128] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained butanol instead of ethanol.

Example 10

[0129] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained NMP instead of water.

Example 11

[0130] A membrane-electrode assembly was manufactured using the same method as in Example 1

except that the dispersion medium contained THF instead of water.

Comparative Example 1

[0131] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained 20 wt. % of ethylene glycol and 80 wt. % of water.

Comparative Example 2

[0132] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the content of the dispersion medium in the catalyst slurry was 80.0 wt. %.

Comparative Example 3

[0133] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the content of the dispersion medium in the catalyst slurry was 98.2 wt. %.

Comparative Example 4

[0134] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained 50 wt. % of ethanol and 50 wt. % of water.

Comparative Example 5

[0135] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained 90 wt. % of ethanol and 10 wt. % of water.

Comparative Example 6

[0136] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained 50 wt. % of ethoxyethanol and 50 wt. % of water.

Comparative Example 7

[0137] A membrane-electrode assembly was manufactured using the same method as in Example 1 except that the dispersion medium contained 50 wt. % of isopropyl alcohol and 50 wt. % of water.

[Analysis of Surface and Section of Membrane-Electrode Assembly]

[0138] The surface and the section of the membrane-electrode assembly of Example 1 were observed using an optical microscope and a scanning electron microscope.

[0139] FIG. 5 is an optical micrograph showing the surface of the membrane-electrode assembly obtained in Example 1, and FIGS. 6(a) and 6(b) are scanning electron micrographs (SEM photographs) respectively showing the surface and the section of the membrane-electrode assembly obtained in Example 1.

[0140] It can be seen from the surface photographs of FIGS. 5 and 6(a) that, for the membrane-electrode assembly of Example 1, the electrode had a smooth surface without cracks during formation of the electrode, unlike most other methods in which even the surface of the electrode was cracked, even though the electrode was formed simultaneously with an increase in surface roughness of the polymer electrolyte membrane.

[0141] Also, it can be seen from a sectional SEM photograph of FIG. 6(b) that grooves each having a depth of 5 μm or less and a width of 10 μm or less (indicated by circles) were formed on the surface of the polymer electrolyte membrane and that the grooves were filled with an electrode material. That is, it can be seen that contact area between the electrode and the polymer electrolyte membrane was increased. It is rationally expected that the adhesive strength therebetween and durability of the interface therebetween would be improved due to such an increase in contact area.

[0142] In the same manner, it was checked from sectional SEM photographs of Examples 2 to 11 and Comparative Examples 1 to 7 whether grooves each having a depth of 5 μm or less and a width of 10 μm or less were formed on the surface of the polymer electrolyte membrane (the first surface having the first electrode formed thereon). The results are shown in Table 1 below.

TABLE-US-00001 TABLE 1 Dispersion medium Content First ingredient Second ingredient											
Grooves each in		Content in	Content in	having depth of	catalyst dispersion	dispersion	5 μm or less				
slurry medium		medium and	width of (wt. %)	Material (wt. %)	Material (wt. %)	Material (wt. %)	10 μm				
96.6	Ethanol	60	Water	40	Yes	Example 2	83.0	Ethanol	60	Water	40
Yes	Example 3	98.0	Ethanol	60	Water	40	Yes	Example 4	96.6	Ethanol	55
Yes	Example 5	96.6	Ethanol	80	Water	20	Yes	Example 6	96.6	Methanol	60
Yes	Example 7	96.6	Propanol	60	Water	40	Yes	Example 8	96.6	Ethanol	60
Yes	Example 9	96.6	Ethanol	60	Water	40	Yes	Example 10	96.6	Ethanol	60
Yes	Example 11	96.6	Ethanol	60	Water	40	Yes	Comparative Example 1	20.0	Ethylene glycol	80
Yes	Comparative Example 2	80.0	Ethylene glycol	80	Water	20	Yes	Comparative Example 3	98.2	Ethylene glycol	80
Yes	Comparative Example 4	50.0	Ethanol	50	Water	50	Yes	Comparative Example 5	90.0	Ethanol	10
Yes	Comparative Example 6	50.0	Ethoxyethanol	50	Water	50	Yes	Comparative Example 7	50.0	Isopropyl alcohol	50
Yes	Example 1	96.6	Ethanol	60	Water	40	Yes	Example 2	83.0	Ethanol	60
Yes	Example 3	98.0	Ethanol	60	Water	40	Yes	Example 4	96.6	Ethanol	55
Yes	Example 5	96.6	Ethanol	80	Water	20	Yes	Example 6	96.6	Methanol	60
Yes	Example 7	96.6	Propanol	60	Water	40	Yes	Example 8	96.6	Ethanol	60
Yes	Example 9	96.6	Ethanol	60	Water	40	Yes	Example 10	96.6	Ethanol	60
Yes	Example 11	96.6	Ethanol	60	Water	40	Yes	Comparative Example 1	20.0	Ethylene glycol	80
Yes	Comparative Example 2	80.0	Ethylene glycol	80	Water	20	Yes	Comparative Example 3	98.2	Ethylene glycol	80
Yes	Comparative Example 4	50.0	Ethanol	50	Water	50	Yes	Comparative Example 5	90.0	Ethanol	10
Yes	Comparative Example 6	50.0	Ethoxyethanol	50	Water	50	Yes	Comparative Example 7	50.0	Isopropyl alcohol	50

96.6 Ethoxyethanol 60 Water 40 Yes Example 9 96.6 Butanol 60 Water 40 Yes Example 10 96.6 Ethanol 60 NMP 40 Yes Example 11 96.6 Ethanol 60 THF 40 Yes Comparative 96.6 Ethylene glycol 20 Water 80 No Example 1 Comparative 80.0 Ethanol 60 Water 40 No Example 2 Comparative 98.2 Ethanol 60 Water 40 No Example 3 Comparative 96.6 Ethanol 50 Water 50 No Example 4 Comparative 96.6 Ethanol 90 Water 10 No Example 5 Comparative 96.6 Ethoxyethanol 50 Water 50 No Example 6 Comparative 96.6 Isopropyl 50 Water 50 No Example 7 alcohol

[0143] It can be seen from Table 1 above that grooves each having a depth of 5 μm or less and a width of 10 μm or less were formed on the surface of the polymer electrolyte membrane of each of the membrane-electrode assemblies manufactured according to Examples 1 to 11. In contrast, it can be seen that, when the content of the dispersion medium in the catalyst slurry deviated from the range of the present disclosure (Comparative Examples 2 and 3) and when the content of the first ingredient in the dispersion medium deviated from the range of the present disclosure (Comparative Examples 1 and 4 to 7), no grooves each having a depth of 5 μm or less and a width of 10 μm or less were formed. In particular, for Comparative Example 5, in which the content of the first ingredient in the dispersion medium was 90 wt. %, grooves each having a depth of greater than 5 μm and a width of greater than 10 μm were formed.

[Evaluation of Physical Durability and Chemical Durability of Membrane-Electrode Assembly]

[0144] Physical durability and chemical durability of each of the membrane-electrode assemblies of Example 1 and Comparative Example 1 were evaluated based on a durability evaluation protocol of the United States Department of Energy (DOE). Specifically, in order to evaluate physical durability of the membrane-electrode assembly, 20,000 wet/dry cycles were performed, and then H.sub.2 crossover was measured. The measured values are shown in Table 2 below. FIG. 7 is a graph showing H.sub.2 crossover measured while 20,000 wet/dry cycles were performed on the membrane-electrode assembly obtained in Example 1.

[0145] Also, in order to evaluate chemical durability of the membrane-electrode assembly, an OCV hold method was performed for 500 hours, and then H.sub.2 crossover and voltage loss were measured. The measured values are shown in Table 2 below. FIGS. 8(a) and 8(b) are graphs respectively showing voltage retention and H.sub.2 crossover measured while the OCV hold method was performed for 500 hours on the membrane-electrode assembly obtained in Example 1.

TABLE-US-00002

TABLE 2	Comparative Example 1	Example 1	Before evaluation	After evaluation	Before evaluation	After evaluation
Wet/dry cycle						
H.sub.2 crossover @ (20,000 cycles)	3.6	3.8	3.6	9.6		
0.2 V (mA/cm.sup.2)						
OCV hold						
H.sub.2 crossover @ (500 hours)	3.9	4.1	3.9	10.6		
0.2 V (mA/cm.sup.2)						
Voltage loss (%)	0	7.7	0	14.3		

[0146] It can be seen from Table 2 above and the graph of FIG. 7 that the membrane-electrode assembly of Example 1 satisfied DOE standards (H.sub.2 crossover ≤ 15 mA/cm.sup.2 @ Wet/Dry 20,000 cycles) and exhibited very stable physical durability before/after durability evaluation, compared to the membrane-electrode assembly of Comparative Example 1. Also, it can be seen from Table 2 above and the graph of FIG. 8 that the membrane-electrode assembly of Example 1 satisfied DOE standards (Voltage loss $\leq 20\%$ @ 500 hrs, H.sub.2 crossover ≤ 15 mA/cm.sup.2 @ 500 hrs) and exhibited chemical durability having less voltage loss, compared to the membrane-electrode assembly of Comparative Example 1.

[0147] The membrane-electrode assemblies of Examples 2 to 11, in each of which grooves each having a depth of 5 μm or less and a width of 10 μm or less were formed on the surface of the polymer electrolyte membrane, also exhibited excellent physical and chemical durabilities, similarly to the membrane-electrode assembly of Example 1. In contrast, the membrane-electrode assemblies of Comparative Examples 2 to 7, in each of which no grooves each having a depth of 5 μm or less and a width of 10 μm or less were formed on the surface of the polymer electrolyte membrane, exhibited relatively low physical and chemical durabilities.

[0148] It can be seen from the above results of evaluation that the membrane-electrode assembly manufacturing method according to the present disclosure is capable of improving durability of the

membrane-electrode assembly while not deteriorating durability of the polymer electrolyte membrane.

Claims

1. A membrane-electrode assembly comprising: a polymer electrolyte membrane; and a first electrode on a first surface of the polymer electrolyte membrane, wherein the first electrode comprises a first catalyst and a first ion conductor, a plurality of grooves are randomly formed on the first surface, each of the grooves has a depth of 5 μm or less and a width of 10 μm or less, each of the grooves is filled with a portion of the first electrode, and a content of the first ion conductor in the portion of the first electrode with which the grooves are filled is higher than a content of the first ion conductor in a remaining portion of the first electrode.
 2. The membrane-electrode assembly according to claim 1, wherein a difference between the content of the first ion conductor in the portion of the first electrode with which the grooves are filled and the content of the first ion conductor in the remaining portion of the first electrode is 2 to 12% of the content of the first ion conductor in the remaining portion of the first electrode.
-