

# US Patent & Trademark Office

## Patent Public Search | Text View

---

|                      |                    |
|----------------------|--------------------|
| United States Patent | 12414398           |
| Kind Code            | B2                 |
| Date of Patent       | September 09, 2025 |
| Inventor(s)          | Noh; Hyunpil       |

---

### Image sensor

---

#### Abstract

An image sensor includes a substrate having a plurality of pixel sections. The substrate has first and second surfaces that are opposite to each other. A photoelectric conversion region is in each of the pixel sections. A first isolation pattern is disposed in the substrate and is positioned between the pixel sections. A gate electrode is on the photoelectric conversion region. A lower portion of the gate electrode is inserted into the substrate. An upper portion of the gate electrode protrudes beyond the first surface of the substrate. A floating diffusion region is on the photoelectric conversion region. The floating diffusion region is positioned on one side of the gate electrode. The floating diffusion region includes a doping pad and a first impurity region. The first impurity region surrounds a lower portion of the doping pad. The doping pad is horizontally spaced apart from the first isolation pattern.

---

|                   |                                                     |
|-------------------|-----------------------------------------------------|
| <b>Inventors:</b> | <b>Noh; Hyunpil (Seongnam-si, KR)</b>               |
| <b>Applicant:</b> | <b>SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)</b> |
| <b>Family ID:</b> | <b>85478649</b>                                     |
| <b>Assignee:</b>  | <b>SAMSUNG ELECTRONICS CO., LTD. (Suwon-si, KR)</b> |
| <b>Appl. No.:</b> | <b>17/743765</b>                                    |
| <b>Filed:</b>     | <b>May 13, 2022</b>                                 |

#### Prior Publication Data

|                            |                         |
|----------------------------|-------------------------|
| <b>Document Identifier</b> | <b>Publication Date</b> |
| US 20230083953 A1          | Mar. 16, 2023           |

#### Foreign Application Priority Data

|    |                 |               |
|----|-----------------|---------------|
| KR | 10-2021-0121208 | Sep. 10, 2021 |
|----|-----------------|---------------|

---

Publication Classification

Int. Cl.: H10F39/00 (20250101)

U.S. Cl.:

CPC H10F39/807 (20250101); H10F39/8023 (20250101); H10F39/8053 (20250101); H10F39/8063 (20250101);

Field of Classification Search

USPC: None

References Cited

U.S. PATENT DOCUMENTS

| Patent No.   | Issued Date | Patentee Name | U.S. Cl. | CPC          |
|--------------|-------------|---------------|----------|--------------|
| 9123834      | 12/2014     | Fujii         | N/A      | N/A          |
| 9893123      | 12/2017     | Lee et al.    | N/A      | N/A          |
| 11121163     | 12/2020     | Kim           | N/A      | N/A          |
| 2008/0042170 | 12/2007     | Han           | N/A      | N/A          |
| 2014/0077271 | 12/2013     | Fujii         | 438/59   | H10F 39/8033 |
| 2017/0170239 | 12/2016     | Lee           | N/A      | H10F 39/802  |
| 2020/0381473 | 12/2019     | Kim et al.    | N/A      | N/A          |
| 2020/0403025 | 12/2019     | Kim et al.    | N/A      | N/A          |
| 2021/0136310 | 12/2020     | Uchida        | N/A      | N/A          |

FOREIGN PATENT DOCUMENTS

| Patent No.      | Application Date | Country | CPC |
|-----------------|------------------|---------|-----|
| 2011-155248     | 12/2010          | JP      | N/A |
| 10-0792334      | 12/2007          | KR      | N/A |
| 10-2020-0105197 | 12/2019          | KR      | N/A |

OTHER PUBLICATIONS

Office Action dated Jun. 17, 2025 issued in corresponding Korean Patent Application No. 10-2021-0121208. cited by applicant

Primary Examiner: Jang; Bo B

Attorney, Agent or Firm: Morgan, Lewis & Bockius LLP

Background/Summary

CROSS-REFERENCE TO RELATED APPLICATION

(1) This application claims priority under 35 U.S.C § 119 to Korean Patent Application No. 10-2021-0121208, filed on Sep. 10, 2021 in the Korean Intellectual Property Office, the disclosure of

which is incorporated by reference in its entirety herein.

## 1. TECHNICAL FIELD

(2) The present disclosure relates to an image sensor, and more particularly, to a complementary metal oxide semiconductor (CMOS) image sensor.

## 2. DISCUSSION OF RELATED ART

(3) An image sensor is a semiconductor device that transforms optical images into electrical signals. Recent advances in the computer and communication industries have led to strong demands for high performances image sensors in various types of consumer electronic devices, such as digital cameras, camcorders, PCSs (Personal Communication Systems), game devices, security cameras, medical micro cameras, etc. An image sensor can be classified into a charge coupled device (CCD) type and a complementary metal oxide semiconductor (CMOS) type. A CMOS type image sensor (CIS) has a plurality of two-dimensionally arranged pixels. Each of the pixels includes a photodiode (PD). The photodiode transforms an incident light into an electrical signal. The plurality of pixels are defined by a deep isolation pattern disposed therebetween.

## SUMMARY

(4) Some embodiments of the present inventive concept relate to an image sensor that prevents gate induced drain leakage (GIDL) phenomena and a method of fabricating the same.

(5) According to an embodiment of the present inventive concept, an image sensor includes a substrate having a plurality of pixel sections. The substrate has first and second surfaces that are opposite to each other. A photoelectric conversion region is in each of the pixel sections. A first isolation pattern is disposed in the substrate and is positioned between the pixel sections. A gate electrode is on the photoelectric conversion region. A lower portion of the gate electrode is inserted into the substrate. An upper portion of the gate electrode protrudes beyond the first surface of the substrate. A floating diffusion region is on the photoelectric conversion region. The floating diffusion region is positioned on one side of the gate electrode. The floating diffusion region includes a doping pad and a first impurity region. The first impurity region surrounds a lower portion of the doping pad. The doping pad is horizontally spaced apart from the first isolation pattern.

(6) According to an embodiment of the present inventive concept, an image sensor includes a substrate having a first surface and a second surface that are opposite to each other. A first isolation pattern is disposed in the substrate. The first isolation pattern defines a pixel section. A photoelectric conversion region is in the pixel section. A gate electrode is on the photoelectric conversion region. A floating diffusion region is on the photoelectric conversion region. The floating diffusion region is positioned on one side of the gate electrode. The floating diffusion region includes an impurity region and a doping pad disposed on the impurity region. The doping pad is horizontally spaced apart from the first isolation pattern. A bottom surface of the doping pad is positioned at a level that is lower than a level of the first surface of the substrate.

(7) According to an embodiment of the present inventive concept, an image sensor includes a substrate that has a first surface and a second surface that are opposite to each other. The substrate includes a first trench that is recessed from the first surface of the substrate. A first isolation pattern is in the substrate. The first isolation pattern defines a pixel section. A second isolation pattern is in the first trench. A photoelectric conversion region is in the pixel section. A gate electrode is on the second isolation pattern. A floating diffusion region is on the photoelectric conversion region. The floating diffusion region is positioned on one side of the gate electrode. The floating diffusion region includes an impurity region and a doping pad on the impurity region. A contact plug is on the first surface of the substrate and is electrically connected to the doping pad. A microlens is on the second surface of the substrate. A plurality of color filters is between the substrate and the microlens. A portion of a sidewall of the doping pad directly contacts the second isolation pattern.

---

## Description

### BRIEF DESCRIPTION OF THE DRAWINGS

- (1) FIG. 1 illustrates a simplified block diagram showing an image sensor according to an embodiment of the present inventive concept.
- (2) FIG. 2 illustrates a circuit diagram showing an active pixel sensor array of an image sensor according to an embodiment of the present inventive concept.
- (3) FIG. 3 illustrates a plan view showing an image sensor according to an embodiment of the present inventive concept.
- (4) FIG. 4 illustrates a cross-sectional view of an image sensor taken along line I-I' of FIG. 3, according to an embodiment of the present inventive concept.
- (5) FIG. 5 illustrates an enlarged view of an image sensor taken from section A of FIG. 4 according to an embodiment of the present inventive concept.
- (6) FIG. 6 illustrates a cross-sectional view of an image sensor taken along line I-I' of FIG. 3 according to an embodiment of the present inventive concept.
- (7) FIG. 7 illustrates a cross-sectional view of an image sensor taken along line I-I' of FIG. 3 according to an embodiment of the present inventive concept.
- (8) FIG. 8 illustrates an enlarged view of an image sensor taken from section B of FIG. 7 according to an embodiment of the present inventive concept.
- (9) FIG. 9 illustrates a cross-sectional view of an image sensor taken along line I-I' of FIG. 3 according to an embodiment of the present inventive concept.
- (10) FIGS. 10 to 16 illustrate cross-sectional views taken along line I-I' of FIG. 3, showing a method of fabricating an image sensor according to some embodiments of the present inventive concept.
- (11) FIG. 17 illustrates a cross-sectional view taken along line I-I' of FIG. 3, showing a method of fabricating an image sensor according to an embodiment of the present inventive concept.
- (12) FIGS. 18 and 19 illustrate cross-sectional views taken along line I-I' of FIG. 3, showing a method of fabricating an image sensor according to some embodiments of the present inventive concept.
- (13) FIG. 20 illustrates a plan view showing an image sensor according to an embodiment of the present inventive concept.
- (14) FIG. 21 illustrates a cross-sectional view taken along line II-II' of FIG. 20, showing an image sensor according to an embodiment of the present inventive concept.

### DETAILED DESCRIPTION OF EMBODIMENTS

- (15) Some embodiments of the present inventive concept will now be described in detail with reference to the accompanying drawings to aid in clearly explaining the present inventive concept.
- (16) FIG. 1 illustrates a simplified block diagram showing an image sensor according to an embodiment of the present inventive concept.
- (17) Referring to FIG. 1, an image sensor may include an active pixel sensor array 1, a row decoder 2, a row driver 3, a column decoder 4, a timing generator 5, a correlated double sampler (CDS) 6, an analog-to-digital converter (ADC) 7, and an input/output buffer 8.
- (18) In an embodiment, the active pixel sensor array 1 may include a plurality of two-dimensionally arranged pixels. Each of the two-dimensionally arranged pixels may be configured to convert optical signals into electrical signals. The active pixel sensor array 1 may be driven by a plurality of driving signals, such as a pixel selection signal, a reset signal, and a charge transfer signal, which are provided from the row driver 3. In addition, the correlated double sampler 6 may be provided with the electrical signals which are converted by the active pixel sensor array 1.
- (19) The row driver 3 may provide the active pixel sensor array 1 with several driving signals for driving several pixels in accordance with a decoded result obtained from the row decoder 2. In an

embodiment in which the plurality of pixels are arranged in a matrix shape, the driving signals may be provided for each row.

(20) The timing generator 5 may provide timing and control signals to the row decoder 2 and the column decoder 4.

(21) The correlated double sampler 6 may receive the electrical signals generated from the active pixel sensor array 1, and may hold and sample the received electrical signals. In an embodiment, the correlated double sampler 6 may perform a double sampling operation to sample a specific noise level and a signal level of the electrical signal, and then may output a difference level corresponding to a difference between the noise and signal levels.

(22) The analog-to-digital converter 7 may convert analog signals, which correspond to the difference level received from the correlated double sampler 6, into digital signals and then output the converted digital signals.

(23) The input/output buffer 8 may latch the digital signals and then sequentially output the latched digital signals to an image signal processing unit in response to the decoded result obtained from the column decoder 4.

(24) FIG. 2 illustrates a circuit diagram showing an active pixel sensor array of an image sensor according to some embodiments of the present inventive concept.

(25) Referring to FIGS. 1 and 2, in an embodiment, the active pixel sensor array 1 may include a plurality of pixel sections PX, and the pixel sections PX may be arranged in a matrix shape. Each of the pixel sections PX may include a transfer transistor TX and logic transistors. The logic transistors may include a reset transistor RX, a selection transistor SX, and a drive transistor DX. The transfer transistor TX, the reset transistor RX, and the selection transistor SX may respectively include a transfer gate TRG, a reset gate RG, and a selection gate SG. Each of the pixel sections PX may further include a photoelectric conversion element PD and a floating diffusion region FD.

(26) The photoelectric conversion element PD may create and accumulate photo-charges in proportion to an amount of externally incident light. In an embodiment, the photoelectric conversion element PD may be a photodiode including a p-type impurity region and an n-type impurity region. The transfer transistor TX may transfer charges generated in the photoelectric conversion element PD into the floating diffusion region FD. The floating diffusion region FD may accumulate and store the charges generated and transferred from the photoelectric conversion element PD. The drive transistor DX may be controlled by an amount of photo-charges accumulated in the floating diffusion region FD.

(27) The reset transistor RX may periodically reset the charges accumulated in the floating diffusion region FD. The reset transistor RX may have a drain electrode connected to the floating diffusion region FD and a source electrode connected to a power voltage  $V_{sub,DD}$ . When the reset transistor RX is turned on, the floating diffusion region FD may be supplied with the power voltage  $V_{sub,DD}$  connected to the source electrode of the reset transistor RX. Accordingly, when the reset transistor RX is turned on, the charges accumulated in the floating diffusion region FD may be exhausted and thus the floating diffusion region FD may be reset.

(28) The drive transistor DX may serve as a source follower buffer amplifier. The drive transistor DX may amplify a variation in electrical potential of the floating diffusion region FD and may output the amplified electrical potential to an output line  $V_{sub,OUT}$ .

(29) The selection transistor SX may select each row of the pixel sections P to be readout. When the selection transistor SX is turned on, the power voltage  $V_{sub,DD}$  may be applied to a drain electrode of the drive transistor DX.

(30) FIG. 2 depicts by way of example a unit pixel section PX that includes one photoelectric conversion element PD and four transistors, such as the transfer transistor TX, the reset transistor RX, the drive transistor DX, and the selection transistor SX. However, the image sensor according to embodiments of the present inventive concept are not necessarily limited thereto. For example, in an embodiment, neighboring pixel sections PX may share the reset transistor RX, the drive

transistor DX, or the selection transistor SX. Therefore, the image sensor may increase in integration.

(31) FIG. 3 illustrates a plan view showing an image sensor according to an embodiment of the present inventive concept. FIG. 4 illustrates a cross-sectional view taken along line I-I' of FIG. 3, showing an image sensor according to an embodiment of the present inventive concept. FIG. 5 illustrates an enlarged view showing section A of FIG. 4.

(32) Referring to FIGS. 3, 4A, and 4B, an image sensor according to an embodiment of the present inventive concept may include a photoelectric conversion layer **10**, a wiring layer **20**, and an optical transmission layer **30**. The photoelectric conversion layer **10** may be disposed between the wiring layer **20** and the optical transmission layer **30** (e.g., in the third direction D3).

(33) The photoelectric conversion layer **10** may include a substrate **100**. The substrate **100** may be a semiconductor substrate (e.g., a silicon substrate, a germanium substrate, a silicon-germanium substrate, a II-VI group compound semiconductor substrate, or a III-V group compound semiconductor substrate) or a silicon-on-insulator (SOI) substrate. However, embodiments of the present inventive concept are not necessarily limited thereto. The substrate **100** may have a first surface **100a** and a second surface **100b** that are opposite to each other (e.g., in the third direction D3). For example, the first surface **100a** of the substrate **100** may be a front surface, and the second surface **100b** of the substrate **100** may be a rear surface. The substrate **100** may receive light incident on the second surface **100b**.

(34) The substrate **100** may include a plurality of pixel sections PX. When viewed in plan, the plurality of pixel sections PX may be two-dimensionally arranged along first and second directions D1 and D2 that are parallel to the second surface **100b** of the substrate **100**. The first direction D1 and the second direction D2 may intersect each other. The substrate **100** may include a plurality of photoelectric conversion regions PD therein. The photoelectric conversion regions PD may be positioned between the first surface **100a** and the second surface **100b** of the substrate **100** (e.g., in the third direction D3). In an embodiment, the third direction D3 may be perpendicular to the first and second directions D1, D2. The photoelectric conversion regions PD may be correspondingly provided in the pixel sections PX of the substrate **100**. In this description, the photoelectric conversion region PD may indicate an area that the photoelectric conversion element PD of FIGS. 1 and 2 are disposed thereon.

(35) In an embodiment, the substrate **100** may have a first conductivity type, and the photoelectric conversion region PD may have a second conductivity type different from the first conductivity type. For example, the first conductivity type may be p-type, and the second conductivity type may be n-type. The impurities of a region having the first conductivity may include, for example, at least one compound selected from aluminum, boron, indium, and gallium. However, embodiments of the present inventive concept are not necessarily limited thereto. The impurities of a region having the second conductivity type may include, for example, at least one compound selected from phosphorus, arsenic, bismuth, and antimony. However, embodiments of the present inventive concept are not necessarily limited thereto. The photoelectric conversion region PD and the substrate **100** may form a p-n junction to constitute a photodiode.

(36) The photoelectric conversion layer **10** may include a shallow isolation pattern **103**. The shallow isolation pattern **103** may be disposed adjacent to the first surface **100a** of the substrate **100**. The plurality of pixel sections PX may include corresponding active regions ACT that are defined by the shallow isolation patterns **103**. The shallow isolation patterns **103** may be disposed in a first trench TR1 and a second trench TR2 that are recessed from the first surface **100a** of the substrate **100**. In an embodiment, the shallow isolation pattern **103** may include at least one compound selected from silicon oxide, silicon nitride, and silicon oxynitride. However, embodiments of the present inventive concept are not necessarily limited thereto.

(37) The photoelectric conversion layer **10** may include a deep isolation pattern **150**. The deep isolation pattern **150** may be disposed in the substrate **100** and may be positioned between the

plurality of pixel sections PX. The deep isolation pattern **150** may penetrate at least a portion of the substrate **100**. The deep isolation pattern **150** may penetrate the shallow isolation pattern **103** to extend into the substrate **100**. The deep isolation pattern **150** may be disposed in a third trench TR3. The third trench TR3 may penetrate the shallow isolation pattern **103** to extend toward the second surface **100b** of the substrate **100**. In an embodiment, a width at an upper portion of the third trench TR3 may be less than a width of a bottom surface of the first trench TR1. In this description, the term “width” may mean a distance measured in a direction (e.g., the second direction D2) parallel to the second surface **100b** of the substrate **100**. When viewed in plan, the deep isolation pattern **150** may have a lattice structure that surrounds each of the plurality of pixel sections PX.

According to an embodiment, the deep isolation pattern **150** may extend from the first surface **100a** of the substrate **100** toward the second surface **100b** of the substrate **100**, and may have a bottom surface **150b** substantially coplanar with the second surface **100b** of the substrate **100**. For example, the deep isolation pattern **150** may include a dielectric material having a refractive index that is less than that of the substrate **100**.

(38) The deep isolation pattern **150** may include a separation pattern **151**, a semiconductor pattern **153**, and a dielectric pattern **155**. The separation pattern **151** may penetrate at least a portion of the substrate **100**. The separation pattern **151** may be interposed between the pixel section PX and the semiconductor pattern **153**. The separation pattern **151** may be interposed between the substrate **100** and a lateral surface of the semiconductor pattern **153** and between the shallow isolation pattern **103** and the dielectric pattern **155**. The separation pattern **151** may extend from the lateral surface of the semiconductor pattern **153** toward a lateral surface of the dielectric pattern **155**. The separation pattern **151** may fill at least a portion of the third trench TR3. For example, in an embodiment, the separation pattern **151** may cover an inner sidewall of the third trench TR3. In an embodiment, the separation pattern **151** may expose a bottom surface of the third trench TR3. When viewed in plan, the separation pattern **151** may surround each of the pixel sections PX. In an embodiment, the separation pattern **151** may include, for example, at least one compound selected from oxide, nitride, metal oxide, and metal nitride. The separation pattern **151** may include, for example, at least one compound selected from silicon oxide, silicon nitride, and silicon oxynitride. However, embodiments of the present inventive concept are not necessarily limited thereto.

(39) The semiconductor pattern **153** may penetrate at least a portion of the substrate **100** (e.g., in the first and/or second directions D1, D2). The semiconductor pattern **153** may be interposed between the plurality of pixel sections PX. The semiconductor pattern **153** may fill a lower portion of the third trench TR3. The semiconductor pattern **153** may cover the bottom surface of the third trench TR3. The semiconductor pattern **153** may cover an inner sidewall of the separation pattern **151** and may directly contact the separation pattern **151**. The semiconductor pattern **153** may have a top surface located at a lower level than a level of the first surface **100a** of the substrate **100**. In this description, the term “level” may indicate a height (e.g., length in the third direction D3) from the second surface **100b** of the substrate **100**. The semiconductor pattern **153** may have a bottom surface that corresponds to that of the deep isolation pattern **150**, and may be substantially coplanar with the second surface **100b** of the substrate **100**. In an embodiment, the semiconductor pattern **153** may include a conductive material, for example, a semiconductor material doped with impurities. For example, the semiconductor pattern **153** may include doped polysilicon.

(40) The dielectric pattern **155** may be disposed on the semiconductor pattern **153**. The dielectric pattern **155** may be disposed in the shallow isolation pattern **103** in the first trench TR1. The dielectric pattern **155** may penetrate the shallow isolation pattern **103** in the first trench TR1 and may directly contact the semiconductor pattern **153**. The separation pattern **151** may separate the dielectric pattern **155** from the shallow isolation pattern **103** in the first trench TR1. In an embodiment, the dielectric pattern **155** may include, for example, at least one compound selected from silicon oxide, silicon nitride, and silicon oxynitride. However, embodiments of the present inventive concept are not necessarily limited thereto.

(41) The first surface **100a** of the substrate **100** may include the transfer transistors TX and the logic transistors RX, SX, and DX that are discussed above with reference to FIG. 1. The transistors, such as the transfer transistor TX, the reset transistor RX, the drive transistor DX, and the selection transistor SX, may be correspondingly disposed on the active regions ACT of the pixel sections PX. The transfer transistor TX may include a gate electrode TG and a floating diffusion region FD that are provided on the active region ACT. The gate electrode TG may correspond to the transfer gate TRG discussed above with reference to FIG. 2. The gate electrode TG may be disposed on a corresponding photoelectric conversion region PD. The gate electrode TG may be disposed adjacent to the shallow isolation pattern **103** in the second trench TR2. For example, the gate electrode TG may be disposed on the shallow isolation pattern **103**. A lower portion of the gate electrode TG may be inserted into the substrate **100**. For example, the lower portion of the gate electrode TG being inserted into the substrate **100** means that the lower portion of the gate electrode TG is spaced apart from the first surface **100a** of the substrate (e.g., in the third direction D3) towards the second surface **100b** of the substrate. An upper portion of the gate electrode TG may protrude beyond the first surface **100a** of the substrate **100**. For example, the upper portion of the gate electrode TG protruding beyond the first surface **100a** means that the upper portion of the gate electrode TG extends above the first surface **100a** of the substrate **100** towards the wiring layer **20** (e.g., in the third direction D3). The gate electrode TG may have a bottom surface disposed in the substrate **100**. A gate dielectric layer GI may be interposed between the gate electrode TG and the substrate **100**. In an embodiment, the gate dielectric layer GI may include silicon oxide or a high-k dielectric material having a dielectric constant that is greater than that of silicon oxide. A gate spacer GS may be provided on an upper sidewall of the gate electrode TG. For example, the gate spacer GS may be disposed on a sidewall of an upper portion of the gate electrode TG that protrudes beyond the first surface **100a** of the substrate **100**. In an embodiment, the gate spacer GS may include at least one compound selected from silicon oxide, silicon nitride, and silicon oxynitride. However, embodiments of the present inventive concept are not necessarily limited thereto.

(42) The floating diffusion region FD may be disposed on one side of the gate electrode TG (e.g., in the first and/or second directions D1, D2) and may be located in a corresponding active region ACT. The floating diffusion region FD may be disposed on a corresponding photoelectric conversion region PD. The floating diffusion region FD may have the second conductivity type (e.g., n-type) different from the first conductivity type of the substrate **100**.

(43) Each of the floating diffusion regions FD may include an impurity region **160** and a doping pad **170**. The impurity region **160** may be disposed adjacent to the first surface **100a** of the substrate **100**. The impurity region **160** may be disposed adjacent to the doping pad **170**. The impurity region **160** may surround a lower portion of the doping pad **170**. The impurity region **160** may have the second conductivity type (e.g., n-type). The impurity region **160** may be an area doped with impurities such as, for example, at least one compound selected from phosphorus (P) and arsenic (As). However, embodiments of the present inventive concept are not necessarily limited thereto. For example, the impurity region **160** may be an area doped with low-concentration impurities.

(44) The doping pad **170** may be provided in a corresponding pixel section PX and on a corresponding photoelectric conversion region PD. The doping pad **170** may be disposed adjacent to the first surface **100a** of the substrate **100**. The doping pad **170** may be horizontally spaced apart (e.g., in the first and/or second directions D1, D2) and vertically spaced apart (e.g., in the third direction D3) from the lower portion of the gate electrode TG that is inserted into the substrate **100**. The doping pad **170** may be horizontally spaced apart (e.g., in the first and/or second directions D1, D2) from the deep isolation pattern **150** and may not vertically overlap the deep isolation pattern **150**. The doping pad **170** may be exposed on the first surface **100a** of the substrate **100**. In an embodiment, the doping pad **170** may have a top surface **170a** located at a higher level than the



level of a top surface of the impurity region **160**. In an embodiment, the doping pad **170** may include, for example, at least one compound selected from doped epitaxial silicon and doped polysilicon. The doping pad **170** may have the second conductivity type (e.g., n-type). In some embodiments, when the doping pad **170** includes epitaxial silicon doped with n-type impurities, the photoelectric conversion layer **10** may not include a dummy pattern **175** which will be discussed with reference to FIGS. **7** to **9**. The impurities doped in the doping pad **170** may include, for example, at least one compound selected from phosphorus (P) and arsenic (As). The doping pad **170** may be doped with high-concentration impurities. For example, a concentration of impurities in the doping pad **170** may be greater than a concentration of impurities in the impurity region **160**. (45) In some embodiments, the top surface **170a** of the doping pad **170** may be located at a higher level than the level of the first surface **100a** of the substrate **100**. The doping pad **170** may have a bottom surface **170b** located at a lower level than that of the first surface **100a** of the substrate **100**. The doping pad **170** may have a sidewall having a portion that directly contacts the shallow isolation pattern **103** adjacent thereto. The top surface **170a** of the doping pad **170** may be located at a lower level than that of a top surface **180a** of an etch stop layer **180** (or on the impurity region **160**) which will be discussed below. The bottom surface **170b** of the doping pad **170** may be located at a lower level than the level of a bottom surface **180b** of the etch stop layer **180**. However, embodiments of the present inventive concept are not necessarily limited thereto. In some embodiments, the top surface **170a** of the doping pad **170** may be substantially coplanar with the top surface **180a** of the etch stop layer **180** on the impurity region **160**, and the bottom surface **170b** of the doping pad **170** may be substantially coplanar with the bottom surface **180b** of the etch stop layer **180**.

(46) According to an embodiment of the present inventive concept, the floating diffusion region FD may include the doping pad **170** doped with high-concentration impurities, and the doping pad **170** may be horizontally and vertically spaced apart from the lower portion of the gate electrode TG that is inserted into the substrate **100**. An increase in horizontal and vertical distances between the gate electrode TG and the doping pad **170** may prevent gate induced drain leakage (GIDL) phenomena that occur between the gate electrode TG and the doping pad **170** (or the floating diffusion region FD).

(47) The etch stop layer **180** may be disposed on the first surface **100a** of the substrate **100**. The etch stop layer **180** may be interposed between the first surface **100a** of the substrate **100** and a first interlayer dielectric layer **210** (e.g., in the third direction D3) which will be discussed below. The etch stop layer **180** may cover the first surface **100a** of the substrate **100**. The etch stop layer **180** may cover the transistors, such as the transfer transistor TX, the reset transistor RX, the drive transistor DX, and the selection transistor SX. The etch stop layer **180** may cover the gate electrode TG and the gate spacer GS. The etch stop layer **180** may not cover but may expose the doping pad **170**. In an embodiment, the etch stop layer **180** may include at least one compound selected from silicon oxide, silicon nitride, silicon oxynitride, and silicon carbonitride. However, embodiments of the present inventive concept are not necessarily limited thereto.

(48) The drive transistor DX may include a drive gate SFG on a corresponding active region ACT, and the selection transistor SX may include a selection gate SG on a corresponding active region ACT. The reset transistor RX may include a reset gate RG on a corresponding active region ACT. An additional gate dielectric layer GI may be interposed between the substrate **100** and each of the drive, selection, and reset gates SFG, SG, and RG.

(49) The wiring layer **20** may be disposed on the first surface **100a** of the substrate **100**. In an embodiment, the wiring layer **20** may include a first interlayer dielectric layer **210**, a second interlayer dielectric layer **220**, and a third interlayer dielectric layer **230** that are sequentially stacked on the first surface **100a** of the substrate **100** (e.g., in the third direction D3). The wiring layer **20** may further include contact plugs BCP in the first interlayer dielectric layer **210**, first wiring patterns **222** in the second interlayer dielectric layer **220**, and second wiring patterns **232** in

the third interlayer dielectric layer **230**. The first interlayer dielectric layer **210** may be disposed on the first surface **100a** of the substrate **100** and may cover the transistors, such as the transfer transistor TX, the reset transistor RX, the drive transistor DX, and the selection transistor SX, and some of the contact plugs BCP may be connected to terminals of the transistors. Some of the contact plugs BCP may be coupled to the floating diffusion region FD and may directly contact the doping pad **170**. The contact plugs BCP may be connected to corresponding ones of the first wiring patterns **222**, and the first wiring patterns **222** may be connected to corresponding ones of the second wiring patterns **232**. The first and second wiring patterns **222** and **232** may be electrically connected through the contact plugs BCP to the transistors. In an embodiment, each of the first, second, and third interlayer dielectric layers **210**, **220**, and **230** may include a dielectric material, and the contact plugs BCP, the first wiring patterns **222**, and the second wiring patterns **232** may include a conductive material.

(50) In some embodiments, the pixel section PX may be a shared pixel. For example, a plurality of photoelectric conversion regions PD may share one floating diffusion region FD. For example, the floating diffusion region FD may be shared through the doping pad **170** and the contact plugs BCP.

(51) The optical transmission layer **30** may be disposed on the second surface **100b** of the substrate **100**. The optical transmission layer **30** may include a plurality of color filters CF and a plurality of microlenses **330**. The optical transmission layer **30** may focus and filter externally incident light, and the photoelectric conversion layer **10** may be provided with the focused and filtered light.

(52) The microlenses **330** may be provided on the second surface **100b** of the substrate **100**. In an embodiment, each of the microlenses **330** may be disposed to vertically (e.g., in the third direction D3) overlap the photoelectric conversion region PD of the pixel section PX that corresponds thereto. Each of the microlenses **330** may have a convex shape to condense light that is incident on the pixel section PX.

(53) The color filters CF may be disposed between the microlenses **330** and the second surface **100b** of the substrate **100**. Each of the color filters CF may be disposed to vertically (e.g., in the third direction D3) overlap the photoelectric conversion region PD on the pixel section PX that corresponds thereto. In an embodiment, the color filters CF may include red, green, and blue filters depending on a unit pixel. The color filters CF may be arranged two-dimensionally, and may include a yellow filter, a magenta filter, and a cyan filter. However, embodiments of the present inventive concept are not necessarily limited thereto and the colors of the color filters CF may vary.

(54) An antireflection layer **310** may be disposed on the second surface **100b** of the substrate **100** (e.g., disposed directly thereon in the third direction D3). The antireflection layer **310** may be interposed between the color filters CF and the second surface **100b** of the substrate **100** (e.g., in the third direction D3). The antireflection layer **310** may conformally cover the second surface **100b** of the substrate **100**. The antireflection layer **310** may prevent light reflection such that the photoelectric conversion region PD may be allowed to readily receive light incident on the second surface **100b** of the substrate **100**. In an embodiment, the antireflection layer **310** may include, for example, at least one compound selected from silicon oxide, silicon nitride, silicon oxynitride, and high-k dielectric materials (e.g., hafnium oxide or aluminum oxide). However, embodiments of the present inventive concept are not necessarily limited thereto.

(55) A first passivation layer **312** may be interposed between the antireflection layer **310** and the color filters CF (e.g., in the third direction D3). A second passivation layer **322** may be interposed between the color filters CF and the microlenses **330** (e.g., in the third direction D3). The first passivation layer **312** may conformally cover the antireflection layer **310**. In an embodiment, the first passivation layer **312** may include, for example, at least one compound selected from metal oxide and nitride. For example, the metal oxide may include aluminum oxide, and the nitride may include silicon nitride. However, embodiments of the present inventive concept are not necessarily limited thereto.

(56) A grid pattern **315** may be provided between the pixel sections PX. The grid pattern **315** may

be interposed between the first passivation layer **312** and the color filters CF (e.g., in the first and/or second directions D1, D2). The grid pattern **315** may be disposed to vertically overlap the deep isolation pattern **150**. In an embodiment, when viewed in plan, the grid pattern **315** may have a lattice shape. When the substrate **100** receives light on the second surface **100b** thereof, the grid pattern **315** may guide the light to enter the photoelectric conversion region PD. In an embodiment, the grid pattern **315** may include at least one compound selected from a metallic material or a low-refractive-index (LRI) material. The metallic material may include, for example, at least one compound selected from tungsten and titanium. The low-refractive-index (LRI) material may include, for example, at least one compound selected from silicon oxide and a material having a refractive index that is less than that of the color filters CF. However, embodiments of the present inventive concept are not necessarily limited thereto.

(57) FIG. **6** illustrates a cross-sectional view taken along line I-I' of FIG. **3**, showing an image sensor according to an embodiment of the present inventive concept. For brevity of description, the following discussion will focus on differences from the image sensor discussed with reference to FIGS. **1** to **5** and a repeated description of identical or similar elements may be omitted.

(58) Referring to FIGS. **3** and **6**, an image sensor according to embodiments of the present inventive concept may include the photoelectric conversion layer **10**, the wiring layer **20**, and the optical transmission layer **30**.

(59) The floating diffusion region FD may further include an additional impurity region **173**. The additional impurity region **173** may be interposed between the impurity region **160** and the doping pad **170**. The additional impurity region **173** may be disposed adjacent to the first surface **100a** of the substrate **100**. The additional impurity region **173** may be disposed adjacent to the doping pad **170** (e.g., immediately adjacent). The additional impurity region **173** may surround a lower portion of the doping pad **170**. The additional impurity region **173** may include impurities that are different from the impurities of the doping pad **170**. In an embodiment, the additional impurity region **173** may be, for example, an area doped with impurities including at least one compound selected from carbon (C) and germanium (Ge). However, embodiments of the present inventive concept are not necessarily limited thereto. The additional impurity region **173** may prevent impurities in the doping pad **170** from being diffused or introduced into the substrate **100**. The additional impurity region **173** may prevent metal elements in the contact plug BCP from being diffused or introduced into the substrate **100**.

(60) FIG. **7** illustrates a cross-sectional view taken along line I-I' of FIG. **3**, showing an image sensor according to an embodiment of the present inventive concept. FIG. **8** illustrates an enlarged view showing section B of FIG. **7**. For brevity of description, the following discussion will focus on differences from the image sensor discussed with reference to FIGS. **1** to **5** and a repeated description of identical or similar elements may be omitted.

(61) Referring to FIGS. **3**, **7**, and **8**, an image sensor according to an embodiment of the present inventive concept may include the photoelectric conversion layer **10**, the wiring layer **20**, and the optical transmission layer **30**.

(62) The photoelectric conversion layer **10** may further include a dummy pattern **175**. The dummy pattern **175** may be provided on the first surface **100a** of the substrate **100**. The dummy pattern **175** may be disposed on the etch stop layer **180** (e.g., disposed directly thereon). The dummy pattern **175** may be interposed between the etch stop layer **180** and the first interlayer dielectric layer **210**. The dummy pattern **175** may be disposed on a sidewall of the gate electrode TG and on a stepped part **180ST** of the etch stop layer **180** positioned between the gate electrode TG and the impurity region **160**. The dummy pattern **175** may cover a portion of a sidewall **180s** of the stepped part **180ST**. The dummy pattern **175** may cover a portion the etch stop layer **180** on the gate spacer GS. A location where the dummy pattern **175** is disposed is not limited to that show in the figures, and may be variously changed. In an embodiment, the dummy pattern **175** may include the same material as that of the doping pad **170**. The dummy pattern **175** may include, for example, at least

one compound selected from epitaxial silicon and polysilicon. For example, the doping pad **170** and the dummy pattern may have the second conductivity type (e.g., n-type).

(63) FIG. **9** illustrates a cross-sectional view taken along line I-I' of FIG. **3**, showing an image sensor according to an embodiment of the present inventive concept. A repetitive discussion will be omitted in the interest of brevity of description.

(64) Referring to FIGS. **3** and **9**, an image sensor according to the present inventive concept may include the photoelectric conversion layer **10**, the wiring layer **20**, and the optical transmission layer **30**. The floating diffusion region FD may further include an additional impurity region **173** between the impurity region **160** and the doping pad **170**. The additional impurity region **173** may be, for example, an area doped with impurities including at least one compound selected from carbon (C) and germanium (Ge). However, embodiments of the present inventive concept are not necessarily limited thereto.

(65) The photoelectric conversion layer **10** may be provided between the etch stop layer **180** and the first interlayer dielectric layer **210**, and may further include a dummy pattern **175** disposed on a stepped part **180ST** of the etch stop layer **180** formed on the gate spacer GS. The dummy pattern **175** may be disposed on a sidewall of the gate electrode TG. In an embodiment, the dummy pattern **175** may include the same material as that of the doping pad **170**. For example, the doping pad **170** may include polysilicon doped with n-type impurities, and the dummy pattern **175** may include polysilicon doped with n-type impurities. However, embodiments of the present inventive concept are not necessarily limited thereto.

(66) FIGS. **10** to **16** illustrate cross-sectional views taken along line I-I' of FIG. **3**, showing a method of fabricating an image sensor according to some embodiments of the present inventive concept. For brevity of description, omission will be made to avoid repetitive explanations about the image sensor discussed with reference to FIGS. **1** to **5**.

(67) Referring to FIGS. **3** and **10**, a substrate **100** may be provided which has a first surface **100a** and a second surface **100b** that are opposite to each other (e.g., in the third direction D3). A first trench TR1 and a second trench TR2 may be formed adjacent to the first surface **100a** of the substrate **100**. The first trench TR1 may have a width greater than a width of the second trench TR2. In an embodiment, the formation of the first trench TR1 and the second trench TR2 may include forming a first mask pattern MP1 on the first surface **100a** of the substrate **100** and using the first mask pattern MP1 as an etching mask to etch the substrate **100**. The first trench TR1 and the second trench TR2 may define active regions ACT in the substrate **100**.

(68) Referring to FIGS. **3** and **11**, a device isolation layer **103L** may be formed on the first surface **100a** of the substrate **100**. The device isolation layer **103L** may fill the first trench TR1 and the second trench TR2, while covering the first mask pattern MP1. In an embodiment, the device isolation layer **103L** may include at least one compound selected from silicon oxide, silicon nitride, and silicon oxynitride. However, embodiments of the present inventive concept are not necessarily limited thereto.

(69) A third trench TR3 may be formed in the substrate **100**. The third trench TR3 may have a depth greater than a depth of the first trench TR1 and that of the second trench TR2. The formation of the third trench TR3 may include forming on the device isolation layer **103L** a second mask pattern MP2 that defines an area where the third trench TR3 will be formed, and using the second mask pattern MP2 as an etching mask to etch the device isolation layer **103L** and the substrate **100**. The third trench TR3 may have a bottom surface located at a higher level than a level of the second surface **100b** of the substrate **100**. The third trench TR3 may define a plurality of pixel sections PX in the substrate **100**. The second mask pattern MP2 may then be removed.

(70) Referring to FIGS. **3** and **12**, a separation layer may be formed on the substrate **100**. The separation layer may conformally cover an inner sidewall and the bottom surface of the third trench TR3.

(71) A semiconductor pattern **153** may fill a lower portion of the third trench TR3. The formation

of the semiconductor pattern **153** may include forming a conductive layer that fills the third trench **TR3** and performing an etch-back process on the conductive layer. In an embodiment, the conductive layer may include a conductive material, for example, an impurity-doped semiconductor material. For example, the conductive layer may include doped polysilicon.

(72) A dielectric pattern **155** may be formed to fill an upper portion of the third trench **TR3**. In an embodiment, the formation of the dielectric pattern **155** may include forming, on the substrate **100** in which the semiconductor pattern **153** is formed, a dielectric layer that fills an occupied portion of the third trench **TR3**, and allowing the dielectric layer, the separation layer, and the device isolation layer **103L** to undergo a planarization process until the first surface **100a** of the substrate **100** is exposed. In an embodiment, the dielectric layer may include, for example, at least one compound selected from silicon oxide, silicon nitride, and silicon oxynitride. The planarization process may remove the first mask pattern **MP1**. The dielectric layer, the separation layer, and the device isolation layer **103L** may be planarized to respectively form a dielectric pattern **155**, a separation pattern **151**, and a shallow isolation pattern **103**. Therefore, a deep isolation pattern **150** may be formed which includes the separation pattern **151**, the semiconductor pattern **153**, and the dielectric pattern **155**.

(73) A photoelectric conversion region **PD** may be formed on each of the plurality of pixel sections **PX**. The formation of the photoelectric conversion region **PD** may include, for example, implanting the substrate **100** with impurities. The photoelectric conversion region **PD** may be a region having a second conductivity type (e.g., n-type) different from a first conductivity type (e.g., p-type).

(74) Referring to FIGS. **3** and **13**, a thinning process may be performed on the second surface **100b** of the substrate **100**. The thinning process may partially remove the substrate **100** and the deep isolation pattern **150**. The thinning process may remove a lower portion of the deep isolation pattern **150**, and a bottom surface of the deep isolation pattern **150** may be substantially coplanar with the second surface **100b** of the substrate **100**.

(75) A gate electrode **TG** may be formed on a corresponding active region **ACT**. The formation of the gate electrode **TG** may include patterning the substrate **100** to form a vertical trench, forming a conductive layer that fills the vertical trench, and patterning the conductive layer. In an embodiment, prior to the formation of the conductive layer, a gate dielectric layer **GI** may further be formed to conformally cover the vertical trench.

(76) The first surface **100a** of the substrate **100** may undergo a first implantation process to form an impurity region **160**. For example, the first implantation process may include forming a mask on the first surface **100a** of the substrate **100** and using the mask to dope first impurities into the first surface **100a** of the substrate **100**. The first impurities may include, for example, at least one compound selected from phosphorus (**P**) and arsenic (**As**).

(77) A gate spacer **GS** may be formed on the gate electrode **TG**. The gate spacer **GS** may cover an upper sidewall of the gate electrode **TG**. In an embodiment, the gate spacer **GS** may include at least one selected from silicon oxide, silicon nitride, and silicon oxynitride. Therefore, a transfer transistor **TX** may be formed.

(78) As shown in FIG. **3**, transistors such as the transfer transistor **TX**, the reset transistor **RX**, the drive transistor **DX**, and the selection transistor **SX**, may be formed on the first surface **100a** of the substrate **100** and on each pixel section **PX**. The formation of drive, selection, and reset transistors **DX**, **SX**, and **RX** may include implanting a corresponding active region **ACT** with impurities to form an impurity region, and forming on the corresponding active region **ACT** a corresponding one of drive, selection, and reset gates **SFG**, **SG**, and **RG**.

(79) Referring to FIGS. **3** and **14**, an etch stop layer **180** may be formed on the first surface **100a** of the substrate **100**. The etch stop layer **180** may cover the first surface **100a** of the substrate **100**, the gate electrode **TG**, and the gate spacer **GS**. In an embodiment, the etch stop layer **180** may include at least one compound selected from silicon oxide, silicon nitride, silicon oxynitride, and silicon carbonitride.

(80) A third mask pattern MP3 may be formed on the first surface **100a** of the substrate **100**. The third mask pattern MP3 may include a first opening OP1 that exposes a portion of the etch stop layer **180**. The first opening OP1 may define an area on which a doping pad **170** may be formed as discussed below.

(81) Referring to FIGS. 3 and 15, an etching process may be performed to remove a portion of the etch stop layer **180** that is exposed to the first opening OP1. The etching process may etch a portion of the substrate **100** that is exposed when the portion of the etch stop layer **180** is exposed. Therefore, the substrate **100** may have a recess RC1 that is recessed from the first surface **100a** of the substrate **100**.

(82) In an embodiment, the first opening OP1 may have a width greater than a width of the recess RC1. However, embodiments of the present inventive concept are not necessarily limited thereto. For example, in an embodiment, the first opening OP1 may have a width substantially the same as the width of the recess RC1.

(83) Referring to FIGS. 3 and 16, the third mask pattern MP3 may be removed. A doping pad **170** may be formed on the recess RC1. The formation of the doping pad **170** may include performing an epitaxial growth process to form an epitaxial layer, and performing a second implantation process on the first surface **100a** of the substrate **100**. The epitaxial layer may be, for example, an epitaxial silicon layer. For example, the second implantation process may include using the third mask pattern MP3 of the substrate **100** to dope second impurities into the first surface **100a** of the substrate **100**. The second impurities may include, for example, at least one compound selected from phosphorus (P) and arsenic (As). The doping pad **170** may include, for example, epitaxial silicon doped with n-type impurities. A concentration of the second impurities in the doping pad **170** may be greater than a concentration of the first impurities in the impurity region **160**. After the formation of the doping pad **170**, an annealing process may further be performed. In an embodiment, the annealing process may be, for example, a rapid thermal annealing (RTA) process. The processes mentioned above may form a photoelectric conversion layer **10**.

(84) For example, the second implantation process may be performed simultaneously with the formation of the epitaxial layer. However, embodiments of the present inventive concept are not necessarily limited thereto. For example, in an embodiment, after the formation of the epitaxial layer, the second implantation process may be performed. In an embodiment, the epitaxial layer may be formed, and a first interlayer dielectric layer **210** and contact plugs BCP may be formed which will be discussed below, and thereafter the second implantation process may be performed.

(85) Referring back to FIGS. 3, 4, and 5, a wiring layer **20** may be formed on the first surface **100a** of the substrate **100**. For example, a first interlayer dielectric layer **210** may be formed on the first surface **100a** of the substrate **100**, and may cover the transistors, such as the transfer transistor TX, the reset transistor RX, the drive transistor DX, and the selection transistor SX. Contact plugs BCP may be formed in the first interlayer dielectric layer **210**, and may be connected to terminals of the transistors. Some of the contact plugs BCP may be electrically connected to the doping pad **170**. In an embodiment, a second interlayer dielectric layer **220** and a third interlayer dielectric layer **230** may be sequentially formed on the first interlayer dielectric layer **210** (e.g., in the third direction D3). First wiring patterns **222** and second wiring patterns **232** may be formed in the second interlayer dielectric layer **220** and the third interlayer dielectric layer **230**, respectively. The first and second wiring patterns **222** and **232** may be electrically connected through the contact plugs BCP to the transistors.

(86) An optical transmission layer **30** may be formed on the second surface **100b** of the substrate **100**. For example, an antireflection layer **310** and a first passivation layer **312** may be sequentially formed on the second surface **100b** of the substrate **100**. A grid pattern **315** may be formed on the first passivation layer **312**, and may vertically overlap (e.g., in the third direction D3) the deep isolation pattern **150**. The formation of the grid pattern **315** may include, for example, depositing a metal layer on the first passivation layer **312** and patterning the metal layer. Color filters CF may be

formed on the first passivation layer **312** to cover the grid pattern **315**. The color filters CF may be correspondingly disposed on the pixel sections PX. A second passivation layer **322** may be formed on the color filters CF, and microlenses **330** may be formed on the second passivation layer **322**. (87) FIGS. **10** to **14** and **17** illustrate cross-sectional views taken along line I-I' of FIG. **3**, showing a method of fabricating an image sensor according to some embodiments of the present inventive concept. A duplicate description will be omitted below.

(88) Referring to FIGS. **3** and **17** together with FIG. **14**, the first surface **100a** of the substrate **100** may undergo an additional implantation process to form an additional impurity region **173**. The additional impurity region **173** may be formed on the impurity region **160**. For example, the additional implantation process may include forming a third mask pattern MP3 on the first surface **100a** of the substrate **100** and using the third mask pattern MP3 to dope additional impurities into the first surface **100a** of the substrate **100**. In an embodiment, the additional impurities may include, for example, at least one selected from carbon (C) and germanium (Ge).

(89) However, embodiments of the present inventive concept are not necessarily limited thereto. For example, in an embodiment the etch stop layer **180** may be partially removed which will be discussed below, the third mask pattern MP3 may be removed, and thereafter the additional impurity region **173** may be formed.

(90) An etching process may be performed to partially remove the etch stop layer **180** exposed to the first opening OP1. A description of the etching process may be substantially the same as that discussed above with reference to FIGS. **3** and **15**.

(91) The third mask pattern MP3 may be removed. A doping pad **170** may be formed on the first surface **100a** of the substrate **100**. The formation of the doping pad **170** may be substantially the same as that discussed above with reference to FIGS. **3** and **16**. Therefore, the doping pad **170** may be formed on the additional impurity region **173**. The processes mentioned above may form a photoelectric conversion layer **10**.

(92) A wiring layer **20** may be formed on the first surface **100a** of the substrate **100**. An optical transmission layer **30** may be formed on the second surface **100b** of the substrate **100**. The formation of the wiring layer **20** and the optical transmission layer **30** may be substantially the same as that discussed above with reference to FIGS. **3**, **4**, and **5**.

(93) FIGS. **10** to **15**, **18**, and **19** illustrate cross-sectional views taken along line I-I' of FIG. **3**, showing a method of fabricating an image sensor according to some embodiments of the present inventive concept. A duplicate description will be omitted below.

(94) Referring to FIGS. **3** and **18** together with FIG. **15**, the third mask pattern MP3 may be removed. A polysilicon layer **171** may be formed on the first surface **100a** of the substrate **100**. The polysilicon layer **171** may cover the gate electrode TG and the first surface **100a** of the substrate **100**, and may fill the recess RC1 of the substrate **100**. For example, the polysilicon layer **171** may have a height H1 greater than half a width W1 of the recess RC1. In this description, the term "height" may indicate a distance measured in a direction (e.g., the third direction D3) perpendicular to the second surface **100b** of the substrate **100**. In an embodiment, the polysilicon layer **171** may include, for example, doped polysilicon.

(95) Referring to FIGS. **3** and **19**, the polysilicon layer **171** may undergo an etching process to form a doping pad **170** and a dummy pattern **175**. In the etching process, a portion of the polysilicon layer **171** may remain in the recess RC1 to form the doping pad **170**. In the etching process, another portion of the polysilicon layer **171** may remain on the stepped part **180ST** of the etch stop layer **180** provided between the gate electrode TG and the impurity region **160**.

(96) In some embodiments, second impurities may further be doped into the first surface **100a** of the substrate **100**. The second impurities may include, for example, at least one compound selected from phosphorus (P) and arsenic (As). The doping pad **170** and the dummy pattern **175** may include, for example, polysilicon doped with n-type impurities. The doping pad **170** and the dummy pattern **175** may include, for example, polysilicon doped with at least one impurity selected

from phosphorus (P) and arsenic (As). A concentration of the second impurities in the doping pad **170** may be greater than a concentration of the first impurities in the impurity region **160**.

(97) After the formation of the doping pad **170**, an annealing process may further be performed. The annealing process may be, for example, a rapid thermal annealing (RTA) process.

(98) In some embodiments, before a portion of the etch stop layer **180** is etched, an additional impurity region **173** may further be formed on the impurity region **160**. The formation of the additional impurity region **173** may be substantially the same as that discussed above with reference to FIGS. **3** and **17**. The processes mentioned above may form a photoelectric conversion layer **10**.

(99) A wiring layer **20** may be formed on the first surface **100a** of the substrate **100**. An optical transmission layer **30** may be formed on the second surface **100b** of the substrate **100**. The formation of the wiring layer **20** and the optical transmission layer **30** may be substantially the same as that discussed above with reference to FIGS. **3**, **4**, and **5**.

(100) FIG. **20** illustrates a plan view showing an image sensor according to some embodiments of the present inventive concept. FIG. **21** illustrates a cross-sectional view taken along line II-II' of FIG. **20**, showing an image sensor according to some embodiments of the present inventive concept. A duplicate description of identical or similar elements may be omitted below for convenience of explanation.

(101) Referring to FIGS. **20** and **21**, an image sensor may include a substrate **100** including a pixel array area AR, an optical black area OB, and a pad area PR, a wiring layer **20** on a first surface **100a** of the substrate **100**, a base substrate **40** on the wiring layer **20**, and an optical transmission layer **30** on a second surface **100b** of the substrate **100**. The wiring layer **20** may be disposed between the base substrate **40** and the first surface **100a** of the substrate **100** (e.g., in the third direction D3). The wiring layer **20** may include an upper wiring layer **21** adjacent to the first surface **100a** of the substrate **100**, and may also include a lower wiring layer **23** between the upper wiring layer **21** and the base substrate **40** (e.g., in the third direction D3). The pixel array area AR may include a plurality of pixel sections PX, a deep isolation pattern **150** disposed between the plurality of pixel sections PX, and a floating diffusion region FD disposed adjacent to the first surface **100a** of the substrate **100**. The floating diffusion region FD may be disposed on one side of the gate electrode TG. The floating diffusion region FD may include an impurity region **160** and a doping pad **170**. The pixel array area AR may be configured substantially identical to the image sensor discussed above with reference to FIGS. **1** to **5**. For example, the impurity region **160** and the doping pad **170** may be respectively substantially the same as the impurity region **160** and the doping pad **170** that are discussed above with reference to FIGS. **1** to **5**.

(102) A first connection structure **50**, a first contact **81**, and a bulk color filter **90** may be disposed on the optical black area OB of the substrate **100**. The first connection structure **50** may include a first light-shield pattern **51**, a first separation pattern **53**, and a first capping pattern **55**. The first light-shield pattern **51** may be disposed on the second surface **100b** of the substrate **100**. The first light-shield pattern **51** may cover the first passivation layer **312**, and may conformally cover an inner wall of each of fourth and fifth trenches TR4 and TR5. The first light-shield pattern **51** may penetrate the photoelectric conversion layer **10** and the upper wiring layer **21**. The first light-shield pattern **51** may be connected to the deep isolation pattern **150** of the photoelectric conversion layer **10**, and may be connected to wiring lines in the upper and lower wiring layers **21** and **23**. Therefore, the first connection structure **50** may electrically connect the photoelectric conversion layer **10** to the wiring layer **20**. The first light-shield pattern **51** may include a metallic material (e.g., tungsten). The first light-shield pattern **51** may block light that is incident on the optical black area OB.

(103) The first contact **81** may fill an unoccupied portion of the fourth trench TR4. In an embodiment, the first contact **81** may include a metallic material (e.g., aluminum). The first contact **81** may be connected to the deep isolation pattern **150**. The first separation pattern **53** may fill an



unoccupied portion of the fifth trench TR5. The first separation pattern **53** may penetrate the photoelectric conversion layer **10** and a portion of the wiring layer **20**. The first separation pattern **53** may include a dielectric material. The first capping pattern **55** may be disposed on the first separation pattern **53** (e.g., directly thereon in the third direction D3).

(104) The bulk color filter **90** may be disposed on (e.g., disposed directly thereon) the first connection structure **50** and the first contact **81**. The bulk color filter **90** may cover the first connection structure **50** and the first contact **81**. A first protection layer **71** may be disposed on and encapsulate the bulk color filter **90**.

(105) A photoelectric conversion region PD may be provided in a corresponding pixel section PX on the optical black area OB. The photoelectric conversion region PD on the optical black area OB may be doped with impurities. The photoelectric conversion region PD on the optical black area OB may be a region having a second conductivity type (e.g., n-type) different from a first conductivity type of the substrate **100**. In an embodiment, the photoelectric conversion region PD on the optical black area OB may have a structure similar to the structure of the photoelectric conversion regions PD on the pixel array area AR, but may not perform the same operation (e.g., generation of electrical signals from received light) as that of the photoelectric conversion regions PD on the pixel array area AR.

(106) A second connection structure **60**, a second contact **83**, and a second protection layer **73** may be disposed on the pad area PR of the substrate **100**. The second connection structure **60** may include a second light-shield pattern **61**, a second separation pattern **63**, and a second capping pattern **65**.

(107) The second light-shield pattern **61** may be disposed on the second surface **100b** of the substrate **100**. The second light-shield pattern **61** may cover the first passivation layer **312**, and may conformally cover an inner wall of each of sixth and seventh trenches TR6 and TR7. The second light-shield pattern **61** may penetrate the photoelectric conversion layer **10** and the upper wiring layer **21**. The second light-shield pattern **61** may be connected to wiring lines in the lower wiring layer **23**. Therefore, the second connection structure **60** may electrically connect the photoelectric conversion layer **10** to the wiring layer **20**. The second light-shield pattern **61** may include a metallic material (e.g., tungsten). The second light-shield pattern **61** may block light that is incident on the pad area PR.

(108) The second contact **83** may fill an unoccupied portion of the sixth trench TR6. In an embodiment, the second contact **83** may include a metallic material (e.g., aluminum). The second contact **83** may serve as an electrical connection path between the image sensor and an external device. The second separation pattern **63** may fill an unoccupied portion of the seventh trench TR7. The second separation pattern **63** may penetrate the photoelectric conversion layer **10** and a portion of the wiring layer **20**. The second separation pattern **63** may include a dielectric material. The second capping pattern **65** may be disposed on the second separation pattern **63** (e.g., disposed directly thereon in the third direction D3). The second protection layer **73** may cover the second connection structure **60**.

(109) A current applied through the second contact **83** may flow toward the deep isolation pattern **150** through the second light-shield pattern **61**, the wiring lines in the wiring layer **20**, and the first light-shield pattern **51**. Electrical signals generated from the photoelectric conversion regions PD in the plurality of pixel sections PX on the pixel array area AR may be outwardly transferred through the wiring lines in the wiring layer **20**, the second light-shield pattern **61**, and the second contact **83**.

(110) According to an embodiment of the present inventive concept, a floating diffusion region may include a doping pad doped with high-concentration impurities, and the doping pad may be horizontally and vertically spaced apart from a lower portion of a gate electrode that is inserted into a substrate. An increase in horizontal and vertical distances between the gate electrode and the doping pad may prevent gate induced drain leakage (GIDL) phenomena that occur between the

gate electrode and the doping pad.

(111) According to some embodiments of the present inventive concept, the floating diffusion region may further include an additional impurity region interposed between an impurity region and the doping pad. The additional impurity region may prevent impurities in the doping pad from being diffused or introduced into the substrate. In addition, the additional impurity region may prevent metal atoms in a contact plug from being diffused or introduced into the substrate.

(112) Although the present inventive concept have been described in connection with the some non-limiting embodiments illustrated in the accompanying drawings, it will be understood by one of ordinary skill in the art that variations in form and detail may be made therein without departing from the spirit and essential feature of the present inventive concept. Therefore, the above disclosed embodiments should thus be considered illustrative and not restrictive.

## Claims

1. An image sensor, comprising: a substrate including a plurality of pixel sections, the substrate having a first surface and a second surface that are opposite to each other; a photoelectric conversion region in each of the pixel sections; a first isolation trench disposed in the substrate and positioned between the pixel sections, the first isolation trench comprises a dielectric pattern that is in contact with the first surface of the substrate, a separation pattern disposed on a sidewall of the first isolation trench, and a pattern on the separation pattern; a gate electrode comprising a lower portion inserted into the substrate and an upper portion protruding beyond the first surface of the substrate; a floating diffusion region on the photoelectric conversion region positioned on one side of the gate electrode; and a contact plug connected to the floating diffusion region, wherein the floating diffusion region includes a doping pad on the first surface and a first impurity region on the doping pad, the first impurity region surrounds a lower portion of the doping pad, wherein the contact plug is connected to an upper portion of the doping pad, the upper portion of the doping pad is opposing the lower portion of the doping pad, and wherein the contact plug, the doping pad, and the first impurity region are vertically arranged.
2. The image sensor of claim 1, wherein a height of the doping pad from the first surface of the substrate to the lower portion of the doping pad in a first direction perpendicular to the first surface of the substrate is smaller than a height of the first impurity region from the first surface of the substrate to a lower portion of the first impurity region in the first direction.
3. The image sensor of claim 2, wherein the upper portion of the doping pad is at a level that is higher than a level of the first surface of the substrate.
4. The image sensor of claim 2, wherein the separation pattern comprises metal oxide.
5. The image sensor of claim 2, wherein the height of the first impurity region from the first surface of the substrate to a lower portion of the first impurity region in the first direction is smaller than a height of the dielectric pattern from the first surface of the substrate to a lower portion of the dielectric pattern in the first direction.
6. The image sensor of claim 5, wherein the dielectric pattern comprises silicon oxide.
7. The image sensor of claim 6, wherein a lower portion of the dielectric pattern has an uneven shape, and wherein the lower portion of the dielectric pattern is spaced apart from the first surface of the substrate.
8. The image sensor of claim 2, wherein the height of the first impurity region from the first surface of the substrate to a lower portion of the first impurity region in the first direction is smaller than a height of the gate electrode from the first surface of the substrate to the lower portion of the gate electrode in the first direction.
9. The image sensor of claim 2, wherein the doping pad includes at least one selected from doped epitaxial silicon and doped polysilicon.
10. The image sensor of claim 1, wherein the first impurity region fully surrounds a lower portion

of the doping pad.

11. The image sensor of claim 10, further comprises: a device isolation layer on the first surface of the substrate and disposed adjacent to the first isolation trench.

12. An image sensor, comprising: a substrate having a first surface and a second surface that are opposite to each other; a first isolation trench disposed in the substrate and positioned between the pixel sections, the first isolation trench comprises a dielectric pattern that is in contact with the first surface of the substrate, a separation pattern disposed on a sidewall of the first isolation trench, and a pattern on the separation pattern; a photoelectric conversion region in the pixel section; a gate electrode comprising a lower portion inserted into the substrate and an upper portion protruding beyond the first surface of the substrate; a floating diffusion region on the photoelectric conversion region, the floating diffusion region is positioned on one side of the gate electrode; a contact plug connected to the floating diffusion region, wherein the floating diffusion region includes an impurity region and a doping pad disposed on the impurity region, wherein the contact plug, the doping pad, and the impurity region are vertically arranged, wherein a lower portion of the dielectric pattern has an uneven shape, wherein the first isolation trench is in contact with the first surface of the substrate and the second surface of the substrate, and wherein the lower portion of the dielectric pattern is spaced apart from the first surface of the substrate.

13. The image sensor of claim 12, wherein: the substrate has a first conductivity type; and each of the impurity region and the doping pad has a second conductivity type that is different from the first conductivity type.

14. The image sensor of claim 12, wherein a height of the doping pad from the first surface of the substrate to the lower portion of the doping pad in a first direction perpendicular to the first surface of the substrate is smaller than a height of the impurity region from the first surface of the substrate to a lower portion of the impurity region in the first direction.

15. The image sensor of claim 12, wherein the impurity region fully surrounds a lower portion of the doping pad.

16. The image sensor of claim 15, wherein a width of the doping pad in a second direction parallel to the first surface of the substrate is smaller than a width of the impurity region in the second direction.

17. The image sensor of claim 15, wherein an upper portion of the doping pad is at a level that is higher than a level of the first surface of the substrate, and wherein the upper portion of the doping pad is opposite to the lower portion of the doping pad.

18. An image sensor, comprising: a substrate that has a first surface and a second surface that are opposite to each other; a first isolation trench disposed in the substrate and positioned between the pixel sections, the first isolation trench comprises a dielectric pattern that is in contact with the first surface of the substrate, a separation pattern disposed on a sidewall of the first isolation trench, and a pattern on the separation pattern; a photoelectric conversion region in the pixel section; a gate electrode comprising a lower portion inserted into the substrate and an upper portion protruding beyond the first surface of the substrate; a floating diffusion region on the photoelectric conversion region, the floating diffusion region is positioned on one side of the gate electrode, the floating diffusion region including an impurity region and a doping pad on the impurity region; a contact plug on the first surface of the substrate and electrically connected to the doping pad; a microlens on the second surface of the substrate; and a plurality of color filters between the substrate and the microlens, wherein the contact plug, the doping pad, and the impurity region are vertically arranged, and wherein the impurity region fully surrounds a lower portion of the doping pad.

19. The image sensor of claim 18, wherein a width of the doping pad in a first direction parallel to the first surface of the substrate is smaller than a width of the impurity region in the first direction.

20. The image sensor of claim 19, wherein a height of the doping pad from the first surface of the substrate to the lower portion of the doping pad in a second direction perpendicular to the first

direction is smaller than a height of the impurity region from the first surface of the substrate to a lower portion of the impurity region in the second direction.

---