



US 20250274102A1

(19) **United States**

(12) **Patent Application Publication**
Zhai et al.

(10) **Pub. No.: US 2025/0274102 A1**

(43) **Pub. Date: Aug. 28, 2025**

(54) **SURFACE ACOUSTIC WAVE FILTER
MODULE PACKAGING STRUCTURE AND
PACKAGING METHOD THEREOF**

(52) **U.S. Cl.**
CPC **H03H 9/64** (2013.01); **H03H 3/08**
(2013.01)

(71) Applicant: **AAC ACOUSTIC TECHNOLOGIES
(SHENZHEN) CO., LTD.**, Shenzhen
(CN)

(57) **ABSTRACT**

(72) Inventors: **Zhiming Zhai**, Shenzhen (CN); **Chao
Wang**, Shenzhen (CN); **Ying Liu**,
Shenzhen (CN)

The present invention provides a surface acoustic wave filter module packaging structure and packaging method thereof. Packaging structure includes a substrate, a surface acoustic wave filter chip, a non-filter chip, a dry film layer, and a plastic sealing layer. Filter chip is fixed to substrate by first convex structures, a cavity is formed between filter chip and substrate. Non-filter chip is fixed to substrate by second convex structures. Dry film layer includes a fracture area surrounding non-filter chip, plastic sealing layer is filled between substrate and non-filter chip through fracture area. The packaging structure and method thereof of the present invention can ensure that a cavity can be formed between the bottom of surface acoustic wave filter chip and substrate, convex structures are not easily broken, avoiding the use of injection molding processes based on wafer level packaging filters, reducing costs and damage to chips during reliability testing.

(21) Appl. No.: **18/744,584**


(22) Filed: **Jun. 14, 2024**

Related U.S. Application Data

(63) Continuation of application No. PCT/CN2024/
078205, filed on Feb. 23, 2024.

Publication Classification

(51) **Int. Cl.**
H03H 9/64 (2006.01)
H03H 3/08 (2006.01)






FIG. 1




FIG. 2a




FIG. 2b




FIG. 2c




FIG. 2d




FIG. 2e




FIG. 2f

SURFACE ACOUSTIC WAVE FILTER MODULE PACKAGING STRUCTURE AND PACKAGING METHOD THEREOF

FIELD OF THE PRESENT INVENTION

[0001] The present invention relates to the field of chip packaging technology, and more particularly, to a multi chips module packaging structure and a packaging method thereof.

DESCRIPTION OF RELATED ART

[0002] The working principle of a surface acoustic wave filter is that sound waves are transmitted on a surface of the chip. Therefore, the packaging of the surface acoustic wave filter must ensure that there is sufficient cavity on the surface of the interdigital transducer (the working sensor of the surface acoustic wave filter), otherwise the product will have no signal transmission. At present, the conventional filter RF modules on the market use injection molding packaging solutions based on wafer level packaging. Before packaging the modules, the filter wafers are first packaged at the wafer level to form cavities on the surface of each filter, and then attached to the RF module substrate. Finally, the packaging is completed by injection molding, marking, and cutting.

[0003] However, in related art, the packaging solution of filter modules based on wafer level packaging has a high cost and excessive injection pressure, which can lead to reliability risks of the convex structure of chip deformation and cracking. Moreover, when using compression molding (C-Molding), the plastic packaging structure is easy to forming cavities on the surface of the plastic sealing layer, resulting in the instability of the structure.

[0004] Therefore, it is desired to provide a new surface acoustic wave filter module packaging structure and a packaging method thereof which can overcome the above problems.

SUMMARY

[0005] In view of the above, the embodiments of the present invention provide a new surface acoustic wave filter module packaging structure, the surface acoustic wave filter module packaging structure can ensure that a cavity can be formed between the bottom of the surface acoustic wave filter chip and the substrate, and convex structures are not easily broken, resulting in high reliability.

[0006] The present invention provides a surface acoustic wave filter module packaging structure including a substrate, at least one surface acoustic wave filter chip located on the substrate, at least one non-filter chip located on the substrate and spaced apart from the surface acoustic wave filter chip, a dry film layer covering the surface acoustic wave filter chip and the non-filter chip, and a plastic sealing layer covering the dry film layer. The surface acoustic wave filter chip is fixed to the substrate by a plurality of first convex structures on a surface of the surface acoustic wave filter chip, and a cavity is formed between the surface acoustic wave filter chip and the substrate. The non-filter chip is fixed to the substrate by a plurality of second convex structures on a surface of the non-filter chip. The dry film layer includes a fracture area surrounding the non-filter chip, and the plastic sealing layer is filled in a space between the substrate and the non-filter chip through the fracture area.

[0007] As an improvement, the dry film layer attaches and covers the surface acoustic wave filter chip and the non-filter chip by vacuum airbag lamination.

[0008] As an improvement, a height of each second convex structure is not less than 50 microns.

[0009] As an improvement, a height of each first convex structure is not greater than 40 microns.

[0010] As an improvement, the dry film layer is made of epoxy resin material.

[0011] As an improvement, a thickness of the dry film layer is 40-50 microns.

[0012] As an improvement, a diameter of each first convex structure is 180-200 microns, and/or the diameter of each second convex structure is 180-200 microns.

[0013] As an improvement, a solder mask layer is provided between the substrate and the dry film layer, and the solder mask layer is also provided in a position without the first convex structures in the cavity.

[0014] In view of the above, the embodiments of the present invention also provide a new packaging method of a surface acoustic wave filter module packaging structure, the surface acoustic wave filter module packaging structure made by this method can ensure that a cavity can be formed between the bottom of the surface acoustic wave filter chip and the substrate, and convex structures are not easily broken, resulting in high reliability.

[0015] The present invention provides a packaging method of a surface acoustic wave filter module packaging structure, including: providing a substrate; providing at least one surface acoustic wave filter chip and at least one non-filter chip, a plurality of first convex structures located on a surface of the surface acoustic wave filter chip, and a plurality of second convex structures located on a surface of the non-filter chip; inverting the surface acoustic wave filter chip and the non-filter chip, and soldering the surface acoustic wave filter chip and the non-filter chip on the surface of the substrate through surface mount technology to form a cavity between the surface acoustic wave filter chip and the substrate; providing a dry film layer, the dry film layer covering the surface acoustic wave filter chip and the non-filter chip by vacuum airbag lamination; increasing a pressure of the vacuum airbag lamination, and only causing a part of the dry film layer around the non-filter chip to broken to form a fracture area; providing a plastic sealing layer, the plastic sealing layer covering the dry film layer through injection molding, the plastic sealing layer been filled in a space between the substrate and the non-filter chip through the fracture area; and cutting to form a plurality of the surface acoustic wave filter module packaging structure, and each surface acoustic wave filter module packaging structure including the surface acoustic wave filter chip and the non-filter chip.

[0016] As an improvement, the packaging method further includes: covering a solder mask layer on the substrate when providing the substrate.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] Many aspects of the exemplary embodiments can be better understood with reference to the following drawing. The components in the drawing are not necessarily drawn to scale, the emphasis instead being placed upon clearly illustrating the principles of the present invention. Moreover, in the drawings, like reference numerals designate corresponding parts throughout the several views.

[0018] FIG. 1 is a flowchart of the manufacturing method for a surface acoustic wave filter module packaging structure in accordance with one embodiment of the present invention.

[0019] FIGS. 2a to 2f are illustrative views of the manufacturing process for the surface acoustic wave filter module packaging structure of the present invention.

DETAILED DESCRIPTION OF THE EXEMPLARY EMBODIMENTS

[0020] The present invention will hereinafter be described in detail with reference to exemplary embodiments. To make the technical problems to be solved, technical solutions and beneficial effects of the present invention more apparent, the present invention is described in further detail together with the figures and the embodiments. It should be understood the specific embodiments described hereby is only to explain the disclosure, not intended to limit the disclosure.

[0021] Referring to the FIG. 2f, the present invention provides one embodiment of a surface acoustic wave filter module packaging structure 100. The surface acoustic wave filter module packaging structure 100 includes a substrate 1, at least one surface acoustic wave filter chip 2 located on the substrate 1, at least one non-filter chip 3 located on the substrate 1 and spaced apart from the surface acoustic wave filter chip 2, a dry film layer 4 covering the surface acoustic wave filter chip 2 and the non-filter chip 3, a solder mask layer 5 is provided between the substrate 1 and the dry film layer 4, and a plastic sealing layer 6 covering the dry film layer 4. The surface acoustic wave filter chip 2 is fixed to the substrate 1 by a plurality of first convex structures 71 on a surface of the surface acoustic wave filter chip 2, and a cavity 20 is formed between the surface acoustic wave filter chip 2 and the substrate 1. The non-filter chip 3 is fixed to the substrate 1 by a plurality of second convex structures 72 on a surface of the non-filter chip 3.

[0022] Referring to the FIG. 2e, the dry film layer 4 attaches and covers the surface acoustic wave filter chip 2 and the non-filter chip 3 by vacuum airbag lamination. The dry film layer 4 can prevent other substances entering between the surface acoustic wave filter chip 2 and the substrate 1, ensuring that the cavity 20 can be formed between the surface acoustic wave filter chip 2 and the substrate 1. The dry film layer 4 includes a fracture area 41 surrounding the non-filter chip 3. The dry film layer 4 is made of epoxy resin material. A thickness of the dry film layer 4 is 40-50 microns.

[0023] The solder mask layer 5 locates on the surface of the substrate 1. The solder mask layer 5 is also provided in a position without the first convex structures 71 in the cavity 20, so that the adjacent first convex structures 71 and other circuits on the substrate 1 will not be tinned together, thus it will not cause a short circuit in the circuit.

[0024] The first convex structures 71 and the second convex structures 72 are both tin balls. A diameter of each first convex structures 71 is 180-200 microns, and/or the diameter of each second convex structure 72 is 180-200 microns. A height of each first convex structure 71 is not greater than 40 microns, and a height of each second convex structure 72 is not less than 50 microns. The height limitations of the first convex structures 71 and the second convex structures 72 ensure that only a part of the dry film layer 4 around the non-filter chip 3 will be broken when increasing the pressure of the vacuum airbag lamination, which can

form the fracture area 41, while the part of the dry film layer 4 around the surface acoustic wave filter chip 2 will not be broken.

[0025] The plastic sealing layer 6 is covered on the dry film layer 4 through the compression molding (C-molding) to complete the process of plastic sealing. The plastic sealing layer 6 is filled in a space between the substrate 1 and the non-filter chip 3 through the fracture area 41. The plastic sealing layer 6 between the substrate 1 and the non-filter chip 3 can support the second convex structures 72, preventing stress from causing the second convex structures 72 to broken. The plastic sealing layer 6 is made of epoxy resin material, and the material composition ratio of the epoxy resin forming the plastic sealing layer 6 is different from that of the epoxy resin forming the dry film layer 4.

[0026] Referring to the FIGS. 1 to 2f, the embodiments of the present invention also provide a new packaging method of a surface acoustic wave filter module packaging structure 100, including:

[0027] S1: providing a substrate 1;

[0028] S2: providing a solder mask layer 5, the solder mask layer 5 covering on the substrate 1, removing part of the solder mask layer 5 to avoid the chips;

[0029] S3: providing at least one surface acoustic wave filter chip 2 and at least one non-filter chip 3, a plurality of first convex structures 71 located on a surface of the surface acoustic wave filter chip 2, and a plurality of second convex structures 72 located on a surface of the non-filter chip 3, the first convex structures 71 and the second convex structures 72 being both tin balls, the diameter of each first convex structure 71 being 180-200 microns, and/or the diameter of each second convex structure 72 being 180-200 microns, a height of each first convex structure 71 being not greater than 40 microns, and a height of each second convex structure 72 being not less than 50 microns;

[0030] S4: inverting the surface acoustic wave filter chip 2 and the non-filter chip 3, and soldering the surface acoustic wave filter chip 2 and the non-filter chip 3 on the surface of the substrate 1 through surface mount technology to form a cavity 20 between the surface acoustic wave filter chip 2 and the substrate 1;

[0031] S5: providing a dry film layer 4 covering the surface acoustic wave filter chip 2 and the non-filter chip 3 by vacuum airbag lamination, the dry film layer 4 being made of epoxy resin material, the thickness of the dry film layer 4 being 40-50 microns;

[0032] S6: increasing a pressure of the vacuum airbag lamination, and only causing a part of the dry film layer 4 around the non-filter chip 3 to broken to form a fracture area 41, while the part of the dry film layer 4 around the surface acoustic wave filter chip 2 been not broken;

[0033] S7: providing a plastic sealing layer 6, the plastic sealing layer 6 covering the dry film layer 4 through injection molding, the plastic sealing layer 6 been filled in a space between the substrate 1 and the non-filter chip 3 through the fracture area 41, the plastic sealing layer 6 being made of epoxy resin material;

[0034] S8: cutting to form a plurality of the surface acoustic wave filter module packaging structure 100, and each surface acoustic wave filter module packaging structure 100 including the surface acoustic wave filter chip 2 and the non-filter chip 3.

[0035] The surface acoustic wave filter module packaging structure **100** made by this method can ensure that the cavity **20** can be formed between the bottom of the surface acoustic wave filter chip **2** and the substrate **1**, at the same time, the second convex structures **72** are not easily broken, which resulting in high reliability.

[0036] Comparing with the related art, the present invention provides a surface acoustic wave filter module packaging structure including a substrate, at least one surface acoustic wave filter chip located on the substrate, at least one non-filter chip located on the substrate and spaced apart from the surface acoustic wave filter chip, a dry film layer covering the surface acoustic wave filter chip and the non-filter chip, and a plastic sealing layer covering the dry film layer. The surface acoustic wave filter chip is fixed to the substrate by a plurality of first convex structures on a surface of the surface acoustic wave filter chip, and a cavity is formed between the surface acoustic wave filter chip and the substrate. The non-filter chip is fixed to the substrate by a plurality of second convex structures on a surface of the non-filter chip. The dry film layer includes a fracture area surrounding the non-filter chip, and the plastic sealing layer is filled in a space between the substrate and the non-filter chip through the fracture area. The surface acoustic wave filter module packaging structure of the present invention can ensure that the cavity can be formed between the bottom of the surface acoustic wave filter chip and the substrate, and the second convex structures are not easily broken, avoiding the use of injection molding processes based on wafer level packaging filters, reducing costs and damage to chips during reliability testing.

[0037] Comparing with the related art, the present invention also provides a packaging method of a surface acoustic wave filter module packaging structure, including: providing a substrate; providing at least one surface acoustic wave filter chip and at least one non-filter chip, a plurality of first convex structures located on a surface of the surface acoustic wave filter chip, and a plurality of second convex structures located on a surface of the non-filter chip; inverting the surface acoustic wave filter chip and the non-filter chip, and soldering the surface acoustic wave filter chip and the non-filter chip on the surface of the substrate through surface mount technology to form a cavity between the surface acoustic wave filter chip and the substrate; providing a dry film layer, the dry film layer covering the surface acoustic wave filter chip and the non-filter chip by vacuum airbag lamination; increasing a pressure of the vacuum airbag lamination, and only causing a part of the dry film layer around the non-filter chip to broken to form a fracture area; providing a plastic sealing layer, the plastic sealing layer covering the dry film layer through injection molding, the plastic sealing layer been filled in a space between the substrate and the non-filter chip through the fracture area; and cutting to form a plurality of the surface acoustic wave filter module packaging structure, and each surface acoustic wave filter module packaging structure including the surface acoustic wave filter chip and the non-filter chip. The surface acoustic wave filter module packaging structure made by this method of present invention can ensure that the cavity can be formed between the bottom of surface acoustic wave filter chip and the substrate, and the second convex structures are not easily broken, avoiding the use of injection molding processes based on wafer level packaging filters, reducing costs and damage to chips during reliability testing.

[0038] It is to be understood, however, that even though numerous characteristics and advantages of the present exemplary embodiments have been set forth in the foregoing description, together with details of the structures and functions of the embodiment, the disclosure is illustrative only, and changes may be made in detail, especially in matters of shape, size, and arrangement of parts within the principles of the invention to the full extent indicated by the broad general meaning of the terms where the appended claims are expressed.

What is claimed is:

1. A surface acoustic wave filter module packaging structure, comprising:
 - a substrate,
 - at least one surface acoustic wave filter chip located on the substrate, the surface acoustic wave filter chip fixed to the substrate by a plurality of first convex structures on a surface of the surface acoustic wave filter chip, and a cavity formed between the surface acoustic wave filter chip and the substrate;
 - at least one non-filter chip located on the substrate and spaced apart from the surface acoustic wave filter chip, the non-filter chip fixed to the substrate by a plurality of second convex structures on a surface of the non-filter chip;
 - a dry film layer covering the surface acoustic wave filter chip and the non-filter chip, the dry film layer comprising a fracture area surrounding the non-filter chip; and
 - a plastic sealing layer covering the dry film layer, the plastic sealing layer been filled in a space between the substrate and the non-filter chip through the fracture area.
2. The surface acoustic wave filter module packaging structure as described in claim 1, wherein the dry film layer attaches and covers the surface acoustic wave filter chip and the non-filter chip by vacuum airbag lamination.
3. The surface acoustic wave filter module packaging structure as described in claim 2, wherein a height of each second convex structure is not less than 50 microns.
4. The surface acoustic wave filter module packaging structure as described in claim 2, wherein a height of each first convex structure is not greater than 40 microns.
5. The surface acoustic wave filter module packaging structure as described in claim 2, wherein the dry film layer is made of epoxy resin material.
6. The surface acoustic wave filter module packaging structure as described in claim 2, wherein a thickness of the dry film layer is 40-50 microns.
7. The surface acoustic wave filter module packaging structure as described in claim 1, wherein a diameter of each first convex structure is 180-200 microns, and/or the diameter of each second convex structure is 180-200 microns.
8. The surface acoustic wave filter module packaging structure as described in claim 1, wherein a solder mask layer is provided between the substrate and the dry film layer, and the solder mask layer is also provided in a position without the first convex structures in the cavity.
9. A packaging method of a surface acoustic wave filter module packaging structure, comprising:
 - providing a substrate;
 - providing at least one surface acoustic wave filter chip and at least one non-filter chip, a plurality of first convex structures located on a surface of the surface

acoustic wave filter chip, and a plurality of second convex structures located on a surface of the non-filter chip;

inverting the surface acoustic wave filter chip and the non-filter chip, and soldering the surface acoustic wave filter chip and the non-filter chip on the surface of the substrate through surface mount technology to form a cavity between the surface acoustic wave filter chip and the substrate;

providing a dry film layer, the dry film layer covering the surface acoustic wave filter chip and the non-filter chip by vacuum airbag lamination;

increasing a pressure of the vacuum airbag lamination, and only causing a part of the dry film layer around the non-filter chip to broken to form a fracture area;

providing a plastic sealing layer, the plastic sealing layer covering the dry film layer through injection molding, the plastic sealing layer been filled in a space between the substrate and the non-filter chip through the fracture area; and

cutting to form a plurality of the surface acoustic wave filter module packaging structure, and each surface acoustic wave filter module packaging structure comprising the surface acoustic wave filter chip and the non-filter chip.

10. The packaging method of the surface acoustic wave filter module packaging structure as described in claim **8**, wherein the packaging method further comprises: covering a solder mask layer on the substrate when providing the substrate.

* * * * *