

US Patent & Trademark Office

Patent Public Search | Text View

United States Patent	12417987
Kind Code	B2
Date of Patent	September 16, 2025
Inventor(s)	Chang; Jen-Yuan et al.

Semiconductor die including guard ring structure and three-dimensional device structure including the same

Abstract

A die includes: a semiconductor substrate; an interconnect structure disposed on the semiconductor substrate and including: inter-metal dielectric (IMD) layers; metal features embedded in the IMD layers; and a guard ring structure including concentric first and second guard rings that extend through at least a subset of the IMD layers; and a through silicon via (TSV) structure extending through the semiconductor substrate and the subset of IMD layers to electrically contact one of the metal features. The first guard ring surrounds the TSV structure; and the second guard ring surrounds the first guard ring and is configured to reduce a parasitic capacitance between the guard ring structure and the TSV structure.

Inventors: Chang; Jen-Yuan (Hsinchu, TW), Lee; Chien-Chang (Hsinchu, TW), Lai; Chia-Ping (Hsinchu, TW)

Applicant: Taiwan Semiconductor Manufacturing Company Limited (Hsinchu, TW)

Family ID: 1000008822125

Assignee: Taiwan Semiconductor Manufacturing Company Limited (Hsinchu, TW)

Appl. No.: 18/669577

Filed: May 21, 2024

Prior Publication Data

Document Identifier	Publication Date
US 20240312931 A1	Sep. 19, 2024

Related U.S. Application Data

continuation parent-doc US 18338596 20230621 US 12027475 child-doc US 18669577
continuation parent-doc US 17458687 20210827 US 11728288 20230815 child-doc US 18338596

Publication Classification

Int. Cl.: **H01L23/58** (20060101); **H01L21/768** (20060101); **H01L23/48** (20060101); **H01L23/522** (20060101); **H01L25/065** (20230101); H01L23/00 (20060101); H01L25/18 (20230101)

U.S. Cl.:

CPC **H01L23/585** (20130101); **H01L21/76898** (20130101); **H01L23/481** (20130101); **H01L23/5222** (20130101); **H01L25/0657** (20130101); H01L23/562 (20130101); H01L25/18 (20130101); H01L2225/06544 (20130101)

Field of Classification Search

CPC: H01L (23/585); H01L (21/76898); H01L (23/481)

References Cited

U.S. PATENT DOCUMENTS

Patent No.	Issued Date	Patentee Name	U.S. Cl.	CPC
8168529	12/2011	Lin	438/622	H01L 25/0657
8890293	12/2013	Lu	257/490	H01L 21/76
9691684	12/2016	Park	N/A	H01L 21/76898
10204952	12/2018	Huang	N/A	H01L 23/481
10600888	12/2019	Or-Bach	N/A	H10D 89/10
10784185	12/2019	Li	N/A	H01L 24/92
11270952	12/2021	Wang	N/A	H01L 23/585
11728288	12/2022	Chang	257/621	H01L 21/76898
11855130	12/2022	Chang	N/A	H10D 1/716
11869859	12/2023	Chang	N/A	H01L 24/08
12027475	12/2023	Chang	N/A	H01L 23/481
12125761	12/2023	Chang	N/A	H01L 24/83
12154869	12/2023	Chang	N/A	H01L 23/49822
2010/0187671	12/2009	Lin	257/773	H01L 21/76898
2012/0273782	12/2011	Goel	716/112	H01L 22/32
2015/0061147	12/2014	Lin	438/653	H01L 23/53209
2015/0348871	12/2014	Chiang	257/751	H01L 23/481
2022/0262695	12/2021	Chang	N/A	H01L 25/0657
2022/0301981	12/2021	Chang	N/A	H01L 23/585
2022/0302050	12/2021	Chang	N/A	H01L 23/564
2022/0310570	12/2021	Chang	N/A	H01L 25/105
2023/0060208	12/2022	Chang	N/A	H01L 22/32
2023/0060265	12/2022	Chang	N/A	H01L 23/62

2023/0061861	12/2022	Chang	N/A	H01L 25/18
2023/0062027	12/2022	Chang	N/A	H01L 25/50
2023/0067714	12/2022	Chang	N/A	H01L 25/0657
2023/0069315	12/2022	Chang	N/A	H01L 24/08
2023/0307384	12/2022	Chang	N/A	H01L 23/49827
2023/0352427	12/2022	Chang	N/A	H01L 23/481
2023/0378136	12/2022	Chang	N/A	H01L 25/50
2023/0378247	12/2022	Chang	N/A	H10D 1/716
2024/0312931	12/2023	Chang	N/A	H01L 23/522
2025/0054881	12/2024	Chang	N/A	H01L 24/08

FOREIGN PATENT DOCUMENTS

Patent No.	Application Date	Country	CPC
114709179	12/2021	CN	H01L 21/568
114765153	12/2021	CN	H01L 21/486
114783957	12/2021	CN	H01L 21/56
114823554	12/2021	CN	H01L 23/3107
114823620	12/2021	CN	H01L 21/76898
115513180	12/2021	CN	H01L 23/5384
115527985	12/2021	CN	H01L 23/10
115527987	12/2021	CN	H01L 21/76898
115527990	12/2021	CN	H01L 21/4857
115527992	12/2021	CN	H01L 24/06
115528007	12/2021	CN	H01L 21/56
115528008	12/2021	CN	H01L 23/3128
116454049	12/2022	CN	H01L 23/481
4089725	12/2021	EP	H01L 21/4846
2010166052	12/2009	JP	H01L 21/3065
202131471	12/2020	TW	N/A
202326984	12/2022	TW	H01L 21/76898
202329383	12/2022	TW	H01L 21/76898

OTHER PUBLICATIONS

TW Patent and Trademark Office; TW Application No. 111119242; Office Action mailed Oct. 23, 2024; 8 pages. cited by applicant

Primary Examiner: Menz; Laura M

Attorney, Agent or Firm: The Marbury Law Group, PLLC

Background/Summary

RELATED APPLICATIONS (1) This application is a continuation of U.S. patent application Ser. No. 18/338,596 entitled “Semiconductor Die Including Guard Ring Structure and Three-Dimensional Device Structure Including the Same” filed Jun. 21, 2023, which is a continuation of U.S. patent application Ser. No. 17/458,687, entitled “Semiconductor Die Including Guard Ring Structure and Three-Dimensional Device Structure Including the Same” filed Aug. 27, 2021, now patented as U.S. Pat. No. 11,728,288, the entire contents of both of which are hereby incorporated by reference for all purposes.

BACKGROUND

(1) With the progress of transistor process technology, the dimensions of transistors have decreased. Conversely, the number of transistors per unit area of an integrated circuit has increased accordingly. The increased device density utilizes higher interconnect technology that can achieve signal transport between devices with a desired speed and satisfy low resistance and low capacitance (e.g., low RC time constant) requirements. The effect of interconnect RC time constant on signal delay is exacerbated as integrated circuits become more complex and feature sizes decreases. In semiconductor back-end-of line (BEOL) processing, metal interconnect structures are fabricated with inter-metal dielectric (IMD) layers, which can contribute capacitance to the metal interconnect structures. Thus, increasing the RC time constant delay. The capacitance contribution can undesirably reduce signal transport speed of the semiconductor circuitry.

(2) The use of low dielectric constant (low-k) dielectric material to form the IMD layers has to some extent reduced the capacitance contribution and improved signal transport speed. However, the low-k dielectric material has disadvantageous features and properties such as high porosity, which make it susceptible to damage during certain semiconductor processes such as etching, deposition, and wet processes, which can degrade (increase) their dielectric constants.

Description

BRIEF DESCRIPTION OF THE DRAWINGS

(1) Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

(2) FIG. 1A is a vertical cross-sectional view of a semiconductor die, according to various embodiments of the present disclosure.

(3) FIG. 1B is an enlarged portion P1 of the semiconductor die of FIG. 1A.

(4) FIG. 2A is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the semiconductor die of FIG. 1A.

(5) FIG. 2B is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the semiconductor die of FIG. 1A after the formation of a deep trench.

(6) FIG. 2C is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the semiconductor die of FIG. 1A after the deposition of a barrier layer over a mask layer and in the deep trench.

(7) FIG. 2D is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the semiconductor die of FIG. 1A after the deposition of an electrically conductive material over the barrier layer in the deep trench.

(8) FIG. 2E is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the semiconductor die of FIG. 1A after the planarization of the electrically conductive material, barrier layer and hard mask layer.

(9) FIGS. 3A-3C are cross-sectional views of alternative via guard ring structures, according to various embodiments of the present disclosure.

(10) FIGS. 4A-4C are horizontal cross-sectional views of alternative via guard ring structures, according to various embodiments of the present disclosure.

(11) FIG. 5A is a simplified top view of a three dimensional device structure, according to various embodiments of the present disclosure.

(12) FIG. 5B is a cross-sectional view taken along line I-I' of FIG. 5A.

DETAILED DESCRIPTION

(13) The following disclosure provides many different embodiments, or examples, for implementing different features of the provided subject matter. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

(14) Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly. Unless explicitly stated otherwise, each element having the same reference numeral is presumed to have the same material composition and to have a thickness within the same thickness range.

(15) The present disclosure is directed to semiconductor dies including a guard ring structure disposed around through-silicon via (TSV) structures, and three-dimensional device structures that include one or more of the semiconductor dies.

(16) FIG. 1A is a vertical cross-sectional view of a semiconductor die, according to various embodiments of the present disclosure. FIG. 1B is an enlarged view of a portion of FIG. 1A. Referring to FIG. 1A, a first semiconductor die **100** includes a semiconductor substrate **102** and a first interconnect structure **110**. In some embodiments, the first semiconductor substrate **102** may include an elementary semiconductor such as silicon or germanium and/or a compound semiconductor such as silicon germanium, silicon carbide, gallium arsenic, indium arsenide, gallium nitride or indium phosphide. Other semiconductor materials are within the contemplated scope of disclosure. In some embodiments, the semiconductor substrate **102** may be a semiconductor-on-insulator (SOI) substrate. In various embodiments, the first semiconductor substrate **102** may take the form of a planar substrate, a substrate with multiple fins, nanowires, or other forms known to people having ordinary skill in the art. Depending on the requirements of design, the semiconductor substrate **102** may be a P-type substrate or an N-type substrate and may have doped regions therein. The doped regions may be configured for an N-type device or a P-type device.

(17) In some embodiments, the first semiconductor substrate **102** includes isolation structures defining at least one active area, and a first device layer may be disposed on/in the active area. The first device layer may include a variety of devices. In some embodiments, the devices may include active components, passive components, a combination thereof, or the like. In some embodiments, the devices may include integrated circuits devices. The devices may be, for example, transistors,

capacitors, resistors, diodes, photodiodes, fuse devices, or other similar devices. In some embodiments, the first device layer includes gate electrodes **104**, source/drain regions, spacers, and the like.

(18) The first interconnect structure **110** may include an inter-layer dielectric (ILD) layer **112**, a passivation layer **118**, one or more inter-metal dielectric (IMD) layers **114**, metal features **116**, a first seal ring **120**, and a guard ring structure **160**. In some embodiments, the ILD layer **112** may be formed of a dielectric material such as silicon oxide (SiO₂), silicon nitride (SiN or Si₃N₄), silicon carbide (SiC), or the like, and may be deposited by any suitable deposition process. Herein, “suitable deposition processes” may include a chemical vapor deposition (CVD) process, a physical vapor deposition (PVD) process, an atomic layer deposition (ALD) process, a high density plasma CVD (HDPCVD) process, a low pressure CVD process, a metalorganic CVD (MOCVD) process, a plasma enhanced CVD (PECVD) process, a sputtering process, laser ablation, or the like.

(19) In some embodiments, the interconnect structure **110** may include five IMD layers **114A-114E** as shown in FIGS. **1A** and **1B**. However, the present disclosure is not limited to any particular number of IMD layers **114**. The IMD layers **114** may include an extra low-k (ELK) dielectric material having a dielectric constant (k) less than about 2.6, such as from 2.5 to 2.2. In some embodiments, ELK dielectric materials include carbon-doped silicon oxide, amorphous fluorinated carbon, parylene, bis-benzocyclobutenes (BCB), polytetrafluoroethylene (PTFE) (Teflon), or silicon oxycarbide polymers (SiOC). In some embodiments, ELK dielectric materials may include porous versions of existing dielectric material, such as porous hydrogen silsesquioxane (HSQ), porous methyl silsesquioxane (MSQ), porous polyarylether (PAE), porous SiLK, or porous SiO₂. Other suitable ELK materials are within the contemplated scope of disclosure. The IMD layers **114** may be formed by any suitable deposition process. In some embodiments, the IMD layers **114** may be deposited by a PECVD process or by a spin coating process.

(20) The metal features **116** may include line structures **116L** and via structures **116V**. The metal features **116** may be formed of any suitable electrically conductive material, such as tungsten (W), copper (Cu), a copper alloy, aluminum (Al), an aluminum alloy, combinations thereof, or the like. Other suitable electrically conductive materials are within the contemplated scope of disclosure.

(21) The metal features **116** may be electrically connected to the gate electrodes **104**, such that the first interconnect structure **110** may electrically connect semiconductor devices formed on the first semiconductor substrate **102**.

(22) The first seal ring **120** may extend around the periphery of the first die **100**. For example, the first seal ring **120** may extend through the dielectric layers **112**, **114**, at the periphery of the first interconnect structure **110**. The first seal ring **120** may include line structures **120L** and via structures **120V**. The first seal ring **120** may be configured to protect the first interconnect structure **110** from contaminant diffusion and/or physical damage during device processing, such as plasma etching and/or deposition processes.

(23) The first seal ring **120** may include copper at an atomic percentage greater than 80%, such as greater than 90% and/or greater than 95% although greater or lesser percentages may be used. The first seal ring **120** may include line structures **120L** and via structures **120V** that are electrically connected to each other and may be formed simultaneously with the line structures **116L** and via structures **116V** of the metal features **116**, and/or the line structures **162L**, **164L**, and the via structures **162V**, **164V**, of the first and second guard rings **162**, **164**. The first seal ring **120** may be electrically isolated from the metal features **116**.

(24) In some embodiments, the first die **100** may also include one or more through silicon via (TSV) structures **150**. The TSV structure **150** may extend into and/or through the first semiconductor substrate **102**, the ILD layer **112**, and one or more of the IMD layers **114**, to electrically connect the metal features **116** to elements of the first semiconductor substrate **102** and or elements of adjacent dies. The TSV structure **150** may be formed of an electrically conductive

metal. For example, the TSV structure **150** may include copper at an atomic percentage greater than 80%, such as greater than 90% and/or greater than 95%, although greater or lesser percentages of copper may be used. Other suitable electrically conductive metal materials for the TSV structure may be within the contemplated scope of disclosure.

(25) In various embodiments, the first die **100** may include a first guard ring structure **160** disposed in the interconnect structure **110**, surrounding the TSV structure **150**. The first guard ring structure **160** may be formed of any of the materials used to form the TSV structure and/or the metal features **116**. For example, the first guard ring structure **160** may be formed of Cu, Ta, TaN, Ti, TiN, CoW, combinations thereof, or the like. Other electrically conductive metal materials for the first guard ring structure **160** may be within the contemplated scope of disclosure.

(26) The first guard ring structure **160** may include concentric first and second guard rings **162**, **164**. In particular, the first guard ring **162** may surround the TSV structure **150** and the second guard ring **164** may surround the first guard ring **162**. The first guard ring structure **160** may extend through a subset of the IMD layers **114**, such as IMD layers **114A-114C**. Accordingly, the first guard ring structure **160** and the TSV structure **150** may extend through the same subset of the IMD layers **114**. The first guard ring structure **160** and the TSV structure **150** may also extend through the ILD layer **112**. However, in some embodiments, the first guard ring structure **160** may not extend through the ILD layer **112**.

(27) The guard rings **162**, **164** may respectively include line structures **162L**, **164L** and via structures **162V**, **164V**. In some embodiments, the top surface of the line structures **162L**, **164L** of the first and second guard rings **162**, **164** and the top surface of the line structures **116L** of the metal features **116** may be coplanar in each IMD layer **114**; and the top surface of the via structures **162V**, **164V** of the first and second guard rings **162**, **164** and the top surface of the via structures **116V** of the metal features **116** may be coplanar in each IMD layer **114**.

(28) In some embodiments, the metal features **116**, the guard ring structure **160**, and/or the first seal ring **120** may be formed by a dual-Damascene process or by multiple single Damascene processes. Single-Damascene processes generally form and fill a single feature with copper per Damascene stage. Dual-Damascene processes generally form and fill two features with copper at once, e.g., a trench and overlapping through-hole may both be filled with a single copper deposition using dual-Damascene processes. In alternative embodiments, the metal features **116**, first guard ring structure **160** and/or the first seal ring **120** may be formed by an electroplating process.

(29) For example, the Damascene processes may include patterning the dielectric layers **112**, **114** to form openings, such as trenches and/or through-holes (e.g., via holes). A deposition process may be performed to deposit a conductive metal (e.g., copper) in the openings. A planarization process, such as chemical-mechanical planarization (CMP) may then be performed to remove excess copper (e.g., overburden).

(30) In particular, the patterning, metal deposition, and planarizing processes may be performed for each of the dielectric layers **112**, **114**, in order to form the metal features **116** and/or portions of the guard ring **160**, the first seal ring **120**, and/or the first guard ring structure **160** therein. For example, the ILD layer **112** may be deposited and patterned to form via structures and/or trenches. A deposition process may then be performed to fill the openings in the ILD layer **112** with a conductive material. A planarization process may then be performed to remove the overburden and form via structures **120V**, **162V**, **164V** and/or line structures **116L**, **162L**, **164L**, in the ILD layer **112**.

(31) The above deposition, patterning, and planarization processes may be repeated to form IMD layers **114A-114E** and via structures **116V**, **120V**, **162V**, **164V**, and/or line structures **116L**, **120L**, **162L**, **164L** therein. Accordingly, in some embodiments, elements of the metal features **116**, first seal ring **120**, and first guard ring structure **160** may be formed by the same processes and at the same time, when forming each dielectric layer **112**, **114A-114E**.

(32) In some embodiments, barrier layers (not shown) may be disposed between the dielectric

layers **112**, **114**, and the metal features **116**, the first seal ring **120**, TSV structure **150**, and/or guard ring structure **160**, to prevent metal diffusion into the semiconductor substrate **102** and/or dielectric layers **112**, **114**. The barrier layer may include Ta, TaN, Ti, TiN, CoW, combinations thereof, or the like, for example. Other suitable barrier layer materials are within the contemplated scope of disclosure.

(33) FIG. 2A is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the of the semiconductor die of FIG. 1A. As shown in FIG. 2A, an intermediate structure **110A** including the ILD layer **112** and one or more IMD layers **114**, such as IMD layers **114A-114C**, for example, may be formed on the first semiconductor substrate **102**. However, the present disclosure is not limited to any particular intermediate structure, or any particular number of IMD layers **114**. The intermediate structure **110A** may also include a portion of the metal features **116**, first seal ring **120**, and the guard ring structure **160**. A mask layer **109** may be deposited on the intermediate structure **110A**, using any suitable deposition process and photoresist material.

(34) FIG. 2B is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the of the semiconductor die of FIG. 1A after the formation of a deep trench. Referring to FIG. 2B, the mask layer **109** may be patterned using a photolithography process, for example, to expose a portion of the intermediate structure **110A** inside of the guard ring structure **160**. An etching process may then be performed to form a trench **101** in the exposed portion of the intermediate structure **110A**. The etching may include a dry etching method such as plasma (e.g., fluorine containing plasma) etching, a wet etching process, or a combination thereof.

(35) The trench **101** may extend through the IMD layers **114A-114C**, the ILD layer **112**, and into the first semiconductor substrate **102**. The trench **101** may partially or completely extend through the first semiconductor substrate **102**. The trench **101** may be formed inside of the guard ring structure **160**.

(36) During the etching process and/or after the trench **101** is formed, the intermediate structure **110A** may be exposed to contaminants such as water, etching chemicals, sulfur, fluorine, etc. as part of the device fabrication. The mask layer **109** may be formed of a material that is resistant to the diffusion of the contaminants. However, side walls of the ILD layer **112** and one or more IMD layers **114**, may be exposed to contaminants inside of the trench **101**. As noted above, the IMD layers **114** may be formed of ELK dielectric materials, such as porous ELK dielectric materials. As such, the IMD layers **114** may be particularly susceptible to the diffusion of contaminants, which may result in an electrical failure. For example, contaminants may electrically short the metal features **116**.

(37) FIG. 2C is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the of the semiconductor die of FIG. 1A after the deposition of a barrier layer over a mask layer and in the deep trench as shown in FIG. 2B. Referring to FIG. 2C, a barrier layer **111** may be deposited on the mask layer **109** and in the trench **101**, using any suitable deposition process, such as PVD, CVD, etc. The barrier layer **111** may be formed of any suitable barrier layer material, such as Ta, TaN, Ti, TiN, CoW, combinations thereof, or the like. Other suitable barrier layer materials are within the contemplated scope of disclosure.

(38) FIG. 2D is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure of the of the semiconductor die of FIG. 1A after the deposition of an electrically conductive material over the barrier layer in the deep trench as shown in FIG. 2C. Referring to FIG. 2D, an electrically conductive material **151** may be deposited on the barrier layer **111** and in the trench **101**. The electrically conductive material **151** may be deposited using any suitable method, such as electroplating, CVD, PVD, etc.

(39) FIG. 2E is a vertical cross-sectional view of an intermediate structure formed during the formation of a TSV structure **150** of the of the semiconductor die of FIG. 1A after the planarization of the electrically conductive material **151**, barrier layer **111** and hard mask layer **109** as shown in

FIG. 2D. Referring to FIG. 2E, the intermediate structure may be planarized using CMP, for example, to form the TSV structure **150** by removing portions of the electrically conductive material **151** and the barrier layer **111**. After planarization, additional IMD layers **114**, metal features **116**, and portions of the first seal ring **120**, may be formed as described above.

(40) The first guard ring structure **160** may surround the trench **101** and may be configured to prevent the diffusion of contaminants into the ILD layer **112** and/or the IMD layers **114**. In particular, the first guard ring **162** may be sufficient to contain any contaminants and/or prevent the diffusion of contaminants, since the contaminants cannot diffuse through the metal of the first guard ring **162**. However, since the TSV structure **150** is configured to conduct electrical current, significant parasitic capacitance may be induced between a single guard ring **162** and the TSV structure **150**. Accordingly, the first guard ring structure **160** may include at least the second guard ring **164**, which may operate to reduce the electrical impact of the first guard ring structure **160** on the TSV structure **150**, by reducing the parasitic capacitance.

(41) FIGS. 3A-3C are vertical cross-sectional views respectively showing guard ring structures **160A-160C**, according to various embodiments of the present disclosure. The guard ring structures **160A-160C** may be similar to the guard ring structure **160**. As such, only the difference there between will be discussed in detail.

(42) Referring to FIG. 3A, the guard ring structure **160A** may include first and second guard rings **162**, **164**. However, in contrast to the guard ring structure **160**, the first and second guard rings **162**, **164** of the guard ring structure **160A** may be disposed in only the IMD layers **114**, such as IMD layers **114A-114C**. In particular, the ILD layer **112** may be formed of a material having a higher resistance to contaminant diffusion than the IMD layers **114**. As such, line and/or via structures of the guard ring structure **160A** may be omitted from the ILD layer **112**, in some embodiments.

(43) Referring to FIG. 3B, the guard ring structure **160B** may include first and second guard rings **162**, **164**. However, in contrast to the guard ring structure **160**, the first and second guard rings **162**, **164** of the guard ring structure **160B** may include only via structures **162V**, **164V** in the ILD layer **112**. In other words, the guard ring structure **160B** may omit line structures **162L**, **164L** of the guard ring structure **160** in the ILD layer **112**.

(44) Referring to FIG. 3C, the guard ring structure **160B** may include first, second, and third guard rings **162**, **164**, **166**. In particular, the third guard rings **166** may surround the second guard rings **164**. The third guard ring structures **166** may be configured to further reduce the effects of parasitic capacitance generated by current flow through the TSV structure **150**.

(45) FIGS. 4A-4C are horizontal cross-sectional views of guard ring structures **160D-160F**, respectively taken through lines I-I' of FIGS. 3A-3C, according to various embodiments of the present disclosure. The horizontal cross-sectional views of guard ring structures **160D-160F** may correspond to any of the guard ring structures **160-160C**. As such, only the difference there between will be discussed in detail.

(46) Referring to FIG. 4A, the guard ring structure **160D** may include circular first and second guard rings **162C**, **164C**. In other words, the first and second guard rings **162C**, **164C** may have circular horizontal cross-sections. Referring to FIG. 4B, the guard ring structure **160E** may include rectangular first and second guard rings **162R**, **164R**. In other words, the first and second guard rings **162R**, **164R** may have rectangular horizontal cross-sections. Referring to FIG. 4C, the guard ring structure **160F** may include polygonal first, second, and third guard rings **162F**, **164F**, **166F**. In other words, the first, second, and third guard rings **162F**, **164F**, **166F** may have polygonal horizontal cross-sections. However, the present disclosure is not limited to guard rings having any particular horizontal cross-sectional shape. For example, guard rings may have any suitable horizontal cross-sectional shapes, provided that the guard rings surround a corresponding TSV structure.

(47) FIG. 5A is a simplified top view of a three-dimensional device structure **10** including the first die **100** of FIGS. 1A and 1B, according to various embodiments of the present disclosure. FIG. 5B

is a cross-sectional view taken along line I-I' of FIG. 5A Referring to FIGS. 5A-5B, the three-dimensional (3D) device structure **10** may be referred to herein as a 3D integrated circuit (3D IC) and may include a wafer **50** upon which the first die **100**, a second die **200**, and a third die **300** are stacked and bonded together. Herein, the numbering of the first, second, and third dies **100**, **200**, **300** is used for descriptive purposes only and is not intended to imply that any particular numbered die is required to have any particular feature described herein.

(48) The wafer **50** may include a semiconductor substrate **52**, a passivation layer **54**, and a wafer bonding layer **56**. The semiconductor substrate **52** may include an elementary semiconductor such as silicon or germanium and/or a compound semiconductor such as silicon germanium, silicon carbide, gallium arsenic, indium arsenide, gallium nitride, indium phosphide, or the like. Other semiconductor materials are within the contemplated scope of the disclosure. In some embodiments, the wafer **50** may be a master die including semiconductor devices configured to control the functions of the dies **100**, **200**, **300**.

(49) The dies **100**, **200**, **300** may be, for example, an application-specific integrated circuit (ASIC) chip, an analog chip, a sensor chip, a wireless and radio frequency chip, a voltage regulator chip, or a memory chip. Other chips are within the contemplated scope of disclosure. In various embodiments, the dies **100**, **200**, **300** may be the same or different types of chips. In some embodiments, the dies **100**, **200**, **300** may each be an active component or a passive component.

(50) The first die **100** may be inverted and bonded to the wafer **50**, such that a front side of the first semiconductor substrate **102** faces the wafer **50**. The first interconnect structure **110** may be disposed between the front side of the semiconductor substrate **102** and the wafer **50**.

(51) A front side bonding layer **130** may be disposed on the first interconnect structure **110**, facing the front side of the first semiconductor substrate **102**. The front side bonding layer **130** may be formed by depositing a dielectric material, such as silicon oxide, silicon nitride, a polymer, or the like, or a combination thereof, using any suitable deposition process. Other dielectric materials are within the contemplated scope of disclosure. Bonding metal features **132** may be formed in the front side bonding layer **130**. The metal features **132** may include an electrically conductive metal, such as tungsten (W), copper (Cu), a copper alloy, aluminum (Al), an aluminum alloy, a combination thereof, or the like. As noted above, other suitable electrically conductive metal materials are within the contemplated scope of disclosure. The metal features **132** may be formed by a dual-Damascene processes, or by one or more single-Damascene processes, as described above. In alternative embodiments, the metal features **132** may be formed by an electroplating process.

(52) A first dielectric encapsulation (DE) layer **60** may surround the first die **100** and may cover exposed portions of the wafer **50**. Specifically, the first DE layer **60** may surround the sidewalls of the first die **100**, expose the top of the first die **100**, and overlay the front side of the wafer **50**. In some embodiments, the back side of the first semiconductor substrate **102** may be substantially coplanar with the top surface of the first DE layer **60**. In some embodiments, the first DE layer **60** includes a molding compound. The molding compound may include a resin and a filler. In alternative embodiments, the first DE layer **60** may include silicon oxide, silicon nitride, or a combination thereof, or the like. The first DE layer **60** may be formed by spin-coating, lamination, deposition or the like.

(53) A back side bonding layer **40** may be formed on the back side of the first semiconductor substrate **102** and on the surface of the first DE layer **60**. The back side bonding layer **40** may be formed by depositing a dielectric material, such as silicon oxide, silicon nitride, a polymer, a combination thereof, or the like, using any suitable deposition process. Bonding metal features **42** may be formed in the backside bonding layer **40**. The metal features **42** may be formed of a conductive metal as described above with respect to the metal features **116**.

(54) In some embodiments, the second die **200** may be similar to the first die **100**. For example, the second die **200** may include a second semiconductor substrate **202**, a second interconnect structure

210, and a front side bonding layer **230**. In addition, the second die **200** may include one or more second guard ring **260** structures respectively surrounding second TSV structures **250**.

(55) The second interconnect structure **210** may be disposed over a first side (e.g., front side) of the second semiconductor substrate **202**. The second interconnect structure **210** may have a single-layer or multi-layer structure. For example, as shown in FIG. 5B, the second interconnect structure **210** may include an ILD layer **212**, IMD layers **214**, metal features **216**, and a second seal ring **220**.

(56) The metal features **216** may be electrically connected to an integrated circuit region of the second semiconductor substrate **202**. In some embodiments, the metal features **216** may be electrically connected to gate electrodes **204** of the second semiconductor substrate **202**, such that the second interconnect structure **210** may electrically connect semiconductor devices formed on the second semiconductor substrate **202**.

(57) The second seal ring **220** may be similar to the first seal ring **120**. For example, the second seal ring **220** may include copper at an atomic percentage greater than 80%, such as greater than 90% and/or greater than 95%, although greater or lesser percentages of copper may be used. The second seal ring **220** may be disposed over the front side of the second semiconductor substrate **202**. Specifically, the second seal ring **220** may surround the second interconnect structure **210**, may extend through the dielectric layers **212**, **214**, and may surround the metal features **216**. In some embodiments, the second seal ring **220** may be formed during the formation of the dielectric layers **212**, **214**. The top surface of the second seal ring **220** may be coplanar with the top surfaces of the uppermost metal features **216** of the second interconnect structure **210**.

(58) In some embodiments, the size of the second die **200** may be different from (e.g., less than) the size of the first die **100**. Herein, the term “size” refers to the length, width and/or area. For example, as shown in the top view of FIG. 5A, the size (e.g., area or footprint) of the second die **200** may be less than the size of the first die **100**.

(59) The second TSV structures **250** may extend through the second semiconductor substrate **202**, the ILD layer **212**, and one or more of the IMD layers **214**, to electrically connect one of the metal features **216** to a die bonding pad **46**. The second TSV structure **250** may be formed of an electrically conductive metal. For example, the second TSV structure **250** may include copper at an atomic percentage greater than 80%, such as greater than 90% and/or greater than 95%, although greater or lesser percentages of copper may be used. Other suitable electrically conductive metals may be within the contemplated scope of disclosure.

(60) A second DE layer **62** may surround the second die **200** and may cover exposed portions of the back side bonding layer **40**. Specifically, the second DE layer **62** may surround the sidewalls of the second die **200**, expose the top of the second die **200**, and overlay back side bonding layer **40**. In some embodiments, the back side of the second semiconductor substrate **202** may be substantially co-planar with the top surface of the second DE layer **62**. In some embodiments, the second DE layer **62** includes a molding compound. The molding compound may include a resin and a filler. In alternative embodiments, the second DE layer **62** may include silicon oxide, silicon nitride, a combination thereof, or the like. The second DE layer **62** may be formed by spin-coating, lamination, deposition, or the like.

(61) A back side bonding layer **44** may be formed on the back side of the second semiconductor substrate **202** and on the top surface of the second DE layer **62**. The back side bonding layer **44** may be formed by depositing a dielectric material, such as silicon oxide, silicon nitride, a polymer, a combination thereof, or the like, using any suitable deposition process. Metal features **46** may be formed in the back side bonding layer **44**. The metal features **46** may be formed of a conductive metal as described above with respect to the metal features **116**.

(62) The third die **300** may be similar to the second die **200**. For example, the third die **300** may include a third semiconductor substrate **302**, a third interconnect structure **310**, and a front side bonding layer **330**. In addition, the third die **300** may include third guard ring structures **360** respectively surrounding third TSV structures **350**.

(63) The third interconnect structure **310** may be disposed over a first side (e.g., front side) of the third semiconductor substrate **302**. The third interconnect structure **310** may have a single-layer or multi-layer structure. For example, as shown in FIG. 5B, the third interconnect structure **310** may include an ILD layer **312**, IMD layers **314**, metal features **316**, and a third ring **320**.

(64) The metal features **316** may be electrically connected to an integrated circuit region of the third semiconductor substrate **302**. In some embodiments, the metal features **316** may be electrically connected to gate electrodes **304** of the third semiconductor substrate **302**, such that the third interconnect structure **310** may electrically connect semiconductor devices formed on the third semiconductor substrate **302**.

(65) The third seal ring **320** may be similar in structure and composition to the second seal ring **220**. The front side bonding layer **330** may be similar in structure and composition to the front side bonding layer **230**. In particular, electrically conductive metal features **332** may be formed in the front side bonding layer **330**.

(66) The third TSV structures **350** may extend through the third semiconductor substrate **302**, the ILD layer **312**, and one or more of the IMD layers **314**, to electrically connect one or more of the metal features **316** to corresponding gate electrodes **304** of the third semiconductor substrate **302**. The third TSV structure **350** may be formed of an electrically conductive metal. For example, the TSV structure **350** may include copper at an atomic percentage greater than 80%, such as greater than 90% and/or greater than 95%, although greater or lesser percentages of copper may be used. Other suitable electrically conductive metals may be within the contemplated scope of disclosure.

(67) A third DE layer **64** may surround the third die **300** and may cover exposed portions of the back side bonding layer **44**. Specifically, the third DE layer **64** may surround the sidewalls of the third die **300**, expose the top of the third die **300**, and overlay back side bonding layer **44**. In some embodiments, the back side of the third semiconductor substrate **302** may be substantially coplanar with the top surface of the third DE layer **64**. In some embodiments, the third DE layer **64** includes a molding compound. The molding compound may include a resin and a filler. In alternative embodiments, the third DE layer **64** may include silicon oxide, silicon nitride, a combination thereof, or the like. The third DE layer **64** may be formed by spin-coating, lamination, deposition or the like.

(68) In some embodiments, a diffusion barrier layer (not shown) may be disposed around the metal features **116**, **216**, **316**, and/or the first TSV structure **150**, second TSV structure **250**, third TSV structure **350**, to prevent metal diffusion into adjacent layers. The diffusion barrier layer may include Ta, TaN, Ti, TiN, CoW, a combination thereof, or the like. Other suitable barrier layer materials may be within the contemplated scope of disclosure.

(69) A redistribution layer structure **400** may be disposed on the backside of the third die **300**, over the third DE layer **64**. The redistribution layer structure **400** may include one or more dielectric layers **414**, metal features **416**, bonding pads **418**, a fourth seal ring **420**, and a passivation layer **430**. In some embodiments, the metal features **416** may be electrically connected to the third TSV structures **350**.

(70) In some embodiments, the dielectric layers **414** may include a photo-sensitive material such as polybenzoxazole (PBO), polyimide (PI), benzocyclobutene (BCB), a combination thereof, or the like. In some embodiments, the metal features **416** may include copper, nickel, titanium, a combination thereof, or the like. Other suitable conductive metal materials may be within the contemplated scope of disclosure to form the metal features **416**.

(71) The fourth seal ring **420** may surround the metal features **416**. The fourth seal ring **420** may include materials and structures similar to that of the first seal ring **120** and/or second seal ring **220**.

(72) The bonding pads **418** may be disposed on the dielectric layers **414**. In some embodiments, the bonding pads **418** may be under bump metallization (UBM) pads for mounting conductive connectors, such as metal pillars, micro-bumps or the like. The pads **418** may include a metal or a metal alloy. The bonding pads **418** may include aluminum, copper, nickel, an alloy thereof, or the

like, for example. Other suitable pad materials may be within the contemplated scope of disclosure.

(73) The passivation layer **430** may cover the dielectric layers **414** and edge portions of the pads **418**. Upper surfaces of the pads **418** may be exposed through the passivation layer **430**. In some embodiments, the passivation layer **430** includes silicon oxide, silicon nitride, benzocyclobutene (BCB) polymer, polyimide (PI), polybenzoxazole (PBO), a combination thereof, or the like.

(74) The first die **100** may be flipped (e.g., inverted) and disposed over the wafer **50**. The front side bonding layer **130** may be bonded to the wafer bonding layer **56**, in order to bond the first die **100** to the wafer **50**. The bonding may include any suitable bonding process, such as a thermal annealing or chemical bonding process. The bonding process may include electrically connecting the metal features **132** to metal features (not shown) of the wafer bonding layer **56**. The first DE layer **60** may then be deposited about the first die **100**. The back side bonding layer **40** may be deposited on the first die **100** and the first DE layer **60**, using any suitable deposition process.

(75) The second die **200** may be flipped and disposed over the first die **100**. The front side bonding layer **230** may be bonded to the backside bonding layer **40**, to bond the front side of the second die **200** to the back side of the first die **100**. The bonding may include any suitable bonding process, such as a thermal annealing or chemical bonding process. The bonding process may include electrically connecting the metal features **42**, **232**. The second DE layer **62** may then be deposited about the second die **200**. The back side bonding layer **44** may be deposited on the second die **200** and the second DE layer **62**, using any suitable deposition process.

(76) The third die **300** may be flipped and disposed over the second die **100**. The front side bonding layer **330** may be bonded to the backside bonding layer **44**, to bond the back side of the second die **200** to the front side of the third die **300**. The bonding may include any suitable bonding process, such as a thermal annealing or chemical bonding process. The bonding process may include electrically connecting the metal features **232**, **332**. The third DE layer **64** may then be deposited about the third die **300**. The redistribution layer structure **400** may then be formed on the third die **300** and the third DE layer **64**, using any suitable deposition processes.

(77) The metal features **42**, **44**, **132**, **232**, **332**, may include an electrically conductive bonding material, such as W, Cu, a Cu alloy, Al, an aluminum alloy, a combination thereof, or the like, and the bonding layers **40**, **44**, **56**, **130**, **230**, **330** may be formed of any suitable dielectric material. The metal features **42**, **44**, **132**, **232**, **332**, and the bonding layers **40**, **44**, **56**, **130**, **230**, **330** may be formed by a dual-Damascene processes, by one or more single-Damascene processes, or by etching and electroplating processes.

(78) In various embodiments, the first die **100**, second die **200**, or third die **300** may be formed on wafers and may be singulated prior to being individually positioned and bonded. In other embodiments, wafers including a plurality of the first die **100**, second die **200**, or third die **300** may be disposed over the wafer **50**, the corresponding dies may be wafer-bonded, and then the corresponding dies may be singulated.

(79) In some embodiments, the alignment of the first die **100**, second die **200**, and third die **300** may be achieved by using an optical sensing method. After the alignment is achieved, the bonding may be performed by a hybrid bonding process that includes a metal-to-metal bonding and a dielectric-to-dielectric bonding.

(80) In various embodiments, a dicing process may be performed to singulate the three-dimensional device structure **10**. For example, a grooving process may be performed to form grooves in a first wafer including the first dies **100** and/or in a second wafer including the second dies **200**. In particular, first grooves may be formed that surround the first seal ring **120**, second seal ring **220**, and/or third seal ring **320**. The three-dimensional device structures **10** may be diced along the grooves to complete the dicing process, for example, by mechanical cleavage.

(81) In certain embodiments, the grooving process includes performing one or more laser cutting processes. For example, the laser cutting process may be performed several times with an infrared laser such as an Nd-YAG (neodymium-doped yttrium aluminum garnet) laser. In alternative

embodiments, the grooving process may include a mechanical cutting process, an inscribing process, or an etching process.

(82) Various embodiments provide a die **100** comprising: a semiconductor substrate **102**; an interconnect structure **110** disposed on the semiconductor substrate **102** and comprising: inter-metal dielectric (IMD) layers **114**; metal features **116** embedded in the IMD layers **114**; and a first guard ring structure **160** comprising concentric first and second guard rings **162**, **164** that extend through at least a subset of the IMD layers **114**; and a first through silicon via (TSV) structure **150** extending through the semiconductor substrate **102** and the subset of IMD layers **114** to electrically contact one of the metal features **116**. The first guard ring **162** surrounds the first TSV structure **150**; and the second guard ring **164** surrounds the first guard ring **162** and is configured to reduce a parasitic capacitance between the first guard ring structure **160** and the TSV structure **150**.

(83) Various embodiments provide a die **100** comprising: a semiconductor substrate **102**; an inter-layer dielectric (ILD) layer disposed on the semiconductor substrate; inter-metal dielectric (IMD) layers disposed on the ILD layer; metal features **116** embedded in the IMD layers **114**; a first guard ring structure **160** comprising concentric first and second guard rings **162**, **164** that extend through at least a subset of the IMD layers **114**; a seal ring **120** extending through the ILD and IMD layers and surrounding the metal features **116** and the guard ring structure **160**; and a first through silicon via (TSV) structure **150** extending through the semiconductor substrate **102** and the subset of IMD layers **114** to electrically contact one of the metal features **116**. The first guard ring **162** surrounds the first TSV structure **150**, and the second guard ring **164** surrounds the first guard ring **162** and is configured to reduce a parasitic capacitance between the first guard ring structure **160** and the first TSV structure **150**.

(84) Various embodiments provide a three-dimensional device structure **10** comprising: a first die **100** and a second die **200** bonded to the first die **100**. The first die **100** comprises: a first semiconductor substrate **102**; a first interconnect structure **110** disposed on the semiconductor substrate **102** and comprising: inter-metal dielectric (IMD) layers **114**; a first guard ring structure **160** comprising concentric first and second guard rings **162**, **164** embedded in the IMD layers **114**; metal features **116** embedded in the IMD layers **114**; a first seal ring **120** embedded in the IMD layers **114** and surrounding the metal features **116** and the guard ring structure **160**; and a through silicon via (TSV) structure **150** extending through the first semiconductor substrate **102** and into the first interconnect structure **110**, such that the first and second guard rings **162**, **164** concentrically surround the first TSV structure **150**. The second die **200** comprises a second interconnect structure **210** disposed on a second semiconductor substrate **202**. Metal features **216** of the second interconnect structure **210** electrically connect the first TSV structure **150** to the second semiconductor substrate **202**, and the second guard ring **164** is configured to reduce a parasitic capacitance between the first guard ring structure **160** and the first TSV structure **150**.

(85) The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

Claims

1. A semiconductor chip comprising: a device layer comprising semiconductor devices; an interconnect structure that electrically interconnects the semiconductor devices; a through silicon via (TSV) structure that extends through the device layer and is electrically connected to the

interconnect structure; a first guard ring that surrounds a portion of the TSV structure that is embedded in the interconnect structure; and a second guard ring configured to reduce a parasitic capacitance between the first guard ring and the TSV structure.

2. The semiconductor chip of claim 1, wherein the interconnect structure comprises: inter-metal dielectric (IMD) layers; and metal features embedded in the IMD layers.
3. The semiconductor chip of claim 2, wherein the IMD layers comprise an extra low-k (ELK) dielectric material having a dielectric constant (k) of less than 2.5.
4. The semiconductor chip of claim 3, wherein the ELK dielectric material has a dielectric constant (k) ranging from 2.5 to 2.2.
5. The semiconductor chip of claim 2, wherein: the interconnect structure comprises an inter-layer dielectric (ILD) layer disposed between the semiconductor substrate and the IMD layers; and the first and second guard rings extend through at least one of the IMD layers and the ILD layer.
6. The semiconductor chip of claim 5, wherein the first and second guard rings comprise via structures embedded in the ILD layer.
7. The semiconductor chip of claim 5, wherein the first and second guard rings comprise via structures and line structures embedded in the ILD layer.
8. The semiconductor chip of claim 2, wherein: the interconnect structure comprises an inter-layer dielectric (ILD) layer disposed between the semiconductor substrate and the IMD layers; and the first and second guard rings extend through at least one of the IMD layers and do not extend through the ILD layer.
9. The semiconductor chip of claim 2, wherein the IMD layers have a higher porosity than the ILD layer.
10. The semiconductor chip of claim 2, wherein the interconnect structure comprises a seal ring surrounding the metal features, the first TSV structure, and the second guard ring.
11. The semiconductor chip of claim 2, wherein: the first and second guard rings comprise line structures and via structures embedded in the IMD layers; the metal features comprise line structures and via structures embedded in the IMD layers; the line structures of the first and second guard rings and the line structures of the metal features are coplanar in each IMD layer; and the via structures of the first and second guard rings and the via structures of the metal features are coplanar in each IMD layer.
12. The semiconductor chip of claim 1, further comprising a third guard ring surrounding the second guard ring and configured to further reduce a parasitic capacitance between the first guard ring and the first TSV structure.
13. A semiconductor chip comprising: a substrate; an interconnect structure configured to electrically connect semiconductor devices formed on the substrate; a through silicon via (TSV) structure extending through the substrate and into the interconnect structure; a first guard ring configured to prevent and/or reduce metal diffusion from the TSV structure into the interconnect structure; and a second guard ring configured to reduce a parasitic capacitance between the first guard ring and the TSV structure.
14. The semiconductor chip of claim 13, further comprising a third guard ring surrounding the second guard ring and configured to reduce a parasitic capacitance between the first guard ring and the first TSV structure.
15. The semiconductor chip of claim 13, wherein the interconnect structure comprises: inter-metal dielectric (IMD) layers; metal features embedded in the IMD layers and configured to electrically connect the semiconductor devices; an inter-layer dielectric (ILD) layer disposed between the semiconductor substrate and the IMD layers; and a seal ring surrounding the metal features, the first TSV structure, and the second guard ring.
16. The semiconductor chip of claim 15, wherein: the first and second guard rings extend through the IMD layers and the ILD layer; and the IMD layers have a higher porosity than the ILD layer.
17. A semiconductor chip comprising: a substrate; an interconnect structure comprising: inter-metal

dielectric (IMD) layers; metal features embedded in the IMD layers and configured to electrically connect semiconductor devices formed on a first side of the substrate; and a seal ring surrounding the metal features; a through silicon via (TSV) structure that extends through the substrate to electrically connect the interconnect structure and the redistribution layer structure; a first guard ring surrounding a portion of the TSV structure that is embedded in the interconnect structure; a second guard ring configured to reduce a parasitic capacitance between the first guard ring and the TSV structure; and a third guard ring surrounding the second guard ring and configured to further reduce a parasitic capacitance between the first guard ring and the TSV structure, wherein the IMD layers comprise an extra low-k (ELK) dielectric material having a dielectric constant (k) of less than 2.5.

18. The semiconductor chip of claim 17, wherein first interconnect structure comprises: inter-metal dielectric (IMD) layers; metal features embedded in the IMD layers; a first seal ring embedded in the IMD layers and surrounding the metal features and the second guard ring structure.

19. The semiconductor chip of claim 18, wherein the first and second guard rings comprise line structures and via structures embedded in the IMD layers.

20. The semiconductor chip of claim 18, further comprising an inter-layer dielectric (ILD) layer disposed between the semiconductor substrate and the IMD layers, wherein the first, second, and third guard rings extend through the ILD layer and at least one of the IMD layers and.
