

ROCK

WATERPROOF AND BREATHABLE PLASTER

PRODUCT CHARACTERISTICS

Plastering and waterproofing in one step. Extremely waterproof against water pressure under permanent load. IOzoComponent HARD is an innovative hydrophobic ingredient certified for contact with drinking water.

PRODUCT DESCRIPTION

Waterproof and breathable plaster ROCK is extremely waterproof dry plaster mixture that will create a waterproof membrane after application while it stays breathable at the same time. Hydrophobic ingredient IzoComponent HARD is the key component that ensures waterproof characteristic of the product. Waterproof plaster ROCK offers for you long-term resolution with removing the problems with water leakage on surface of the wall or floor. It is ideal resolution for usage in buildings where it is necessary to protect them before destructive influence of water. This plaster is produced from natural materials and does not contain any harmful or inflammable ingredients and it is environment friendly therefore it is possible to use it for insulation of tanks with drinking water.

USES

- For a full water-insulation of cellars, shafts and underground constructions from groundwater
- For plaster reconstruction in older buildings and additional water-insulation of existing
- moist buildings (it resists not only against water but also nitric salts - efflorescence)
- At new buildings for insulation of pedestal parts against groundwater
- For water-insulation of bathrooms, shower baths, for prevention of water leakage between the floors
- For water-insulation of oversized concrete tanks

ADVANTAGES

- Outstanding waterproof capability
- Resistance against direct contact with water-resistant
- Breathable
- Above-ground or under-ground insulation
- Excellent adhesion and ability of connection
- Frost-proof and sulfur-resistant
- It is possible to apply to wet surfaces
- Prevention against salt crystallization
- Resistant against rain and flowing water
- It can be laid on manually or with spray applicator

APPLICATION DETAILS

Surface Preparation

Before laying on the waterproof and breathable plaster ROCK the ground must be solid, released from free parts and paintings. It must not be greasy, acid, water-repellent or alcoholic base.

SURFACE MUST BE TOTALLY WETTED WITH WATER, BEFORE PLASTER APPLICATION.

Preparation of plaster mixture for laying on

Preparation is being made in gravity mixer or with manual stirrer after adding **3.75-4.75 liters of water** to one 25kg bag of plaster mixture. Mix or stir for 5-10 min. Keep the material stand for 5 min. and then final 1 min. mixing before applying. Mixed material must be worked up within 3 hours. It is recommended to use electrically powered mixing tool, due to hydrophobic abilities of the plaster..

DO NOT ADD ANYTHING INTO MIXED COMPOSITION!

Laying on the plaster and finishing of plaster surface

The plaster is being laid on to prepared ground manually with a smoother or with spray applicator (commonly used method). The plaster is being laid on maximally in three layers in total thickness of the plaster from 10 to 30 mm. Total thickness of the plaster is defined according to a load of brick work with moistness. After only one layer is laid on then the plaster thickness is about 10 to 15 mm. Then it is necessary to slightly rough up a surface of each layer. Particular layers are being laid on the prepared surface after 24 hours.

Care after application

It is necessary to prevent the plaster from too fast drying since the optimal moistness enables permanent hydration of cement materials and minimization of cracking. When the last layer is laid on then it is necessary to slightly moisten the surface of the plaster for 3 days especially at dry and windy weather or at direct sunshine. The last layer can be painted by interior or exterior color or faced by tiles after final roughing up. In case of tiles it is necessary to rough up the plaster.

Important

At plastering of extremely moist brickwork with plaster ROCK aggregation of water drops onto plaster surface can occur. It is inherent forcing the water out of vicinity and the drops will disappear when the plaster gets hard.

Cleaning

Clear water is used for disposal of plaster for the tools and equipment. Hardened material can be disposed only in a mechanical way.

Technical specification

PROPERTY / PARAMETER	SPECIFICATION VALUE
Appearance / Colour	Powder / Grey
Chemical Base	Sand, Cement, IzoComponent HARD
Density of hardened mortar	1680 kg/m ³ +/- 50kg
Layer Thickness	One layer from 10 mm to 15 mm. Max. 3 layers in total thickness of 30 mm.
Consumption	- 1 m ² with thickness 10 mm = 12 kg of dry plaster 25 kg of dry plaster = 2.08 m ² with thickness 10 mm - 1 m ² with thickness 15 mm = 18 kg of dry plaster 25 kg of dry plaster = 1.38 m ² with thickness 15 mm
Packaging	25 kg bag
Shelf-life	18 months in case of its storage at dry conditions
Depth of water penetration into hardened plaster	≤ 1 mm
Diffuse resistance of water vapour, coefficient (μ)	12.40

Waterproof plaster ROCK is produced in a such way that fulfills strictly controlled European standards, it is supplied as industrially produces -mixed plaster mixture that requires only addition of water at the application place. It consists exact ratio of particular components: quality dry sorted sand, specific cement and special hydrophobic and fluidifiers.