Product Data Sheet

Product: VerdeMix GGBS-50 Grade C30
Binder: 50% OPC / 50% GGBS (ground granulated blast-furnace slag)
Characteristic cube strength (28 days): 34 MPa
Maximum free water/binder ratio: 0.48
Slump class: S3 (100-150 mm)
Fresh density: 2380 kg/m3
Supply price (Klang Valley, ex-plant): RM 318 per m3

28-day strength verified by accredited laboratory cube tests (report LRM-QC-2026-118).

Up to 43% lower embodied carbon than a conventional OPC C30 mix (see EPD on page 2).

FICTITIOUS TEST DATA

Environmental Product Declaration - Summary

EPD registration no.: EPD-MY-GGBS-0421

Programme operator: Malaysia Green Building EPD Programme (fictitious)

Standards: ISO 14025 and EN 15804+A2

Verification: Independent third-party verified

Declared unit: 1 m3 of ready-mixed concrete

GWP-total (A1-A3): 182 kgCO2e per m3

Valid until: 2029-03-31

FICTITIOUS TEST DATA