

Manufacturing Process Analysis Report

Process Summary


Total LOTs: 5,000

Defect LOTs: 679


Defect Rate: 13.58%

Average Yield: 85.11%


Yield Trend



Defect Pareto Analysis



Machine Defect Rate Comparison



Quality Parameter Summary

Parameter	count	mean	std	min	25%	50%	75%	max
CZ_Roughness	5000.0	349.941	6.775	321.32	345.29	349.885	354.512	375.94
Total_Thickness	5000.0	32.001	0.368	30.57	31.752	32.004	32.248	33.281
Peel_Strength	5000.0	499.781	20.004	421.68	486.328	499.73	513.32	572.46
ABF_Roughness	5000.0	349.817	6.701	326.59	345.29	349.66	354.26	375.01
Yield	5000.0	85.105	33.746	0.0	97.72	98.34	98.85	100.0