



TISCHLER UND SOHN

Tischler und Sohn (U.S.A.) Limited

Six Suburban Avenue
Stamford, CT 06901 USA


Tel.: (203) 674-0600

Fax: (203) 674-0601

e-mail: info@tischlerwindows.com
Website: www.tischlerwindows.com

Tischler Glass Type #12

Sound Reduction 30/39, Low-E



Glazing From External To Internal:

Pane 1

- ① 10 mm (3/8") Clear Annealed or Tempered Glass

Spacer

- ② 16 mm (5/8") Air Space, 90% Argon Filled

Pane 2

- ③ 4 mm (3/16") Clear Annealed or Tempered Glass with Low-E Coating

Results:

Visible Light (NFRC 100-2010)

Daylight Transmittance

$T_V = 79\%$

Thermal Properties (NFRC 100-2010)

U-Value

= 0.25

R-value

= 4.05

Solar Energy (NFRC 100-2010)

Shading Coefficient [g/0.87]

= 0.67

SHGC

= 0.59

Sound Reduction

STC

= 39