



TISCHLER UND SOHN

Tischler und Sohn (U.S.A.) Limited

Six Suburban Avenue
Stamford, CT 06901 USA


Tel.: (203) 674-0600

Fax: (203) 674-0601

e-mail: info@tischlerwindows.com
Website: www.tischlerwindows.com

Tischler Glass Type #17

Solar Control SGG XTREME 70_33 II



Glazing From External To Internal:

Pane 1

- ① 6 mm (1/4") Clear Heat Strengthened Glass with Solar Control Coating
SGG XTREME 70_33 II

Spacer

- ② 16 mm (5/8") Air Space, 90% Argon Filled

Pane 2

- ③ 6 mm (1/4") Clear Annealed or Tempered Glass

Results:

Visible Light (NFRC 100-2010)

Daylight Transmittance $T_V = 70\%$

Thermal Properties (NFRC 100-2010)

U-Value = 0.25

R-value = 4.05

Solar Energy (NFRC 100-2010)

Shading Coefficient [g/0.87] = 0.34

SHGC = 0.29

Sound Reduction

STC = 33