



TISCHLER UND SOHN

Tischler und Sohn (U.S.A.) Limited

Six Suburban Avenue
Stamford, CT 06901 USA

Tel.: (203) 674-0600


Fax: (203) 674-0601

e-mail: info@tischlerwindows.com

Website: www.tischlerwindows.com

Tischler Glass Type #3

Standard Insulated Low-E / Low Iron



Glazing From External To Internal:

Pane 1

- ① 6 mm (1/4") Low Iron Annealed or Tempered Glass

Spacer

- ② 16 mm (5/8") Air space, 90% Argon Filled

Pane 2

- ③ 6 mm (1/4") Low Iron Annealed or Tempered Glass with Low-E Coating

Results:

Visible Light (NFRC 100-2010)

Daylight Transmittance

$T_V = 82\%$

Thermal Properties (NFRC 100-2010)

U-Value

= 0.25

R-value

= 4.05

Solar Energy (NFRC 100-2010)

Shading Coefficient [g/0.87]

= 0.72

SHGC

= 0.63

Sound Reduction

STC

= 33