



TISCHLER UND SOHN

Tischler und Sohn (U.S.A.) Limited

Six Suburban Avenue
Stamford, CT 06901 USA

Tel.: (203) 674-0600


Fax: (203) 674-0601

e-mail: info@tischlerwindows.com

Website: www.tischlerwindows.com

Tischler Glass Type #4

Laminated Both Sides, Low-E



Glazing From External To Internal:

Pane 1

- ① 3 mm (1/8") Clear Annealed
- 0.38 mm (0.015") PVB Interlayer
- 3 mm (1/8") Clear Annealed

Spacer

- ② 16 mm (5/8") Air space, 90% Argon Filled

Pane 2

- ③ 3 mm (1/8") Clear Annealed Glass with Low-E Coating
- 0.38 mm (0.015") PVB Interlayer
- 3 mm (1/8") Clear Annealed Glass

Results:

Visible Light (NFRC 100-2010)

Daylight Transmittance $T_v = 80\%$

Thermal Properties (NFRC 100-2010)

U-Value = 0.25

R-value = 4.05

Solar Energy (NFRC 100-2010)

Shading Coefficient [g/0.87] = 0.69

SHGC = 0.59

Sound Reduction

STC = 38