# METALOR®

# Au Ag

## Data Sheet

| | | | |
|---|---|---|---|
| **Alloy code:** | 10245 | **Colour:** | Red 5N |
| **General Description:** | Red gold alloy for all kinds of jewellery production; gold shade 5N according to DIN 8238. | | |

**Other properties:**



| | | |
|---|---|---|
| **Density - g/cm³:** | 15,10 | |
| **Melting range:** | 880 - 900 °C | |
| **Composition:** | AU:75,00% AG:5,00% CU:19,50% | |
| **Pickling:** | Hot 10% sulphuric acid | |
| **Hardness - HV5:** | 150 | *Annealed* |

**Casting data:**




| | | |
|---|---|---|
| **Flask Temp.** | ≈ 600 °C | |
| **Casting Temp.** | 1000 - 1100 °C | |
| **Cooling:** | Air cooling | |
| **Hardness - HV5:** | 150 | *Post cast* |

**Recommended Solder:**



| Description: | Melting range: | Material code |
|---|---|---|
| 18 Red Gold Solder HARD | 750°C-810°C | 300002525 |

**Available profiles:**


Casting Pieces


Sheet


Square Wire


Round Wire

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com