# 375 S3 Gold

Colour: white Density: 12,3 g/cm$^3$ Melting Range: 850 ... 915°C

## Chemical Composition

| Element | Au | Ag | Pd | Cu | Zn | | | | |
|---|---|---|---|---|---|---|---|---|---|
| Amount [‰] | 375 | 550 | 15 | x | x | | | | |

## Mechanical Properties

| | casted, not deformed | **annealed, recrystallisated** | hardened, 300°C 60 min |
|---|---|---|---|
| Hardness [HV] | | **105** | |
| Tensile Strength $R_m$ [N/mm$^2$] | | **410** | |
| Yield Strength $R_{p\,0,2}$ [N/mm$^2$] | | **225** | |
| Fracture Elongation [%] | | **≥ 30** | |

## Annealing Properties

| Furnace | Temperature | Annealing Time | Holding Time | Quenching Medium | Atmosphere |
|---|---|---|---|---|---|
| Continous Furnace, Batch Furnace | 700 °C | 15 min | | | $H_2/N_2$-Mixture, 4 ...80 % $H_2$ |

## Hardness Modification by Cold Deformation

