585/40 Red Gold

Colour: red Density: 13.1 g/cm^3 Melting Range: 900 - 920°C

Composition

Element	Au	Ag	Cu						
Amount [‰]	585	40	375						

Mechanical properties

	cast, unformed	**annealed, recrystallized**	cured, 300°C 60 min
Hardness [HV]	130	**130**	***
Tensile strength R_m [N/mm^2]		**510**	
Yield strength $R_{p\,0.2}$ [N/mm^2]		**350**	
Elongation at break [%]		**40**	

Annealing Conditions

Furnace	Temperature	Annealing Time	Holding Time	Quenching Medium	Atmosphere
Continous Furnace, Batch Furnace	650 °C	15 min			H_2/N_2mixture, 4 ... 80% H_2

Change in hardness due to cold deformation

