# METALOR®

# Au Ag

## Data Sheet

| | | | |
|---|---|---|---|
| **Alloy code:** | 424 | **Colour:** | Red |
| **General Description:** | 9ct red gold alloy, for universal use. It can easily be cupped, stamped, rolled, polished, drawn and machined. | | |

**Other properties:**



| | | |
|---|---|---|
| **Density - g/cm³:** | 11,30 | |
| **Melting range:** | 940 - 975 °C | |
| **Composition:** | AU:37,50% AG:3,60% | |
| **Pickling:** | Hot 10% sulphuric acid | |
| **Hardness - HV5:** | 100 | *Annealed* |

**Casting data:**



| | | |
|---|---|---|
| **Flask Temp.** | ≈ 600 °C | |
| **Casting Temp.** | 1040 - 1075 °C | |
| **Cooling:** | Air cooling | |
| **Hardness - HV5:** | 100 | *Post cast* |

**Recommended Solder:**



| Description: | Melting range: | Material code |
|---|---|---|
| 9 Red Gold Solder MEDIUM | 685°C-790°C | 300022410 |

**Available profiles:**



Sheet



Square Wire



Round Wire

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com