METALOR®

Au Ag

Data Sheet

Alloy code:	425	**Colour:**	White
General Description:	9ct standard white gold alloy, for universal use. It can easily be cupped, stamped, rolled, polished, drawn and machined.		

Other properties:



Density - g/cm³:	12,60	
Melting range:	915 - 965 °C	
Composition:	AU:37,60% AG: 57,60%	
Pickling:	Hot 10% sulphuric acid	
Hardness - HV5:	80	*Annealed*

Casting data:



Flask Temp.	na
Casting Temp.	na
Cooling:	na
Hardness - HV5:	na

Recommended Solder:



Description:	Melting range:	Material code
9 White Gold Solder MEDIUM	735°C-755°C	300018233

Available profiles:



Sheet



Round Wire



D-Shape Wire

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com