METALOR®

Au Ag

Data Sheet

Alloy code:	10036	Colour:	Yellow
General Description:	9ct standard yellow gold alloy, for universal use. It can easily be cupped, stamped, rolled, polished, drawn and machined. Suitable for casting in air.		

Other properties:



Density - g/cm³:	11,15	
Melting range:	850 - 910 °C	
Composition:	AU:37,60% AG: 10,30%	
Pickling:	Hot 10% sulphuric acid	
Hardness - HV5:	130	*Annealed*

Casting data:



Flask Temp.	≈ 600 °C	
Casting Temp.	950 - 1010 °C	
Cooling:	Air cooling	
Hardness - HV5:	130	*Post cast*

Recommended Solder:



Description:	Melting range:	Material code
9 Yellow Gold Solder EXTRA EASY	620°C-690°C	300018229
9 Yellow Gold Solder EASY	650°C-720°C	300018230
9 Yellow Gold Solder MEDIUM	735°C-755°C	300018231
9 Yellow Gold Solder HARD	755°C-795°C	300018232

Available profiles:



Grain

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com