METALOR®

Pt Co

Data Sheet

Alloy code:	10242	Colour:	White
General Description:	950 ‰ Platinum alloy. It can be cupped, stamped, rolled, polished, and drawn. Recommended for machining hard metal. Suitable for casting.		

Other properties:



Density - g/cm³:	20,80	
Melting range:	1750 - 1765 °C	
Composition:	Pt:95,00% - Co:5,00%	*Co= Cobalt*
Pickling:	Hot 10% sulphuric acid	
Hardness - HV5:	135	*Annealed*

Casting data:




Flask Temp.	≈ 1000 °C	
Casting Temp.	1950 - 2150 °C	
Cooling:	Air cooling	
Hardness - HV5:	190	*Post cast*

Recommended Solder:



Description:	Melting range:	Material code
Platinum Solder EXTRA EASY	935°C-955°C	300018200
Platinum Solder EASY	1010°C-1029°C	300018201
Platinum Solder MEDIUM	1179°C-1217°C	300018202
Platinum Solder HARD	1422°C-1445°C	300018203
Platinum Solder EXTRA HARD	1700°C	300018214

Available profiles:



Casting Pieces



Square Wire



Round Wire

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com