METALOR®

Au Ag

Data Sheet

Alloy code:	10074	**Colour:**	Yellow
General Description:	14ct gold alloy with grain refiner for casting under protective atmosphere.		

Other properties:



Density - g/cm³:	13,65	
Melting range:	825 - 835 °C	
Composition:	AU:58,50% AG: 20,50%	
Pickling:	Hot 10% sulphuric acid	
Hardness - HV5:	185	*Annealed*

Casting data:



Flask Temp.	≈ 600 °C	
Casting Temp.	950 - 1050 °C	
Cooling:	Air cooling	
Hardness - HV5:	185	*Post cast*


Recommended Solder:



Description:	Melting range:	Material code
14 Yellow Gold Solder EASY	710°C-730°C	300018228

We would advise our 18ct yellow solder range for other requirements.

Available profiles:



Casting Pieces

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com