METALOR®

Au Pd

Data Sheet

Alloy code:	3165	Colour:	White
General Description:	18ct white gold nickel-free alloy containing Pd, for universal use. It can easily be cupped, stamped, rolled, drawn, polished and machined. Alloy for casting under protective atmosphere.		

Other properties:



Density - g/cm³:	15.80	
Melting range:	1035 - 1115 °C	
Composition:	AU: 75,00% PD: 13,00%	
Pickling:	Hot 10% sulphuric acid	
Hardness - HV5:	155	*Annealed*

Casting data:




Flask Temp.	≈ 650 °C	
Casting Temp.	1175 - 1225 °C	
Cooling:	Quench in water	
Hardness - HV5:	155	*Post cast*

Recommended Solder:



Description:	Melting range:	Material code
18 White Gold Solder EASY	690°C-710°C	300018224
18 White Gold Solder MEDIUM	705°C-720°C	300018225
18 White Gold Solder HARD	855°C-875°C	300018226

Available profiles:



Casting Pieces

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com