METALOR®

Au Ag

Data Sheet

Alloy code:	10249	Colour:	Yellow 2N
General Description:	18 ct pale-yellow gold alloy (2N). It can easily be cupped, stamped, rolled, drawn and machined. Recommended for casting under protective atmosphere.		

Other properties:



Density - g/cm³:	15,50	
Melting range:	880 - 895 °C	
Composition:	AU:75,00% AG: 15,70%	
Pickling:	Hot 10% sulphuric acid	
Hardness - HV5:	130	*Annealed*

Casting data:




Flask Temp.	≈ 600 °C	
Casting Temp.	995 - 1045 °C	
Cooling:	Quench in water	
Hardness - HV5:	130	*Post cast*

Recommended Solder:



Description:	Melting range:	Material code
18 Yellow gold Solder EASY	700°C-715°C	300018221
18 Yellow gold Solder MEDIUM	730°C-765°C	300018222
18 Yellow gold Solder HARD	790°C-830°C	300018223

Available profiles:



Casting Pieces

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com