Allgemeine	Quality Datasheet	Serial number: PH-DF 3023 /0 Page 1 Of 1

375/27 Red Gold

Color: red Density: 11.0 g/cm^3 Melting Range: 960 ... 990°C

Composition

Element	Au	Ag	Cu	Zn					
Share [‰]	375	27	x	x					

Mechanical properties

	cast, unformed	**annealed, recrystallized**	cured, 300°C 60 min
Hardness [HV]		**100**	
Tensile strength R_m [N/mm^2]			
Yield strength $R_{p\ 0.2}$ [N/mm^2]			
Fracture Elongation [%]			

Annealing Conditions

Furnace	Temperature	Annealing Time	Holding Time	Quenching Medium	Atmosphere
Continous Furnace, Batch Furnace	640 °C	15 min	2 min	And	H_2/N_2mixture, 4 ... 80% H_2

Change in hardness due to cold deformation (orientation values)

